HIGH TEMPERATURE LATTICE PARAMETERS OF ZnSiP₂, ZnGeP₂ AND CdGeP₂

A. J. Miller, R. Humphreys, B. Chapman

► To cite this version:

A. J. Miller, R. Humphreys, B. Chapman. HIGH TEMPERATURE LATTICE PARAMETERS OF ZnSiP₂, ZnGeP₂ AND CdGeP₂. Journal de Physique Colloques, 1975, 36 (C3), pp.C3-31-C3-34. 10.1051/jphyscol:1975306 . jpa-00216276

HAL Id: jpa-00216276

<https://hal.science/jpa-00216276>

Submitted on 1 Jan 1975

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

HIGH TEMPERATURE LATTICE PARAMETERS OF ZnSiP_2 , ZnGeP_2 AND CdGeP_2

A. MILLER (*), R. G. HUMPHREYS and B. CHAPMAN

School of Physics, University of Bath, U. K.

Résumé. — Nous avons étudié la variation des paramètres cristallins des semiconducteurs à structure chalcopirite, ZnSiP_2 , ZnGeP_2 et CdGeP_2 entre la température ambiante et 1 100 °C en utilisant un appareil de diffraction X à haute température. Pour les trois composés, la compression tétragonale croît avec la température. Nous avons interprété ces résultats en termes de dilatation des liaisons II-V et IV-V.

Abstract. — The variation of the lattice parameters from room temperature to 1.100 °C have been studied for the chalcopirite semiconductors, ZnSiP_2 , ZnGeP_2 and CdGeP_2 using a high temperature X-ray camera. All three compounds show an increase in the tetragonal compression with temperature. The results are interpreted in terms of the thermal expansions of the II-V and IV-V bonds.

1. Introduction. — The variation of the lattice parameters of three $A^{II}B^{IV}C_2^V$ chalcopirite compounds, ZnSiP_2 , ZnGeP_2 and CdGeP_2 have been measured by the high temperature X-ray technique. The range covered was from room temperature to the decomposition temperature for each material. There were three reasons for carrying out this study.

Firstly, as some of these materials are potentially useful for use in heterojunctions with binary semiconductors, the lattice parameters at the temperature of growth should be known for liquid or vapour epitaxy [1]. Secondly, some of the compounds have been reported to have high temperature structural modifications which have not been identified directly. In particular, differential thermal analysis indicates a phase transition at 950 °C in ZnGeP_2 , but the high temperature structure has not been retained by quenching to room temperature [2, 3, 4]. Finally, it is interesting to observe how the tetragonal compression, or c/a ratio varies with temperature and to consider this in terms of the two types of bond of the chalcopirite structure.

Some work has previously been carried out on thermal expansions of these compounds. CdGeAs_2 has been studied by X-ray [5] and optomechanical [6] techniques. There is also a Russian report of high temperature X-ray measurements of several II-IV-V₂ compounds including the three compounds of type ZnSnC_2 which have zero tetragonal compression at room temperature [7].

2. Experimental. — Single crystals were grown from molten metal solution; ZnSiP_2 in zinc [8] and ZnGeP_2 and CdGeP_2 in lead [9]. Powdered samples were sealed in 0.3 mm diameter silica tubes and mounted on a 19 cm Unicam S150 high temperature camera with Van Arkel film configuration. The camera was previously calibrated using alumina (Al_2O_3). Heating was by radiation from electrical elements surrounding the sample in an evacuated cavity. A least squares fit of the data to a correction function took account of absorption and eccentricity errors by extrapolating the results to 180° scattering.

3. Results and discussion. — Figure 1 shows the results obtained for the variations of a , c , c/a and the volume V with temperature for the three compounds. The first point to note is that ZnGeP_2 remained in the chalcopirite structure until it decomposed above 1.020 °C. The melting point of ZnGeP_2 is 1.025 °C [2], so that no high temperature zinc blende phase appears to exist for this material, contrary to expectation from differential thermal analysis data. The results for ZnSiP_2 (m. p. 1.370 °C) [10] were limited to below 1.100 °C, due to softening of the silica container. The highest temperature obtained for CdGeP_2 (m. p. 800 °C) [10] was 755 °C after which it decomposed. Again, no high temperature phases were observed up to these temperatures.

TABLE I

Room temperature lattice parameters

ZnSiP_2	(Zn solution)		
a	$= 5.399$	c	$= 10.438$
		c/a	$= 1.933$
ZnGeP_2	(Pb solution)		
a	$= 5.464$	c	$= 10.708$
		c/a	$= 1.960$
CdGeP_2	(Pb solution)		
a	$= 5.741$	c	$= 10.770$
		c/a	$= 1.876$

(*) Present address : Department of Physics, Heriot-Watt University, Edinburgh, U. K.

FIG. 1. — Lattice parameters of ZnSiP_2 , ZnGeP_2 and CdGeP_2 between 0° and $1,000^\circ\text{C}$.

The second point of interest is the result that the c/a axial ratios are seen to decrease with increasing temperature. This is away from the *ideal* value of 2. This seems surprising at first sight because one would normally expect a move towards the more symmetrical pseudocubic position with $c/a = 2$ at higher temperature. It is also evident from these three compounds that the rate of change of distortion increases with tetragonal compression as pointed out by Weaire *et al.* [11]. This also applies to the CdGeAs_2 results [5, 6] and for the results of the three zinc-tin compounds containing phosphorus, arsenic and antimony which have zero tetragonal compression at room temperature since no shift from $c/a = 2$ was observed on heating to 600°C [7].

Our results showed linear increases of lattice parameters with temperature within experimental error. In table II, we quote the thermal expansion coefficients given by the best straight line fits to the data. These are thus average coefficients for the temperature ranges covered and are normalised by dividing by the room temperature values.

We note that although the coefficients for a , c and c/a vary significantly for the materials studied, they have very similar volume coefficients. The values for

GaP [12], the isoelectronic analogue of ZnGeP_2 are listed for comparison and are seen to be significantly smaller. The free x -parameter of the chalcopyrite structure complicates direct comparison, but this may be due to a larger average ionicity of the ternary compounds. This will be considered later.

We have attempted to interpret the increase in tetragonal compression with temperature in terms of the thermal expansions of the individual II-V and IV-V bonds, by applying the Abrahams and Bernstein relations [13] to our results. Work by these investigators produced the presently accepted picture of the $A^{II}B^{IV}C_2^V$ compounds as consisting of an almost perfect BC_4 tetrahedral arrangement with tetrahedral angles within 1 % of the ideal value of 109.47° . The IV-V bonds thus show strong directional covalent character while the distortion is taken up in the position of the group II cations. The net result is a relative displacement of the anions (P) towards the two nearest neighbour group IV cations, figure 2. This shift determines the x -parameter of the chalcopyrite structure. Assuming a perfect tetrahedron, the x parameter and the bond lengths can be expressed in terms of the lattice parameters, a and c ,

$$x = 0.5 - \left[\frac{c^2}{32a^2} - \frac{1}{16} \right]^{1/2} \quad (1)$$

$$A - C = \left[a^2 x^2 + \frac{4a^2 + c^2}{64} \right]^{1/2} \quad (2)$$

$$B - C = \left[a^2 \left(\frac{1}{2} - x \right)^2 + \frac{4a^2 + c^2}{64} \right]^{1/2} \quad (3)$$

$$c = \frac{8}{\sqrt{3}} (B - C). \quad (4)$$

Lind and Grant [14] showed that, except for the compounds of type ZnSnC_2 , $A^{II}B^{IV}C_2^V$ compounds fell close to the line defined by eq. (4). Figure 3 shows the calculated x parameters for the present results and also the previously measured room temperature values [13, 14, 15]. The x parameters all increase with temperature as expected for increasing distortion from the cubic value of 0.25, so the phosphorus atoms move relative

TABLE II

Average thermal expansion coefficients

	$\frac{1}{a} \frac{da}{dT}$	$\frac{1}{c} \frac{dc}{dT}$	$\frac{1}{c/a} \frac{d(c/a)}{dT}$	$\frac{1}{V} \frac{dV}{dT}$
ZnSiP_2	7.9×10^{-6}	3.2×10^{-6}	-4.8×10^{-6}	1.9×10^{-5}
ZnGeP_2	7.8×10^{-6}	5.0×10^{-6}	-2.9×10^{-6}	2.0×10^{-5}
CdGeP_2	8.9×10^{-6}	3.7×10^{-7}	-9.3×10^{-6}	1.8×10^{-5}
GaP	4.65×10^{-6}			1.40×10^{-5}

Thermal expansion coefficients are defined by, $\alpha = \frac{1}{\xi_0} \cdot \frac{d\xi}{dT}$ where ξ_0 is the room temperature value.

FIG. 2. — Chalcopyrite structure.

FIG. 3. — Calculated x parameters.

vely closer to the group IV atoms. The thermal expansions of the bonds given by eq. (2) and (3) are shown in figure 4 and indicate the reason for the increase in tetragonal distortion with temperature. The more ionic II-V bonds have higher thermal expansion coefficients than the covalent IV-V bonds, so that, the group V atoms move relatively nearer the group IV cations on heating, thus increasing the distortion through eq. (1). The calculated thermal expansions are listed in table III along with existing values for other materials [12, 16, 17]. Unfortunately data do not exist for all of the binary analogues of these compounds. Covalent silicon and germanium have small expansion coefficients. The value for the slightly ionic gallium phosphide is larger. These may be compared with the Si-P and Ge-P coefficients although the value obtained

FIG. 4. — Calculated thermal expansions of the $A-C$ and $B-C$ bonds.

TABLE III
Calculated bond expansion coefficients

	$\frac{1}{x} \frac{dx}{dT}$	$\frac{1}{A-C} \frac{d(A-C)}{dT}$	$\frac{1}{B-C} \frac{d(B-C)}{dT}$
ZnSiP ₂	9.2×10^{-6}	9.8×10^{-6}	2.8×10^{-6}
ZnGeP ₂	5.8×10^{-6}	9.1×10^{-6}	5.0×10^{-6}
CdGeP ₂	1.7×10^{-5}	1.5×10^{-5}	6.4×10^{-7}
Si		2.95×10^{-6}	
Ge		3.01×10^{-6}	
GaP		4.65×10^{-6}	
ZnSe		8.01×10^{-6}	

from this model for CdGeP_2 looks anomalously low. The Zn-P and Cd-P coefficients resemble the more ionic ZnSe value.

To conclude, no high temperature structural modification has been found for ZnGeP_2 and the observed increase in tetragonal distortions of ZnSiP_2 , ZnGeP_2 and CdGeP_2 with temperature can be interpreted in

terms of the larger thermal expansion coefficients of the more ionic II-V bonds. Bulk expansion coefficients are larger than group IV and III-V analogues.

Acknowledgments. — The Science Research Council and Honeywell Inc. are acknowledged for financial assistance.

References

- [1] SHAY, J. L., BACHMANN, K., BUEHLER, E., WERNICK, J. H., *Appl. Phys. Lett.* **5** (1973) 226.
- [2] BUEHLER, E., WERNICK, J. H., WILEY, J. D., *J. Electron. Mater.* **2** (1973) 445.
- [3] MASUMOTO, K., ISOMURA, S., GOTO, W., *J. Phys. Chem. Solids* **27** (1966) 1939.
- [4] RAY, B., PAYNE, A. J., BURRELL, G. J., *Phys. Stat. Sol.* **35** (1969) 197.
- [5] CERVINKA, L., KASPER, J., *Czech. J. Phys.* **B 20** (1970) 101.
- [6] KILDAL, H., Technical report AFML-TR-72-277 Wright Patterson Air Force Base, Ohio, U. S. A. (1972).
- [7] KOZHINA, I. I., BORSHCHEVSKII, A. S., *Vestnik Leningrad Skogo Universiteta Fizika and Khimi* **4** (1971) 87.
- [8] HUMPHREYS, R. G., M. Sc. Thesis, Bath University (1973).
- [9] MILLER, A., HOLAH, G. D., CLARK, W. C., *J. Phys. Chem. Solids* **35** (1974) 685.
- [10] SHAY, J. L., WERNICK, J. H., *Ternary Chalcopyrite Semiconductors. Growth, electronic properties and applications* (Pergamon, N. Y.) 1975.
- [11] WEAIRE, D. L., NOOLANDI, J., *J. Physique Colloq.* **36** (1975) C 3-27.
- [12] SLACK, G. A., BARTRAM, S. F., *J. Appl. Phys.* **46** (1975) 89.
- [13] ABRAHAMS, S. C., BERNSTEIN, J. L., *J. Chem. Phys.* **52** (1970) 5607 and *J. Chem. Phys.* **55** (1971) 796.
- [14] LIND, M. D., GRANT, R. W., *J. Chem. Phys.* **58** (1973) 357.
- [15] GRIGOROVICI, R., MĂNĂILĂ, R., *Acta. Crystallogr.* **B 24** (1968) 535.
- [16] NOVIKOVA, S. I., *Semiconductors and Semimetals* (Ed. : Willardson & Beer, Acad. Press) 1966, Vol. 2, p. 33.
- [17] PEARSON, W. B., *Handbook of lattice spacings and structures of metals and alloys* (Pergamon, Oxford) 1967 Vol. 2.