



Heat capacity of rare earth metals near the melting point and the vacancy mechanism of melting

T. Górecki

► To cite this version:

T. Górecki. Heat capacity of rare earth metals near the melting point and the vacancy mechanism of melting. Journal de Physique Colloques, 1979, 40 (C5), pp.C5-63-C5-64. 10.1051/jphyscol:1979525 . jpa-00218942

HAL Id: jpa-00218942

<https://hal.science/jpa-00218942>

Submitted on 4 Feb 2008

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Heat capacity of rare earth metals near the melting point and the vacancy mechanism of melting

T. Górecki (*)

Max-Planck-Institut für Metallforschung, Institut für Werkstoffwissenschaften,
7000 Stuttgart-1, Seestraße 92, F.R.G.

Résumé. — On utilise le modèle lacunaire de fusion des métaux pour calculer la valeur du changement de chaleur spécifique $\Delta C_p = C_{pl} - C_{ps}$ provoqué par la fusion. On constate que pour tous les métaux la valeur de ΔC_p est égale à $3,50 \text{ J g.atom}^{-1} \text{ K}^{-1}$. Le résultat obtenu est en bon accord avec les valeurs mesurées par d'autres auteurs sur les métaux des terres rares (Y, La, Ce, Pr, Nd, Sm, Dy, Tm).

Abstract. — The vacancy mechanism of the melting process is utilized as a starting point for deriving the formula for the difference of the heat capacity of the liquid and solid metal in the neighbourhood of the melting point. From these calculations it follows that the difference $C_{pl} - C_{ps}$ is the same for all the metals and equals $3.50 \text{ J g.atom}^{-1} \text{ K}^{-1}$. This result is compared with the existing in the literature experimental data for 8 REM (Y, La, Ce, Pr, Nd, Sm, Dy, Tm) and the agreement is found to be very good.

In a series of papers [1-4] the existence of correlations between the changes of various physical properties of metals at the melting point and changes of the same properties of metals due to the creation of vacancies has been demonstrated. On the basis of these correlations a vacancy mechanism of the melting process of metals has been proposed, according to which :

— Melting starts when the vacancy concentration in solid metal reaches a critical value of the order of 10^{-3} , and

— The melting process is a process of creation of additional vacancies at the cost of the heat of melting. The vacancy concentration increase during the melting of metals is approximately equal to $\Delta c \approx 0.1$.

The present paper is an attempt to derive a formula for the difference of the atomic heat capacity of solid and liquid metals at the melting point. The basis for this calculation is the proposed vacancy mechanism of the melting process. The comparison of the results obtained in this way with the existing experimental data may serve as an important test for the correctness of the proposed vacancy mechanism of melting of metals.

It is well known [5] that vacancies contribute significantly to the specific heat. The increase in atomic specific heat caused by vacancy formation is especially pronounced near the melting point and can be represented by the formula :

$$C_{vac} = AN_A \exp(-E_f/kT) E_f^2/kT^2 \quad (1)$$

(*) Research fellow of the Alexander von Humboldt Foundation.
On leave from Physics Laboratory, Higher School of Engineering,
Opole, Poland.

where N_A is the Avogadro's number, E_f -vacancy formation energy, k -Boltzmann constant and A -constant (entropy factor).

According to the second postulate of the proposed vacancy mechanism of the melting process, the changes of all the physical properties of metals during the melting process are governed by the change of the vacancy concentration taking place during melting [1-4, 6]. Assuming that the vacancy formation entropy does not change significantly during the melting one obtains the following expression for the change of the atomic heat capacity of metals at the melting point

$$C_{pl} - C_{ps} = A \frac{N_A}{k} \left[\frac{E_{f1}^2}{T_m^2} \exp(-E_{f1}/kT_m) - \frac{E_{fs}^2}{T_m^2} \exp(-E_{fs}/kT_m) \right] \quad (2)$$

where T_m is the melting temperature. Subscripts 1 and s denote the liquid and solid state of metal, respectively.

As it has previously been shown [1], the ratio E_{fs}/T_m is for all the metals the same and equals $1 \text{ eV}/1200 \text{ K}$. It is also known that the value of the vacancy formation energy in the liquid state, E_{f1} , is equal to $0.9 E_{fs}$ [6]. Therefore, taking into consideration the fact that the entropy factor A has for all the metals the same value of 60.34 [1], one finally obtains

$$C_{pl} - C_{ps} = 3.50 \text{ J g.atom}^{-1} \text{ K}^{-1} \quad (3)$$

It can also be stated that for all the metals the change of the atomic specific heat at the melting

point has the same value. In table I the data available in the literature on the atomic specific heat for both the solid and liquid states of 8 rare earth metals for the temperature range close to the melting point are collected and the values of the difference $C_{pl} - C_{ps}$ are calculated. It has been found, that the mean value of the difference $C_{pl} - C_{ps}$ equals $3.49 \text{ J g.atom}^{-1} \text{ K}^{-1}$ and the standard deviation does not exceed $0.72 \text{ J g.atom}^{-1} \text{ K}^{-1}$ (21%). Taking into account the difficulties encountered in the measurements of the heat capacity of metals in the high-temperature range, it is fair to say that the agreement between the theory and experiment is very good. This agreement corroborates the correctness of the proposed vacancy mechanism of melting of metals.

Table I. — *Experimental values of the atomic heat capacity of liquid, C_{pl} , and solid, C_{ps} , REM at the melting point. All the values are given in*

$\text{J g.atom}^{-1} \text{ K}^{-1}$ units.

Metal	C_{pl}	C_{ps}	$C_{pl} - C_{ps}$
Y	39.79 [11]	35.02 [11]	4.77
La	44.35 [7]	40.38 [7]	3.97
Ce	40.38 [8]	37.87 [8]	2.51
Pr	41.71 [12]	38.45 [9]	3.26
Nd	47.32 [10]	44.56 [10]	2.76
Sm	50.21 [8]	46.94 [11]	3.27
Dy	46.02 [8]	42.55 [8]	3.47
Tm	41.38 [11, 13]	37.49 [11, 13]	3.89

References

- [1] GÓRECKI, T., *Z. Metallkde* **65** (1974) 426.
- [2] GÓRECKI, T., *Z. Metallkde* **67** (1976) 269.
- [3] GÓRECKI, T., *Z. Metallkde* **68** (1977) 231.
- [4] GÓRECKI, T., *Scr. Metall.* **11** (1977) 1051.
- [5] CEZAIRLIYAN, A., MORSE, M. S., BERMAN, A. H. and BECKETT, C. W., *J. Res. NBS* **74A** (1970) 65.
- [6] GÓRECKI, T., *Z. Metallkde* (in press).
- [7] MARDYKIN, I. P., KASHIN, V. I. and SBITNIEV, P. P., *Izv. AN SSSR, Metally* No 6 (1973) 77.
- [8] NOVIKOV, I. I. and MARDYKIN, I. P., *Teplofizika Vysokikh Temperatur* **11** (1973) 527.
- [9] MARDYKIN, I. P. and KASHIN, V. I., *Izv. AN SSSR, Metally* No 4 (1973) 77.
- [10] MARDYKIN, I. P., KASHIN, V. I. and WERTMAN, A. A., *Izv. AN SSSR, Metally* No 6 (1972) 96.
- [11] HULTGREN, R., DESAI, P. D., HAWKINS, D. D., GLEISER, M., KELLEY, K. K. and WAGMAN, D. D., *Selected Values of Thermodynamic Properties of the Elements* (ASM, Metals Park, Ohio) 1973.
- [12] DENNISON, D. H., GSCHNEIDNER, K. A. and DAANE, A. H., *J. Chem. Phys.* **44** (1966) 4273.
- [13] STRETTZ, L. A. and BAUTISTA, R. G., *J. Chem. Eng. Data* **21** (1976) 13.