THE COMPLEMENTARY USE OF ATOM PROBE FIELD ION MICROSCOPY AND ANALYTICAL TRANSMISSION ELECTRON MICROSCOPY FOR THE STUDY OF A Ni-BASE SUPERALLOY

A. Melmed, M. Twigg, R. Klein, M. Kaufman, H. Fraser

► To cite this version:

A. Melmed, M. Twigg, R. Klein, M. Kaufman, H. Fraser. THE COMPLEMENTARY USE OF ATOM PROBE FIELD ION MICROSCOPY AND ANALYTICAL TRANSMISSION ELECTRON MICROSCOPY FOR THE STUDY OF A Ni-BASE SUPERALLOY. Journal de Physique Colloques, 1984, 45 (C9), pp.C9-373-C9-378. 10.1051/jphyscol:1984962 . jpa-00224449

HAL Id: jpa-00224449

<https://hal.science/jpa-00224449>

Submitted on 1 Jan 1984

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

THE COMPLEMENTARY USE OF ATOM PROBE FIELD ION MICROSCOPY AND ANALYTICAL TRANSMISSION ELECTRON MICROSCOPY FOR THE STUDY OF A Ni-BASE SUPERALLOY

A.J. Melmed, M.E. Twigg, R. Klein, M.J. Kaufman* and H.L. Fraser*

National Bureau of Standards, Gaithersburg, MD 20899, U.S.A.

Résumé : Les compositions des phases γ, γ' et DO_{22} dans le superalliage à base Nickel RSR 143 (76Ni-13Al-9Mo-2Ta, % at.) ont été déterminées via la microscopie ionique à sonde à atomes (APFIM) comme étant 76Ni-6Al-18Mo, 67Ni-25Al-4Mo-4Ta et 73Ni-4Al-20Mo-3Ta respectivement. En utilisant la spectroscopie d'énergie dispersive x en microscopie électronique (TEM), la composition de la phase γ' (69Ni-22Al-4Mo-5Ta) s'est avérée similaire à celle déterminée par APFIM. L'écart de la composition DO_{22} par rapport à Ni_3Mo est en accord avec les prévisions tirées d'une récente étude en TEM (Martin et al, 1980, 1982).

Abstract: Compositions of the γ, γ' and DO_{22} phases in the nickel-base superalloy RSR 143 (76Ni-13Al-9Mo-2Ta, at. %) have been determined via atom probe field-ion microscopy (APFIM) as 76Ni-6Al-18Mo, 67Ni-25Al-4Mo-4Ta and be 73Ni-4Al-20Mo-3Ta respectively. Using energy dispersive x-ray spectroscopy in the analytical transmission electron microscopy (TEM), the composition of the γ' phase (69Ni-22Al-4Mo-5Ta) was found to be similar to that determined by APFIM. The deviation of the DO_{22} composition from Ni_3Mo is in agreement with the prediction of a recent TEM study (Martin et al, 1980, 1982).

At temperatures below 800°C, RSR 143 (76Ni-13Al-9Mo-2Ta, at. %) exhibits a 20 % improvement in stress capability over directionally solidified Mar-M200. Pearson et al. have ascribed this improvement to fine scale secondary precipitates and have recommended the stabilization of these precipitates through compositional modification of the alloy. /1/ Such an objective in alloy design would be more easily accomplished if the composition of the precipitates and the surrounding γ matrix were known and if the kinetics for formation and dissolution of such precipitates were understood. The question of kinetics has been addressed in an extensive transmission electron microscopy (TEM) study by Martin et al. /2/3/. The small size of these secondary precipitates hinders the determination of such compositions through current analytical TEM techniques. The compositions can, however, be determined using atom probe field ion microscopy (APFIM), the principal technique employed in this study.

Experimental

The heat treatment for RSR 143 chosen for the purpose of this analysis was taken from one of the cases examined by Martin /3/. The sample used here, a slice from a single crystal of RSR 143, was solution treated in vacuum at 1300°C for 1 hour and then quenched to ambient temperature. Subsequently, the sample was held at a temperature of 800°C for 100 hours. As confirmed by TEM observations, this heat treatment resulted in a large volume fraction of secondary precipitates of the DO_{22} structure; no precipitates of structures D_{1a} or Pt_2Mo were observed. The DO_{22} phase precipitated as platelets on the {100} faces of the cuboidal γ' particles and in the γ matrix. The location and morphology of these precipitates can be seen in Figs. 1a and 1b.

*Department of Metallurgy, University of Illinois, Urbana, IL.

The three phases occurring in the RSR 143 crystal subjected to the above heat treatment were found to be easily distinguishable from one another when imaged in the field ion microscope (FIM). From Figs. 2a, 2b, and 2c, we see that the DO_{22} phase appeared as a bright and very ordered region whereas the γ phase appeared as bright but less ordered in FIM specimens imaged in Ne and cooled by liquid N_2 . In Fig. 2d we see that the γ' cuboids imaged less brightly under the same imaging conditions. The γ' phase appeared more ordered than the γ phase, though less ordered than the DO_{22} phase.

Microelemental analysis using the APFIM revealed the composition of the DO_{22} phase as 73Ni-4Al-20Mo-3Ta (at.%). The composition of the surround γ matrix was found to be 76Ni-6Al-18Mo. Transmission electron microscopy revealed the size of the γ' cuboids to be on the order of .5 μ ; large enough for composition determination by analytical TEM techniques. Using energy dispersive X-ray spectroscopy (EDXS), we found the composition of the γ' to be 69Ni-22Al-4Mo-5Ta (at.%). This composition compared favorably with that obtained using APFIM: 67Ni-25Al-4Mo-4Ta. In Table 1, we list the composition for each of the three phases.

Discussion

It is apparent from the TEM study conducted by Martin /3/ that the DO_{22} phase is very stable in RSR 143 held at 800°C. According to van Tendeloo et al., /4/ however, in an alloy of composition Ni_3Mo , the DO_{22} phase dissolved in 5 minutes when held at 800°C. One might suppose then, that additions of Al and Ta play some role in enhancing the stability of the DO_{22} phase. Because the ordered DO_{22} is based on the same fcc lattice as the γ' precipitates, Martin discussed this role in terms of the statistical theory of long-range order (LRO) developed by de Fontaine /5/.

In many theoretical treatments, it is assumed that LRO occurs when an atom of a given species is more strongly attracted to atoms of a different species than to atoms of its own species. One might also guess that the structure of the resulting LRO might be influenced by the relative strength of second nearest neighbor bonds as compared to first nearest neighbor bonds. Indeed, the average pairwise interaction energy existing between i^{th} nearest neighbors is regarded as the fundamental parameter influencing LRO in alloy systems. For a binary alloy system composed of atomic species A and B, the average pairwise interaction energy for i^{th} nearest neighbors is

$$V_i = \frac{1}{2} (V_i^{AA} + V_i^{BB} - 2V_i^{AB}). \quad (1)$$

Here V_i^{AA} and V_i^{BB} are the pairwise interaction energies for like i^{th} nearest neighbors. The term V_i^{AB} is the pairwise interaction energy for unlike i^{th} nearest neighbors. The energies V_i^{AA} , V_i^{BB} , and V_i^{AB} are negative quantities which become increasingly negative as the bond in question strengthens. In order to favor unlike i^{th} nearest neighbors, V_i must then be positive.

The significance of the average pairwise interaction energies for first and second nearest neighbors (V_1 and V_2) in ordering reactions can be seen in terms of their effect on atomic scale composition modulations. The DO_{22} phase can be described by two sets of standing waves corresponding to composition modulations on an atomic scale: $\langle 1\frac{1}{2}0 \rangle$ waves and the $\langle 100 \rangle$ waves. The presence of these modulations is obvious from the transmission electron diffraction pattern of the DO_{22} phase in Fig. 3a. According to de Fontaine, /5/ the $\langle 1\frac{1}{2}0 \rangle$ modulation is favored for $0 \leq V_2/V_1 \leq 0.5$, whereas the $\langle 100 \rangle$ modulation is favored for $V_2/V_1 \leq 0$. For both $\langle 1\frac{1}{2}0 \rangle$ and $\langle 100 \rangle$ modulations, $V_1 > 0$. According to Moss and Clapp, /6/ x-ray diffraction measurements of Spruiell and Stansbury /7/ indicate that $V_2/V_1 = 0.3$ for Ni-Mo alloys. For the same alloy system, Das

et al., /8/ using transmission electron diffraction, found that $V_2/V_1 = 0.4$. One would then presume that the instability of the DO_{22} phase in the Ni_3Mo alloy was due to a value of V_2/V_1 too large to allow a stable $\langle 100 \rangle$ wave to develop.

The V_2/V_1 ratio in a Ni-Mo alloy could be lowered by adding a small concentration of a third element known to lower V_2/V_1 in another Ni-base alloy system. It is well known that alloy phases of nominal composition Ni_3Al (such as the γ' cuboids in RSR 143) are of the $L1_2$ structure. As the presence of $\langle 100 \rangle$ reflections in the diffraction pattern for the γ' cuboids in Fig. 3b indicates, $\langle 100 \rangle$ concentration modulations order the $L1_2$ superlattice. In order for the $\langle 100 \rangle$ modulation in this phase to exist, however, V_2/V_1 must be less than zero. Therefore, substituting Al for some of the Mo in the DO_{22} phase would lower V_2/V_1 and in so doing enhance the stability of the $\langle 100 \rangle$ modulation. Because Ni_3Ta has a high temperature DO_{22} phase, the addition of Ta would also be expected to lower V_2/V_1 and stabilize the $\langle 100 \rangle$ modulation /3/. Clearly, these scenarios for stabilizing the DO_{22} phase are in accord with the observed composition of 73Ni-4Al-20Mo-3Ta.

References

1. D. D. Pearson et al., "Factors controlling the creep behavior of a nickel-base superalloy," Creep and Fracture of Engineering Materials and Structures, B. Wilshire and D. R. J. Owen, Eds., Swansea, U. K.: Pineridge Press, 1981, 213-233.
2. P. L. Martin et al., "The structure of as-extruded RSR Ni-Al-Mo and Ni-Al-Mo-X alloys," Rapid Solidification Processing Principles and Technologies II, R. Mehrabian et al., Eds., Baton Rouge, La.: Claitors, 1980, 123-128.
3. P. L. Martin, Ordering Reactions in Ni-Mo Alloys, Pittsburgh, Pa.: Carnegie-Mellon University (Ph. D. Thesis), 1982.
4. Gustaff van Tedeloo et al., "The DO_{22} intermediate phase in the Ni-Mo system," Phys. Stat. Sol. (a) 20: 457-468, 1975.
5. Didier de Fontaine, "k-Space symmetry rules for order-disorder reactions," Acta Met. 23: 553-571, 1975.
6. S. C. Moss and P. C. Clapp, "Correlation functions of disordered binary alloys III," Phys. Rev. 171: 764-777, 1968.
7. J. E. Spruiell and E. E. Stansbury, "X-ray studies of short-range order in nickel-base alloys containing 10.7 and 20.0 at. % molybdenum," J. Phys. Chem. Sol. 26: 811-822, 1965.
8. S. K. Das et al., "Short range order in Ni-Mo, Au-Cr, Au-V, and Au-Mn alloys," Acta Met. 21: 913-928, 1973.

Table 1. Analysis of RSR 143

	Ni	Al	Mo	Ta
RSR 143	76	13	9	2
DO_{22} , APFIM	73	4	20	3
γ , APFIM	76	6	18	-
γ , APFIM	67	25	4	4
γ' , TEM/EDXS	69	22	4	5

Fig. 1 Transmission electron micrographs of RSR 143.

- a) Bright field micrograph.
0.5 μ to 0.1 μ cuboids are
 γ' precipitates set in the
 γ matrix.

- b) Dark field micrograph.
Bright, finely dispersed
particles set in the γ
matrix are DO_{22} platelets.

Fig. 2 Field ion micrographs of RSR 143 imaged in Ne at a specimen temperature of 80°K. a) Highly ordered DO_{22} platelet (upper left, diagonally towards center) against background of less ordered γ matrix. b) DO_{22} phase. c) γ phase. d) γ' phase. Micrographs b, c, and d are of the same magnification.

Fig. 3 Transmission electron diffraction patterns viewed on the [001] zone axis.

- a) Selected area diffraction pattern for a region of the γ matrix containing DO_{22} platelets. $\langle 1\frac{1}{2}0 \rangle$ and $\langle 100 \rangle$ superlattice reflections correspond to composition modulations in the $\langle 1\frac{1}{2} \rangle$ and $\langle 100 \rangle$ directions.

- b) Selected area diffraction pattern for a γ' (L1_2) cuboidal precipitate. $\langle 100 \rangle$ superlattice reflections correspond to composition modulations in $\langle 100 \rangle$ directions.