INTERNAL FRICTION BEHAVIOUR OF SOME FERROMAGNETIC AMORPHOUS ALLOYS

M. ABOKI, G. BOISSEAU and G. BOUQUET

Laboratoire de Métallurgie Structurale, Ecole Nationale Supérieure de Chimie, 11, rue Pierre et Marie Curie, 75231 Paris Cedex 05, et Centre d'Etudes de Chimie Métallurgique (CNRS), F-94400 Vitry-sur-Seine, France

Résumé - La technique du frottement intérieur à basse fréquence (1 Hz) a été utilisée afin d'étudier les réarrangements atomiques susceptibles d'intervenir dans les verres métalliques ferromagnétiques sous l'effet de la température entre l'ambiante et 550°C.

Pour les alliages étudiés, tels que FeBSi, FeBSiCrC et FeNiMoB, le domaine de température envisagé a permis de suivre les évolutions structurales correspondant à la relaxation structurale et aux processus de cristallisation.

L'influence d'un écrouissage ou d'un pré-recuit a également été abordée.

Abstract - In order to study the atomic reorganization occurring in ferromagnetic metallic glasses under the effect of the temperature between 20 and 550°C, internal friction experiments have been carried out on an inverted pendulum at low frequency (1 Hz).

For the studied alloys such as FeBSi, FeBSiCrC and FeNiMoB, the chosen temperature range permitted us to investigate the atomic configurations evolution corresponding to structural relaxation and crystallization processes.

Furthermore, we studied the influence of cold-working or pre-annealing treatments on the internal friction spectra.

I. INTRODUCTION

We studied atomic rearrangements occurring in amorphous alloys as a function of the temperature in order to define the ideal temperature range in which diffusion experiments between metallic amorphous films could be tempted. In this aim various ferromagnetic amorphous alloys have been tested by internal friction measurements at low frequency (1 Hz) between room temperature and 550°C. For this temperature range, structural relaxation and crystallization phenomena are able to take place in the studied materials: FeBSi, FeBSiCrC, FeBSiC and FeNiMoB alloys. Only the results concerning FeBSi, FeBSiCrC and FeNiMoB will be presented here and in the following text these alloys will be named respectively "A, B and C".

Furthermore our investigation consisted of the modification of the internal friction spectrum shape of the alloys, under the influence of various structural states.

II. EXPERIMENTAL RESULTS

Internal friction spectra of "as-cast" alloys. A typical internal friction spectrum of FeBSi amorphous alloy (A), is presented in Fig. 1a. In this figure we can note that after a non-significant initial evolution of Q^{-1} (20-200°C), the spectrum exhibits some anomalies consisting of a low and large maximum at about 300°C, two little maxima between 350 and 450°C and lastly high and sharp maxima at about 550-570°C.

The internal friction spectrum presented in Fig. 1b refers to FeBSiCrC alloy (B). The Q^{-1} evolution is similar to that of A alloy in that sense that comparable anomalies occur but not necessarily at the same temperatures.

Fig. 1

Internal friction spectra as a function of the temperature:

- 1a : "as-cast" FeSiB alloy
- 1b : "as-cast" FeSiBCrC alloy.

In Fig.2 we have reported the internal friction spectrum of FeNiMoB alloy (C). In regards to the previous spectra, we can note a really different behaviour of the material under the influence of temperature. Indeed, we note an initial decrease of Q^{-1} background between room temperature and 150°C. Above this temperature the internal friction increases, leading to two large maxima, respectively at about 250 and 350°C, and lastly to a high and narrow maximum at 540°C.

Fig. 2

Internal friction spectrum of FeNiMoB alloy as a function of the temperature in "as-cast" conditions.

According to these results, the internal friction evolution appears appreciably different from one alloy to the other. Consequently the question is whether the chemical composition or the structural state is responsible of each kind of behaviour. In order to throw light on this last subject, experiments have been carried out with various initial structural states for the alloys.

Internal friction spectra of cold-worked specimens. FeBSi and FeBSiCrC alloys were initially cold-worked by scratching the two sides of the flat specimens with abrasive paper. The corresponding internal friction spectra are reported in Fig.3.

In this figure we can note that the initial Q^{-1} background is much higher than in the case of "as-cast" specimens and that only a little recovery of Q^{-1} is performed under the influence of low temperatures (20-150°C). The internal friction maximum which appeared at about 300°C in the case of "as-cast" A and B specimens, is always observed, but this maximum is higher and narrower in the present case. The enhancement of this maximum will be discussed later. Above 400°C and 350°C for A and B alloys respectively, the internal friction spectra exhibit the same behaviour that in the case of "as-cast" materials.

Fig. 3

Internal friction spectra as a function of the temperature of cold-worked alloys:
 — 3a : FeSiB alloy
 — 3b : FeSiBCrC alloy

Internal friction spectra of pre-annealed specimens. According to the previous results and depending on the nature of the amorphous alloys tested, we could notice that the initial evolution of Q^{-1} between 20 and 200-250°C could be either a decrease or an increase or even a plateau. In the case of a decrease as it is observed for A and C alloys, it is suggested that the "as-cast" structure can be stabilized by annealing treatments. In order to verify such an idea, internal friction spectra have been described after pre-annealing treatments of the various alloys. The results are reported in Fig. 4 and Fig. 5 for A and C alloys respectively.

Fig. 4

Internal friction spectra as a function of the temperature of FeSiB alloy after various pre-annealing treatments at 350°C:
 ... 2 hours, --- 3 hours, — 5 hours,
 -.- 7 hours.

Fig. 5

Internal friction spectra as a function of the temperature of FeNiMoB alloy after various pre-annealing treatments at 300°C: — "as-cast",
 ... 10 min., --- 20 min., -.- 1 hour,
 - - 5 hours, — 9 hours

As in the case of "as-cast" conditions, the behaviour of these alloys is remarkably different. For A alloy the internal friction decreases after short-time pre-annealings and reaches a value, stable up to 400°C. Above this temperature, internal friction increases sharply and passes through the high maximum at about 550°C.

Concerning alloy C, the effect of pre-annealing on Q^{-1} is more progressive and long-time thermal treatments are necessary to obtain a stabilization of the structure in regards of structural relaxation phenomena. For this alloy, interesting data are obtained from the spectrum in Fig. 5 because a maximum emerges from the internal friction background at about 420°C. Moreover after long-time pre-annealings (5-9 hours) the internal friction evolution is restricted to two maxima, the first one at 420°C and the second one at 540°C. Whatever the alloy is, A or C, pre-annealing treatments lead to internal friction spectra where no evolution is detectable up to the Curie transition. Above this temperature internal friction increases as undefined pre-crystallization phenomena occur and then crystallization stages take place.

III. DISCUSSION

In view of internal friction results of "as-cast" A and B amorphous alloys, their Q^{-1} evolution can be divided into four stages. The first one, from room temperature to 200-250°C, must be concerned by little atomic rearrangements because of the light evolution of Q^{-1} in this temperature range. The second one, characterized by a low and large maximum at about 300°C, was attributed to structural relaxation. However this phenomenon is thought to be partly hysteretic in view of the non-reversible character of this maximum when thermal cycles are performed between room temperature and 350°C. A third stage between 400 and 500°C is more difficult to explain. In this temperature range the Curie transition and possibly some phenomena associated with the glassy transition occur, but the two little maxima observed in this stage are not explained (1). Finally the last stage, where two narrow and high maxima are detected, was related to crystallization phenomena. The first maximum corresponds to the alloy decomposition into Fe and Fe₃B compound, the second one is concerned by the transformation into Fe₂B. This result was supported by electron microscopy (2) and differential scanning calorimetry experiments (3) as it will be shown in the following text for FeNiMoB alloys.

Precisely in the case of this last alloy the internal friction spectrum of "as-cast" specimens exhibits two large maxima, at 250 and 350°C respectively, and a narrow one at 540°C. The first maximum was connected with structural relaxation, the explanation of the second one would be difficult without the effect of annealing results. Indeed in these experiments a maximum emerges from the background level and this maximum corresponds to the crystallisation process according to thermal analysis data. Consequently the second large maximum observed in the "as-cast" conditions is assumed to be the superposition of ferromagnetic or glassy transitions phenomena on a first stage in the recrystallization progress. Finally the maximum detected at 540°C was attributed to a second stage of the crystallization phenomenon. These results, concerning the partition of crystallization into two stages, was supported by scanning differential calorimetry experiments performed on alloy C (Fig. 6)

Fig. 6
Differential scanning calorimetry of "as-cast" FeNiMoB alloy.

From the results on the effect of cold-working on internal friction spectra, the main feature is the enhancement of the maximum associated with the structural relaxation. If the relaxation part of this phenomenon is assumed to be characterized by a large spectrum of relaxation times (4), our explanation (5) is based on the possibility of a decrease of the total number of atomic configurations varieties under the effect of the temperature (relaxation times spectrum narrower) and a correlative increase of the number of atomic arrangements of a particular topology (higher contribution to internal friction level).

Informations on the possible effects of cold-working or pre-annealing treatments on the crystallization phenomenon were expected from internal friction spectra but the obtained results were not clearly explainable. Only cold-working seems to have little influence on the crystallization progress but more experiments have to be performed.

IV. CONCLUSION

The ferromagnetic amorphous alloys which have been studied, exhibited important internal friction fluctuations related to atoms reorganization under the effect of the temperature. According to the nature of the tested material, the internal friction evolution as a function of the temperature is quite different, nevertheless in each alloy it appeared that a wide and low maximum could be associated with structural relaxation while high and sharp maxima were related to two stages in the crystallization process.

Cold-working treatments increased the internal friction background and modified the shape of the maximum connected with the structural relaxation. This result was attributed to modification and redistribution of atomic aggregates configurations. Cold-working treatments seemed to modify the crystallization process but the results are not reproducible.

Concerning the influence of pre-annealing on the internal friction behaviour of the studied alloys, it was shown the occurrence of a significant evolution in the temperature range where structural relaxation took place. When structural relaxation is completely achieved, on internal friction spectra, anomalies are restricted to Curie transition and to crystallization stages.

Among the tested amorphous materials, FeNiMoB alloy exhibited a specific behaviour in that sense that important internal friction fluctuations, as a function of the temperature, revealed a high atomic mobility in the low temperature range. Such a phenomenon could be used for diffusion experiments between amorphous metallic films.

V. REFERENCES

1. N. Morito, T. Egami, Acta Met. 32, 603 (1984).
2. A. Quivy, Thèse - Université Paris VI (Déc. 1985), Paris.
3. J. Devaud-Rzepski, A. Quivy, M. Harmelin, J.P. Chevalier, Y. Calvayrac, First international workshop on non crystalline solids (San Feliu de Guixols Mai 1986).
4. Z.Z. Shi, Z.X. Wang, Proc. of the 8th I.C.I.F.U.A.S. - Urbana 1985 (U.S.A.) J. de Physique C 10 46, 469 (1985).
5. M. Aboki, G. Bouquet To be published in Scripta Met.

ACKNOWLEDGMENTS

The authors wish to thank Ms. M. Harmelin for valuable D.S.C. experiments.