RADIATION METHOD OF TEMPERATURE MEASUREMENT IN THE ZONE OF LOCALIZED IMPACT LOADING

I.B. CHERVIAKOV and D.V. LAPTEV

*Moscow Oil and Gas Institute, Department of Mechanical Engineering, Leninsky Prospect 65, Moscow 117917, USSR*Abstract

The radiation low-inertial method was developed for temperature measurement in the impact contact zone, using the pyrometer based on the non-cooled photoresistor and flexible fibre-optical cable. The pyrometer is attached to the "pneumatic gun" testing rig, which provides the collision of steel balls having the diameters up to 3×10^{-3} m and other hard particles with the specimen surface at the velocities up to 300 m/sec. The impact angles vary continuously from 0 to 90°. This method allows to measure the temperatures in the impact zone of the materials with low and high electroconductivity and is advantageous in comparison with methods using thermocouples of different types. The experimental data are obtained for some technically pure metals and structural steels at various impact energies and angles. They show the experimental possibilities of this method and have their own scientific value.

Introduction

The hard particle-material surface interaction at collision is a non-stationary process and is characterized by high loading speed and low contact time. Obviously, the processes of heat emission at the contact area are as fast as the process of impact itself. It was found in [1] that at the collision speed of two bodies 100 m/sec, the time of temperature rise in the loading zone is 10^{-4} sec and less. At the same time cooling of the heated impact zone is much longer process than heating. Difference in time constants for these two pro-

cesses is at least of one order and depends upon the parameters of loading and thermal properties of the materials /2,3/.

At high rates of the order of $10^3 - 10^4 \text{ sec}^{-1}$ the heat emission in the deformed volume of the material can be considered as adiabatic /4/. In this case all the thermal energy is concentrated in the given volume and in the moment of impact loading the energy of infrared radiation will correspond to the maximum emitted thermal energy.

Method and materials

The testing technique for temperature measurement in the zone of hard particle collision with the surface of material using the pyrometer with fibre-optical cable was developed in Moscow Oil and Gas Institute.

The functional block-diagram of the technique is given in Fig.I. The testing rig consists of compressed gas cylinder 1, pressure reduction valve 2, intermediate chamber 3, standard pressure meter 4, electromagnetic valve 5, loading device 6 for steel balls and the gun tube 7.

Measurement of impact and rebound velocities v_0 and v_I of the particle is made in the following way. The particle crosses the light beam from the source (not shown). The photodiode 8 generates the pulse triggering the clock II. At the collision of the particle with the specimen 9, the piezoceramic sensor, attached to the specimen, generates the pulse, stopping the clock II and triggering the clock I2. The next pulse, generated by the sensor 10 at the impact of the rebounded particle, stops the clock I2. Knowing the distance between the positions of sensors 8-9 and 9-10 and the time shown by the clocks II and I2, we can calculate the velocities v_0 and v_I . The accuracy of velocity measurement is $\pm 1\%$, the accuracy of the impact angle is $\pm 1^\circ$.

This technique provides the following loading parameters: initial particles' velocities up to 200 m/sec, impact angles 15-90°, particles diameters 1-4 mm.

The optical cable which transmits the infrared radiation from the interaction zone to the detector is made of Ge-As-Se material. The diameter of the optical core is 430 micrometers. For mechanical safety the cable is mounted in the steel tube and centered in it with plastic inserts. For decreasing energy losses due to reflections from the ends of the optical cable they were precisely polished.

As a detector the non-cooled Se-Pb photoresistor of the type

FR-64 was used. The technical characteristics of the detector allow to use it in the infrared region of the spectrum. The time constant of the detector is 10-15 microseconds, allowing to analyze the thermal processes in the impact zone with the same time parameters.

The broad-band amplifier I5 is used for conditioning the signal, obtained from the sensor I4. The output pyrometric signal (voltage) U_{out} , corresponding to the monochrome radiation with a constant value of effective wavelength λ_{eff} , is directly related to the temperature of the radiating object. The oscilloscope I6 with memory is used for visualizing and recording the temperature pulses generated by the pyrometer.

Before the measurements the instrument was calibrated against statically heated surfaces with known temperatures of the same materials used for dynamic tests by particles impacts. For modelling of the dynamic loading conditions the mechanical chopper was used, modulating the infrared flux from the heated body with the frequency of 1 kHz. The preliminary experiments showed that the radiation modulation frequency does not affect the output parameters of the pyrometer up to the values of 0,5 MHz. In this way the pyrometer was calibrated in the dynamic conditions as close to the actual measurement process as possible.

The temperature measurement at the impact of the surface of tested material by the hard particle is performed in the following way. The input end of the optical cable I3 is positioned perpendicularly to the surface of the specimen 9 at the distance $L = d_p + 2 \text{ mm}$ (d_p - diameter of the particle, 2 mm - the methodically chosen distance required for an unobstructed rebound of the particle) and is directed to the suggested point of interaction. Then the shot is made from the "pneumatic gun" and the infrared radiation from the contact zone is recorded by the pyrometer into the memory of the oscilloscope I6. In order to eliminate the noise and interference triggering of the oscilloscope is synchronized with the moment of impact via the piezoceramic transducer 9. The calibration allows to convert the values of U_{out} into the temperature data.

The temperature measurements in the contact zone were performed using the materials shown in the Table I.

Fig.1 Block diagram of the testing rig.

Fig.2 Effect of particle velocity on the temperature in the collision zone

Fig.3 Effect of impact angle on the temperature in the collision zone.

Table I

No.	Material	Heat treatment	Hardness HV, MPa
1	Cu	-	1000
2	Fe Armco	-	1300
3	Steel 3	-	1400
4	Steel 45	Normalizing	1900
5	Steel U8	Normalizing	2100
6	Steel 45	Quenched from 850 °C and tempered at 500 °C	3000
7	Steel U8	Quenched from 850 °C and tempered at 470 °C	3500
8	Ti	-	3600
9	Mo	-	4500
Steel balls	Steel 95Cr18	Quenched and tempered	60-62 HRC

Results

The experiments have shown that at higher initial velocities of impact the temperature in the collision zone increases (Fig. 2). This growth of temperature T_k principally is determined by increased plastic deformation. The generation of high local heating in the deformed zone is caused mainly by the strain rate.

In case of high-speed deformation the heat has not sufficient time to dissipate, the process becomes adiabatic and leads to the temperature rise in the collision zone. The locality of temperature flash was proved by the following experiment. The optical cable of the pyrometer was focused on the zone adjacent to the supposed dimple. At collision the pyrometer in this case has not recorded any temperature pulse.

As it is seen from Fig. 2, the temperature T_k in the impact zone reaches the highest value of 530 K.

It is interesting to observe the dependence of T_k upon the impact angle. It was shown that this dependence is characterized by the maximum at impact angles around 45° (Fig. 3). This was observed for all tested materials and impact velocities used in these experiments,

and can be explained by the simultaneous effects of the degree and the rate of plastic deformation upon the temperature T_k . Decreasing of the impact angle α and consequently the degree of deformation leads to decreasing of the temperature T_k .

Significant, in our opinion, effect upon the temperature change in the collision zone is caused by the frictional events in the contact area. It was shown /5,6/ that the friction coefficient at the collision of hard particle with the surface is not constant but has its maximum value in the region of sliding impact angles. So the temperature maximum T_k around impact angles 40-50° is due to the additional heating of the contact zone by friction of the particle against the surface of tested material.

It was reported in /7/ about the extreme adsorption by the material of initial kinetic energy of the particle in the range of impact angles $\alpha = 25 - 45^\circ$ due to the sliding friction of the particle over the surface.

The experiments have shown that the size of the particles has very low effect on the temperature in the collision zone. It is so, because the plastic deformation parameters, responsible for temperature growth, practically do not depend upon the size the particles. It is supported by the results of /8/ where it was shown that the temperature in the contact zone is not sensitive to the particle size.

We did not find any explicit correlation between the temperature and material properties. Probably it is due to the temperature dependence upon the combination of strength, plasticity and thermal properties of the material. To distinguish the effects of each factor was not possible in this work.

Conclusion

The experimental technique has been developed, allowing to measure the temperature in the impact zone at the collision of hard particle with the surface of various materials. The pyrometer with non-cooled photoresistor and flexible fibre-optical cable is the part of this technique.

It was shown that the temperature in the contact zone rises continuously with rising impact velocity and achieves the value of 530K.

The maximum of temperature was observed in the region of impact angles of 40 - 50° and varies weakly with the size of the particles.

References

1. Kononenko V.G. High-speed forming and fracture of metals (in Russian). Charkov, 1980.
2. Babichev et al. Pribery i tehnika experimenta, 1985, N 5, p. 197-198.
3. Vinogradov V.N. et al. Wear at impact (in Russian). Moscow, Mashinostroenie, 1982.
4. Shock waves and high-speed deformation of metals (in Russian). Moscow, Metallurgia, 1984.
5. Pateiuk G.M. Nauchnye trudy OMIIT, 1965, v. 57, p. 67-76.
6. Styller E.E. Sbornik trudov VNIPTUGLEMASH, Moscow, 1975, issue 20, p. 75-81.
7. Sorokin G.M. Vestnik mashinostroenia, 1986, N 5, p. II-15.
8. Kilchevsky N.A. The theory of solid bodies collision (in Russian). Kiev, Naukova Dumka, 1969.