Investigation of the kinetics of MOCVD with a stagnation cell

O. Yu Gorbenko, W. Decker, G. Wahl

► To cite this version:

O. Yu Gorbenko, W. Decker, G. Wahl. Investigation of the kinetics of MOCVD with a stagnation cell. Journal de Physique IV Proceedings, 1993, 03 (C3), pp.C3-25-C3-33. 10.1051/jp4:1993303 . jpa-00251360

HAL Id: jpa-00251360

<https://hal.science/jpa-00251360>

Submitted on 1 Jan 1993

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Investigation of the kinetics of MOCVD with a stagnation cell

O. YU GORBENKO, W. DECKER* and G. WAHL*

Dept. of Chemistry, Moscow State University, B-234, 119899 Moscow, Russia

** Institut für Oberflächentechnik, Technische Universität Braunschweig, Bienroder Weg 53, 38108 Braunschweig, Germany*

Solutions of the mass transfer equation in the stagnation cell are described. It is shown that the application of the stagnation cell can be used for the determination of Da^* , distinguishing different types of process control, sensing gas phase condensation and homogeneous nucleation. The results obtained with cylindrical cell for MOCVD of YBCO are discussed.

INTRODUCTION

Many MOCVD processes occur in the diffusion controlled regime [1-3]. In a diluted gas mixture at the constant temperature the diffusion of reactants in the carrier gas can be described independently. The diffusion flux of each reactant j_s is given by Fick equation:

$$j_s = -D_{ij} \nabla C_i \quad (1)$$

where D_{ij} - binary diffusion coefficient of i in the mixture, C_i - molar concentration of i .

The concentration gradient is determined by reactant concentration on the reacting surface (C_{is}) and outside boundary layer (C_{io}). For stagnation flow reactors [4] the formula

$$j_s = D_{ij} (C_{io} - C_{is}) * Sc^{1/3} Re^{1/2} / D \quad (2)$$

is valid for the deposition rate on the surface, where Sc - Schmidt number, Re - Reynolds number, D - diameter of flow inlet.

C_{is} can be calculated from thermodynamical data. The deposition rate correlates with the shift of the chemical equilibrium. The chemical processes in the gas phase namely species transformation (elimination, association and dissociation, disproportion, etc.) (a), lead to formation of condensed phase (homogeneous nucleation) (b) lead to a variation of D_{ij} . Appearance of (b) is possible at high supersaturation C_i/C_{ie} (C_{ie} - equilibrium value of the component i).

There is a lack of kinetic data for processes such as deposition of metal oxides (high T_c superconductors, ferroelectric perovskites, magnetic spinels and garnets, solid ionics, glasses) using metal organic compounds (MOC). Today the complete kinetic description is impossible in difference to the CVD of Si [5-6]. The deposition in a stagnation cell is helpful to determine kinetic data for the deposition of oxides.

1. STAGNATION CELL

A stagnation cell (fig. 1 a b) can be arranged in a stagnation flow reactor (fig. 1 c). For the considerations in this section we assume, that no homogeneous reactions exist, the reactions at the surface are very fast and at the surface the concentration $C_{is} = 0$ of the precursor molecule i is assumed. For the estimation we assume as a first approximation that in the cell are no convection effects. Then the deposition profile can be calculated by solution of the Laplace equation $\Delta C_i = 0$, if the concentration C_i of the component i at $z = L$ is known. The solution of the equation is independent of D_{ij} . For an infinite rectangular split (fig. 1a) with width d and depth L with the boundary condition on the wall $C_{is} = 0$ and at the inlet of the cell $C_i(x, L) = C_0$ the solution [7] is

$$C_i(x, z) = \frac{4C_0}{\pi} \sum_{l=1}^{\infty} \frac{1}{(2l-1)} \frac{e^{\frac{\pi(2l-1)z}{d}} - e^{-\frac{\pi(2l-1)z}{d}}}{e^{\frac{\pi(2l-1)L}{d}} - e^{-\frac{\pi(2l-1)L}{d}}} \sin \frac{\pi(2l-1)x}{d} \quad (3)$$

According (1) (minus sign is omitted below) in the case $L \gg d$ we have after substitution $z' = L - z$:

$$j_s(z') = \frac{4D_{ij}C_0}{d} \frac{e^{\frac{\pi z'}{d}}}{(e^{\frac{2\pi z'}{d}} - 1)} \quad (4)$$

and for large z' ($2\pi z' / d > 1$):

$$j_s(z') \rightarrow \frac{4D_{ij}C_0}{d} * e^{-\frac{\pi z'}{d}} \quad (5)$$

For a cylindrical cell (radius R and depth L , fig. 1b) with boundary conditions $C_{is} = 0$ and $C(r, L) = C_0$ the solution has the form

$$C_i(r, z) = 2C_0 \sum_{n=1}^{\infty} \frac{1}{B_n J_1(B_n)} \frac{e^{\frac{B_n z}{R}} - e^{-\frac{B_n z}{R}}}{e^{\frac{B_n L}{R}} - e^{-\frac{B_n L}{R}}} J_0\left(\frac{B_n r}{R}\right) \quad (6)$$

where J_0, J_1 are the Bessel functions of 0 and 1st order, B_n - zeros of J_0 ($J_0(B_n) = 0$).

For $L \gg R$ after substitution $z' = L - z$ and using $B_n - B_{n-1} \approx \pi$ it can be derived:

$$j_s(z') \approx \frac{2D_{ij}C_0}{R} \frac{e^{\frac{(\pi - B_1)z'}{R}}}{(e^{\frac{\pi z'}{R}} - 1)} \quad (7)$$

and for large z' ($2\pi z' / R > 1$):

$$j_s(z') \rightarrow \frac{2D_{ij}C_0}{R} e^{-\frac{B_0 z'}{R}} \quad (8)$$

So for the deposition controlled by gas phase diffusion with ($C_{is} = 0$) the following conclusions can be made: 1. Geometry of the cell determines the normalized deposition profile; 2. The stoichiometry of the deposit is independent of z' if different elements are deposited from different precursors.

With the boundary conditions used the deposition rate is infinite at $z' = 0$ as C_i changes unsteady from C_0 to 0. A more realistic condition $C_i(r, L)$ is desirable. Using Fourier-Bessel expansion and neglecting negative exponents we obtain:

$$j_s(z') = \frac{D_{ij}}{R} \sum_{n=1}^{\infty} B_n A_n e^{-\frac{B_n z'}{R}} \quad (9)$$

The A_n are determined by $C_i(r, L)$:

$$A_n = \frac{2}{J_1^2(B_n) R^2} \int_0^R r C_i(r, L) J_0\left(\frac{B_n r}{R}\right) dr \quad (10)$$

For $C_i(r, L) = C_0$ eq.(9) leads to (7). As $C_i(r, L) > 0$ the sum of members with $n > 1$ can be neglected in comparison with the first member for large z' :

$$j_s(z') \rightarrow \frac{B_1 D_{ij}}{R} A_1 e^{-\frac{B_1 z'}{R}} \quad (11)$$

The formula (11) gives the same normalized deposition profile for component i as formula (8). The profile is valid at $z' \geq 0$ for the boundary condition

$$C_i(r, L) = C_0 J_0\left(\frac{B_1 r}{R}\right) \quad (12)$$

with deposition rate

$$j_s(z') = \frac{D_{ij} B_1 J_1(B_1)}{R} e^{-\frac{B_1 z'}{R}} \quad (13)$$

The profile is referred to so-called ground diffusion mode (GM).

In order to determine the applicability of equ. 13 the Laplace equation was solved numerically with the code FLUENT V3.03. For these simulations the more realistic case was assumed, that above the stagnation surface ($z=L$) a stagnant boundary layer with the thickness δ was formed. The thickness δ was varied between 0 and 10 mm. For the simulations an uniform grid with a step width of 0.2mm was used. With growth of z' the normalized concentration profile of i in radial direction converges to $J_0(B_1 r/R)$. Inlet C_i profile with growth of δ converges rapidly to a function different from $J_0(B_1 r/R)$.

The comparison of the normalized profiles which were calculated numerically with the profile calculated by equ.(13) shows that at $z' > z'_0$ the profile can be described by equ.(13) with a maximum deviation of 5%. The value of z'_0 is: $z'_0 = 0.25 d$ and $z'_0 = 0.5 R$. The normalization of the profiles were carried out with a value at $z' > z'_0$. At these calculations d and R were varied between $2 < d < 7$ mm and $1 < R < 4$ mm. The depth was always $L = 20$ mm.

In order to observe flow effects we carried out calculations for a stagnation flow reactor (fig.1c) at different Re. Inlet velocity profile was $v = v_m(1 - 4r^2/D^2)$, $D=10$ mm, $R=3.6$ mm. At low Re ($Re < 40$, Re was calculated with the mean velocity $v_m/2$ and D) the normalized inlet C_i and j_s profiles coincide with profiles obtained with the stagnant boundary layer. For high Re the convection leads to enrichment of i in the cell. With growth of z' the influence of convection decreases. For $Re=75$ the convection only is important for $z' < 1$ mm. For larger z' the profile converges to the GM profile.

Summarizing the basic features are:

1. For $z' > z'_0$ the deposition profile corresponds to the GM profile in the normalized form. The plot of $\ln j_s(z')$ vs. z' is a straight line.

2. For $z'_1 < z' < z'_0$ ($z'_1 \approx 0.06 R$ or $0.05 d$) the following profiles were determined empirically (deviation from simulated profile less than 6% for R in the range 1-3.6 mm, d in the range 1.4-5.2 mm):

$$j_s(d, z') \sim \frac{e^{\frac{2\pi z'}{d}}}{(e^{\frac{3\pi z'}{d}} - 3/4)} \quad (14)$$

$$j_s(R, z') \sim \frac{e^{\frac{3}{2} \frac{(\pi - B_1) z'}{d}}}{(e^{\frac{3}{2} \frac{\pi z'}{d}} - 6/7)} \quad (15)$$

3. For $Re > 50$ the deposition profile at the entrance is steeper and it can be described by an equation of the type of equ.(7).

These calculations are only correct for $Kn < 0.01$ where Kn is the Knudsen number determined as the ratio of the mean free length λ in the gas mixture to cell width. In the gas mixture Ar-MOC (collision radius $10\text{\AA}$) at $T=1073\text{ K}$ and $p=10\text{ mbar}$ we have found that the calculations are correct at $R > \sim 0.5\text{ mm}$.

2. INFLUENCE OF GAS PHASE KINETICS

The basic elementary gas phase reactions involved in MOCVD are:

where A, B, C - metal containing species, R - gas phase reactant containing no metal atoms, ΣP - elimination products.

In the case of reaction II-2 with the rate constant k we have the following equations of mass transfer in the stagnation cell:

$$D_A \Delta C_A - 2kC_A^2 = 0 \quad (16)$$

$$D_B \Delta C_B + kC_A^2 = 0 \quad (17)$$

We define the formal function C_f :

$$C_f = D_A C_A + 2D_B C_B \quad (19)$$

Evidently

$$\Delta C_f = 0, \quad j_s = D_A \frac{\partial C_A}{\partial n} + 2D_B \frac{\partial C_B}{\partial n} = \frac{\partial C_f}{\partial n} \quad (18)$$

where n is a direction parallel to j_s .

The equation for C_f is a Laplace equation. If $C_{is}=0$ (i is A and/or B) then $C_{fs}=0$. Inlet boundary condition for A in the absence of reactions is $C_A = f(\zeta_1, \zeta_2, \zeta_3) > 0$ where $\zeta_1, \zeta_2, \zeta_3$ are orthogonal coordinates.

In the presence of reaction for each point at the inlet we consider the conversion factor $\omega(\zeta_1, \zeta_2, \zeta_3) = 2C_B / (C_A + 2C_B)$ where $0 \leq \omega \leq 1$. So the boundary condition for C_i is

$$C_i(\xi_1, \xi_2, \xi_3) = (\omega(\xi_1, \xi_2, \xi_3) * (D_B - D_A) + D_A) * F(\xi_1, \xi_2, \xi_3) = \tau F \quad (20)$$

If $\omega = \text{const}$ then $C_B = \text{const} * f$. τ defined by (20) has the dimension of a diffusion coefficient. It is equal to D_A if reaction occurs only in the cell (cold wall reactor) or to D_B if rapid reaction takes place outside. Otherwise τ is between D_A and D_B determined by the volume Damköhler number $Da^v = k * L * C_0 / v_0$, where C_0 is inlet concentration of A and L a characteristic length. For reaction II-2 the inlet conversion factor depends on C_i . So the assumption $\omega = \text{const}$ is not valid. For the reaction I inlet conversion factor is independent C_0 (also $Da^v = k * L / v_0$). Reactions II-1 occur in MOCVD at the $C_R \gg C_A$. C_R can be included in k then mass transfer equations for C_A and C_B are the same as for reaction I. Reactions II-3 are absent in the case of MOCVD processes using a single precursor.

The molecular size determines the value of D_{ij} . So a remarkable change of D_{ij} for metal carriers is observed in reactions II-2, II-3. A series of reactions II-2 (II-3) results in a decrease of diffusivity. The condensation of nuclei on the surface is another mass transfer effect. The rate of condensation I_c is determined from the binary collision theory:

$$I_c = \pi \gamma n_i \bar{V}_i \sum_N r_N^2 n_N, \quad j_s = \gamma C_i \frac{\bar{V}_i}{4}, \quad \bar{V}_i = \sqrt{\frac{8RT}{\pi M_i}} \quad (21)$$

where γ is the accommodation coefficient, C_i - concentration of i in the gas phase, n_i , n_N - numbers of i and nuclei in volume unit, M_i - molecular mass of i , r_N - radius of the nucleus.

The expression can be used for $r_N < \lambda$. Particles produced by the growth of nuclei in the gas phase during LPCVD obey this condition [8]. In the presence of homogeneous nucleation the deposition profile has a form between the profiles with minimum and maximum of D_{ij} .

For the evaluation of experimental profiles we recommend to calculate the ratio of normalized deposition profiles to the standard profile (Q). The standard profile is the profile calculated in section 1. If Q deviates strongly from $Q = 1$ the initial hypothesis about the pure diffusion controlled deposition can not be used. If $Q \approx 1$ for large z' and $Q > 1$ for small z' then condensation takes place. Q is the lower limit of D_{ij} variation for carriers of i . If $Q \approx 1$ for large z' and $Q < 1$ for small z' the elimination reactions are present. Nevertheless this case seems to be hypothetical as conversion factor for reaction I doesn't depend on the concentration of reactant. If $Q \approx 1$ for all z' it means that the conversion factor is constant at the cell inlet. Increase (decrease) of absolute deposition rate on the walls of the cell with temperature growth indicates elimination (condensation) processes in the gas phase. No significant variation of deposition rate in the temperature range means conversion factor 0 or 1 at the cell inlet. The reliability of the technique is enhanced if simultaneous deposition of metal components occur.

3. SURFACE KINETICS

The kinetics of the first order reaction can be used as a boundary condition in the stagnation cell:

$$D_{ij} \frac{\partial C_i}{\partial n_s} + k C_i = 0 \quad (22)$$

where n_s - direction normal to the deposition surface, k - reaction constant of the first order reaction.

The kinetic investigation in the cylindrical stagnation cells [9-15] were described. Solutions with boundary condition (22) and $C_i(r, L) = C_0$ is

$$C_i(x, z) = 2C_0 \sum_{n=1}^{\infty} \frac{J_1(\alpha_n)}{\alpha_n (J_1^2(\alpha_n) + J_0^2(\alpha_n))} \frac{e^{\frac{\alpha_n z}{R}} + p_n e^{-\frac{\alpha_n z}{R}}}{e^{\frac{\alpha_n L}{R}} + p_n e^{-\frac{\alpha_n L}{R}}} J_0\left(-\frac{\alpha_n x}{R}\right) \quad (23)$$

where α_n are solutions of equation $Da^s J_0(\alpha) = \alpha J_1(\alpha)$, p_n is calculated by $(\alpha_n - Da^s)/(\alpha_n + Da^s)$ and Da^s is the surface Damköhler number ($Da^s = kR/D_{ij}$). For small α_1 the value of α_1 is given by $\alpha_1 = (2Da^s)^{1/2}$ [11,12].

For $Da^s \gg 1$ α_n approximates B_n . For $Da^s \ll 1$ α_n approximates B_{1n} , where B_{1n} are zeros of J_1 (generally $B_{n-1} < B_{1n} < \alpha_n < B_n$). Condition $\alpha_n \rightarrow B_{1n}$ means $J_1(\alpha_1) \rightarrow \alpha/2$ and $J_1(\alpha_{n+1})/\alpha_{n+1} \rightarrow 0$. So at $Da^s \rightarrow 0$ the reacting component is homogeneously distributed in the cell. The deposition rate is constant for all z and equal to kC_0 . The conditions with small Da^s are of great practical importance as for industrial LPCVD in the horizontal reactor, CVD of porous substrates [14,15] and fibre bundle coatings [16].

The experimental data can be approximated by the first term of equ.(23)

$$j_s(z) \sim e^{\frac{\alpha_1(L-z')}{R}} + p_1 e^{-\frac{\alpha_1(L-z')}{R}} \quad (24)$$

where z is replaced by $z = L - z'$.

The profile is a function of single parameter Da^s . Therefore Da^s can be determined by the profile. In the case of large α_1 the negative exponent in equ.(24) can be neglected:

$$\ln(j_s(z')) \sim -\frac{\alpha_1 z'}{R} \quad (25)$$

Simulations carried out with FLUENT 3.03 in the geometry of stagnation flow reactor (fig.1c) for $Da^s = 0.69$ and $Da^s = 2.7 \cdot 10^{-4}$ gave good accordance with the analytical calculations (fig.2, subscript sc is used for normalized profiles).

4. EXPERIMENTAL

The MOCVD of $YBa_2Cu_3O_{7-x}$ films was investigated using vapor of thd-complexes (2,2,6,6-tetramethylheptandion-3,5-ates) of Y, Ba, Cu and diglyme obtained by evaporation of aerosol. A hot wall stagnation flow reactor was used. Experimental details can be found in [17]. Process parameters: pressure 2000 Pa, inlet temperature 270°C, total flow 33 l/h including 30 l/h O_2 (STP). Analysis of deposits was fulfilled with EDX.

The influence of the deposition temperature on the profiles in the cylindrical cell (radius 2 mm, length 20 mm) was studied. The deposition profiles obtained at 650°C, 750°C and 850°C are shown in fig.3. At 650°C deposition profiles for Y and Cu correlate with GM profile. Ba-profile at 650°C doesn't agree with the ground diffusion mode profile. The experimental data can be approximated by equ.(25) with $\alpha_1 = 1.2$ which corresponds to $Da^s = 0.9$ (points with $z' < 0.25$ mm were not taken into account). The result can be compared with data for MOCVD of YBCO films [1] which show that process is diffusion controlled at app. $T > 600^\circ\text{C}$.

Growth of deposition temperature to 750°C results in change of deposition profiles for Y and Cu. Deposition profile of Y doesn't agree with the GM in the used range of z' (it was normalized to GM profile at the last experimental point available). Homogeneous nucleation in the gas phase is obvious because of the very small equilibrium vapor pressure of Y_2O_3 at 750°C. Very small crystals of Y_2O_3 were observed in the YBCO films obtained by MOCVD [18,19]. In the case of Cu $Q \geq 1$ was found and the profile converges to the GM profile in the z' range used. So condensation reactions can be assumed for

Cu species under the conditions. Ba profile has Q values in the range $Q \leq 1$.

At the of deposition temperature of 850°C new effects occur. For Cu nearly the GM profile is observed for $z' > 0.5$ mm. The change of the condensed phase ($\text{CuO} \rightarrow \text{Cu}_2\text{O}$) in the thermodynamic equilibrium can be the reason. It is interesting that the P_{O_2} -T conditions for the growth of epitaxial YBCO films correspond to the $\text{CuO}/\text{Cu}_2\text{O}$ equilibrium [20]. Y shows the same behaviour as at 750°C. The Ba profile converges to the diffusion controlled profile.

The results correlate with data on MOCVD of YBCO [1,18-20] and explain e.g. the Y_2O_3 inclusions in YBCO films.

CONCLUSIONS

Deposition in the stagnation cell can be used for the investigation of MOCVD with different processes, e.g. gas phase condensation and homogeneous nucleation processes. The technique enables determination of Da^* . The different deposition profiles of Y, Ba and Cu shows, that it is difficult e.g. to deposit on carbon fibre bundles a coating with a composition independent of the position on the fibre.

REFERENCES

1. Wahl G. *Jahrbuch von Oberflächentechnik* 49 (1993) 253.
2. Blocher J.M. *Thin Solid Films* 77 (1981) 51.
3. Fitzer E. *J.de Phys.IV Col.C2 suppl.J.de Phys.II* 1 (1991) 509.
4. Chin D.T., Tsang C.H. *J.Electrochem.Soc.* 125 (1978) 1461.
5. Coltrin M.E., Kee R.J., Evans G.H. *J.Electrochem.Soc.* 136 (1989) 819.
6. Kleijn C.R. *Transport Phenomena in Chemical Vapor Deposition Reactors*, Delft (1991).
7. Bronstein I.N., Semendjajev K.A. *Taschenbuch der Mathematik*, 22. Aufl, (1984) 496.
8. Murthy T.U.M.S., Miyamoto M., Shimbo M., Nishizawa J.-J. *J.Cryst. Growth* 33 (1976) 1.
9. Wise H, Ablow C.N *J.Chem.Phys.* 29.(1958) 634; Wood B.J., Wise H. *J.Chem.Phys.* 29 (1958) 1416.
10. Armas B., Combescure C., Diaz-Salgado C. *Proceed.V European Conf. on CVD Uppsala(Sweden)* (1985) 183.
11. van den Brekel C.H.J, Fonville R.M.M., van der Straten P.J.M., Verspui G. *Proceed. of VIII Int.Conf. on CVD* (1981) 142.
12. van den Brekel C.H.J., Lersmacher B. *Proceed. IV European Conf. on CVD, Eindhoven (The Netherlands)* (1983) 321.
13. Egashira Y., Sorita T., Shiga S., Ikuta K., Komiyama H. *J.de Phys. IV Col.C2 suppl.J.de Phys. II* 1 (1991) 55.
14. Fitzer E., Fritz W., Schoch G. *J.de Phys. IV Col.C2 suppl.J.de Phys.II* 1 (1991) 143.
15. Naslain R., Langlais F., Fedou R. *J.de Phys.* 50 Col.C5 (1989) 191.
16. Stumm T., Fitzer E., Wahl G. *J.de Phys. III* 2 (1992) 1413.
17. Decker W., Nürnberg A., Pulver M., Stolle R., Wahl G., Erokhin Yu.Yu., Gorbenko O.Yu., Graboy I.E., Kaul A.R., Sommer M., Vogt U. *Proceed. of Int. Conf. on CVD Honolulu (USA)* (1993) to be published.
18. Schulte B., Maul M., Häusler P., Adrian H. *Appl.Phys.Lett.* 62 (1993) 633.
19. Lu P., Li Q., Zhao J., Chern C.S., Gallois B., Norris P., Kear B., Cosandey F. *Appl.Phys.Lett.* 60 (1992) 1265.
20. Yamane H., Hasei M., Kurosawa H., Watanabe K., Awaji S., Kobayashi, Hirai T., Muto Y. *Physica C* 190 (1991) 79.

FIGURE 1. Geometry of cells: infinite rectangular split (a); cylindrical cell (b); stagnation flow reactor with cylindrical cell (c).

FIGURE 2. Simulation of deposition profiles of the component ($D_i=1 \text{ cm}^2/\text{s}$) in the cylindrical cell ($R=2\text{mm}$, $L=20\text{mm}$) at $T=1073 \text{ K}$ for Da_s 0.69 (a) and $2.7 \cdot 10^{-4}$ (b) (stagnation flow reactor, fig.1c).

FIGURE 3. $j(z')$ profiles for components of YBCO layers deposited by MOCVD in the cylindrical tube (2 mm radius, 20 mm length) at 650°C (a), 750°C (b) and 850°C (c) (stagnation flow reactor [16]).