Studies of laser induced-MOCVD zinc oxide films

Z. Tan, P. Ren, W. Luo

► To cite this version:

Z. Tan, P. Ren, W. Luo. Studies of laser induced-MOCVD zinc oxide films. Journal de Physique IV Proceedings, 1993, 03 (C3), pp.C3-261-C3-264. 10.1051/jp4:1993335 . jpa-00251392

HAL Id: jpa-00251392

<https://hal.science/jpa-00251392>

Submitted on 1 Jan 1993

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Studies of laser induced-MOCVD zinc oxide films

Z. TAN, P. REN and W. LUO

Center for Functional Materials Research, Qingdao Institute of Chemical Technology, Qingdao 266042, China

Abstract-Thin films of ZnO have been prepared by the double photobeams ultraviolet laser induced- metallorganic chemical vapour deposition (MOCVD) technique. The structure and transparent photoconductive property of these films are investigated by X-ray diffraction(XRD) , reflecting electron diffraction(RED) , scanning electron microscopy(SEM) and ultraviolet visible absorption spectrometry(UV) . The experiment shows that the technique produces superior quality films of polycrystal ZnO and possesses higher deposition rate, lower temperature of growth and far better transparent photoconductive property than those grown by the conventional CVD or MOCVD technique.

1-INTRODUCTION

Zinc oxide(ZnO) in pure form is a n-type semiconductor with wide band gaps near 3. 3ev, with large piezoelectric and optical coupling constants. Thin films of ZnO with high conductivity and optical transparency have been applied to solar cells[1, 2] , surface acoustic wave devices[3] , transparent conducting materials[4], and gas sensors [5] . A variety of techniques, including sputtering[6] , chemical vapor deposition (CVD) [7], and metallorganic -CVD technique(MOCVD)[8,9]. To obtain uniform films of ZnO at high deposition rates and low temperature of growth, we have studied laser induced MOCVD technique with double-beams. The transparent photoconductive property of these films are reported in this paper.

2-EXPERIMENTS

The experimental arrangement for photodepositing the ZnO film is shown in Fig.1.

Fig.1 Experimental arrangement: 1.photon source 2.reactant gases
3.power meter 4.substrate 5.reactor 6.to vacuum pump

Using purity dimethyl zinc (DMZ) as a zinc source $\text{He-N}_2\text{O}$ mixture as the carrier gas, excimer laser $\lambda = 266\text{nm}$ as photon source, the pressure in the reactor is 2 Torr, on glass and mica substrates, at room temperature to 240°C . The substrate is placed on a temperature controlled heater. The nonstoichiometric (Oxygen-deficient) zinc oxide (ZnO_{1-x}) polycrystalline films are formed when the temperature of the substrate is between $80-240^\circ\text{C}$. The irradiation of focused laser beam parallel and perpendicular to substrate surface. These ZnO_{1-x} films (thickness $50-200\text{ nm}$) with lower resistivities and higher optical transmission are obtained at deposition rate 300 nm/min . The films are characterized by SEM, RED and UV spectrometry. The results are shown in the Fig.2.3.4. The opposite intensity of XRD line are listed in table 1.

(a)

(b)

Fig.2 SEM morphology (X5.00K) of ZnO films on (111) single crystal silicon (a) grown at 220°C; (b) grown at 420°C

(a)

(b)

Fig.3 RED morphology of ZnO films on (111) single crystal silicon at 220°C. (a) polycrystalline diffractive ring; (b) the direction of the C-axis

Fig.4 The UV absorption spectrum
1--deposition rate 230nm/min
2--deposition rate 200nm/min

Fig.5 The photoconductivity of ZnO films (thickness 150nm)
A--deposition rate 230nm/min
B--deposition rate 200nm/min

TABLE 1. The opposite intensity of XRD lines

substrates*	XRD line opposite indensity				
	100	002	101	102	103
pyre	0.04	1	0.02	0.06	0.09
mica**	0.02	1	0.01	0.03	0.05

* substrates temperature 220°C

** direction <001> of the mica

3-CONCLUSIONS

The electron diffraction experiment indicates that laser induce MOCVD technique can produce uniform films at a high deposition rate (300nm/min) Fig.2. The maximum crystal orientation is along C-axis, the temperature range is 80-240°C and the best structural perfection is obtained on mica substrate and the growing direction of ZnO suits mica(Fig.3 and table 1). These films are always characterized by the presence of (002) as the strongest line(table 1). The ZnO films obtained by laser-induced MOCVD technique possess far better transparent photoconductive property (Fig.4-5), higher deposition rate and lower temperature of growth than obtained by other methods.

REFERENCE

- [1] MENNER R.,DIMMLER B.,MAUCH R.H. and SCHOCK H.W.,
J.Cryst.Growth 86(1988)906.
- [2] YOO J.B.,FAHRENBRUCH A.L.,and BUBE R.H.,J.Appl.Phys. 68(1990)4694.
- [3] LEE C.T.,SU Y.K. and CHEN S.L., J.Cryst.Growth 96(1989)785.
- [4] IGASAKI Y.and SAITO H., J.Appl.Phys. 70(1991)3613.
- [5] PIZZINI S.,BUTTA N.,NARDUCCI D.and PALLADIND M.,
J.Electrochem.Soc. 136(1989)1945.
- [6] BANERJEE A.,WOLF D.,YANG J. and GUHA S.,J.Appl.Phys. 70(1991)1692.
- [7] SHIMIZU M.,SHIOSAKI T. and KAWABATA A., J.Cryst.Growth 57(1982)94.
- [8] SOULETIE P.,BETHKE S.,WESSELS B.W. and PAN H.,
J.Cryst.Growth 86(1988)248.
- [9] KIM J.S.,MARZOUK H.A.,REUCROFT P.J. and HAMRIN C.E.,
Thin Solid Films 217(1992)133.