Experimental Evidence of Kink Relaxation and Kink Resonance in Dislocations of FCC Metals

A.O. Moreno-Gobbi, J.A. Eiras*, M.A. Marotti and A. Ghilarducci**

Inst. de Física, Fac. de Ciencias, Tristán Narvaja 1674, CP 11200, Montevideo, Uruguay

** Centro Atómico CC 439, 8400 Bariloche RN, Argentina*

*** Dept. Física, UFSCar-Rod, Washington Luiz km 235, CEP 13565-905, São Carlos SP, Brazil*

Abstract. Many papers have been devoted to the motion of dislocation lines in crystals. The string model and the kink model presented the most relevant theoretical approach. However, each model independently can not describe all experimental data. In this paper is presented experimental data of logarithmic decrement associated to dislocation lines, measured in Hz and MHz ranges, on high purity copper single crystals plastically deformed by compression and torsion at room temperature. The experimental data obtained for the Bordoni Peak, analyzed on the basis of the kink model, shows the predicted temperature dependence of the effective enthalpy, a evidence of the kink diffusion mechanism. The data can be well fitted over all temperature range investigated, assuming the contribution of kink relaxation and kink resonance aging simultaneously. From the last mechanism a temperature dependent kink density is assumed. This procedure allows to explain the width and the asymmetry of the Bordoni peak.

1. INTRODUCTION

The high asymmetry and the great width of the Bordoni Peak (BP) [1] compared to a Debye one are two relevant characteristics of the BP. Moreno-Gobbi and Eiras [2] proposed that the asymmetry of the BP may be due to the contributions of two different dislocation mechanisms: kink relaxation (with a Debye relaxation time) and overdamped kink resonance. But the width of the fitted peaks remains lower than the experimental peaks.

In this paper we propose that the large width of the high frequency BPs may be understood considering the relaxation time calculated by Seeger [4] using the diffusion theory of kink-pair formation in dislocations. The most relevant theoretical characteristic of this mechanism is the existence of an effective kink pair creation enthalpy which is temperature dependent.

This paper presents an Arrhenius plot with data obtained from BPs measurements at Hz and MHz frequencies, on samples cut from the same original crystal and also submitted to identical thermal treatment. Completing the frequency range, all other measurements on copper samples reported in the literature were included to complete the frequency range.

The interpretation of high frequency (10 to 50MHz) logarithmic decrement obtained from ultrasonic attenuation measured on a sample of high purity crystalline copper plastically deformed in 5% at room temperature, was done in terms of a superposition of kink relaxation and kink resonance were done, considering Seeger's model of creation of kink-pairs submitted to kink-diffusion, and kink-resonance with a temperature dependent kink density.

2. THEORETICAL CONSIDERATIONS

In Seeger's model [4] the Bordoni relaxation is due to the thermally activated formation of kink-pairs submitted to diffusion, with the relaxation time

$$\tau = \frac{k_B L}{\pi w_k H_k D_k} \frac{T (1 + \rho_k^{eq} L / 2)}{(\rho_k^{eq})^2} \quad (1)$$

where L = average free length of segment of the dislocation line; w_k = kink width; H_k = half the formation activation enthalpy of kink-pairs; D_k = kink diffusion coefficient and ρ_k^{eq} = average density of kinks in thermal equilibrium on the dislocation. For temperatures above the value $\theta_D 2a/\pi$ $w_k = 44$ K ($\theta_D = 343$ K = Debye temperature of copper; a = interatomic distance in the dislocation line), it can be applied the high temperature approximation for ρ_k^{eq}

$$\rho_k^{eq,ht} = \frac{1}{w_k} \left(\frac{2\pi H_k}{2k_B T} \right)^{1/2} \exp\left(\frac{-H_k}{k_B T}\right) \quad (2)$$

A relevant consequence of this relaxation time is the existence of an equivalent creation enthalpy H_{eff} which is temperature dependent

$$H_{eff} = \frac{d \ln \tau}{d(1/k_B T)} \quad (3)$$

At measurements with high frequency ultrasonic waves, the Bordoni peak will be in the high temperature region (120 to 170K). As a consequence of eqs (1-2), at high temperatures ($\rho L / 2 \gg 1$) the relaxation time is

$$\tau = (L^2 w_k / 4a^2 S_d D_k) (k_B T)^{3/2} \exp(H_k/k_B T) \quad (4)$$

This expression for τ means that at high frequencies the BP relaxation becomes wider than a Debye peak (DP). This fact is very important considering that at high frequencies the BPs are widened in about 2.5 times a DP [3].

On dislocation lines at little angles with Peierls valleys geometrical kinks must be present. Suzuki and Elbaum [5] proposed that resonance of these kink chain may occur. Alefeld [6] pointed out that those chains may have a density of kinks which is a function of temperature. Above certain critical temperature T_C (≈ 150 K for copper, considering 15 geometrical kinks in the dislocation line) the thermal kinks will also be created with a zero applied stress, contributing to the resonance component with a temperature dependent density. Moreno-Gobbi and Eiras showed that the addition of the resonance mechanism to relaxation allows to explain the large asymmetry of the BP [2].

For the simultaneous contributions of relaxation and resonance mechanisms [2], the general expression for the logarithmic decrement is

$$\begin{aligned} \delta &= \Delta_B \omega \tau / [1 + (\omega \tau)^2] + A_1 N_k(T) B(T) \omega + \delta_0 = \\ &= \Delta_B \omega \tau / [1 + (\omega \tau)^2] + A_2 T^2 + \delta_0 \end{aligned} \quad (5)$$

$$\tau = A_2 (k_B T)^{3/2} \exp(H_k/k_B T) \quad (6)$$

where Δ_B = Bordoni relaxation intensity; A_1 and A_2 = constants which depend on the material and the dislocation structure, $N_k(T)$ = density of kinks participating in the resonance process, ω = wave angular frequency and δ_0 = constant. For the resonance component an overdamped process is considered, where $N_k(T) \propto T$ [2] and $B(T) \propto T$ [7], and the low frequency approximation ($\omega \ll \omega_{res}$, resonance frequency) is used [2].

3. EXPERIMENTAL DATA AND DISCUSSION

Attenuation measurements were made by the pulse-echo method [8], cooling the sample between 5K and 373K at a maximum rate of one degree per minute, on a high purity crystalline copper sample deformed plastically in 5% in the [111] direction. Measurements were obtained at 10, 30 and 50 MHz.

For low frequency internal friction measurements, a sample of 19.55 x 2.45 x 0.90 mm cut from the same crystal of the ultrasonic samples was used. Also this sample was prepared in an identical way as the ultrasonic samples. Measurements at 5 to 20Hz were obtained with a subresonant torsion pendulum and are reported in another paper [9].

In fig.1 an Arrhenius plot with all copper temperature peaks obtained from the literature [3,7] and those obtained from our samples is shown. In this plot the fitted curve with the model of eqs. (1) and (2) is shown, finding a very good agreement with experimental data. From the parameters of the fitted curve we obtained $D_k \approx 2,91 \text{ cm}^2/\text{s}$, $w_k/L \approx 2 \cdot 10^{-3}$ and $H_k \approx 0.075 \text{ eV}$. The value of D_k is not yet reported, but the other data are in very good agreement with the expected data from the literature. This fact contributes to the confirmation of the diffusion process controlling kink mobility, a fact which do not have yet an experimental confirmation [10].

Fig. 1. Dots: Arrhenius plot for data measured on samples cut from the same original copper crystal, in the Hz and MHz range. Experimental data of copper from other authors are also included, specially at intermediate frequencies. Full line: fitted curve using equations (2) and (3), with $H_k = 0.074 \text{ eV}$, $L = 10^4 a$, $w_k = 20a$ and $a = 5 \cdot 10^{-8} \text{ cm}$.

In figures 2(a) and 2(b) experimental data (dots) of logarithmic decrement in the temperature range from 373 to 80K, measured at 30 and 50 MHz in a 5% deformed sample are shown. The line curves are the fitted curves obtained with the model proposed for δ , equations (5) and (6). Because the second BP modifies the δ -curves below 80K, this region was not considered in the fits and were omitted in the figures. The coefficients obtained from the Arrhenius fit were employed in the logarithmic decrement fitting equation, and a relaxation strength of 2.1×10^{-3} was obtained from the fitted curves.

The good agreement obtained in fitting the experimental data shows that they can be interpreted in terms of the two mechanisms proposed. The overdamped resonance mechanism is very important in the interpretation of modulus defect at temperatures above peak temperature, as Moreno-Gobbi and Eiras recently pointed out [2] and also it results very important in the interpretation of the high temperature side of the BP. The Seeger's theory with kink diffusion is particularly interesting to explain the great width of the Bordoni peak at MHz frequencies.

Fig.2(a) Dots: Logarithmic decrement measured at 30 MHz on a high purity crystalline copper sample plastically deformed at room temperature in 5%. Line: fitted curve obtained with the contribution of relaxation and kink-resonance mechanisms, equations (5) and (6)..

Fig.2(b) Dots: Logarithmic decrement measured at 50 MHz on the same sample of fig. 2(a). Line: fitted curve obtained with the contribution of relaxation and kink-resonance mechanisms, equations (5) and (6)..

4. CONCLUSIONS

The logarithmic decrement in crystalline copper samples was investigated at Mhz frequencies. The samples were oriented in the $\langle 111 \rangle$ crystallographic direction and plastically deformed in 5%. The data were fitted considering the simultaneous contributions of two different dislocation mechanisms: overdamped kink-resonance and kink-relaxation. A linear temperature dependence of kink density was assumed for the kink resonance in the temperature range considered. The Bordoni relaxation was described considering the kink pairs creation process submitted to a diffusion process. An effective activation enthalpy of 0.075 eV was obtained from an Arrhenius plot fitted with the same relaxation model. Also the relaxation intensity and the diffusion coefficient were obtained, being 2.1×10^{-3} and $2.91 \text{ cm}^2/\text{s}$ respectively. The fitted curves shows that the diffusion mechanism proposed in the kink-pair creation process is experimentally supported. Also an overdamped resonance mechanism is necessary in order to fit the high temperature side of the BPs, especially those measured at high frequencies.

References

- [1] Bordoni, P. G., *Ric. Sci.*, **19** (1949) 851.
- [2] Moreno-Gobbi, A. and Eiras, J. A., *Journal Alloys and Compounds*, **211-212** (1994) 152.
- [3] Moreno-Gobbi, A. and Eiras, J.A., *Mater. Sci. Forum*, **119-120** (1993) 189
- [4] Seeger, A., *J. Physique*, **42** (1981) C5-201.
- [5] Suzuki, T., Elbaum, C., *J. Appl. Phys.*, **35** (1964) 1539.
- [6] Alefeld, G., Chambers, R. H. and Firlie, T. E., *J. Appl. Phys.*, **36** (1965) 2642.
- [7] Niblett, D. H., Bordoni Peak in Face Centered Cubic Metals, in *Physical Acoustics*, ed. by W. P. Mason Vol. IIIA, Part A, Academic Press, New York, 1966.
- [8] Papadakis, E.P., in *Physical Acoustics*, de. by R.N. Thurston and A.D. Pierce, Vol. XIX, Academic Press, New York, 1990.
- [9] Ghilarducci, A., Moreno-Gobbi, A., Marotti, M. and Eiras, J. A. *Proceedings from 11 ICIFUAS*, France, 1996.
- [10] Richie, Y., Fantozzi, G., *Internal Friction due to the Intrinsic Properties of Dislocations in Metals: Kink Relaxation*, in *Dislocations in Solids*, ed. by F.R.N. Nabarro, chap.45, Elsevier Sci. Publ., 1992.