Neutron study of Al or Mn substituted LaNi₅ hydrogen sponges

J. Achard, F. Givord, A. Percheron-Guegan, J. Soubeyroux, F. Tasset

► To cite this version:

J. Achard, F. Givord, A. Percheron-Guegan, J. Soubeyroux, F. Tasset. Neutron study of Al or Mn substituted LaNi₅ hydrogen sponges. *Journal de Physique Colloques*, 1979, 40 (C5), pp.C5-218-C5-220. 10.1051/jphyscol:1979582 . jpa-00218999

HAL Id: jpa-00218999

<https://hal.science/jpa-00218999>

Submitted on 1 Jan 1979

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Neutron study of Al or Mn substituted LaNi_5 hydrogen sponges

J. C. Achard (*), F. Givord (**), A. Percheron-Guegan (*), J. L. Soubeyroux (***) and F. Tasset (***)

(*) ER 209 C.M.S. Terres Rares, 92190 Bellevue Meudon, France

(**) Laboratoire Louis-Néel, 166X, 38042 Grenoble Cedex, France

(***) ILL, 156X, 38042 Grenoble Cedex, France

Résumé. — La diffraction des neutrons montre que les substitutions de Al et Mn occupent principalement le site 3g dans LaNi_5 . La largeur anormale des raies de diffraction du composé LaNi_5 activé montre que les grains sont subdivisés en filaments. Cette anomalie disparaît pour les composés substitués.

Abstract. — Neutron diffraction measurements show that substituted Al and Mn atoms occupy mainly the 3g site in LaNi_5 . The anomalous width of *activated* LaNi_5 diffraction lines shows that the grains are subdivided into filaments. These anomalies disappear for substituted compounds.

1. Introduction. — Partial substitution of La or Ni changes the equilibrium pressure of the related reversible hydride [1] proportionally to the primary intermetallic cell volume change [2, 3]. Little evidence has been obtained to date about the action of such substitution on the hydrogen content. Following already published neutron diffraction [4, 5] and NMR [6, 7] results for the non substituted LaNi_5H_6 , the aim of our work is to determine the position of the substitutions and the hydrogen sites in substituted compounds.

2. Sample characterization. — Intermetallic compounds were prepared as described in ref. [8]. Upper limits for substitutions correspond to $\text{LaNi}_{3.8}\text{Al}_{1.2}$ and $\text{LaNi}_{2.7}\text{Mn}_{2.3}$. Homogeneous *activated* powder (5-15 μ particle size) was obtained after several absorption-desorption hydrogen cycles (40 bar at

40 °C). Shown on figure 1 are typical composition isotherms determined as explained in ref. [9]. The replacement of hydrogen by deuterium does not change the capacity of the β phase.

3. Crystal structure and grain size of intermetallic compounds. — **3.1 EXPERIMENTAL.** — D1A and D1B multidetector powder diffractometer of the Institut Laue Langevin were used for neutron measurements. Scattering by the 1 mm thick quartz container was easy to correct for. The deuterium pressure (0-10 bar) applied to the sample was continuously monitored.

3.2 LaNi_5 ALLOY. — An obvious broadening of $hk0$ lines relative to the instrument resolution of the D1A diffractometer was detected. This indicates a lack of long range coherence in the (a, b) crystalline plane. On the contrary the narrower width of $00l$ diffraction lines shows that there is coherence along the C axis leading to a very anisotropic, filament like, metallic sponge model for these *activated* grains. Complementary high resolution X-ray measurements are being made on this interesting phenomenon. Intensities of individual reflections were determined by fitting gaussian peak shapes and from these the structure was refined. The $\text{P6}_3/\text{mm}$ space group with La atoms on 1a site and Ni atoms on 2c and 3g sites leads to an R -factor of 2.9 %, the stoichiometric effect being reflected in the replacement of 2 % La by pairs of Ni in 2e positions [table I], [10].

3.3 $\text{LaNi}_{5-x}\text{M}_x$ ALLOYS ($\text{M} = \text{Al}, \text{Mn}$; $0.5 < x < 2$). — The breadth of diffraction lines found is normal so that the standard profile refinement technique [11] can be used. The same $\text{P6}_3/\text{mm}$ space group leads to the results of table I. The M atoms exhibit a strong

Fig. 1. — Comparison of absorption-desorption isotherms for LaNi_5 , LaNi_4Al at 25 °C and LaNi_4Mn , LaNi_4Al at 60 °C.

Table I. — *Intermetallic compounds* $\text{LaNi}_{5-x}\text{M}_x$

Comp.	$\text{La}_{1-s}\text{Ni}_{5+2s}$	$\text{LaNi}_{4.5}\text{Al}_{0.5}$	LaNi_4Al	$\text{LaNi}_{4.5}\text{Mn}_{0.5}$	LaNi_4Mn	LaNi_3Mn_2
a (Å)	5.017(1)	5.031(1)	5.063(1)	5.042(1)	5.096(1)	5.162(1)
c (Å)	3.993(2)	4.019(1)	4.063(1)	4.014(1)	4.075(1)	4.135(1)
s_{La}	0.020(3)	0.036(7)	0.024(8)	0.027(7)	0.021(6)	0.016(6)
s_1 ($z = 0$)		0.08(6)	0.12(8)	0.06(2)	0.23(5)	0.28(3)
s_2 ($z = \frac{1}{2}$)		0.42(9)	0.94(10)	0.40(3)	0.90(5)	1.62(2)
B_{La}	1.0(2)	0.75(20)	0.87(25)	0.70(14)	1.35(25)	0.6(2)
B_{Ni}	0.8(1)	0.6(1)	0.5(1)	0.6(1)	0.66(7)	0.90(15)
B_{M}		0.6(1)	0.5(1)	0.6(1)	0.66(7)	0.90(15)
Final Comp.	La Ni	La Ni Al	La Ni Al	La Ni Mn	La Ni Mn	La Ni Mn
	0.98 5.04	0.96 4.58 0.5	0.98 3.98 1.06	0.97 4.6 0.46	0.98 3.9 1.13	0.98 3.14 1.9
Residu	2.9 %	5.6 %	8.6 %	6.0 %	8.4 %	8.9 %

Table II. — *Hydrides of intermetallic compounds*

LaNi ₄ MnD ₆		a (Å) = 5.437(2)		c (Å) = 4.332(2)		
		Final composition : La _{0.98} Ni _{3.9} Mn _{1.13} D _{5.97} Residu : 8.1 %				
		Thermal B (Å ²) La : 2.1(2) Ni, Mn : 1.3(1) D : 4.0(4)				
D site :		3f	4h	6m	12n	12o
x		0.5	0.33	0.133(1)	0.452(6)	0.227(3)
y		0.0	0.66	0.266(2)	0.0	0.454(6)
z		0.0	0.38(1)	0.5	0.117(9)	0.38(1)
n		0.59(5)	0.33(3)	1.92(9)	2.11(9)	1.02(8)
LaNi ₄ AlD ₄		a (Å) = 5.310(2)		c (Å) = 4.249(2)		
		Final composition : La _{0.98} Ni _{3.98} Al _{1.06} D _{4.8} Residu : 2.5 %				
		Thermal B (Å ²) La : 2.0 Ni, Mn : 1.2 D : 2.9				
D site :		3f	6m	12n	12o	
x		0.5	0.132(2)	0.438(6)	0.233	
y		0.0	0.264(4)	0.0	0.466	
z		0.0	0.5	0.112(5)	0.34	
n		0.13	1.88	2.64	0.46	

preference for the 3g site (amount S_2) relative to the 2c site (amount S_1). There is no obvious difference in the behaviour of Al and Mn atoms.

4. Crystal structure of substituted $\text{LaNi}_{5-x}\text{M}_x\text{D}_y$ hydrides. — Deuterides were used to reduce neutron incoherent scattering. Using the Rietveld technique we have found possible structures for $\text{LaNi}_4\text{MnD}_6$

Fig. 2. — Neutron diffractogram of LaNi_5 ($D1A : \lambda = 1.909$ Å).

and $\text{LaNi}_4\text{AlD}_4$ [table II]. Although deuterium atoms are widely distributed on possible sites in qualitative agreement with NMR results [8, 9], some preference exists for the 6m site.

5. Conclusion. — We have determined the crystal structure of LaNi_5 and substituted Al and Mn alloys. An interesting difference appears to be the existence

of subgrains in activated LaNi_5 which could be of some importance in rapid hydrogen uptake. We found no obvious correlation between changes of crystal structure and hydrogen content. Complementary X-ray and neutron diffraction measurements are now being made and should help for a better understanding of this interesting class of substituted compounds.

Reference

- [1] ZIJLSTRA, H. and WESTENDROP, F., *Solid State Commun.* **7** (1969) 857.
- [2] VAN VUCHT, J. H. N., KUIJPERS, F. A., BRUNING, H. C., *Philips Res. Reports* **25** (1970) 133.
- [3] VAN MAL, H. H., BUSCHOW, K. H. J., MIEDEMA, A. R., *J. Less-Common Met.* **35** (1974) 65.
- [4] BOWMAN, A. L., ANDERSON, J. L., NERESON, N. G., Proceedings Tenth Rare Earth Res. Conf. Carefree Arizona (1973) 485.
- [5] FISCHER, P., FURRER, A., BUSCH, G., SCHLAPBACH, L., *Helv. Phys. Acta* **50** (1977) 421.
- [6] HALSTEAD, T. K., *J. Solid State Chem.* **11** (1974) 114.
- [7] BARNES, R. G., HARPER, W. C., NELSON, S. O., Meeting Hydrogen in Metals, Birmingham 1976.
- [8] PERCHERON-GUEGAN, A., SCHLAPBACH, L., ACHARD, J. C., SARRADIN, J., BRONOËL, G., Société Chimique de France, septembre 1974.
- [9] ACHARD, J. C., PERCHERON-GUEGAN, A., DIAZ, H., Proceedings of 2nd International Congress Hydrogen in Metals, Paris France **8** (1977) 1E12.
- [10] TASSET, F., Thesis no. A.O. 10916 Grenoble (1975).
- [11] RIETVELD, H. M., *Acta Cryst.* **22** (1967) 151.