The crystal structure of K₂FeF₅

Marcus Vlasse, G. Matejka, Alain Tressaud, B. M. Wanklyn

► To cite this version:

Marcus Vlasse, G. Matejka, Alain Tressaud, B. M. Wanklyn. The crystal structure of K₂FeF₅. Acta crystallographica Section B: Structural crystallography and crystal chemistry, 1977, 33 (11), pp.3377-3380. 10.1107/S0567740877011030 . hal-00156618

HAL Id: hal-00156618

<https://hal.science/hal-00156618>

Submitted on 21 Jun 2007

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Acta Crystallographica Section B

**Structural
Science**

ISSN 0108-7681

Editor: **Carolyn P. Brock**

The crystal structure of K_2FeF_5

M. Vlasse, G. Matejka, A. Tressaud and B. M. Wanklyn

Copyright © International Union of Crystallography

Author(s) of this paper may load this reprint on their own web site provided that this cover page is retained. Republication of this article or its storage in electronic databases or the like is not permitted without prior permission in writing from the IUCr.

The Crystal Structure of K_2FeF_5

BY M. VLASSE, G. MATEJKA AND A. TRESSAUD

*Laboratoire de Chimie du Solide du CNRS, Université de Bordeaux I, 351 cours de la Libération,
33405 Talence CEDEX, France*

AND B. M. WANKLYN

Clarendon Laboratory, University of Oxford, Oxford, England

(Received 17 March 1977; accepted 22 April 1977)

The structure of K_2FeF_5 has been refined for 1088 counter intensities to $R = 0.048$. It is orthorhombic, space group $Pn2_1a$, with $a = 20.39$ (1), $b = 7.399$ (5), $c = 12.84$ (1) Å, $Z = 16$. The structure is made up of infinite zigzag *cis* chains of FeF_6 octahedra with common corners running along *a*. One-dimensional magnetism may be predicted for this compound.

Introduction

The fluorides of transition metals are of interest because of their physical properties and the diversity of their structures. Anderson (1963) and Goodenough (1963) showed that the magnetic couplings in these fluorides are primarily by superexchange which facilitates the magnetic study and the establishment of relationships between structure and properties.

The study of fluorides with a general formula $A_xM_yF_z$, where *A* is a monovalent cation and *M* a 3d transition element, and in particular of the systems $AF-FeF_3-FeF_2$ (*A* = Li, Na, K, Rb, Tl) has allowed the derivation of a structural classification explaining their magnetic properties (Portier, Tressaud, de Pape & Hagenmuller, 1968; Tressaud, Portier, de Pape & Hagenmuller, 1970). In this classification the phases $AFFe_3$ have three-dimensional octahedral lattices, the phases $A_3Fe_2F_7$ are composed of double layers of octahedra, the phases $AFFe_4$, A_2Fe_4 and $A_5Fe_3F_{14}$ are made up of single octahedral sheets, and the phases A_2FeF_5 have octahedral chain structures. The study of $Na_5Fe_3F_{14}$ has brought about a partial verification of this classification (Vlasse, Menil, Moriliere, Dance, Tressaud & Portier, 1976; Tressaud, Dance, Vlasse & Portier, 1976). The structural determination of K_2FeF_5 will further check this systematic description and allow a better explanation of the magnetic properties.

Experimental

Specimen preparation

Single crystals were prepared by the flux method in a fluorinating atmosphere. The synthesis was carried out in a Pt crucible containing $PbCl_2$, KF and FeF_3 . This mixture was raised to 650°C and then cooled to

330°C at the rate of 1.5°C h⁻¹. Colourless transparent crystals were obtained with a maximum size of 4 × 3 × 3 mm. Their powder pattern was similar to those of K_2CrF_5 and K_2GaF_5 (Wanklyn, 1975).

Table 1. Atomic coordinates ($\times 10^4$) and isotropic temperature factors for K_2FeF_5 , with standard deviations in parentheses

	<i>x</i>	<i>y</i>	<i>z</i>	<i>B</i> (Å ²)
Fe(1)	4224 (3)	34 (15)	2505 (6)	0.42 (5)
Fe(2)	3294 (3)	6744 (6)	521 (6)	0.79 (6)
Fe(3)	1721 (4)	0	544 (6)	0.78 (6)
Fe(4)	783 (4)	6661 (16)	2534 (7)	1.27 (7)
K(1)	43 (5)	8483 (18)	176 (9)	1.56 (9)
K(2)	1662 (4)	4732 (13)	420 (7)	1.11 (7)
K(3)	850 (4)	1703 (15)	2791 (6)	0.99 (6)
K(4)	2511 (6)	3453 (17)	3224 (3)	0.84 (7)
K(5)	4181 (5)	4880 (17)	2632 (7)	1.51 (8)
K(6)	2483 (9)	8325 (30)	2877 (4)	1.76 (9)
K(7)	4914 (4)	8240 (17)	187 (8)	0.96 (8)
K(8)	3394 (5)	1785 (15)	339 (8)	1.72 (9)
F(1)	2211 (10)	256 (30)	4636 (15)	1.42 (17)
F(2)	2015 (13)	1273 (39)	1787 (21)	2.39 (24)
F(3)	4600 (12)	1180 (35)	1331 (20)	0.50 (20)
F(4)	3494 (14)	1652 (39)	2349 (20)	3.89 (30)
F(5)	4721 (9)	1560 (31)	3378 (15)	0.77 (13)
F(6)	977 (9)	1555 (14)	484 (16)	1.62 (17)
F(7)	1379 (14)	3160 (40)	4453 (25)	2.50 (29)
F(8)	3584 (11)	3340 (32)	4507 (20)	1.34 (17)
F(9)	4041 (12)	5440 (39)	488 (23)	2.84 (14)
F(10)	1521 (10)	5263 (28)	2463 (17)	0.34 (14)
F(11)	322 (13)	5147 (22)	3442 (24)	2.81 (30)
F(12)	416 (15)	5657 (41)	1263 (24)	3.29 (31)
F(13)	2784 (10)	6191 (29)	4491 (15)	1.07 (16)
F(14)	2444 (8)	8157 (24)	721 (8)	0.90 (12)
F(15)	4989 (10)	8343 (34)	2388 (15)	0.97 (11)
F(16)	3721 (4)	8397 (44)	1581 (23)	3.25 (31)
F(17)	1210 (9)	8436 (28)	1519 (15)	0.41 (13)
F(18)	3882 (14)	8819 (38)	3623 (21)	2.55 (28)
F(19)	1104 (12)	8241 (35)	3577 (18)	1.44 (21)
F(20)	2959 (14)	5403 (41)	1598 (23)	1.58 (26)

Single-crystal diffraction data

Weissenberg and precession photographs indicate orthorhombic Laue symmetry mmm . The systematic extinctions, $0kl$: $k + l = 2n$ and $hk0$: $h = 2n$, are consistent with space groups $Pn2_1a$ and $Pnma$. The lattice parameters refined from single-crystal data are $a = 20.39$ (1), $b = 7.399$ (5), $c = 12.84$ (1) Å. The cell contains 16 formula units [$d_x = 3.16$ (2), $d_c = 3.14$ g cm^{-3}].

A single crystal in the form of a rectangular block

$0.07 \times 0.09 \times 0.16$ mm was mounted about **b**. The intensities were collected on an Enraf-Nonius CD-3 three-circle automatic diffractometer with Mo $K\alpha$ radiation ($\lambda = 0.70942$ Å), a pyrolytic graphite monochromator (002) and a 4° take-off angle. A scintillation counter and a θ - 2θ multiple scanning technique with a scan rate of 10° (2θ) min^{-1} were used. The background was taken at each end of the scan range for a time equal to the actual scan time. Three control reflexions measured for every batch of 50 reflexions showed a random fluctuation of about 6%.

Table 2. *Interatomic distances (in Å ± 0.009 Å) and bond angles [in ($^\circ$) $\pm 0.1^\circ$] for K_2FeF_5*

Fe(1)—F(3)	1.892	Fe(2)—F(1 <i>b</i>)	1.888	Fe(3)—F(2)	1.948	Fe(4)—F(10)	1.828
Fe(1)—F(4)	1.921	Fe(2)—F(7 <i>b</i>)	1.850	Fe(3)—F(6)	1.906	Fe(4)—F(11)	1.870
Fe(1)—F(5)	1.886	Fe(2)—F(9)	1.804	Fe(3)—F(8 <i>c</i>)	1.915	Fe(4)—F(12)	1.943
Fe(1)—F(15 <i>a</i>)	2.005	Fe(2)—F(14)	2.040	Fe(3)—F(13 <i>c</i>)	1.903	Fe(4)—F(15 <i>d</i>)	2.044
Fe(1)—F(16 <i>a</i>)	1.982	Fe(2)—F(16)	2.026	Fe(3)—F(14 <i>a</i>)	2.021	Fe(4)—F(17)	2.045
Fe(1)—F(18 <i>a</i>)	1.832	Fe(2)—F(20)	1.834	Fe(3)—F(17 <i>a</i>)	1.998	Fe(4)—F(19)	1.894
⟨Fe(1)—F⟩	1.920	⟨Fe(2)—F⟩	1.907	⟨Fe(3)—F⟩	1.949	⟨Fe(4)—F⟩	1.937
K(1)—F(5 <i>e</i>)	3.008	K(2)—F(1 <i>b</i>)	2.539	K(3)—F(2)	2.721	K(4)—F(1)	3.042
K(1)—F(5 <i>b</i>)	2.757	K(2)—F(2)	3.186	K(3)—F(3 <i>d</i>)	2.814	K(4)—F(2)	2.651
K(1)—F(6 <i>f</i>)	2.991	K(2)—F(6)	2.736	K(3)—F(5 <i>d</i>)	2.750	K(4)—F(4)	2.656
K(1)—F(6 <i>g</i>)	2.662	K(2)—F(8 <i>b</i>)	2.958	K(3)—F(6)	2.976	K(4)—F(7)	2.804
K(1)—F(8 <i>b</i>)	2.931	K(2)—F(10)	2.668	K(3)—F(7)	2.623	K(4)—F(8)	2.740
K(1)—F(12)	2.624	K(2)—F(12)	2.845	K(3)—F(10)	2.998	K(4)—F(10)	2.612
K(1)—F(12 <i>g</i>)	2.625	K(2)—F(13 <i>c</i>)	3.092	K(3)—F(11)	2.890	K(4)—F(13)	2.657
K(1)—F(15 <i>d</i>)	3.128	K(2)—F(14)	3.019	K(3)—F(15 <i>h</i>)	3.052	K(4)—F(14 <i>i</i>)	3.215
K(1)—F(17)	2.937	K(2)—F(18 <i>c</i>)	2.648	K(3)—F(17 <i>a</i>)	3.008	K(4)—F(20)	2.697
K(1)—F(18 <i>d</i>)	2.834	K(2)—F(20)	3.087	K(3)—F(19 <i>a</i>)	2.801	⟨K(4)—F⟩	2.786
⟨K(1)—F⟩	2.850	⟨K(2)—F⟩	2.878	⟨K(3)—F⟩	2.863		
K(5)—F(4)	2.793	K(6)—F(1 <i>f</i>)	2.729	K(7)—F(3 <i>f</i>)	2.702	K(8)—F(1 <i>b</i>)	2.989
K(5)—F(5)	2.857	K(6)—F(2 <i>f</i>)	2.762	K(7)—F(3 <i>k</i>)	2.665	K(8)—F(3)	2.805
K(5)—F(8)	2.929	K(6)—F(10)	3.044	K(7)—F(7 <i>b</i>)	2.800	K(8)—F(4)	2.591
K(5)—F(9)	2.799	K(6)—F(13)	2.677	K(7)—F(9)	2.759	K(8)—F(7 <i>c</i>)	2.950
K(5)—F(11 <i>j</i>)	2.712	K(6)—F(14)	2.772	K(7)—F(9 <i>i</i>)	2.818	K(8)—F(9)	3.015
K(5)—F(12 <i>j</i>)	2.947	K(6)—F(16)	3.024	K(7)—F(11 <i>j</i>)	3.005	K(8)—F(13 <i>c</i>)	2.674
K(5)—F(15)	3.062	K(6)—F(17)	3.128	K(7)—F(11 <i>b</i>)	2.691	K(8)—F(16 <i>a</i>)	3.045
K(5)—F(16)	3.078	K(6)—F(18)	3.031	K(7)—F(15)	2.831	K(8)—F(19 <i>c</i>)	2.707
K(5)—F(20)	2.850	K(6)—F(19)	2.953	K(7)—F(16)	3.022	⟨K(8)—F⟩	2.847
⟨K(5)—F⟩	2.892	K(6)—F(20)	2.883	K(7)—F(19 <i>j</i>)	2.900		
		⟨K(6)—F⟩	2.900	⟨K(7)—F⟩	2.819		
F(3)—Fe(1)—F(18 <i>a</i>)	177.1	F(9)—Fe(2)—F(20)	92.5	F(11)—Fe(4)—F(17)	174.9		
F(4)—Fe(1)—F(15 <i>a</i>)	169.7	F(7 <i>b</i>)—Fe(2)—F(14)	96.3	F(12)—Fe(4)—F(19)	164.3		
F(5)—Fe(1)—F(16 <i>a</i>)	178.6	F(7 <i>b</i>)—Fe(2)—F(16)	90.1	F(15 <i>d</i>)—Fe(4)—F(10)	177.0		
F(15 <i>a</i>)—Fe(1)—F(18 <i>a</i>)	92.8	F(14)—Fe(2)—F(16)	88.3	F(11)—Fe(4)—F(10)	96.1		
F(16 <i>a</i>)—Fe(1)—F(18 <i>a</i>)	88.4	F(2)—Fe(3)—F(8 <i>c</i>)	168.4	F(11)—Fe(4)—F(12)	95.8		
F(16 <i>a</i>)—Fe(1)—F(15 <i>a</i>)	88.6	F(13 <i>c</i>)—Fe(3)—F(17 <i>a</i>)	171.8	F(10)—Fe(4)—F(12)	93.4		
F(3)—Fe(1)—F(15 <i>a</i>)	87.2	F(6)—Fe(3)—F(14 <i>a</i>)	173.1	F(15 <i>d</i>)—Fe(4)—F(17)	88.7		
F(3)—Fe(1)—F(5)	89.3	F(2)—Fe(3)—F(6)	89.2	F(15 <i>d</i>)—Fe(4)—F(19)	82.1		
F(4)—Fe(1)—F(5)	96.0	F(2)—Fe(3)—F(13 <i>c</i>)	101.2	F(17)—Fe(4)—F(19)	84.7		
F(1 <i>b</i>)—Fe(2)—F(16)	172.2	F(6)—Fe(3)—F(13 <i>c</i>)	96.5	Fe(1 <i>f</i>)—F(16)—Fe(2)	173.4		
F(7 <i>b</i>)—Fe(2)—F(20)	178.2	F(8 <i>c</i>)—Fe(3)—F(14 <i>a</i>)	83.2	Fe(2)—F(14)—Fe(3 <i>f</i>)	162.0		
F(9)—Fe(2)—F(14)	174.0	F(8 <i>c</i>)—Fe(3)—F(17 <i>a</i>)	84.0	Fe(3 <i>f</i>)—F(17)—Fe(4)	173.4		
F(1 <i>b</i>)—Fe(2)—F(9)	97.7	F(14 <i>a</i>)—Fe(3)—F(17 <i>a</i>)	85.4	Fe(1)—F(15)—Fe(4 <i>f</i>)	172.8		
F(1 <i>b</i>)—Fe(2)—F(20)	86.3						

Symmetry code

- (a) $x, y - 1, z$
 (d) $x - \frac{1}{2}, y, \frac{1}{2} - z$
 (g) $\bar{x}, y + \frac{1}{2}, \bar{z}$
 (j) $\frac{1}{2} + x, y, \frac{1}{2} - z$

- (b) $\frac{1}{2} - x, \frac{1}{2} + x, z - \frac{1}{2}$
 (e) $x - \frac{1}{2}, y + 1, \frac{1}{2} - z$
 (h) $\frac{3}{2} - x, y + \frac{1}{2}, z - \frac{1}{2}$
 (k) $1 - x, \frac{1}{2} - z, \bar{z}$

- (c) $\frac{1}{2} - x, y - \frac{1}{2}, z - \frac{1}{2}$
 (f) $x, 1 + y, z$
 (i) $\frac{1}{2} - x, y - \frac{1}{2}, \frac{1}{2} + z$
 (l) $1 - x, y + \frac{1}{2}, \bar{z}$

1179 independent reflexions were measured to a value of $2\theta_{\max} = 70^\circ$. 1088 had $I > 3\sigma(I)$, where $\sigma(I) = [\text{total counts} + \text{background}]^{1/2}$, and were considered to be observed. These intensities were corrected for Lorentz and polarization effects, but not for absorption $\{\mu[\lambda(\text{Mo } K\alpha)] = 55 \text{ cm}^{-1}\}$.

Determination and refinement of the structure

The positions of the heavy atoms were determined from a Patterson synthesis. The F atoms were located in a difference synthesis at an intermediate stage of refinement. The refinement was carried out in the noncentrosymmetric space group $Pn2_1a$ [4(a): x, y, z ; $\frac{1}{2} + x, y, \frac{1}{2} - z$; $\frac{1}{2} - x, \frac{1}{2} + y, \frac{1}{2} + z$; $\bar{x}, \frac{1}{2} + y, \bar{z}$] which was indicated by a heavy concentration of vectors on the Harker plane ($u, \frac{1}{2}, w$), as well as an acentric distribution of intensities. Full-matrix least-squares refinement (Busing, Martin & Levy, 1962) with isotropic temperature factors reduced R ($= \Sigma ||F_o| - |F_c|| / \Sigma |F_o|$) to

0.048, based on a data-to-parameters ratio of 8.5:1, with 128 independent parameters. A final $(F_o - F_c)$ synthesis confirmed the proposed solution.

$\Sigma w(|F_o| - |F_c|)^2$ was minimized with w taken as unity for all reflexions. The overall scale factor was 1.305 ($F_o = kF_c$). The form factors for K^+ , Fe^{3+} and F^- were taken from McMaster, Kerr del Grande, Mallet & Hubbel (1969), with the real and imaginary anomalous-dispersion terms given by Cromer (1965).

The final atomic and thermal parameters are given in Table 1. Table 2 contains the interatomic distances and angles. A table giving the calculated and observed structure amplitudes may be obtained on request from MV.*

* This table has also been deposited with the British Library Lending Division as Supplementary Publication No. SUP 32689 (8 pp.). Copies may be obtained through The Executive Secretary, International Union of Crystallography, 13 White Friars, Chester CH1 1NZ, England.

Fig. 1. Projection of the structure on the (010) plane.

Fig. 2. Chains of FeF_6 octahedra in K_2FeF_5 .

Description and discussion of the structure

Projections of the structure on (010) and (001) are shown in Figs. 1 and 2. The structure can be described as an assembly of infinite chains along [100] made up of octahedra sharing two of their corners. When two vertices of an octahedron are shared they can be either adjacent (*cis*) or opposite (*trans*). The sharing of two *cis* vertices leads to cyclic molecules or zigzag chains. On the other hand, a *trans* configuration leads to straight linear chains. In K_2FeF_5 we observe, in fact, zigzag *cis* chains of $[FeF_6]_n^{2n-}$. The K^+ ions with nine- or tenfold coordination are found between the chains and assure their cohesion.

The FeF_6 octahedra are regular with an average $Fe-F$ distance ranging from 1.907 to 1.949 Å for four independent Fe atoms (Table 2). This is in agreement with the sum of their ionic radii, 1.925 Å [$r_{Fe^{3+}}(VI) = 0.645$, $r_{F^{2-}}(II) = 1.28$ Å; Shannon & Prewitt, 1969]. Similar average $Fe-F$ distances were observed in $CaFeF_5$ ($Fe-F = 1.92$ Å; von der Mühl & Ravez, 1974) and in $SrFeF_5$ ($Fe-F = 1.93$ Å; von der Mühl, Daut & Ravez, 1973). However, there seems to be a clear difference between the terminal and bridging $Fe-F$ bonds. The average $Fe-F_t$, 1.882 Å, is clearly shorter than $Fe-F_b$, 2.020 Å. The same observation was made in $K_2VO_2F_3$ (Ryan, Martin & Reisfeld, 1971) where $V-F_t = 1.89$ Å and $V-F_b = 2.10$ Å, and in RhF_5 (Morell, Zalkin, Tressaud & Bartlett, 1973) where $Rh-F_t = 1.808$ Å and $Rh-F_b = 1.999$ Å. This may be considered as an electrostatic effect, which is quite normal for a highly electronegative atom such as F. The bridging $Fe-F-Fe$ angles range from 162.0 to 173.4° with an average of 170.4°. This angle is closer to the ideal angle of 180° than the minimum of 132°. The average $K-F$ distances are in general shorter than the sum of the ionic radii of 1.91 Å [$r_{K^+}(X) = 1.58$ Å]. This indicates the close-packed nature of the $[FeF_6]_n^{2n-}$ chains and K^+ ions in this structure.

The structures of a number of A_2BF_5 -type compounds have been determined, such as Tl_2AlF_5 (Brosset, 1937), $(NH_4)_2MnF_5$ (Sears & Hoard, 1969), Rb_2CrF_5 (Jacoboni, de Pape, Poulain, Le Marouille & Grandjean, 1974) and K_2SmF_5 (Bochkova, Sav'yanov, Kuz'min & Belov, 1973). Tl_2AlF_5 and $(NH_4)_2MnF_5$ are made up of linear octahedral *trans* chains held together by the Tl^+ and NH_4^+ ions in sixfold coordination. Both Rb_2CrF_5 and K_2FeF_5 possess similar octahedral zigzag *cis* chains with the cations in sixfold and nine- or tenfold coordination respectively.

The increase of the A atom coordination and the shorter $A-F$ distances in K_2FeF_5 compared with Rb_2CrF_5 imply a more compact structure, which leads us to believe that under pressure Rb_2CrF_5 will transform to a K_2FeF_5 -type structure.

The octahedral chain character of this structure allows the prediction that K_2FeF_5 will show relatively one-dimensional magnetic behaviour with a low anti-ferromagnetic transition temperature. The magnetic study is presently under way.

References

- ANDERSON, P. W. (1963). *Magnetism*, Vol. I, p. 25. London, New York: Academic Press.
- BOCHKOVA, R. I., SAV'YANOV, YU. N., KUZ'MIN, E. A. & BELOV, N. V. (1973). *Dokl. Akad. Nauk SSSR*, **212**, 357-359.
- BROSSET, C. (1937). *Z. anorg. allgem. Chem.* **235**, 139-147.
- BUSING, W. R., MARTIN, K. O. & LEVY, H. A. (1962). *ORFLS*. Report ORNL-TM-305. Oak Ridge National Laboratory, Tennessee.
- CROMER, D. T. (1965). *Acta Cryst.* **18**, 17-23.
- GOODENOUGH, J. B. (1963). *Magnetism and the Chemical Bond*. New York: Interscience.
- JACOBONI, C., DE PAPE, R., POULAIN, M., LE MAROUILLE, J. Y. & GRANDJEAN, D. (1974). *Acta Cryst.* **B30**, 2688-2691.
- MCMASTER, W. H., KERR DEL GRANDE, N., MALLET, J. H. & HUBBEL, J. H. (1969). *Compilation of X-ray Cross Sections*. Natl. Bur. Stand. UCRL-50174, Sec. II, Rev. 1.
- MORELL, B. K., ZALKIN, A., TRESSAUD, A. & BARTLETT, N. (1973). *Inorg. Chem.* **12**, 2640-2644.
- MÜHLL, R., VON DER DAUT, F. & RAVEZ, J. (1973). *J. Solid State Chem.* **8**, 206-212.
- MÜHLL, R., VON DER DAUT, F. & RAVEZ, J. (1974). *Rev. Chim. Minér.* **11**, 652-663.
- PORTIER, J., TRESSAUD, A., DE PAPE, R. & HAGENMULLER, P. (1968). *Mater. Res. Bull.* **3**, 433-436.
- RYAN, R. R., MARTIN, S. H. & REISFELD, M. J. (1971). *Acta Cryst.* **B27**, 1270-1274.
- SEARS, D. R. & HOARD, J. L. (1969). *J. Chem. Phys.* **50**, 1066-1072.
- SHANNON, R. D. & PREWITT, C. T. (1969). *Acta Cryst.* **B25**, 925-945.
- TRESSAUD, A., DANCE, J. M., VLASSE, M. & PORTIER, J. (1976). *C. R. Acad. Sci. Paris, Sér. C*, **282**, 1105-1108.
- TRESSAUD, A., PORTIER, J., DE PAPE, R. & HAGENMULLER, P. (1970). *J. Solid State Chem.* **2**, 269-277.
- VLASSE, M., MENIL, F., MORILIERE, C., DANCE, J. M., TRESSAUD, A. & PORTIER, J. (1976). *J. Solid State Chem.* **17**, 291-298.
- WANKLYN, B. M. (1975). *J. Mater. Sci.* **10**, 1487-1493.