Structure and properties of the mixed-valence compound $\text{Eu}_5\text{Zr}_3\text{S}_{12}$

Dirk Johrendt, Petra Jakubcova, Falko M. Schappacher, Rainer Pöttgen

► To cite this version:

Dirk Johrendt, Petra Jakubcova, Falko M. Schappacher, Rainer Pöttgen. Structure and properties of the mixed-valence compound $\text{Eu}_5\text{Zr}_3\text{S}_{12}$. Journal of Inorganic and General Chemistry / Zeitschrift für anorganische und allgemeine Chemie, 2009, 635 (4-5), pp.759. 10.1002/zaac.200900075 . hal-00482074

HAL Id: hal-00482074

<https://hal.science/hal-00482074>

Submitted on 8 May 2010

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Zeitschrift für Anorganische und
Allgemeine Chemie

**Structure and properties of the mixed-valence compound
Eu₅Zr₃S₁₂**

Journal:	<i>Zeitschrift für Anorganische und Allgemeine Chemie</i>
Manuscript ID:	zaac.200900075
Wiley - Manuscript type:	Article
Date Submitted by the Author:	30-Jan-2009
Complete List of Authors:	Johrendt, Dirk; LMU Muenchen, Department Chemie und Biochemie Jakubcova, Petra; LMU München, Chemie und Biochemie Schappacher, Falko M.; Universität Münster, Anorganische Chemie Pöttgen, Rainer; Universität Münster, Anorganische Chemie
Keywords:	Europium, Mixed valence, Sulfides, Magnetism, Crystal structure

Structure and properties of the mixed-valence compound $\text{Eu}_5\text{Zr}_3\text{S}_{12}$

Petra Jakubcová^a, Falko M. Schappacher^b, Rainer Pöttgen^b and Dirk Johrendt^{a,*}

Dedicated to Professor Reinhard Nesper on the Occasion of his 60th Birthday

^a Department Chemie und Biochemie, Ludwig-Maximilians-Universität München, Butenandtstrasse 5–13 (Haus D), D–81377 München (Germany)

^b Institut für Anorganische und Analytische Chemie, Westfälische Wilhelms-Universität Münster, Corrensstraße 30, 48149 Münster (Germany)

Abstract. Needle shaped crystals of $\text{Eu}_5\text{Zr}_3\text{S}_{12}$ and $\text{Eu}_{3.67}\text{Sr}_{1.33}\text{Zr}_3\text{S}_{12}$ were synthesized by solid state reactions of the elements and ZrS_2 at 673–1273 K in alumina crucibles and their crystal structures were determined by single crystal methods. Both are isotypic with hexagonal symmetry (space group $P\bar{6}2m$, $Z = 1$, $\text{Eu}_5\text{Zr}_3\text{S}_{12}$: $a = 1170.7(2)$, $c = 394.27(8)$ pm, $wR2 = 0.0636$ for 552 F^2 and 27 parameters; $\text{Eu}_{3.67}\text{Sr}_{1.33}\text{Zr}_3\text{S}_{12}$: $a = 1167.0(2)$, $c = 395.71(8)$ pm, $wR2 = 0.0887$ for 484 F^2 and 29 parameters) and contain one-dimensional chains of edge-sharing $\text{ZrS}_2\text{S}_{4/2}$ octahedra, running parallel to [001]. Two europium sites are seven- or nine-fold coordinated by sulfur. $\text{Eu}_5\text{Zr}_3\text{S}_{12}$ is a Curie paramagnet with an effective magnetic moment of $\mu_{\text{eff}} = 13.37(1) \mu_{\text{B}}/\text{fu}$ in agreement with three Eu^{2+}/fu . ^{151}Eu -Mössbauer spectra show two absorption lines suggesting a static mixture of Eu^{2+} and Eu^{3+} according to $\text{Eu}_3^{2+}\text{Eu}_2^{3+}\text{Zr}_3^{4+}\text{S}_{12}^{2-}$. This assignment is not in line with the observed Eu–S distances. To resolve this, we suggest pure Eu^{2+} at the $2c$ site and inhomogeneous mixed valence at the $3f$ site according to $(\text{Eu}_2^{2+})^{2c}(\text{Eu}^{2+}\text{Eu}_2^{3+})^{3f}\text{Zr}_3^{4+}\text{S}_{12}^{2-}$. This is supported by the site preference of Sr^{2+} in $\text{Eu}_{3.67}\text{Sr}_{1.33}\text{Zr}_3\text{S}_{12}$.

Running title: Mixed valence in $\text{Eu}_5\text{Zr}_3\text{S}_{12}$

Keywords: Europium, Sulfides, Crystal structure, Mixed valence, Magnetism

* Prof. Dr. Dirk Johrendt

Department Chemie und Biochemie, Universität München

Butenandtstrasse 5–13 (Haus D), D-81377 München, Germany

e-mail: dirk.johrendt@cup.uni-muenchen.de

Introduction

Mixed valence compounds have been a matter of interest for decades [1]. In solids, europium can be divalent (Eu^{2+} , $4f^7$) or trivalent (Eu^{3+} , $4f^6$) and fluctuations between these configurations frequently occur. In structures with one crystallographic Eu site and fast fluctuation frequencies, Eu^{2+} and Eu^{3+} are not observable separately and thus homogeneously-mixed (intermediate) valence results. Di- and trivalent europium ions on different crystallographic sites can lead either to a static valence mixture or inhomogeneous mixed-valence if the fluctuation frequency depends strongly on temperature. In the latter case, the europium ions become equivalent above the Verwey-temperature. Homogeneous mixed-valence is known from metallic compounds like EuCu_2Si_2 [2] or EuNi_2P_2 [3]. The non-metallic compounds Eu_3O_4 [4], Eu_2CuS_3 [5] and $\text{Eu}_5\text{Sn}_3\text{S}_{12}$ [6] are examples for static mixed-valence with different europium sites. Inhomogeneous mixed-valence associated with Verwey-transitions have been observed in Eu_3S_4 [7], Eu_4As_3 [8] and in the metallic compounds EuPtP [9, 10], EuPdAs [11] and EuNiP [12, 13].

Recently, we reported on the ternary thiostannate $\text{Eu}_5\text{Sn}_3\text{S}_{12}$, a mixed valence compound with three Eu^{2+} and two Eu^{3+} occupying five different crystallographic sites [6]. The static nature of the valence mixture was verified by ^{151}Eu -Mössbauer spectra, showing two separate absorptions with almost temperature-independent chemical shifts. In $\text{Eu}_5\text{Sn}_3\text{S}_{12}$, the assignments of the Eu^{2+} and Eu^{3+} sites are in line with the different europium coordinations, hence the divalent ions with larger radii (Eu^{2+} 117 pm; Eu^{3+} 95 pm) occupy positions with significantly longer Eu–S distances and vice versa. This, however, is also consistent with the charge balanced formula $\text{Eu}_3^{2+}\text{Eu}_2^{3+}\text{Sn}_3^{4+}\text{S}_{12}^{2-}$ as expected by the semiconducting behaviour of the material.

We noticed the existence of the europium-thiozirconate with the same formula type. $\text{Eu}_5\text{Zr}_3\text{S}_{12}$ [14] crystallizes in a similar, but hexagonal structure with two crystallographic europium sites, namely one threefold and one twofold. This is suggestive of assigning the

threefold site with Eu^{2+} and the twofold with Eu^{3+} resulting in the charge balanced formula $\text{Eu}_3^{2+}\text{Eu}_2^{3+}\text{Zr}_3^{4+}\text{S}_{12}^{2-}$ as indicated by the authors. However, the compound has been obtained only as a by-product of another synthesis in Ref. [14] and no further data beyond the structure are given. In this paper, we report on the synthesis, single crystal structure determination, magnetic properties and ^{151}Eu -Mössbauer spectroscopy of the mixed-valence compound $\text{Eu}_5\text{Zr}_3\text{S}_{12}$.

Experimental

Synthesis

$\text{Eu}_5\text{Zr}_3\text{S}_{12}$ was synthesized by heating a mixture of Eu metal (99.9% Smart Elements), ZrS_2 and S (99.999%, ChemPur) in a NaCl/KCl flux in an alumina crucible, which was sealed in a silica tube under an atmosphere of purified argon. The sample was heated to 943 K at a rate of 50 K/h, kept at this temperature for 72 h and slowly cooled down to 673 K at a rate of 3 K/h and then to room temperature at a rate of 50 K/h. The crucible was smashed and the NaCl/KCl flux dissolved in warm water. This procedure resulted in needle gray crystals of $\text{Eu}_5\text{Zr}_3\text{S}_{12}$, which are stable in air.

$\text{Eu}_{3.67}\text{Sr}_{1.33}\text{Zr}_3\text{S}_{12}$ could be obtained by heating a stoichiometric mixture of Eu metal, (99.9%, Alfa Aesar), S (99.999%, ChemPur), SrS and ZrS_2 at 1275 K for 130 hours. After cooling, the sample is homogenized and heated to 1275 K for 69 h. This procedure resulted in a multiphase mixture with needle-shaped gray crystals of $\text{Eu}_{3.67}\text{Sr}_{1.33}\text{Zr}_3\text{S}_{12}$.

X-ray structure determination

X-ray powder patterns of the $\text{Eu}_5\text{Zr}_3\text{S}_{12}$ and $\text{Eu}_{3.67}\text{Sr}_{1.33}\text{Zr}_3\text{S}_{12}$ samples were recorded using a STOE STADI-P diffractometer (Mo- $K_{\alpha 1}$ radiation, Ge(111)-monochromator, 7° PSD detector or Cu $K_{\alpha 1}$ radiation, Ge(111)-monochromator, SiO_2 as external standard).

Small single crystals of $\text{Eu}_5\text{Zr}_3\text{S}_{12}$ and $\text{Eu}_{3.67}\text{Sr}_{1.33}\text{Zr}_3\text{S}_{12}$ were selected directly from the samples and inspected by Laue photographs (white Mo-radiation). Single crystal intensity data were collected at room temperature on a STOE IPDS imaging plate detector (Mo- K_{α} , graphite-monochromator, φ -scan). The EXPOSE [15] and X-RED [16] software was used for data collection and processing. Analytical absorption corrections were performed using crystal shapes obtained by the video system and optimized by the X-SHAPE [17] software.

The structures were solved with the direct methods program SHELXS and refined with full-matrix least squares using SHELXL [18]. All final cycles included anisotropic displacement parameters.

Crystallographic data and experimental details of the data collections are listed in Table 1, final atomic positions and equivalent displacement parameters in Table 2. Selected interatomic distances are given in Table 3. Further details of the structure determinations may be obtained from: Fachinformationszentrum Karlsruhe, D-76344 Eggenstein-Leopoldshafen (Germany) by quoting the Registry No's CSD-420279 ($\text{Eu}_5\text{Zr}_3\text{S}_{12}$) and CSD-420280 ($\text{Eu}_{3.67}\text{Sr}_{1.33}\text{Zr}_3\text{S}_{12}$).

Electrical resistivity

A cold pressed pellet (diameter 6 mm, height ~1 mm) of the $\text{Eu}_5\text{Zr}_3\text{S}_{12}$ powder sample was contacted with silver wires and silver paste and the specific electrical resistivity was measured between 80 and 320 K using a *dc* four point current reversal method [19].

Magnetic measurements

Magnetic properties of $\text{Eu}_5\text{Zr}_3\text{S}_{12}$ were measured with a SQUID magnetometer (MPMS-XL Quantum Design Inc.). Finely ground powder sample was inserted in capsules and those into a straw of known diamagnetism. The magnetic susceptibilities of the sample were collected in a temperature range from 1.8 to 300 K with magnetic flux densities up to 5 Tesla. The data were corrected for diamagnetic contributions of the capsule, the straw and the sample using diamagnetic increments [20, 21].

^{151}Eu -Mössbauer spectroscopy

The 21.53 keV transition of ^{151}Eu with an activity of 130 MBq (2% of the total activity of a $^{151}\text{Sm}:\text{EuF}_3$ source) is used for the Mössbauer spectroscopic experiments which were conducted in the usual transmission geometry. The measurements were performed with a commercial helium bath cryostat. The temperature of the absorber was varied between 4.2 K and room temperature, while the source was kept at room temperature. The sample was placed within a thin-walled PVC container at a thickness corresponding to about 10 mg Eu/cm^2 . The material for the Mössbauer spectroscopic measurements and the magnetic investigations was taken from the same batch.

Results and discussion

The crystal structure of $\text{Eu}_5\text{Zr}_3\text{S}_{12}$ (space group $P\bar{6}2m$) is shown in Figure 1. The unit cell consists of one formula unit with two crystallographically different Eu sites, one Zr and three S sites. The europium atoms at the Wyckoff positions $2c$ and $3f$ are coordinated by sulphur atoms either in the shape of tri-capped (Eu1) or single capped (Eu2) trigonal prisms, as shown in Figure 2. Nine sulphur atoms surround Eu1 at distances of 303.0–340.1 pm. Eu2 is sevenfold coordinated with Eu–S bond lengths of 286.5(2)–291.5(3) pm. These prisms share faces or edges and thus form chains. Zr is found in a sixfold octahedral co-ordination sphere consisting of sulphur atoms with Zr–S bond lengths between 254.9(2) and 265.1(2) pm. One-dimensional chains of edge-sharing $\text{ZrS}_2\text{S}_{4/2}$ octahedra run parallel to $[001]$ (Figure 3).

According to the interatomic distances, the assignment of the europium valences seems to be straightforward. Eu^{2+} should clearly occupy the $2c$ site with a mean Eu1–S distance of 315.4 pm and Eu^{3+} is expected on the $3f$ site with a mean Eu2–S distance of 288.3 pm. This would be completely in line with known europium sulfides, where Eu^{2+} –S distances are always significantly longer than Eu^{3+} –S distances. Examples are EuS (298 pm), Eu_2S_3 (270 pm), EuZrS_3 (311 pm) as well as the static mixed valence compounds $\text{Eu}_5\text{Sn}_3\text{S}_{12}$ (306/286 pm) and Eu_2CuS_3 (305/281 pm). Calculations of the bond valence sums $V_i = \sum_j \exp\left(\frac{R_0 - d_{ij}}{b}\right)$ resulted in $V_{\text{Eu1}} = 2.13$ and $V_{\text{Eu2}} = 3.12$ ($R_0 = 2.58$ Å, $b = 0.35$ Å) [22, 23] and indicate the expected assignment of the europium valences. But in this case, the formula would be $\text{Eu}_2^{2+}\text{Eu}_3^{3+}\text{Zr}_3^{4+}\text{S}_{12}^{2-}$ and thus no longer charge neutral. This can be possible if the compound is metallic according to $\text{Eu}_2^{2+}\text{Eu}_3^{3+}\text{Zr}_3^{4+}\text{S}_{12}^{2-} \cdot 2e^-$. However, the temperature dependent electrical resistance of $\text{Eu}_5\text{Zr}_3\text{S}_{12}$ shows semiconducting behavior (Figure 4). From the Arrhenius-plot we estimate a band-gap of $E_G \approx 0.42$ eV at room temperature.

The static magnetic susceptibility $\chi_{\text{mol}}(T)$ and inverse susceptibility $\chi_{\text{mol}}^{-1}(T)$ of $\text{Eu}_5\text{Zr}_3\text{S}_{12}$ is displayed in Figure 5. From the linear part of the $\chi_{\text{mol}}^{-1}(T)$ -plot between 7 and 300 K we extracted the effective magnetic moment $\mu_{\text{eff}} = 13.37(1)\mu_B/\text{fu}$ and the paramagnetic Curie temperature (Weiss-constant) $\theta = 0.02(1)$ K. Thus, $\text{Eu}_5\text{Zr}_3\text{S}_{12}$ can be considered as Curie paramagnet. The experimental magnetic moment is close to the

theoretical value of three Eu^{2+}/fu ($\sqrt{3} \times 7.94 = 13.75 \mu_{\text{B}}/\text{fu}$). The magnetization behavior is presented in Figure 6. At 40 K, the magnetization increases linearly with increasing magnetic field as expected for a paramagnet. Magnetization measurements at 6 K show saturation, which perfectly fits to the Brillouin-function with three Eu^{2+} ($J = 7/2$). No magnetic ordering is detected in agreement with θ close to zero.

The ^{151}Eu Mössbauer spectra of $\text{Eu}_5\text{Zr}_3\text{S}_{12}$ at 77 and 4.2 K are presented in Figure 7 together with transmission integral fits. The corresponding fitting parameters are listed in Table 4. In the whole temperature range, we observe two signals at isomer shifts around -12 and 0.5 mm/s, indicating static mixed valence of Eu^{2+} and Eu^{3+} . There is no pronounced shift of the isomer shifts with decreasing temperature. At 4.2 K the area ratio of the two signals $\text{Eu}^{2+}/\text{Eu}^{3+}$ is 59/41, in good agreement with the ionic formula $\text{Eu}_3^{2+}\text{Eu}_2^{3+}\text{Zr}_3^{4+}\text{S}_{12}^{2-}$.

Thus, magnetic and Mössbauer spectroscopic data congruently show the existence of three divalent and two trivalent europium ions in $\text{Eu}_5\text{Zr}_3\text{S}_{12}$ in agreement with the semiconducting property. But this clearly contradicts with the crystal structure, because this would lead to implausible Eu–S distances (*vide supra*). One may firstly think the crystal structure could be wrong. We were aware of possible twinning as found for some crystals of the similar orthorhombic thiostannate $\text{Eu}_5\text{Sn}_3\text{S}_{12}$, which simulated hexagonal symmetry. We checked for this and found no indication of twinning. The structure of $\text{Eu}_5\text{Zr}_3\text{S}_{12}$ was also smoothly refined by using x-ray powder data. Then we checked the behavior of the lattice parameters with temperature down to 10 K and found no anomaly. At the end, we have no indication of any inconstancy regarding the crystal structure of $\text{Eu}_5\text{Zr}_3\text{S}_{12}$.

To unravel this mystery, we suggest inhomogeneous mixed valence of the europium atoms at the $3f$ site and pure divalent europium at the $2c$ site in $(\text{Eu}_2^{2+})^{2c}(\text{Eu}^{2+}\text{Eu}_2^{3+})^{3f}\text{Zr}_3^{4+}\text{S}_{12}^{2-}$. This would be consistent with the observed Eu–S distances, physical properties and Mössbauer spectroscopic data. A similar situation has been found in the low temperature phase of Eu_3S_4 [7] with one pure Eu^{3+} site and one mixed site according to $(\text{Eu}^{3+})^{4a}(\text{Eu}^{2+}\text{Eu}^{3+})^{8d}\text{S}_4^{2-}$ (space group $I\bar{4}2d$).

As a chemical approach to this hypothesis, we tried to substitute the Eu^{2+} ions by Sr^{2+} ions with similar radius. We did not obtain phase pure samples, but small single crystals could be selected from the samples. The structure determination resulted in the composition $\text{Eu}_{3.67}\text{Sr}_{1.33}\text{Zr}_3\text{S}_{12}$. Details of the crystal structure are given in Tables 1-3. The strontium atoms are distributed over both, the $2c$ and the $3f$ positions, but with a significant preference to the $2c$ site providing the longer Eu/Sr-S distances in $(\text{Eu}_{1.06}\text{Sr}_{0.94})^{2c}(\text{Eu}_{2.61}\text{Sr}_{0.39})^{3f}\text{Zr}_3^{4+}\text{S}_{12}^{2-}$. This clearly supports the suggestion of inhomogeneous mixed valence at the $3f$ site in $\text{Eu}_5\text{Zr}_3\text{S}_{12}$. However, this could be proved by Mössbauer spectroscopic experiments to high temperatures.

In summary, we have synthesized phase pure samples and single crystals of the mixed valence compound $\text{Eu}_5\text{Zr}_3\text{S}_{12}$. The crystal structure reported in [13] was confirmed, but the assignment of Eu^{2+} to the $3f$ -site with shorter Eu-S distances and Eu^{3+} to the $2c$ site with longer ones is very unlikely. Magnetic measurements and ^{151}Eu -Mössbauer spectra prove the existence of three Eu^{2+} and two Eu^{3+} in the unit cell. To solve these contradicting results, we suggest pure Eu^{2+} at the $2c$ site and inhomogeneous mixed valence at the $3f$ site according to $(\text{Eu}_2^{2+})^{2c}(\text{Eu}^{2+}\text{Eu}_2^{3+})^{3f}\text{Zr}_3^{4+}\text{S}_{12}^{2-}$. This hypothesis is supported by the Sr^{2+} distribution in $\text{Eu}_{3.67}\text{Sr}_{1.33}\text{Zr}_3\text{S}_{12}$.

References

- [1] C. M. Varma, *Rev. Mod. Phys.* **1976**, 48, 219.
- [2] E. R. Bauminger, D. Froindlich, I. Nowik, S. Ofer, I. Felner, I. Mayer, *Phys. Rev. Lett.* **1973**, 30, 1053.
- [3] R. Nagarajan, E. V. Sampathkumaran, L. C. Gupta, R. Vijayaraghavan, V. Prabhawalkar, Bhaktdarshan, B. D. Padalia, *Phys. Lett. A* **1981**, 84A, 275.
- [4] H. H. Wickman, E. Catalano, *J. Appl. Phys.* **1968**, 39, 1248.
- [5] F. Furuuchi, M. Wakeshima, Y. Hinatsu, *J. Solid State Chem.* **2004**, 177, 3853.
- [6] P. Jakubcova, D. Johrendt, C. P. Sebastian, S. Rayaprol, R. Pöttgen, *Z. Naturforsch.* **2007**, 62b, 5.
- [7] H. Ohara, S. Sasaki, Y. Konoike, T. Toyoda, K. Yamawaki, M. Tanaka, *Physica B: Condens. Matter* **2004**, 350, 353.
- [8] G. Wortmann, E. V. Sampathkumaran, G. Kaindl, *J. Magn. Magn. Mater.* **1986**, 54-57, 338.
- [9] N. Lossau, H. Kierspel, J. Langen, W. Schlabit, D. Wohlleben, A. Mewis, C. Sauer, *Z. Phys. B: Condens. Matter* **1989**, 74, 227.
- [10] G. Michels, C. Huhnt, W. Scharbrodt, W. Schlabit, E. Holland-Moritz, M. M. Abd-Elmeguid, H. Micklitz, D. Johrendt, V. Keimes, A. Mewis, *Z. Phys. B: Condens. Matter* **1995**, 98, 75.
- [11] G. Michels, S. Junk, N. Lossau, W. Schlabit, D. Wohlleben, D. Johrendt, A. Mewis, C. Sauer, T. Woike, *Z. Phys. B: Condens. Matter* **1992**, 86, 53.
- [12] V. Ksenofontov, H. C. Kandpal, J. Ensling, M. Waldeck, D. Johrendt, A. Mewis, P. Guetlich, C. Felser, *Europhys. Lett.* **2006**, 74, 672.
- [13]
- [14] Y. L. I. Klawitter, Dissertation, Universität Kiel, **2004**.
- [15] EXPOSE, Stoe & Cie GmbH, Darmstadt, **2000**.
- [16] X-RED32, 1.26 ed., Stoe & Cie GmbH, Darmstadt, **2004**.
- [17] X-SHAPE, Stoe & Cie GmbH, Darmstadt, **1999**.
- [18] G. M. Sheldrick, *Acta Crystallogr. A* **2008**, A64, 112.
- [19] KEITHLEY, *Low Level Measurements, Precision DC Current, Voltage and Resistance Measurements*, 5 ed., Keithley Instruments, Inc., Cleveland, Ohio, **1998**.
- [20] H. Lueken, *Magnetochemie*, Teubner, Stuttgart, Leipzig, **1999**.
- [21] S. Hatscher, H. Schilder, H. Lueken, W. Urland, *Pure Appl. Chem.* **2005**, 77, 497.
- [22] I. D. Brown, D. Altermatt, *Acta Crystallogr. B* **1985**, B41, 244.
- [23] N. E. Brese, M. O'Keeffe, *Acta Crystallogr. B* **1991**, B47, 192.

Table 1 Crystallographic data for $\text{Eu}_5\text{Zr}_3\text{S}_{12}$ and $\text{Eu}_{3.67}\text{Sr}_{1.33}\text{Zr}_3\text{S}_{12}$

Chemical formula	$\text{Eu}_5\text{Zr}_3\text{S}_{12}$	$\text{Eu}_{3.67}\text{Sr}_{1.33}\text{Zr}_3\text{S}_{12}$
Molar mass / g/mol	1418.18	1332.61
Crystal system	hexagonal	hexagonal
Space group	$P\bar{6}2m$ (Nr. 189)	$P\bar{6}2m$ (Nr. 189)
Lattice parameters /pm	$a = 1170.7(2)$ $c = 394.27(8)$	$a = 1167.0(2)$ $c = 395.71(8)$
$V / 10^6 \text{ pm}^3$	468 (1)	466.7 (1)
Formula units per cell	$Z = 1$	$Z = 1$
Calculated density /g/m ³	5.03	4.74
Absorption coefficient / mm ⁻¹	19.4	18.8
Diffractometer	STOE IPDS	STOE IPDS
Radiation type	Mo- K_α ($\lambda = 71.073 \text{ pm}$)	Mo- K_α ($\lambda = 71.073 \text{ pm}$)
Data collection method	φ -scan, oscillation	φ -scan, oscillation
Absorption correction	analytical	analytical
Transm. Ratio (min/max)	0.385 / 0.558	0.354 / 0.567
Total no. reflections	5013	4130
Independent reflections	566 ($R_{int} = 0.0346$)	577 ($R_{int} = 0.0747$)
Reflections with $I > 2\sigma(I)$	552	484
Parameter	27	29
Goodness-of-fit (F^2)	1.259	0.968
Final R indices ($I > 2\sigma(I)$)	$R_1 = 0.0231$ $wR_2 = 0.0631$	$R_1 = 0.0375$ $wR_2 = 0.0849$
R Indices (all data)	$R_1 = 0.0240$ $wR_2 = 0.0636$	$R_1 = 0.0495$ $wR_2 = 0.0887$
Larg.diff peak and hole / e Å ⁻³	3.13, -1.03	3.00, -1.33
Extinction coefficient	0.0012(2)	0.0013(5)

Table 2 Atomic coordinates and equivalent isotropic displacement parameters ($U_{\text{eq}} / \text{pm}^2$) for $\text{Eu}_5\text{Zr}_3\text{S}_{12}$ and $\text{Eu}_{3.67}\text{Sr}_{1.33}\text{Zr}_3\text{S}_{12}$ (space group: $P\bar{6}2m$).

$\text{Eu}_5\text{Zr}_3\text{S}_{12}$	Site	X	y	z	U_{eq}	$occ.$
Eu1	$2c$	$1/3$	$2/3$	0	124(2)	
Eu2	$3f$	0.71674(5)	0	0	104(2)	
Zr	$3g$	0.3298(1)	0	$1/2$	128(3)	
S1	$6k$	0.2509(2)	0.4424(2)	$1/2$	112(4)	
S2	$3f$	0.1783(3)	0	0	171(6)	
S3	$3f$	0.4677(2)	0	0	151(6)	
$\text{Eu}_{3.67}\text{Sr}_{1.33}\text{Zr}_3\text{S}_{12}$						
Eu1	$2c$	$1/3$	$2/3$	0	190(6)	0.53
Sr1	$2c$	$1/3$	$2/3$	0	190(6)	0.47
Eu2	$3f$	0.7184(1)	0	0	161(3)	0.87
Sr2	$3f$	0.7184(1)	0	0	161(3)	0.13
Zr	$3g$	0.3297(2)	0	$1/2$	206(6)	
S1	$6k$	0.2506(4)	0.4409(4)	$1/2$	177(8)	
S2	$3f$	0.1787(5)	0	0	252(13)	
S3	$3f$	0.4674(5)	0	0	252(13)	

Table 3 Selected bond lengths (in pm) for $\text{Eu}_5\text{Zr}_3\text{S}_{12}$ and $\text{Eu}_{3.67}\text{Sr}_{1.33}\text{Zr}_3\text{S}_{12}$.

$\text{Eu}_5\text{Zr}_3\text{S}_{12}$			$\text{Eu}_{3.67}\text{Sr}_{1.33}\text{Zr}_3\text{S}_{12}$		
Eu1	S1	303.0(2) 6 ×	Eu1/Sr1	S1	304.0(3) 6 ×
	S3	340.1(1) 3 ×		S3	339.0(1) 3 ×
	Ø Eu–S	315.4		Ø Eu/Sr–S	315.7
Eu2	S1	286.5(2) 4 ×	Eu2/Sr2	S1	285.9(2) 4 ×
	S2	290.4(1) 2 ×		S2	288.0(2) 2 ×
	S3	291.5(3)		S3	292.7(6)
	Ø Eu–S	288.3		Ø Eu/Sr–S	287.5
Zr	S1	254.8(2) 2 ×	Zr	S1	253.9(4) 2 ×
	S2	265.1(2) 2 ×		S2	264.9(4) 2 ×
	S3	254.9(2) 2 ×		S3	255.0(4) 2 ×
	Ø Zr–S	258.3		Ø Zr–S	257.9

Table 4 Fitting parameters of ^{151}Eu Mössbauer spectroscopic measurements of $\text{Eu}_5\text{Zr}_3\text{S}_{12}$. Numbers in parentheses represent the statistical errors in the last digit. (δ), isomer shift; (Γ), experimental line width; ΔE_Q , electric quadrupole splitting parameter.

T (K)	δ_1 (mm s ⁻¹)	ΔE_{Q1} (mm s ⁻¹)	Γ_1 (mm s ⁻¹)	δ_2 (mm s ⁻¹)	ΔE_{Q2} (mm s ⁻¹)	Γ_2 (mm s ⁻¹)	$A1:A2$
77	-12.19(1)	3.1(2)	2.9(1)	0.49(1)	2.9(1)	2.2(1)	60:40
4.2	-11.88(3)	2.7(5)	3.3(1)	0.58(3)	3.3(3)	2.1(1)	59:41

Figure Captions

Figure 1. Crystal structure of $\text{Eu}_5\text{Zr}_3\text{S}_{12}$, projection onto the ab -plane. The octahedral zirconium coordination is emphasized.

Figure 2. Coordination polyhedra of the Eu atoms in $\text{Eu}_5\text{Zr}_3\text{S}_{12}$.

Figure 3. One-dimensional edge sharing octahedra in $\text{Eu}_5\text{Zr}_3\text{S}_{12}$.

Figure 4. Temperature dependence of the relative resistivity of $\text{Eu}_5\text{Zr}_3\text{S}_{12}$. The inset shows the Arrhenius-plot.

Figure 5. Temperature dependence of the magnetic susceptibility (χ) and inverse magnetic susceptibility (χ^{-1}) of $\text{Eu}_5\text{Zr}_3\text{S}_{12}$ measured in $H = 10$ kOe. The behavior at low temperatures is shown in the insert.

Figure 6. Magnetization as a function of ramping field measured at various temperatures for $\text{Eu}_5\text{Zr}_3\text{S}_{12}$.

Figure 7. Experimental and simulated ^{151}Eu Mössbauer spectra of $\text{Eu}_5\text{Zr}_3\text{S}_{12}$ at 77 and 4.2 K.

937x624mm (96 x 96 DPI)

119x45mm (600 x 600 DPI)

937x624mm (96 x 96 DPI)

283x202mm (150 x 150 DPI)

284x198mm (150 x 150 DPI)

288x203mm (150 x 150 DPI)

141x159mm (600 x 600 DPI)