Formation of an inorganic-organic host-guest material by intercalation of acetone formaldehyde sulfite polycondensate into a hydrocalumite structure

Johann Plank, Friedrich von Hoessle

► To cite this version:

Johann Plank, Friedrich von Hoessle. Formation of an inorganic-organic host-guest material by intercalation of acetone formaldehyde sulfite polycondensate into a hydrocalumite structure. *Journal of Inorganic and General Chemistry / Zeitschrift für anorganische und allgemeine Chemie*, 2010, 636 (8), pp.1533. 10.1002/zaac.201000001 . hal-00552439

HAL Id: hal-00552439

<https://hal.science/hal-00552439>

Submitted on 6 Jan 2011

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

**Formation of an inorganic-organic host-guest material by
intercalation of acetone formaldehyde sulfite
polycondensate into a hydrocalumite structure**

Journal:	<i>Zeitschrift für Anorganische und Allgemeine Chemie</i>
Manuscript ID:	zaac.201000001.R1
Wiley - Manuscript type:	Article
Date Submitted by the Author:	20-Apr-2010
Complete List of Authors:	Plank, Johann; Technische Universität München, Institute of Inorganic Chemistry von Hoessle, Friedrich; Technische Universität München, Institute of Inorganic Chemistry
Keywords:	Host-Guest Systems, Intercalations, Layered compounds, Polymers, Colloids
Note: The following files were submitted by the author for peer review, but cannot be converted to PDF. You must view these files (e.g. movies) online.	
figure1.cdx

ARTICLE

DOI: 10.1002/zaac.200((will be filled in by the editorial staff))

Formation of an inorganic-organic host-guest material by intercalation of acetone formaldehyde sulfite polycondensate into a hydrocalumite structure

Johann Plank,^{*,[a]} Friedrich von Hoessle^[a]

Keywords: Intercalations; Layered compounds; Polymers; Host-Guest Systems; Colloids

An acetone formaldehyde sulfite based polycondensate (Mw ~ 64 kDa) which is commonly used as a superplasticizer in cement and concrete, was intercalated into a hydrocalumite type LDH structure. Preparation was done by controlled rehydration of tricalcium aluminate in the presence of the polymer. Formation of the LDH phase was confirmed by XRD, IR and TG measurements. Elemental composition of the organo-mineral phase reveals charge

balancing of the cationic LDH main layers by the polycondensate and OH⁻ ions. Low crystallinity observed by XRD and presence of LDH foils was verified by SEM images. There, the novel Ca-Al-LDH phase shows a morphology of intergrown platelets which is typical for layered calcium aluminate hydrates. Depending on the preparation method, ultra-thin foils with 20 nm – 50 nm thickness were observed. TEM images also support presence of a layered structure.

from 0 to 12 [11]. At room temperature and relative humidity of approximately 30%, the phase C₄AH₁₃ (x = 13) is the stable modification.

Introduction

Dispersants such as e.g. polycarboxylates (PCE) and β-naphthalenesulfonate-formaldehyde based polycondensates (BNS) which are widely used as superplasticizers in concrete have been reported to intercalate into cement hydrates under favorable conditions [1-4]. Upon hydration which is often referred to as rehydration [5], the cement clinker phase tricalcium aluminate (Ca₃Al₂O₆, abbreviation C₃A) can form layered double hydroxides of the hydrocalumite type. Anionic superplasticizer polymers of various structure and molecular weight can counterbalance the charge of the cationic sheets and intercalate between the layers. In this study, a linear acetone formaldehyde sulfite polycondensate (AFS) [6] has been synthesized and was used in rehydration experiments with tricalcium aluminate. Its chemical structure is presented in Figure 1. Because of the structural similarity of AFS with other polycondensates (e.g. BNS) it seemed possible to obtain novel organo-mineral phases from the reaction of AFS with C₃A.

Results and Discussion

XRD analysis

The Ca-Al-AFS-LDH composite was synthesized by reacting 1 g of tricalcium aluminate with 100 mL of a 2 wt.% aqueous AFS solution for 24 hours at room temperature under nitrogen protection to avoid carbonation of the product. The XRD pattern for the Ca-Al-AFS-LDH is shown in Figure 2. At 3.3° 2θ a reflection is observed which can be attributed to the [00l] reflections of the layered material. The corresponding d value which represents the basal spacing in the intercalate is 27 Å. One weak harmonic is observed at d = 13.5 Å (6.5° 2θ). Further reflections for [hk0] of the host-guest system can be found at approx. 31.5° 2θ and for [0k0] at about 55.8° 2θ. This XRD pattern confirms the intercalation of AFS into the Ca-Al-LDH host structure and a certain stacking regularity of the tactoid. Similar d values were reported for organic sulfonated compounds such as e.g. poly(vinyl sulfonate) and poly(styrene sulfonate) [12] and alkyl sulfonates [13]. There, basal spacings in the range of 13.2 Å – 19.6 Å and 27.0 Å – 32.3 Å, respectively were found. For comparison, the XRD pattern of synthesized C₄AH₁₃ is shown in Figure 2. It exhibits a [00l] reflection at 11.2° 2θ which corresponds to a basal spacing of only 7.9 Å, compared to 27 Å for the intercalate. Thus it is shown that incorporation of AFS significantly increases the interlayer distance. The steric size of AFS, the elemental composition of the intercalate as shown below and the d value obtained from XRD suggest that the polycondensate is positioned in a zig zag mode in between the cationic sheets whereby the sulfonated side chains are bound alternatively to the top and bottom layer, and hydroxide anions and water molecules fill the interstitial space.

* Prof. J.Plank,
E-mail: johann.plank@bauchemie.ch.tum.de
[a] Technische Universität München,
Lehrstuhl für Bauchemie,
Lichtenbergstr.4, 85747 Garching, Germany
Fax: +49 (89) 289 13152
http://www.bauchemie.ch.tum.de

For this purpose, the aluminate phase was reacted with the polymer to form structures of the type [Ca₂Al(OH)₆]⁺[Polymer]⁻·yH₂O. The reaction product was characterized regarding its structure, composition and morphology. Moreover, typical features of organic polymer-LDH compounds usually reported in literature [7-9] have been probed. To be able to compare the properties of the resulting intercalate, the layered model compound 4CaO · Al₂O₃ · xH₂O (abbreviation C₄AH_x) which represents the host structure for the AFS guest molecule was also synthesized. It possesses the ideal composition of [Ca₂Al(OH)₆]⁺[OH]⁻ · y(H₂O) [10], with y being in the range

IR and ^{27}Al NMR analysis

In Figure 3, a comparison of the IR spectra of the AFS polymer, the model phase C_4AH_x , and the organo-LDH phase is presented. The IR bands for C_4AH_{13} have already been described by Henning [14] and Houtepen [15]. Strong absorption occurs at 430 cm^{-1} and 540 cm^{-1} , due to the vibrational modes of calcium-oxygen and aluminum-oxygen octahedra within the sheets. Other typical absorptive bands of calcium aluminates are overlapping with the polymeric absorption bands in the intercalate. Frequencies for AFS are detected in the range of 1040 cm^{-1} for the ether linkage and at 1200 cm^{-1} and 1400 cm^{-1} for the stretching modes of the sulfonate group. The carbonyl function can be observed at 1700 cm^{-1} and CH_2 stretching at frequencies of 2900 cm^{-1} . The organo-LDH phase shows the frequencies of both individual compounds, C_4AH_x and AFS. Obviously, both the inorganic host structure and the organic guest molecule are present in the product.

^{27}Al MAS NMR spectroscopy was performed to probe the coordination state of aluminium in the dried hydration product. The spectrum exhibits only one sharp resonance at $\delta = 9.2\text{ ppm}$ which signifies octahedral coordination of Al (see Figure 4). The absence of a broad signal occurring at a lower chemical shift than the resonance from the Ca-Al-AFS-LDH structure confirms that no $\text{Al}(\text{OH})_3$ was formed as a by-product of this reaction.

Elemental analysis

Incorporation of the AFS polymer into the Ca-Al-LDH frame was confirmed by elemental analysis. A carbon content of 27.9 wt.% was found for the product (see Table 1). This value significantly exceeds the usual 5 wt.% which is the typical upper limit for surface adsorption of AFS-type polyelectrolytes on LDH crystal surfaces. Additionally, a sulphur content of 6.6 wt.% was determined for the composite, verifying the chemisorption of AFS into the hydrocalumite host structure. Based on the analytical data, the approximate composition for the Ca-Al-AFS-LDH was calculated and is shown in Table 1. For calculation of the formula, the points as follows were considered: The molar ratio of calcium to aluminum in the intercalate is 2:1. Charge compensation between the cationic main sheets and the guest anions is achieved by AFS molecules and OH^- ions. The formation of $\text{Ca}(\text{OH})_2$ and $\text{Al}(\text{OH})_3$ as by-products was ruled out because of the results obtained by elemental analysis, XRD and ^{27}Al MAS NMR spectroscopy. The value of the organic part can be derived from the calculated formula of the LDH. Additionally, water molecules are present in the interlayer region.

Table 1. Elemental composition and calculated formula of the Ca-Al-AFS-LDH

Sample	Elemental composition				
	C wt. %	H wt. %	S wt. %	Ca wt. %	Al wt. %
AFS polymer	40.5	5.8	9.3	-	-
Ca-Al-AFS LDH	27.9	5.2	6.6	11.1	3.8

	Organic part wt. %	Calculated formula
AFS polymer	-	$\text{C}_{12}\text{H}_{20}\text{SO}_8\text{Na}$
Ca-Al-AFS LDH	~ 68.0	$\text{Ca}_2\text{Al}(\text{OH})_6 \cdot (\text{AFS})_{1.4} \cdot (\text{OH})_{0.015} \cdot 3.3\text{H}_2\text{O}$

TG analysis

Thermogravimetric results are shown in Figure 5. The thermal decomposition of the pure LDH phase C_4AH_x follows a simple dehydration route as can be seen from Figure 6. Water release occurs at temperatures around 200°C (9 wt.%), 300°C (11 wt.%) and above 400°C (5 wt.%). The first two conversions stem from dehydration of C_4AH_{13} to C_4AH_{10} and C_4AH_7 respectively, the latter being the ideal composition of $[\text{Ca}_2\text{Al}(\text{OH})_6]^+[\text{OH}]^-$. Each weight loss is within the range of the theoretical value of approx. 10 wt.% for each release of water. Beginning from 400°C , the inorganic framework decomposes because of dehydroxylation. AFS polymer shows release of water at $110^\circ\text{C} - 150^\circ\text{C}$ and in the range of 250°C to 380°C . This second area of temperature stability is moved to slightly higher temperatures in the LDH material and a sharp release of water occurs at 400°C . The final steep drop in the TG graph of the AFS-LDH can also be ascribed to the release of SO_2 (see Figure 7). The sulfonate groups present in free AFS polymer start to decompose $\sim 300^\circ\text{C}$ whereas the hybrid material releases SO_2 beginning at $\sim 400^\circ\text{C}$. Obviously, the LDH framework keeps the polymer from decomposing until the framework itself breaks down. This result confirms that strong interaction between the anionic guest polyelectrolyte and the cationic host sheets occur.

SEM and TEM investigations

SEM images show platy crystals which are intergrown to form flower-like particles. In some cases, ultra-thin sheets were observed. There, several layers are grouped together to form nanometer scaled structures possessing a thickness of only $20\text{ nm} - 50\text{ nm}$, as shown in Figure 8. No evidence for pure C_4AH_x particles exhibiting the morphology of hexagonal platelets or any other crystalline impurities were found in microscopic investigations. TEM observations indirectly support intercalation and subsequent layer-spacing enlargement (see Figure 9).

Conclusions

Several investigations have been conducted to probe the intercalation ability of acetone formaldehyde sulfite polycondensate superplasticizers into a hydrocalumite structure. It is demonstrated that AFS can be successfully intercalated into a Ca-Al-LDH structure, resulting in a host-guest compound. These phases of low crystallinity and organic contents of approx. 70 wt.% show enhanced thermal stability of the AFS polymer. The practical importance of this study is that it offers an explanation for the differences in dispersing effectiveness of AFS at early and delayed addition to concrete. When AFS is present at the start of

concrete mixing, a portion of it may intercalate into early C_3A hydrates and therefore is lost for dispersion effect. Whereas at delayed addition, C_3A has already hydrated sufficiently to form C_4AH_x phases which no longer allow intercalation of AFS. Second, the AFS-LDH could be a useful admixture for concrete, namely for slow release formulations where AFS superplasticizer is gradually exchanged by other anions present in the cement pore solution.

Experimental Section

The acetone formaldehyde sulfite polycondensate was synthesized according to a description by Plank et al. using a base catalyzed aldol-type reaction [16]. The polymer was dialyzed prior to usage using a SpectraPor dialysis membrane (MWCO = 6000 Da). The molar ratio of acetone, formaldehyde and sulfite was chosen as 1 : 3 : 0.5, the resulting molecular weight (M_w) was determined by GPC measurement to be 64 kDa with a polydispersity index of 4.0. The amount of anionic charge present in the polymer was determined by polyelectrolyte titration in a streaming current charge detector (PCD 03 pH; Mutek Analytic, Herrsching, Germany) to be 2800 $\mu\text{eq/g}$.

Cubic tricalcium aluminate was prepared according to Stephan and Wilhelm [17] using a sol-gel method and subsequent calcination. The resulting product was ground to a particle size (D_{50}) of 4.0 μm . Purity of the C_3A sample was confirmed via XRD measurement. Pure C_4AH_x was prepared according to Faucon et al. [18] by reacting C_3A with saturated lime solution at low temperature ($\sim 5^\circ\text{C}$) under exclusion of air to avoid carbonation. The resulting precipitate was centrifuged and after washing with cold water, white crystals were obtained. This powder was dried over saturated CaCl_2 solution at room temperature. Preparation of Ca-Al-AFS-LDH was done as follows: Under vigorous stirring 1 g of C_3A was added to 100 mL of 2 wt.% aqueous AFS solution and reacted at room temperature for 24 hours, again under exclusion of air to avoid carbonation. The product was recovered by centrifugation. The wet precipitate was dried in a desiccator under reduced pressure (~ 15 Torr / silica gel).

XRD diffraction patterns were recorded using $\text{Cu K}\alpha$ radiation on a BRUKER AXS D8 diffractometer. The phases of interest were dried as already described prior to measurement and a slight grinding was applied to the powder products. TG measurements were conducted using a NETZSCH TG 209 system which was equipped with a mass spectrometer for weight loss investigation. IR spectra were taken on a JASCO FT-IR 460 Plus using KBr pellets. ^{27}Al MAS NMR spectroscopy was performed on a Bruker AV300 NMR spectrometer using a 4 mm rotor and 15 kHz with 2050 scans (78.2061 MHz for ^{27}Al). The elemental composition of the samples was determined using conventional CHNS analysis. Ca and Al contents were obtained by atomic absorption spectroscopy. SEM pictures were taken on a FEI XL 30 FEG environmental scanning electron microscope. TEM investigation was conducted on a JEOL JEM 2010 microscope.

Acknowledgments

The authors would like to thank Dr. M. Hanzlik for the TEM images, Dr. G. Raudaschl-Sieber for NMR measurements, Dipl.-Chem. M. Gretz for recording of SEM pictures and R. Beiderbeck for TG measurements. The contribution of N. Zou is greatly acknowledged.

- [1] V. Fernon, A. Vichot, N. Le Goanvic, P. Colombet, F. Corazza, U. Costa, *American Concrete Institute* **1997**, SP-173, 225 - 248.
- [2] J. Plank, Z. Dai, P. Andres, *Mater. Lett.* **2006**, 6, 3614 - 3617.
- [3] J. Plank, H. Keller, P. Andres, Z. Dai, *Inorg. Chim. Acta* **2006**, 359, 4901 - 4908.
- [4] J. Plank, Z. Dai, N. Zouaoui, *J. Phys. Chem. Solids* **2007**, 69, 1048 - 1051.
- [5] S. Carlino, *Solid State Ionics* **1997**, 98, 73 - 84.
- [6] J. Plank, A. Aignesberger, *DE 3344291A1* **1985**
- [7] C. Taviot-Guého, F. Leroux in *Struct. Bonding* **2006**, 119, pp. 121 - 159.
- [8] F. Leroux, J. Besse, *Chem. Mater.* **2001**, 13, 3507 - 3515.
- [9] A. Khan, D. O'Hare, *J. Mater. Chem.* **2002**, 12, 3191 - 3198.
- [10] R. Allmann, *Chimia* **1970**, 24, 99 - 108.
- [11] W. Dosch, *Clays Clay Miner.* **1967**, 15, 273 - 292.
- [12] C.O. Oriakhi, I.V. Farr, M.M. Lerner, *J. Mater. Chem.* **1996**, 6, 103 - 107.
- [13] M. Meyn, K. Beneke, G. Lagaly, *Inorg. Chem.* **1990**, 29, 5201 - 5207.
- [14] O. Henning in *Infrared Spectra Miner.* **1974**, pp. 445 - 463.
- [15] C. Houtepen, H. Stein, *Spectrochim. Acta* **1976**, 32A, 1409 - 1414.
- [16] J. Plank, F. Dugonjic-Bilic, N. Lummer, *J. Appl. Polym. Sci.* **2009**, 111, 2018 - 2024.
- [17] D. Stephan, P. Wilhelm, *Z. Anorg. Allg. Chem.* **2004**, 630, 1477 - 1483.
- [18] P. Faucon, T. Charpentier, D. Bertrandie, A. Nonat, J. Virlet, J. Petit, *Inorg. Chem.* **1998**, 37, 3726 - 3733.

Received: ((will be filled in by the editorial staff))
Published online: ((will be filled in by the editorial staff))

Figure 1. Chemical structure of the acetone formaldehyde sulfite polycondensate

Figure 2. XRD pattern of the Ca-Al-AFS-LDH and C_4AH_{13}

Figure 3. IR spectra of C_4AH_x , AFS and the Ca-Al-AFS-LDH

Figure 4. ^{27}Al MAS NMR spectra of Ca-Al-AFS-LDH

Figure 5. TG analysis of C_4AH_x , AFS and the Ca-Al-AFS-LDH

Figure 6. TG-MS curves of C_4AH_x , AFS and the Ca-Al-AFS-LDH for $m/z = 18$ (release of H_2O)

Figure 7. TG-MS curves of C_4AH_x , AFS and the Ca-Al-AFS-LDH for $m/z = 64$ (release of SO_2)

Figure 8. SEM micrograph of Ca-Al-AFS-LDH
(magnification: 20,000)

Figure 9. TEM micrograph of Ca-Al-AFS-LDH

33x27mm (600 x 600 DPI)

33x27mm (600 x 600 DPI)

34x27mm (600 x 600 DPI)

35x27mm (600 x 600 DPI)

33x27mm (600 x 600 DPI)

34x27mm (600 x 600 DPI)

227x170mm (72 x 72 DPI)