Electrically Insulated Molecular Wires

Mircea Grigoras, Loredana Stafie

► **To cite this version:**

Mircea Grigoras, Loredana Stafie. Electrically Insulated Molecular Wires. *Supramolecular Chemistry*, 2010, 22 (04), pp.237-248. 10.1080/10610270903410496 . hal-00576632

HAL Id: hal-00576632

<https://hal.science/hal-00576632>

Submitted on 15 Mar 2011

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Electrically Insulated Molecular Wires

Journal:	<i>Supramolecular Chemistry</i>
Manuscript ID:	GSCH-2009-0020.R2
Manuscript Type:	Review
Date Submitted by the Author:	12-Oct-2009
Complete List of Authors:	GRIGORAS, MIRCEA; "P. Poni" Institute of Macromolecular Chemistry, Electroactive Polymers department Stafie, Loredana; "P. Poni" Institute of Macromolecular Chemistry, Electroactive Polymers Department
Keywords:	supramolecular structures, conducting polymers, macrocyclic compounds, pseudorotaxane and rotaxane architecture, electrically insulated molecular wires

150x150mm (96 x 96 DPI)

Article type: **MINI-REVIEW**

Electrically Insulated Molecular Wires

Mircea Grigoras^{*}, Loredana Stafie

“P. Poni” Institute of Macromolecular Chemistry, Electroactive Polymers Department, 41A Gr.
Ghica Voda Alley, 700487, Iasi, Romania

Abstract: This paper is an up-to-date mini-review based on literature data and own results regarding synthesis and properties of conducting (pseudo)rotaxane supramolecular structures. Conjugated polymers e.g. polyarylene, polyheteroarylene, polyaniline, polyarylenevinylene or polyaryleneimine were used as axle, while the macrocyclic components were cyclodextrins, cucurbiturils, cyclophanes or crown ethers. Properties of the supramolecular structure such as solubility, thermal or chemical stability, conductivity, etc can be drastically modified by inclusion of hydrophobic conjugated polymers inside of the macrocycle, without any chemical modification. For instance, the photophysical properties (i.e., quantum yield of fluorescence and electroluminescence) of the supramolecular structures were enhanced when compared with uninsulated conjugated polymers. The doping process is also affected, because the access of dopant to conjugated chain is limited only to the uncovered domains of conjugated chain.

Keywords: supramolecular structures, conducting polymers, macrocyclic compounds, pseudorotaxane and rotaxane architecture, electrically insulated molecular nanowires.

^{*)} Corresponding author: Tel: +40-0232-217454 Fax: +40-0232-211299

E-mail: grim@icmpp.ro, grigoras47@yahoo.com

1. Introduction

Conjugated polymers and their doped forms have recently attracted tremendous interest due to their potential applications in micro- and nano-electronics and optoelectronics [1]. Their important role in macromolecular chemistry and material science was recognized by awarding the 2000 Nobel Prize in Chemistry "*for the discovery and development of conductive polymers*" to Professors Alan Heeger and Alan MacDiarmid from USA and Hideki Shirakawa from Japan [2]. Moreover, their applications in organic light emitting diodes (OLED) [3] and organic field effect transistors (OFET) [4] had been reported. Recently, work investigating their use as active elements in solar energy conversion as photovoltaic cells is very encouraging and many efforts have been directed in this field [5]. Unfortunately, due to their intrinsic structure, conjugated polymers are insoluble and non-moldable materials, with poor mechanical and environmental properties and thermal instability. Therefore their technological applications are limited by processing difficulties and in most cases they cannot be transformed into usable forms after synthesis, meaning the desired form for devices has to be obtained directly during the polymerisation process. Electrochemical polymerisation is the best method from this point of view but is limited only to a few monomers and some applications. Various studies have been undertaken to obtain soluble conjugated polymers and overcome these drawbacks by changing the structure of monomers or by the introduction of a bent, crankshaft-shaped, or lateral substituent in the main chain of the polymer [1 and references therein]. Alternatively, the structural irregularities in the main chain of the polymers can be controlled by copolymerization. All these variations need new monomers, new polymerisation methods and techniques or sophisticated and expensive catalytic systems. Moreover, the increase of solubility by modifying the main chain structure is accompanied in most cases by an alteration of electronic conjugation with resulting effects on electronic and optoelectronic properties.

An alternative strategy for improving conducting polymer processability is to build supramolecular structures by wrapping the polymer into several macrocyclic molecules. This usually involves non-covalent interactions between the linear polymer chain and cyclic component to form a mechanically interlocked molecule such as pseudopolyrotaxane or polyrotaxane [6-13]. The role of macrocycles is both to insulate the conjugated backbone and to control intermolecular interactions, while the electronic structure of the conjugated core is fully

preserved. The macrocycles have freedom to translate or rotate along or around the polymer backbone without affecting the effective conjugation length.

A conducting polymer with (pseudo)rotaxane architecture can be envisioned as an electrically molecular nanowire. It is based on a one-dimensional conjugated macromolecular chain as a good transporter of the charge carriers, electrons and holes, insulated by many macrocycles threaded on it (Figure 1).

< Insert Figure 1 >

To prevent dethreading of the macrocycles, the ends of the linear molecular wire are blocked with bulky groups (stoppers), and the pseudorotaxane is transformed in a rotaxane structure. The conducting macromolecular (pseudo)rotaxanes have been synthesized by three routes [6]:

- (a) monomer polymerization in the presence of a macrocyclic compound,
- (b) threading of a preformed linear polymer chain through many macrocycles, and
- (c) polymerisation of a (pseudo)rotaxane monomer.

Depending on the location of the rotaxane/pseudo(rotaxane) unit, polymeric rotaxanes can be divided in two classes: main chain- or side chain polyrotaxanes.

Most of the studies reported so far regarding conducting polymers are focused on the main chain polyrotaxanes using cyclodextrins or cucurbiturils as hosts.

2. Conjugated polymers

It is known that conducting polymers are insoluble in most organic solvents but their rotaxane structures are soluble in polar solvents (DMF, DMAc, THF, etc) and even in water. The following conjugated polymers were encapsulated in macrocycles: polyheterocycles (polythiophenes and polypyrroles), polyarylenes, polyarylenevinylenes, polyaryleneimines and polyanilines (Figure 2). Heterocyclic polymers, polypyrrole and polythiophene, were synthesized starting from thiophene or pyrrole, either by chemical or electrochemical oxidative polymerization. In some instances, functional derivatives were successfully polymerized via metal-catalyzed polycondensations [14,15]. Polyarylenes [16], polyarylenevinylenes [17] and polyaryleneimines [18] are obtained mostly by polycondensation methods. Polyaniline is another well-known conjugated polymer, which can be synthesized as a powder or a thin film with colours depending strongly on the experimental conditions and doping state [19]. Polyaniline is of particular interest since it is the only conjugated polymer of the above mentioned that is

usually synthesised in aqueous solution. The good solubility of aniline in 1M HCl aqueous solution makes its oxidative polymerization possible in this solvent. In contrast, the water solubility of other monomers (pyrrole, thiophene and their derivatives) is very low but it can be increased by encapsulation in water-soluble macrocyclic compounds such as cyclodextrins (CDs) and crown ethers.

< Insert Figure 2 >

3. Macrocyclics as insulating materials

A variety of macrocyclic compounds were tried as shell materials for electrical insulation of conducting polymers. So far, most of the synthesised electrically insulated molecular wires are based on cyclodextrins and cucurbiturils as protecting shell. The chemical structures and average dimensions of cyclodextrins and cucurbiturils are presented in Figure 3 and Table 1.

Cyclodextrins (CDs) are carbohydrate-based cyclic compounds consisting of six, seven or eight α -(1,4)-linked D-glucopyranose units. They have a torus-shaped structure characterized by hydrophobic cavities and are soluble in water and some protic polar solvents. The CDs can form highly stable inclusion complexes by hydrophobic interactions with a variety of organic guests. This is possible because of their accessibility and good water solubility.

< Insert Figure 3 >

< Insert Table 1 >

Cucurbit[n]urils, abbreviated as CB[n], are a family of macrocyclic cavitands that contain n units derived from glycoluril linked by $2n$ methylene groups derived from formaldehyde and are obtained by acid-catalyzed condensation of glycoluril and formaldehyde. The molecule is like an open-ended pumpkin with a hydrophobic cavity accessible through two polar and identical carbonyl fringed portals. Similar to CDs, CBs have rigid structures and hydrophobic cavities and are useful building blocks of supramolecular structures. Rotaxane, pseudorotaxane and catenane supramolecular assemblies containing CB[6] and its higher homologues [$n=7,8$] as hosts and non-conjugated polymers have been synthesized and studied recently [23-29]. However, unlike CDs, the CB[n] compounds are rarely used in molecular wire synthesis, mainly due to lower solubility in common organic solvents. Their solubility in strongly acidic aqueous solutions

limits their use because the synthesis of the conjugated polymers is more difficult in these solvents. However, two conjugated polymers (polyaniline and polyphenylene vinylene) have been used in obtaining of pseudopolyrotaxane structures with CB[6] or CB[7] as macrocycles. Both polymers can be synthesized in aqueous solution either by oxidative polymerization of aniline [19] or alkaline modification of polyelectrolyte precursors [17].

The first members of the two macrocyclic classes, α -CD and CB[5], have small internal diameters and the inclusion of aniline, thiophene or pyrrole monomers is difficult to induce due to geometric constrictions.

Other macrocyclics used in synthesis of supramolecular assemblies are presented in Scheme 1.

Scheme 1

Calix[n]arenes, the most accessible type of cyclophanes, are sparingly soluble in some organic solvents and insoluble in aqueous solutions [30]. The water-soluble calixarenes are obtained by the introduction of anionic (sulfonate) groups on the upper or lower rim, or cationic (ammonium) groups on the upper rim [31]. Calix[n]arenes possess architecture similar to CDs but have many conformational isomers because of rotational modes of the phenolic unit. Thus, calix[6]arenes can adopt eight possible conformational forms; cone, partial cone, 1,2-alternate, 1,3-alternate, 1,4-alternate, 1,2,3-alternate, 1,2,4-alternate and 1,3,5-alternate [32]. This large conformational freedom of calix[n]arenes is a disadvantage in rotaxane synthesis compared to CDs and CBs that have a rigid conformation accessible for guest complexation. The inner cavity of calix[6]arene has an opening between 2-2.9 Å, while calix[8]arene in its most expanded conformation (cone) has an opening of 4.5 Å or more in diameter. Therefore, only calix[8]arenes possess a large enough annulus to allow an organic guest molecule to pass through openings. There are a few reports in literature about the use of calix[6]arene for synthesis of a rotaxane [33], but a

conducting polymer hosted by calixarenes has never been reported. Electron poor macrocycles such as bipyridinium-based tetracationic cyclophane, cyclobis (paraquat-p-phenylene) possess the ability to host electron rich guest in order to form pseudorotaxane and catenanes [7-9,34]. Recently the encapsulation of thiophene, bithiophene and terthiophene into an electron-poor macrocycles has been reported although in this example the studies on polyrotaxane formation are not described [35].

Other cyclophane or crown ether compounds possessing two p-phenylene groups or a phenanthroline ring linked by $(-\text{CH}_2-\text{CH}_2-\text{O}-)$ can be used as receptors for metal-template synthesis of catenanes and rotaxanes [6-9,34]. For instance, bithiophene-bipyridine and bithiophene-phenanthroline monomers (Scheme 2) have been prepared and used for template-synthesis of rotaxane monomers with phenanthroline macrocyclic compounds [36-39]. In the presence of Cu^+ and Zn^{2+} salts, bithiophene monomer and phenanthroline macrocycle form a pseudorotaxane in a high yield. Then, the pseudorotaxane is electropolymerized to form polymetallorotaxane structures or metal-free polyrotaxanes after demetallation (Scheme 3) [36].

Scheme 2

Scheme 3 [ref.36]

Swager and colab.[40] have reported in a short communication the inclusion of the electron deficient poly(pyridinium vinylene) into electron rich macrocyclic crown ether. Efficient synthesis of rotaxane supramolecular structures is dependent on intermolecular attractive forces between linear polymer and cyclic component. These forces are entirely physical in nature: hydrophobic-hydrophilic interactions, hydrogen bonding, dipole-dipole interactions (more important in CDs and CB[n] hosts), π - π stacking, π electron donor-acceptor and transition-metal complexation (more important for hosts presented in Scheme 1).

4. Conducting poly(pseudo)rotaxanes

4.1. Polypyrroles and polythiophenes

Pyrrole and thiophene are poorly soluble in water but their solubility can be strongly increased by encapsulation inside CDs or hydroxypropyl -CDs. When pyrrole or thiophene was added to a saturated aqueous solution of CD at room temperature and slight heating, the solution became turbid and a crystalline inclusion complex was formed. Guest molecules can be included inside of CDs in two extreme conformations, with polymerisable positions 2,5 (a) perpendicular or (b) parallel on torrus axle (Scheme 4).

$X = \text{NH}; \text{S}$

$R = (-\text{CH}_2\text{CH}_2\text{O}-)_n \text{ or } (-\text{CH}_2-)_n$

Scheme 4

In the first case, heteroaromatic ring has the polymerisable positions sterically blocked by macrocycle walls and polymerisation is impossible, while for the second case these positions are more accessible.

However, even in the favourable case (b) the monomer is not long enough and the active sites are positioned inside the host. The access of the oxidant in the initiation step or of the monomer molecules in the growing chain step to the aromatic ring is difficult. Therefore an induction period is observed in all oxidative polymerisation of heterocyclics or aniline inclusion products. In fact, this property of CDs has often been used to protect sensitive drugs, by encapsulation or by time releasing of the drugs.

In the rotaxane synthesis, the guest has to preserve its polymerisation ability and to fit inside the host. Additionally, the guest molecules need to be long enough to contain polymerisable sites outside of the macrocycle to facilitate the polymerisation. Lacaze et al [41] reported in 1997 the host-guest complexation of dipyrrolyl monomers with β -CD in aqueous solution. The monomer was modified with aromatic rings linked at N,N' atoms by long and flexible (aliphatic or ethyleneoxide) spacers. Every pyrrole ring was separately encapsulated inside of CD molecules

while the spacer remained free (Scheme 4c). The composition of the inclusion adduct was 1:2. Because the encatennation positions are situated inside of the inner macrocycle cavity, they have hindered access to an oxidant or for electrophilic attack to a neutral molecule. The propagation step is more probable as a result of dissociation of the inclusion adduct. The adduct is in dynamic equilibrium with the host and the guest, and addition to the growing polymer chain is performed outside of the macrocyclic cavity with the participation of free monomers. Thus, the chemical and electrochemical polymerization takes place only with monomers in the decomplexed state and finally polypyrroles without β -CD are obtained (Scheme 5).

Scheme 5

Other heterocycles such as pyrrole and 3,4-ethylenedioxythiophene with α -, β - or γ -CD or randomly dimethylated α -, β - or γ -CD form 1:1 molar ratio crystalline adducts, with a herringbone fashioned cage-type crystal structure [42]. The chemical oxidative polymerisation of these adducts in water, using $K_2S_2O_8$ or $FeCl_3$ as oxidants have led to the formation of insoluble polymers. During the polymerisation reaction, because the adduct is decomplexed, CDs remain in solution and insoluble conjugated polymers are obtained [41]. However, there are few reports on the synthesis of conducting polymers with pseudorotaxane structures using a 2,2'-bithiophene or 5,5-dibromo 2,2'-bithiophene. These monomers were included inside of CD only in the parallel configuration and are long enough to have encatennation positions outside of the macrocycle. Thus, Lacaze et al.[43] have studied the electrochemical polymerisation in aqueous solution of 2,2'-bithiophene hosted inside of hydroxypropyl- β -CD. The complex was soluble in water and a soluble polythiophene with low molecular weight was synthesised. Also, Harada et al.[44] have obtained a low molecular weight polythiophene (5000 daltons) within β -CD or modified β -CD by chemical oxidative polymerization in the presence of $FeCl_3$ as oxidant in aqueous solution. X-ray studies of the crystalline adduct 2,2'-bithiophene/ β -CD consistently showed a 3:2 complex, regardless of the molar ratio between guest and host. Two bithiophene

molecules were included inside the β -CD cavity with a third molecule located horizontally between two β -CD on the secondary hydroxyl side (Scheme 6).

Scheme 6

The third molecule was easily removed by washing with an organic solvent giving the 1:1 composition between 2,2'-bithiophene and β -CD [43]. Conducting pseudorotaxanes were also obtained by including polythiophene or poly(3-methylthiophene) in the cavity of β -CD [45]. Synthesis of polythiophenes by polycondensation using bromine-functionalized bithiophenes allowed blocking of the ends with bulky groups preventing the unthreading of macrocycles. The metal-catalysed polycondensation (Yamamoto reaction) of 5,5'-dibromobithiophene/ β -CD inclusion adduct followed by the blocking of the bromine ends with 9-bromoanthracene led to a polythiophene with rotaxane structure soluble in water and DMSO (Scheme 7) [46]. Usually, polythiophenes with a polymerisation degree greater than 6 are insoluble in any organic solvents but in this case the molecular weight of the water-soluble polythiophene determined by MALDI TOF method corresponds to a degree of polymerisation of 24.

NiCOD is nickel 2,5-cyclooctadiene

Scheme 7 [ref. 46]

Small angle neutron scattering measurements show that the polymer chains have lengths between 4 and 20 nm, while the maximum coverage with the β -CDs is 60%. This suggests that rest of the macrocycles were de-threaded during the polymerisation step.

Another interesting example was the electrochemical synthesis of insulated nanosized wires and nanodots of polypyrrole or polyaniline using thiolated β -CD modified gold electrodes [47,48]. Firstly, the whole surface of the electrode was covered with β -CD molecules anchored by covalent linkages and containing seed molecules of pyrrole or aniline in the inner cavity. Polymerisation started from within the cavities where single nanofibers grown up and are subsequently aligned leading to films with well-oriented morphologies. Sulfonated CDs used in synthesis of polypyrrole play a double role as host and dopant of the conjugated chain [49]. In this case, the presence of sulfonated CDs in the final polymer was evidenced by spectroscopic methods, although the formation of pseudorotaxane structure was not clear demonstrated.

4.2. Polyanilines

Only β -CD, CB[6] and CB[7] were used as hosts in synthesis of polyaniline with pseudorotaxane structure.

Polyaniline/ β -CD pseudorotaxanes were synthesised by two ways.

(i) Chemical oxidative polymerisation of aniline/ β -CD [50] or N-phenyl-1,4-phenylenediamine/ β -CD [51] inclusion adducts, in aqueous solution using ammonium persulfate as oxidant.

Aniline monomer has a small molecular volume with cross sectional diameter of about 0.4 nm. Therefore, it fits closer in the α -CD cavity and an 1:1 adduct resulted, while in β or γ -CD, two aniline molecules can be included but the resulted adduct is less stable due to higher differences between partner dimensions. Chemical oxidative polymerization of aniline/ β -CD adduct was carried out in aqueous solution in acidic (1M HCl) or neutral medium (pH=7). Polyaniline with pseudorotaxane structure was obtained only at pH=7 while in acidic conditions free PANi emeraldine salt was synthesized [50]. The inner surface of the CD's cavity is almost neutral and CDs bind preferentially neutral guest molecules. In acidic conditions, aniline monomer exists predominantly as the anilinium cation carrying a highly hydrophilic $-\text{NH}_3^+$ group and the aniline/ β -CD inclusion complex dissociates to free partners.

(ii) Inclusion of polyaniline emeraldine base inside β -CD rings. The process was carried out by mixing the two solutions of polymer and β -CD in two miscible solvents [50-53]. A blue

precipitate was formed which suggests the formation of the inclusion complex between the two components. Typically, the inclusion of a long linear polymer chain into one or many cyclic molecules is an entropically unfavourable process. However, the hydrophobic interactions, hydrogen-hydrogen and donor-acceptor interactions have promoted the threading of β -CD onto polyaniline when working at lower temperatures (lower than 275 K) [51,53].

Unlike CDs which preferentially host neutral guest molecules, CBs[n] can form very stable host-guest complexes with positively charged molecules, such as anilinium cations or polyaniline-emeraldine salt. Therefore, CB[n] can form more stable complexes with anilinium cations than β -CD. This property, together with CB solubility in acidic aqueous solution, could explain why the first insulating molecular wire containing cucurbit[6]uril has used polyaniline as its conducting core [54]. We have synthesized pseudopolyrotaxane polyaniline/ CB[6] by two methods (Scheme 8):

- (i) by chemical oxidative polymerisation of aniline in presence of CB[6] in acidic aqueous solution using ammonium persulfate as oxidant, and
- (ii) by threading the preformed polyaniline chain through the inner cavity of CB[6]. The second method is entropically unfavorable but is enthalpically driven by noncovalent interactions.

Scheme 8

The number of macrocycles threaded onto polymer chain could not be estimated by elemental analysis or IR and NMR spectroscopy [54].

A polymeric pseudorotaxane based on cucurbit[7]uril and polyaniline has been reported by Liu et al. [55]. Using NMR the authors calculated that every repeating unit contains three aniline units and one CB[7] macrocycle, as shown in Scheme 9 [55].

Scheme 9 [ref. 55]

The threading of many macrocycles onto a single conjugated conducting polymer is accompanied by a coil-rod transition and electronic conjugation can spread over the whole macromolecule. The AFM images evidenced the existence of many small particles for uncomplexed polyaniline (Figure.4,a) and straight fibers for polyaniline/CB[7].

< Insert Figure 4 >

Both samples were synthesised in the same conditions. The widths (ca. 1.5 nm) of PANi/CB[7] fibres are consistent with the outer diameter of CB[7]. A schematic possible structure of PANi-CB[7] is presented in Figure.4,e) [55]. Therefore, the interchain interactions could be avoided by keeping the chains at a distance determined by the thickness of macrocycles, and the electronic properties could be studied for a single conjugated chain. For the first time, Shimomura et al. [56] have determined conductivity of a single insulated molecular wire positioned between two electrodes. The wire is based on a polyaniline macromolecule inserted into a CD nanotube followed by doping of PANi with iodine. The value of conductivity ($4 \cdot 10^{-2} \text{ S} \cdot \text{cm}^{-1}$) was smaller than that of the PANi/I₂ film and explained by the low doping level. The doping process is slow for the encapsulated polymer and needs a larger quantity of dopant or the process is limited only to uncovered domains because the dopant molecules do not have free access to the conjugated chain to reduce or oxidise it [52,56].

4.3. Polyaryleneimines

The first arylenimine polymer (also known as polyazomethines or polyimines) with rotaxane architecture has been synthesised by Simionescu et al [57] by polycondensation in solution of terephthalaldehyde with inclusion adduct α - or β -CD/1,6-diaminohexane. In this case the chain ends have been blocked with a bulky aromatic amine, i.e., p-aniline triphenylmethane to prevent the macrocycle slipping. Fully conjugated rotaxane polyazomethines have been obtained by polycondensation of N-alkyl 3,6-diformyl carbazole with aromatic diamines (1,4-diaminobenzene, 4,4'-diaminobiphenyl) included in α - or β -CD, using p-toluene sulfonic acid (TSA) as a catalyst in N,N'-dimethylformamide and 4-aniline triphenylmethane as stopper [58-62] (Scheme 10). If the alkyl group on the carbazole moiety is butyl or a higher homologue, the use of stoppers at the chain ends for the prevention of macrocycles slippage is not necessary because the movement of the macrocycle along the polymer chain is limited only to the monomer unit. As compared with uninsulated polymers, incorporation of CDs into the imine chain gave a hygroscopic and soluble polymer.

Scheme 10

Other authors have used 60-fullerene as an end-capping agent in the polycondensation of terephthalaldehyde with 1,4-diaminobenzene in the presence of β -CD (Scheme 11) [63]. The macrocycles are able to move along the polymer chain without dethreading from the supramolecular arrangement due to bulky end capping groups.

Scheme 11 (ref. 63)

If the end capping groups agent is not a bulky molecule, for example 2,4-dinitrofluorobenzene, a supramolecular polypseudorotaxane structure was obtained by polycondensation of two complexes, β -CD / o-toluidine and β -CD / terephthalaldehyde (Scheme 12) [64].

Scheme 12 [ref. 64]

The high resolution scanning tunneling microscopy (STM) is a very useful technique to prove the supramolecular structure. The supramolecular aggregates are nanometer-sized molecular wires having ~1.5 nm in diameter (equal with the outer diameter of β -CD) (Figure 5) [64]. All rotaxane polyimines are more hygroscopic and soluble in polar solvents in comparison with the polymers without rotaxane structure [58-64].

< Insert Figure 5 >

4.4. Polyarylenes and polyarylenevinylenes (PPV)

The idea to use polyrotaxane structures to obtain insulated molecular wires came from the Anderson group who has employed polyarylenes and polyarylenevinylenes as conducting axes [65]. The polyarylene rotaxane oligomers have been synthesised by Suzuki cross coupling reaction in aqueous media, for example, the 4,4'-biphenyl *bis*-boronic acid was coupled with 4,4'-diiodobiphenyl 2,2'-dicarboxylic acid in the presence of high excess of α - or β -CD. A bulky

water soluble 1-iodonaphthalene 3,6-disulfonate has been added as a stopper to obtain the rotaxane structure (Scheme 13) [66]. The rotaxane polyarylenes have an average polymerisation degree, $DP=8$, and are soluble in water. This is a useful property as, for instance, polyarylenes with five *para*-phenylene units have very low solubility in any solvent, only 5 mg/L in toluene [67].

Scheme 13 [ref. 66]

This method was further extended for synthesis of poly(*para*-phenylenevinylene) rotaxanes using the palladium catalyzed Heck coupling of benzene 1,4-*bis* vinylboronic acid with 4,4'-diiodostilbene derivatives, in the presence of iodoisophthalate or 1-iodonaphthalene 3,6-disulfonate as stoppers and α - and β -CD as hosts (Scheme 14) [68]. The average polymerisation degree was ~ 10 while the average number of CD per monomer unit was ~ 0.7 .

Scheme 14 [ref. 68]

It was observed that encapsulation always increased the fluorescence efficiency and fluorescence yield because the non-radiative and quenching processes were reduced by protective CD macrocycles [69].

Other attempts to obtain PPV/CB[7] rotaxanes have used the Wessling approach, with *p*-xylylene sulfonium derivatives as intermediates [70]. The formation of a stable inclusion complex between *bis*-sulfonium salt and CB[7] was observed by mass spectroscopy, NMR and UV spectroscopy. It was shown that the phenylene ring is centered in the CB[7] cavity. The

carbonyl portals on CB[7] interacted with the positively charged sulfur atoms via strong ion-dipole interactions. The precursor was very stable and Wessling polymerisation failed [70]. However, recently, the successful synthesis of *rotax*-polyphenylenevinylene encapsulated in CB[7]s was reported (Scheme 15) [71].

Scheme 15 [ref. 71]

The ylide precursor of PPV could be encapsulated inside of CB[6], CB[7] and CB[8] but not inside of CB[5], due to spatial restrictions. However, only ylide-CB[7] complex has been transformed to a pseudorotaxane structure. In other cases, the only PPVs without rotaxane structure were obtained, thought to be due to low stability of the complexes. From chemical analysis based on the N content it was assumed that a CB[7] macrocycle was threaded at every six phenylene vinylene units. Unfortunately, there are no studies that involve the optical and electronic properties of these materials, especially their use in OLED devices.

5. Properties and applications

Properties of (pseudo)rotaxanes are dependent on the nature of the two components: the macrocycle and the conjugated polymer. Encapsulation of the conjugated polymer chain by macrocycles has a positive impact on the overall polymer properties. Supramolecular assemblies are more hydrophilic and more chemically, thermally and environmentally stable, properties induced mainly by the macrocyclic component. The solubility of pseudopolyrotaxanes and polyrotaxanes is dependent on both the conjugated polymer and the macrocycle nature and content. The threading of hydrophilic CD macrocycles onto a hydrophobic polymer chain makes the supramolecular assembly soluble in water or organic polar solvents (DMF, DMAc, THF, DMSO), while the conjugated polymer is insoluble in these solvents. The conformation of the

polymer chain could also be modified by encapsulation. Polyaniline-emeraldine base has a coil conformation but by its inclusion in CD, the conformation was changed to a rodlike one with extended π -conjugation [53]. The insulating shells have a protective action against different destructive factors (oxygen, UV radiations, thermal degradation, chemical reactants) and confer greater resistance to fluorescence quenching by impurities. The macrocycles have isolated and separated the single polymer chain preventing intermolecular interactions between conjugated chains and the aggregation tendency, avoiding formation of excimers, with visible effects in foto- and electroluminescence properties. Also in polyrotaxanes structures, photo- and electroluminescence efficiency is increased compared to free polymers and blue-shifted emission is observed. The conductivity measurements carried out on a single insulated molecular wire could help to differentiate the contribution of intra- and intermolecular charge transfer. However, these studies are in an incipient stage. There is only a short communication dedicated conductivity investigation of a single conducting polymer chain isolated in a CD nanotube [56].

6. Conclusions

The building of conducting polyrotaxane structures has emerged from the necessity to improve solubility and processability of conjugated polymers. Despite the progress of recent years in supramolecular chemistry, much remains to be done in this specific domain.

In general, the synthesis of insulated molecular wires is performed by two methods:

- polymerisation of inclusion compounds formed between monomer (as guest) and macrocyclic component (as host), and
- threading of the macrocycles onto the preformed conducting polymer.

In both cases the compatibility between the monomer/polymer and macrocycles are crucial in the formation of these structure, as well as the physical interactions between the two partners. Moreover, the guest has to fit perfectly in the inner cavity of the macrocyclic compounds and to form stable complexes. If the dimensions of molecular partners are not correlated, they cannot form inclusion adducts (linear partner cannot be threaded inside of inner cavity of macrocyclic compound), or the inclusion adducts are not stable causing macrocycle dethreading. Another requirement is the accessibility of encatennation positions of the monomer included in the cyclic compound to initiator or monomer in the polymerization or polycondensation steps. Otherwise, polymerisation or polycondensation takes place with free (uncomplexed) monomers. Solvents

used in inclusion or polymerization steps also have to be chemically inert for both partners. Control of the degree of insulation of the molecular wire is very difficult, because during the polymerisation or purification steps some macrocycles are unthreaded. The fluorescence quantum yield, electroluminescence efficiency and chemical stability, parameters important for LED applications, are enhanced for encapsulated molecular wires.

Acknowledgments

The authors thank the Romanian National Authority for Scientific Research for financial support (Grant PN II-IDEI-993).

References

- [1] Skotheim, T.A.; Reynolds, J.R. eds. *Handbook of Conducting Polymers*, 3-rd edition CRC Press, New York, 2007.
- [2] Shirakawa, H. The Discovery of Polyacetylene: The Dawning of an Era of Conducting Polymers. *Angew. Chem. Int. Ed.* **2001**, *40*, 2574-2580; MacDiarmid, A.G. Synthetic Metals: A Novel Role for Organic Polymers. *Angew. Chem. Int. Ed.* **2001**, *40*, 2581-2590; Heeger, A.J. Semiconducting and Metallic Polymers: The Fourth Generation of Polymeric Materials. *Angew. Chem. Int. Ed.* **2001**, *40*, 2591-2611 (Nobel Lectures).
- [3] Walzer, K.; Maennig, B.; Pfeiffer, M.; Leo, K. Highly Efficient Organic Devices Based on Electrically Doped Transport Layers. *Chem. Rev.* **2007**, *107*, 1233-1271; Burroughes, J.H.; Bradley, D.D.C.; Brown, A.R.; Marks, R.N.; Mackay, K.; Friend, R.H.; Burns, P.L.; Holmes, A.B. Light-Emitting Diodes Based on Conjugated Polymers. *Nature* **1990**, *347*, 539-540; Forest, S.R. The Path to Ubiquitous and Low Cost Organic Electronic Appliances on Plastic. *Nature* **2004**, *428*, 911-918; Kraft, A.; Grimsdale, A. C.; Holmes, A.B. Electroluminescent Conjugated Polymers- Seeing Polymers in a New Light. *Angew. Chem. Int. Ed.* **1998**, *37*, 402-428.
- [4] Sirringhaus, H.; Tessler, N.; Friend, R.H. Organic Thin Film Transistors for Large Area Electronics. *Adv. Mater.* **2002**, *14*, 99-117.; Murphy, A.R.; Frecht J.M.J. Organic Semiconducting Oligomers for Use in Thin Films Transistors. *Chem. Rev.* **2007**, *107*, 1066-1096.
- [5] Coakley, K.M.; McGehee, M.D. Conjugated Polymer Photovoltaic Cells. *Chem. Mater.* **2004**, *16*, 4533-4542; Granstrom, M.; Petritsch, K.; Arias, A.C.; Lux, A.; Andersson, M.R.; Friend, R.H. Laminated Fabrication of Polymeric Photovoltaic Diodes. *Nature* **1998**, *395*, 257-259.
- [6] Gibson, H.W.; Bheda, M.C.; Engen, P.T. Rotaxanes, Catenanes, Polyrotaxanes, Polycatenanes and Related Materials. *Progr. Polym. Sci.* **1994**, *19*, 843-945.
- [7] Nepogodiev, S.A.; Stoddart, J.F. Cyclodextrin-Based Catenanes and Rotaxanes. *Chem. Rev.* **1998**, *98*, 1959-1976.
- [8] Raymo, F.M.; Stoddart, J.F. Interlocked Macromolecules. *Chem. Rev.* **1999**, *99*, 1643-1663.
- [9] Sauvage, J.P.; Dietrich-Buchecker, C. Eds. *Molecular Catenanes, Rotaxanes and Knots*; Wiley-VCH, Weinheim, 1999.

- [10] Takata, T.; Kihara, N.; Furusho, Y. Polyrotaxanes and Polycatenanes: Recent Advances in Synthesis and Applications of Polymers Comprising of Interlocked Structures. *Adv. Polym. Sci.* **2004**, *171*, 1-76.
- [11] Kim, K.; Selvapalam, N.; Oh, D.H. Cucurbiturils-a New Family of Host Molecules. *J. Incl. Phenom. Macrocylic Chem.* **2004**, *50*, 31-36.
- [12] Wenz, G.; Han, B. H.; Muller, A. Cyclodextrin Rotaxanes and Polyrotaxanes. *Chem. Rev.* **2006**, *106*, 782-817.
- [13] Harada, A.; Hashidzume, A.; Yamaguchi, H.; Takashima, Y. Polymeric Rotaxanes. *Chem. Rev.* **2009**, Publ. Date (web) September 8, 2009; doi 10.1021/cr9000622
- [14] Jeffries-El, M.; McCullough, D. Regioregular Polythiophenes, p. 9.1-9.49, in: Skotheim, T.A.; Reynolds, J.R. eds. *Handbook of Conducting Polymers*, 3-rd edition CRC Press, New York, 2007.
- [15] Cho, S.H.; Song, K.T.; Lee, J. Y. Recent Advances in Polypyrrole, p. 8.1-8.87, in: Skotheim, T.A.; Reynolds, J.R. eds. *Handbook of Conducting Polymers*, 3-rd edition CRC Press, New York, 2007.
- [16] Lis, E.J.W.; Scherf, U. Blue-Emitting Poly(para-Phenylene)-Type Polymers, p. 5.1-5.35, in: Skotheim, T.A.; Reynolds, J.R. eds. *Handbook of Conducting Polymers*, 3-rd edition CRC Press, New York, 2007.
- [17] Grimsdale, A.C.; Holmes, A.B. Synthesis and Properties of Poly(arylenevinylene)s, p.4.1-4.22, in: Skotheim, T.A.; Reynolds, J.R. eds. *Handbook of Conducting Polymers*, 3-rd edition CRC Press, New York, 2007.
- [18] Grigoras M.; Catanescu, C.O. Imine Oligomers and Polymers. *J. Macromol. Sci. Part C-Polym. Rev.* **2004**, *44*, 131-173.
- [19] Gospodinova, N; Terlemezyan, L. Conducting Polymers Prepared by Oxidative Polymerization: Polyaniline. *Prog. Polym. Sci.* **1998**, *23*, 1443-1484.
- [20] Szejtli, J. *Cyclodextrins and Their Inclusion Complexes*. Akademiai Kiado, Budapest, 1982.
- [21] Lagona J.; Mukhopadhyay P.; Chakrabarti, S.; Isaacs, L. The Cucurbit[n]uril Family. *Angew. Chem. Int. Ed.* **2005**, *44*, 4844-4870.
- [22] Kim, J.; Jung, I.S.; Kim, S.Y.; Lee, G.; Kang, J.K.; Sakamoto, S.; Yamaguchi, K.; Kim, K. New Cucurbituril Homologues: Synthesis, Isolation, Characterization and X-ray Crystal Structures of Cucurbit[n]uril (n= 5,7, and 8). *J. Amer. Chem. Soc.* **2000**, *122*, 540-541.

- [23] Tuncel, D.; Steinke, J.H.G. Catalytic Self-Threading: A New Route for the Synthesis of Polyrotaxanes. *Macromolecules*, **2004**, *37*, 288-302.
- [24] Whang, D.; Jeon, Y.M.; Heo, J.; Kim, K. Self-assembly of a Polyrotaxane Containing a Cyclic "Bead" in Every Structural Unit in the Solid State: Cucurbituril Molecules Threaded on a One-Dimensional Coordination Polymer. *J. Am. Chem. Soc.* **1996**, *118*, 11333-11334.
- [25] Wang, D.; Kim, K. Polycatenated Two-Dimensional Polyrotaxane Net. *J. Am. Chem. Soc.* **1997**, *119*, 451-452.
- [26] Whang, D.; Park, K.M.; Heo, J.; Ashton, P.; Kim, K. Molecular Necklace: Quantitative Self-Assembly of a Cyclic Oligorotaxane from Nine Molecules. *J. Am. Chem. Soc.* **1998**, *120*, 4899-4900.
- [27] Park, K.M.; Kim, S.Y.; Heo, J.; Whang, D.; Sakamoto, S.; Yamaguchi, K.; Kim, K. Designed Self-Assembly of Molecular Necklaces. *J. Am. Chem. Soc.* **2002**, *124*, 2140-2147.
- [28] Tan, Y.; Choi, S.W.; Lee, J.W.; Ko, Y.H.; Kim, K. Synthesis and Characterization of Novel Side-Chain Pseudopolyrotaxanes Containing Cucurbituril. *Macromolecules* **2002**, *35*, 7161-7165.
- [29] Isobe, H.; Sato, S.; Nakamura, E. Synthesis of Disubstituted Cucurbit[6]uril and Its Rotaxane Derivative. *Org. Lett.* **2002**, *4*, 1287-1289.
- [30] Gutsche, C.D.; Dhawan, B.; No, K.H.; Muthukrishnan, R. Calixarene.4. The Synthesis, Characterization of the Calixarenes from *p*-*tert*-Butylphenol. *J. Am. Chem. Soc.* **1981**, *103*, 3782-3792.; Gutsche, C.D. Calixarenes. *Acc. Chem. Res.* **1983**, *16*, 161-170.
- [31] Shinkai, S.S.; Arimura, T.; Araki, K.; Kawabata, H.; Satoh, H.; Tsubaki, T.; Manabe, O.; Sunamoto, J. Synthesis and Aggregation Properties of New Water-soluble Calixarenes. *J. Chem. Soc. Perkin Trans I* **1989**, 2039-2045.
- [32] Ikeda, A.; Shinkai, S. Novel Cavity Design Using Calix[n]arene Skeletons: Toward Molecular Recognition and Metal Binding. *Chem. Rev.* **1997**, *97*, 1713-1734.
- [33] Arduini, A.; Ferdani, R.; Pochini, A.; Secchi, A.; Ugozzoli, F. Calix[6]arene as a Wheel for Rotaxane Synthesis. *Angew Chem. Int. Ed.* **2000**, *39*, 3453-3456.
- [34] Dietrich-Buchecker, C.O.; Sauvage, J.P.; Interlocked of Molecular Threads: From the Statistical Approach to the Templated Synthesis of Catenands. *Chem. Rev.* **1987**, *87*, 795-810.
- [35] Ikeda, T.; Higuchi, M.; Kurth, G.G. Inclusion complexation of cyclobis(paraquat-p-

phenylene) with thiophene, bithiophene and terthiophene. *J. Incl. Phenom. Macrocycl Chem.* early view DOI 10.1007/s10847-009-9566-1.

[36] Zhus, S.S.; Carroll, P.J.; Swager, T.M. Conducting Polymetallorotaxanes: A Supramolecular Approach to Transition Metal Ion Sensors. *J. Amer. Chem. Soc.* **1996**, *118*, 8713-8714.

[37] Zhu, S.S.; Swager T.M. Conducting Polymetallorotaxanes: Metal Ion Mediated Enhancements in Conducting and Charge Localization. *J. Amer. Chem. Soc.* **1997**, *119*, 12568-12577.

[38] Vidal P.L.; Billon, M.; Divisia-Blohorn, B.; Bidan, G.; Kern, J.M.; Sauvage J.P. Conjugated Polyrotaxanes Containing Coordinating Units: Reversible Copper (I) Metallation-Demetallation using Lithium Intermediate Scaffolding. *Chem. Commun.*, **1998**, 629-630.

[39] Kern, J. M.; Sauvage, J. P.; Bidan, G.; Divisia- Blohorn, B. Transition-Metal-Templateed Synthesis of Rotaxanes and Catenanes: From Small Molecules to Polymers. *J. Polym. Sci., Polym. Chem.*, **2003**, *41*, 3470-3477.

[40] Marsella, M.J.; Swager, T.M. Conducting Polyrotaxanes: Insulated Wires and Molecular Straws. *Polym. Prepr. ACS*, **1994**, *35*(1) 275-276.

[41] Chane-Ching, K.I.; Lacroix, J.C.; Jouini, M.; Lacaze, P.C. Electropolymerization of hydrophobic dipyrrolys in aqueous medium based on inclusion chemistry. *J. Mater. Chem.* **1999**, *9*, 1065-1070.

[42] Storsberg, J.; Ritter, H.; Pielartzik, H.; Groenendaal, L. Cyclodextrin in Polymer Synthesis: Supramolecular Cyclodextrin Complexes of Pyrrole and 3,4-Ethylenedioxythiophene and Their Oxidative Polymerization. *Adv. Mater.* **2000**, *12*, 567-569.

[43] Lagrost, C.; Lacroix, J.C.; Aeijach, S.; Jouini, M.; Chane-Ching, K.I.; Lacaze, P.C. Host-Guest Complexation: a New Strategy for Electrodeposition of Processable Polythiophene Composites from Aqueous Medium. *Chem. Commun.* **1998**, 489-490.

[44] Takashima, T.; Oizumi, Y.; Sakamoto, K.; Miyauchi, M.; Kamitori, S.; Harada, A. Crystal Structure of the Complex of β -Cyclodextrin with Bithiophene and their Oxidative Polymerization in Water. *Macromolecules* **2004**, *37*, 3962-3964.

[45] Yamaguchi, K.; Kashiwagi, T.; Yamamoto, T. β -Cyclodextrin Pseudopolyrotaxanes with π -Conjugated Polymer Axels. *Macromol. Rapid Commun.* **2004**, *25*, 1163-1166.

- [46] Boogard, M.; Bonnet, G.; van't Hoff, P.; Wang, Y.; Brochon, C.; Hutten, P.; Lapp, A.; Hadziioannou, G. Synthesis of Insulated Single-Chain Semiconducting Polymers Based on Polythiophene, Polyfluorene, and β -Cyclodextrin. *Chem. Mater.* **2004**, *16*, 4383-4385.
- [47] Lee, J.; Park, S. Electrochemistry of Conductive Polymers: XXIV. Polypyrrole Films Grown at Electrodes Modified with β -Cyclodextrin Molecular Templates. *J. Electrochem. Soc.* **2000**, *147*, 4189-4195.
- [48] Park, S. M.; Lee, J. Y.; Choi, S. J. Growth and Characterization of Nanosized Structures of Conducting Polymers. *Synth. Met.* **2001**, *121*, 1297-1298.
- [49] Chen, W.; Wan, X.; Xu, N.; Xue, G. Ordered Conducting Polypyrrole Doped with Sulfopropyl Ether of β -Cyclodextrin. *Macromolecules* **2003**, *36*, 276-278.
- [50] Grigoras, M.; Conduruta, G. D. Chemical Oxidative Polymerization of β -Cyclodextrin/Aniline Inclusion Complex. *J. Incl. Phenom. Macrocylic Chem.* **2006**, *54*, 101-107.
- [51] Yuan, G.L.; Kuramoto, N.; Takeishi, M. Preparation of Inclusion Complex between Polyaniline and β -Cyclodextrin. *Polym Adv. Technol.* **2003**, *14*, 428-432.
- [52] Shimomura, T.; Yoshida, K.; Ito, K.; Hayakawa, R. Insulation Effect of an Inclusion Complex Formed by Polyaniline and β -Cyclodextrin in Solution. *Polym. Adv. Technol.* **2000**, *11*, 837-839.
- [53] Yoshida, K.; Shimomura, T.; Ito, K.; Hayakawa, R. Inclusion Complex Formation of Cyclodextrin and Polyaniline. *Langmuir* **1999**, *15*, 910-913.
- [54] Grigoras, M.; Conduruta, D.G. Pseudorotaxanes based on Polyaniline and Cucurbituril, *Rev. Roum. Chim.* **2006**, *51*, 987-992.
- [55] Liu, Y., Shi, J., Chen, Y., Ke, C.F. A Polymeric Pseudorotaxane Constructed from Cucurbituril and Aniline, and Stabilization of Its Radical Cation. *Angew. Chem. Int. Ed.*, **2008**, *47*, 1-5.
- [56] Shimomura, T.; Akai, T.; Fujimori, M.; Heike, S.; Hashizume, T.; Ito, K. Conductivity measurement of insulated molecular wire formed by molecular nanotube and polyaniline. *Synth. Met.* **2005**, *153*, 497-500.
- [57] Simionescu, C.I.; Grigoras, M.; Farcas, A.; Stoleru, A. Synthesis and Characterization of Poly(azomethine)s with Rotaxane Architecture. *Macromol. Chem. Phys.* **1998**, *199*, 1301-1306.

- [58] Farcas, A.; Grigoras, M. Poly(azomethine)s with Rotaxane Architecture Containing a Blocking group in Every Structural Unit: Synthesis and Characterization. *High Perf. Polym.* **2001**, *13*, 149-158.
- [59] Farcas A.; Grigoras, M. Synthesis and Characterization of a Fully Aromatic Polyazomethine with Main Chain Rotaxane Architecture *High Perf. Polym.* **2001**, *13*, 201-210.
- [60] Farcas A.; Grigoras M.; Simionescu C. I. Poly(aromatic azomethine)s Containing Non-covalently bound Cyclodextrins in the Main-chains: Synthesis and Characterization. *Rev. Roum. Chim.* **2001**, *46*, 25-30.
- [61] Farcas, A.; Grigoras M. Semiconducting Polymers with Rotaxane Architecture. *J. Optoelectron. Adv. Mater.* **2000**, *2*, 525-530.
- [62] Farcas, A.; Grigoras, M. Synthesis and Characterization of a Fully Aromatic Polyazomethine with Rotaxane Architecture. *Polym. Int.* **2003**, *52*, 1315-1320.
- [63] Nepal, D.; Samal, S.; Geckeler, K. E. The First Fullerene-Terminated Soluble Poly(azomethine) Rotaxane. *Macromolecules* **2003**, *36*, 3800-3802.
- [64] Liu, Y.; Zhao, Y.L.; Zhang, H.Y.; Li, X.Y.; Liang, P.; Zhang, X.Z.; Xu, J.J. Supramolecular Pseudorotaxane with Conjugated Polyazomethine prepared Directly from Two Inclusion Complexes of β -Cyclodextrin with Tolidine and Phthaldehyde. *Macromolecules* **2004**, *37*, 6362-6369.
- [65] Anderson, S.; Anderson, H.L. Synthesis of a Water-Soluble Conjugated [3]rotaxane. *Angew. Chem. Int. Ed.* **1996**, *35*, 1956-1958.
- [66] Stanier, C.A.; O'Connell, J.; Clegg, W.; Anderson, H.L. Synthesis of Fluorescent Stilbene and tolan Rotaxanes by Suzuki Coupling. *Chem. Commun.* **2001**, 493-494.
- [67] Wirth, H. O.; Kern, W.; Schmitz, E. Synthese und eigenschaften von verzweigten Oligophenylenen, die sich von 1,3,5-Triphenylbenzol ableiten 14. Mitteilung. *Makromol. Chem.* **1963**, *68*, 69-99.
- [68] Terao, J.; Tang, A.; Michels, J.J.; Krivokapic, A.; Anderson, H.L. Synthesis of Poly(para-phenylenevinylene) Rotaxanes by Aqueous Suzuki Coupling. *Chem. Commun.* **2004**, 56-57.
- [69] Caccialli, F.; Wilson, J.S.; Michels, J.J.; Daniel, C.; Silva, C.; Friend, R.H.; Severin, N.; Samori, P.; Rabe, J.P.; O'Connell, M.J.; Taylor, P.N.; Anderson, H.L. Cyclodextrin-threaded Conjugated Polyrotaxanes as Insulated Molecular Wires with Reduced Interstrand Interactions. *Nature Materials* **2002**, *1*, 160-164.

[70] Ling, Y.; Kaifer, A.E. Complexation of Poly(phenylenevinylene) Precursors and Monomers by Cucurbituril Hosts. *Chem. Mater.* **2006**, *18*, 5944-5949

[71] Corma A., Garcia, H., Montes-Novajas, P. A Pseudopolyrotaxane Consisting in PPV threaded in Multiple Cucurbiturils. *Tetrahed. Lett.*, **2007**, *48*, 4613-4617.

For Peer Review Only

FIGURES

Figure 1: Structure of insulated organic molecular wires.

Figure 2: Chemical structure of some conducting polymers used as axles.

Figure 3: Chemical and geometrical structure of cyclodextrins and cucurbiturils.

Figure 4: AFM images of (a) polyaniline; (b) section analysis of the black line in (a); (c) polyaniline/CB[7]; (d) section analysis of the black image in (c), and (d) possible structure of polyaniline/CB[7]. [Reproduced with permission from ref. 55].

Figure 5: STM images of the pseudorotaxane obtained from condensation of β -cyclodextrin/o-tolidine with β -cyclodextrin/p-phthaldehyde; (a) on a highly ordered pyrolytic graphite; (b) 3D mode of STM image, and (c) the molecular modeling structure of polypseudorotaxane. [Reproduced with permission from ref. 64]

Table 1: Average dimensions of CD[n]s and CB[n]s

Macrocycles				Reference
Cyclo[n]dextrins	n=6 (α -CD)	n=7 (β -CD)	n=8 (γ -CD)	[20,21]
Upper portal (nm)	0.47	0.60	0.75	
Lower portal (nm)	0.53	0.65	0.83	
Height of molecule (nm)	0.79	0.79	0.79	
Cucurbit[n]uril	n=6, CB[6]	n=7, CB[7]	n=8, CB[8]	[22]
Diameters:				
Portal diameter (nm)	0.39	0.54	0.69	
Cavity diameter (nm)	0.58	0.73	0.81	
Outer diameter (nm)	1.44	1.60	1.75	
Cavity volume ($\text{\AA}^3$)	164	279	470	
Height of molecule (nm)	0.91	0.91	0.91	

Table 1: Average dimensions of CD[n]s and CB[n]s

Macrocycles				Reference
Cyclo[n]dextrins	n=6 (α -CD)	n=7 (β -CD)	n=8 (γ -CD)	[20,21]
Upper portal (nm)	0.47	0.60	0.75	
Lower portal (nm)	0.53	0.65	0.83	
Height of molecule (nm)	0.79	0.79	0.79	
Cucurbit[n]uril	n=6, CB[6]	n=7, CB[7]	n=8, CB[8]	[22]
Diameters:				
Portal diameter (nm)	0.39	0.54	0.69	
Cavity diameter (nm)	0.58	0.73	0.81	
Outer diameter (nm)	1.44	1.60	1.75	
Cavity volume ($\text{\AA}^3$)	164	279	470	
Height of molecule (nm)	0.91	0.91	0.91

Figure 1: Structure of insulated organic molecular wires.
150x150mm (96 x 96 DPI)

Figure 2: Chemical structure of some conducting polymers used as axes.
150x150mm (96 x 96 DPI)

Figure 3: Chemical and geometrical structure of cyclodextrins and cucurbiturils.
150x150mm (96 x 96 DPI)

Figure 4: AFM images of (a) polyaniline; (b) section analysis of the black line in (a); (c) polyaniline/CB[7]; (d) section analysis of the black image in (c), and (d) possible structure of polyaniline/CB[7]. [Reproduced with permission from ref. 55].
150x150mm (96 x 96 DPI)

Figure 5: STM images of the pseudorotaxane obtained from condensation of β -cyclodextrin/o-tolidine with β -cyclodextrin/p-phthaldehyde; (a) on a highly ordered pyrolytic graphite; (b) 3D mode of STM image, and (c) the molecular modeling structure of polypseudorotaxane. [Reproduced with permission from ref. 64]
150x150mm (96 x 96 DPI)

Scheme 1
150x150mm (96 x 96 DPI)

Scheme 2
150x150mm (96 x 96 DPI)

Scheme 3 [ref.36]
246x150mm (96 x 96 DPI)

Scheme 4
150x150mm (96 x 96 DPI)

Scheme 5
150x150mm (96 x 96 DPI)

Scheme 6
150x150mm (96 x 96 DPI)

NiCOD is nickel 2.5-cyclooctadiene

Scheme 7 [ref. 46]
150x150mm (96 x 96 DPI)

Scheme 8
150x150mm (96 x 96 DPI)

Scheme 9 [ref. 55]
240x150mm (96 x 96 DPI)

Scheme 10
170x150mm (96 x 96 DPI)

Scheme 11 (ref. 63]
252x150mm (96 x 96 DPI)

Scheme 12 [ref. 64]

299x150mm (96 x 96 DPI)

Scheme 13 [ref. 66]
150x150mm (96 x 96 DPI)

Scheme 14 [ref. 68]
208x150mm (96 x 96 DPI)

Scheme 15 [ref. 71]
182x150mm (96 x 96 DPI)