Fabrication and characterization of acoustic waveguides using Silicon/PPT/Silicon structures and analysis of diffraction effects for various modelings

F. Bassignot, G. Ulliac, Thierry Laroche, J. Garcia, E. Courjon, S. Ballandras, J.-M. Lesage

► To cite this version:

F. Bassignot, G. Ulliac, Thierry Laroche, J. Garcia, E. Courjon, et al.. Fabrication and characterization of acoustic waveguides using Silicon/PPT/Silicon structures and analysis of diffraction effects for various modelings. 2010 IEEE International Frequency Control Symposium, Jun 2010, New Port Beach, United States. pp.137-141, 10.1109/FREQ.2010.5556358 . hal-00578913

HAL Id: hal-00578913

<https://hal.science/hal-00578913>

Submitted on 19 Apr 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Distributed under a Creative Commons Attribution| 4.0 International License

Fabrication and characterization of acoustic waveguides using Silicon/PPT/Silicon structures and analysis of diffraction effects for various modelings

F. Bassignot, G. Ulliac, T. Laroche, J. Garcia,
E. Courjon, S. Ballandras
Institut FEMTO-ST
UMR 6174 CNRS-UFC-ENSMM-UTBM
26 che. de l'épitaظه, 25000 Besançon, France
florent.bassignot@femto-st.fr

J.M. Lesage
CELAR
DGA
Rennes, France

Abstract—In this paper, we present new results on the development of a new acoustic waveguide concept using an acoustic wave excited by a Periodically Poled Transducer (PPT) and guided by guiding layers. Periodically poled transducers have been investigated recently as an alternative to classical inter-digital transducers for the excitation and detection of guided acoustic waves. The fabrication of PPTs operating in the range 50 – 500 MHz has been achieved on 3 and 4 inches 500 μm thick lithium niobate (LiNbO_3) and tantalate (LiTaO_3) Z-cut wafers. The compact structure proposed allows high frequency operation with a simplified package based on Si/ LiNbO_3 /Si material combination. Dispersion properties have been studied for this structure in order to find operating points corresponding to a specific thickness/period ratio. Two main devices have been fabricated, a Si/500 μm thick PPT/Si structure in order to validate the concept and a Si/20 μm thick PPT/Si structure to excite only one acoustic wave in the purpose of diffracting this wave. The experimental responses of the tested devices are compared to the predicted harmonic admittances, showing a good agreement between both results. The temperature sensitivity of the excited wave of both structures are also been measured and predicted. Finally, we expose different structures with impedance mismatches generating scattering effects.

I. INTRODUCTION

New guiding principles are currently investigated to develop high frequency devices capable to answer the RF manufacturer demand for telecommunication components. Nowadays, these components are more and more based on acoustic devices. In fact, acoustic resonators are usually based on surface or bulk acoustic waves but they are sensitive to their environment and present some technological limits. Passive components using trapped acoustic waves are thus well-suited for such an application. We suggest a compact structure allowing to guide an acoustic wave operating at high frequency. An acoustic wave is excited by a Periodically Poled Transducer (PPT) which is an alternative to classical inter-digital transducers. This wave is then trapped within a guiding structure. LiNbO_3 and LiTaO_3 , as two piezoelectric and

ferroelectric materials, are tested to fabricate successfully PPTs and silicon substrates are used to guide the acoustic wave and allow a low cost package. Many diffraction analyses are studied to define the best configuration enabling to reflect in-phase the acoustic wave generated in order to exhibit a resonance behavior.

We describe the fabrication process of the new acoustic waveguides. These devices result from the development of piezoelectric transducers based on periodically poled ferroelectric domains in a LiNbO_3 and LiTaO_3 thinned plate bonded between two silicon wafers. By the dispersion properties analysis, we obtain operating points corresponding to a specific thickness/period ratio. We present new experimental results of acoustic waveguides based on sandwich structures as Si/ LiNbO_3 /Si material combinations. We report theoretical results using our finite and boundary element (FEM-BEM) simulation tool. We expose different structures with impedance mismatches generating scattering effects.

The dispersion properties analyses have shown an optimum thickness of the ferroelectric plate, corresponding to the maximum electromechanical coupling coefficient, is found for each PPT period. Si/PPT/Si test vehicles, exhibiting a 50 μm period and a 20 μm thick ferroelectric layer, have pointed out the existence of an isolated mode operating at frequencies near 110 MHz for a LiNbO_3 PPT. Moreover, we have demonstrated experimentally and theoretically that the temperature coefficient of frequency of thinned LiNbO_3 is smaller than the one of thick LiNbO_3 . The diffraction analyses point out a stop-band just with a Si/PPT/Si structure. The corresponding parameters are found close to those of quartz (reflection coefficient magnitude between 0.5 and 1% for one period) with resonance occurring at the end of the stop-band. The addition of reflection structures, as etched patterns in the silicon or the ferroelectric substrates, plays a significant role in the efficiency of wave scattering.

II. A NEW WAVEGUIDE CONCEPT: SUBSTRATE/PPT/SUBSTRATE :

In this part, we will first present a new waveguide concept. We expose then the theoretical results achieved using our finite element/boundary element simulation tool [1], allowing the simulation of such material combinations. After that, the combination of material Si/PPT/Si is chosen (the easiest and the cheapest structure to fabricate) and the dispersion properties of this transducer are studied providing the best operating points.

A. New waveguide concept

An innovative solution has been retained in order to answer to the need of high frequencies sources (RF until X band domain). These sources indeed need spectral purity, short-term stability and phase noise around the carrier wave. The purpose is to fabricate resonators based on the ultrasonic waves propagation through a waveguide. This resonator operates with a PPT structure inserted between two guiding substrates. A wave propagates without any acoustic losses and decreases exponentially in the structure (fig. 1). This definition is similar in these interface waves [2]. Nevertheless, the principle is substantially different for various reasons. First, the transduction structure corresponds to a layer in which ferroelectric domains have been artificially structured as developed in [3-4-5]. Classical interdigital transducers have been given up in this kind of structure because the bonding is difficult due to the electrode pattern. In this case, a polymer film is deposited between both substrates to be bonded in order to create an elastic link introducing important acoustic losses.

Figure 1. Scheme of the new concept waveguide based on PPT

B. Analysis of dispersion properties of this waveguide

We propose to closely investigate how to efficiently derive the dispersion curves and then to show at least for the elliptic mode of the waveguide the influence of the PPT geometry and the operating frequency on the mode properties. In that matter, we have considered the general shape of the waveguide symbolized in fig.2. We assume here a propagation between two silicon layers but the approach can be generalized to any guiding substrate. The period is arbitrarily fixed to 50 μm (i.e. width of each LiNbO_3 domain set to 25 μm , poling ratio=0.5).

Figure 2. Scheme of PPT principle and generic shape for dispersion curve derivation

In Figure 3, we have plotted the theoretical admittance (conductance and susceptance) versus frequency for a thickness/period (h/p) ratio equal to 0.1 with 50 μm of period, in order to identify the main contribution corresponding to an elliptically shaped mode.

Figure 3. Harmonic admittance of the structure plotted in fig.2 for a thickness/period ratio equal to 0.1 with 50 μm of period

Once the mode identified, we follow the evolution of its resonance frequency and electromechanical coupling coefficient for h/p ratios ranging from 0.1 to 2, is plotted on fig.4.

Figure 4. (a) Evolution of the elliptic mode synchronism frequency and (b) electromechanical coupling for small values of h/p ratio (ranging from 0.1 to 2 in our calculation) for different periods

The optimum point of the electromechanical coupling of this device depends of the transducer period (fig.4.a). In fact, the smaller the period, the weaker the electromechanical coupling. Besides, the electromechanical coupling approaches to a

maximum for a 50 μm period. At this point, the coupling is about 0.7%. When the period is smaller than 50 μm , the coupling decreases. The advantage to reduce the period size is to rise the wave celerity (fig.4.b). We can also observe that for a h/p ratio corresponding at an optimum of the electromechanical coupling, we find the maximum of the wave celerity. These operating points are particularly important as it conditions the possibility to improve the design reliability by choosing operation condition poorly affected by technology, which is a key point for any practical exploitation of the device. The next section shows the different technological steps of the fabrication of a Si/PPT/Si device.

III. FABRICATION AND CHARACTERIZATION OF THE NEW ACOUSTIC WAVEGUIDE: SI/THINNED PPT/SI

The analysis of the dispersion properties of a device constituted by Si/LiNbO₃ PPT ($\lambda=50 \mu\text{m}$)/Si has shown a specific operating point for which a single wave is excited with a maximum electromagnetic coupling. This point is obtained for a h/p ratio of about 0.6 corresponding to a 30 μm thick LiNbO₃ PPT. We will also show experimental results obtained with a thick layer of LiNbO₃ in order to compare both devices. Technological steps checking the reliability of the concept using a thick PPT are described in [6].

A. Fabrication of the new waveguide

The fabrication of acoustic waveguides based on PPTs consists in bonding a silicon wafer on each side of the periodically poled wafer. In that purpose, the 500 μm thick Z cut lithium niobate wafer is poled and bonded on a (100) 3" doped silicon wafer using a wafer bonding technique developed in our group based on a metal-metal adhesion at room temperature promoted by a high pressure applied to the material stack (fig.7b). The study of the dispersion properties enables to define a specific configuration using a thinned PPT layer of about 30 μm . The LiNbO₃ wafer thinning is achieved by home-made lapping and polishing techniques. After this step, the stack of Si(380 μm)/LiNbO₃(20 μm) is bonded again on a doped silicon wafer with the same properties that the first one.

Figure 5. (a) Flowchart which summarizes the different steps of fabrication (b) Double bonding of a 20 μm thick lithium niobate layer with two silicon wafers using room temperature Au/Au bonding process

B. Characterizations and comparisons with theory

Two test vehicles have been achieved. The first one allows to check the reliability of the concept, using a Si (380 μm)/LiNbO₃ PPT (500 μm)/Si (380 μm) structure. This structure is easier to fabricate because the PPT is not thinned. The second one based on a Si (380 μm)/LiNbO₃ PPT (20 μm)/Si (380 μm) structure, enables to excite only one isolated mode. In fact, the final project is to create a resonator using this acoustic wave. The characterizations of both devices are obtained with a network analyzer. Figure 6 and 7 present the comparison between the measured responses of the implemented devices and the theoretical harmonic admittances calculated with our periodic finite element code. Measurements have been achieved successfully for the 50 μm period devices, as explained above. Since the implemented single-port test devices are quite long and almost behave as single port resonators, the comparison between measurement and harmonic admittance results makes sense.

Figure 6. Comparison between the test vehicle with 500 μm thick LiNbO₃ admittance and the calculated one

This plot points out the good agreement between both results. We find two main contributions corresponding to the elliptical mode (at 3800 m/s) and the longitudinal mode (at 6500 m/s). We can notice that the experimental admittance increases gradually. The main cause seems to be the wire length of the connection between the device and the support. This proves the feasibility of LiNbO₃-based Silicon/PPT/Silicon devices.

Figure 7. Comparison between the test vehicle with 20 μm thick LiNbO₃ admittance and the calculated one

This plot points out also the good agreement between both results. Only one contribution (except bulk waves) is exited (at 5500 m/s) by the PPT thinned and guided by the silicon. This wave corresponds to an elliptical isolated mode. As we have seen on the dispersion curve, the elliptical wave celerity rises when the thickness of the PPT decreases. In fact, the thinner the PPT, the higher the wave celerity because waves are accelerated by the silicon, which is the guiding material. The parasitic bulk waves seem to come from the electrode shape which is bigger than the transducer. Thanks the experimental admittance curve, the quality factor of the resonance and the electromechanical coupling can be calculated. We have found a Q_f product of $1.1 \cdot 10^{11}$ and a k^2 of 0.65%. As we have seen previously in the analysis part, there is a good agreement between the theoretical and experimental results.

For both devices, we have also measured the experimental admittance at different temperatures (fig.8). For the structure based on a 500 μm thick PPT, the theoretical and the experimental Temperature Coefficient of Frequency (TCF) are in the same order of magnitude at around -80 ppm/K. We can notice that the TCF is sensibly the same than the one of isolated LiNbO_3 devices. For the second structure (20 μm thick PPT), the TCF is considerably smaller than the previous one. We found indeed a TCF equal to about -35 ppm/K. There is a good agreement between experimental and theoretical results. We can notice that the TCF is sensibly the same than the one of the silicon [7].

Figure 8. Theory/experiment comparison for the Temperature Coefficient of Frequency (TCF) for both test vehicles

So the waveguide concept based on a double silicon bonding on a thinned LiNbO_3 PPT layer (about 20 μm) has been validated. Now, the purpose is to use the isolated wave excited to make a resonator for instance. Thus, in the next part, we expose different structures with impedance mismatches generating scattering effects.

IV. DIFFRACTION ANALYSIS

In this part, we propose some structures which would allow the reflection of the wave exited by the PPT. The exploitation of parametric adjustment methods enables, as we have shown in [1], to extract the typical characteristics of the PPT

propagation. Figure 9 presents different structures with impedance mismatches generating scattering effects. Figure 10 points out the stop band evolution for a structure based on a Si/10 μm thick PPLT/Si stack (no etched materials) for periods varying between 15 μm and 35 μm .

Figure 9. Different reflecting structures for the isolated wave

Figure 10. Stop band evolution for various PPLT periods based on the structure with integer reflection coefficient (γ) for a 10 μm thick layer

So, we can notice that the first diffraction analysis point out a stop-band just with a Si/PPT/Si structure.

V. CONCLUSION

Si/PPLN/Si test vehicles, exhibiting a 50 μm period and a 20 μm thick ferroelectric layer, have pointed out the existence of an isolated mode operating at frequencies near 110 MHz. We have experimentally and theoretically demonstrated that the temperature coefficient of frequency of thinned LiNbO_3 (20 μm) is smaller than the one of thick LiNbO_3 (500 μm). This parameter has to be considered for radar applications. The diffraction analyses point out a stop-band just with a Si/PPT/Si structure. The corresponding parameters are found close to those of quartz (reflection coefficient magnitude between 0.5 and 1% for one period) with resonance occurring at the end of the stop-band. The addition of reflection structures, as etched patterns in the silicon or the ferroelectric substrates, plays a significant role in the efficiency of wave scattering.

ACKNOWLEDGMENT

This work was supported by the french DGA (Délégation Générale pour l'Armement) under grant#07-34-020.

REFERENCES

- [1] S. Ballandras, R. Lardat, M. Wilm, Th. Pastureaud, A. Reinhardt, N. Champavert, W. Steichen, W. Daniau, V. Laude, R. Armati, G. Martin, "A mixed finite element/boundary element approach to simulate complex guided elastic wave periodic transducers", accepted for publication in *Journal of Applied Physics*, 2008
- [2] H. Majjad, D. Gachon, V. Laude, S. Ballandras, "Interface acoustic wave devices made by indirect bonding of lithium niobate on silicon", *Proc. of the IEEE US*, 2006
- [3] E. Courjon, J. Hauden, J. Masson, D. Gachon, L. Gauthier Manuel, W. Daniau, N. Bodin, S. Ballandras, "Pure longitudinal plate mode excited by poled domains transducers on LiNbO_3 ", *Proc. of the IEEE IFCS*, 2007
- [4] E. Courjon, J. Hauden, P. Parruch, J. Masson, D. Gachon, L. Gauthier Manuel, W. Daniau, , N. Bodin, J.M. Triscone, S. Ballandras, "Fabrication of periodically poled domains transducers on LiNbO_3 ", *Proc. of the IEEE IFCS, Miami*, 2006
- [5] S. Ballandras, W. Daniau, B. Gautier, D. Hauden, M. Wilm, V. Laude, V. Ruch, S.Flambart, "A novel surface wave transducer based on periodically poled piezoelectric domain", *Proc of the IEEE EFTF-IFCS*, 2003
- [6] F. Bassignot, E. Courjon, G. Ulliac, T. Laroche, J. Garcia, S. Queste, J-P. Romand, S. Ballandras, "An acoustic waveguide using doubly-bonded silicon/thinned PPT/silicon structures for RF applications", *Proc. of the IEEE IUS, Rome*, 2009
- [7] Landolt-Börnstein, Numerical data and functional relationships in science and technology, Group III, Crystal and solid state physics, Vol. 11, K.H. Hellwege and A.M. Hellwege Eds., Springer-Verlag Berlin – Heidelberg – New York (1979)