Controlled Synthesis of Polyepichlorohydrin with Pendant Cyclic Carbonate Functions for Isocyanate-Free Polyurethane Networks

ANNE-LAURE BROCAS,¹ GABRIEL CENDEJAS,¹ SYLVAIN CAILLOL,² ALAIN DEFFIEUX,¹ STEPHANE CARLOTTI¹

¹Université de Bordeaux, Laboratoire de Chimie des Polymères Organiques, CNRS, ENSCBP, 16 avenue Pey Berland, 33607 Pessac Cedex, France

²Institut Charles Gerhardt, UMR5253 CNRS/UM2/ENSCM/UM1, Ecole Nationale Supérieure de Chimie de Montpellier, 8 rue de l'Ecole Normale, 34296 Montpellier Cedex 5, France

Received 2 February 2011; accepted 1 April 2011

DOI: 10.1002/pola.24699

Published online 27 April 2011 in Wiley Online Library (wileyonlinelibrary.com).

ABSTRACT: Poly(allyl glycidyl ether) and poly(allyl glycidyl ether-*co*-epichlorohydrin) were prepared by monomer-activated anionic polymerization. Quantitative and controlled polymerization of allyl glycidyl ether (AGE) giving high molar mass polyether was achieved in a few hours at room temperature in toluene using tetraoctylammonium salt as initiator in presence of an excess of triisobutylaluminum ($[i\text{-Bu}_3\text{Al}]/[\text{NOct}_4\text{Br}] = 2\text{--}4$). Following the same polymerization route, the copolymerization of AGE and epichlorohydrin yields in a living-like manner gradient-type copolymers with controlled molar masses. Chemical

modification of the pendant allyl group into cyclic carbonate was then investigated and the corresponding polymers were used as precursors for the isocyanate-free synthesis of polyurethane networks in presence of a diamine. Formation of cross-linked materials was followed and characterized by infrared and differential scanning calorimetry. © 2011 Wiley Periodicals, Inc. *J Polym Sci Part A: Polym Chem* 49: 2677–2684, 2011

KEYWORDS: anionic polymerization; isocyanate-free; monomer activation; polyepichlorohydrin; polyethers; polyurethanes

INTRODUCTION Polyurethanes materials, thanks to their versatile properties, are found in many applications in everyday life.¹ They are most generally prepared from the reaction of polyols with isocyanates.² However, today researches are more and more focused on a friendly environmental chemistry.^{3,4} One motivation deals with the development of an isocyanate-free route to polyurethanes that would prevent the use of isocyanates and therefore of highly toxic phosgene involved in their synthesis. A second motivation concerns the decrease of fossil feedstock and the use of natural products⁵ as renewable raw chemicals. Among them, vegetable oils constitute an important feedstock already used for the synthesis of biodiesel and as a source of green chemicals.^{6–9} Glycerol, a byproduct of both the biodiesel production and the saponification of animal fats is obtained in large amount (400,000 tons in 2005) and needs to be better valorized as raw material. Their transformations into glycerol carbonate, aldehydes, ketones, and carboxylic acids,¹⁰ as well as epichlorohydrin¹¹ (ECH) and allyl glycidyl ether¹² (AGE), were reported. Production of ECH from glycerol via dichlorination and deshydrochlorination has been recently industrialized.^{13,14} AGE can be synthesized by the reaction of ECH with allyl alcohol,¹² the latter being obtained by heating glycerol in presence of formic acid. ECH and AGE possess two functional groups, which make these monomers of interest

for the preparation of reactive polymers even if the first one is toxic. Polyepichlorohydrin (PECH) can be readily modified by chemical substitution of the chloride atoms to yield a broad series of functional side chain polymers^{15,16} and more particularly to the synthesis of poly(glycidyl azide) used as precursor for energetic polyurethanes in the field of propellants.¹⁷

In the same way, pendant allylic unsaturation of poly(allyl glycidyl ether) (PAGE) allows introducing various functions *via* the thiol-ene chemistry,^{18–21} as well as epoxide side groups by oxidation of the double bond.²² This latter group has a great chemical interest as it can be easily transformed into cyclic carbonate by reaction with carbon dioxide (CO_2).²³

Beside polyethers with polymodal molar mass distribution that can be obtained by coordinated polymerization mechanisms, low to medium molar mass PECH and PAGE can be prepared by cationic (most preferably via the monomer activated mechanism), and/or by conventional anionic ring-opening polymerizations.^{24,25} Indeed, the anionic polymerization of AGE, and more generally of alkylene oxides, suffers from chain transfer to monomer, which drastically limits the control of the polymerization. For AGE, best polymerization results were obtained with a suspension of potassium hydride

Additional Supporting Information may be found in the online version of this article. Correspondence to: S. Carloti (E-mail: carloti@enscbp.fr)
Journal of Polymer Science Part A: Polymer Chemistry, Vol. 49, 2677–2684 (2011) © 2011 Wiley Periodicals, Inc.

and 18-crown-6²⁶ in tetrahydrofuran (THF), potassium hydride in association with benzyl alcohol,²⁰ or potassium 3-phenyl-1-propanolate.²⁴ These systems exhibit a relatively good activity at 25 or 100 °C but obtained PAGEs possess molar masses lower than 10,000 g mol⁻¹. Because of the nucleophilic attack of chloride by the alkoxide chain end in ECH anionic polymerization, PECH could not be prepared by conventional anionic polymerization. This is only recently that controlled polymerization of ECH could be achieved by anionic-activated monomer polymerization, using a combination of tetraalkylammonium salts and trialkylaluminum as initiator, thanks to the very low basicity of the propagating centers involved in this mechanism.²⁷ This approach was applied in this study to the polymerization of AGE and to its statistical copolymerization with ECH, the latter monomer being also a model of numerous epoxides.

The chemical modification of the pendant allyl groups into cyclic carbonates by reaction with a peroxide and CO₂ was then investigated. Indeed, the reaction of oxiranes with CO₂ to afford five-membered cyclic carbonates was reported to proceed in mild conditions in high yield.^{23,28–30} The reaction of cyclic carbonate with amines to produce polyurethanes was also documented in literature. Bifunctional five-membered cyclic carbonates and various alkyl amines were used to synthesize linear polyhydroxyurethanes without the use of isocyanate.^{31–36} By the same way, Wilkes³⁷ and Petrovic³⁸ synthesized polyurethanes starting from epoxidized soybean oil reacted with CO₂ and then with diamines. As reported by Keul and Höcker, such materials can also be prepared by cationic ring-opening polymerization of trimethylene urethane^{39,40} or by reaction of activated carbonates with α,ω -diamines.⁴¹

In the last part of this work, the chemically modified PAGE and poly(allyl glycidyl ether-*co*-epichlorohydrin) [P(AGE-*co*-ECH)] bearing cyclic carbonate groups were investigated as precursors for the synthesis of polyurethane networks in presence of a diamine.

EXPERIMENTAL

Materials

ECH (99%, Sigma Aldrich) and AGE (>99%, TCI) were purified over CaH₂ and distilled and stored under vacuum at room temperature in graduated glass tubes until use. Triisobutylaluminum (*i*-Bu₃Al) (1 mol L⁻¹ in toluene, Aldrich) was used without further purification. Toluene (98%, J.T. Baker) was purified with polystyryllithium seeds, distilled under vacuum and then stored in graduated glass tubes. Tetraoctylammonium bromide (NOct₄Br, 98%, Aldrich) was solubilized into dried toluene in calibrated glass tubes fitted with PTFE stopcocks. *m*-chloroperoxybenzoic acid (mCPBA, ≤77%) and lithium bromide (LiBr, 99+%), were purchased from Aldrich and used without further purification. Isophorone diamine (IPDA, 99+%) was purchased from Acros Organics. CO₂ was purchased from Air Liquide.

Procedures

All (co)polymerizations were carried out at 25 °C under argon in a glass reactor equipped with a magnetic stirrer and fitted

with Teflon stopcocks. As example, a polymerization reactor was flamed under vacuum and cooled down prior introduction of 6 mL of toluene, 0.80 mL of AGE (6.74 mmol), and 0.65 mL of ECH (8.31 mmol) through connected glass tubes. Then, 0.70 mL (0.15 mmol) of a toluene solution of NOct₄Br (*C* = 0.22 M) followed by 0.31 mL (0.31 mmol) of *i*-Bu₃Al solution in toluene (*C* = 1 M) were added via a syringe under argon. The polymerization was allowed to proceed at -30 °C for the initiation and at 25 °C for 1 h. A small amount of ethanol was then added to stop the reaction. The polymer conversion was determined gravimetrically (100%) after complete drying of the polymer under vacuum, at 50 °C. $\overline{M}_n$ Size exclusion chromatography (SEC) = 15,000 g mol⁻¹, *I*_p = 1.09.

¹H NMR of P(AGE-*co*-ECH): -O-CH₂(1)-CH(2)[CH₂(3)-O-CH₂(4)-CH(5)-CH₂(6)]-*co*-O-CH₂(7)-CH(8)[CH₂(9)-Cl]: 1, 2, 3, 7, 8, 9, multiplet at 3.33–3.67 ppm; 4, doublet at 3.98 ppm; 5, 5.87 ppm (1H); 6, 5.15–5.27 ppm (2H). ¹³C NMR of P(AGE-*co*-ECH): -O-CH₂(1)-CH(2)[CH₂(3)-O-CH₂(4)-CH(5)-CH₂(6)]-*co*-O-CH₂(7)-CH(8)[CH₂(9)-Cl]: 1, 3, 4, 7, 8, 70–72 ppm; 2, 79.14 ppm; 5, 135.4 ppm; 6, 117.01 ppm; 9, 43.99 ppm.

Epoxidation of AGE Units

A typical epoxidation reaction of the allyl groups of P(AGE-*co*-ECH) was carried out in dichloromethane with 2.5 molar excess of mCPBA. The reaction mixture was stirred for 8 h at room temperature. Then the solution was washed three times with a NaHCO₃ solution and dried for 1 night under vacuum.

¹H NMR of an epoxidized P(AGE-*co*-ECH): -O-CH₂(1)-CH(2)[CH₂(3)-O-CH₂(4)-CH(5)-O-CH₂(6)]-*co*-O-CH₂(7)-CH(8)[CH₂(9)-Cl]: 1, 2, 3, 4, 7, 8, 9, 3.13–3.76 ppm; 5, 2.98 ppm (1H); 6, 2.43, and 2.62 ppm (2H). ¹³C NMR of an epoxidized P(AGE-*co*-ECH): -O-CH₂(1)-CH(2)[CH₂(3)-O-CH₂(4)-CH(5)-CH₂(6)]-*co*-O-CH₂(7)-CH(8)[CH₂(9)-Cl]: 1, 3, 4, 7, 8, 70–72 ppm; 2, 79.37 ppm; 5, 59.42 ppm; 6, 43.75 ppm; 9, 43.75 ppm.

Carbonatation Reaction

One gram of an epoxidized P(AGE-*co*-ECH) (4.38 mmol of epoxide groups) and 19 mg of LiBr (0.22 mmol) were dissolved in 15 mL of dimethylformamide (DMF). The solution was introduced into a reactor and the atmosphere was replaced with CO₂ (*P* = 1 bar). The solution was then allowed to stand at 80 °C with continuous stirring during 12 h. The solution was dried under vacuum at 70 °C.

¹H NMR of carbonated P(AGE-*co*-ECH): -O-CH₂(1)-CH(2)[CH₂(3)-O-CH₂(4)-CH(5)-O-CO-O-CH₂(6)]-*co*-O-CH₂(7)-CH(8)[CH₂(9)-Cl]: 1, 2, 3, 4, 7, 8, 9, 3.42–3.98 ppm; 5, 4.83 ppm (1H); 6, 4.39–4.50 ppm (2H). ¹³C NMR of carbonated P(AGE-*co*-ECH): -O-CH₂(1)-CH(2)[CH₂(3)-O-CH₂(4)-CH(5)-O-C(5')O-O-CH₂(6)]-*co*-O-CH₂(7)-CH(8)[CH₂(9)-Cl]: 1, 3, 4, 5, 7, 8, 69–72 ppm; 2, 79.37 ppm; 5', 155.32 ppm; 6, 66.44 ppm; 9, 43.99 ppm.

Polyurethane Synthesis

0.5 g of carbonated copolymers and IPDA were stirred at 80 °C for 2 h. IPDA was used in stoichiometric molar amount with respect to the number of epoxide groups.

TABLE 1 Polymerization of Allyl Glycidyl Ether initiated by NOct₄Br/*i*-Bu₃Al

Run	[<i>i</i> -Bu ₃ Al]/[NOct ₄ Br]	Time (h)	$\overline{M}_{n,th}^b$ (g mol ⁻¹)	$\overline{M}_{n,exp}$ (RI) ^c (g mol ⁻¹)	$\frac{\overline{M}_w}{\overline{M}_n}$	$\overline{M}_{n,exp}$ (Visco) ^d (g mol ⁻¹)	$\frac{\overline{M}_w}{\overline{M}_n}$
1	2	1.5	5,000	6,900	1.08	nd	nd
2	2	1.5	10,000	14,500	1.07	nd	nd
3	2	1.5	20,000	30,000	1.05	21,000	1.09
4	2	1.5	50,000	70,000	1.22	46,000	1.24
5	3	2	75,000	72,000	1.40	60,000	1.37
6	4	4	100,000	109,000	1.32	70,000	1.35

Toluene, 20 °C, [AGE] = 1.5 mol L⁻¹, conversion^a: 100%.

^a Determined gravimetrically.

^b $\overline{M}_{n,th} = [AGE]_0 / [NOct_4 Br] \times M_{AGE} \times \text{yield}$.

^c Number-average molar mass determined by size exclusion chromatography in tetrahydrofuran using a calibration with polystyrene standards.

^d Number-average molar mass determined by size exclusion chromatography equipped with a viscometer detector in tetrahydrofuran.

Analysis

Polymer molar masses were determined by SEC at 40 °C using THF as eluent. Measurements in THF were performed on a PL GPC50 integrated system with RI, UV, and viscometer detectors and three TSK columns: G4000HXL (particles of 5 μm, pore size of 200 Å, and exclusion limit of 400,000 Da), G3000HXL (particles of 5 μm, pore size of 75 Å, and exclusion limit of 60,000 Da), G2000HXL (particles of 5 μm, pore size of 20 Å, and exclusion limit of 10,000 Da) at THF an elution rate of 1 mL min⁻¹. Polystyrenes were used as standards.

¹H and ¹³C NMR (400 MHz) analysis of the polymers and copolymers were performed on a Bruker Avance 400 spectrometer in CDCl₃ at room temperature.

FTIR (transmission mode) spectra were obtained using a Bruker Tensor 27 spectrometer.

Differential scanning calorimetry (DSC) measurements were carried out on a DSC Q100 apparatus from TA Instruments. Polyurethane samples were heated from -90 to 220 °C at a rate of 5 °C min⁻¹. Consecutive cooling and second heating runs were performed at 10 °C min⁻¹.

RESULTS AND DISCUSSION

Controlled Synthesis of Poly(allyl glycidyl ether)

The polymerization of AGE was performed using the monomer-activated anionic polymerization approach that was already applied for various other epoxide monomers.^{27,42–46} This polymerization process requires the use of an organic salt as initiator (typically NOct₄Br) in association with an organometallic Lewis acid activator (triisobutylaluminum) present in slight molar excess with respect to the initiator. In the case of AGE, the polymerization was initiated at -30 °C to reduce the initial polymerization rate and to prevent side reactions,⁴³ then the reaction medium was allowed to rise up to room temperature. Some polymerization results are collected in Table 1. Depending on the targeted PAGE molar mass and to achieve quantitative polymerization, initial [*i*-Bu₃Al]/[NOct₄Br] ratio ranging from 2 to 4 were used. At ratio 4, PAGE with an absolute molar mass equal to 70,000 g

mol⁻¹ and a dispersity of 1.35 were obtained in less than 3 h (run 6, Table 1). Ratio 3 or 4 was needed to get the highest molar masses and keep short polymerization times. They allow to increase the concentration of complexed monomer and, as a consequence, to increase the polymerization rate. It also induces a slight increase of chains distribution, observed for high molar masses, due to possible transfer reactions.⁴³ Moreover, and as already reported for protected glycidol polymerization,⁴⁶ *i*-Bu₃Al can be trapped by complexation with the oxygen of side group of PAGE units requiring a higher [*i*-Bu₃Al]/[NOct₄Br] ratio in contrary to propylene oxide polymerization for example.

Lower true molar masses values, as compared to theoretical ones, were generally measured by SEC equipped with a viscosimeter detector. Higher ones were obtained with a refractive index detector calibrated with polystyrene (PS) standards showing an apparent difference of hydrodynamic volumes between PAGE and PS. According to all values, one can assume the formation of about one PAGE chain per initiator molecule and probably some residual transfer reactions for the high molar masses. The experimental values obtained increase linearly with conversion and with the initial molar ratio [AGE]/[Initiator]. These results are consistent with a living-like process with strongly limited transfer reactions, which is often the limiting point in conventional anionic polymerization of epoxides.

On the basis of our previous and present results, it may be concluded that AGE polymerization follows the mechanism presented in Scheme 1. It involves the formation of a NOct₄Br:triisobutylaluminum (1:1) complex of low basicity and the complexation of AGE by the trialkylaluminum allowing its strong activation toward the nucleophilic attack of the aluminate complex that yields rapid and controlled AGE polymerization.

The structure of PAGE was checked by ¹H and ¹³C NMR analysis (see spectra in Supporting Information Figs. S1 and S2). The characteristic peak areas of pendant allyl group were observed at 5.87 ppm (=CH) and 5.15–5.27 ppm (=CH₂). Absence of epoxide groups at 3.2 and 2.6–2.8 ppm was taken as a proof of the selectivity of the mechanism toward the

SCHEME 1 Anionic ring opening polymerization mechanism via activation of allyl glycidyl ether.

epoxide ring opening. ^{13}C NMR spectrum also showed two single peaks at 117 ppm ($=\text{CH}_2$) and 135 ppm ($=\text{CH}$). In addition and according to literature, data⁴⁷ in-chain methylene and methine carbon signals were attributed to head-to-tail irregularities indicates an anionic coordinated type mechanism. The relative peak intensities of CH_2 (77.0–77.6 ppm) resolved into mm, mr, and rr triads agrees with the formation of atactic PAGE.⁴⁸

Synthesis of Poly(allyl glycidyl ether-*co*-epichlorohydrin)

We have recently reported that controlled polymerization of ECH proceeds in similar experimental conditions using $\text{NOct}_4\text{Br}:\text{i-Bu}_3\text{Al}$ as initiating system.²⁷ ECH was chosen as a model monomer of other epoxides such as ethylene oxide, propylene oxide, or various glycidyl ethers and because its possible synthesis from glycerol. It also carries a reactive side group, which can be subject to a chemically post-modification giving especially poly(glycidyl azide) used as precursor for energetic polyurethanes.¹⁷ The copolymerization of AGE with ECH was investigated and results collected in Table 2. As confirmed both by gravimetry and copolymer composition, quantitative conversion of the two monomers was achieved in short time (<1 h 30 min at 20°C in toluene) for $[\text{i-Bu}_3\text{Al}]/[\text{NOct}_4\text{Br}]$ ratios from 2 to 3. $\text{P}(\text{AGE-}co\text{-ECH})$ copolymers (see Supporting Information Fig. S3 for ^1H NMR)

of low dispersity with molar masses (apparent SEC values) increasing almost linearly with the ratio $[\text{monomers}]/[\text{initiator}]$ were obtained.

Information on the distribution of AGE and ECH monomer units in the copolymers was gained by determining the comonomer reactivity ratios using the Kelen/Tüdös method.⁴⁹ Several experiments were carried out at various comonomer feeds, and all copolymerizations were stopped at low conversion (less than 10%). Reactivity ratios were found to be $r_{\text{AGE}} = k_{\text{AGEAGE}}/k_{\text{AGEECH}} = 1.4$ and $r_{\text{ECH}} = k_{\text{ECHECH}}/k_{\text{ECHAGE}} = 6.6$. This indicates a small tendency to form gradient-like copolymers with a preferred ECH incorporation in the early stages of the reaction. This was further confirmed by monitoring the comonomer composition feed as a function of conversion, Figure 1. A 50:50 molar comonomer feed yields, at 10% conversion, a copolymer composed of 20% of AGE units, and 80% of ECH units, in agreement with a gradient structure.

Synthesis of (Co)polyethers with Ethylene Carbonate Side Groups

Transformation of allylic side groups of PAGE and $\text{P}(\text{AGE-}co\text{-ECH})$ into five-membered ethylene carbonate groups was achieved via epoxidation of the allylic unsaturation with

TABLE 2 Copolymerization of Allyl Glycidyl Ether and Epichlorohydrin Initiated by $\text{NOct}_4\text{Br}/\text{i-Bu}_3\text{Al}$

Run	Initial Comonomer Feed (mol %)		Copolymer Composition (mol %) ^b		$[\text{i-Bu}_3\text{Al}]/[\text{I}]$	$\overline{M}_{\text{nth}}$ (g mol ⁻¹)	$\overline{M}_{\text{nexp}}^c$ (g mol ⁻¹)	$\overline{M}_w/\overline{M}_n$
	AGE	ECH	AGE	ECH				
1	71	29	65	35	2	2,000	2,800	1.13
2	45	55	41	59	2	2,000	3,000	1.10
3	21	79	18	82	2	2,000	3,000	1.08
4	9	91	7	93	2	2,000	3,300	1.09
5	45	55	42	58	2	5,000	7,500	1.10
6	45	55	42	58	2	10,000	14,300	1.07
7	45	55	42	58	3	25,000	28,800	1.06

Toluene, $T = 20^\circ\text{C}$, Conversion^a: 100%, time = 1 h 30 min.

^a Determined gravimetrically.

^b Experimental values are determined by ^1H NMR.

^c Number-average molar mass determined by size exclusion chromatography in tetrahydrofuran using polystyrene as standards.

FIGURE 1 Evolution of the allyl glycidyl ether and ECH copolymer units composition with conversion (AGE/ECH (mol %) = 50/50, toluene, $T = 25\text{ }^{\circ}\text{C}$, $[i\text{-Bu}_3\text{Al}]/[\text{NOct}_4\text{Br}] = 2$, $[\text{AGE}+\text{ECH}] = 1.5\text{ mol L}^{-1}$, 100% conversion = 45 min).

meta-chloroperbenzoic acid and carbonation of the epoxide with CO_2 as shown Scheme 2.

Epoxidation of the (co)polymers was carried out in dichloromethane with 2.5 molar excess of *m*CPBA at room temperature. ^1H NMR spectrum of an epoxidized copolymer P(AGE-*co*-ECH) is shown Figure 2. A total disappearance of the characteristic peaks of the allylic protons at 5.87 ppm and 5.15–5.27 ppm completely disappeared and the presence of three new peaks corresponding to epoxide protons at 2.98 ppm, 2.43 and 2.62 ppm support quantitative epoxidation of AGE units. Carbonatation was then carried out in DMF at $80\text{ }^{\circ}\text{C}$ under 1 bar of CO_2 for 10 h. The ^1H NMR spectrum of the carbonated copolymer P(AGE-*co*-ECH) is shown Figure 3. It confirms the quantitative disappearance of the epoxide group and the formation of new signals at 4.83 ppm and

between 4.39 and 4.50 ppm attributed to the ethylene carbonate group. This was further confirmed by the presence of a carbonyl signal at 155 ppm in ^{13}C NMR.

Polyurethane Synthesis

Five members cyclic carbonate groups were reported to react with primary amines to form hydroxyurethane group^{30–37} as illustrated in Scheme 3 for the present system. Synthesis of polyurethane networks by reaction of P(AGE-*co*-ECH) with IPDA was investigated. Results are presented Table 3.

The number of carbonated groups per chain corresponds to the number of allyl groups as reactions were quantitative. The glass transition temperatures (T_g) before crosslinking, measured by DSC, were given by the first heating run. During this run, an exothermic peak characteristic of the crosslinking reaction was observed. The T_g after crosslinking was determined during the second heating run. The absence of the exothermic peak also confirmed the end of the cyclic carbonate-amine reaction. As shown in Table 3, various copolymer compositions were prepared. As expected, T_g after crosslinking were shown to be higher than T_g before reaction. The polyurethane with the higher T_g ($90\text{ }^{\circ}\text{C}$) corresponds to the copolymer bearing the higher number of cyclic carbonate functions in agreement with a highly crosslinked network, all materials being nonsoluble.

Using IPDA and polyethers with pendant cyclic ethylene carbonate groups, crosslinked polyurethanes with T_g between -24 and $90\text{ }^{\circ}\text{C}$ were obtained. The formation of such materials was then characterized by infrared spectroscopy (Fig. 4). Spectra of P(AGE-*co*-ECH) showed absorption bands at 1795 cm^{-1} for cyclic carbonate carbonyl function. The formation of polyurethanes was followed by the decrease and disappearance of this peak (1795 cm^{-1}) on spectrum (b)

SCHEME 2 Epoxidation of P(AGE-*co*-ECH) followed by carbonatation to yield polyethers with ethylene carbonate side groups.

FIGURE 2 ^1H NMR spectrum in CDCl_3 of epoxidized poly(allylglycidyl ether-*co*-epichlorohydrin) P(AGE-*co*-ECH) (initial AGE/ECH = 45/55 mol %, run 6, Table 2).

FIGURE 3 ^1H NMR spectrum in CDCl_3 of carbonated poly(allylglycidyl ether-*co*-epichlorohydrin) P(AGEc-*co*-ECH) (initial AGE/ECH = 45/55 mol %, run 6, Table 2).

SCHEME 3 Formation of hydroxyurethane by reaction of ethylene carbonate group of P(AGEc-*co*-ECH) with isophorone diamine.

and the appearance of peaks characteristic of the urethane function, the carbonyl at 1710 cm^{-1} and amide at 1650 cm^{-1} . As complementary information, the reaction between polyepichlorohydrin and IPDA gives no reaction. A particular focus on properties of polyhydroxyurethane materials based on various polyethers will be the object of further discussion.

CONCLUSIONS

A series of well-defined PAGE were prepared via anionic polymerization using NOct_4Br as organic initiator and trii-

sobutylaluminum as coinitiator and activator. This approach enables the formation of high molar mass polyethers up to $70,000\text{ g mol}^{-1}$ with a low dispersity in a few hours at room temperature. It allows the preparation of copolyethers based on allyl glycidyl ether and ECH, both monomers potentially coming from the glycerol chemistry. Post-chemical modifications applied to the side double bonds afforded epoxidized and cyclocarbonated polyethers by a consecutive addition of peroxide and CO_2 . The formation of polyurethane materials via a nonisocyanate route was taken as a final proof for the reactivity of

TABLE 3 Polyurethane Network Synthesis from Carbonated Poly(allyl glycidyl ether-*co*-epichlorohydrin) and Isophorone Diamine

Run	% (mol) exp. ^a		$N_{\text{CO}_3/\text{chain}}^b$	$\overline{M}_{\text{nexp}}$ (g mol^{-1})	T_g ($^{\circ}\text{C}$) before Crosslinking	T_g ($^{\circ}\text{C}$) after Crosslinking
	AGEc	ECH				
1	65	35	13.1	2,800	-36	90
2	41	59	8.8	3,000	-45	66
3	18	82	4.4	3,000	-42	40
4	7	93	2.0	3,300	-40	-24

$\overline{M}_n$ (th) = $2,000\text{ g mol}^{-1}$, $T = 80\text{ }^{\circ}\text{C}$, time = 3 h.

^a Experimental values are determined by NMR.

^b $N_{\text{CO}_3/\text{chain}}$: average number of ethylene carbonate group per polymer chain.

FIGURE 4 FTIR spectra of carbonated poly(allyl glycidyl ether-co-epichlorohydrin) (a) and polyurethane (b) after its reaction with isophorone diamine ($T = 80\text{ }^{\circ}\text{C}$, time = 3 h).

polyethers bearing pendant five-membered ethylene cyclic carbonates.

REFERENCES AND NOTES

- 1 Chattopadhyay, D. K.; Raju, K. V. S. N. *Prog Polym Sci* 2007, 32, 352–418.
- 2 Ephraim, S.; Woodward, A. E.; Mesrobian, R. B. *J Am Chem Soc* 1958, 80, 1326–1328.
- 3 Eissen, M.; Metzger, J. O.; Schmidt, E.; Schneidewind, U. *Angew Chem Int Ed* 2002, 41, 414–436.
- 4 Raquez, J. M.; Deléglise, M.; Lacrampe, M. F.; Krawczak, P. *Prog Polym Sci* 2010, 35, 487–509.
- 5 Petrovic, Z. S. *Polym Rev* 2008, 48, 109–155.
- 6 Behr, A.; Gomes, J. P. *Eur J Lipid Sci Technol* 2009, 112, 31–50.
- 7 Galià, M.; de Espinosa, L. M.; Ronda, J. C.; Lligadas, G.; Cadiz, V. *Eur J Lipid Sci Technol* 2009, 112, 87–96.
- 8 Van der Steen, M.; Stevens, C. V. *ChemSusChem* 2009, 2, 692–713.
- 9 Lligadas, G.; Ronda, J. C.; Galià, M.; Biermann, U.; Metzger, J. O. *J Polym Sci Part A: Polym Chem* 2006, 44, 634–645.
- 10 Pagliaro, M.; Ciriminna, R.; Kimura, H.; Rossi, M.; Della Pina, C. *Angew Chem Int Ed* 2007, 46, 4434–4440.
- 11 Santacesaria, E.; Tesser, R.; Di Serio, M.; Casale, L.; Verde, D. *Ind Eng Chem Res* 2009, 49, 964–970.
- 12 Xie, H. Q.; Guo, J. S.; Yu, G. Q.; Zu, J. *J Appl Polym Sci* 2001, 80, 2446–2454.
- 13 Bell, B.; Briggs, J. R.; Campbell, R. M.; Chambers, S. M.; Gaarenstroom, P. D.; Hippler, J. G.; Hook, B. D.; Kearns, K.; Kenney, J. M.; Kruper, W.; Schreck, D.; Therlault, C. N.; Wolfe, C. P. *Clean: Soil Air Water* 2008, 36, 657–661.
- 14 (a) Krafft, P.; Gilbeau, P.; Balthasart, D. FR2913683, 2008; (b) Kubicek, P.; Sladek, P.; Buricova, I., US0082601, 2009.
- 15 (a) Brochu, S.; Ampleman, G. *Macromolecules* 1996, 29, 5539–5545; (b) Callau, L.; Reina, J. A.; Mantecon, A. *J Polym Sci Part A: Polym Chem* 2002, 40, 3893–3908.
- 16 Jackson, M. B.; Vickers, L. J. *React Polym Ion Exch Sorbents* 1988, 8, 211–220.
- 17 (a) Frankel, M. B.; Grant, L. R.; Flanagan, J. E. *J Propul Power* 1992, 8, 560–563; (b) Mohan, Y. M.; Raju, M. P.; Raju, K. M. *J Appl Polym Sci* 2004, 93, 2157–2163.
- 18 Koyama, Y.; Umehara, M.; Mizuno, A.; Itaba, M.; Yasukouchi, T.; Natsume, K.; Suganaka, A.; Watanabe, K. *Bioconjugate Chem* 1996, 7, 298–301.
- 19 Yoshikawa, K.; Yoshikawa, Y.; Koyama, Y.; Kanbe, T. *J Am Chem Soc* 1997, 119, 6473–6477.
- 20 Hrubý, M.; Konak, C.; Ulbrich, K. *J Appl Polym Sci* 2005, 95, 201–211.
- 21 Giguère, G.; Zhu, X. X. *Biomacromolecules* 11, 201–206.
- 22 He, F.; Wang, Y. P.; Liu, G.; Jia, H. L.; Feng, J.; Zhuo, R. X. *Polymer* 2008, 49, 1185–1190.
- 23 Calo, V.; Nacci, A.; Monopoli, A.; Fanizzi, A. *Org Lett* 2002, 4, 2561–2563.
- 24 Erberich, M.; Keul, H.; Moller, M. *Macromolecules* 2007, 40, 3070–3079.
- 25 Aukaszczuk, J.; Jaszcz, K. *Macromol Chem Phys* 2002, 203, 301–308.
- 26 Stolarzewicz, A.; Neugebauer, D. *Macromol Chem Phys* 1999, 200, 2467–2470.
- 27 Carlotti, S.; Labbé, A.; Rejsek, V.; Doutaz, S.; Gervais, M.; Deffieux, A. *Macromolecules* 2008, 41, 7058–7062.
- 28 (a) Kihara, N.; Hara, N.; Endo, T. *J Org Chem* 1993, 58, 6198–6202; (b) Sakai, T.; Kihara, N.; Endo, T. *Macromolecules* 1995, 28, 4701–4706.
- 29 (a) Ochiai, B.; Endo, T. *J Polym Sci Part A: Polym Chem* 2007, 45, 5673–5678; (b) Ochiai, B.; Iwamoto, T.; Miyagawa, T.; Nagai, D.; Endo, T. *J Polym Sci Part A: Polym Chem* 2004, 42, 3812–3817.
- 30 Boyer, A.; Cloutet, E.; Tassaing, T.; Gadenne, B.; Alfes, C.; Cramail, H. *Green Chem* 2010, 12, 2205–2213.
- 31 Rokicki, G.; Piotrowska, A. *Polymer* 2002, 43, 2927–2935.
- 32 Steblyanko, A.; Choi, W.; Sanda, F.; Endo, T. *J Polym Sci Part A: Polym Chem* 2000, 38, 2375–2380.
- 33 (a) Tomita, H.; Sanda, F.; Endo, T. *J Polym Sci Part A: Polym Chem* 2001, 39, 162–168; (b) Tomita, H.; Sanda, F.; Endo, T. *J Polym Sci Part A: Polym Chem* 2001, 39, 851–859.
- 34 Tomita, H.; Sanda, F.; Endo, T. *J Polym Sci Part A: Polym Chem* 2001, 39, 3678–3685.
- 35 Kihara, N.; Kushida, Y.; Endo, T. *J Polym Sci Part A: Polym Chem* 1996, 34, 2173–2179.

- 36** He, Y.; Keul, H.; Möller, M. *React Funct Polym* 2011, 71, 175–186.
- 37** Tamami, B.; Sohn, S.; Wilkes, G. L. *J Appl Polym Sci* 2004, 92, 883–891.
- 38** Javni, I.; Doo, P. H.; Petrovic, Z. S. *J Appl Polym Sci* 2008, 108, 3867–3875.
- 39** Neffgen, S.; Keul, H.; Höcker, H. *Macromol Rapid Commun* 1996, 17, 373–382.
- 40** Neffgen, S.; Keul, H.; Höcker, H. *Macromolecules* 1997, 30, 1289–1297.
- 41** Prömpers, G.; Keul, H.; Höcker, H. *Green Chem* 2006, 8, 467–478.
- 42** Billouard, C.; Carlotti, S.; Desbois, P.; Deffieux, A. *Macromolecules* 2004, 37, 4038–4043.
- 43** Labbe, A.; Carlotti, S.; Billouard, C.; Desbois, P.; Deffieux, A. *Macromolecules* 2007, 40, 7842–7847.
- 44** Rejsek, V.; Sauvanier, D.; Billouard, C.; Desbois, P.; Deffieux, A.; Carlotti, S. *Macromolecules* 2007, 40, 6510–6514.
- 45** Labbé, A.; Carlotti, S.; Deffieux, A.; Hirao, A. *Macromol Symp* 2007, 249–250, 392–397.
- 46** Gervais, M.; Brocas, A.-L.; Cendejas, G.; Deffieux, A.; Carlotti, S. *Macromolecules* 2010, 43, 1778–1784.
- 47** Antelmann, B.; Chislom, H. C.; Iyer, S. S.; Huffman, J. C.; Navarro-Llobet, D.; Pagel, M.; Simonsick, W. J.; Zhong, W. *Macromolecules* 2001, 34, 3159–3175.
- 48** Chisholm, M. H.; Navarro-Llobet, D. *Macromolecules* 2002, 35, 2389–2392.
- 49** Kelen, T.; Tüdös, F. *J Macromol Sci Chem* 1975, A9, 1–27.