Direct synthesis of L10 FePt nanoparticles within carbon nanotubes by wet chemical procedure

A Capobianchi, S Laureti, D Fiorani, S Foglia, E Palange

► To cite this version:

A Capobianchi, S Laureti, D Fiorani, S Foglia, E Palange. Direct synthesis of L10 FePt nanoparticles within carbon nanotubes by wet chemical procedure. *Journal of Physics D: Applied Physics*, 2010, 43 (47), pp.474013. 10.1088/0022-3727/43/47/474013 . hal-00597840

HAL Id: hal-00597840

<https://hal.science/hal-00597840>

Submitted on 2 Jun 2011

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Direct Synthesis of L1₀ FePt nanoparticles within Carbon Nanotubes by Wet Chemical Procedure

A. Capobianchi¹, S. Laureti¹, D. Fiorani¹, S. Foglia² and E. Palange³

1.Consiglio Nazionale delle Ricerche (CNR), Istituto di Struttura della Materia (ISM), Rome, Italy

2.Consiglio Nazionale delle Ricerche (CNR), Istituto di Fotonica e Nanotecnologie, Rome, Italy

3.Università degli Studi dell'Aquila, Dipartimento di Ingegneria Elettrica e dell'Informazione, L'Aquila, Italy

aldo.capobianchi@ism.cnr.it

Abstract

This paper reports on the low temperature synthesis of L1₀ iron-platinum (FePt) particles within Multi Wall Carbon Nanotubes using a novel wet chemical method that allows the filling of the nanotube cavity keeping clear its external wall. In the proposed procedure, nanotubes are filled with a precursor salt of hexaaquairon(II) hexachloroplatinate, ([Fe(H₂O)₆][PtCl₆]) and nanoparticles of the magnetically hard phase are directly obtained by heating at 400°C in a reductive atmosphere. The advantage of such precursor, allowing to obtain at low temperature the L1₀ phase without passing through the soft fcc phase, is due to its structure, where the Fe and Pt atoms are arranged in alternating planes, like in the fct FePt structure. Morphological, structural and magnetic properties of the filled nanotubes have been investigated by transmission electron microscopy, X-ray diffraction and magnetization measurements. The results show the coexistence of nanoparticles in the superparamagnetic and blocked state, depending on the temperature, due to the particle size distribution.

1. Introduction

FePt alloys in the chemically ordered face-centered tetragonal (fct) ($L1_0$) are materials of great interest for perpendicular recording media, as they have a large uniaxial magneto-crystalline anisotropy [1] (magnetic anisotropic constant, $K_u = 7 \times 10^6 \text{ J/m}^3$), making particles so small as 2-3 nm magnetically stable at room temperature. Generally, FePt nanoparticles are obtained in the chemically disordered face-centered cubic (fcc) phase and a post-growth annealing treatment at around 600 °C is necessary to induce the transition to the chemically ordered face-centered tetragonal (fct) phase ($L1_0$). Organic precursors are commonly used for the synthesis, e.g. FePt nanoparticles in fcc phase are synthesized by reduction of mixed metal salts (i.e., Fe(CO)_5 and Pt(acac)_2), in the presence of a long chain carboxylic acid and primary amines in organic solvent [2]. Recently, we reported [3, 4] a new chemical strategy for the direct synthesis of FePt alloy starting from a polycrystalline salt of complex hexaaquairon(II) hexachloroplatinate ($[\text{Fe(H}_2\text{O)}_6][\text{PtCl}_6]$), in which Fe and Pt atoms are arranged on alternating planes like in the fct FePt structure. The reduction of such compound by 5% H_2 and 95% Ar at 400 °C leads directly to the highly ordered $L1_0$ phase.

In this paper we report on the preparation of FePt $L1_0$ nanoparticles within multi wall carbon nanotubes (MWCNTs) using the above reported synthesis method. The encapsulation of organic and inorganic materials inside carbon nanotubes (CNTs) has attracted a great interest for the capability to modify and design the physical properties of composite materials at nanometric scale in a host medium with high surface area and unique mechanical and electrical properties. This has opened the way to a variety of applications in many scientific and technological fields, e.g. in polymer science [6], catalysis [8], nanoelectronics [10], photovoltaic devices [9], hydrogen storage [7]. In particular, CNTs filled with magnetic nanoparticles are of great interest for magnetic recording media [13], in biomedicine for drug delivering [14] and for tips in magnetic force microscopy. Recently, we reported a new patented strategy to fill the CNTs cavities [15, 16]. In this work, such strategy is applied to the filling with $L1_0$ FePt nanoparticles, directly synthesized

without passing through the fcc phase. In a preliminary work [17], the synthesis of FePt in $L1_0$ phase inside MWCNTs has been obtained by mixing the nanotubes in a starting water solution of two precursors salts and then heating at 700°C in a reductive atmosphere. In the present paper, the same product is obtained by using a unique salt water solution precursor and reducing the transition temperature at 400 °C. The morphological, microstructural and magnetic characterization of the FePt@MWCNTs nanocomposite is reported.

2. Experimental

The MWCNTs used in this study, supplied by Nanocyl S.A. (Namur, Belgium), were grown by carbon catalytic vapor deposition technique. The wet chemical method used to fill the MWCNTs is a patented technique reported in detail in a previous work for the encapsulation of CdS crystal nanoclusters in MWCNTs [15-17]. MWCNTs were first opened at tips with nitric acid at 140°C, washed and dried. Then, a starting solution of $[\text{Fe}(\text{H}_2\text{O})_6][\text{PtCl}_6]$ salt at two different concentrations (0.1M and 0.01M) was used to fill the MWCNT cavity following a two step procedure. First, the opened MWCNTs was mixed in the aqueous solution of $[\text{Fe}(\text{H}_2\text{O})_6][\text{PtCl}_6]$ salt at room temperature under vacuum (10^{-2} mmHg). The filling of the nanotubes occurs just by capillarity, when the atmospheric pressure is quickly restored by flowing nitrogen gas and the resulting high difference in pressure between the internal and external nanotube wall induces the solution penetration into the MWCNT cavity. After few minutes of ultrasonic treatment and successive stirring for a day, the mixture was frozen in a cold bath at a temperature just below the solution freezing point. In these conditions, the solvent was sublimated at a pressure close to 10^{-2} mmHg for 2 days. At the end of this process, the samples were constituted of $[\text{Fe}(\text{H}_2\text{O})_6][\text{PtCl}_6]$ salt clusters encapsulated inside the MWCNTs and deposited on the external MWCNTs surface. In the second step, the solid mixture of filled MWCNTs and salt clusters were treated with an organic solvent, such as benzene, in which the $[\text{Fe}(\text{H}_2\text{O})_6][\text{PtCl}_6]$ salt is not soluble. The solvent penetrates through the MWCNTs opened tips by capillarity protecting the filling material from the washing solvent that was added right after.

The washing solvent must be, at the same time, immiscible with benzene and able to dissolve $[\text{Fe}(\text{H}_2\text{O})_6][\text{PtCl}_6]$ salt. Thus, as solvent we used water that cannot enter into the tubes because of either the relatively high surface tension at the water/benzene interface and the small area of the MWCNT ends. As a consequence, benzene protects from water the salts clusters located inside the MWCNTs, while the other ones attached to the MWCNT external surface are in contact with both benzene and water. For the well known phase distribution process, the water soluble salts fasten on the external MWCNT surface are extracted by water and washed away. At the end of this procedure, the $[\text{Fe}(\text{H}_2\text{O})_6][\text{PtCl}_6]$ clusters are present mainly inside the MWCNTs. In order to transform the $[\text{Fe}(\text{H}_2\text{O})_6][\text{PtCl}_6]$ salt into FePt L_{10} alloy [4], the $([\text{Fe}(\text{H}_2\text{O})_6][\text{PtCl}_6])@\text{MWCNTs}$ were heated, with a rate increase of $5\text{ }^\circ\text{C}/\text{min}$, up to $400\text{ }^\circ\text{C}$ in a reductive atmosphere of H_2 5% and Ar 95%. The reaction takes place in more steps during the temperature increasing, and the complete chemical reaction is:

The morphological characterization was performed by using a transmission electron microscope (TEM) Philips CM200 (thermoionic gun and acceleration voltage of 200 kV). The carbon nanotubes were observed by placing the specimens on high resolution Agar S160 carbon film 200 Mesh Cu grids.

The structural characterization was performed by X-ray diffraction (XRD) measurements by using a Seifert XRD 3000 P powder diffractometer, using Cu Ka radiation ($\lambda = 0.15418\text{ nm}$).

The magnetic measurements were carried out at $T=300\text{ K}$ and at $T=5\text{ K}$ by means of a commercial SQUID magnetometer (maximum magnetic field $H_{\text{max}} = 55\text{ kOe}$).

3. Results and discussion

In the synthesis of L_{10} MePt alloys (Me = Co, Fe) usually reported in the literature, a high temperature treatment [18] is necessary in order to transform the obtained chemically disordered fcc structure into the fct phase (L_{10}). In our case, the direct formation of the L_{10} phase at low

temperature (400 °C) is due to the peculiar atomic arrangement of the precursor salt, whose structure is reported in ref [3]. A view of the crystal packing is shown in Figure 1, with octahedral representing $[\text{PtCl}_6]^{2-}$ and $[\text{Fe}(\text{H}_2\text{O})_6]^{2+}$ ions, linked together through a network of hydrogen bonds. Two different sets of alternating Fe and Pt atomic planes can be distinguished along the [001] and [011] directions, respectively.

In Figure 2, the transmission electron microscopy (TEM) images of the filled FePt@MWCNTs are reported for two concentrations. It is shown that FePt nanoparticles are located only inside the nanotubes and that the external nanotube walls are clean. The average nanoparticle size is related to the initial salt solution concentration, resulting in a larger size distribution (between 1 and 10 nm) for the 0.1 M concentration. For the 0.01 M concentration the particle size is between 1 and 3 nm. The powder X-Ray diffraction (XRD) pattern of the FePt-filled MWCNTs prepared from the concentrated salt solution is reported in Figure 3. In the inset, the XRD pattern of empty and opened MWCNTs is also reported, showing the typical reflections reported in the literature [19]. The (002) reflection occurs at $2\theta = 25.823^\circ$, corresponding to an interlayer distance of 0.343 nm. This confirms that the MWCNT structure was not modified by the chemical opening procedure. The XRD pattern of FePt-filled nanotubes, in particular the presence and the positions of the (001), (110), (111), (201), (112) reflections and the splitting of the (200), (002), (220) and (202) reflections, provides evidence of the formation of the L_{10} phase. Applying the Scherrer's formula to the XRD peaks, an average particle size of 4.3 nm is obtained, consistent with the CNTs diameter and in agreement with the results of TEM measurements.

The magnetic properties of the FePt@MWCNTs were investigated by measuring hysteresis cycles at 300 K and 5 K. First we measured the hysteresis loop of empty and open MWCNTs. In Figure 4, the loop at 5 K is reported. The saturation magnetization is $M_s = 0.4 \text{ emu/g}$ and the coercive field $H_c = 1.2 \text{ kOe}$. The observed behaviour is due to the presence of ferromagnetic metallic impurities coming from residual nanoparticles of catalysts used in the preparation of the CNTs, not completely

removed by nitric acid during the opening procedure. Such impurities are commonly found in CNTs.

The hysteresis loops for the nanotubes filled with FePt particles are reported in Figure 5 for the sample obtained starting from a 0.1 M solution. The cycles show the presence of two contributions to the magnetization. At 5 K ($M_s = 2.74$ emu/g), one contribution, responsible for the high anisotropy field (the cycle is not closed at 5 K) and the large measured coercive field ($H_c = 20$ kOe at 5 K; the actual value should be even larger), is attributed to the hard ferromagnetic FePt $L1_0$ particles in the blocked state. A second contribution, responsible for the rapid variation of the magnetization at low fields, is due to a softer magnetic component, corresponding to the ferromagnetic metallic impurities coming from the growth of carbon nanotubes. In principle, the presence of a small fraction of soft ferromagnetic fcc FePt particles, coming from a not completed salt crystallization and not detected by X-ray diffraction, contributing to the low field behaviour of the magnetization, cannot be excluded. At 300 K, $H_c = 5$ kOe and $M_s = 1.9$ emu/g. The low coercive field suggests that a fraction of FePt nanoparticles moved to a superparamagnetic state with increasing temperature. The high field irreversibility indicates that a fraction of still blocked FePt $L1_0$ nanoparticles is still present at room temperature. Such coexistence of blocked and superparamagnetic particles is coherent with the temperature dependence of the low field magnetization (Figure 6), measure after zero field cooling (ZFC) field cooling (FC), indicating a large distribution of particle size. The observed behaviour indicates a quite large distribution of blocking temperature.

In Figure 7, the hysteresis loops of the sample prepared starting from a 0.01M salt solution is reported. For this diluted sample, the contribution of the soft component to the magnetization is much more important. At 5 K, $H_c = 1.3$ kOe and $M_s = 0.5$ emu/g. Although these values are very close to those observed for the empty MWCNTs, the high field irreversibility is a clear indication of the presence of a fraction of the $L1_0$ hard phase even at room temperature.

4. Conclusions

In this paper, the filling of MWCNTs with $L1_0$ FePt nanoparticles, directly synthesized at 400 °C starting from a salt of the layered precursor hexaaquairon(II) hexachloroplatinate, $[\text{Fe}(\text{H}_2\text{O})_6][\text{PtCl}_6]$, is reported. The FePt nanoparticles encapsulation into the MWCNTs was achieved by using a wet chemical method that allows to introduce the particles within the MWCNT maintaining the external wall free of particles. The hysteresis cycles, measured at 5 K and at 300 K, show the characteristics of the high anisotropy $L1_0$ phase (high coercivity, high field irreversibility). Due to the particle size distribution, at room temperature there is a coexistence of magnetic nanoparticles in the blocked and superparamagnetic state.

A low solution concentration was used in order to obtain the FePt $L1_0$ nanoparticles well separated and dispersed in the whole tube. Moreover, a further advantage of this filling technique is the possibility of controlling the nanoparticle size and then the magnetic properties of the composite material by choosing proper values of the initial salt solution concentration. This is very important in view of the promising applications of the $L1_0$ FePt filled MWCNTs as magnetic tips for magnetic force microscopy. In this context, work is in progress aimed at filling just the terminal part of MWCNTs.

Acknowledgments

The UE Contract N. FP7-ICT-2007-2-224001 is acknowledged.

References

- [1] Inomata K, Sawa T, Hashimoto S 1988 *J. Appl. Phys.*, 64 (5) 2537.
- [2] Sun S 2006 *Adv. Mater.* 18 393
- [3] Capobianchi A, Campi G, Camalli M, Veroli C 2009 *Z. Kristallogr.* 224 384
- [4] Capobianchi A, Colapietro M, Fiorani D., Foglia S, Imperatori P, Laureti S, Palange E 2009 *Chem. Mater.* 21 2007
- [5] Iijima S 1991 *Nature* 354 6348.
- [6] Chen J, Hamon M A, Hu H, Chen Y, Rao A M, Eklund P C, Haddon R C 1998 *Science* 282 95
- [7] Yao X, Wu C, Du A, Zou J, Zhu Z, Wang P, Cheng H, Smith S, Lu G 2007 *J. Am. Chem. Soc.* 129 15650.
- [8] Pan X, Fan Z, Chen W, Ding Y, Luo H, Bao X 2007 *Nature Materials* 6 507.

- [9] Kamat P V 2007 *J. Phys. Chem. C* 111 2834.
- [10] Materials Today, special issue on “Nanowire and nanotubes: electronics and photonics in one dimension”, 9, No. 10, October 2006.
- [11] Wildgoose G G, Banks C E, Compton R G 2006 *Small*. 2 182.
- [12] Monthieux M, Flahaut E, Cleuziou J-P 2006 *J Mater Res* 21 2774.
- [13] Terrones H, López-Urías F, Muñoz-Sandoval E, Rodríguez-Manzo J A, Zamudio A, Elías A L 2006 *Solid State Sciences* 8 303.
- [14] Emerich D F, Thanos C G 2006 *Biomolecular Engineering* 23 171.
- [15] Capobianchi A, Foglia S, Imperatori P 2006 International patent application, No PCT/IT2006/000119.
- [16] Capobianchi A, Foglia S, Imperatori P, Notargiacomo A, Giammatteo M, Del Buono T, Palange E 2007 *Carbon* 45 2205.
- [17] Capobianchi A, Foglia S, Palange E, Arrizza L, Veroli C, Vasquez Mansilla M, Fiorani D 2009 *Solid State Phenomena* 151 166
- [18] Sun S, Murray C B, Weller D, Folks L, Moser A 2000 *Science* 287 1989
- [19] Saito Y, Yoshikawa T, Bandow S, Tomita M, Hayashi T 1993 *Phys Rev B* 48 1907.

Figures

Figure 1. $[\text{Fe}(\text{H}_2\text{O})_6][\text{PtCl}_6]$ complex crystal packing showing the alternating Fe and Pt atomic planes.

Figure 2. FePt@MWCNTs from 0.1M (left) and 0.01M (right) solution of $[\text{Fe}(\text{H}_2\text{O})_6][\text{PtCl}_6]$ complex. Bars are equal to 50 nm in both figures.

Figure 3. XRD patterns of FePt@MWCNTs; In the inset XRD pattern of open and empty MWCNTs is reported.

Figure 4. Low temperature hysteresis loop of open and empty MWCNTs.

Figure 5. Hysteresis loop at $T=5$ K (closed circles) and 300 K (open circles) of the FePt@MWCNTs obtained from the 0.1 M starting solution.

Figure 6. ZFC (lower curve) FC (upper curve) measurement ($H_{\text{appl}}=100$ Oe) of FePt@MWCNTs sample obtained from 0.1 M starting solution.

Figure 7: hysteresis loop at $T=5$ K (closed circles) and 300 K (open circles) of the FePt@MWCNTs sample obtained from the 0.01M starting solution.