High-yield preparation of polystyrene/silica clusters of controlled morphology

Anthony Désert, Isabelle Chaduc, Sarah Fouilloux, Jean-Christophe Taveau, Olivier Lambert, Muriel Lansalot, Elodie Bourgeat-Lami, Antoine Thill, Olivier Spalla, Serge Ravaine, et al.

► To cite this version:

Anthony Désert, Isabelle Chaduc, Sarah Fouilloux, Jean-Christophe Taveau, Olivier Lambert, et al.. High-yield preparation of polystyrene/silica clusters of controlled morphology. *Polymer Chemistry*, 2012, 3 (5), pp. 1130-1132. 10.1039/C2PY20058A . hal-00685215

HAL Id: hal-00685215

<https://hal.science/hal-00685215>

Submitted on 12 Feb 2013

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

High-yield preparation of polystyrene/silica clusters of controlled morphology

Anthony Désert^{1,2}, Isabelle Chaduc³, Sarah Fouilloux⁴, Jean-Christophe Taveau², Olivier Lambert², Muriel Lansalot³, Elodie Bourgeat-Lami³, Antoine Thill⁴, Olivier Spalla⁴, Serge Ravaine⁵ and Etienne Duguet^{1*}

DOI: 10.1039/c2py20058a

Large amounts of regular tetrapods and hexapods made of a central silica core and four or six polystyrene satellite nodules were prepared with yields over 80 % from 55-nm and 85-nm silica seeds, respectively. The robustness of the process is supported by extensive statistical analyses and large-field transmission electron microscopy images.

Colloidal clusters made of robust aggregates of a few spherical particles that resemble molecules (often called “colloidal molecules”) have attracted recent interest not only as models to investigate fundamental packing questions, but also as building units for new materials expected to display unique properties established through directional interactions.¹ Several synthetic methods are being developed, but only a few of them are expected to combine someday production in large amounts, *i.e.* at the gram scale, morphology versatility and high yield in the expected morphology.²

Among the most promising ones is the aqueous seeded-growth emulsion polymerization route using styrene, Synperonic® NP30, sodium persulfate and silica nanoparticles as monomer, initiator, surfactant and seeds, respectively.^{3,4} The surface of the silica seeds needs to be previously treated by compatibilizers, *e.g.* methacryloxymethyltriethoxysilane (MMS) in low surface density, in order to create reactive (co)polymerizable loci promoting the surface capture of the growing macromolecules and therefore the nucleation/growth of the polystyrene (PS) nodules (Scheme 1).⁵ According this strategy, PS/silica clusters had been observed: snowman-like particles,³ tetrapods (tetrahedrons) and hexapods (octahedrons) for a mean diameter of silica seeds of 85 and 125 nm, respectively.⁴ Nevertheless, up to now the process was far to be optimal and repeatable. First, the morphology yield (calculated with respect to silica seeds) was tending to decreasing rapidly when the number of PS nodules per seed was increasing, essentially because the non-monodisperse silica seeds used for these experiments were leading to mixtures of clusters whose pod number was differing from one or two units. Second, optimal morphologies had been observed for a monomer-to-polymer conversion lower than 30 %. Therefore, tedious purification efforts were necessary for removing styrene excess from the aqueous cluster dispersion before characterization and use.

Scheme 1 Synthesis strategy of PS/silica clusters.

As a result, getting large amounts of identical and regular clusters was envisaged in the present work on the dual front of the narrowing of the silica size-distribution and the completion of the styrene polymerization. We focused on the synthesis of tetrapods since such structures might be used as building blocks for the fabrication of diamond-like colloidal crystals with a complete photonic band gap.⁶ Special efforts were dedicated to extensive calculations of morphology yields and features from the statistical analysis of electron microscopy images and to the checking of the synthesis repeatability.

The preparation of size-monodisperse batches of silica particles was performed thanks to a first nucleation/growth stage leading to silica “pre-seeds”,⁷ combined with regrowth stages allowing simultaneously to reach precisely the expected diameter. The first stage used L-arginine as base catalyst, while tetraethoxysilane (TEOS) as silica precursor was heterogeneously delivered in the amino-acid aqueous solution from a top organic layer.⁸ Different batches of silica “pre-seeds” were prepared by simply varying the volume of TEOS introduced. It was demonstrated that their final number concentration does not vary significantly and that only their average diameter depends on the TEOS amount with values ranging from 17 to 34 nm (*See* ESI, Figure S1). Polydispersity index (PDI) values were systematically found lower than 1.04. Regrowth experiments were performed in order to get several batches of silica seeds of controlled size and PDI targeting the values of 85 nm and 1.005, respectively. TEOS was added at a controlled rate and its hydrolysis/condensation was catalysed by ammonia in ethanol. One or two regrowth stages were necessary for adjusting the final diameter to the target values (*See* ESI, Table S1). The regrowth stages lead to a significant narrowing of the size distributions allowing reaching PDI values as low as 1.002. Moreover, Transmission Electron Microscopy (TEM) images showed that regrown silica particles were more regular in shape than the initial “pre-seeds” (*See* ESI,

Figure S2).

Concerning the styrene polymerization recipe, we took advantage of the complementary roles of non-ionic and ionic surfactants for controlling the arrangement of the PS pods around the silica seeds and increasing the polymerization kinetics, respectively. Using a mixture of Synperonic® NP30 and sodium dodecylsulfate (SDS) (95/5 wt. %), the rate of styrene consumption was greatly increased making the polymerization complete in 5 h (See ESI, Figure S3). This result was supported by the latex particle concentration, because the polymerization rate in emulsion polymerization is known to be proportional to the particle number. Indeed, N_{PS} was determined to be $2.2 \times 10^{16} \text{ L}^{-1}$ against 10^{16} L^{-1} without SDS. The size-distribution of the final latex particles was also found to be narrowed with PDI values lower than 1.001 (See ESI, Figure S4). Lastly, the polymerization appeared to be reproducible with average diameters of $189 \pm 4 \text{ nm}$ on the basis of four batches prepared in identical conditions.

The preparation of PS/silica clusters was first carried out from the size-monodisperse batches of 85-nm silica particles, which were previously surface-modified with MMS at the nominal surface density of $0.5 \text{ function.nm}^{-2}$. Such a diameter had been previously demonstrated to be optimal for getting tetrapods.⁴ Nine polymerisation experiments were performed using the new recipe in identical conditions (See ESI, Table S2) and the resulting clusters were statistically analysed by TEM by counting a minimum of 600 clusters per batch. Surprisingly, most of the fabricated clusters weren't tetrapods, but hexapods with an average yield of $82 \pm 5 \%$ (Figure 1). The average PS nodule diameter was $150 \pm 6 \text{ nm}$ against $189 \pm 4 \text{ nm}$ in the absence of silica seeds, revealing that, concurrently to surfactant molecules, the MMS-modified silica seeds help in stabilizing the PS nuclei and therefore contribute to an increase of the number of PS particles which are consequently smaller at complete monomer-to-polymer conversion. Most of the hexapods appeared highly symmetrical thanks to the narrow size-distribution of the PS nodules, their regular arrangement on the silica seed and the fact that most of them were in contact with the TEM grid via three PS nodules making the main axis of the triangular antiprism parallel to the observation axis. The main by-products were essentially clusters with a number of PS nodules lower than 6, and some of them were obviously hexapods which were partially broken during the TEM grid preparation because the released latex particles were observed in their surrounding environment (Figure 1). Moreover, no cluster bearing more than 6 PS nodules was observed, except rare ones which weren't made of a single silica core, but of a silica doublet (See ESI, Figure S5). In the pie chart, these clusters are called "multi-silica".

Fig. 1 TEM image of hexapods obtained by styrene emulsion polymerization from ~85-nm silica seeds (batch # H8). On the bottom image, the undoubtedly-identified hexapods were labelled for appreciating the yield of hexapod morphology: from this single image, it was estimated to 93 % with respect to silica seeds (64 hexapods against 5 silica seed bearing five or four pods, labelled "5" or "4", respectively). Free (or torn) PS particles have been labelled with the letter "L" for latex (scale bar: 200 nm). The pie chart displays the overall statistical results over 9 fabrication batches (See ESI, Table S2).

The fact that hexapods were obtained instead of tetrapods may be quite easily explained by the diameter of the PS nodules which reached a final average value lower than that observed in the previous study.⁴ The smaller the nodules, the higher the average number of those which may be accommodated on the surface of each silica seed. This factor is indeed included in the multiplicative constant K of the equation used for calculating the

silica-seed diameter (D_{silica}) as a function of the number of PS nodules per silica seed ($N_{\text{PS/silica}}$):⁴

$$\frac{D_{\text{silica}}}{2} = K \left(\frac{2N_{\text{PS/silica}}}{3} - \frac{1}{2N_{\text{PS/silica}}} \right)$$

A first calculation based on the results showing that hexapods
 5 were mainly obtained with 85-nm silica seeds allowed to
 determine that $K \sim 10.9$ (against the previous value of 16.2^4). A
 second calculation indicated that tetrapods could be obtained for
 silica seeds with a diameter of about 55 nm. MMS-modified
 seeds were prepared in this size range (*See* ESI, Table S1) and
 10 used in emulsion polymerization of styrene at the concentration
 of $1.8 \times 10^{16} \text{ L}^{-1}$. Six batches of clusters were prepared in identical
 conditions and thoroughly analysed by TEM (*See* ESI, Table S3).
 The results showed that the concentration of PS nodules ($N_{\text{PS}} =$
 $5.1 \times 10^{16} \text{ L}^{-1}$) was increased again to the detriment of their size
 15 ($145 \pm 4 \text{ nm}$). As expected, tetrapods were mainly obtained with
 an average yield of $81 \pm 3 \%$. As seen on some TEM images, the
 yield may reach locally 100 % (Figure 2), which illustrates the
 ability of the tetrapods to self-organize and segregate in specific
 areas.

20

Fig. 2 TEM image of tetrapods obtained by styrene emulsion
 polymerization from ~55-nm silica seeds (batch # T4). On the bottom
 image, the undoubtedly-identified tetrapods were labelled with two types
 25 of patterns depending on their arrangement onto the substrate for
 appreciating the yield of tetrapod morphology: from this single image, it
 was estimated to 100 % with respect to silica seeds (88 tetrapods against
 no extra cluster). Free (or torn) PS nodules have been labelled with the
 letter “L” for latex (scale bar: 200 nm). The pie chart displays the overall
 30 statistical results over 6 fabrication batches (*See* ESI, Table S3).

Conclusions

Highly regular PS/silica tetrapods and hexapods were obtained
 at complete monomer-to-polymer conversions and with typical
 morphology yields over 80 % with respect to silica seeds. The
 35 determination of the nature of the by-products revealed the
 morphology yield could be probably increased again in

optimizing the seed dispersion for promoting the formation of clusters made of a single silica core. Nevertheless, as far as we know, this paper is the first report where such yields were obtained for “colloidal molecules” or related complex colloids, and supported by extensive statistical analyses of TEM images. Moreover, the amounts of clusters obtained per batch are at the gram scale, *i.e.* typically 70 g.L⁻¹. Therefore, extensive studies of their assembling ability are henceforth possible.

Notes and references

¹ CNRS, Univ. Bordeaux, ICMCB, UPR 9048, F-33600 Pessac, France, Fax: +33 540 002 761; Tel: +33 540 002 651; E-mail: duguet@icmcb-bordeaux.cnrs.fr

² Univ. Bordeaux, CNRS, CBMN, UMR 5248, F-33600 Pessac, France.

³ Université de Lyon, Univ. Lyon 1, CPE Lyon, CNRS, UMR 5265,

¹⁵ Laboratoire de Chimie, Catalyse, Polymères et Procédés (C2P2), LCP group, F-69616 Villeurbanne, France.

⁴ Commissariat à l’Energie Atomique, DSM/IRAMIS/SIS2M/LIONS, UMR CEA/CNRS 3299, F-91191 Gif-sur-Yvette, France.

⁵ CNRS, Univ. Bordeaux, CRPP, UPR 8641, F-33600 Pessac, France.

²⁰ † Electronic Supplementary Information (ESI) available: Experimental details; Chemical structures of the main chemicals used; Evolution of the diameter and particle concentration of silica « pre-seeds » as a function of the added amount of TEOS; Experimental conditions for the silica regrowth stages and size measurement results of the 85-nm and 55-nm silica seeds; TEM images of silica « pre-seeds », silica seeds obtained after a 1st and 2nd regrowth stage; Influence of the substitution for 5 wt.% of Synperonic® NP30 by SDS on the evolution of the monomer-to-polymer conversion; TEM images of PS particles obtained in the absence of silica seeds; Experimental conditions for the synthesis of silica/PS clusters from ~85-nm silica seeds and their main morphology features as extracted from the statistical analysis of TEM images; SEM image of hexapods obtained by styrene emulsion polymerization from ~85-nm silica seeds; Experimental conditions for the synthesis of silica/PS clusters from ~55-nm silica seeds and their main morphology features as extracted from the statistical analysis of TEM images. See DOI: 10.1039/b000000x/

⁴⁰ ‡ The authors thank Sonia Gomez for SEM experiments performed at CREMEM facilities. The support of the Conseil Régional d’Aquitaine and the Agence Nationale pour la Recherche is gratefully acknowledged for ICMCB, CRPP and CBMN facilities, and ToCoMo project (contract # ANR-07-BLAN-0271), respectively.

⁴⁵ 1 A. van Blaaderen, *Nature*, 2006, **439**, 545; F. Li, D. P. Josephson, A. Stein, *Angew. Chem. Int. Ed.*, 2011, **50**, 360; S. Sacanna, D. J. Pine, *Curr. Opin. Colloid Interface Sci.*, 2011, **16**, 96.

2 E. Duguet, A. Désert, A. Perro, S. Ravaine, *Chem. Soc. Rev.*, 2011, **40**, 941.

⁵⁰ 3 S. Reculosa, C. Poncet-Legrand, A. Perro, E. Duguet, E. Bourgeat-Lami, C. Mingotaud, S. Ravaine, *Chem. Mater.*, 2005, **17**, 3338.

4 A. Perro, E. Duguet, O. Lambert, J. C. Taveau, E. Bourgeat-Lami, S. Ravaine, *Angew. Chem. Int. Ed.*, 2009, **48**, 361.

⁵⁵ 5 E. Bourgeat-Lami, M. Insulaire, S. Reculosa, A. Perro, S. Ravaine, E. Duguet, *J. Nanotech. Nanosci.* 2006, **6**, 432.

6 V. N. Manoharan, M. T. Elsesser, D. J. Pine, *Science*, 2003, **301**, 483.

⁶⁰ 7 Exceptionally, the term “pre-seeds” is employed in this paper for describing the very small silica particles obtained at the end of the first stage, because the term of “seeds” is used here for describing the silica particles introduced in the styrene emulsion polymerization.

8 K. D. Hartlen, A. P. T. Athanasopoulos, V. Kitaev, *Langmuir*, 2008, **24**, 1714; S. Fouilloux, A. Désert, O. Taché, O. Spalla, J. Daillant, A. Thill, *J. Colloid Interface Sci.*, 2010, **346**, 79; S. Fouilloux, O. Taché, O. Spalla, A. Thill, *Langmuir*, 2011, **27**, 12304.

Graphical abstract

Large amounts of regular tetrapod-like silica/polystyrene clusters are obtained through an optimized process based on the emulsion polymerization of styrene in the presence of 55-nm silica seeds.