Enhancement of nanograting formation assisted by silver ions in a sodium gallophosphate glass

Marie Vangheluwe, Feng Liang, Yannick Petit, Patricia Hée, Yannick Ledemi, Sébastien Thomas, Evelyne Fargin, Thierry Cardinal, Younes Messaddeq, Lionel Canioni, et al.

► To cite this version:

Marie Vangheluwe, Feng Liang, Yannick Petit, Patricia Hée, Yannick Ledemi, et al.. Enhancement of nanograting formation assisted by silver ions in a sodium gallophosphate glass. *Optics Letters*, 2014, 39 (19), pp.5491-5494. 10.1364/OL.39.005491 . hal-01074507

HAL Id: hal-01074507

<https://hal.science/hal-01074507>

Submitted on 23 Feb 2016

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Distributed under a Creative Commons Attribution - NonCommercial| 4.0 International License

Enhancement of nanograting formation assisted by silver ions in a sodium gallophosphate glass

Marie Vangheluwe,^{1,2} Feng Liang,² Yannick Petit,^{1,3,*} Patricia Hée,^{2,3} Yannick Ledemi,² Sébastien Thomas,³ Evelyne Fargin,³ Thierry Cardinal,³ Younès Messaddeq,² Lionel Canioni,¹ and Réal Vallée²

¹University of Bordeaux, LOMA, UMR 5798, F 33400 Talence, France and CNRS, LOMA, UMR 5798, F 33400 Talence, France

²Centre d'Optique, Photonique et Laser Université Laval, 2375 Rue de la Terrasse, Québec, QC G1V 0A6, Canada

³CNRS, ICMCB, UPR 9048, F 33608 Pessac, France, and Univ. Bordeaux, ICMCB, UPR 9048, F 33400 Pessac, France

*Corresponding author: petit@icmcb.bordeaux.cnrs.fr

We investigated the influence of silver ions during the direct femtosecond laser induced formation of nanogratings (NGs) at the surface of a tailored sodium gallophosphate glass. We observed that the silver ions had a remarkable influence because the silver containing glass showed (1) lower fluence thresholds for the formation of the NGs; (2) much smoother NG shapes; and (3) a bifunctional behavior because fluorescence from laser induced silver clusters occurs prior to the formation of the NGs. We demonstrate for the first time, to our knowledge, the formation of NGs assisted by noble metal ions, such as ions playing a kind of catalytic like role that enhances and improves the NG formation and its incubation process. Our innovative approach provides promising potential for further improvements in processes for NG formation.

OCIS codes: (160.2540) Fluorescent and luminescent materials; (140.3390) Laser materials processing; (140.3450) Laser induced chemistry; (190.4180) Multiphoton processes; (310.6628) Subwavelength structures, nanostructures.

Femtosecond (fs) laser manufacturing has led to continuous innovation in the last decade, especially in the inscription of structures with inner dimensions smaller than those of the considered beam size, such as the formation of nanogratings (NGs), which shows great potential for optical waveguides, solar cells, and biological devices [1–3]. The spatial distributions of NGs in bulk silica glass have been reported in detail in pioneer and recent works [4–7], both for bulk and surface NGs. Different mechanisms and descriptions have been proposed, including the incubation model [8]. While NGs have mostly been studied in silica by precisely tuning the laser irradiation parameters, very little attention has been paid to the material itself until now. No effort has been clearly made to adapt the considered glass matrices, either by exploring exotic compositions or by engineering a photosensitized material with the introduction of noble metal ions [9]. While silica cannot stand large amounts of silver ions [10], phosphate glasses can sustain high concentrations, allowing the direct laser writing (DLW) of strong and stable linear and nonlinear optical properties, such as silver cluster fluorescence, third-harmonic generation, or electric field-induced second-harmonic generation [11–16]. In this framework, the photochemistry of silver ions triggered under fs laser irradiation has never been explored for NG formation.

In this Letter, we study the role of silver ions incorporated in a tailored sodium gallophosphate matrix during the NG formation at its surface by means of fs laser irradiation. Accordingly, we compare the behaviors of such a sodium gallophosphate glass matrix with and without silver ions. In the silver-containing glass, we observed significant improvements due to the silver ions, such as lower fluence thresholds for the NG formations and much smoother NG shapes (also much smoother than the usual nanostructures, as in fused silica [17]). We also observed that fluorescent silver clusters are created prior to NG formation at lower fluencies, leading to spatially

correlated fluorescent patterns and NGs. Moreover, material removal was eased in the case of the silver-containing glass, with cleaner final NGs. Our innovative approach, based on noble metal doping, creates the potential for the optimal engineering and generation of NGs.

Glass samples with the initial composition 20.0Ga₂O₃-40.0Na₂O-40.0P₂O₅ (mol. %) and 97[20.0Ga₂O₃-40.0Na₂O-40.0P₂O₅]-3Ag₂O (mol. %), respectively labeled GPN and GPN-Ag, were synthesized using the conventional melt-quenching technique. The proper amount of Ga₂O₃, NaPO₃, and Ag₂O powders were thoroughly mixed, placed in a 100% Pt platinum crucible, heated up to 1100°C in ambient air, and kept at maximum temperature for 30 min before quenching. The glass samples obtained were annealed for 6 h at 40°C below the glass transition temperature of each sample. Further description of the preparation and characterizations of the sodium gallophosphate glasses can be found in [18]. The GPN and GPN-Ag samples were cut into pieces with 1 mm thickness. Finally, one of each were bound together to a silica glass substrate and polished to optical quality. This allows the two material samples to share the same interface, which guaranteed identical focusing conditions during laser structuring.

The experimental setup of the NG formation, as detailed elsewhere [8], is composed of a commercial Ti:Sapphire chirped-pulse amplification laser system (Spitfire, Spectra-Physics) with a maximum output energy of 2 mJ per pulse at the central wavelength $\lambda_{\text{laser}} = 800$ nm, with a pulse duration $\tau = 45$ fs (FWHM) and a repetition rate $f_{\text{rep}} = 1$ kHz. The beam was tightly focused at the surface sample with a microscope objective (Mitutoyo, 50 $\times$, N.A. = 0.42), which was adjusted by maximizing the retro-reflection from a He-Ne laser beam. The diameter of the focal spot was estimated at $2 \times \omega_0 = 2$ μ m. The samples were mounted on motorized three-dimensional (3D) translation stages (Melles Griot). The

considered writing speeds, with sample motion at constant speed from $v = 10$ to $100 \mu\text{m/s}$, allowed the estimation of the number of pulses N that overlapped at each position during laser structuring, as $N = 2 \times \omega_o \times f_{\text{rep}}/v$. The laser beam was linearly polarized perpendicular to the sample translation direction. The energy per pulse ($E_p = 10$ to 100 nJ) was adjusted with a half-wave plate and a Glan polarizer and was measured after the objective lens. The estimated pulse fluence is $F_p = E_p/\pi \times \omega_o^2$, whereas the effective beam fluence is defined as $F = N \times F_p$. After irradiation, the samples were imaged first by standard bright-field and fluorescence microscopy. Then, the samples were gently cleaned in an ultrasonic bath with distilled water for 4 min and characterized by a scanning electron microscope (SEM in the secondary electron emission mode) (FEI, model Quanta 3D FEG).

Both the silver-free and silver-containing samples were laser-processed and subsequently characterized under the same experimental conditions to ensure that the differences between GPN and GPN-Ag can only be attributed to the presence of silver ions.

The refractive indices at λ_{laser} of the GPN and GPN-Ag samples were estimated at 1.536 and 1.544, respectively, as inferred from the Sellmeier fitting of M-lines prism coupling measurements (Metricon 2010) at different wavelengths (532, 633, 972, 1308, and 1538 nm). The close values of the refractive indices of both the Ag-doped and nondoped GPN samples ensure that the focusing conditions will be similar for both glasses. Optical transmission spectroscopy of the two pristine glasses led to the estimation of the linear absorption coefficient in the UV-visible range. As seen in Fig. 1(a), the transmission cutoff of the GPN-Ag is significantly shifted toward longer wavelengths, suggesting a potentially much larger nonlinear three-photon absorption cross section (at 266 nm) for the fs irradiation [17]. Fluorescence spectroscopy revealed the silver-doping influence because the pristine GPN-Ag sample showed a strong excitation band centered at 272 nm, related to a broad emission band centered at 412 nm, as shown in Fig. 1(b). Such fluorescence behavior is typical of silver ion-containing glasses [19], whereas the nondoped sample showed no fluorescence

Fig. 1. (a) Linear absorption coefficients of the GPN and GPN Ag pristine samples and the upshifted UV cutoff wavelength due to the Ag^+ insertion. (b) Normalized excitation (emission wavelength at 412 nm) and emission fluorescence (excitation wavelength at 272 nm) spectra of the pristine GPN Ag glass. Absence of emission in the nondoped GPN sample confirms that these fluorescent properties result from the silver ions.

response. The excitation band of silver ions is to be correlated with the shift of the transmission cutoff in the GPN-Ag, strongly suggesting that the introduction of such ions is responsible for enhanced nonlinear absorption during the laser structuring process.

Laser irradiations were first performed at constant speed ($20 \mu\text{m/s}$) by increasing the pulse energy from 10 to 65 nJ. Features were observed under bright-field microscopy and luminescence imaging (excitation by a laser diode at $483 \pm 35 \text{ nm}$ and collection after a band-pass filter at $536 \pm 40 \text{ nm}$). The GPN sample showed a damage threshold at 35–40 nJ per pulse with bright-field microscopy [Fig. 2(a)], but it showed no sign of a fluorescence response [Fig. 2(c)]. Comparatively, the GPN-Ag sample showed a much lower threshold, with optical damages starting from 25–30 nJ [Fig. 2(b)]. Additionally, GPN-Ag led to a fluorescent emission [Fig. 2(d)], which is typical of the laser-induced creation of silver clusters [12], with an increasing fluorescence emission while increasing the input pulse energies. Probing the associated migration of silver ions during the creation of silver clusters is still in progress. Fluorescent clusters appeared prior to the damage threshold in GPN-Ag, demonstrating the photoreactivity of the silver ions in the early stages of the glass matrix modifications toward NG formation. Finally, no evidence of metallic silver nanoparticle formation was observed under such laser irradiances, suggesting their absence in these experimental conditions.

Once irradiated and softly cleaned with distilled water, the revealed structures were then observed with SEM, showing a NG formation threshold between 25 and 30 nJ per pulse in GPN-Ag (Fig. 3), which is significantly lower than the 35–40 nJ required in the nondoped GPN sample (Fig. 3). In addition to the lowering of the NG formation threshold, the SEM images also revealed that the NGs in GPN-Ag were impressively smoother than those in GPN. Their full width—labeled W—is also wider for given irradiation conditions, including a larger number of grooves. The width of individual grooves typically

Fig. 2. (a) and (b) Bright field images ($100\times$, $\text{NA} = 0.9$) of the GPN and GPN Ag samples, respectively, after the femtosecond (fs) direct laser writing (DLW) of lines at the surface at a constant scan speed at $20 \mu\text{m/s}$ for decreasing pulse energies before the cleaning process of the samples. (c) and (d) Related fluorescence images excited by a laser diode at $483 \pm 35 \text{ nm}$ and collected after a bandpass filter at $536 \pm 40 \text{ nm}$. These images clearly indicate that (1) NGs in GPN Ag appear for lower pulse energies than those in GPN; and (2) silver cluster fluorescence patterns appear prior to NG formation in GPN Ag.

provide enhanced abilities for the manufacturing of high-quality NGs for photonic devices.

This research was supported by the French Agency of National Research, the French Aquitaine region, the Cluster of Excellence LAPHIA, the Canada Foundation for Innovation (CFI), the Canadian Excellence Research Chair (CERC) in Photonic Innovations, the Natural Sciences and Engineering Research Council of Canada (NSERC), and the Fonds de Recherche du Québec—Nature et Technologies (FRQNT). We thank S. Gagnon and M. D'Auteuil for their technical support.

References

1. F. Liang, R. Vallée, and S. L. Chin, *Opt. Express* **20**, 4389 (2012).
2. C. Mauchlaire, A. Mermillod Blondin, N. Huot, E. Audouard, and R. Stoian, *Opt. Express* **16**, 5481 (2008).
3. F. Zhang, H. Zhang, G. Dong, and J. Qiu, *J. Opt. Soc. Am. B* **31**, 860 (2014).
4. P. G. Kazansky, H. Inouye, T. Mitsuyu, K. Miura, J. Qiu, and K. Hirao, *Phys. Rev. Lett.* **82**, 2199 (1999).
5. Y. Shimotsuma, P. G. Kazansky, J. Qiu, and K. Hirao, *Phys. Rev. Lett.* **91**, 247405 (2003).
6. R. Taylor, C. Hnatovsky, and E. Simova, *Laser Photon. Rev.* **2**, 26 (2008).
7. S. Richter, A. Plech, M. Steinert, M. Heinrich, S. Döring, F. Zimmermann, U. Peschel, E. B. Kley, A. Tünnermann, and S. Nolte, *Laser Photon. Rev.* **6**, 787 (2012).
8. F. Liang, R. Vallée, D. Gingras, and S. L. Chin, *Opt. Mater. Express* **1**, 1244 (2011).
9. A. Royon, Y. Petit, G. Papon, M. Richardson, and L. Canioni, *Opt. Mater. Express* **1**, 866 (2011).
10. M. Yamane and Y. Asahara, *Glass for Photonics* (Cambridge University, 2000).
11. K. Bourhis, A. Royon, M. Bellec, J. Choi, A. Fargues, M. Treguer, J. J. Videau, D. Talaga, M. Richardson, T. Cardinal, and L. Canioni, *J. Non Cryst. Solids* **356**, 2658 (2010).
12. M. Bellec, A. Royon, K. Bourhis, J. Choi, B. Bousquet, M. Treguer, T. Cardinal, J. J. Videau, M. Richardson, and L. Canioni, *J. Phys. Chem. C* **114**, 15584 (2010).
13. A. Royon, K. Bourhis, M. Bellec, G. Papon, B. Bousquet, Y. Deshayes, T. Cardinal, and L. Canioni, *Adv. Mater.* **22**, 5282 (2010).
14. L. Canioni, M. Bellec, A. Royon, B. Bousquet, and T. Cardinal, *Opt. Lett.* **33**, 360 (2008).
15. G. Papon, Y. Petit, N. Marquestaut, A. Royon, M. Dussauze, V. Rodriguez, T. Cardinal, and L. Canioni, *Opt. Mater. Express* **3**, 1855 (2013).
16. G. Papon, N. Marquestaut, Y. Petit, A. Royon, M. Dussauze, V. Rodriguez, T. Cardinal, and L. Canioni, *J. Appl. Phys.* **115**, 113103 (2014).
17. F. Liang, "Femtosecond laser writing of nanogratings on the surface of fused silica," Ph.D. thesis (Université Laval, 2012).
18. P. Hee, R. Christensen, Y. Ledemi, J. C. Wren, M. Dussauze, T. Cardinal, E. Fargin, S. Kroeker, and Y. Messaddeq, *J. Mater. Chem. C* **2**, 7906 (2014).
19. I. Belharouak, C. Parent, B. Tanguy, G. Le Flem, and M. Couzi, *J. Non Cryst. Solids* **244**, 238 (1999).
20. F. Liang, R. Vallée, and S. L. Chin, *Appl. Phys. Lett.* **100**, 251105 (2012).