Influence of the Incorporation of CeO₂ Nanoparticles on the Ion Exchange Behavior of Dodecylsulfate Doped Polypyrrole Films: Ac-Electrogravimetry Investigations

Chabba Benmouhoub, Jeronimo Agrisuelas, N. Benbrahim, Françoise Pillier, Claude Gabrielli, A. Kadri, Alain Pailleret, Hubert Perrot, Ozlem Sel

► To cite this version:

Chabba Benmouhoub, Jeronimo Agrisuelas, N. Benbrahim, Françoise Pillier, Claude Gabrielli, et al.. Influence of the Incorporation of CeO₂ Nanoparticles on the Ion Exchange Behavior of Dodecylsulfate Doped Polypyrrole Films: Ac-Electrogravimetry Investigations. *Electrochimica Acta*, 2014, 145, pp.270-280. 10.1016/j.electacta.2014.07.151 . hal-01079695

HAL Id: hal-01079695

<https://hal.science/hal-01079695>

Submitted on 4 Nov 2014

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

**INFLUENCE OF THE INCORPORATION OF CeO₂
NANOPARTICLES ON THE ION EXCHANGE BEHAVIOR OF
DODECYLSULFATE DOPED POLYPYRROLE FILMS :
AC-ELECTROGRAVIMETRY INVESTIGATIONS**

C. Benmouhoub^{a,c,d}, J. Agrisuelas^b, N. Benbrahim^a, F. Pillier^{c,d}, C. Gabrielli^{c,d},
A. Kadri^a, A. Pailleret^{c,d}, H. Perrot^{c,d} and O. Sel^{c,d}

^a*Laboratoire de Physique et Chimie des Matériaux (LPCM), Université Mouloud Mammeri, B.P. 17, 15000, Tizi-Ouzou, Algeria*

^b*Univ Valencia, Dept Quim Fis, E-46100 Valencia, Spain*

^c*Sorbonne Universités, UPMC Univ Paris VI, UMR 8235, Laboratoire Interfaces et Systèmes Electrochimiques (LISE), 4, place Jussieu, case courrier 133, F-75005, Paris, France*

^d*CNRS, UMR 8235, LISE, F-75005, Paris, France*

Abstract

Cerium oxide (CeO₂) nanoparticles (NPs) possessing defined size and crystallinity have been synthesised by a co-precipitation method. The effect of several parameters, such as the nature of the solvent and the calcination process, on the crystallite size was studied by XRD, TEM and BET methods. These CeO₂ nanoparticles were then incorporated in dodecylsulfate (DS) doped PPy films during their electrodeposition in potentiodynamic conditions in order to produce PPy-DS/CeO₂ NPs nanocomposite thin films on gold coated quartz crystals. Simultaneous EQCM experiments revealed successful incorporation of increasing amounts of cerium oxide nanoparticles in the polypyrrole matrix during each of the consecutive CV scans. This was confirmed using FEG-SEM and EDS microanalysis.

The ion exchange phenomena occurring in the resulting nanocomposite materials were studied by *ac*-electrogravimetry in NaCl aqueous electrolyte. PPy-DS films appear to be mainly cation exchangers, independently from the incorporation of CeO₂ nanoparticles (NPs) even though chloride anions in smaller amounts, and free water molecules, are

1
2
3 simultaneously transferred at the film/electrolytic solution interface. This study also reveals
4
5 that the kinetics of Cl^- ion insertion occurring at the film/electrolyte interface upon
6
7 oxidation is persistently slower in PPy-DS/CeO₂ NPs films than in PPy-DS films
8
9 throughout the entire potential window of investigation. However, the relative
10
11 concentration changes of Cl^- ions in PPy-DS/CeO₂ NPs films is about two times greater
12
13 than that occurring in pristine PPy-DS films. Such conclusion tends to demonstrate that
14
15 CeO₂ NPs have the ability to modify the morphology of electrodeposited PPy-DS thin films
16
17 as well as their subsequent permeability towards ions contained in the electrolytic solution,
18
19 possibly via the perturbation of polymer chain interactions and organisation.
20
21
22
23
24
25
26

27 **1. Introduction**

28
29 Composite materials based on an electronically conducting polymer (ECP) matrix
30
31 incorporating metal oxide nanoparticles constitute a fascinating class of functional
32
33 materials, as shown by review articles [1]. They are potentially aimed at a vast range of
34
35 applications among which one can cite protection against corrosion of iron [2],
36
37 electrocatalysis [3], supercapacitors [4,5] or Li-ion batteries [6]. Besides their applications,
38
39 such composite materials are also interesting from a fundamental point of view. Their
40
41 complex chemical composition, the distribution of the different phases and their physico-
42
43 chemical interactions inside the bulk of the overall composite material make their main
44
45 properties unpredictable. For example, in a recent contribution, our group showed that the
46
47 conductivity of electrodeposited polypyrrole thin films undergoes opposite influences from
48
49 dodecylsulfate (DS) anions and incorporated iron oxide particles [2]. More specifically,
50
51 PPy-DS films were shown to possess a rather good electronic conductivity, compared to
52
53 PPy films doped with other anions, as a consequence of the beneficial effect of
54
55 dodecylsulfate anions. However, PPy-DS films containing iron oxide particles were found
56
57
58
59
60
61
62
63
64
65

1
2
3 to have a lower conductivity that was moreover found to depend on the identity and/or
4
5 crystallographic variety of the incorporated iron oxide (α -Fe₂O₃, γ -Fe₂O₃, Fe₃O₄) [2].
6
7 Literature also contains many reports showing that incorporation of metal or metal oxide
8
9 nanomaterials in ECPs may substantially modify their well-known physico-chemical
10
11 properties, besides providing new ones, which is beyond this discussion. In a non-
12
13 exhaustive list, one can remind that polypyrrole/WO₃ nanomaterials based composite
14
15 materials possess a rare negative permittivity and their switching frequency can be tuned
16
17 with the help of particle loading. In particular, among other parameters, increased
18
19 nanoparticle loading was also shown to improve the electrical conductivity, dielectric
20
21 permittivity, and thermal stability of the resulting nanocomposites [7]. One should also
22
23 notice that magnetite incorporation stabilizes the polaronic form of polypyrrole matrices
24
25 and also preserves it from further oxidation [8] or allows production of unexpected 1 μ m
26
27 wide stripe-like microstructures resulting from the self-assembly of magnetic components
28
29 [9].
30
31
32
33
34
35
36

37 In this contribution, one of our goals was to identify a likely influence of the
38
39 incorporation of cerium oxide nanoparticles on the ion transfer behaviour observed at the
40
41 interface between PPy-DS/CeO₂ NPs nanocomposite materials and an aqueous electrolytic
42
43 solution. During the last decades, cerium (IV) oxide (CeO₂), also named ceria, was widely
44
45 applied in many fields and thus, established as one of the most interesting rare earth oxides.
46
47 Numerous CeO₂ synthesis procedures have been reported in literature [10-13] leading to
48
49 various nanoparticle morphologies. These materials were extensively studied owing to their
50
51 many distinctive characteristics and applications such as catalysts in the fuel cell
52
53 technology [14], gas sensor [15], catalytic wet oxidation [16-17], oxygen storage and
54
55 release [18], wastewater treatment [19] or photo-catalytic oxidation of water [20].
56
57
58
59
60
61
62
63
64
65

In our work, CeO₂ oxide was selected as it is expected to provide its strong oxidizing power to the resulting PPy-DS/CeO₂ NPs nanocomposite materials.

The technique employed for the investigations of ion exchange behaviour of nanocomposite PPy-DS/CeO₂ NPs materials reported hereafter is *ac*-electrogravimetry, according to recent contributions showing it is an appropriate methodology for such investigations [21-28]. Specifically, *ac*-electrogravimetry, *i.e.* simultaneous measurements of the usual electrochemical impedance, $\frac{\Delta E}{\Delta I}(\omega)$, and of the mass/potential transfer function, $\frac{\Delta m}{\Delta E}(\omega)$, provides a clear separation and identification of all the species. These species involved in the electrochemical reactions associated to the film can be charged or non-charged and, their contributions can be clearly determined thanks to *ac*-electrogravimetry [21-28].

2. Theory

Briefly, *ac*-electrogravimetry consists in coupling electrochemical impedance measurements with a fast response quartz crystal microbalance (QCM) used in *ac*-mode. It allows the response in current, $\frac{\Delta E}{\Delta I}(\omega)$, electrical transfer function, and in mass, $\frac{\Delta m}{\Delta E}(\omega)$, mass-potential transfer function to be simultaneously obtained owing to a sinusoidal potential perturbation with a small amplitude (ΔE) [21-23]. The advantage of combining such transfer functions is the possibility of a fair separation of the different electrochemical processes, which involves concomitantly the mass and charge changes. In fact, at the film/electrolyte interface, the ion-exchange phenomenon is modified when a small sine wave potential perturbation, (ΔE), is applied.

The equation describing the insertion/expulsion of species i ($i = a, c$, and s for anion, cation, and solvent, respectively), characterizing the ionic transfer at the film/electrolyte interface, is the following:

$$\frac{\Delta C_i}{\Delta E}(\omega) = -\frac{G_i}{j\omega d_{film} + K_i} \quad (1)$$

where $\omega = 2\pi f$ is the pulsation, f is the potential perturbation frequency, d_{film} is the film thickness, C_i is the concentration of the species i in the electroactive film and K_i and G_i are the partial derivatives of flux with respect to the concentration and potential respectively, $K_i = \left(\frac{\partial J_i}{\partial C_i} \right)_E$ and $G_i = \left(\frac{\partial J_i}{\partial E} \right)_{C_i}$, where J_i stands for the flux of the species i crossing the film/electrolyte interface. From Eq. 1, $\frac{\Delta m}{\Delta E}(\omega)$ is easily deduced in the case

where three species are involved:

$$\frac{\Delta m}{\Delta E}(\omega) = -d_{film} \sum_{i=a,c,s} \left(m_i \frac{G_i}{j\omega d_{film} + K_i} \right) \quad (2)$$

where m_i is the atomic mass of the species a, c , or s . Based on the same model and according to Eq. 1, $\frac{\Delta E}{\Delta I}(\omega)$ is also obtained, taking into account only the charged species transferred through the film/electrolyte interface. If one cation and one anion are involved in the electrochemical process, the following equation can be used:

$$\frac{\Delta E}{\Delta I}(\omega) = \frac{1}{j\omega d_{film} F \left[\frac{G_c}{j\omega d_{film} + K_c} - \frac{G_a}{j\omega d_{film} + K_a} \right]} \quad (3)$$

When the response of the electrochemical system is perturbed at low frequencies with a parasitic electrochemical reaction, characterized by a parasitic impedance ($Z_{par}(\omega)$)

described in equation (4), in parallel with the ionic transfer, the global electrochemical impedance (equation 5) becomes:

$$Z_{par}(\omega) = R_{par} + \frac{1}{j\omega C_{par}} \quad (4)$$

$$\frac{\Delta E}{\Delta I}(\omega) = R_{el} + \frac{1}{j\omega C_{dl} + \frac{\Delta I}{\Delta E}_{ions}}(\omega) + \frac{1}{Z_{par}(\omega)} \quad (5)$$

In Eq. 5, R_{el} is the electrolyte resistance and C_{dl} is the interfacial capacitance.

Another pertinent transfer function can also be simulated here, the so-called charge/potential transfer function, $\frac{\Delta q}{\Delta E}(\omega)$. This transfer function generally presents loops which correspond to the ionic transfer occurring at low frequencies. By this way, it is easier to determine the K_i and G_i parameters related to each species. The equation used is given by:

$$\frac{\Delta q}{\Delta E}(\omega) = d_{film} F \left[\frac{G_c}{j\omega d_{film} + K_c} - \frac{G_a}{j\omega d_{film} + K_a} \right] \quad (6)$$

These theoretical expressions were used to simulate the experimental responses of the electrochemical impedances, $\frac{\Delta E}{\Delta I}(\omega)$, the charge/potential transfer function, $\frac{\Delta q}{\Delta E}(\omega)$, and the electrogravimetric transfer functions, $\frac{\Delta m}{\Delta E}(\omega)$. These results were compared with the experimental data which provided the key parameters, m_i , K_i and G_i , to be extracted.

3. Experimental

3.1. Synthesis of CeO₂ nanoparticles

The schematic diagram of the experimental procedure described hereafter is shown in Figure 1. All the chemical reagents were used without purification. The cerium (III) nitrate salt precursor ($Ce(NO_3)_3 \cdot 6 H_2O$) was initially dissolved in only H_2O or in a C_2H_5OH / H_2O mixture (1/1 vol.). The solution was stirred at $30^\circ C$ and a solution of NH_4OH was added. Immediately, a precipitate of $Ce(OH)_3$ was formed because of its low solubility product ($K_s(Ce(OH)_3) = 7 \cdot 10^{-21}$) [29], leading in a further step to a light brown coloration of the solution. Subsequently, as the pH was maintained at 9-9.5, the coloration of the precipitate turned purple, which is a characteristic of the oxidation of $Ce(OH)_3$ into $Ce(OH)_4$ by dissolved oxygen. At last, it became a light yellow suspension of CeO_2 . The reaction is stopped after about 1.5 hour of vigorous stirring. The obtained precipitate was centrifuged, washed with distilled H_2O and ethanol alternatively three times, and then dried in a drying oven at $60^\circ C$ for 24 hours (sometimes up to calcination at $600^\circ C$ in a furnace). In order to evaluate the influence of some of the synthesis parameters, four different powders have been compared in this work (see Table 1). Apart from CeO_2 NPs of the a type that were purchased from Aldrich, CeO_2 NPs of the b and c types were synthesized in aqueous medium and in a C_2H_5OH / H_2O mixture (1/1 by vol.) respectively. The latter one (c) was calcinated at $600^\circ C$ for 1 h and noted powder of the d type. The overall chemical reaction of formation of cerium oxide in alkaline solution is as follows:

Let us emphasise that the liquid-phase precipitation process includes three steps: chemical reaction, nucleation and crystal growth. Generally, these three steps are fast, hence, the mixing step has a large influence on the product particle size and its distribution [29]. It is thus important to define the crystalline variety as well as an accurate estimation of the size of the resulting nanoparticles.

3.2 Morphological Characterisation of CeO₂ nanoparticles using XRD, TEM and BET

The crystallite size (d_{XRD}) was estimated using XRD (Bruker AXS, D8 ADVANCE) by inserting Full Width Half Maximum (FWHM) of characteristic peak (111) in the Scherrer equation [30] (see Table 1):

$$d_{XRD} = 0.9 \lambda / FWHM \cos \theta \quad (8)$$

where λ was the incident wavelength (1.5406 Å in this study) of X-ray and θ was the diffraction angle for the (111) plane.

The CeO₂ nanoparticle diameter and morphology were determined by transmission electron microscopy (TEM, JEOL 2000Fx). For that purpose, samples for TEM were prepared by ultrasonically dispersing the CeO₂ NPs in ethanol, and then dropped onto carbon-coated copper grids. Corresponding TEM images and electron diffraction patterns were recorded. The average particle size (d_{TEM}) was determined by TEM images with a 50 particles sample.

The specific surface area of CeO₂ nanoparticles ($A(m^2.g^{-1})$) was measured by nitrogen adsorption at 77.3 K using a Quantachrome instrument and calculated by Brunauer-Emmett-Teller equation, assuming that the CeO₂ nanoparticles are spherical and non-porous [3]. The corresponding particle size (d_{BET}) can be estimated as:

$$d_{BET} = 6/\rho A \quad (9)$$

where ρ is the density of CeO₂, $\rho = 7.28 \text{ g.cm}^{-3}$ [31].

3.3. Electrosynthesis and characterization of PPy-DS/CeO₂ NPs nanocomposite thin films

PPy-DS and PPy-DS/CeO₂ NPs nanocomposite films were electrodeposited from an electrolytic and colloidal aqueous solution containing freshly distilled pyrrole (Py, 0.1 mol.dm⁻³), sodium dodecylsulfate (SDS, 0.025 mol.dm⁻³) and, when necessary, cerium

oxide nanoparticles (CeO_2 NPs, 2 g.dm^{-3}) ultrasonically dispersed in the electrolytic solution prior to the proper electrosynthesis step. This latter was carried out using a Bio-Logic SP300 potentiostat connected to a frequency meter (Keithley) and a lab-made oscillator by applying 10 consecutive cyclic voltammetric scans between -1.5 and 0.4 V/SSE using a 50 mV.s^{-1} scan rate. The three-electrode cell used for this purpose consists of a platinum grid as counter-electrode, a reference electrode (saturated sulphate $\text{Hg}_2\text{SO}_4/\text{Hg}$ electrode, SSE) and a working electrode. This latter was either a working electrode made from a modified gold-patterned quartz crystal in view of simultaneous electrodeposition and EQCM experiments, or a thin film of platinum deposited on mica with the help of the sputtering technique for FEG-SEM experiments.

The morphology of the nanocomposite films was examined with a scanning electron microscope (FEG-SEM, Ultra 55 from Zeiss) coupled with EDS microanalysis.

3.4. *ac*-electrogravimetry

The electrochemical experiments were carried out in a classical three-electrode cell adapted for *ac*-electrogravimetry experiments in which the three electrodes were the same as those mentioned above for EQCM experiments.

The conditions for the electrochemical synthesis of PPy-DS and PPy-DS/ CeO_2 NPs were identical to those reported above (see Part 3.3), except that, in the case of nanocomposite materials, the electrosynthesis solution contained CeO_2 nanoparticles at two different concentrations, either 2 g.dm^{-3} or 5 g.dm^{-3}) in order to evaluate the influence of the amount of cerium oxide nanoparticles incorporated in the PPy-DS matrix on the ion exchange behaviour of the resulting nanocomposite films.

As far as *ac*-electrogravimetry experiments are concerned, they were carried out in a 0.5 mol.dm^{-3} NaCl aqueous electrolytic solution that was de-aerated prior to the

measurements. They were performed using a lab-made 9 MHz oscillator acting as a microbalance as well as quartz resonators (AWS, Spain) with a fundamental resonant frequency of 9 MHz. A four-channel frequency response analyzer (FRA, Solartron 1254) and a potentiostat (SOTELEM-PGSTAT) were used. The QCM was used under a dynamic regime, the modified working electrode (0.2 cm^2) was polarized at a selected potential, and a sinusoidal small amplitude potential perturbation was superimposed. The microbalance frequency change, Δf_m , corresponding to the mass response, Δm , of the modified working electrode was measured simultaneously with the *ac* response, ΔI , of the electrochemical system. The resulting signals were sent to the four-channel FRA, which allowed the electrogravimetric transfer function, $\frac{\Delta m}{\Delta E}(\omega)$, and the electrochemical impedance, $\frac{\Delta E}{\Delta I}(\omega)$, to be simultaneously obtained at a given potential situated inside the potential range allowing the redox switching of the polymer film [21-23]. The third transfer function, $\frac{\Delta q}{\Delta E}(\omega)$, can be experimentally calculated by using the following equation:

$$\frac{\Delta q}{\Delta E}(\omega) = \frac{1}{j\omega \frac{\Delta E}{\Delta I}(\omega)} \quad (7)$$

4. Results and Discussion

4.1. Characterization of CeO₂ nanoparticles

The crystalline variety of the CeO₂ nanoparticles prepared according to different methods can be deduced from the X-ray diffraction spectra shown on Figure 2. Whatever the synthesis method, these latter exhibit lines (111), (200), (220), (311), (222) and (400) that are characteristics of CeO₂, according to those of centered face cubic (CFC) fluorite structured CeO₂ crystal (see JCPDS N°34-394). Compared to the XRD patterns of a

commercial sample, the rays appeared broader for some of those spectra because of a smaller crystallite size.

TEM was used to investigate the morphology of the synthesised nanoparticles (see Figure 3). The TEM images show a heterogeneous size and non-uniform shape for the commercial powder (a). Consequently, the size distribution is very large (from 20 to 300 nm). The particles synthesised in a mixed solvent (water/ethanol: 1/1 in vol.) are smaller, homogeneous in size and spherical in shape compared to those prepared in pure water (see Figures 3b-c). Moreover, one can also observe the effect of calcination. Indeed, a higher calcination temperature and/or longer calcination duration both seem to tend to increase the particle size (see Figure 3d).

The CeO₂ nanoparticle diameter was also determined from BET technique by using specific area measurement (d_{BET}) and from direct measurement on TEM images (d_{TEM}) and compared with that measured by XRD (d_{XRD} , see Table 1). One can observe from Table 1 that XRD, TEM and BET techniques give diameter values that are fairly close for the three different synthesis methods. This demonstrates that the CeO₂ nanoparticles are primary and non-porous and also monodisperse in terms of diameter.

4.2. Electrosynthesis and composition of PPy-DS/CeO₂ NPs nanocomposite films.

In the following investigations, the CeO₂ nanoparticles that were used are those obtained from the synthesis method d for which d_{BET} , d_{XRD} and d_{TEM} are 12 nm, 10 nm and 12 nm respectively (see Table 1). Moreover, BET allowed the determination of a 70 m²/g specific area for those ceria nanoparticles (see Table 1).

In a first set of experiments, PPy-DS/CeO₂ NPs nanocomposite materials were electrodeposited on the gold electrode of an electrochemical quartz crystal microbalance

(EQCM) used simultaneously as a working electrode in a usual three electrode set-up (see section 3.3 and Figure 4b). For the need of comparison, a similar experiment was carried out in the absence of cerium oxide nanoparticles (see Figure 4a). Both voltammograms are similar as they both show the expected irreversible oxidation of the monomer known to constitute the first step of the electropolymerisation of the monomer and subsequent formation of the polymer film on the working electrode surface. One can also observe an anodic and a cathodic peak corresponding to the electroactivity of the polymer film. Intensity of both peaks increases with the number of scans, which indicates that the polymer film thickness increases as well. A similar conclusion can be drawn for the mass of the film, as observed from the curve showing the variation of the microbalance frequency. Let us remember here that according to the well-known Sauerbrey's law, an increase of the oscillation frequency of the quartz corresponds to a decrease of the mass of the deposit on the golden quartz electrode acting as a working electrode. Such electrogravimetric curves show both mass variations resulting from ions and solvent exchange occurring upon oxidation/reduction (doping/undoping) of the conducting polymer in the potential region situated between -0.5 and -1.5 V vs. SSE, as well as global mass increase of the film in the potential region allowing the monomer electrochemical oxidation and polymerisation, i.e. between -0.25 and 0.4 V vs. SSE. The mass variation deduced from the frequency variation measured at the end of each cyclic scan, i.e. at -1.5 V vs. SSE on the backward scan, was extracted and plotted as a function of each scan for both Figures 4a and 4b (see Figure 4c). This potential value was chosen because it corresponds to a situation where the electrodeposited film is in a reduced state. By doing so, one can consider that the mass increase observed for a given scan by comparison with the previous one actually corresponds to the global mass increase of the film. By considering that the incorporation of CeO₂ NPs do not alter the electrochemical deposition of the polymer, one can consider

that the difference in the mass uptake for a given cyclic scan extracted from both figures actually correspond to the mass uptake resulting exclusively from the incorporation of NPs. This CeO₂ mass uptake was plotted as a function of the number of cycles (see blue curve on Figure 4c) and reaches 4 µg at the ninth scan. The insert in Figure 4c shows a magnification of this plot for the five initial cycles. It clearly indicates that incorporation of CeO₂ NPs in the PPy matrix starts right from the first cycle. This possibly occurs thanks to electrostatic interactions between the oxidised and thus cationic polypyrrole film and CeO₂ NPs bearing negative surface charges as a consequence of adsorption of dodecylsulfate anions on their surface, according to a situation already reported in literature and encountered in the case of the incorporation of magnetite nanoparticles in polypyrrole films [32]. Taking into account an average value of 5.7 nm for the radius of spherical CeO₂ NPs (see CeO₂ NPs of the d type in Table 1) and a density value of 7.28 g/cm⁻³ for CeO₂ [31], one can estimate that 7.2 10¹¹ CeO₂ NPs were incorporated in the nanocomposite film in the course of the electrodeposition process illustrated in Figure 4b. Due to the selected film thickness, our films can be considered as acoustically thin enough and under these conditions, gravimetric response are exclusively obtained here. In other words, viscoelastic contributions can be neglected here.

4.3 Composite morphology

FEG-SEM observations and EDS analysis of the resulting nanocomposite films show a globular morphology bearing randomly oriented platelets (see Figure 5a), as already reported in literature for PPy films elaborated in similar experimental conditions [33]. On the surface of this complex morphology, CeO₂ nanoparticle clusters (aggregates) were observed to be inhomogeneously dispersed. All these observations remain true whatever the

CeO₂ NPs concentration in the electrosynthesis solution. The EDS microanalysis confirms the presence of cerium, and thus of CeO₂ nanoparticles (see Figure 5b), on and in the bulk of composite films (indeed EDS revealed the presence of ceria even in places where CeO₂ nanoparticles could not be seen on the surface). Let us emphasise that the other elements detected by this analysis came from the counter-ions (S, O) and the polypyrrole skeleton (C, N).

4.4. Film electrogeneration

DS doped PPy films were electrogenerated in the presence or in the absence of ex-situ synthesized CeO₂ nanoparticles according to the electrochemical procedure reported above (see section 3.3, 3.4 and 4.2 and Figure 4). It must be emphasized that consecutive cyclic voltammograms corresponding to the electrodeposition of the films investigated in this work were very similar in every aspects, whether the concentration of cerium oxide nanoparticles in the electrodeposition solution was 0, 2, or 5 g.dm⁻³.

4.5. Classical electrochemical characterization

The electrochemical reactivity and stability of the resulting PPy-DS and PPy-DS/CeO₂ NPs films were then tested after transfer in an electrolytic aqueous solution containing NaCl (0.5 mol.dm⁻³). The consecutive voltammograms observed in Figure 6 show the expected pair of peaks corresponding to the above mentioned doping/undoping process of polypyrrole. There is no significant change of the shape and peak intensities of the voltammogram upon potential cycling, indicating that PPy-DS and nanocomposite PPy-DS/CeO₂ NPs films possess an electrochemical behaviour that is sufficiently stable for *ac*-electrogravimetry investigations. It has to be emphasized that such observations are also

valid when the CeO₂ NPs are incorporated during the film electrodeposition. The peak intensities are not significantly altered whatever the content of CeO₂ NPs in the electrodeposition solution and thus, in the resulting electrodeposited film.

4.6. *ac*-electrogravimetric measurements

The ion exchange behaviour was studied by *ac*-electrogravimetry in NaCl aqueous electrolyte (0.5 mol.dm⁻³) in the active potential range between -0.6 to -1.1 V *vs.* SSE. In the following part, the interpretation procedure of *ac*-electrogravimetry data is reported for a selected potential, at E = -1.0 V *vs.* SSE.

4.6.1. *ac*-electrogravimetric measurements at E = -1.0 V *vs.* SSE:

(i) Electrochemical response

Figure 7 exhibits the electrochemical impedance spectroscopy, $\frac{\Delta E}{\Delta I}(\omega)$, and the charge/potential transfer function, $\frac{\Delta q}{\Delta E}(\omega)$, data for the three different PPy films measured at E = -1.0 V *vs.* SSE for PPy-DS (Figures 7a-b), PPy-DS/CeO₂ NPs (2 g.dm⁻³) (Figures 7c-d) and PPy-DS/CeO₂ NPs (5 g.dm⁻³) (Figures 7e-f) films. The experimental transfer functions and the simulated data from the model (see theoretical part, eqs. 5 and 6) are reported on the same graphs. A good agreement between the two sets of data is obvious in terms of shape and frequency distribution.

The electrochemical impedance, $\frac{\Delta E}{\Delta I}(\omega)$, (see Figures 7a, c and e) has a usual shape, when dealing with a ion-blocking electrode, from which it is difficult to easily extract information. The low frequency trend was related to a parasitic response and was simulated using equations 4 and 5. Nevertheless, considering the experimental responses

given by these electrochemical impedances, it should be noticed that the global response seems fairly constant independent from the film composition. It should also be noted that there is no obvious part with a slope equal to 45° or less in the electrochemical impedance response. Therefore, the rate limiting step is not mass transport in the film or in the solution but rather ionic transfer between the solution and the film [24]. The charge/potential transfer function, $\frac{\Delta q}{\Delta E}(\omega)$, (see Figures 7b, d and f) experimentally calculated through equation 7 permits to separate the ionic contribution without any possibility to identify the ionic species involved. It should be indicated here that the contribution of the parasitic reaction, occurring at low frequencies, was removed for keeping only the ionic transfer response. Two loops seem to appear in the three representations even if a fair separation is not easy to obtain. Indeed, the time constants corresponding to each ionic transfer appear to be very close to each other. At this stage, it is impossible to distinguish between anion and cation contributions and to determine which ionic species are involved. Nevertheless, the constants K_i and G_i were determined for two ions (see Table 2 for the K_i values corresponding to the two ions) and were used in the following simulations.

(ii) Electrogravimetric response

Then, to clarify the contribution of the charged and also the uncharged species (*i.e.* free solvent molecules), the mass/potential transfer functions, $\frac{\Delta m}{\Delta E}(\omega)$, are scrutinized. To show the evolution of the ionic transfer behavior as a function of the potential, the $\frac{\Delta m}{\Delta E}(\omega)$ responses at -1 V vs. SSE of the PPy-DS (Figure 8a), PPy-DS/CeO₂ NPs (2 g.dm⁻³) (Figure 8c) and PPy-DS/CeO₂ NPs (5 g.dm⁻³) (Figure 8e) films are shown. For all the responses, three species, sodium and chloride ions and free solvent molecules, were used in their simulations.

The DS doped polypyrrole films have been studied earlier in our group [24]. During oxidation, the anions were inserted in the film, whereas cations and solvent were expelled during oxidation. The kinetic constants of cations were the highest, followed by those of free solvent molecules and the anions contributed at low frequencies. As far as the PPy-DS films of the present study are concerned, the time constants of cations, solvent and anions are very close to each other and the different values obtained here do not correspond exactly with those reported previously. This could be attributed to the differences in the film preparation, specifically to the SDS concentration and potential range used during the potentiodynamic electrogeneration of the present PPy-DS films.

It should be noted that the contributions of the cation, the anion and the free solvent molecules are not perfectly separated as it can be seen in Figure 8. To solve this problem, partial transfer functions, $\left. \frac{\Delta m}{\Delta E} \right)_{as}(\omega)$ (corresponding to anion and solvent contribution) and $\left. \frac{\Delta m}{\Delta E} \right)_{cs}(\omega)$ (corresponding to cation and solvent contribution), were calculated and simulated to separate these contributions as it was already described elsewhere [24]. This method allows the contribution of one charged species to be removed; for example either a cation or an anion in case of cation, anion and free solvent contributions. Moreover, the response of the cation or of the anion is amplified in the resulting partial mass/potential transfer functions. This permits to a better separation between the charged species contribution and that of the free solvent. Here, only the anion/solvent mass-potential transfer functions, $\left. \frac{\Delta m}{\Delta E} \right)_{as}(\omega)$, were shown in Figures 8b, d and f for the three different films. The sodium contribution was removed from the global mass-potential transfer function, $\left. \frac{\Delta m}{\Delta E} \right)(\omega)$. For the three films, a high frequency loop is observed in the third

quadrant indicating a motion in the same direction as sodium ions and corresponding to the free solvent. At low frequency appears a small loop, located in the fourth quadrant, associated to chloride ions with an opposite flux compared with cations and free solvent motion for a same potential change. This approach is the only way to clearly demonstrate the anion contribution since a minor loop is observed in the total $\left(\frac{\Delta m}{\Delta E}\right)(\omega)$ diagram. For the water response, the semi-circle diameter is smaller for the PPy-DS compared to the two composite films, which indicates a greater contribution of water in this case.

At -1 V vs. SSE, using the parameters, K_c , K_a , G_c and G_a obtained from the previous electrochemical simulations (Figure 7 and Table 2), the atomic weight of the three mentioned species, m_c , m_a and m_s , the last two unknown parameters, K_s and G_s , associated to the free solvent transfer, can be estimated. For the three different films, at this potential, the *ac*-electrogravimetric response is located in the third quadrant: H₂O contribution appears at high frequencies, Na⁺ for the intermediate frequencies and Cl⁻ at low frequencies. The values of the key parameters K_i and G_i , for the three species, are listed in Table 2. The values of K_i are coherent with the rate of transfer associated to the three species *i.e.* $K_s > K_c > K_a$. In the case of the PPy-DS film, the three K_i values are higher compared with those obtained with the two other films containing CeO₂ NPs. This result demonstrates qualitatively different ion-exchange behaviours between PPy-DS and PPy-DS/CeO₂ NPs films. Another interesting parameter, the ionic transfer resistance, Rt_i , can also be estimated using the G_i values and the relation $Rt_i = \frac{1}{FG_i}$. For all the films, water transfer is easy as Rt_{H_2O} show the smallest values. The chloride transfer, characterized by Rt_{Cl^-} , presents higher values, especially in the case of the composite films. Thus, chloride transfer is more difficult and slower with the composite layers. Another interesting variable

named concentration/potential transfer function $\left(\frac{\Delta C_i}{\Delta E}\right)_{\omega \rightarrow 0}$ can be described as the concentration change related to the individual species, following a potential step. This quantity can be estimated through the following relation $\left(\frac{\Delta C_i}{\Delta E}\right)_{\omega \rightarrow 0} = -\frac{G_i}{K_i}$. According to Table 2, in the case of PPy-DS, the water contribution is predominant which is followed by the sodium contribution and finally, only a small part is due to chloride ions. In the case of the two PPy-DS/CeO₂ NPs films, this ratio remains constant for Cl⁻, it decreases slightly for Na⁺ and becomes more important for H₂O. A more porous structure can be pictured in the case of composite films, which favors the water transfer after a potential jump.

4.6.2. The changes of key parameters over the potential applied

For all the potential values selected in the active range, the two key parameters K_i and Rt_i were determined according to the procedure described above and shown for the measurements at -1 V vs. SSE. These values are presented in Figure 9.

For the sodium contribution (see Figure 9a), two domains can be distinguished in terms of transfer rate. In the cathodic region, i.e. below -1 V vs. SSE, Na⁺ is faster for the PPy-DS films while it is faster in the anodic region, i.e. above -0.9 V vs. SSE, for the composite films. In the case of Cl⁻ anions, the kinetics of transfer is independent of the potential and remains faster in the case of the PPy-DS film (see Figure 9b). For the free solvent, the plot of the influence of potential on K_s values shows bell-shaped curves for the composite materials and decreasing trend for the PPy-DS film (Figure 9c).

There are also two distinct domains in the charge transfer resistance values for Na⁺ ions (see Figure 9d). In the cathodic range situated below -0.8 V vs. SSE, Na⁺ transfer is rather easier for the PPy-DS films than in the anodic region situated above this same value.

When CeO₂ particles are present in the films (Figure 9d), the opposite behaviour is observed with a threshold potential of -0.85 V vs. SSE. The chloride ion transfer presents higher values in the case of the composite films. This is more pronounced in the cathodic region situated below -0.8 V vs. SSE. Thus, chloride transfer is more difficult and slower in the composite layers (Figures 9b and e).

4.6.3. Evolution of the relative concentration, ΔC_i , of each species as a function of the applied potential.

To quantify the role of each species, $\left. \frac{\Delta C_i}{\Delta E} \right|_{\omega \rightarrow 0}$ has been estimated as a function of the potential. It was shown that at low frequencies, $\left. \frac{\Delta C_i}{\Delta E} \right|_{\omega \rightarrow 0}$ becomes $\left. \frac{\Delta C_i}{\Delta E} \right|_{\omega \rightarrow 0} = -\frac{G_i}{K_i}$ (K_i and G_i values are obtained from simulation of the data shown in Figures 7 and 8) [21-23]. The integration of the $\left. \frac{\Delta C_i}{\Delta E} \right|_{\omega \rightarrow 0}$ against potential gives the insertion isotherm. Figure 10 presents the relative concentration change, ΔC_{Na^+} , ΔC_{Cl^-} and ΔC_{H_2O} , for Na⁺, Cl⁻ and H₂O, respectively.

The ΔC_{Na^+} values of the PPy-DS films with and without incorporation of CeO₂ nanoparticles do not show a remarkable difference. C_{Na^+} decreases, indicating the expulsion of the Na⁺ ions during oxidation (Figure 10a). Although slightly faster transfer of the cations at the film/electrolyte interface was observed, when CeO₂ NPs are present in PPy-DS films, one can observe that at E = -0.8 V vs. SSE for example, ΔC_{Na^+} becomes very close for the three investigated materials. Total H₂O amount involved indirectly in the

charge compensation process is magnified when the PPy-DS films contain CeO₂ nanoparticles. The water content increases as a function of the CeO₂ NPs content in the PPy-DS/CeO₂ NPs films (Figure 10b). This is possibly due to the increased porous volume in the conducting polymer as a result of the added CeO₂ nanoparticles. Interestingly, the ΔC_{Cl^-} values of PPy-DS/CeO₂ NPs (2 g.dm⁻³) and PPy-DS/CeO₂ (5 g.dm⁻³) films are about three times greater than that of PPy-DS films (Figure 10c). The kinetic study discussed above showed that the Cl⁻ ions in PPy-DS/CeO₂ NPs films at the film/electrolyte interface are slower compared with pristine PPy-DS films. Although the kinetics is slower in the presence of CeO₂ nanoparticles, the total amount of the Cl⁻ ions inserted during oxidation are substantially higher than for pristine PPy-DS films.

Further experiments are currently underway to gain further information about the reasons explaining why PPy-DS/CeO₂ NPs composite films possess a permeability to water and chloride anions different from that observed for pristine PPy-DS films. One possible explanation can be based on a predictable effect (although poorly characterised at the present stage of our investigations) of cerium oxide nanoparticles incorporation on the porosity of such films. Another interesting issue is the electrocatalytic behaviour of cerium oxide nanoparticles towards water oxidation [20] resulting in water consumption and protons production that may enhance water and chloride exchanges observed at rather anodic potentials for PPy-DS/CeO₂ NPs composite films.

5. Conclusion

In this contribution, PPy-DS/CeO₂ NPs nanocomposite films were electrogenerated successfully, as evidenced from cyclic electrogravimetry, SEM-FEG and EDS experiments, from electrolytic and colloidal aqueous solutions containing CeO₂ nanoparticles

synthesised ex-situ. The incorporation of cerium oxide nanoparticles was shown to affect substantially the ion exchange behaviour of dodecylsulfate doped polypyrrole films upon electrochemical doping/undoping, as revealed from ac-electrogravimetry experiments, but not its electrochemical behavior as observed from cyclic voltammetry technique used for the electrodeposition step or after transfer in a blank electrolytic and aqueous solution. In this latter case, whatever the CeO₂ nanoparticles content is, upon electrochemical oxidation of the film, chloride anions and sodium cations were actually found to be inserted in and expelled out of the film, respectively. In addition, free water molecules were found to be systematically expelled (as sodium cations) upon oxidation of the film (except for rather anodic potentials in the absence of ceria nanoparticles in the film). The main influence of the presence of cerium oxide nanoparticles was observed on the transfer rates of the exchanged species. As the cerium oxide nanoparticles content increases in the PPy-DS films, sodium cations and chloride anions were found to be exchanged much faster and much slower respectively. Finally, chloride anions were found to be exchanged in higher amounts in the presence of CeO₂ nanoparticles than in their absence. All these observations tend to indicate that the incorporation of cerium oxide nanoparticles increases the permeability of PPy-DS thin films towards chloride anions in terms of quantities but not from a kinetic aspect.

Acknowledgements

C. Benmouhoub acknowledges sincerely the Algerian government for having delivered to her a 18 month PNE-type scholarship.

References

- [1] D.W. Hatchett, M. Josowicz, Composites of Intrinsically Conducting Polymers as Sensing Nanomaterials, *Chem. Rev.* 108 (2008) 746.
- [2] A. Pailleret, N.T.L. Hien, D.T.M. Thanh, C. Deslouis, Surface reactivity of polypyrrole/iron-oxide nanoparticles: electrochemical and CS-AFM investigations, *J. Solid State Electrochem.* 11 (2007) 1013.
- [3] J.F. Rivera, C. Bucher, E. Saint-Aman, B.L. Rivas, M.C. Aguirre, J. Sanchez, I. Pignot-Paintrand, J.C. Moutet, Removal of arsenite by coupled electrocatalytic oxidation at polymer-ruthenium oxide nanocomposite and polymer-assisted liquid phase retention, *Appl. Catal. B*, 129 (2013) 130.
- [4] R.K. Sharma, L. Zhai, Multiwall carbon nanotube supported poly(3,4-ethylenedioxythiophene)/ manganese oxide nano-composite electrode for super-capacitors, *Electrochim. Acta*, 54 (2009) 7148.
- [5] M. Jin, G. Han, Y. Chang, H. Zhao, H. Zhang, Flexible electrodes based on polypyrrole/manganese dioxide/polypropylene fibrous membrane composite for supercapacitor, *Electrochim. Acta* 56 (2011) 9838.
- [6] I. Boyano, J.A. Blazquez, I. De Meatza, M. Bengoechea, O. Miguel, H. Grande, Y. Huang, J.B. Goodenough, Preparation of C-LiFePO₄/Polypyrrole lithium rechargeable cathode by consecutive potential steps electrodeposition, *Journal of Power Sources* 195 (2010) 5351–5359.
- [7] J. Zhu, S. Wei, L. Zhang, Y. Mao, J. Ryu, P. Mavinakuli, A.B. Karki, D.P. Young, Z. Guo, Conductive Polypyrrole/Tungsten Oxide Metacomposites with Negative Permittivity, *J. Phys. Chem. C*, 114 (2010) 16335–16342.

- [8] P. Montoya, F. Jaramilloa, J. Calderóna, S.I. Córdoba de Torresi, R.M. Torresi, Evidence of redox interactions between polypyrrole and Fe_3O_4 in polypyrrole- Fe_3O_4 composite films, *Electrochimica Acta*, 55 (2010) 6116–6122.
- [9] C. Janáky, C. Visy, O. Berkesi, E. Tombácz, Conducting Polymer-Based Electrode with Magnetic Behavior: Electrochemical Synthesis of Poly(3-thiophene-acetic-acid)/Magnetite Nanocomposite Thin Layers, *J. Phys. Chem. C*, 113 (2009) 1352–1358.
- [10] Q. Wu, F. Zhang, P. Xiao, H. Tao, X. Wang, Z. Hu, Y. Lü, Great Influence of Anions for Controllable Synthesis of CeO_2 Nanostructures: From Nanorods to Nanocubes, *J. Phys. Chem. C*, 112 (2008) 17076.
- [11] N.J. Lawrence, J.R. Brewer, L. Wang, T.-S. Wu, J. Wells-Kingsbury, M.M. Ihrig, G. Wang, Y.-L. Soo, W.-N. Mei, C.L. Cheung, Defect Engineering in Cubic Cerium Oxide Nanostructures for Catalytic Oxidation, *Nano Lett.*, 11 (2011) 2666.
- [12] X. Liang, J. Xiao, B. Chen, Y. Li, Catalytically Stable and Active CeO_2 Mesoporous Spheres, *Inorg. Chem.*, 49 (2010) 8188.
- [13] C. Slostowski, S. Marre, O. Babot, T. Toupance, C. Aymonier, Near- and Supercritical Alcohols as Solvents and Surface Modifiers for the Continuous Synthesis of Cerium Oxide Nanoparticles, *Langmuir*, 28 (2012) 16656.
- [14] J. Kaspar, P. Fornasiero, N. Hickey, Automotive catalytic converters: current status and some perspectives, *Catal. Today* 77 (2003) 419.
- [15] N. Izu, W. Shin, N. Murayama, S. Kanzaki, Resistive oxygen gas sensors based on CeO_2 fine powder prepared using mist pyrolysis, *Sens. Actuator B-Chem.* 87 (2002) 95.
- [16] A. Trovarrelli, C. De Leitenberg, M. Boaro, G. Dolcetti, The utilization of ceria in industrial catalysis, *Catal. Today* 50 (1999) 353.
- [17] F. Larachi, J. Pierre, A. Adnot, A. Bernis, Ce 3d XPS study of composite $\text{Ce}_x\text{Mn}_{1-x}\text{O}_{2-y}$ wet oxidation catalysts, *Appl. Surf. Sci.* 195 (2002) 236.

- [18] H. Imagawa, A. Suda, K. Yamamura, S. Sun, Monodisperse CeO₂ Nanoparticles and Their Oxygen Storage and Release Properties, *J. Phys. Chem. C*, 115 (2011) 1740.
- [19] H. Xiao, Z. Ai, L. Zhang, Nonaqueous Sol-Gel Synthesized Hierarchical CeO₂ Nanocrystal Microspheres as Novel, Adsorbents for Wastewater Treatment, *J. Phys. Chem. C*, 113 (2009) 16625.
- [20] G.R. Bamwenda, H. Arakawa, Cerium dioxide as a photocatalyst for water decomposition to O₂ in the presence of Ce(aq)(4+) and Fe(aq)(3+) species, *J. Mol. Catal. A* 161 (2000) 105.
- [21] L.T.T. Kim, C. Gabrielli, A. Pailleret, H. Perrot, Correlation between ion-exchange properties and swelling/shrinking processes in hexasulfonated calix[6]arene doped polypyrrole films: ac-electrogravimetry and electrochemical atomic force microscopy investigations, *Electrochim. Acta* 56 (2011) 3516.
- [22] L.T.T. Kim, C. Gabrielli, A. Pailleret, H. Perrot, Ions/Solvent Exchanges and Electromechanical Processes in Hexasulfonated Calix[6]Arene Doped Polypyrrole Films: Towards a Relaxation Mechanism, *Electrochem. Solid-State Lett.* 14 (2011) F9.
- [23] C. Gabrielli, J.J. Garcia-Jareno, M. Keddam, H. Perrot, F. Vicente, Ac-electrogravimetry study of electroactive thin films. I. Application to Prussian Blue *J. Phys. Chem. B* 106 (2002) 3182.
- [24] C. Gabrielli, J.J. Garcia-Jareno, M. Keddam, H. Perrot, F. Vicente, Ac-electrogravimetry study of electroactive thin films. II. Application to Polypyrrole *J. Phys. Chem. B* 106 (2002) 3192.
- [25] C. Gabrielli, H. Perrot, in: M. Schlesinger (Ed.), *Modern Aspects of Electrochemistry* No.44, Modeling and Numerical Simulations II, Springer, 2009, Chap. 5.

[26] O. Sel, L. To Thi Kim, C. Debiemme-Chouvy, C. Gabrielli, C. Laberty-Robert, H. Perrot, C. Sanchez, Proton Insertion Properties in a Hybrid Membrane/Conducting Polymer Bilayer Investigated by AC Electrogravimetry, *J. Electrochem. Soc.* 157 (2010) F69.

[27] L. To Thi Kim, C. Debiemme-Chouvy, C. Gabrielli, H. Perrot, Redox Switching of Heteropolyanions Entrapped in Polypyrrole Films Investigated by ac-Electrogravimetry, *Langmuir* 28 (2012) 13746.

[28] O. Sel, L. To Thi Kim, C. Debiemme-Chouvy, C. Gabrielli, C. Laberty-Robert, H. Perrot, Determination of the Diffusion Coefficient of Protons in Nafion Thin Films by ac-Electrogravimetry, *Langmuir* 29 (2013) 13665-13660.

[29] X.D. Zhou, W. Huebner, H.U. Anderson, Processing of nanometer-scale CeO_2 particles, *Chem. Mater.* 15(2) (2003) 378–382.

[30] R. Jenkins, R. L. Snyder, *X-Ray Powder Diffractometry*, Ed. Wiley-Interscience, 1996, 89–91.

[31] S. Tsunekawa, T. Fukuda, A. Kasuya, Blue shift in ultraviolet absorption spectra of monodisperse CeO_{2-x} nanoparticles, *J. Appl. Phys.* 87(3) (2000) 1318–1321.

[32] C. Janáky, B. Endrődi, O. Berkesi, C. Visy, Visible-light-Enhanced electrocatalytic activity of a polypyrrole/magnetite hybrid electrode toward the reduction of dissolved dioxygen, *J. Phys. Chem. C*, 114 (2010) 19338-19344.

[33] D. Kowalski, M. Ueda, T. Ohtsuka, Corrosion protection of steel by bi-layered polypyrrole doped with molybdophosphate and naphthalenedisulfonate anions, *Corros. Sci.* 49 (2007) 1635–1644.

Figure 1: Synoptic scheme of CeO₂ nanoparticles synthesis.

Figure 2: XRD diffraction patterns of ceria nanoparticles (CeO_2): a) commercial sample, b) prepared in water at 30°C , c) prepared in water/ethanol (1/1 by vol.) at 30°C , d) as (c) then calcinated at 600°C for 1 h.

Figure 3: TEM images and corresponding electronic diffractions of a, b, c and d-type CeO₂ nanoparticles.

Figure(s)

a)

b)

Figure 4 : a,b) cyclic voltammetry (black curve) and EQCM response (blue curve) obtained simultaneously in the course of the electrodeposition of PPy-DS films on a gold coated quartz a) in the absence, b) in the presence of CeO_2 nanoparticles (2 g.dm^{-3}), in an aqueous electrolytic solutions containing Py monomer (0.1 mol.dm^{-3}) and sodium dodecylsulfate ($0.025 \text{ mol.dm}^{-3}$) during 10 scans. Scan rate : 50 mV.s^{-1} . c) frequency variation (black and red dots) and mass variation difference (blue dots) all measured at the end of each cyclic voltammetry scan (-1.5 V vs. SSE) and extracted from Figures 4a,b. Mass variation difference is calculated from the difference between the mass variation measured during the electrodeposition of PPy-DS film in the presence of CeO_2 NPs (red dots) and that measured in the absence of CeO_2 NPs (black dots) and is attributed in a first approximation to the uptake of CeO_2 NPs only.

Figure 5: a) SEM image and b) EDS spectrum of PPy-DS/CeO₂ NPs nanocomposite films electrodeposited from an electrolytic and colloidal aqueous solution containing SDS (0.025 mol.dm⁻³), CeO₂ NPs (1 g.dm⁻³) and pyrrole (0.1 mol.dm⁻³).

Figure 6: Consecutive cyclic voltammograms (solid line : 1st scan, dash line : 15th scan) obtained for a working electrode modified with a PPy-DS/CeO₂ NPs nanocomposite thin film doped with DS anions in an aqueous electrolytic solution containing NaCl (0.5 mol.dm⁻³). Working electrode : gold coated quartz crystal adapted for *ac*-electrogravimetry experiments, counter-electrode: platinum grid, reference electrode: SSE and scan rate: 50 mV.s⁻¹.

b)

Figure 7: Measured and simulated transfer functions $\frac{\Delta E}{\Delta I}(\omega)$ and $\frac{\Delta q}{\Delta E}(\omega)$ of the PPy-DS (a and b), PPy-DS/CeO₂ NPs (2 g.dm⁻³) (c and d) and PPy-DS/CeO₂ NPs (5 g.dm⁻³) (e and f) films at -1 V vs. SSE in 0.5 mol.dm⁻³ NaCl aqueous electrolyte. The film thickness is 200 nm and the parameters used for the calculations are given in Table I.

Figure 8: Measured and estimated mass transfer functions, $\frac{\Delta m}{\Delta E}(\omega)$, and partial anion-solvent transfer functions of the PPy-DS (a and b), PPy-DS/CeO₂ NPs (2 g.dm⁻³) (c and d) and PPy-DS/CeO₂ NPs (5 g.dm⁻³) (e and f) films at -1 V vs. SSE in 0.5 mol.dm⁻³ NaCl aqueous electrolyte. The film thickness is 200 nm and the molar mass of the species involved in the charge compensation as follows: $m(\text{Na}^+) = 23 \text{ g.mol}^{-1}$, $m(\text{Cl}^-) = 35.5 \text{ g.mol}^{-1}$, $m(\text{H}_2\text{O}) = 18 \text{ g.mol}^{-1}$. The parameters used for the calculations are given in Table I.

a)

b)

c)

d)

e)

f)

Figure 9: Estimated values for the kinetic parameters a-c) K_i and d-f) $R_{t_i} = \frac{1}{FG_i} / \Omega \cdot \text{cm}^2$ as

a function of potential for the PPy-DS, PPy-DS/ CeO_2 NPs (2 g.dm⁻³) and PPy-DS/ CeO_2 NPs (5 g.dm⁻³) films.

Figure 10: Relative concentration change, ΔC_i , for **a)** Na^+ , **b)** H_2O , and **c)** Cl^- of the PPy-DS, PPy-DS/CeO₂ NPs (2 g.dm⁻³) and PPy-DS/CeO₂ NPs (5 g.dm⁻³) films as a function of the applied potential in 0.5 mol.dm⁻³ NaCl aqueous electrolyte.

CeO ₂ samples	A (m ² /g)	d _{BET} (nm)	d _{XRD} (nm)	d _{TEM} (nm)
a	-	-	43	60±40*
b	62	13	13	15±2
c	84	10	9	10±1
d	70	12	10	12±1

Table 1: Crystallite size values obtained by BET, XRD and TEM. (*size distribution for this sample is very large, from 20 nm to 300 nm, as deduced from the exploitation of Figure 3a).

Table 2: Estimated values for K_i , Rt_i and $-G_i/K_i$ parameters from *ac*-electrogravimetry measurements/simulations in 0.5 mol.dm⁻³ NaCl at -1 V vs. SSE for the three tested films.

-1 V vs. SSE	$K_i \times 10^5 / \text{cm.s}^{-1}$			$Rt_i = \frac{1}{FG_i} / \Omega.\text{cm}^2$			$\left. \frac{\Delta C_i}{\Delta E} \right)_{\omega \rightarrow 0} = -\frac{G_i}{K_i} / \text{mmol.cm}^{-3}.\text{V}^{-1}$		
	Na^+	Cl^-	H_2O	Na^+	Cl^-	H_2O	Na^+	Cl^-	H_2O
PPy-DS	15.7	2.5	116.0	47.1	1473.0	4.0	1.4	0.3	2.1
PPy-DS / CeO ₂ NPs (2 g.dm ⁻³)	6.4	1.4	27.0	175.7	2585.0	11.8	0.9	0.3	3.2
PPy-DS / CeO ₂ NPs (5 g.dm ⁻³)	11.3	1.5	11.6	80.3	2200.0	28.7	1.1	0.3	3.1