Eco-Efficient Synthesis of LiFePO_4 with Different Morphologies for Li-Ion Batteries

Nadir Recham, Michel Armand, Lydia Laffont-Dantras, Jean-marie Tarascon

► To cite this version:

Nadir Recham, Michel Armand, Lydia Laffont-Dantras, Jean-marie Tarascon. Eco-Efficient Synthesis of LiFePO_4 with Different Morphologies for Li-Ion Batteries. *Electrochemical and Solid-State Letters*, 2008, vol. 12 (n° 2), pp.A39-A44. 10.1149/1.3039090 . hal-01164609

HAL Id: hal-01164609

<https://hal.science/hal-01164609>

Submitted on 17 Jun 2015

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Open Archive TOULOUSE Archive Ouverte (OATAO)

OATAO is an open access repository that collects the work of Toulouse researchers and makes it freely available over the web where possible.

This is an author-deposited version published in : <http://oatao.univ-toulouse.fr/>
Eprints ID : 8658

To link to this article : doi: 10.1149/1.3039090
URL : <http://dx.doi.org/10.1149/1.3039090>

To cite this version : Recham, Nadir and Armand, Michel and Laffont-Dantras, Lydia and Tarascon, Jean-Marie *Eco-Efficient Synthesis of LiFePO₄ with Different Morphologies for Li-Ion Batteries*. (2008) Electrochemical and Solid State Letters, vol. 12 (n° 2). A39-A44. ISSN 1099-0062

Any correspondence concerning this service should be sent to the repository administrator: staff-oatao@listes-diff.inp-toulouse.fr

Eco-Efficient Synthesis of LiFePO₄ with Different Morphologies for Li-Ion Batteries

N. Recham, M. Armand, L. Laffont, and J-M. Tarascon^z

Laboratoire de Réactivité et Chimie des Solides, Université de Picardie Jules Verne, CNRS UMR6007, 80039 Amiens, France

LiFePO₄ is presently the most studied electrode material for battery applications. It can be prepared via solution, although it requires well-controlled pH conditions to master the iron valence state in the newly created material. Here we report its synthesis via the use of “latent bases” capable of releasing a nitrogen base upon heating. This way of controlling the reaction pH enables, in the absence of excess Li, the preparation of Fe⁺³-free LiFePO₄ powders having various morphologies and showing good electrochemical performance. This approach is shown to offer great opportunities for the low-temperature synthesis of various electrode materials.

Rechargeable Li-ion cells, which are powering most of today’s portable electronics, are strongly considered for automotive transportation. Yet, safety and cost issues remain to be solved, prior to seeing this environmentally much-needed market extend globally.¹ The cost is mainly determined by the material abundance, thus 3d metal redox elements, such as in LiFePO₄,² are receiving increased attention, while Co- or Ni-based electrodes are electronic market niches. The carbon nanopainting techniques, applied to insulating LiFePO₄, yield high-rate yet safe batteries.³ The environmental attractiveness of LiFePO₄ prevails over an energy density penalty due to low packing density, even more so in the presence of carbon. LiFePO₄ is the main contender for electric vehicle automakers, but natural sources of triphylite are scarce. Synthetic triphylite has to be made with directly processable grain sizes while looking for the most expeditious and energy-saving carbon coating.

Precipitation from aqueous medium, under normal pressure⁴ or in autoclave,^{5,6} is often preferred to ceramic methods; the latter require high temperatures to ensure the diffusion of the reactants and the growth of the grains; they therefore demand high energy while leading to highly polydispersed powders. Precipitation methods in liquid media (e.g., solvothermal synthesis)⁷ require little energy, and if nucleation and growth phenomena are controlled, the size distribution is much narrower.

Basically, a solvothermal synthesis reaction consists in reacting metal/nonmetal-based soluble salts with a base, and increasing the temperature to promote the growth of the desired phase via Ostwald ripening. Inherent drawbacks are formation of hydroxides from the metals used, without any control over the nucleation step and possible oxidation by air oxygen. This is particularly worrisome in the case of Fe^{II} and cobalt^{II}.

Hydrothermal synthesis of lithium iron phosphate, according to the reaction $\text{H}_3\text{PO}_4 + \text{FeSO}_4 + 3\text{LiOH} \Rightarrow \text{LiFePO}_4 + \text{Li}_2\text{SO}_4 + 3\text{H}_2\text{O}$, has been demonstrated,⁸ though some Fe^(III) impurities remain in the final product. More recently, Delacourt et al.⁴ succeeded in preparing at low temperature (ca. 108°C) electrochemically active LiFePO₄ nanoparticles having a few percent of Fe⁺³^{9,10} via a precipitation process in a pH range close to neutrality using a water-dimethyl sulfoxide acidic mixture containing equimolar amounts of 0.1 M FeSO₄·7H₂O and H₃PO₄, to which they added dropwise 0.3 M LiOH solution (e.g., to end with a Li/Fe/P molar ratio of 3:1:1). For either hydrothermal or precipitation processes, there are drawbacks (i) the use of costly LiOH in threefold excess (compared to LiFePO₄) and then the need to recycle Li₂SO₄, falling short of the economy of atoms now sought in industrial chemistry, and (ii) the increased risk of forming Fe(OH)₂ precursor to Fe⁺³ impurities in the final product, respectively. Ferric species are thought to be responsible for the leaching of metal ions in the electrolyte and

through their reduction products, increasing the impedance of the anode.¹¹ All of these aforementioned issues are detrimental to reproducible and low-cost manufacturing.

To remedy these issues, we searched for different synthetic approaches and have been inspired by recent studies aiming toward the low-temperature synthesis of various inorganic compounds, either in bulk or nanocrystalline forms, such as ammonium–thorium phosphates,¹² cerium biphosphate, hydrotalcites,¹³ TiO₂,¹⁴ La_{0.8}Sr_{0.2}Ga_{0.8}Mg_{0.2}O_{2.8},¹⁵ or (NH₄)₂Ce(PO₄)₂·H₂O,¹⁶ via the use of a basic medium created by the temperature-driven decomposition of urea. Herein we implemented the aforementioned approach to the synthesis of tailor-made LiFePO₄ powders via a solvothermal process in either aqueous or nonaqueous solvents. This synthesis does not rely on the use of LiOH but rather on the use of additives (urea, hexamethylene tetramine, and others), which upon mild heating liberate in situ the basic species needed to complete the precipitation reaction.

The use of urea as an initially neutral chemical yielding NH₃ and CO₂ upon hydrolysis at 90°C according to Scheme 1 has been suggested as early as 1989 by Matijevic’s group^{17–19} for the precipitation of alkaline earth carbonates, but in this case, CO₂ is immediately trapped as CO₃^{2–} in the lattice, displacing the equilibrium. However, the preparation of the olivines using latent bases is not known and an essential difference is the need to go >100°C, below which the anhydrous LiFePO₄ does not form.

In light of this previous work on forced hydrolysis, we first attempted the hydrothermal synthesis of LiFePO₄ in aqueous medium as follows. Urea and LiH₂PO₄ in a molar ratio 1.2:1, so as to have a slight excess of NH₃ to neutralize LiH₂PO₄ and raise the solution pH through the reaction, were dissolved under magnetic stirring in water during 10 min. Stoichiometric (Li/P = 1:1) amount of FeSO₄·7H₂O to produce LiFePO₄ is then added to the solution. After 5 min of magnetic stirring, the solution, which pH is 3.4, is poured into a poly(tetrafluoroethylene) (PTFE) container which is placed in an autoclave. Once the atmosphere of the autoclave has been deoxygenated by flushing with argon, the solution temperature, while being maintained under constant agitation, was increased to 180°C at a rate of 1°C/min, maintained at that temperature for 3 h, then left to cool to ambient temperature. The recovered greenish suspension was then filtered, washed, and dried (Fig. 1). The X-ray diffraction (XRD) pattern, recorded on a Bruker D8 Advance diffractometer (Cu Kα radiation, λ₁ = 1.54053 Å) indicates the pres-

^z E-mail: jean-marie.tarascon@sc.u-picardie.fr

Figure 1. (Color online) Rietveld refinement for LiFePO_4 made in water. Experimental X-ray powder diffraction pattern (dotted curve) compared to the Rietveld-refined profile (continuous line) and difference curve.

ence of the single-phase LiFePO_4 , as all the peaks were entirely indexed in the space group $Pnma$. The lattice parameters $a = 10.3601 \text{ \AA}$, $b = 6.0027 \text{ \AA}$, $c = 4.7075 \text{ \AA}$; $V = 292.75 \text{ \AA}^3$, obtained from full pattern matching refinements via the program Fullprof²⁰ using the pseudo-Voigt profile function of Thompson et al.,²¹ are in good agreement with literature reports.^{22–24}

To gain insight into the reacting path leading to the growth of LiFePO_4 , we monitored the variation of the pH together with the nature of the phases formed as a function of time for various temperatures. To do so, the autoclave was equipped with an in situ sampling device, allowing intermittent aliquots to withdraw while the reaction proceeded. In a typical experiment the reaction mixture was placed in the autoclave and flushed with N_2 gas prior to turning on the autoclave mantle heater. A ramp of $1^\circ\text{C}/\text{min}$ was used to reach 150 and 180°C (pressures ≈ 10 and 20 bars, respectively). Once such isothermal temperatures were reached (time T_0), samples were intermittently withdrawn. The samples were first checked for their pH and the solids twice centrifuged and filtered through a 0.1 mm filter (Millipore) and X-rayed. Figure 2a shows the evolution of pH as a function of time, implying the efficient and rapid hydrolysis of the urea additive because at 180°C the pH of the solution becomes basic in ~ 40 min, while, as expected, it takes ~ 60 min at 150°C . In parallel, XRD data (Fig. 2b) indicate that under such experimental conditions the growth of LiFePO_4 enlists sequentially the appearance, at an early stage of the reaction, of $\text{Fe}_3(\text{PO}_4)_2 \cdot 8\text{H}_2\text{O}$ (vivianite), which after ~ 40 min leads to the dehydrated version $\text{Fe}_3(\text{PO}_4)_2$, which transforms into LiFePO_4 over the next hundred minutes. The same sequence, but with longer time intervals, occurs at lower temperatures. The scanning electron microscopy (SEM) images of the powders, taken with a field emission gun (FEI Quanta F200P), revealed nicely crystallized $2\text{--}4 \text{ }\mu\text{m}$ cubic particles having salient facets (Fig. 3a), regardless of whether they were prepared at either 150 or 180°C . Temperatures lower than 120°C fail in producing LiFePO_4 powders. Finally, Mössbauer measurements recorded in transmission mode (data not shown) on the micrometric samples repeatedly indicate amounts of Fe^{3+} falling within the $0\text{--}1\%$ range and they are stable in time. Nanometric samples kept in laboratory atmosphere, however, tend to oxidize. The details of such results will be addressed in a forthcoming paper.

Because this approach was validated, it was extended to the use of numerous molecules, some of which were previously used such as amines²⁵ that could produce in situ, via a solvolysis reaction or via a temperature-controlled decarboxylation, Brønsted or Lewis bases necessary to the formation of LiFePO_4 . Table I captures some of the molecules (guanidinium or isocyanate salts, hexamethylene-

Figure 2. (Color online) In situ monitoring of the solvothermal reaction with (a) variation of pH of the solution as a function of time for two distinct experiments run separately at 150 and 180°C and (b) structural evolution of the precipitated materials for the same samples as in (a).

tetramine), together with their hydrolysis reaction in water at mild temperatures, which we have successfully used. In all cases, yields were 100%, within error for losses during filtration/washing. For conciseness, rather than giving a detailed experimental description of all LiFePO_4 specimens prepared using various combinations of solvents and latent bases which are summarized in Table II together with the lattice parameters of the obtained phases, we focused on an additional aspect which lies in the nature/choice of a solvolysis agent chemically compatible with the “latent bases” to trigger the liberation of a base.

Water is by all means the most popular solvolysis agent, but other polar liquids containing OH groups such as diols or amides can be used as previously reported,²⁶ hence providing a myriad of opportunities to adjust the morphology/texture of the newly born phases. 1,2-propanediol (to avoid toxic 1,2-ethanediol) was first tried, as an alternative to water, on the basis of the reaction in Scheme 2, which we have shown to occur at around 150°C . Such a finding was applied to the hydrothermal synthesis of LiFePO_4 . Stoichiometric amounts of LiH_2PO_4 and urea in slight excess (for rea-

Figure 3. SEM images for LiFePO_4 powders made in water are shown in (a), while the TEM/HRTEM images for powders grown in water/diol, formamide/diol, and DMF-diol are shown in (b), (c), and (d) (inset left: DMF before heating, right after heating at 680°C), respectively. For each picture, the bright-field images give information on the particle shape and size (left) combined with a selected area diffraction (SAED) pattern only for (c). HRTEM images and SAED were combined with Fourier transform, providing structural details both at the core and surface material level, with the presence of a well-defined carbon layer covering the particles when DMF was used.

sons already described) were dissolved under magnetic stirring in 1,2-propanediol, to which we added the right amount of $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$ to produce LiFePO_4 . The solution was placed into an autoclave in which the temperature was raised to 180°C in 2 h and maintained for 24 h, the time that we determined necessary after several trials to obtain a complete reaction; nicely crystallized LiFePO_4 powders having the following lattice parameters $a = 10.3470 \text{ \AA}$, $b = 6.0032 \text{ \AA}$, $c = 4.6997 \text{ \AA}$, and $V = 291.92 \text{ \AA}^3$ resulted. We found that the particle size and morphology of the powders can be deliberately modified using varying water/1,2-propanediol mixtures, with smaller particle sizes (200 nm), having platelet shapes obtained for an 80:20% water/1,2-propanediol volume ratio as apparent from transmission electron microscopy (TEM) (Fig. 3b) using a FEI Tecnai F20 S-TWIN microscope. The bright-field image (Fig. 3b; left) shows platelet-shaped particles with sizes ranging from 200 to 800 nm. One part of the bright-field image has been studied in high resolution showing that the LiFePO_4 particles are monoliths. Overall, the powders prepared in diol-based solvents were always found to be more dispersed than those prepared in pure water.

To further explore the feasibility of controlling the size and morphology of the oxides hydrothermally prepared via the use of “latent bases,” we decided to explore formamide (F) and dimethylformamide (DMF) solvents. Besides having higher boiling temperatures (210°C for F at 153°C for DMF) than water, hence enabling a reaction at higher temperatures with lower pressures, such solvents have high solubilizing power due to their higher dielectric constant (110 for F as compared to 75 for water), hence enabling a wider use of precursors.

PTFE vessels, containing LiH_2PO_4 , urea, and anhydrous FeCl_2 dissolved in a formamide/propanediol solution (95-5 by volume), were placed in the autoclave and flushed with N_2 prior to raising its

temperature to 150°C . From a survey of various reacting times we deduced that 24 h was the minimum time needed to ensure the nucleation/growth of single-phased LiFePO_4 powders made of poly-disperse, well-crystallized particles (size: from 50 nm to $2 \mu\text{m}$) having a lozenge shape and lying in the ab plane with the c -axis perpendicular to ab (when LiFePO_4 is indexed in $Pnma$), as deduced from TEM study (Fig. 3c). In Fig. 3c (left) the particles show a surface effect clearly visible on the high-resolution TEM (HR-TEM) image. In fact, the thickness is different from the edge to the center of the particle, which explains the different contrast, but the particle is still LiFePO_4 .

With the same experimental protocol, reaction time, and temperature, but using DMF rather than formamide, we succeeded in producing LiFePO_4 powders made of $1\text{--}2 \mu\text{m}$ particles covered with a polymeric layer in Fig. 3d (inset left). Most likely this film is of organic nature, as it was occasionally found to melt under the microscope beam during TEM investigation. This was confirmed by a flash annealing at 680°C and under Ar atmosphere, which indicated that such a polymeric coating layer does transform into a $3\text{--}5 \text{ nm}$ carbon layer clearly visible on the HRTEM of Fig. 3d (right). In Fig. 3d, the LiFePO_4 powders present now $50\text{--}200 \text{ nm}$ well-crystallized particles having an oblong shape. Such a serendipitous result is of great importance for the use of LiFePO_4 in Li-ion batteries as it directly provides the carbon nanopainting. Thus, the use of DMF provides an interesting alternative to simplify the synthesis of carbon-coated LiFePO_4 particles, although we recognize that we do not presently control the nature and composition of the polymer, which most likely results from the interaction between DMF and urea, because it is not observed in the absence of urea. The use of anhydrous FeCl_2 is proof that water brought by hydrated Fe^{II} sulfate is not needed. FeCl_2 can be advantageously replaced by inexpensive $\text{FeCl}_3 + \text{Fe}^\circ$.

Table I. Reaction schemes by which various “latent bases” release a Lewis or Bronsted base (this seems to always be ammonia) via solvolysis reactions in the presence of water or diol-based solvents.

The above reaction based on the use of F could also proceed in the absence of urea, implying that this solvent can act as a "latent base." Obviously it could not occur via a solvolysis reaction but rather through a temperature-driven decomposition reaction that results in the release of NH_3 and CO, which starts at 180°C and becomes appreciable near 200°C , offering another dimension to our concept of latent bases, although it is more difficult to control.

Overall, the aforementioned examples demonstrated the richness of the low-temperature “latent base” synthesis method to produce LiFePO_4 powders of various morphologies. While each synthesis produced single-phased LiFePO_4 , we note a spread in the unit cell volumes of about $3 \text{ \AA}^3$ that we ascribed to the existence of some Li/Fe disorder within the structure based on early neutron diffraction and powder Rietveld refinement studies carried out on hydrothermal or solvothermal-made samples having unit cell volumes of 293 and $289 \text{ \AA}^3$, respectively. We found such a spread to narrow down to $0.3 \text{ \AA}^3$ by a postanneal treatment under argon of the low-temperature powders, suggesting that the annealing step tends to

lack the Li and Fe ions in their respective M1 and M2 sites. Although we evidenced the feasibility of manipulating the particle morphology by acting on the base/solvent combinations, we must note that our powders are far from being monodisperse, with size distribution ranging from 2 to 4 μm , 200–800 nm, 50 nm to 2 μm , and 50–200 nm when water, water/diol, formamide/diol, and DMF were used as reacting solvents, respectively. Mastering particle coarsening requires tedious field-trial approaches aimed at surveying various synthesis parameters. Further work to improve size uniformity has been undertaken.

Whatever the sample size distribution, Swagelok Li/LiFePO₄ cells were assembled in an argon-filled glove box to check the electrochemical performances on the various batches of LiFePO₄ powders. The cells, using 1 M LiPF₆ electrolyte solution in 1:1 dimethyl carbonate:ethylene carbonate as separator/electrolyte, were cycled at a rate of one lithium in 10 h. All LiFePO₄ samples were found to be electrochemically active. However, again for brevity, we solely report data for the most representative samples made in water/diol

Table II. Summary of the experimental parameters (solvents, latent bases, temperature) used to prepare various LiFePO₄ samples together with the cell parameters of obtained phases. Regardless of the sample, χ^2 values lower than 3 were obtained for our refinement.

Latent base	Solvent	Temperature (°C)	Cell parameters (Å)
Urea	Water	150	$a = 10.35922(4)$ $b = 6.00717(4)$ $c = 4.70446(4)$
Urea	Water	160	$a = 10.34787(5)$ $b = 5.99748(4)$ $c = 4.69968(4)$
Urea	Water	170	$a = 10.35727(5)$ $b = 6.00254(4)$ $c = 4.70532(4)$
Urea	Water	180	$a = 10.36019(5)$ $b = 6.00275(7)$ $c = 4.70750(6)$
HMT	Water + 2 mL H ₂ SO ₄	150	$a = 10.35496(5)$ $b = 5.99814(7)$ $c = 4.70625(4)$
HMT	Water + 2 mL H ₂ SO ₄	180	$a = 10.36791(3)$ $b = 6.00658(4)$ $c = 4.71104(4)$
Ammonium 2-cyanoéthanoate	Water	150	$a = 10.35697(4)$ $b = 6.00286(4)$ $c = 4.70709(4)$
Commercial guanidinium sulfate	Water	150	$a = 10.35690(3)$ $b = 6.00179(4)$ $c = 4.70672(4)$
HMT	Formamide + 5 mL 1,2-propanediol	150	$a = 10.32599(5)$ $b = 5.99040(4)$ $c = 4.71266(6)$
Urea	DMF + 5 mL 1,2-propanediol	150	$a = 10.31801(6)$ $b = 6.00259(5)$ $c = 4.68841(4)$
HMT	Absolute ethanol + 5 mL 1,2-propanediol	150	$a = 10.36112(5)$ $b = 5.99850(5)$ $c = 4.70715(5)$
Urea	Water-1,2-propanediol	180	$a = 10.36042(5)$ $b = 6.00853(5)$ $c = 4.69908(4)$
Formamide	Formamide	180	$a = 10.35362(3)$ $b = 6.00713(5)$ $c = 4.70724(4)$

(Fig. 4a) and DMF/diol (as solvolysis agent) (Fig. 4b) solvent mixtures. For the former, the voltage composition curve shows at a C/10

Scheme 2.

rate a reversible and sustainable capacity of 150 mAh/g, which is somewhat spectacular knowing that this sample was neither chemically coated nor ever treated at temperatures greater than 200°C. Turning back to the LiFePO₄ powders grown in DMF/diol mixtures, they initially show only weak signs of electrochemical activity, even when hand-milled with 15% C; this is most likely due to the surface polymeric film. To counter such a difficulty, we flash-annealed our powders at 680°C, resulting in 2% carbon coating, as deduced by thermogravimetric analysis (TGA) measurement.²⁶ Subsequent hand mixing of such coated powders with 15 wt % of additional carbon was shown to give electrodes displaying a sustained reversible capacity of 150 mAh/g at C/10 (Fig. 4b). Such an electrode exhibits

Figure 4. (Color online) Room-temperature voltage–composition curves together with capacity retention (inset) are reported in (a) and (b) for samples made out of water/diol and DMF/diol solvent mixtures. The positive electrodes, containing 7 to 10 mg of active material per cm^2 , were made by ballmilling (Spex 800 for 15 min) LiFePO_4 powders and carbon SP (carbon black from MM, Belgium) mixtures in a 85–15 wt % ratio. The power rate capabilities of such electrodes, determined using a “signature curve,”²⁷ are shown in (c) and (d), respectively, with in each case the data for the carbon-free sample (open circles) and carbon-coated sample (full circles). Note that in (d) the open circle data corresponds to a 2% in situ carbon coating (see text) while the full circles data refers to an additional 3% ex situ carbon.

better kinetics than the previous one as evidenced by its lower polarization (50 mV) together with the power rate plot (Fig. 4c). Nevertheless, such rate capabilities are far from today’s state-of-the-art electrodes based on carbon nanopainted LiFePO_4 powders made from the traditional pyrolysis of sugar precursors at 700°C. For comparative studies, we applied such treatment to our water-diol-grown LiFePO_4 powders. The rate capability of such carbon-coated 200–300 nm powders shown in Fig. 4c shows a drastic improvement. Improving further the kinetics of such an electrode will constitute the next stage of our research after the choice of a solvent/temperature/latent base trio for optimal grain size and tap density.

In summary, we have presented an alternative low-temperature synthesis approach for the preparation of LiFePO_4 . The choice of latent bases is very large, as the possibility of shifting from water to water/glycol or organic solvents alone. Besides acting on the particle size and shape, a side advantage of DMF resides in the growth of a polymer surface layer, which leads to a carbon coating at higher temperatures. Addition of surface active agents during synthesis is also a means of controlling the powder morphology. Although LiFePO_4 was the main focus, we should mention that this new technique applies to the successful synthesis of a wide variety of electrode materials [LiMPO_4 ($M = \text{Mn, Co, Ni}$), $\text{Li}_2\text{FeSiO}_4$, Fe_2SiO_4].²⁵ In short, we believe that such work will open new opportunities to solution chemistry, with the economy of atoms (Li) for sustainability and cost considerations, as the latent bases we used are industrial compounds, and the innocuousness of by-products [e.g., $(\text{NH}_4)_2\text{SO}_4$, a fertilizer], we hope, will lead to industrial processes.

Acknowledgments

The authors warmly thank C. Delacourt and C. Masquelier for helpful discussions regarding their experience on solution chemistry, and J-C Jumas for collecting the Mössbauer experiments.

Université de Picardie Jules Verne assisted in meeting the publication costs of this article.

References

1. J. M. Tarascon and M. Armand, *Nature (London)*, **414**, 359 (2001).
2. A. K. Padhi, K. S. Nanjundaswamy, and J. B. Goodenough, *J. Electrochem. Soc.*, **144**, 1188 (1997).
3. N. Ravet, J. B. Goodenough, S. Besner, M. Simoneau, P. Hovington, and M. Armand, Abstract 127, The Electrochemical Society Meeting Abstracts, Vol. 99-2, Honolulu, HI, Oct 17–22, 1999.
4. C. Delacourt, P. Poizot, S. Levasseur, and C. Masquelier, *Electrochem. Solid-State Lett.*, **9**, A352 (2006).
5. B. Jin and H.-B. Gu, *Solid State Ionics*, **178**, 1907 (2008).
6. J. Chen, M. J. Vacchio, S. Wand, N. Chernova, P. Y. Zavalij, and M. S. Whittingham, *Solid State Ionics*, **178**, 1676 (2008).
7. C. Xu, J. Lee, and A. S. Teja, *J. Supercrit. Fluids*, **44**, 92 (2008).
8. J. Chen, S. Wang, and M. S. Whittingham, *J. Power Sources*, **174**, 442 (2007).
9. C. Delacourt, P. Poizot, and C. Masquelier, World Pat., WO 20070051 (2007).
10. C. Delacourt, Ph.D. Thesis, LRCS Université de Picardie-Jules Verne, Amiens, France (2005).
11. K. Amine, J. Liu, and I. Belharouak, *Electrochem. Commun.*, **7**, 669 (2005).
12. M. A. Salvado, P. Pertierra, A. I. Bortun, C. Trobajo, and J. R. Garcia, *Inorg. Chem.*, **47**, 7207 (2008).
13. P. Benito, M. Herrero, C. Barriga, F. M. Labajos, and V. Rives, *Inorg. Chem.*, **47**, 5453 (2008).
14. L.-H. Kao, T.-C. Hsu, and H.-Y. Lu, *J. Colloid Interface Sci.*, **316**, 160 (2007).
15. T.-Y. Chen and K.-Z. Fung, *J. Eur. Ceram. Soc.*, **28**, 803 (2008).
16. M. A. Salvado, P. Pertierra, C. Trobajo, and J. R. Garcia, *J. Am. Chem. Soc.*, **129**, 10970 (2007).
17. L. L. Springsteen and E. Matijevic, *Colloid Polym. Sci.*, **267**, 1007 (1989).
18. L. Wang, I. Sondi, and E. Matijevic, *J. Colloid Interface Sci.*, **218**, 545 (1999).
19. I. Sondi and F. Matijevic, *J. Colloid Interface Sci.*, **238**, 208 (2001).
20. J. Rodríguez-Carvajal, Recent Developments of the Program FULLPROF, in *CPD Newsletter 2001*, Vol. 26, p. 12, available at <http://www.iucr.org/iucr-top/news/index.html>. The program and documentation can be obtained from: <http://www.ill.fr/dif/Soft/fp>
21. P. Thompson, D. E. Cox, and J. B. Hastings, *J. Appl. Crystallogr.*, **20**, 79 (1987).
22. C. Delacourt, L. Laffont, R. Bouchet, C. Wurm, J.-B. Leriche, M. Morcrette, J.-M. Tarascon, and C. Masquelier, *J. Electrochem. Soc.*, **152**, A913 (2005).
23. C. Delacourt, C. Wurm, P. Reale, M. Morcrette, and C. Masquelier, *Solid State Ionics*, **173**, 113 (2004).
24. C. Wurm, Ph.D. Thesis, LRCS Université de Picardie-Jules Verne, Amiens, France (2002).
25. C. Yan, L. Zou, D. Xue, J. Xu, and M. Liu, *J. Mater. Sci.*, **43**, 2263 (2008).
26. N. Recham, M. Armand, and J. M. Tarascon, Eur. Pat. 0803233 (2008).
27. M. Doyle, J. Newman, and J. Reimers, *J. Power Sources*, **52**, 211 (1994).