One step synthesis of D-A-D chromophores as active materials for organic solar cells by basic condensation

Victorien Jeux, Olivier Segut, Dora Demeter, Theodulf Rousseau, Magali Allain, Clément Dalinot, Lionel Sanguinet, Philippe Leriche, Jean Roncali

► To cite this version:

Victorien Jeux, Olivier Segut, Dora Demeter, Theodulf Rousseau, Magali Allain, et al.. One step synthesis of D-A-D chromophores as active materials for organic solar cells by basic condensation. *Dyes and Pigments*, 2015, 113, pp.402-408. 10.1016/j.dyepig.2014.09.012 . hal-01390934

HAL Id: hal-01390934

<https://hal.science/hal-01390934>

Submitted on 16 Jun 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Distributed under a Creative Commons Attribution| 4.0 International License

One step synthesis of D-A-D chromophores as active materials for organic solar cells by basic condensation

Victorien Jeux, Olivier Segut, Dora Demeter, Théodulf Rousseau, Magali Allain, Clément Dalinot,
Lionel Sanguinet, Philippe Leriche*, Jean Roncali

MOLTECH - Anjou UMR CNRS 6200, Groupe systèmes conjugués linéaires, University of Angers, 2 boulevard Lavoisier, 49045 Angers, France

Donor-Acceptor-Donor conjugated systems are synthesized in good yield by double condensation of aromatic aldehydes of triarylamine with 2,3-diaminomaleonitrile under microwave activation with trifluoroacetic acid as catalyst. The electronic properties of the compounds are investigated and discussed and a first evaluation of their potential as donor material in organic photovoltaic cells is presented.

1. Introduction

Over the past few years, many molecular conjugated chromophores combining electron donor (D) and acceptor (A) blocks have been designed and synthesized as active materials for organic solar cells (OSC) [1]. In particular solution-processable symmetrical systems D-A-D or A-D-A or even more complex structures such as D-A-D-A-D have attracted particular interest [2,3]. Intensive multi-disciplinary research effort has rapidly generated impressive progresses and power conversion efficiencies (*PCE*) in the range of 8.0–9.0% have been reported for solution-processed bulk heterojunction (BHJ) organic solar cells by combining extended chromophores of advanced structures with soluble derivatives of C₇₀ fullerene and specific additives [3].

However, such highly efficient molecules generally combine complex structure, high molecular weight and multi-step syntheses with limited overall yield. Recently several papers have discussed the key issues regarding the future industrial production of OSCs and underlined the necessity to limit the overall economic cost and environmental impact of the synthesis of

active materials while taking care of the possibility of up-scaling the syntheses [4].

Some recent works have demonstrated the possibility of synthesizing D-A or D-A-D systems by means of more environmental friendly methods such as click chemistry [5] or basic condensations [6]. Additionally, the two-fold condensation of aromatic aldehydes onto commercial (Z)-2,3-diaminomaleonitrile to form D-A-D compounds with a central diiminofumaronitrile electro-deficient group has been scantily studied and most articles have been focused on the optical [7] or aggregative [8] properties of the compounds. A first report on the use of *N,N*-bis[4-(*N,N*-diethylamino)benzylidene]diaminomaleonitrile as active material in a Schottky solar cell has been published some years ago leading to a *PCE* of 0.38% under low intensity illumination [9].

In this context, we report here on D-A-D compounds **P**, **T** and **PT** obtained by condensation of mono-formyl triarylamine with 2,3-diaminomaleonitrile (Fig. 1). The optimization of the synthesis of the target compounds is presented and their electronic properties characterized by spectroscopic and electrochemical techniques with the aid of theoretical calculations are discussed in terms of structure–property relationships. If such D-A-D compounds may be useful for several kinds of applications (mainly 2 photon absorption, dyes and solar cells), we first focused on the evaluation of their potentialities as donor material in basic planar heterojunction solar cells.

* Corresponding author. Tel.: +33 241735010.
E-mail address: philippe.leriche@univ-angers.fr (P. Leriche).

Fig. 1. Structures of the target compounds.

2. Experimental

2.1. General

Solvents were purified and dried using standard protocols. ^1H NMR and ^{13}C NMR spectra were recorded on a Bruker AVANCE DRX 300 spectrometer; chemical shifts are given in ppm (relative to tetramethylsilane) and coupling constants (J) in Hz. MALDI-TOF experiments were carried out on a Bruker Biflex-III with N_2 laser (337 nm) as irradiation source with dithranol in CH_2Cl_2 as matrix. High resolution mass spectra were recorded under FAB mode on a Jeol JMS 700 spectrometer. UV-visible optical data were recorded with a Perkin-Elmer lambda 950 spectrophotometer. Thermal analyses were performed using a DSC 2010 CE (TA Instruments). For cyclic voltammetry (scan rate 100 mV s^{-1}), the electrochemical apparatus consisted of a potentiostat Biologic SP 150 driven by EC-lab software and of a standard three-electrode cell. As the working and counter electrodes, a platinum foil and a platinum wire were used, respectively, while an SCE electrode was used as a reference.

2.2. Devices preparation and characterization

Fullerene C_{60} (99+%) was purchased from Merck and used as received. The Baytron suspension used to apply smoothing and hole conducting/injecting layers was purchased as "Baytron P PE FL" (HC Stark). All thin film devices were prepared in laboratory conditions. As electrodes, ITO coated glasses ($20 \Omega/\square$, Solem) and evaporated Al films (ca. 150 nm thickness) were used. The ITO electrodes were cleaned in ultrasonic baths, subjected to an UV-ozone treatment (15 min), and then modified by a spin-casted layer of Baytron (40 nm thickness), which was dried at 115°C during 30 min. The Baytron suspension was filtered through a $0.45 \mu\text{m}$ membrane

Scheme 1. Synthetic routes to compounds **3** and **P**. a) ethanol reflux; b) toluene reflux with Dean-Stark; c) toluene, P_2O_5 , microwave activation, 110°C , 250 mW, 6 bar; d) toluene, TFA, microwave activation, 110°C , 250 mW, 6 bar.

(Minisart RC 15, Sartorius) just prior to casting. The donor layer was spin-casted from chloroform solutions of the compound (5 mg L^{-1}) onto ITO slides initially pre-coated with a 40 nm PEDOT-PSS layer. Then, a layer of C_{60} (30 nm) was deposited by thermal evaporation under high vacuum. A 150 nm thick layer of Al was finally thermally evaporated through a shadow mask, at a pressure of about 10^{-6} mbar. The mask geometry defined a device's area of 0.28 cm^2 . Each ITO coated glass supports two individual devices. Different "sets" of devices, using the same batch and solution and whereon Al was evaporated simultaneously, were prepared. For each experiment, a minimum of 16 OSC (8 devices containing 2 cells of 0.28 cm^2 active area) were characterized. All devices were thermally treated. A sacrificed cell was first heated for 5 min at 80°C after what temperature was increased by increments of 10°C until PCE decreases. Then, the other cells were directly heated at the optimized temperature during 5 min.

After preparation, the devices were stored and characterized in an argon glovebox (200B, MBraun). The $J-V$ curves of the devices were recorded in the dark and under illumination using a Keithley 236 source-measure unit and a home-made acquisition program. The light source was an AM 1.5 Solar Constant 575 PV simulator (Steuernagel Lichttechnik, equipped with a metal halogenide lamp). The light intensity was measured by a broad-band power meter (13PEM001, Melles Griot). The devices were illuminated through the ITO electrode side. The efficiency values reported here are not corrected, for possible solar simulator spectral mismatch nor for the reflection/absorbance of the glass/ITO/Baytron coated electrodes.

2.3. Synthesis

2.3.1. 2-amino-3-((E)-(4-(bis(4-methoxyphenyl)amino)benzylidene)amino)maleonitrile – 3

The 4-(bis(4-methoxyphenyl)amino)benzaldehyde [10] (0.1 g, 0.3 mmol) is dissolved in ethanol and 2,3-diaminomaleonitrile (35 mg, 0.32 mmol) is added. The solution is refluxed for 2 h and then, the mixture is cooled at room temperature. An orange solid is filtered off, and is washed with water and ethanol to afford the target compound (0.125 g, 98%). Monocrystals are obtained by slow evaporation of ethyl acetate. M.p.: 167–172 °C; ^1H NMR (300 MHz, CDCl_3): 8.27 (s, 1H), 7.58 (d, 2H, $J = 8.7$ Hz), 7.12 (d, 4H, $J = 9$ Hz), 6.88 (d, 4H, $J = 9$ Hz), 6.84 (d, 2H, $J = 8.7$ Hz), 4.95 (s, 2H), 3.82 (s, 6H); ^{13}C NMR (125 MHz, CDCl_3): 158.5, 157.1, 152.6, 139, 130.6, 127.8, 125.7, 122.3, 117.7, 114.9, 114.1, 112.6, 109.7, 55.5; IR (neat): $\nu = 2208$, 2229 cm^{-1} ($\text{C}\equiv\text{N}$), 3304, 3410 (N–H); X-Ray structure: Triclinic, P $\bar{1}$ (CCDC 1015083, details see below).

2.3.2. 2,3-bis((E)-(4-(bis(4-methoxyphenyl)amino)benzylidene)amino)fumaronitrile – P

Route B: 4-(bis(4-methoxyphenyl)amino)benzaldehyde (120 mg, 0.36 mmol) and 2,3-diaminomaleonitrile (18 mg, 0.17 mmol) are dissolved in benzene (20 mL) and several drops of piperidine are added. The solution is vigorously stirred for 30 min and then heated to reflux with a Dean–Stark apparatus during 5 days. The reaction mixture is cooled to room temperature, diluted with CH_2Cl_2 , and washed with a saturated solution of NaHCO_3 ,

water and brine. After removal of solvent the residue is purified by column chromatography on silica gel using methylene chloride as eluent to afford a purple solid (30 mg, 24%).

Route D: 4-(bis(4-methoxyphenyl)amino)benzaldehyde (90 mg, 0.27 mmol) and 2,3-diaminomaleonitrile (14 mg, 0.13 mmol) are dissolved in toluene (5 mL) in a 10-mL vial. Then trifluoroacetic acid is added (30 μL) and the vial is sealed with a crimp cap and placed in the microwave cavity (CEM Discover). After irradiation at 250 W, 110 °C, (6 bar) during 60 min and subsequent cooling, the reaction mixture is then diluted with CH_2Cl_2 , washed with a saturated solution of NaHCO_3 , water and brine. After removal of solvent, the residue is chromatographed on silica gel using methylene chloride as eluent to afford a purple solid (77 mg, 80%).

Monocrystals are obtained by slow evaporation of chloroform. M.p.: 174–178 °C; $\text{RMN-}^1\text{H}$ (300 MHz, CDCl_3): 8.56 (s, 1H), 7.74 (d, 2H, $J = 8.7$ Hz), 7.13 ppm (d, 4H, $J = 8.7$ Hz), 6.88 ppm (m, 6H), 3.82 (s, 6H); $\text{RMN-}^{13}\text{C}$ (125 MHz, CDCl_3): 162.5, 157.3, 153.3, 138.7, 131.8, 130.5, 127.9, 125.8, 117.5, 115, 111.5, 55.5; IR (neat): $\nu = 2210$ cm^{-1} ($\text{C}\equiv\text{N}$); Elemental analysis: calculated for $\text{C}_{46}\text{H}_{38}\text{N}_6\text{O}_4$: C, 74.78; H, 5.18; N, 11.31; found: C, 74.72; H, 5.21; N, 11.31; X-Ray structure: Orthorhombic, P 21 21 21 (CCDC 1015081, see below).

2.3.3. 2,3-bis((E)-(5-(bis(4-methoxyphenyl)amino)thiophen-2-yl)methylene)amino)fumaronitrile – T

5-(bis(4-methoxyphenyl)amino)thiophene-2-carbaldehyde [11] (70 mg, 0.21 mmol) and 2,3-diaminomaleonitrile (11 mg, 0.1 mmol) are dissolved in toluene (5 mL) in a 10-mL vial. Then trifluoroacetic

Fig. 2. ORTEP view of **3** (top) and **P** (bottom).

Fig. 4. UV-Vis Absorption spectra of the target compounds in CH_2Cl_2 . **P** (blue), **T** (green) and **PT** (red). (For interpretation of the references to colour in this figure legend, the reader is referred to the web version of this article.)

to 5-(bis(4-methoxyphenyl)amino)thiophene-2-carbaldehyde **4** [11] and 5-(4-(bis(4-methoxyphenyl)amino)phenyl) thiophene-2-carbaldehyde **5** [12] led to compounds **T** and **PT** in 16 and 11% yield respectively.

The difficulty to achieve the second condensation reaction prompted us to study the crystallographic structure of compounds **3** and **P**. After slow evaporation from chloroform solution,

Fig. 5. CV traces of **P** (top), **T** (middle) and **PT** (bottom) in 0.10 M $\text{TBAPF}_6/\text{CH}_2\text{Cl}_2$ scan rate 100 mV/s.

compound **P** crystallizes in an orthorhombic $\text{P}2_12_12_1$ space group (Fig. 2, bottom). Evaporation from an ethyl acetate solution leads to crystallisation in a $\text{P}-1$ triclinic space group with two independent molecules **3a** and **3b** by unit (Fig. 2, top). The crystallographic structures of the compounds show the typical geometry of TPA (for more details see ESI). For compound **3**, the double bond linking the two cyano groups presents the *Z* configuration of the starting 2,3-diaminomaleonitrile. In contrast for compound **P**, this bond is isomerized into an *E* configuration in agreement with previous X-ray data of parent systems.

This *Z/E* isomerization from **3** to **P** could contribute to explain the low yield of the second condensation reaction. The main conjugated system of compound **P** presents a strong quinodimethanic character from the lateral triarylated nitrogen atom to the central cyano group. For example, the lengths of C19–C20 1.366 Å and C16–C17 1.372 Å in the aromatic spacer and the C22–N2 central single bond (1.379 Å) appear particularly short (Fig. 3). For compound **3**, this quinodimethanic character is also present but less marked due to the presence of an internal charge transfer between the lateral amino and central cyano groups.

Thus, compared to those of **P**, bond lengths of **3** (in red on Fig. 3) show significant lengthening for double and triple bonds and notable shortening for single ones. This observation suggests the existence of a strong ICT between nitrogen atoms N5 and N10 and the C23–N3 and C48–N8 cyano groups respectively. This assumption is corroborated by the sp^2 geometry of N5 and N10 shown by the localization (determined from their electronic densities) of hydrogen atoms H5a-b and H10a-b in the same plane as the conjugated system. This observation may explain the lack of reactivity of compound **3** in which the terminal doublet on nitrogen looses a part of its nucleophile properties.

Whereas the low nucleophilicity of the nitrogen is probably a limiting factor, the required *Z/E* isomerization of the central double bond represents a major obstacle to the efficiency of the bis-condensation. This isomerization must occur during the second condensation step since the *Z* isomer of **P** has never been observed. Thus, in the next experiment, the catalytic amount of basic piperidine was replaced by dehydrating and acidic phosphorus oxide. While P_2O_5 does not improve the yield of condensation under atmospheric conditions, its association with microwave activation [17] strongly accelerates the reaction allowing the formation of **P** in 40% yield (route c, Scheme 1). After several attempts with other acids associated with microwave activation, it was found that small amounts of trifluoroacetic acid provides the best results (route d, Scheme 1). Under these conditions, 2 eq. of aldehyde **2** with 1 eq. of **1** gives compound **P** in ca 80% yield. On the other hand, a similar yield of **P** is obtained by reaction of stoichiometric quantities of **3**

Fig. 6. HOMO and LUMO energetic levels for **P**.

Table 2

Photovoltaic characteristics of OSC before and^a after 5 min annealing at 120 °C,^b after 5 min annealing at 110 °C.

Cpnd	V_{oc} (V)	J_{sc} (mA cm ⁻²)	FF (%)	PCE (%)
P	0.73	2.49	35	0.70
P^a	0.84	3.65	35	1.18
T	0.47	2.20	47	0.53
T^b	0.52	4.28	36	0.89

and **2**. Application of these optimized conditions to aldehydes **4** and **5** leads in every case to a large improvement of the reaction yield and the target compounds **T** and **PT** are obtained in 68 and 60% yield respectively.

3.2. Electronic properties of the donors

Table 1 lists the results of UV–Vis absorption spectroscopy and cyclic voltammetry for the three target compounds. The absorption spectrum of all compounds presents a first series of bands between 280 and 420 nm followed by an intense band in the 450–750 nm region assigned to an internal charge-transfer (Fig. 4). The replacement of a phenyl ring by a thienyl unit from **P** to **T** leads to a large red shift (61 nm) of the absorption maximum λ_{max} , and hence to a decrease of the optical bandgap. However, the extension of the conjugated system from **T** to **PT** produces only a small red shift of λ_{max} (3 nm).

The cyclic voltammogram of the three compounds presents two one-electron reversible oxidation processes followed by an irreversible wave (Table 1, Fig. 5). As expected the potential of the two first oxidation processes decreases from **P** to **T** due to the lower aromaticity of thiophene. The extension of the conjugation length in **PT** leads to the coalescence of the two one-electron processes at a less positive potential. For all compounds, the CV present an irreversible reduction peak in the –1.00 to –1.30 V region.

Ab initio theoretical calculations were performed using Gaussian 09 (DFT-B3LYP/6-31g (d, p)). In agreement with the crystal structure of **P**, the optimized geometries of compounds all exhibit shortening of single bonds and lengthening of double bonds of the conjugated system from the lateral triarylated nitrogen atom to the central cyano group, characteristic of internal charge transfer.

Fig. 7. Current density vs voltage curve for the bilayer planar heterojunction cell **P/C60** in obscurity (black) and under white illumination at a power of 90 mW cm⁻² before (grey) and after (violet) annealing. (For interpretation of the references to colour in this figure legend, the reader is referred to the web version of this article.)

Whereas compounds **P** and **T** appear nearly planar, steric interactions between phenyl and thiophene rings of **PT** produces a dihedral angle of 19° (see ESI). This twist angle which limits electron delocalization could explain the very small red shift observed between **T** and **PT** as well as the coalescence of oxidation processes.

The HOMO is delocalized on the whole molecule with smaller coefficients on the central acceptor part while the LUMO is essentially localized on the electron-withdrawing part and vicinal spacer (Fig. 6 and ESI). The calculated HOMO and LUMO levels are consistent with optical and electrochemical results.

3.3. Evaluation of the new donor molecules in organic solar cells

The thermal stabilities of the target compounds were investigated by differential scanning calorimetry and thermogravimetry. They all exhibit reasonable thermal stabilities with melting and decomposition points up to 150 °C and 200 °C respectively (Table 1). Compounds **P**, **T** and **PT** have been evaluated as donor material in PHJ solar cells ITO/PEDOT-PSS/**donor**/C₆₀/Al (see SI). The open-circuit voltage (V_{oc}), short-circuit current densities (J_{sc}), fill factor (FF) and power conversion efficiencies (PCE) of cells of 0.28 cm² active area were determined under AM 1.5 simulation solar illumination (Table 2).

Compound **PT** did not lead to devices of quality sufficient for evaluation. As-fabricated devices obtained from **P** and **T** respectively gave PCE of 0.70 and 0.53%. Both devices show similar J_{sc} associated with V_{oc} related on relative oxidation potentials. Thus, compound **P**, which presents a 1st oxidation potential 160 mV anodically shifted relatively to **T**, leads to a higher V_{oc} of 0.73 V. In each case thermal annealing improves the photovoltaic performances due to a slight increase of V_{oc} and J_{sc} . Thus, PCE of the device based on **T** increases from 0.53 to 0.89% upon thermal treatment. The highest value of 1.18% was obtained with **P** after annealing at 120 °C, with V_{oc} of 0.84 V and a J_{sc} of 3.65 mA cm⁻² (Fig. 7).

4. Conclusion

To summarize, three new D-A-D molecular systems based on a central diiminofumaronitrile acceptor group substituted by two diarylamine side blocks have been synthesized.

The optimization of the reaction by association of microwave activation and trifluoroacetic acidic catalysis improves the reproducibility of the synthesis and increases the yield from 10–15 to 65–80%. Preliminary results obtained on bilayer heterojunction solar cells gave efficiencies higher than 1.0% which suggests that the diiminomaleonitrile **1** block may represent an interesting synthon for the synthesis of functional molecular or polymeric conjugated systems for several kind of applications including OSC.

Acknowledgements

Victorien Jeux Thanks the French minister of research for financial support. Clément Dalinot thanks the University of Angers for granting. Authors thank the Johnson Matthey Company for their generous providing of palladium salts (necessary for the syntheses of starting aldehydes).

Appendix A. Supplementary data

Supplementary data related to this article can be found at <http://dx.doi.org/10.1016/j.dyepig.2014.09.012>.

References

- [1] Roncali J, Blanchard P, Leriche P. Molecular materials for organic photovoltaics: small is beautiful. *Adv Mater* 2014;26:3821–38; Lin Y, Li Y, Zhan X. Small molecule semiconductors for high-efficiency organic photovoltaics. *Chem Soc Rev* 2012;41:4245–72.
- [2] Walker B, Tamayo AB, Dang XD, Zalar P, Seo JH, Garcia A, et al. Nanoscale phase separation and high photovoltaic efficiency in solution-processed small molecule bulk heterojunction solar cells. *Adv Funct Mater* 2009;19:3063–9; Ripaud E, Demeter D, Rousseau T, Boucard-Cétol E, Allain M, Po R, et al. Structure–properties relationships in conjugated molecules based on diketopyrrolopyrrole for organic photovoltaics. *Dyes Pigments* 2012;95:126–33; Kim Y, Song CE, Cho A, Kim J, Eom Y, Ahn J, et al. Synthesis of diketopyrrolopyrrole (DPP)-based small molecule donors containing thiophene or furan for photovoltaic application. *Mat Chem Phys* 2014;143:825–9; Mei J, Graham KR, Stalder R, Reynolds JR. Synthesis of isoindigo-based oligothiophenes for molecular bulk heterojunction solar cells. *Org Lett* 2010;12:660–3; Yassin A, Leriche P, Allain M, Roncali J. Donor–acceptor–donor (D–A–D) molecules based on isoindigo as active material for organic solar cells. *New J Chem* 2013;37:502–7; Rousseau T, Cravino A, Bura T, Ulrich G, Ziesel R, Roncali J. Bodipy derivatives as donor materials for bulk heterojunction solar cells. *Chem Commun* 2009:1673–5; Rousseau T, Cravino A, Ripaud E, Leriche P, Rihn S, De Nicola A, et al. A tailored hybrid bodipy-oligothiophene donor for molecular bulk heterojunction solar cells with improved performances. *Chem Commun* 2010:5082–4.
- [3] Sun Y, Welch GC, Leong WL, Takacs CJ, Bazan G, Heeger AJ. Solution-processed small-molecule solar cells with 6.7% efficiency. *Nat Mater* 2011;11:44–8; Coughlin JE, Henson ZB, Welch GC, Bazan G. Design and synthesis of molecular donors for solution-processed high-efficiency organic solar cells. *Acc Chem Res* 2014;47:257–70; Zhou J, Zuo Y, Wan X, Long G, Zhang Q, Ni W, et al. Solution-processed and high-performance organic solar cells using small molecules with a benzodithiophene unit. *J Am Chem Soc* 2013;135:8484–7; Chen Y, Wan X, Long G. High performance photovoltaic applications using solution-processed small molecules. *Acc Chem Res* 2013;46:2645–55; Shen S, Jiang P, He C, Zhang J, Shen P, Zhang Y, et al. Solution-processable organic molecule photovoltaic materials with bithienyl-benzodithiophene central unit and indenedione end groups. *Chem Mater* 2013;25:2274–81.
- [4] Jorgensen M, Carlé JE, Sondergaard RR, Lauritzen M, Dagnaes-Hansen NA, Byskov SL, et al. The state of organic solar cells—a meta analysis. *Sol En Mater Sol Cells* 2013;119:84–93; Po R, Bernardi A, Calabrese A, Carbonera C, Corso G, Pellegrino A. The role of buffer layers in polymer solar cells. *Energy Environ Sci* 2014;4:285–310; Krebs FC, Jorgensen M. Polymer and organic solar cells viewed as thin film technologies: what it will take for them to become a success outside academia. *En Mater Sol Cells* 2013;119:73–6; Anctil A, Babbitt CW, Raffaele RP, Landi BJ. Cumulative energy demand for small molecule and polymer photovoltaics. *Prog Photovolt Res Appl* 2013;21:1541–54.
- [5] Leliege A, Blanchard P, Rousseau T, Roncali J. Triphenylamine/tetracyanobutadiene-based DAD pi-conjugated systems as molecular donors for organic solar cells. *Org Lett* 2011;12:3098–101.
- [6] Moussallem C, Allain M, Gohier F, Frère P. Synthesis, electronic properties and packing modes of conjugated systems based on 2,5-di(cyanovinyl)furan or thiophene and imino-perfluorophenyl moieties. *New J Chem* 2013;37:409–15; Moussallem C, Segut O, Gohier F, Allain M, Frère P. Facile access via Green procedures to a material with the benzodifuran moiety for organic photovoltaics. *Sus Chem Eng* 2014;2(4):1043–8; Demeter D, Mohamed S, Diac A, Grosu I, Roncali J. Small molecular donors for organic solar cells obtained by simple and clean synthesis. *ChemSusChem* 2014;7(4):1046–50.
- [7] Lu Y, Hasegawa F, Goto T, Ohkuma S, Fukuhara S, Kawazu Y, et al. Highly sensitive two-photon chromophores applied to three-dimensional lithographic microfabrication: design, synthesis and characterization towards two-photon absorption cross section. *J Mater Chem* 2004;4:75–80; Shirai K, Matsuoka M, Fukunishi K. New syntheses and solid state fluorescence of azomethine dyes derived from diaminomaleonitrile and 2,5-diamino-3,6-dicyanopyrazine. *Dyes Pigments* 2000;47:107–15.
- [8] Kinashi K, Lee KP, Matsumoto S, Ishida K, Ueda Y. Alkyl substituent effects on J- or H-aggregate formation of bisazomethine dyes. *Dyes Pigments* 2012;92:783–8; Kim BS, Kashibuchi D, Son YA, Kim SH, Matsumoto S. Effect of phenyl ring substitution on J-aggregate formation ability of novel bisazomethine dyes in vapour-deposited films. *Dyes Pigments* 2011;90:56–64; Tanaka T, Matsumoto S, Kobayashi T, Soatoh M, Aoyama TJ. Highly oriented J-aggregates of bisazomethine dye on aligned poly(tetrafluoroethylene) surfaces. *Phys Chem C* 2011;115:19598–605.
- [9] Hosokai T, Aoyama T, Kobayashi T, Nakao A, Matsumoto S. Photovoltaic properties of bisazomethine dye thin films. *Chem Phys Lett* 2010;487:77–80.
- [10] He Z, Kan CW, Ho CL, Wong WY, Chui CH, Tong KL, et al. Light-emitting dyes derived from bifunctional chromophores of diarylamine and oxadiazole: synthesis, crystal structure, photophysics and electroluminescence. *Dyes Pigments* 2011;88:333–43.
- [11] Davies JA, Elangovan A, Sullivan PA, Olbricht BC, Bale DH, Ewy TR, et al. Rational enhancement of second-order nonlinearity: bis-(4-methoxyphenyl) hetero-aryl-amino donor-based chromophores: design, synthesis, and electrooptic activity. *J Am Chem Soc* 2008;130:10565–75.
- [12] Yu QY, Liao JY, Zhou SM, Shen Y, Liu JM, Kuang DB, et al. Effect of hydrocarbon chain length of disubstituted triphenyl-amine-based organic dyes on dye-sensitized solar cells. *J Phys Chem C* 2011;115:22002–8.
- [13] Robertson PS, Vaughan J. Derivatives of the hydrogen cyanide tetramer: structure and chemistry. *J Am Chem Soc* 1958;80:2691–3; Nesterov VV, Antipin MY, Nesterov VN, Moore CE, Cardelino BH, Timofeeva TV. Thermally stable heterocyclic imines as new potential nonlinear optical materials. *J Phys Chem B* 2004;108:8531–9.
- [14] Rivera A, Rios-Motta J, Leon F. Revisiting the reaction between diaminomaleonitrile and aromatic aldehydes: a green chemistry approach. *Molecules* 2006;11:858–66.
- [15] Lin CW, Chou PT, Liao YH, Lin YC, Chen CT, Chen YC, et al. Photoisomerization of a maleonitrile-type Salen Schiff base and its application in fine-tuning infinite coordination polymers. *Chem Eur J* 2010;16:3770–82.
- [16] Kim SH, Yoon SH, Kim SH, Han EM. Red electroluminescent azomethine dyes derived from diaminomaleonitrile. *Dyes Pigments* 2005;64:45–8.
- [17] Experiments were conducted with a CEM « Discover » machine