Thermal stability study of NiAl_2O_4 binders for Chemical Looping Combustion application

Lucia Blas, Patrick Dutournié, Sophie Dorge, Ludovic Josien, Damaris Kehrli, Arnold Lambert

► To cite this version:

Lucia Blas, Patrick Dutournié, Sophie Dorge, Ludovic Josien, Damaris Kehrli, et al.. Thermal stability study of NiAl_2O_4 binders for Chemical Looping Combustion application. *Fuel*, 2016, 182, pp.50-56. 10.1016/j.fuel.2016.05.080 . hal-01398800

HAL Id: hal-01398800

<https://hal.science/hal-01398800>

Submitted on 2 Feb 2017

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Thermal stability study of NiAl₂O₄ binders for Chemical Looping Combustion application

Lucia Blas^{a,*}, Patrick Dutournié^b, Sophie Dorge^c, Ludovic Josien^b, Damaris Kehrli^c, Arnold Lambert^d

^a NS3E, ISL-CNRS-UNISTRA (Nanomatériaux pour les Systèmes Sous Sollicitations

Extrêmes) UMR 3208, French-German Research Institute of Saint-Louis

5, rue du Général Cassagnou, BP 70034, 68301 St Louis, France.

*Corresponding author: luciablas@gmail.com,

phone: +33 3 89 69 56 72; fax: +33 3 89 69 50 74

^b Institut de Science des Matériaux de Mulhouse (IS2M), UMR 7361 CNRS-Université de

Haute-Alsace (UHA), 3 bis, rue Alfred Werner, 68093 Mulhouse, France

patrick.dutournie@uha.fr, phone: +33 3 89 33 67 52;

ludovic.josien@uha.fr, phone: +33 3 89 33 68 21;

^c Laboratoire Gestion des Risques et Environnement, UHA,

3 bis, rue Alfred Werner, 68093 Mulhouse, France.

sophie.dorge@uha.fr, phone: +33 3 89 33 61 59;

damaris.kehrli@uha.fr, phone: +33 3 89 33 61 68;

^d IFP Energies nouvelles, Rond-point de l'échangeur de Solaize, BP 3, 69360 Solaize, France

arnold.lambert@ifpen.fr, phone: +33 4 37 70 29 30;

Abstract

The influence of the preparation method of NiAl₂O₄ binders on their thermal stability was studied. For this purpose, the reactivity of two different NiAl₂O₄ binders with CO as fuel was studied in a fixed bed reactor device. Successive oxidation-reduction cycles were performed

on the two binders to study their reactivity with the fuel and their structural modifications as cycles proceed. Results reveal that binders are not inert in reducing atmosphere; they both react with the fuel to produce CO_2 . The total reduction capacity (TRC) of the first binder (B1, synthesized by pyrolytic pulverization) increases during the first cycles and levels off after 20 cycles. However, the TRC of the second binder (B2, synthesized by calcination of a mixture of $\text{Ni}(\text{OH})$ and $\gamma\text{-Al}_2\text{O}_3$), increases progressively and reaches a maximum after 80 cycles. The growing amount of available oxygen in the binders leads both binders to structural modifications. X-Ray Diffraction studies performed on fresh and aged binders presented a shift of the peaks related to NiAl_2O_4 . Moreover, quantitative X-Ray Diffraction studies and Temperature Programmed Reduction measurements were performed in order to quantify the NiO present in each binder before and after oxidation-reduction cycles. These experiments revealed the presence of NiO in fresh binders due to the preparation method, and an increase of this amount after oxidation-reduction cycles. Therefore, NiAl_2O_4 in the binder is progressively decomposed producing NiO and Al_2O_3 . Finally, the decomposition of the binder NiAl_2O_4 as cycles proceed was also observed in studies performed on the oxygen carrier NiO/ NiAl_2O_4 . This work showed that the binder reacts with the fuel and therefore it can contribute to the modification of the oxygen carrier reactivity.

Keywords: Oxygen Carrier, NiAl_2O_4 binder, X-Ray Diffraction, Standard Addition Method,

Temperature Programmed Reduction

1. Introduction

To limit the increase of greenhouse gas emissions and stabilize climate at safe levels, CO_2 capture and sequestration technologies are nowadays being studied and developed [1]. Among these, Chemical Looping Combustion (CLC) has been suggested as an interesting alternative to conventional combustion to produce energy with inherent CO_2 capture [2-3]. CLC consists

of an indirect combustion, where the oxygen needed for fuel oxidation is provided by a solid oxygen carrier. During this process, the fuel is first oxidized by the oxygen carrier and the latter is afterwards regenerated (re-oxidized) by air [4]. The most common CLC device consists of two interconnected fluidized beds (“combustion” and “regeneration” reactors) with a circulation of the solid oxygen carrier. However Noorman *et al.* [5-6] also proposed the possibility of working in a packed bed reactor where the oxygen carrier remains static and the different oxidation/reduction gas mixtures are alternatively injected. Gases produced in the combustion reactor are primarily CO₂ and H₂O. Thus, after water condensation, pure CO₂ is obtained and it can be directly stored or used. Outlet gases from the regeneration step (depleted air) can be directly emitted to the atmosphere. In conclusion, power generation by CLC technology does not require an energy intensive gas separation of CO₂ from exhaust gases, which is the most expensive step of CO₂ capture and sequestration.

Finding suitable oxygen carriers with sufficient reactivity, good mechanical properties and stability is strategic to increase the efficiency of CLC processes. Oxygen carriers are generally

composed of an active phase (generally a metal oxide based on Ni, Fe, Cu, Mn or Co) and a porous binder (Al₂O₃, NiAl₂O₄, SiO₂, TiO₂, yttrium-stabilized zirconia...), which provides higher surface area for reaction, mechanical strength and attrition resistance [7-8]. The final properties of the oxygen carrier (reactivity, mechanical strength, thermal and chemical stability...) depend mainly on the metal oxide used, but also on the binder, as well as the preparation method. Several methods have been studied in the literature and can be classified in three groups:

- Mixing of metal oxide and binder powders (mechanical mixing [9-10], freeze granulation [11-12], spray drying [13-14], spin flash [15-16]...).
- Preparation by precipitation (co-precipitation [17-18], sol-gel [19-20]...).
- Preparation by impregnation (wet and incipient wetness impregnation...) [21-22].

The Freeze granulation is the most common preparation method at laboratory scale. However, only spray drying, spin flash and impregnation methods can be used at large scale for industrial production.

Numerous materials based on Ni, Fe, Cu, Mn and Co oxides have been studied and tested as oxygen carriers for CLC, at different working scales (laboratory and pilot scale) [7-10]; [17]; [21-35]. Among all these candidates, NiO/NiAl₂O₄ oxygen carrier is considered as a model oxygen carrier, due to its high reactivity and its good thermal stability. Indeed, it can work at high temperatures (900-1100°C) owing to the high melting points of NiO and metallic Ni [7], [9], [17], [23]. For these reasons Ni-based oxygen carriers are widely studied at laboratory scale, however their use should be minimized at industrial scale due to the high toxicity of this metal and health/safety issues.

Among all the possible metal oxide/binder combinations, some authors studied the use of γ -Al₂O₃ as a binder for NiO, but they observed that at high operating temperatures (> 800°C) the binder reacts with NiO to form NiAl₂O₄ [17], [36], [37]. NiAl₂O₄ is less reactive with fuel for CLC operations, although it can be partially reduced by the fuel[38]. Thus, the formation of NiAl₂O₄ reduces the amount of NiO able to deliver oxygen for combustion and so, the global performance of the oxygen carrier. To avoid the decrease of reactivity due to NiAl₂O₄ formation, Cho *et al.* [39] studied adding nickel in excess to get enough free NiO inside the particle and compensate for the loss of “reactive” nickel species. They showed that the initial NiO content must be very high (around 80 wt. %) to obtain a NiO free content of 60 wt. %. Gayán *et al.* [7] demonstrated that the formation of the spinel NiAl₂O₄ depends on the crystalline nature of the binder. They proposed to use a thermal treatment (at 1150°C) to perform the phase transformation of γ -Al₂O₃ to α -Al₂O₃, in order to improve binder thermal stability. Results showed that the use of α -Al₂O₃ partially reduced the formation of NiAl₂O₄.

Furthermore, Jin *et al.* [40] suggested to use NiAl_2O_4 directly as a binder instead of Al_2O_3 . Afterwards, several authors studied the performances of the oxygen carrier $\text{NiO}/\text{NiAl}_2\text{O}_4$ and they generally observed high reactivity towards oxidation of different fuels (CH_4 , syngas...) and high stability. The reactivity of Al_2O_3 (used as binder) with NiO to form NiAl_2O_4 was studied by Adánez *et al.* [41] and Dueso *et al.* [36], [42]. Adánez *et al.* [41] studied methane combustion (30 vol. % in N_2) in a CLC plant of 500 Wth during 100 hours. The oxygen carrier used for this study was composed of 18 wt. % of NiO and 82 wt. % of $\alpha\text{-Al}_2\text{O}_3$. They observed that $\alpha\text{-Al}_2\text{O}_3$ reacted partially with NiO at high temperature to produce NiAl_2O_4 . Moreover, their results revealed that both phases (NiO and produced NiAl_2O_4) could react with the fuel. Therefore, NiAl_2O_4 (used as binder or produced by reaction between NiO and the binder Al_2O_3) cannot be considered as an inert material in CLC processes: it is an additional source of oxygen for combustion [43]. The experiments also showed that the relative amount of free NiO in the oxygen carrier (after metal oxide NiO and binder Al_2O_3 reaction) depends on the oxygen carrier/fuel ratio (ϕ). Therefore, the production of NiAl_2O_4 decreased when ϕ decreased. Dueso *et al.* [36] performed thermogravimetric analyses simulating oxidation/reduction cycles with the same oxygen carrier ($\text{NiO}/\alpha\text{-Al}_2\text{O}_3$) and CH_4 as fuel. They observed that the produced NiAl_2O_4 was less reactive than NiO . Furthermore, there was a direct relation between oxygen carrier conversion during the reduction step and the proportion of free NiO and NiAl_2O_4 present in the oxygen carrier after re-oxidation. 80% of nickel reduced in the previous cycle was reoxidized into free NiO while the rest was reoxidised into NiAl_2O_4 (fresh oxygen carrier composition: 18 wt. NiO , 82 wt. % Al_2O_3 ; final composition: 14.4 wt. % NiO , 77 wt. % Al_2O_3 and 8.6 wt. % NiAl_2O_4). However, these authors have not studied the reactivity of the binder NiAl_2O_4 alone.

The stability of the nickel aluminate binder used in CLC is a very important parameter to ensure good mechanical strength of the oxygen carrier, and so, limit particles agglomeration

and fragmentation which could [damage](#) the CLC process. In previous work [43], we studied the reactivity of the NiAl_2O_4 binder by performing oxidation/reduction cycles in a fixed bed reactor with CO as fuel. The major observation was that the binder underwent a structural modification, which modified its reactivity. X-Ray Diffraction analyses showed that peaks
5 related to NiAl_2O_4 were enlarged and shifted to wide diffraction angles. These results were explained by the gradual decomposition of NiAl_2O_4 to produce NiO and $\gamma\text{-Al}_2\text{O}_3$.

The [purpose](#) of the present work is to study the influence of the preparation method on the reactivity and stability of the binder NiAl_2O_4 and to quantify the amount of NiO produced by
[decomposition](#) of the NiAl_2O_4 spinel phase during successive reduction/oxidation
10 experiments.

The reactivity of two different binders was studied in a fixed bed reactor with CO as fuel. The evolution of both binders, in terms of reactivity and structural changes, was also investigated by the measurement of the amount of produced CO_2 during successive cycles. The materials were analyzed by X-Ray Diffraction and Temperature Programmed Reduction to quantify the
15 amount of NiO present in both materials before and after oxidation/reduction cycles. Additional tests were performed to compare the evolution of nickel aluminate [in the binders](#)
[and](#) in the oxygen carrier ($\text{NiO/NiAl}_2\text{O}_4$).

2. Experimental section

2.1 Materials

20

Two NiAl_2O_4 binders were studied in this work. Cabot Corp. synthesized the first one (noted as B1) by spray pyrolysis of a mixture of nickel nitrate $\text{Ni}(\text{NO}_3)_2$ and gamma alumina $\gamma\text{-Al}_2\text{O}_3$ (spectral 100). Afterwards the mixture was calcined at 800°C and 1000°C (during 24 hours at each temperature). The material was pelletized by *IFP Energies Nouvelles* (Solaize, France),
25 these pellets were ground and sieved to obtain particle sizes between 125 and $300\text{ }\mu\text{m}$.

The preparation of the second binder (noted as B2) was performed by *IFP Energies Nouvelles* (Solaize, France). A mixture of nickel hydroxide Ni(OH) and gamma alumina $\gamma\text{-Al}_2\text{O}_3$ was calcined at 1200°C during 24 hours. The material was pelletized, ground and sieved to 100 and 300 μm . While calcining binder B1 at 1000°C was enough to obtain nearly pure NiAl_2O_4 , the second preparation method required an increase of the calcination temperature up to 1200°C for most of the nickel oxide to react with alumina and produce NiAl_2O_4 . Despite this very high calcination temperature, some NiO was still unreacted (*vide infra*).

Both binders were characterized by X-Ray Diffraction, analyses were performed in Lindemann tubes with the same quantity of material for each sample. Peak identification was carried out by means of the PDF (Powder Diffraction File) database.

An oxygen carrier NiO/ NiAl_2O_4 was also studied in this work. The composition of the oxygen carrier was 60 wt. % metallic oxide (NiO) and 40 wt. % of binder (NiAl_2O_4) and it was supplied by *IFP Energies nouvelles* (Solaize, France). The particles were first produced by granulation in a Guedu granulator and then calcined at 1200°C for 2 hours under air flow.

Only particles in the range between 100 and 300 μm were used in this study.

2.2 Experimental set-up

Several oxidation-reduction cycles were performed on all materials in a fixed bed reactor device described in previous work [44], [45]. The binder was placed in a quartz reactor with an inner diameter of 6 mm. The mass introduced (around 0.2 g) was estimated to have a bed height of around 5 mm. The reactor was heated by a tubular furnace (Pekly/Herrmann-Moritz), and the operating temperature was measured by two thermocouples placed above and below the material bed. The fuel used in this study was carbon monoxide ($[\text{CO}] = 0.55 \text{ vol. \%}$ in N_2), and the regeneration step was carried out under air. All gas flow rates were controlled and maintained constant at 50 NL h^{-1} by four mass flow controllers (BROOKS 5850). The

gases concentrations (CO and CO₂) at the outlet of the reactor were continuously measured by an infrared analyzer NG2000 (CO and CO₂ concentration in the range 0-1 vol. %).

2.3 Experimental methodology

5 Oxidation / reduction cycling experiments started with an oxidation step, carried out under air from ambient temperature to the operating temperature (heating rate of 10°C min⁻¹). When operating temperature was reached, an inerting step was performed under pure N₂ to avoid contact between fuel and air. Afterwards, a mixture of CO/N₂ was injected in the reactor (reduction step) at the operating temperature. The reaction was finished when the CO
10 concentration at the reactor's outlet was the same as the inlet concentration. The material was finally cooled down to ambient temperature under inert atmosphere and a new oxidation step could be started (new cycle).

2.4 Sample characterization

15 X-Ray Diffraction (XRD) analyses were performed using a PAN analytical, X'Pert Pro diffractometer operating with Cu K α radiation ($\lambda = 0.15418$ nm) equipped with a X'Celerator detector. Measurements were achieved for 2 θ angles in the 10–90° range, by step of 0.02° (220 s per step).

Temperature Programmed Reduction (TPR) experiments were performed in a SDT Q-600
20 thermobalance of TA Instruments. Operating conditions for TPR experiments were: 6 NL h⁻¹ of H₂/N₂ (5 vol. %) gas flow rate and 2°C min⁻¹ of temperature heating ramp, from ambient temperature to 1200°C.

Surface area analysis by krypton adsorption were performed on aged samples (after several oxidation-reduction cycles) using a Micromeritics ASAP 2420 apparatus.

3. Results

3.1 Evolution of the Total Reduction Capacity (TRC) of binders B1 and B2 as cycles proceed

Two binders stability and reactivity were studied under the same operating conditions: 0.2 g of material (B1 or B2), 900°C, 0.55 vol. % of CO as fuel in N₂, gas flow rate fixed at 50 NL h⁻¹. The Total Reduction Capacity (TRC) was the parameter chosen to study the evolution of the materials reactivity. TRC corresponds to the number of CO₂ moles produced per gram of material, and it is calculated by the integration of the CO₂ breakthrough curves obtained during the reduction step. Oxidation-reduction cycles were performed with both binders (B1 and B2) until the TRC stabilisation. The results obtained with each binder are represented in figure 1 for the CO₂ concentration curves and in table 1 for the TRC values.

The CO₂ curves obtained on both binders clearly indicate a notable activity of the materials in the oxidation of CO. This activity could partially be explained by the presence of residual NiO in the materials due to the preparation method. However, the amount of CO₂ produced clearly increases as cycles proceed for binders B1 and B2, indicating an evolution of the oxidizing ability of the two binders. Indeed, this TRC increase (table 1) cannot solely be explained by the presence of residual NiO.

As it is observed in table 1, TRC of B1 increases during the first cycles and tends to level off (after 20 cycles), whereas for B2, TRC increases progressively and converges slowly to the maximal TRC (after 80 cycles). If we consider that only ¼ of the oxygen in NiAl₂O₄ is available to oxidize CO (we consider that the oxygen of alumina is not available at all), 75% of this oxygen reacts in B1 during the 20th cycle, and 43% for B2 during the 80th cycle. During the first reduction cycle, the amount of available oxygen which reacts is equal to 56% and 10% for B1 and B2 respectively. In conclusion, at 900°C, a non-negligible amount of oxygen is available in both binders, which does not only come from residual NiO in the fresh materials. The growing amount of available oxygen in the binders as cycles proceed shows

structural modifications of the two binders that depend on the preparation method. Indeed, reactivity and stability of B1 and B2 during oxidation-reduction cycles are not the same. B1 reacts more rapidly than B2 and generates more available oxygen.

5 3.2 Binder characterization by X-Ray Diffraction investigation

Both binders were characterized by X-Ray Diffraction (XRD) to understand the evolution of their structures. XRD analyses were performed on the fresh and the aged binders (after successive cycles). On the fresh binders, two different crystalline phases with cubic structure were identified: NiO (ICDD PDF 00-047-1049) and NiAl₂O₄ (ICDD PDF 01-081-0715). The principal peaks of NiO and NiAl₂O₄ are represented in figure 2. The nickel and aluminum were introduced in stoichiometric proportions ($\frac{Ni}{Al} = 1$). XRD patterns show the presence of NiO traces, which leads us to suppose that there are traces of alumina in the mixture. For binder B1, as the diffraction peaks of γ -Al₂O₃ are at 2θ angles close to the NiAl₂O₄ ones, it is impossible to distinguish traces of alumina in the fresh material. However, low intensity peaks of α -Al₂O₃ are detected in fresh B2 (ICDD PDF 00-046-1212) ($2\theta = 57.4$ and 68.1). The presence of NiO and α -Al₂O₃ traces in this material is due to the preparation method (the reactants did not fully react to produce NiAl₂O₄). The alumina present in B2 is in its alpha polymorph because of the high calcination temperature used for its preparation (1200°C). Indeed, at temperatures higher than 1100°C, there is a phase transformation from γ -Al₂O₃ to α -Al₂O₃.

As it was observed in previous studies [43], XRD analyses reveal a shift and an enlargement of the peaks related to NiAl₂O₄ for both aged binders, while NiO peaks remain at the same diffraction angles. These observed shifts reveal a structural modification of both binders as cycles proceed. It seems that the peaks of NiAl₂O₄ shift towards γ -Al₂O₃ angles (cubic phase

Fd-3m). This observation could be explained by the progressive decomposition of NiAl_2O_4 to form NiO and $\gamma\text{-Al}_2\text{O}_3$. Moreover, for the aged binder B2, a diffraction peak ($2\theta = 66.6^\circ$) appears corresponding to $\gamma\text{-Al}_2\text{O}_3$. This hypothesis seems to be confirmed by the evolution of TRC during experiments, which increases for both binders. Indeed, NiO produced at high temperature is probably the compound which reacts with CO and which progressively increases TRC.

3.3 Quantitative estimation of NiO content in the binders

3.3.1 Quantification by X-Ray Diffraction analyses: Standard Addition Method

To estimate the NiO content present in each binder, quantitative XRD analyses were performed by using the Standard Addition Method (SAM). This standard method is used in analytical chemistry and has the advantage of eliminating possible matrix effects due to the analyzed sample which can modify the values obtained by quantitative measurements. Particularly in XRD analyses, the shape of the diffraction patterns can be modified by the difference of X-ray adsorption coefficients according to the mass and the composition of the sample. This method consists in measuring the response (in this case, the surface area of the integrated NiO diffraction peaks) for each successive addition (known masses) of the analyte NiO to the binder. 3 peaks of NiO were considered to perform the calculations. For example, figure 3 represents an enlargement of four XRD patterns corresponding to the fresh binder B2 and for three NiO additions. For each standard addition, the surface of the NiO peaks increases while the surface of the peaks related to NiAl_2O_4 remain almost constant.

The integration of the NiO peaks is systematically corrected by the integration of six peaks relative to NiAl_2O_4 for each standard addition.

Finally, the initial mass fraction of NiO of the binders (before addition, noted $\%\text{NiO}(0)$) is obtained by representing the ratio between mass fraction of NiO (addition k) calculated from

weighted masses versus exactly the same function calculated by peak integration (equation I).

The initial content of NiO (%NiO(0)) is estimated by adjusting the latter to have a straight line with a slope equal to 1 and passing through the origin (first bisector). This mathematical analysis reduces classical calculation errors carried out by estimation of the slope and the interception of a linear curve. A minimum of four points (initial content + 3 additions) were used in calculations for a good precision.

$$y = \frac{\%NiO(k)}{\%NiO(0)} = f \left(\frac{\%NiAl_2O_4(0)}{\%NiAl_2O_4(k)} \times \frac{\frac{1}{n} \sum_{i=1}^n \frac{S_{NiO}^i(k)}{S_{NiO}^i(0)}}{\frac{1}{m} \sum_{j=1}^m \frac{S_{NiAl_2O_4}^j(k)}{S_{NiAl_2O_4}^j(0)}} \right) \quad \text{Eq. I}$$

S corresponds to the surface of the peak of test k, i the number of peak related to NiO (i=1 to n=3), j the number of peak related to NiAl₂O₄ (j=1 to m=6). The initial experiment (without addition) is named 0.

This procedure was used for the four studied samples (fresh B1 and B2 and after oxidation-reduction cycles). The best fit lines obtained have in all cases a correlation coefficient (R²) higher than 0.999 (figure 4).

Table 2 shows the NiO mass fraction of the four samples (fresh and aged B1 and B2) estimated by using the Standard Addition Method

The results presented in table 2 confirm the observations obtained from TRC measurements. The initial NiO contents in the fresh binders are not equal: B1 contains more residual NiO than B2, which can explain the higher value of TRC obtained during the first cycle (3.17 moles CO₂/mg for B1 against 0.59 moles CO₂/mg for B2). The NiO content of the two binders increases as cycles proceed and can be explained by a decomposition of nickel aluminate to form NiO and probably alumina. These results show that nickel aluminate is

reacting with the fuel from the first cycle (0.75 and 0.23 moles of NiO per milligram of B1 and B2 respectively).

3.3.2 NiO content estimation by Temperature Programmed Reduction measurements

5 To confirm the X-Ray Diffraction data, Temperature Programmed Reduction (TPR) experiments were performed with the same samples (fresh and aged B1 and B2). These experiments consist in the reduction of the different crystalline phases contained in the two binders (NiO and NiAl_2O_4) which occurs at different temperatures under a H_2 gas flow. Alumina is probably present in the sample, but does not react with H_2 . TPR investigations
10 were conducted in a thermobalance, where mass variations were measured as a function of temperature with a slow ramp of temperature to ensure separation of the two reductions of NiO and NiAl_2O_4 . The operating conditions were: 8 mg of sample, gas flow rate 6 NL h^{-1} , 5 vol. % H_2 in nitrogen, 2°C min^{-1} heating rate, from ambient temperature to 1200°C . Results obtained for the fresh and the aged B1 and B2 are presented in figure 5.

15

Figures 5 shows the mass variation and its first derivative as a function of temperature for each studied material. In all cases we observe a first mass loss between 350° and 600°C corresponding to the reduction of NiO and a second one at temperatures higher than 600°C corresponding to the reduction of NiAl_2O_4 . The NiO content of each material have been
20 estimated from this data and are given in table 2.

3.3.3 Discussion

Both quantitative X-Ray Diffraction analyses and TPR experiments confirm that the NiO content present in both binders increases as oxidation-reduction experiments are performed.

From these results, the partial decomposition of the spinel phase NiAl_2O_4 to form NiO and Al_2O_3 is demonstrated and quantified. This decomposition and its kinetics depend on the binder's preparation method. Indeed, binder B2 obtained with a higher calcination temperature (1200°C) generates lower quantities of available oxygen than binder B1. The binder B2 is also less reactive. These observations can be explained by the fact that the surface available for reaction is higher for B1 ($31.5 \text{ m}^2 \text{ g}^{-1}$) than for B2 ($2.9 \text{ m}^2 \text{ g}^{-1}$) (measured by krypton adsorption after several oxidation-reduction cycles).

The TPR analyses indicate the same trend. The reduction reaction of NiO present in the two binders started approximately at the same temperature (around 350°C), whereas NiAl_2O_4 starts to reduce around 600°C for B1 and around 700°C for B2. In both cases (binders B1 and B2), the peaks related to NiAl_2O_4 reduction shift to higher temperatures after numerous cycles. These results could be the consequence of accessibility decrease of reaction sites (NiAl_2O_4) due to the presence of alumina and nickel. Some authors [46] observed an influence of the calcination temperature on the final reactivity of the material. They postulate that a higher calcination temperature leads to a less reactive binder. Moreover, these shifts could not be explained by a diffusion limitation in the particles. Han et al. [47] did a comprehensive analysis of the diffusion limitations of a very similar system and demonstrated that the internal diffusion resistance was significant only for particles with mean diameter greater than 1.0 mm.

Gayán *et al.* [10] performed comparative reactivity studies of different NiO -based oxygen carriers prepared by dry impregnation and supported on $\gamma\text{-Al}_2\text{O}_3$ (21 wt. % of NiO) or on $\alpha\text{-Al}_2\text{O}_3$ (11-38 wt. % of NiO). They observed that using $\gamma\text{-Al}_2\text{O}_3$ as a binder, most of the impregnated NiO reacted to form NiAl_2O_4 , therefore the reactivity of the oxygen carrier decreased. On the other side, if $\alpha\text{-Al}_2\text{O}_3$ was used as binder, the reactivity between the

alumina and NiO was decreased, less NiAl_2O_4 was produced, and the reactivity of the oxygen carrier was higher.

Our present results show that nickel aluminate partially decomposes to form nickel oxide and alumina ($\text{NiAl}_2\text{O}_4 = \text{NiO} + \text{Al}_2\text{O}_3$) under reducing conditions. This chemical decomposition

- 5 seems to reach a thermodynamic equilibrium after several cycles. At the beginning (in the fresh binder) the reaction quotient is almost zero (no products) and NiO and Al_2O_3 are preferably generated (until the reaction quotient is inferior to the equilibrium constant). Moreover, during the reduction step, the reduction of nickel oxide (to produce metallic Ni) leads to a decrease of the reaction quotient and so, to the decomposition of nickel aluminate.
- 10 In these operating conditions, the reaction is slow (in terms of kinetics), because 20 and 80 successive cycles are necessary to reach the equilibrium for binder B1 and B2 respectively.

3.4 Binder evolution in the oxygen carrier NiO/NiAl₂O₄

To check if results obtained with the binder (NiAl_2O_4) could be extrapolated to the oxygen carrier ($\text{NiO/NiAl}_2\text{O}_4$), a long reduction cycle (8 hours) at 900°C was performed with the oxygen carrier. The aim is to sufficiently reduce the oxygen carrier to observe NiAl_2O_4 reduction, despite the high content of NiO present in the material (60 wt. % of NiO). After reduction, the obtained material was oxidized and analyzed by XRD. Figure 6 shows the XRD pattern (enlargement between 57 and 69°) of the fresh and the reduced $\text{NiO/NiAl}_2\text{O}_4$.

- 20 The figure reveals (as with the binder alone) that peaks relative to NiO are at the same diffraction angles before and after oxidation reduction cycles, whereas peaks related to NiAl_2O_4 are enlarged and shifted to wider diffraction angles. As it was previously deduced for the binder, this shift shows a decomposition of NiAl_2O_4 to form NiO and Al_2O_3 . These results demonstrate that the binder in the oxygen carrier $\text{NiO/NiAl}_2\text{O}_4$ can also react with the fuel

during the reduction phase, producing additional NiO. The major role of the binder is to ensure the stability of the oxygen carrier and good mechanical properties. However the binder reactivity with the fuel [modifies](#) the oxygen carrier performance.

5 4. Conclusion

Oxidation-reduction cycles performed on both binders showed that they cannot be considered as inert materials, because they react with the fuel. The evolution of the Total Reduction Capacity revealed that the reactivity of the two binders is different, and it depends on their synthesis method. The first binder (B1) has a higher initial content of NiO (5.6 wt. % by XRD and 6.2 wt. % by TPR) and its Total Reduction Capacity increases during the first cycles and reaches a maximum after 20 oxidation-reduction cycles. The aged binder has a final amount of 17.3 wt. % calculated by XRD, [24% by TPR](#). An increase of the NiO content is also observed on the second binder, from 1.7% (XRD and TPR) to 11.8 % (XRD); 15.8% (TPR). [The Total Reduction Capacity levels off](#) after 80 cycles. Two different methods have been used in this work to calculate the NIO content present in these materials. Results obtained by both methods are in good agreement for lower contents of NiO and their deviations increase moderately for higher contents. [These results are in good agreement with experimental measurements of Total Reduction Capacity.](#)

The increase of NiO present in binder is explained by the progressive decomposition of NiAl_2O_4 to produce NiO and Al_2O_3 . Moreover, the decomposition of the binder as cycles proceed, was also observed on the oxygen carrier ($\text{NiO}/\text{NiAl}_2\text{O}_4$). This study revealed the influence of the preparation method on the binder final reactivity.

References

- [1] MacDowell N, Florin N, Buchard A, Hallett J, Galindo A, Jackson G, Adjiman CS, Williams CK, Shah N, Fennell P. An overview of CO₂ capture technologies. *Energy Environ Sci* 2010; 3: 1645-1669.
- [2] Ishida M, Jin H. A new advanced power-generation system using chemical-looping combustion. *Energy* 1994; 19: 415-422.
- [3] Ishida M, Zheng D, Akehata T. Evaluation of a chemical-looping-combustion power-generation system by graphic exergy analysis. *Energy* 1987; 12: 147-154.
- [4] Lyngfelt A, Leckner B, Mattisson T. A fluidized-bed combustion process with inherent CO₂ separation; application of chemical-looping combustion. *Chem Eng Sci*; 56: 3101-3113.
- [5] Noorman S, van Sint Annaland M, Kuipers JAM. Packed Bed Reactor Technology for Chemical-Looping Combustion. *Ind Eng Chem Res* 2007; 46: 4212-4220.
- [6] Noorman S, van Sint Annaland M, Kuipers JAM. Experimental validation of packed bed chemical-looping combustion. *Chem Eng Sci* 2010; 65: 92-97.
- [7] Gayán P, de Diego LF, García-Labiano F, Adánez J, Abad A, Dueso C. Effect of support on reactivity and selectivity of Ni-based oxygen carriers for chemical-looping combustion. *Fuel* 2008; 87: 2641-2650.
- [8] Adanez J, Abad A, Garcia-Labiano F, Gayan P, de Diego LF. Progress in Chemical-Looping Combustion and Reforming technologies. *Prog Energy Combust Sci* 2012; 38: 215-282.
- [9] Adánez J, de Diego LF, García-Labiano F, Gayán P, Abad A, J. M. Palacios JM. Selection of Oxygen Carriers for Chemical-Looping Combustion. *Energy Fuels* 2004; 18: 371-377.
- [10] de Diego LF, García-Labiano F, Adánez J, Gayán P, Abad A, Corbella BM, Palacios JM. Development of Cu-based oxygen carriers for chemical-looping combustion. *Fuel* 2004; 83: 1749-1757.
- [11] Mattisson T, Johansson M, Lyngfelt A. The use of NiO as an oxygen carrier in chemical-looping combustion. *Fuel* 2006; 85: 736-747.
- [12] Jerndal E, Mattisson T, Lyngfelt A. Thermal Analysis of Chemical-Looping Combustion. *Chem Eng Res Des* 2006; 84: 795-806.
- [13] Jerndal E, Mattisson T, Thijs I, Snijkers F, Lyngfelt A. Investigation of NiO/NiAl₂O₄ oxygen carriers for chemical-looping combustion produced by spray-drying. *Int J Greenh Gas Control* 2010; 4: 23-35.
- [14] Kuusik R, Trikkel A, Lyngfelt A, Mattisson T. High temperature behavior of NiO-based oxygen carriers for Chemical Looping Combustion. *Energy Procedia* 2009; 1: 3885-3892.
- [15] Linderholm C, Abad A, Mattisson T, Lyngfelt A. 160 h of chemical-looping combustion in a 10 kW reactor system with a NiO-based oxygen carrier. *Int J Greenh Gas Control* 2008; 2: 520-530.
- [16] Leion H, Lyngfelt A, Mattisson T. Solid fuels in chemical-looping combustion using a NiO-based oxygen carrier. *Chem Eng Res Des* 2009; 87: 1543-1550.
- [17] Villa R, Cinzia C, Gianpiero G, Luca L, Pio F, Ugo C, Stefano R. Ni based mixed oxide materials for CH₄ oxidation under redox cycle conditions. *J Mol Catal* 2003; 204: 637-646.
- [18] Lambert A, Delquie C, Clémeneçon I, Comte E, Lefebvre V, Rousseau J, Durand B. Synthesis and characterization of bimetallic Fe/Mn oxides for chemical looping combustion. *Energy Procedia* 2009; 1: 375-381.
- [19] Ishida M, Jin H, Okamoto T. A Fundamental Study of a New Kind of Medium Material for Chemical-Looping Combustion. *Energy Fuels* 1996; 10: 958-963.
- [20] Zhao H, Liu L, Wang B, Xu D, Jiang L, Zheng C. Sol-Gel-Derived NiO/NiAl₂O₄

Oxygen Carriers for Chemical-Looping Combustion by Coal Char. *Energy Fuels* 2008; 22: 898-905.

- [21] Mattisson T, Johansson M, Lyngfelt A. Multicycle Reduction and Oxidation of Different Types of Iron Oxide Particles Application to Chemical-Looping Combustion. *Energy Fuels* 2004; 18: 628-637.
- [22] Mattisson T, Järnäs A, Lyngfelt A. Reactivity of Some Metal Oxides Supported on Alumina with Alternating Methane and Oxygen Application for Chemical-Looping Combustion. *Energy Fuels* 2003; 17: 643-651.
- [23] Abad A, Adánez J, García-Labiano F, de Diego LF, Gayán P, Celaya J. Mapping of the range of operational conditions for Cu-, Fe-, and Ni-based oxygen carriers in chemical-looping combustion. *Chem Eng Sci* 2007; 62: 533-549.
- [24] Hossain MM, de Lasa HI. Chemical-looping combustion (CLC) for inherent separations—a review. *Chem Eng Sci* 2008; 63: 4433-4451.
- [25] Abad A, Mattisson T, Lyngfelt A, Johansson M. The use of iron oxide as oxygen carrier in a chemical-looping reactor. *Fuel* 2007; 86: 1021-1035.
- [26] Yang J, Cai N, Li Z. Reduction of Iron Oxide as an Oxygen Carrier by Coal Pyrolysis and Steam Char Gasification Intermediate Products. *Energy Fuels* 2007; 21: 3360-3368.
- [27] Corbella BM, Palacios JM. Titania-supported iron oxide as oxygen carrier for chemical-looping combustion of methane. *Fuel* 2007; 86: 113-122.
- [28] Ishida M, Takeshita K, Suzuki K, Ohba T. Application of $\text{Fe}_2\text{O}_3\text{-Al}_2\text{O}_3$ Composite Particles as Solid Looping Material of the Chemical-Loop Combustor. *Energy Fuels* 2005; 19: 2514-2518.
- [29] García-Labiano F, de Diego LF, Adánez J, Abad A, Gayán P. Reduction and Oxidation Kinetics of a Copper-Based Oxygen Carrier Prepared by Impregnation for Chemical-Looping Combustion. *Ind Eng Chem Res* 2004; 43: 8168-8177.
- [30] Forero CR, Gayán P, de Diego LF, Abad A, García-Labiano F, Adánez J. Syngas combustion in a 500 Wth Chemical-Looping Combustion system using an impregnated Cu-based oxygen carrier. *Fuel Process Technol* 2009; 90: 1471-1479.
- [31] Johansson M, Mattisson T, Lyngfelt A. Investigation of Mn_3O_4 with Stabilized ZrO_2 for Chemical-Looping Combustion. *Chem Eng Res Des* 2006; 84: 807-818.
- [32] Forutan HR, Karimi E, Hafizi A, Rahimpour MR, Keshavarz P. Expert representation chemical looping reforming: A comparative study of Fe, Mn, Co and Cu as oxygen carriers supported on Al_2O_3 . *J Ind Eng Chem* 2015; 21: 900-911.
- [33] Abad A, Mattisson T, Lyngfelt A, Rydén M. Chemical-looping combustion in a 300 W continuously operating reactor system using a manganese-based oxygen carrier. *Fuel* 2006; 85: 1174-1185.
- [34] Gu Z, Li K, Wang H, Qing S, Zhu X, Wei Y, Cheng X, Yu H, Cao Y. Bulk monolithic Ce-Zr-Fe-O/ Al_2O_3 oxygen carriers for a fixed bed scheme of the chemical looping combustion: Reactivity of oxygen carrier. *Appl Energy* 2016; 163: 19-31.
- [35] Wang J, Zhao H. Evaluation of CaO-decorated $\text{Fe}_2\text{O}_3/\text{Al}_2\text{O}_3$ as an oxygen carrier for in-situ gasification chemical looping combustion of plastic wastes. *Fuel* 2016; 165: 235-243.
- [36] Dueso C, Abad A, García-Labiano F, de Diego LF, Gayán P, Adánez J, Lyngfelt A. Reactivity of a $\text{NiO}/\text{Al}_2\text{O}_3$ oxygen carrier prepared by impregnation for chemical-looping combustion. *Fuel* 2010; 89: 3399-3409.
- [37] Gayán P, Dueso C, Abad A, Adanez J, de Diego LF, García-Labiano F. $\text{NiO}/\text{Al}_2\text{O}_3$ oxygen carriers for chemical-looping combustion prepared by impregnation and deposition-precipitation methods. *Fuel* 2009; 88: 1016-1023.
- [38] Cheng Z, Wu Q, Li J, Zhu Q. Effects of promoters and preparation procedures on reforming of methane with carbon dioxide over $\text{Ni}/\text{Al}_2\text{O}_3$ catalyst. *Catal Today* 1996; 30:

147-155.

[39] Cho P, Mattisson T, Lyngfelt A. Carbon Formation on Nickel and Iron Oxide-Containing Oxygen Carriers for Chemical-Looping Combustion. *Ind Eng Chem Res* 2005; 44: 668-676.

[40] Jin H, Okamoto T, Ishida M. Development of a Novel Chemical-Looping Combustion: Synthesis of a Looping Material with a Double Metal Oxide of CoO–NiO. *Energy Fuels* 1998; 12: 1272-1277.

[41] Adánez J, Dueso C, de Diego F, García-Labiano F, Gayán P, Abad A. Methane Combustion in a 500 Wth Chemical-Looping Combustion System Using an Impregnated Ni-Based Oxygen Carrier. *Energy Fuels* 2009; 23: 130-142.

[42] Dueso C, Ortiz M, Abad A, García-Labiano F, de Diego LF, Gayán P, Adánez J. Reduction and oxidation kinetics of nickel-based oxygen-carriers for chemical-looping combustion and chemical-looping reforming. *Chem Eng J* 2012; 188: 142-154.

[43] Blas L, Dorge S, Dutournié P, Lambert A, Chiche D, Bertholin S, Josien L. Study of the performances of an oxygen carrier: Experimental investigation of the binder's contribution and characterization of its structural modifications. *Comptes Rendus Chim* 2015; 18: 45-55.

[44] Blas L, Dorge S, Zouaoui N, Lambert A, Dutournié P. Influence of the oxidation step on the behaviour and the performances of an oxygen carrier in fixed bed reactor. *Mater Res* 2014; 17: 219-226.

[45] Blas L, Dorge S, Michelin L, Dutournié P, Lambert A, Chiche D, Bertholin S. Influence of the regeneration conditions on the performances and the microstructure modifications of NiO/NiAl₂O₄ for chemical looping combustion. *Fuel* 2015; 153: 284-293.

[46] Cesteros Y, Salagre P, Medina F, Sueiras JE. Preparation and Characterization of Several High-Area NiAl₂O₄ Spinel. Study of Their Reducibility. *Chem Mater* 2000, 12: 331-335.

[47] Han L, Zhou Z, Bollas GM. Heterogeneous modeling of chemical-looping combustion. Part 2: Particle model. *Chem Eng Science* 2014, 113: 116-128.