LATTICE MODES IN THE LINEAR CHAIN COMPOUND ZrTe_5

A. Zwick, G. Landa, R. Carles and M.A. Renucci

Laboratoire de Physique des Solides, Associé au C.N.R.S., Université Paul Sabatier
118, Route de Narbonne, 31062 Toulouse Cédex, France

and

A. Kjekshus

Kjemisk Institutt, Universitetet i Oslo
Blindern, Oslo 3, Norway

(Received 13 April 1982 by M. Balkanski)

We report Raman scattering experiments on the linear chain compound ZrTe_5 . Room and low temperature measurements rule out the existence of a structural phase transition, suggested by the resistive anomaly near 150 K. The eight $\vec{k} = 0$ vibrationnal modes allowed by the scattering geometry are observed and their symmetries determined from polarized spectra. Some of the modes are identified on the basis of symmetry properties and (or) in comparison with the Raman spectra of the related compound ZrTe_3 . Moreover, this comparison indicates surprisingly similar strengths for atomic interactions in ZrTe_3 and ZrTe_5 .

Introduction

ZrTe_5 crystallizes in a chain structure¹ closely related to that of the transition-metal trichalcogenides. In some of these low dimensional compounds, such as NbSe_3 , a particular form of the Fermi surface produces electronic instabilities which drive structural phase transitions^{2,3}. This explains the recent attention devoted to the pentatellurides ZrTe_5 and HfTe_5 ⁴ and the subsequent investigation of their structural and transport properties by means of various techniques. In spite of a resistive anomaly⁵ observed near 150 K, the other measurements⁶ ruled out the possibility of an electronically-driven phase transition similar to that reported in NbSe_3 .

In the present paper, we report the results of room and low temperature Raman scattering experiments on crystalline ZrTe_5 . The crystal structure is described in Sec. 2. The experimental details are given in Sec. 3. Following the factor group analysis of the crystal and chain $\vec{k} = 0$ vibrationnal modes, the experimentally observed spectra are presented and discussed in Sec. 4.

2. Crystal Structure

ZrTe_5 was shown to be isostructural with HfTe_5 , the crystal structure of which has been determined by the X-ray work of Furuseth et al.¹ ZrTe_5 crystallizes in the Cmcm (D_{2h}^{17}) space group. The conventional non-primitive unit cell contains four formula units and has the dimensions $a = 3.9876 \text{ \AA}$, $b = 14.502 \text{ \AA}$ and $c = 13.727 \text{ \AA}$.

ZrTe_5 possesses an interesting structure with both layer and chain features that are responsible for the easy (010) cleavage and the fibrous looking of the crystals. Fig. 1(a) shows

projections of the structure into different crystallographic planes, and displays the 12-atom primitive unit cell, with two chains passing through. One can build up the infinite atomic chains parallel to the a axis by stacking together distorted bicapped trigonal prisms of tellurium with the zirconium atoms located in the centre. The chains are linked by Te-Te bonds so as to form layers approximately parallel to the (010) plane. The layers are held together by weak Van der Waals-type forces.

This structure is closely related to that of ZrTe_3 ⁶ and other IV_b transition-metal trichalcogenides. The main difference, which accounts for the difference in composition, lies in the linkage between the basic coordination units [see fig. 1(b)].

3. Experiment

The samples studied in this work were single crystals of ZrTe_5 , with typical dimensions $6 \times 0.2 \times 0.4 \text{ mm}^3$. The Raman measurements were taken on freshly cleaved (010) surfaces in order to avoid scattering from Te, left behind by surface oxidation. The prepared samples were immediately immersed in the exchange gas of an Oxford CF 204 cryostat for room and low temperature experiments.

The Raman spectra of ZrTe_5 , excited with the 5145 Å and 5309 Å lines of Spectra Physics argon and krypton ion lasers, were measured in the back-scattering geometry. The laser beam was focused onto the surface sample at nearly normal incidence. The scattered light was collected along the crystal b axis direction and analyzed in a T800 Coderg triple monochromator, in conjunction with standard photoncounting electronics.

Fig.1. Structure of ZrTe_5 type crystals

(a) Projections in the (001) and (100) planes.

The primitive unit cell is shown on the top diagram. The crystal-symmetry elements are indicated on both diagrams.

(b) Interchain linkage in ZrTe_5 , compared to that in ZrTe_3 .

The principal axes X, Y, Z are chosen to coincide with the crystallographic axes a, b, c.

4. Results and Discussion

4.1. Factor group analysis

The crystal factor-group contains the eight representative symmetry elements :

- 1 : the identity,
- $2_a, 2_b$: twofold axes parallel respectively to the a and b axes,
- 2_c : a twofold screw axis parallel to c,
- $\bar{1}$: a centre of symmetry,
- $\bar{2}_a, \bar{2}_c$: mirror planes perpendicular respectively to a and c,
- $\bar{2}_b$: a glide plane perpendicular to b.

Four of these symmetry elements (the identity, the 2_b twofold axis and the $\bar{2}_a, \bar{2}_c$ mirror planes) are in common with the factor group of a single chain.

The symmetries of the long-wavelength phonons are determined by the representation Γ_{crystal} of the crystal factor group generated by the displacements of the atoms in the primitive unit cell.

Γ_{crystal} is 36 dimensional for the 12-atom primitive unit cell of ZrTe_5 . The reduction of Γ_{crystal} into irreducible representations of the isomorphic point group mmm (D_{2h}) is as follows :

$$\Gamma_{\text{crystal}} = 6A_g + 6B_{3g} + 2B_{2g} + 4B_{1g} + 6B_{2u} + 2A_u + 4B_{3u} + 6B_{1u}$$

Because of the inversion operation contained in the crystal factor-group, Raman and infra-red activities are mutually exclusive. The eighteen even-parity modes are optical Raman active phonons, while the eighteen odd-parity modes consist of three acoustical and fifteen optical infra-red active phonons. The $\mathbf{k} = \mathbf{0}$ modes can further be classified according to atomic displacements, parallel to the chains (or out-of- $\bar{2}_a$ mirror plane) for $B_{1g}, B_{2g}, B_{3u}, A_u$ symmetries and perpendicular to the chains (or in $\bar{2}_a$ mirror plane) for $A_g, B_{3g}, B_{2u}, B_{1u}$.

Since the chains constitute well-defined

units in the crystal, it is convenient to first look at the long-wavelength modes of a single chain and then establish a compatibility relationship connecting the chain to the crystal. The chain factor-group representation Γ_{chain} generated by the displacements of atoms in the 6-atom primitive unit cell is 18 dimensional, and reducible into irreducible representations of the isomorphic point group $2mm$ (C_{2v}):

$$\Gamma_{\text{chain}} : 6A_1 + 6B_1 + 2A_2 + 4B_2$$

Due to the lack of a centre of symmetry, the long-wavelength optical modes of the chain are not divided into even and odd-symmetry types. The chains modes can be classified according to atomic displacements in or out of $\bar{2}_a$ mirror plane, corresponding respectively to indices 1 and 2. A and B stands for modes respectively symmetric and antisymmetric with respect to the twofold rotation. The correlation method was used to relate the irreducible representations of the zirconium and tellurium atoms site groups to those of the chain factor group. From the correlation chart presented in table I(a), we can determine which atoms move in each normal mode and whether this motion is along or perpendicular to the chain axis.

Table I(b) displays the correlation diagram relating the long-wavelength chain and crystal phonons in ZrTe_5 . Since there are two chains per primitive unit cell correlated via an inversion centre, each chain mode splits into a g-u pair in the crystal. Furthermore, because the crystal retains all the symmetry elements of the chain, there is no mixing of the chain modes symmetries in the crystal.

In particular, the A and B symmetries do not mix, in contrast to what happens in the monoclinic structure of the IV_b metal-transition trichalcogenides. Lastly, as a result of the interchain coupling, the $A_1 + 2B_1 + B_2$ zero frequency modes of the chain divide up into four odd crystal modes (three acoustical $B_{2u} + B_{1u} + B_{3u}$ and one infra-red B_{1u}) and four low-lying even modes $A_g + 2B_{3g} + B_{1g}$. These Raman active modes are expected to be largely rigid chain motions. They can be classified in three translational modes B_{1g} , A_g , B_{3g} respectively along the a-, b- and c axes, and a librational mode B_{3g} about the a axis.

4.2. Experimental results and discussion

In the XYZ set of principal axes, chosen so as to coincide with the abc crystallographic axes of the crystal, the polarizability tensors γ of the $\vec{k} = 0$ Raman-active modes of ZrTe_5 have the form:

$$A_g: \begin{bmatrix} a & & \\ & b & \\ & & c \end{bmatrix} \quad B_{1g}: \begin{bmatrix} d & & \\ & d & \\ & & e \end{bmatrix} \quad B_{2g}: \begin{bmatrix} e & & \\ & f & \\ & & f \end{bmatrix} \quad B_{3g}: \begin{bmatrix} f & & \\ & f & \\ & & f \end{bmatrix}$$

The backscattering geometry described in 3 allows the measurements of Raman tensor components XX, ZZ, XZ. Thus six A_g and two B_{2g} modes should be experimentally observed among the eighteen modes theoretically predicted.

Fig. 2 shows unanalyzed Raman spectra for two temperatures, above and below 150 K. As can be seen, eight peaks are clearly observed at room temperature. No new peak occurs at low temperature that would reveal any change of the

crystallographic unit cell, such as those induced by charge density waves in many layered transition dichalcogenides^{8,9}.

The different components of Raman tensor allowed by the scattering geometry are shown in Fig. 3, which depicts modes polarized respectively parallel (B_{2g}) and perpendicular (A_g) to the chains. The symmetries and wavenumbers of the observed $\vec{k} = 0$ Raman active modes are given in Table II.

We shall approach the mode assignment from the analysis of the single chain vibrations, substantiated by a comparison with the Raman spectra of ZrTe_3 . We present in Table III the list of $\vec{k} = 0$ phonons in ZrTe_3 and their assignment to chain modes according to the Raman works of Zwick et al.¹⁰, and Wieting et al.¹¹.

As it appears from the comparison of Table III, the longwavelength phonons of ZrTe_5 lie very near in frequency to those of ZrTe_3 . Beyond the close relation between the two structures, this provides evidence of similar strengths for atomic interactions in the two compounds.

Considering first in ZrTe_5 the two B_{2g} modes polarized along the a axis, we see from Table I(b) that they originate from A_2 chain modes. Table I(a) shows that these A_2 modes are mixtures of shearing motions of the Te_{II} and Te_{III} pairs respectively. In the crude model of bond stretching forces between nearest neighbours in the chain, the shearing motion of Te_{III} atoms does not imply any stretching of the Zr-Te_{III} bonds, which are perpendicular to the chains. The inter-chain coupling rises this zero frequency mode until it mixes with the shearing mode of the Te_{II} pair, which depends essentially on intra-chain Zr-Te_{II} interaction. Assuming the same interaction between Zr and Te_{II} atoms within the chains in ZrTe_3 and ZrTe_5 , we expect in ZrTe_5 a B_{2g} crystal doublet, very close in frequency to the B_g mode of ZrTe_3 originating from the shearing of the Te_{II} pair in the chain. The B_{2g} spectrum of ZrTe_5 (Fig.3) exhibits clearly a doublet of lines lying respectively at 74 and 89.5 cm^{-1} , close in frequency to the single B_g mode observed at 68 cm^{-1} in ZrTe_3 . The Raman study of ZrTe_5 thus substantiates in turn mode assignment in ZrTe_3 : we confidently attribute to A_2 chain mode the 68 cm^{-1} line in ZrTe_3 , in agreement with previous assignment by Wieting and coworkers¹¹ based on the line intensity.

Looking now at the six A_g modes of ZrTe_5 , we refer back to Table I(b) and conclude that they all proceed from A_1 chain modes. According to theoretical expectations, we assign the lowest lying line at 39 cm^{-1} to the quasi-rigid translational motion of the chains along the b-axis. Its wavenumber is surprisingly close to that of the lowest A_g mode in ZrTe_3 (37 cm^{-1}), which was attributed¹⁰ to a translational chain mode of the crystal. This might prove in turn the A_1 symmetry of the 37 cm^{-1} line of ZrTe_3 , as we proposed in earlier work¹⁰. The highest frequency line at 239 cm^{-1} is attributed to the stretching mode of the diatomic $(\text{Te}_{II})_2$ "molecule". This mode lies at slightly higher frequency than the corresponding mode of ZrTe_3 (217 cm^{-1}), that would indicate stronger atomic interaction and shorter covalent bond length between the pairing Te_{II} atoms in ZrTe_5 than in ZrTe_3 . As for the others A_g lines, such a qualitative discussion

Table I.

- (a) Correlation chart between C_{2V} and C_S site groups of (Zr , Te_I) and (Te_{II} , Te_{III}) atoms and C_{2V} chain factor group in ZrTe_5 .
- (b) Compatibility diagram relating the chain and crystal vibrations of ZrTe_5 .

Site Group		Chain Factor Group		Site Group
(Zr , Te_I)				(Te_{II} , Te_{III})
C_{2V}		C_{2V}		C_S
(T_Y) A_1	—	A_1	—	$A'(T_Y, T_Z)$
(T_Z) B_1	—	B_1	—	
(T_X) B_2	—	A_2	—	$A''(T_X)$
		B_2	—	

(a)

Single Chain (C_{2V})		Crystal (D_{2h})
Internal modes		
R, IR $5A_1$	—	$5A_g$ R
		$5B_{2u}$ IR
R, IR $3B_1$	—	$3B_{3g}$ R
		$3B_{1u}$ IR
R $2A_2$	—	$2B_{2g}$ R
		$2A_u$ IR
R, IR $3B_2$	—	$3B_{1g}$ R
		$3B_{3u}$ IR
External modes		
		B_{3g} R
		B_{3g} R
		A_g R
		B_{1g} R
		B_{1u} IR
R, IR $A_1 + 2B_1 + B_2$	—	$B_{2u} + B_{1u} + B_{3u}$ acoustical
T_Y T_Z, R_X T_X		

(b)

Table II. Wavenumbers and symmetries of $\vec{k} = \vec{0}$ Raman active phonons of ZrTe_5 at 300 K and 77 K.

Symmetry	Chain	A_1	A_2	A_2	A_1	A_1	A_1	A_1	A_1
	Crystal	A_g	B_{2g}	B_{2g}	A_g	A_g	A_g	A_g	A_g
$\nu(\text{cm}^{-1})$	300 K	39	72	86.5	116	121	147	181.5	
	77 K	40	74	89.5	117	123	152	183.5	239

Fig.2. Unpolarized Raman spectra of ZrTe_5 excited with $\lambda = 5145 \text{ \AA}$ at 300 K and 77 K. The structures marked by an asterisk are due to scattering by A_1 and E modes of crystalline Te, left behind by surface oxidation.

Table III. Wavenumbers and symmetries of $\vec{k} = \vec{0}$ Raman active phonons of ZrTe_3 at 300 K.

Ref. 11			Ref. 10		
Symmetry		$\nu \text{ (cm}^{-1}\text{)}$	Symmetry		$\nu \text{ (cm}^{-1}\text{)}$
Crystal	Chain		Crystal	Chain	
A_g	$B_1(T_X)$	11			
A_g	$B_1(R_Y)$	38	A_g	$A_1(T_Z)$	37.5
A_g	$A_1(T_Z)$	62	A_g	$B_1(T_X)$	61.5
B_g	A_2	64	B_g		66.5
A_g	B_1	86	A_g	$B_1(R_Y)$	84.5
A_g	A_1	108	A_g	A_1	111
A_g	A_1	144	A_g	A_1	143.5
A_g	A_1	216	A_g	A_1	215

Fig.3. Polarized Raman spectra of ZrTe_5 excited with $\lambda = 5309 \text{ \AA}$ at 77 K.

is not sufficient, and an interatomic-force model is needed to describe the lattice dynamics of ZrTe_5 and calculate the eigenvectors of the corresponding modes.

3. Conclusion

The Raman study of crystalline ZrTe_5 at room and liquid nitrogen temperatures rules out the possibility of an electronically driven phase transition near 150 K suggested by a resistive anomaly. All the $\vec{k} = \vec{0}$ phonons predicted by group

theory analysis and allowed by the scattering geometry have been observed, and their symmetry determined by polarization measurements. An approach of the crystal lattice dynamics from the "molecular" point of view allows the identification of some crystal modes, in absence of complete calculation based on an interatomic-force model. The comparison with the Raman spectra of the closely related compound ZrTe_3 demonstrates that, in spite of the dissimilarity in internal architecture of the basic layers, the strengths of atomic interactions are similar in the two compounds.

References

- ¹ S. Furuseth, L. Brattas and A. Kjekshus, *Acta Chem. Scand.* 27, 2367 (1973).
- ² N.P. Ong and P. Monceau, *Phys. Rev. B* 16, 3443 (1977).
- ³ R.M. Fleming, D.E. Moncton and D.B. McWhan, *Phys. Rev. B* 15, 5560 (1976).
- ⁴ F.J. DiSalvo, R.M. Fleming and J.V. Waszczak, *Phys. Rev. B* 24, 2935 (1981).
- ⁵ T.J. Wieting, D.U. Gubser, S.A. Wolf and F. Levy, *Bull. Am. Phys. Soc.* 25, 340 (1980).
- ⁶ S. Furuseth, L. Brattas and A. Kjekshus, *Acta Chem. Scand.* A29, 623 (1975).
- ⁷ R. Loudon, *Adv. Phys.* 13, 423 (1964).
- ⁸ J.R. Duffey, R.D. Kirby and R.V. Coleman, *Solid State Commun.* 20, 617 (1976).
- ⁹ J.E. Smith, J.C. Tsang and M.W. Shafer, *Solid State Commun.* 19, 283 (1976).
- ¹⁰ A. Zwick, M.A. Renucci and A. Kjekshus, *J. Phys. C Solid. State Phys.* 13, 5603 (1980).
- ¹¹ T.J. Wieting, A. Grisel and F. Lévy, *Physica* 105B, 366 (1981).