Nitridation enhancement of TiSi₂ powders by addition of nickel

Jerome Roger, Laurine Nouvian, Yann Le Petitcorps, Laurence Maillé

► To cite this version:

Jerome Roger, Laurine Nouvian, Yann Le Petitcorps, Laurence Maillé. Nitridation enhancement of TiSi₂ powders by addition of nickel. Journal of Alloys and Compounds, 2017, 10.1016/j.jallcom.2017.07.031 . hal-01567344

HAL Id: hal-01567344

<https://hal.science/hal-01567344>

Submitted on 22 Jul 2017

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Distributed under a Creative Commons Attribution - NonCommercial - NoDerivatives| 4.0 International License

Nitridation enhancement of TiSi₂ powders by addition of nickel

J. Roger^{a,*}, L. Nouvian^a, Y. Le Petitcorps^a, L. Maillé^a

^a Université de Bordeaux, CNRS, Laboratoire des Composites ThermoStructuraux,

UMR 5801, 33600 Pessac, France

* Corresponding author: e-mail: jerome.roger@lcts.u-bordeaux.fr

Abstract

The nitridation enhancement of a TiSi₂ powder by nickel addition was examined. The quantities of the added metal were comprised between 2.5 and 25mol.%, the balance being TiSi₂. The isothermal heat treatments were made at 1100°C for durations up to 40 hours under normal pressure and continuous flow of pure nitrogen. Comparing to pure TiSi₂ powder, an improvement of the conversion in TiN and Si₃N₄ is obtained for compositions containing 10.0; 12.5 and 15.0 mol.% of nickel. According to the quaternary Ti-Si-Ni-N phase diagram, nickel was found to form Ni₄Ti₄Si₇ compound. Thermogravimetric analysis of these three compositions showed the existence of three successive stages during the conversion. First, an initiate reaction occurred with a very weak weight gain. Then, the second stage exhibited an acceleration of the weight gain. Those two stages are both controlled by nucleation and growth, as represented by the kinetic equation $[-\ln(1-\alpha)]^{1/2} = k.t$. Finally, the reaction is limited by three-dimension diffusion, as represented by the kinetic equation: $[1-(1-\alpha)^{1/3}]^2 = k.t$. From this behavior, an activation mechanism is proposed.

Keywords: A. ceramics; B. Gas-liquid reactions; C. Catalysis; C. Kinetics; E. thermodynamic properties; D. Thermal analysis;

1. Introduction

Materials based on silicon nitride are one of the more promising materials for use in high-temperature applications thanks to their high heat resistance, refractoriness, hardness, durability, thermal shock resistance, and chemical resistance. They have a high potential in the practical utilization not only as a structural material but also as a functional material. Understanding of the silicon nitridation process has evolved significantly over the past decades, and the effects of many of the reaction variables on the reaction kinetics and product morphology are well documented [1-18]. In addition to monolithic ceramics, some works have also focused on using reaction-bonded silicon nitride as a composite matrix [19,20]. But, this way requires long durations and temperatures that exceed 1400°C. This is problematic for composite applications because the whiskers or fibers used as reinforcements could be degraded at elevated temperatures. The formation of Si_3N_4 from pure silicon generates a low volume expansion of 22%. So, full densification implies an initial powder compactness of about 82%. This starting value is unrealistic and full densification is then not possible by this way. An alternative possibility is to use an intermetallic compound as TiSi_2 . Indeed, the reaction to form Si_3N_4 -TiN composite from TiSi_2 is accompanied by a 60% volume expansion which occurs in the void space of the compact, such that complete nitridation should fully densified a 62.5% dense TiSi_2 body. Titanium nitride is an interesting compound which is widely used to prepare metal ceramic, cutting tools, molds, coatings because of its high strength, high hardness, thermal stability, high electrical conductivity, good wear and corrosion resistance. The conventional synthesis of TiN involves direct nitridation, laser cladding, self propagating high-temperature synthesis and mechanical milling [21,22]. The combustion synthesis of TiN was investigated by several authors and was found relatively easy to proceed [23-27]. M. Ade and J. Haußelt [28] reported that the maximum conversion (90%) of a pure TiSi_2 powder with a mean grain size less than 2 μm was obtained for a temperature close to 1400°C, probably because of the formation of liquid silicon

($T_{\text{melting}}(\text{Si})=1414^{\circ}\text{C}$). The exothermicity of this reaction and the formation of liquid silicon could be detrimental in the case of fibrous composites. In a previous work, we focused our attention on the nitridation of pure TiSi_2 compacts at lower temperatures ($1000\text{-}1200^{\circ}\text{C}$) to produce the matrix of a fibers-reinforced composite [29]. Accordingly to previous papers [30-33], it was found that the nitridation is sluggish in these conditions because of diffusional limitations. Indeed, the titanium nitridation is easily but silicon reacts very slowly due to the formation of a TiN layer at the surface of the grains. This TiN layer behaves as a diffusion barrier towards nitrogen and silicon [30,31,34]. To circumvent this pitfall, it is required to set up a strategy to enhance the nitridation of TiSi_2 , this is the objective of the present work. It has been known that transition metals can regulate kinetics of silicon nitridation as well as the phases formation [3,12,35-37]. Since sintering additives are always used in the fabrication of materials from silicon nitride powder, the nitridation enhancement role of minor additions of common metals in the starting Si powder is well established [12,35,36,38-41]. Especially, it was shown that Fe, Ni or Al addition promotes the formation of nitrides [36-38]. These metals should promote the crystallization and the disruption of the amorphous native silica layer located at the surface of the grains. Another explanation suggested that metals form a liquid phase by reacting with silicon to form a eutectic. On this way, we examine the effect of adding a metal powder to a TiSi_2 powder to improve nitridation. Several metals were considered to promote nitridation at a temperature as low as 1100°C . Based on the hypothesis that the formation of a liquid phase should enhance atomic mobility and consequently nitridation rate, the attention was focused on nickel because of the low-temperature eutectic NiSi-NiSi_2 (956°C). In the present work, the synthesis of $\text{Si}_3\text{N}_4\text{-TiN}$ -based composite has been studied by the nitridation of TiSi_2 and Ni powders mixtures under nitrogen atmosphere.

2. Thermodynamic analysis of the Ti-Si-Ni-N system equilibrium

Prior to experimental investigation, a preliminary thermodynamic analysis of the equilibrium in the Ti-Si-Ni-N system was performed with the help of the ThermoCalc software [42]. The

relevant thermodynamic descriptions of the Ti-Si-N and Ti-Si-Ni systems reported by S. Sambasivan et al. and T. Tokunaga et al., respectively, were used for these calculations [43,44]. The so-calculated equilibrium diagrams at 1100°C are shown in Figure 1a and Figure 1b. The particularity of the Ti-Si-Ni system is the formation of a Si-rich ternary liquid phase at this temperature. This liquid phase originates from the NiSi-NiSi₂ eutectic reaction at only 956°C, as shown in Figure 2 [45]. The phases stability diagrams for the (1-x) TiSi₂ + x Ni mixtures were calculated as a function of nitrogen content at 1100°C for x = 0.025; 0.100; 0.150 and 0.250. The so-obtained diagrams are shown in Figure 3. In each case, the formation of TiN and Si₃N₄ nitrides is announced. Depending on the nitrogen quantity, nickel generates first the ternary compound Ni₄Ti₄Si₇, then the ternary liquid and finally binary nickel silicides in equilibrium with gaseous nitrogen. This means that the formation of the liquid phase is possible at the interface with the atmosphere, what is favorable to nitrides formation by improving atomic diffusion. When looking at the variation of the nickel activity versus nitrogen content shown in Figure 4-a, one note that the lower Ni-activity value corresponds to the TiN+Si₃N₄+Ni₄Ti₄Si₇+TiSi₂ and TiN+Si₃N₄+Ni₄Ti₄Si₇ equilibriums. So, one could expect that the equilibrium TiN+Si₃N₄+Ni₄Ti₄Si₇ should be favored as a further nitridation implies an increase of nickel activity whereas nitrogen activity increases during the conversion (Figure 4-b). The expected reaction is (Reaction 1):

The Gibbs free energy that varies with the progress of this reaction was also calculated. This reaction is favorable as it implies a large negative Gibbs free energy and decreases with the progress of the reaction as shown in Figure 5.

3. Materials and experimental procedures

The starting TiSi₂ powder (99.95%, d₅₀ = 44 μm, Neyco) used in these experiments was analyzed by spectrographic analysis (S.C.A.-C.N.R.S., Villeurbanne, France) to determine the

impurities content: 1.64% O, 0.43% C and 0.48% Fe in mass. The nickel powder was supplied by Strem Chemicals (99.9%, $d_{50} = 5 \mu\text{m}$). The two raw powders were milled together during 1 hour in ethanol with a vibratory mixer mill (Retsch MM200) (WC-milling-bowl and -balls) to reduce the grain size to $d_{50} = 3\text{-}4 \mu\text{m}$. The mean grain size of the powders was determined with the help of a Fritsch Analysette 22 Nanotec Plus granulometric analyser. The compositions of the powder mixtures are listed in Table 1. A part of each milled preparation was isostatically pressed to form a 10 mm diameter pellet. The green density was closed to 50% of theoretical. The pellets, weighing about 1g each, were put into an alumina boat and were separated each other by alumina splitters (Figure 6). The nitridation reaction of these samples was performed in a horizontal quartz-tube furnace at 1100°C up to 40 hours in the presence of titanium powder as a getter. Mass variation measurements versus time were also performed in a thermogravimetric analyzer (Setaram TAG24) from 20°C to the treatment temperature at a heating rate of 10°C/min for various durations up to 20 hours. TGA measurements were limited to this duration because of technical limitations due to the volatility of silicon. Nitridation processes were realized at normal pressure under a continuous nitrogen gas flow (50 mL/min). The powder masses used for thermogravimetric analysis were comprised between 100 and 110 mg for each sample, the mass conversion degree (α) of reaction at a time t was estimated according to Equation 1:

$$\alpha = \frac{(w_i - w_0)}{(w_f - w_0)}$$

where w_0 , w_i , w_f are the initial, intermediate and final sample masses for complete conversion of TiSi_2 in TiN , Si_3N_4 and $\text{Ni}_4\text{Ti}_4\text{Si}_7$ phases. XRD experiments in Bragg-Brentano geometry were performed with a Bruker D8 Advance diffractometer using a $\text{Cu K}\alpha$ radiation fitted with a one-dimensional position sensitive silicon strip detector (Bruker, Linxeye). XRD patterns were recorded using a step size of 0.01° for 2θ range $10\text{-}90^\circ$ and a counting time of 0.3 second per step. Sections of nitrided grains were prepared using ion polishing system (Cross Polisher JEOL Ltd.). These sections were observed with a FEI Quanta 400 FEG scanning

electron microscope whereas the chemical composition was analyzed by EDX (EDAX Genesis XM4), operated at 5 kV (interaction volume of roughly 150 nm wide in this condition).

4. Results and discussion

4.1 Effect of nickel addition on TiSi_2 nitridation

The results regarding the effects of nickel content in $(1-x) \text{TiSi}_2 + x \text{Ni}$ mixtures for $0.000 \leq x \leq 0.250$ by step of 0.025 or 0.050 on the overall conversion at 1100°C are reported in Table 1. It is clearly indicated that the addition of nickel investigated results in higher contents of TiN and Si_3N_4 nitrides than obtained from pure TiSi_2 powders. However, the overall mass conversion increases with nickel content up to $x = 0.150$. The conversion is decreased when higher nickel fractions are added to the TiSi_2 powder because large quantity of this metal hinders the gas diffusion and the nitridation of TiSi_2 . Moreover, the phases composing the compacts after nitridation depend on the nickel content. It is found from Table 1 that for nickel contents lower than 0.100, nitridation is uncompleted as remaining TiSi_2 and free silicon are detected; the ternary compound $\text{Ni}_4\text{Ti}_4\text{Si}_7$ being however formed. In these cases, the nickel content is insufficient to rapidly and completely convert the powder. When the nickel content is larger than 0.150, TiSi_2 and free silicon are no more detected but undesired nickel silicides are obtained. In this situation, it is confirmed that the nickel quantity is too high. Consequently, the appropriate quantity of nickel x is comprised between 0.100 and 0.150. X-ray diffraction experiments of the samples with $x = 0.100$ (Figure 7), $x = 0.125$ or $x = 0.150$ showed that the final phase composition is TiN , $\alpha\text{-Si}_3\text{N}_4$, $\beta\text{-Si}_3\text{N}_4$ and $\text{Ni}_4\text{Ti}_4\text{Si}_7$. The morphologies of the resulting nitrided compacts are similar for these three compositions. On the micrographies of the mixture with $x = 0.125$ (Figure 8), one can note the homogeneity of the phases dispersion, the absence of cracks and the smallness of the produced grains. The starting porosity was close to 50% whereas the final porosity is of about 25%, the volumes of

the compacts being unchanged. The results of the nitridation experiments agree partially with the calculated thermodynamic equilibriums exposed herein for $x = 0.025$; 0.100 ; 0.150 and 0.250 (Figures 3,4,5). Indeed, in all cases, the thermodynamic calculations for an excess of nitrogen predict the formation of TiN , Si_3N_4 and Ni_5Si_2 . The experimentally formed phases do not strictly correspond to this calculated state. From Table 1, one note that the nitrides are effectively generated as expected but Ni_5Si_2 is in no case formed. This partial unreliability of the calculations is attributable to the fact that the conversion reaction occurs only at the interface between TiSi_2 and the gaseous nitrogen. Nickel particles are located at the surface of the TiSi_2 grains and despite the milling stage; these metal particles are unlikely dispersed in a perfectly homogeneous way. The consequence is a partial improvement of the conversion for weak nickel contents ($x \leq 0.075$) with remaining TiSi_2 and free silicon. In contrast, these two last phases are no more detected for high nickel contents ($x \geq 0.175$) but NiSi and NiSi_2 are generated. In this case, the nickel particles may be locally concentrated and promote the formation of large amounts of liquid which solidified in forming these nickel silicides and maybe of others undetected phases. The hypothesis is confirmed by the decrease of the conversion rate when increasing nickel content because of the filling of the porosities by the liquid inducing a limitation of gaseous diffusion preventing the conversion. For $0.100 \leq x \leq 0.150$, the final phases are TiN , Si_3N_4 and $\text{Ni}_4\text{Ti}_4\text{Si}_7$. This promising equilibrium state was expected from thermodynamic considerations and it is experimentally generated with conversion percentages of at least 90%. $\text{Ni}_4\text{Ti}_4\text{Si}_7$ stabilization is improved because of the probable gradual reduction of the interactions between this ternary phase and nitrogen due to the protective effect induced by the surrounding nitrides crust. The kinetics and the conversion mechanism were subsequently examined for the three retained compositions $(1-x)\text{TiSi}_2 + x\text{Ni}$ corresponding to $x = 0.100$; 0.125 and 0.150 .

4.2 Thermogravimetric analysis and reaction mechanism

The thermogravimetric curves of two samples of pure TiSi_2 powders ($d_{50} = 1.4$ and $4.5 \mu\text{m}$) and three samples of $(1-x) \text{TiSi}_2 + x \text{Ni}$ mixtures ($x = 0.100$; 0.125 and 0.150) reacting with N_2 were measured at 1100°C until durations close to 20 hours. According to Equation 1 and Reaction 1, the relationship between the conversion degree and the time is shown in Figure 9. In all cases, the conversion percentages tended to increase with rising reaction duration. The achieved degrees of conversion after 17 hours were found equal to 88.7%, 92.8% and 92.9% for the $(1-x) \text{TiSi}_2 + x \text{Ni}$ mixtures with $x = 0.100$; 0.125 and 0.150 , respectively. The corresponding percentages for pure TiSi_2 powders are significantly lower as equal to 43.3% and 51.9% for $d_{50} = 4.5 \mu\text{m}$ and $1.4 \mu\text{m}$, respectively. The kinetic models of the solid-state reactions are basically divided into three main categories: 1) models in which the reaction rate is determined by nucleation and growth; 2) the models in which the controlling step is the diffusion of reactants or diffusional models; 3) models in which the administered mechanism is the chemical reaction at the interphase of the reactant-product [46]. The most appropriate kinetic models are listed in Table 2. Fitting the experimental data to the corresponding kinetic model functions $g(\alpha) = k.t$ involves nucleation-growth, chemical reaction and diffusion. So, the best fitting k coefficient represents the specific reaction mechanism. In this study, the three $(1-x) \text{TiSi}_2 + x \text{Ni}$ mixtures ($x = 0.100$; 0.125 and 0.150) were found to have the same three successive stages during nitridation. For the first stage, the best fitting function was identified as the A2 nucleation-growth model with a weak weight gain. For the second stage, the best fitting function was also the A2 nucleation-growth model with a strong increase of the weight gain for a short duration. The third stage was found to be described by the D3 three-dimensional diffusion model for a spherical symmetry. Data fitting of the selected model functions for the three stages is shown in Figure 10. This method provides a reaction mechanism for the whole process of TiN , Si_3N_4 and $\text{Ni}_4\text{Ti}_4\text{Si}_7$ synthesis. The nitridation reaction of a TiSi_2 powder activated by addition of nickel can be summarized by three successive stages associated to three specific kinetics coefficients k_1 , k_2 and k_3 as follows:

- 1) TiSi_2 and nickel powders react and form $\text{Ni}_4\text{Ti}_4\text{Si}_7$. This ternary phase begins to react with nitrogen and generates TiN , Si_3N_4 and a low quantity of a ternary liquid with a weak weight gain (step ① in Figure 9 and Figure 11-a);
- 2) the increase of the liquid quantity promotes the rapid nucleation and growth of TiN and Si_3N_4 grains up to forming a nitrided layer (step ② in Figure 9 and Figure 11-a);

3) the gas transfer through the product layer implies a diffusion limitation until full nitridation (step ③ in Figure 9 and Figure 11-a).

This mechanism is evidenced by the micrograph of the Figure 11-b since it shows a large grain exhibiting the phases sequence $\text{TiN}+\text{Si}_3\text{N}_4/(\text{Si},\text{Ni},\text{Ti})\text{Liquid}/\text{Ni}_4\text{Ti}_4\text{Si}_7/\text{TiSi}_2$. In a previous study, we reported the assumption that the nitridation of pure TiSi_2 powders with close mean grain size can be described by two successive steps. During the first step, only TiN is formed and generates a layer that behaves as a diffusion barrier limiting silicon nitridation. The second step occurs after significantly longer exposures and involves a sluggish nitridation of silicon at the center of the TiSi_2 grain thanks to the formation of opened porosities generated by the Kirkendall effect [29]. This mechanism slows down the progress of the reaction so that the nitridation kinetics are very low and the conversion is inadequate. In the present case, the addition of metallic nickel to TiSi_2 powder modified the nitridation mechanism to such an extent that full nitridation is substantially reached. The efficiency of nickel addition on the conversion is clearly demonstrated. The kinetic deceleration for conversion percentages larger than 80% visible in Figure 9 is presumably induced by an enlargement of the necks between the grains and by the reduction of the porosity which limit all the more the gaseous diffusion. When comparing the slopes of the curves corresponding to the k kinetic coefficients, the highest values are found with $x = 0.125$ for the three stages ($k_1^{0.125} = 0.18 \text{ h}^{-1}$, $k_2^{0.125} = 0.53 \text{ h}^{-1}$, $k_3^{0.125} = 0.022 \text{ h}^{-1}$) (Figure 10). The k coefficients for $x = 0.150$ have intermediate values with $k_1^{0.150} = 0.15 \text{ h}^{-1}$, $k_2^{0.150} = 0.41 \text{ h}^{-1}$, $k_3^{0.150} = 0.024 \text{ h}^{-1}$. The k values of the two first stages for $x = 0.100$ are close to an half of the values for $x = 0.125$ and 0.150 i.e. $k_1^{0.100} = 0.087 \text{ h}^{-1}$, $k_2^{0.100} = 0.27 \text{ h}^{-1}$. The $k_3^{0.100}$ coefficient of the third stage for $x = 0.100$ is equal to 0.020 h^{-1} , this value is close but slightly lowest than the corresponding coefficients for $x = 0.125$ and 0.150 i.e. $k_3^{0.125} = 0.022 \text{ h}^{-1}$ and $k_3^{0.150} = 0.024 \text{ h}^{-1}$. Finally, the global highest kinetic is attributed for $x = 0.125$. An intermediate but close global kinetic is obtained with $x = 0.150$ and the slowest global kinetic is associated to $x = 0.100$. The slowest kinetics measured for this composition can be justified by a lower

content of nickel which consequently generates a lower quantity of liquid. The quantity of liquid blatantly influences the conversion kinetic. On the other hand, the kinetic progression of the conversion for $x = 0.150$ is close but slightly slower than the one with $x = 0.125$ despite a more elevated nickel content. This behavior is probably induced by the formation of a larger content of the $\text{Ni}_4\text{Ti}_4\text{Si}_7$ compound. However, the conversion percentages move towards comparable values of about 90%. When considering the theoretical volume increase during the nitridation (Table 1), the most interesting composition corresponds to $x = 0.100$ as the corresponding volume gain is the most elevated. Despite a slower conversion kinetic, this composition is the most interesting to obtain the highest densification effect. TiSi_2 -metal samples containing 10 mol.% of iron or cobalt instead of nickel were also prepared and heat treated at 1100°C by applying a similar protocol. It was then found the formation of $\text{Fe}_4\text{Ti}_4\text{Si}_7$ or $\text{Co}_4\text{Ti}_4\text{Si}_7$, TiN and free silicon as shown in Figure 12. The weight gains are lower than pure TiSi_2 . The weak conversion rates obtained in these cases are justified by the absence of liquid phases in these systems at 1100°C . So, the nitridation conversion is not enhanced and the ternary phase layers formed at the surface of the grains limit the nitrides formation. This demonstrates the essential role played by the formation of a liquid phase.

5. Conclusion

TiSi_2 powders blended with nickel were nitrided in a stream of pure nitrogen at 1100°C to investigate the catalytic effect of metal addition on the direct nitridation. As expected from thermodynamic considerations, the nitridation of TiSi_2 in the presence of metallic nickel generated the TiN , Si_3N_4 and $\text{Ni}_4\text{Ti}_4\text{Si}_7$ phases for the $(1-x) \text{TiSi}_2 + x \text{Ni}$ mixtures with $0.100 \leq x \leq 0.150$. The conversion percentage is greatly enhanced within this composition range as the final values are around 90%. It is suggested that the presence of liquid phase formed during the reaction is at the origin of the kinetic increase of the conversion. The whole reaction process includes three main stages. During the first stage, the weight gain is negligible as the

controlling mechanism is the reaction between TiSi_2 and nickel grains to form the $\text{Ni}_4\text{Ti}_4\text{Si}_7$ compound. A very weak weight gain is however measured corresponding to a nucleation and growth limiting process resulting from the induction of the nitrides growth instigating the formation of the liquid phase. During the second stage, the nucleation and growth process of the nitrides phases is the limiting process controlling mechanism with an impressive increase of the kinetic. A deceleration of the kinetic coefficients is measured during the third stage because the conversion is limited by the three-dimensional gas transfer process due to the nitride layer thickening.

Acknowledgement

This work has been performed within the frame of the training of Brice Ripoche from ESIREM, Dijon, France.

References

- [1] A. Atkinson, P.J. Leatt, A.J. Mouslon, The role of nitrogen flow into the nitriding compact in the production of reaction-sintered silicon nitride, *Proc. Brit. Ceram. Soc.* 22 (1973) 253-274.
- [2] H.M. Jennings, M.H. Richman, Structure, formation mechanisms and kinetics of reaction-bonded silicon nitride, *J. Mater. Sci.* 11(11) (1976) 2087-2098.
- [3] H.M. Jennings, On reactions between silicon and nitrogen Part 1 Mechanisms, *J. Mater. Sci.* 18(4) (1983) 951-967.
- [4] H. Kim, C.H. Kim, The effects of second-component gases on the transport properties of silicon nitriding atmosphere, *J. Mater. Sci. Letters*, 3 (1984) 199-200.
- [5] C.E. Bouldin, E.A. Stern, M.S. Donley, T.G. Stoebe, Iron impurities in Si_3N_4 processing, *J. Mater. Sci.* 20 (1985) 1807-1810.
- [6] H. Kim, C.H. Kim, The influence of the various transport properties of the nitriding atmosphere on the formation of reaction-bonded Si_3N_4 , *J. Mater. Sci.* 20 (1985) 149-156.
- [7] W.R. Moser, D.S. Briere, R. Correia, G.A. Rossetti, Kinetics of iron-promoted silicon nitridation, *J. Mater. Res.* 1 (1986) 797-802.
- [8] H.M. Jennings, B.J. Dalglish, P.L. Pratt, Reactions between silicon and nitrogen: Part 2. Microstructure, *J. Mater. Sci.* 23(7) (1988) 2573-2583.
- [9] G.A. Rossetti Jr, R.P. Denkwicz Jr, Kinetic interpretation of α - and β - Si_3N_4 formation from oxide-free high-purity silicon powder, *J. Mater. Sci.* 24(9) (1989) 3081-3086.
- [10] A. Varma, R.G. Pigeon, A.E. Miller, Kinetics of α - and β - Si_3N_4 formation from oxide-free high-purity Si powder, *J. Mater. Sci.* 26(16) (1991) 4541-4544.
- [11] R.G. Pigeon, A. Varma, Some chemical reaction engineering considerations in the synthesis of silicon nitride, *Chem. Eng. Sci.* 47(9-11) (1992) 2585-2590.
- [12] R.G. Pigeon, A. Varma, A.E. Miller, Some factors influencing the formation of reaction-bonded silicon nitride, *J. Mater. Sci.* 28 (1993) 1919-1936.
- [13] B.W. Sheldon, J.R. Rankin, J.S. Haggerty, Formation of reaction-bonded silicon nitride from silane-derived silicon powders: nucleation and growth mechanisms, *J. Am. Ceram. Soc.* 78(6) (1995) 1624-1632.
- [14] M. Maalmi, A. Varma, Intrinsic nitridation kinetics of high-purity silicon powder, *AIChE Journal*, 42 (1996) 3477-3483.
- [15] M. Maalmi, A. Varma, W.C. Strieder, Reaction-bonded silicon nitride synthesis: experiments and model, *Chem. Eng. Sci.* 53(4) (1998) 679-689.
- [16] F.W. Chang, T.H. Liou, F.M. Tsai, The nitridation kinetics of silicon powder compacts, *Thermochimica Acta*, 354 (2000) 71-80.

- [17] M.K. Kim, J.K. Park, H.W. Lee, S. Kang, A cyclic process for the nitridation of Si powder, *Mater. Sci. Eng. A* 408(1-2) (2005) 85-91.
- [18] F. Wang, X. Qin, G. Jin, X. Guo, Temperature-controlled synthesis of Si_3N_4 nanomaterials via direct nitridation of Si powders, *Physica*, E42 (2010) 2033-2035.
- [19] A.J. Moulson, Reaction-bonded silicon nitride: its formation and properties, *J. Mater. Sci.* 14 (1979) 1017-1051.
- [20] R.T. Bhatt, R.E. Phillips, Thermal effects on the mechanical properties of SiC fibre reinforced reaction-bonded silicon nitride matrix composites, *J. Mater. Sci.* 25 (1990) 3401-3407.
- [21] I. Brokhin, A. Fridman, The preparation and investigation of some titanium nitride-molybdenum cermets, *Sov. Powder Metall. Met. Ceram.* 4 (7) (1965) 545-550.
- [22] Y.H. Hwang, C.I. Lin, Preparation of titanium nitride from direct nitridation of titanium, *J. Chem. Eng. Jpn.* 31 (2) (1998) 214-219.
- [23] Z.A. Munir, J.B. Holt, The combustion synthesis of refractory nitrides: Part 1. Theoretical analysis, *J. Mater. Sci.* 22(2) (1987) 710-714.
- [24] H. Rode, V. Hlavacek, Detailed kinetics of titanium nitride synthesis, *AIChE J.* 41(2) (1995) 377-388.
- [25] A. Pivkina, P.J. van der Put, Yu. Frolov, J. Schoonman, Reaction-bonded titanium nitride ceramics, *J. Eur. Ceram. Soc.* 16(1) (1996) 35-42.
- [26] A.S. Bolokang, M.J. Phasha, Formation of titanium nitride produced from nanocrystalline titanium powder under nitrogen atmosphere, *Int. J. Refract. Met. Hard Mater.* 28(5) (2010) 610-615.
- [27] C. Li, X. Lv, J. Chen, X. Liu, C. Bai, Kinetics of titanium nitride synthesized with Ti and N_2 , *Int. J. Refract. Met. Hard Mater.* 52 (2015) 165-170.
- [28] M. Ade, J. Haußelt, Electroconductive ceramic composites with low-to-zero shrinkage during sintering, *J. Eur. Ceram. Soc.* 23 (2003) 1979-1986.
- [29] J. Roger, L. Maillé, M.A. Dourges, Isothermal nitridation kinetics of TiSi_2 powders, *J. Solid State Chem.* 212 (2014) 134-140.
- [30] M. Wittmer, Self-aligned diffusion barrier by nitridation of TiSi_2 , *Appl. Phys. Lett.* 52 (1988) 1573-1575.
- [31] A. Kamgar, F.A. Baiocchi, A.B. Emerson, T.T. Sheng, M.J. Vasile, R.W. Haynes, Self-aligned TiN barrier formation by rapid thermal nitridation of TiSi_2 in ammonia, *J. Appl. Phys.* 66 (1989) 2395-2401.
- [32] J. Perez-Rigueiro, C. Jimenez, L. Vazquez, R. Perez-Casero, J.M. Martinez-Duart, Nitridation of TiSi_2 thin films by rapid thermal processing, *Surf. Coat. Technol.* 80 (1996) 72-75.

- [33] J.C. Han, G.Q. Chen, S.Y. Du, J.V. Wood, Synthesis of Si_3N_4 -TiN-SiC composites by combustion reaction under high nitrogen pressures, *J. Eur. Ceram. Soc.* 20 (2000) 927-932.
- [34] K.G. Grigorov, G.I. Grigorov, M. Stoyanova, J.L. Vignes, J.P. Langeron, P. Denjean, J. Perriere, Diffusion of Silicon in Titanium Nitride Films. Efficiency of TiN Barrier Layers, *Appl. Phys. A55* (1992) 502-504.
- [35] S.M. Boyer, A.J. Moulson, A mechanism for the nitridation of Fe-contaminated silicon, *J. Mater. Sci.* 13(8) (1978) 1637-1646.
- [36] S.S. Lin, Comparative studies of metal additives on the nitridation of silicon, *J. Am. Ceram. Soc.* 60(1-2) (1977) 78-81.
- [37] V. Pavarajarn, S. Kimura, Catalytic effects of metals on direct nitridation of silicon, *J. Am. Ceram. Soc.* 84(8) (2001) 1669-1674.
- [38] M. Mitomo, Effect of Fe and Al additions on nitridation of silicon, *J. Mater. Sci.* 12(2) (1977) 273-276.
- [39] C.G. Cofer, J.A. Lewis, Chromium catalysed silicon nitridation, *J. Mater. Sci.* 29(22) (1994) 5880-5886.
- [40] V. Pavarajarn, T. Vongthavorn, P. Praserttham, Enhancement of direct nitridation of silicon by common metals in silicon nitride processing, *Ceram. Inter.* 33(4) (2007) 675-680.
- [41] J. Huang, S. Zhang, Z. Huang, M. Fang, Y. Liu, K. Chen, Co-catalyzed nitridation of silicon and in-situ growth of α - Si_3N_4 nanorods, *Ceram. Inter.* B40(7) (2014) 11063-11070.
- [42] J.O. Andersson, T. Helander, L. Höglund, P.F. Shi, B. Sundman, Thermo-Calc and DICTRA, Computational tools for materials science, *Calphad*, 26 (2002) 273-312.
- [43] S. Sambasivan, W.T. Petuskey, Phase chemistry in the Ti-Si-N system : Thermochemical review with phase stability diagrams, *J. Mater. Res.* 9 (1994) 2362-2369.
- [44] T. Tokunaga, K. Hashima, H. Ohtani, M. Hasebe, Thermodynamic analysis of the Ni-Si-Ti system using thermochemical properties determined from ab initio calculations, *Mater. Trans.* 45(5) (2004) 1507-1514.
- [45] T. Tokunaga, K. Nishio, H. Ohtani, M. Hasebe, Thermodynamic assessment of the Ni-Si system by incorporating ab initio energetic calculations into the CALPHAD approach, *Calphad*, 27(2) (2003) 161-168.
- [46] J. Hancock, J. Sharp, Method of comparing solid-state kinetic data and its application to the decomposition of kaolinite, brucite, and BaCO_3 , *J. Am. Ceram. Soc.* 55 (2) (1972) 74-77.

Figure 1: Equilibrium diagrams simulated at 1100°C with ThermoCalc software [42]:
a) N-Ti-Si [43] and b) Ni-Ti-Si [44].

Figure 2: Ni-Si phases diagram simulated with ThermoCalc software [42,45].

Figure 3: Thermodynamic stability of $(1-x) \text{TiSi}_2 + x \text{Ni}$ ($x = 0.025; 0.100; 0.150$ and 0.250) versus nitrogen content system at 1100°C simulated with ThermoCalc software [42-44]
 $(\text{N4T4S7} = \text{Ni}_4\text{Ti}_4\text{Si}_7, \text{Ni2SiD} = \text{Ni}_2\text{Si}-\delta, \text{Ni2SiT} = \text{Ni}_2\text{Si}-\theta)$

Figure 7: X-ray powder diffraction pattern of the 0.900 TiSi_2 + 0.100 Ni composition nitrided at 1100°C for 40 hours

Figure 8: Backscattered electrons images of the 0.875 TiSi_2 + 0.125 Ni composition treated at 1100°C for 40 hours

Figure 9: Mass conversion rate versus time at 1100°C of pure TiSi_2 powder [29] in comparison to $(1-x)\text{TiSi}_2 + x\text{Ni}$ mixtures with $x = 0.100$; 0.125 and 0.150 . (fits of the three successive stages with the A_2 and D_3 models plotted in dot lines)

Figure 10: $g(\alpha) = k.t$ plots and linear regressions of the compositions $(1-x)\text{TiSi}_2 + x\text{Ni}$ with $x = 0.100$; 0.125 and 0.150 at 1100°C : a) stage ①: A_2 model, b) stage ②: A_2 model, and c) stage ③: D_3 model

Figure 11: Nitridation of a TiSi_2 grain in presence of Ni:
a) proposed conversion mechanism with four successive steps and
b) backscattered electrons image of a large grain in the sample $0.900 \text{ TiSi}_2 + 0.100 \text{ Ni}$ treated at 1100°C

Figure 12: Backscattered electrons images of a TiSi_2 powder heat treated at 1100°C in nitrogen with addition of: a) Fe and b) Co

Table 1: Nickel contents, theoretical volume gains, mass conversion and phases composition of the $(1-x) \text{TiSi}_2 + x \text{Ni}$ ($0.000 \leq x \leq 0.250$) compact samples heat treated at 1100°C for 40 hours

Nickel content (x)	Theoretical volume gain (%)	Mass conversion α (%)	Phases detection from XRD and EDS analysis					
			(detected: + ; undetected: -)					
			TiN	Si_3N_4	Si	TiSi_2	NiSi/ NiSi ₂	$\text{Ni}_4\text{Ti}_4\text{Si}_7$
0.000 [29]	58.7	48.8	+	+	+	+		
0.025	56.8	77.5	+	+	+	+	-	+
0.050	54.9	77.5	+	+	+	+	-	+
0.075	82.9	87.0	+	+	-	+	-	+
0.100	50.8	90.2	+	+	-	-	-	+
0.125	48.6	96.0	+	+	-	-	-	+
0.150	46.4	96.3	+	+	-	-	-	+
0.175	44.0	88.8	+	+	-	-	+	-
0.200	41.5	68.9	+	+	-	-	+	-
0.250	36.2	53.1	+	+	-	-	+	-

Table 2: Common kinetic models [46]

Kinetic models		$g(\alpha)$	Code
Nucleation-growth	Random nucleation and subsequent growth	$[-\ln(1-\alpha)]^{1/2} = k.t$	A2
	Random nucleation and subsequent growth	$[-\ln(1-\alpha)]^{1/3} = k.t$	A3
	Random nucleation and subsequent growth	$[-\ln(1-\alpha)]^{1/4} = k.t$	A4
Chemical reaction	Phase boundary reaction, cylindrical symmetry	$1 - (1-\alpha)^{1/2} = k.t$	R2
	Phase boundary reaction, spherical symmetry	$1 - (1-\alpha)^{1/3} = k.t$	R3
Diffusion model	One-dimensional diffusion	$\alpha^2 = k.t$	D1
	Two-dimensional diffusion, cylindrical symmetry	$[(1-\alpha).\ln(1-\alpha)] + \alpha = k.t$	D2
	Three-dimensional diffusion, spherical symmetry	$[1 - (1-\alpha)^{1/3}]^2 = k.t$	D3
	Three-dimensional diffusion, cylindrical symmetry	$1 - (2/3). \alpha - (1-\alpha)^{2/3} = k.t$	D4