Magnetic Properties of Some Rare Earth Aluminum Alloys

B. Barbara, C. Bècle, R. Lemaire, and R. Pauthenet

Citation: *J. Appl. Phys.* **39**, 1084 (1968); doi: 10.1063/1.1656172

View online: <http://dx.doi.org/10.1063/1.1656172>

View Table of Contents: <http://jap.aip.org/resource/1/JAPIAU/v39/i2>

Published by the [American Institute of Physics](#).

Additional information on J. Appl. Phys.

Journal Homepage: <http://jap.aip.org/>

Journal Information: http://jap.aip.org/about/about_the_journal

Top downloads: http://jap.aip.org/features/most_downloaded

Information for Authors: <http://jap.aip.org/authors>

ADVERTISEMENT

The advertisement banner for AIP Advances features a light green background with abstract, flowing, wavy lines in a darker green shade. The text 'AIPAdvances' is prominently displayed in the center, with 'AIP' in blue and 'Advances' in green. To the right of the text is a circular seal with the text 'Now Indexed in Thomson Reuters Databases'. Below the main text, there is a blue horizontal bar with the text 'Explore AIP's open access journal:' in white. To the right of this bar is a list of three bullet points: '• Rapid publication', '• Article-level metrics', and '• Post-publication rating and commenting'.

AIPAdvances

Now Indexed in Thomson Reuters Databases

Explore AIP's open access journal:

- Rapid publication
- Article-level metrics
- Post-publication rating and commenting

Intermetallic Compounds

R. STREET AND J. E. GOLDMAN, *Chairmen*

Magnetic Properties of Some Rare Earth-Aluminum Alloys

B. BARBARA, C. BÈCLE, R. LEMAIRE, AND R. PAUTHENET

Laboratoire d'Electrostatique et de Physique du Métal, C.N.R.S., Grenoble, France

The RAl alloys are orthorhombic; the structure can be described with a trigonal motif similar to a half-cell of CsCl. The R_2Al_3 alloys are tetragonal. The magnetic properties of the RAl alloys, where R is any rare earth from Ce to Tm, and those of the R_2Al_3 alloys, with R passing from Gd to Tm, have been measured in fields up to 25 kOe or 60 kOe and at temperatures between 1.4° and 400°K. The RAl alloys, with R from Pr to Tb, order antiferromagnetically at temperature between 20°K (PrAl) and 72°K (TbAl); the magnetic configuration of TbAl has been studied by neutron diffraction; HoAl is ferromagnetic with a Curie point at 26°K; DyAl, ErAl and TmAl exhibit metamagnetism at 4.2°K. Gd_2Al_3 is ferromagnetic with a Curie point at 282°K, close to that of Gd; Dy_2Al_3 shows an antiferromagnetic transition near 20°K in zero field and metamagnetic behavior induced by a field below this temperature; its Curie point is 76°K. All compounds exhibit a Curie-Weiss behavior above their transition points, with a paramagnetic moment close to that of the corresponding free tripositive rare earth ions.

The rare earth-aluminum phase diagrams¹ generally present five intermetallic compounds. The magnetic properties of the RA_2 ,² RA_3 ³ and some RAl compounds⁴ (where R is a rare earth metal) have already been determined. We have concerned ourselves with those of the RAl and R_2Al_3 compounds. They are pre-

studied only compounds which were found free from all other phases by x-ray examination. The magnetizations are measured using the extraction method, in fields H up to 25 kOe or 60 kOe and at temperatures ranging from 1.4° to 400°K.

RAI COMPOUNDS

The crystal structures of the RAl compounds belong to two types. The first type,⁵ CeAl, crystallizes in the

TABLE I. Experimental results for RAl compounds.

Compound	θ_C (°K)	θ_N (°K)	θ_P (°K)	M_e (μ_B/R)
CeAl		9	4	2.34
PrAl		20	11	3.58
NdAl		29	-4	3.53
GdAl		42	64	8.15
TbAl		72	10	10.0
DyAl		20	25	10.6
HoAl	26		17	10.7
ErAl		13	23	9.65
TmAl		10	-2	7.70

FIG. 1. Reciprocal susceptibility-temperature behavior of GdAl, TbAl, and DyAl. Magnetization-field strength behavior of DyAl at 4.2°K.

pared by melting the required proportions of the elements in a high-frequency levitation furnace. We have

¹ K. H. J. Buschow and J. H. N. Van Vucht, *Z. Metallk.* **57**, 162 (1966).

² H. J. Williams, J. H. Wernick, E. A. Nesbitt, and R. Sherwood, *J. Phys. Soc. Japan, Suppl. B-1* **17**, 91 (1962).

³ K. H. J. Buschow and J. F. Fast, *Z. Phys. Chem.* **50**, 1 (1966).

⁴ F. Kissel and W. E. Wallace, *J. Less-Common Metals* **11**, 417 (1966).

Cmcm group; LaAl and slowly cooled PrAl is isotypic with it. The second type,⁶ DyAl, crystallizes in the *Pbcm* group; the compounds from neodymium up to thulium, with the exception of europium, are isotypic with it. These structures are both formed from the same motifs: aluminum chains and trigonal prisms showing similarities with a half-cell of CsCl; only the arrangement of these motifs differs. The magnetic results obtained with CeAl and PrAl are in good agreement with those

⁵ C. Bècle and R. Lemaire, *Compt. Rend.* **264B**, 887 (1967).

⁶ C. Bècle and R. Lemaire, *Compt. Rend.* **264B**, 543 (1967).

reported by Kissel and Wallace,⁴ however, the paramagnetic Curie points θ_p that we have determined are higher. NdAl, GdAl and TbAl are antiferromagnetic. DyAl exhibits a metamagnetic behavior below its order temperature (Fig. 1). HoAl has a spontaneous magnetization at low temperature, however at 4.2°K a field of 70 kOe is not sufficient to saturate it, a law of approach in $1/H$ gives a saturation magnetization of $6.2 \mu_B/\text{HoAl}$. ErAl and TmAl are metamagnetic below the Néel temperature. At high temperature all the compounds follow a Curie-Weiss law. The effective moment M_e in Bohr magnetons, deduced from the Curie constant is in good agreement with that of the free R^{3+} ion (Table I). For numerous compounds, at low temperature, the variation of the reciprocal susceptibility no longer follows a Curie-Weiss law (Fig. 1). This difference cannot be attributed to crystal field effects, since it is maximum for GdAl. But neutron diffraction studies⁷ of TbAl show at 110°K a short-range magnetic order. Below the Néel temperature of TbAl the antiferromagnetic arrangement of the moments is not collinear; it is closely related to the existence of the trigonal prisms formed by the rare earth atoms. In fact it results from a compromise between anisotropic exchange interactions and a magnetocrystalline anisotropy exerted along two different axes.

FIG. 2. Magnetization-field strength behavior at 4.2° and 20°K and temperature variation of magnetization at 24 kOe of Tb_3Al_2 .

⁷ C. Bècle, R. Lemaire, and E. Parthé (to be published).

TABLE II. Experimental results for R_3Al_2 compounds.

Compound	θ_C (°K)	θ_N (°K)	θ_t (°K)	θ_p (°K)	M_e (μ_B/R)
Gd_3Al_2	282			285	8.2
Tb_3Al_2	203		11	125	9.6
Dy_3Al_2	76		20	31	10.8
Ho_3Al_2	33		11	10	10.9
Er_3Al_2		9		-3	9.6
Tm_3Al_2		3		-10	7.8

R_3Al_2 COMPOUNDS

The R_3Al_2 compounds crystallize⁸ in the $P4_3nm$ group, their structure can be generated from rare earth chains and aluminum centered trigonal rare earth prisms. Gd_3Al_2 is ferromagnetic with a Curie temperature θ_C at 282°K, its absolute saturation magnetization is $7.1 \mu_B$ per gadolinium atom. Tb_3Al_2 exhibits a ferromagnetic behavior from a transition temperature $\theta_t=10^\circ\text{K}$ to the Curie point (203°K), below 10°K the magnetization decreases rapidly if measured in fields lower than 30 kOe; in the higher fields, it is practically the same as it is at 20°K (Fig. 2). Dy_3Al_2 and Ho_3Al_2 have magnetic behavior similar to that of Tb_3Al_2 . The temperature of the different transitions are listed in Table II. Er_3Al_2 and Tm_3Al_2 have Néel temperature at 9° and 3°K, respectively below these temperatures they are metamagnetic. At high temperature, all compounds follow a Curie-Weiss law; the effective magnetic moment of the rare earth atoms corresponds to that of the trippositive free ion. Neutron-diffraction studies of Tb_3Al_2 showed that, from 10° to 203°K, the terbium magnetic moments are parallel to one another; in a zero field, at 4.2°K, the moments are no longer collinear and exhibit a resultant which is not nil. As a conclusion, Gd_3Al_2 is typically ferromagnetic but when the rare earth spin decreases and that its orbital moment increases, the compounds exhibit an antiferromagnetic behavior more and more accentuated at low temperature and which seems due to crystal-field effects.

⁸ N. C. Baenziger and J. J. Hegenbarth, Acta Cryst. 17, 620 (1964).