



**HAL**  
open science

## Superconducting cryo-magnets processed by Spark Plasma Sintering and Texturing

Jacques Noudem, Louis Dupont, Pierre Bernstein, Richard Retoux, Geoffroy Chevallier, Claude Estournès, Kévin Berger, Muralidhar Miryala, Masato Murakami

► **To cite this version:**

Jacques Noudem, Louis Dupont, Pierre Bernstein, Richard Retoux, Geoffroy Chevallier, et al.. Superconducting cryo-magnets processed by Spark Plasma Sintering and Texturing. 4th International Workshop on Spark Plasma Sintering, May 2018, Cagliari, Italy. pp.185-199, 10.1016/B978-0-12-817744-0.00008-8 . hal-01798373

**HAL Id: hal-01798373**

**<https://hal.science/hal-01798373>**

Submitted on 23 May 2018

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



4th International Workshop  
on Spark Plasma Sintering  
23 – 25 May 2018, Cagliari, Italy

**Superconducting cryo-magnets processed by  
Spark Plasma Sintering and Texturing**

J. Noudem<sup>1\*</sup>, L. Dupont<sup>1</sup>, P. Bernstein<sup>1</sup>, R. Retoux<sup>1</sup>, G. Chevallier<sup>2</sup>, C. Estournès<sup>2</sup>, K. Berger<sup>3</sup>, M. Muralidhar<sup>4</sup> and M. Murakami<sup>4</sup>

<sup>1</sup>CRISMAT, CNRS/ENSICAEN-UNICAEN, 6 bd Maréchal Juin, 14050 CAEN Cedex 4, France

<sup>2</sup> Université de Toulouse, CIRIMAT, CNRS-INPT-UPS, Université Paul-Sabatier, 118 route de Narbonne, F-31062 Toulouse cedex 9, France

<sup>3</sup>GREEN, University of Lorraine, BP 70239, 54506 Vandoeuvre-lès-Nancy Cedex, France

<sup>4</sup>Superconducting Materials Laboratory, Graduate School of Science & Engineering, Shibaura Institute of Technology, 3-7-5 Toyosu, Koto-ku, Tokyo 135-8548, Japan

*\*E-mail address: [jacques.noudem@ensicaen.fr](mailto:jacques.noudem@ensicaen.fr)*

In this paper, three main superconducting compounds have been studied:

- Dense oxide  $\text{YBa}_2\text{Cu}_3\text{O}_7$  was prepared by Spark Plasma Sintering (SPS) in air using tungsten carbide mould under high pressure. The superconducting properties were measured and discussed.
- The SPS was modified with the aim of obtaining textured lamellar compounds with the  $\text{Bi}_2\text{Ca}_2\text{Sr}_2\text{CuO}_8$  superconductor ceramics. The new process is referred to as “Spark Plasma Texturing” (SPT). During SPT, the bulk material can freely deform itself. As a result, inter-grain preferential crystallographic orientation is favoured.
- The last study was focused on preparation by SPS of magnesium diboride ( $\text{MgB}_2$ ) cryo-magnets. The role of the starting powder on the superconducting properties of  $\text{MgB}_2$  has been investigated. Three sets of bulk  $\text{MgB}_2$  material were processed from: (i) commercial available powder, (ii) a mixture of Mg metal and amorphous B using a single-step solid-state reaction process and (iii) a mixture of amorphous boron coated with carbon and Mg metal. The samples were prepared by varying different SPS processing conditions such as temperature, dwell time, applied pressure and atmosphere. The structural, microstructures of the samples were investigated by SEM and TEM and correlated to their superconducting properties. The best sample was prepared at 850°C. At 20 K its critical current density was  $J_c = 500 \text{ kA/cm}^2$ . Herein, we demonstrate that  $\text{MgB}_2$  makes an excellent cryo-magnet, maintaining 3,9 T at 20 K at the surface of a 20 mm diameter disk.

**Keywords**

SPS in air, Spark Plasma Texturing (SPT), superconducting cryo-magnets