Structure of single sheet iron oxides produced from surfactant interlayered green rusts

Zhou Yin, Knud Dideriksen, Mustapha Abdelmoula, Christian Ruby, Frederick Marc Michel, Morten Jannik Bjerrum, Christian Hansen

► To cite this version:

Zhou Yin, Knud Dideriksen, Mustapha Abdelmoula, Christian Ruby, Frederick Marc Michel, et al.. Structure of single sheet iron oxides produced from surfactant interlayered green rusts. Applied Clay Science, 2019, 170, pp.86-96. 10.1016/j.clay.2019.01.009 . hal-02000218

HAL Id: hal-02000218

<https://hal.science/hal-02000218>

Submitted on 6 Oct 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Structure of Single Sheet Iron Oxides Produced from 2 Surfactant interlayered Green Rusts

Zhou Yin^{*1}, Knud Dideriksen², Mustapha Abdelmoula³, Christian Ruby³, F. Marc Michel⁴, Morten
Jannik Bjerrum², Hans Christian B. Hansen¹

¹Dept. of Plant and Environmental Sciences, University of Copenhagen, Denmark

²Dept. of Chemistry, University of Copenhagen, Denmark

³Laboratoire de Chimie Physique et Microbiologie pour l'Environnement - LCPME UMR 7564 CNRS-Université de
Lorraine, France.

⁴Dept. of Geosciences, Virginia Tech, Blacksburg, Virginia 24061-0420, United States

GRAPHIC ABSTRACT

ABSTRACT

Two-dimensional (2D) single sheets formed via delamination of Layered Double Hydroxides (LDHs) are of great interest because of their high reactive surface area and unique chemical and physical properties. Here, we focus on formation and properties of single sheet iron oxides (SSI) that may be used as sorbents, electro- and photocatalysts. We have developed a method for synthesis of SSIs from the Fe^{II}-Fe^{III} LDH (green rust, GR) using surfactant intercalation of preformed GR, followed by aerial oxidation and delamination. The average height of the SSIs from AFM is 1 nm and the lateral dimensions vary from 20 to 100 nm. Selected area electron diffraction of SSI shows a hexagonal pattern with $d \approx 0.28$ nm consistent with diffraction along [001] in metal hydroxide layers in GR. Chemical analysis, thermogravimetric analysis and X-ray photoelectron spectra analysis lead to SSI formula of FeO_{0.82}(OH)_{1.38}·0.7H₂O. For the oxidized, surfactant-intercalated GR and SSI, pair distribution functions from high energy X-ray scattering data demonstrate that two distinct interatomic distances exist for first neighbor Fe-Fe pairs, somewhat similar to the patterns for ferrihydrite and goethite, but in contrast to the single Fe-Fe distance

observed for the unoxidized GR. A modeled structural rearrangement with vertical displacements of Fe atoms from the original hydroxide layer to form a trilayer with Fe polyhedra that are linked via both corner- and edge-sharing produced a PDF in agreement with the main features of the measured pattern. Mössbauer spectroscopy shows that the SSI orders magnetically at 130 K and that the hyperfine parameters are distinct for SSI and different from other iron oxides such as ferrihydrite and feroxyhite. The synthesis pathway via GR_{C12} is critical for formation of SSI as the “insulating” C12 interlayer hinders bonding and polymerization between Fe^{III}-O/OH octahedra across interlayers during oxidation and thus only structural reorganisations of single brucitic Fe^{II}-Fe^{III} hydroxide layers can take place during oxidation with no possibilities for nucleation of iron oxides with higher crystallinity like goethite. The strong increase of single- and double coordinated O/OH groups in the SSI compared with the parent GRs predicts a high reactivity of SSI as surface complexation sorbents.

KEYWORDS: Green Rust, Delamination, Two-dimensional iron oxide, Pair distribution function

1. INTRODUCTION

Layered Double Hydroxides (LDHs) consist of positively charged, brucite-type metal hydroxide layers separated by interlayers of charge compensating anions and water molecules.¹ Belonging to the hydrotalcite group, they can be represented by the general formula $[M_a^{II}{}_{1-x}M_b^{III}{}_x(OH)_2]^{x+}[A^{n-}{}_{x/n}]^{x-} \cdot mH_2O$, where M_a^{II} and M_b^{III} represent di- and trivalent metal cations in the metal hydroxide layer (x is in the range from 0.2 to 0.33), and A^{n-} is an n -valent anion in the interlayer.² Recently, the successful preparation of two-dimensional (2D) single sheets of a thickness of 1 nm via delamination of LDHs have been described.^{3,4} These nanosheets, which are made of single or a few stacked layers derived from the parent LDH, exhibit specific chemical and physical properties, including superior electron mobility and high catalytic activity. Due to their heritage from LDHs, the chemical composition and properties of the parent LDHs are thought to be crucial for the chemical and physical properties of the delaminated material.

The synthesis of these nanosheets can be generally classified into two approaches: “bottom-up” and “top-down”. The “bottom-up” method involves direct synthesis of the nanosheet materials from solution by creating a physical/chemical micro-environment for oriented growth of single-layered LDH nanosheets.⁵ The “top-down” approach is the more widely developed method, which is based

on delamination of the LDHs. However, since the charge density of LDHs is significantly higher than that of most other lamellar solids, it has been difficult to achieve full delamination.⁶ Key factors that control the success of delamination are the electrostatic attraction on the metal hydroxide layers of the LDHs and property of the solvent used for delamination. To weaken the electrostatic attraction between the layers, several attempts have been taken to enlarge the interlayer distance by exchanging inorganic interlayer anions with larger organic anionic molecules. By intercalation of surfactants, amino acids or other long-chain carboxylates, the electrostatic attraction between the positively charged metal hydroxide layers and the anionic interlayers is weakened, and subsequent delamination of LDHs is facilitated. After ion exchange, delamination in formamide, butanol, water and other reagents have been reported as a result of osmotic swelling of LDHs caused by the interaction between the interlayer anions and the solvents.^{4,7,8}

Structural investigations of exfoliated LDH products demonstrate that the local coordination around the divalent and trivalent metal atoms remains unchanged after delamination. For example, Leroux et al.⁹ demonstrated by use of X-ray absorption fine structure (EXAFS) that the local ordering around Zn atoms in Zn-Al LDHs was unaffected by delamination. More recently, Funnell et al.¹⁰ reported the atomic-scale structure of a Zn-Al LDHs by reverse Monte Carlo (RMC) modeling of pair distribution function (PDF) analysis. The refined data showed that after delamination, the coordination of Zn and Al atoms were similar to that found in the metal hydroxide layers of Zn-Al LDHs, whereas there was no evidence of strong Zn-Al ordering within the delaminated material.¹¹

The focus in this work is on the delaminated products formed from so-called green rusts. Green rusts (GRs) are Fe^{II}-Fe^{III} LDH compounds with the chemical formula $[\text{Fe}^{\text{II}}_{(1-x)} \text{Fe}^{\text{III}}_x(\text{OH})_2]^{x+} \cdot [(x/n) \text{A}^{n-}, y \text{H}_2\text{O}]^{x-}$. In our previous work, we have used the “top-down” approach to produce 2D single sheets of Fe^{III} hydroxides (SSI) from directly synthesized dodecanoate intercalated GRs.^{12,13} In this approach, the dodecanoate intercalated GR is oxidized by O₂ to its corresponding Fe^{III} form before delamination via dispersion in alkaline solutions.¹⁸ Compared to other Fe^{III} hydroxide particles, SSI with a thickness of 1 nm has the highest possible surface area to volume ratio ideally with all Fe-OH groups in the structure exposed to the solution. Because of their high specific surface area, SSIs have interesting uses as sorbents (e.g. for phosphate)¹³ and for electro-catalysts.^{14,15} A first structural study has shown that SSI has a thickness of 1 nm and lateral sizes ranging from 100 to 200 nm¹². The authors claimed that the trioctahedral structure of the parent Fe^{II}-Fe^{III} hydroxide

89 layers were kept intact during oxidation and thus inherited by the delaminated material. However,
90 whether this is true is still questionable. In GR, the Fe atoms are octahedrally coordinated to O
91 atoms and the octahedra are linked via edge-sharing to form planar layers. In such a structure, all
92 nearest neighbor Fe-Fe distances are almost the same.¹⁶ However, if the local atomic structure
93 changes during delamination, other types of Fe^{III} hydroxides such as feroxyhite, ferrihydrite,
94 lepidocrocite and goethite might form. In fact, these Fe^{III} hydroxides are readily formed by
95 oxidation of GRs,^{17,18}. However, these compounds have Fe^{III} octahedra linked by both corner and
96 edge-sharing and consequently features several distances for nearest neighbor Fe-Fe pairs.^{19–21}
97 Therefore, determination of Fe-Fe distances in the SSI could reveal if brucite-like layers in the GR
98 is kept intact during delamination, or reorganization has taken place. In the present investigation,
99 we have been using a variety of techniques including X-ray diffraction, infrared spectroscopy,
100 Mössbauer spectroscopy, X-ray photoelectron spectra (XPS), and high-energy X-ray scattering to
101 obtain further insight on the structure of the SSI phase. Pair distribution function (PDF) analysis of
102 X-ray scattering data is a powerful technique to gain structural information for phases lacking long-
103 range order. The PDF methods have been applied previously to bulk GR²² and have given a useful
104 insight on metal coordination.

105 In this study, we have developed a robust method to synthesize SSI via a dodecanoate
106 intercalated GR (GR_{C12}) formed by ion exchange of chloride-GR. Subsequently, the GR_{C12} has been
107 oxidized by air followed by alkaline delamination to produce SSI. The main objective of this work
108 has been to investigate the structure of the resulting SSI and in particular to test if the brucite-like
109 Fe^{II}-Fe^{III} hydroxide layers in GR are kept intact during oxidation and subsequent delamination. The
110 results have important implications for the use of SSI as sorbents and catalyst materials.

111 2. EXPERIMENTAL SECTION

112 2.1 Materials

113 All chemicals were of analytical grade and used without further purification. Glycine
114 (NH₂CH₂COOH, 99%), dodecanoic acid (C₁₂H₂₄O₂, 99%), iron chloride (FeCl₃, 99%), sodium
115 chloride (NaCl, 99%) and sodium hydroxide (NaOH, 98%), iron nitrate nonahydrate
116 (Fe(NO₃)₃·9H₂O, 99%) were all obtained from Sigma-Aldrich. A 0.5 M FeCl₂ stock solution was
117 prepared according to the method described by Koch and Hansen²³. Thus, 3.5 g Fe⁰ powder (10 μm,
118 EMSURE, 99%) was mixed with 100 ml of 1 M HCl (O₂ free) in a glass beaker and magnetically

119 stirred in a 70 °C water bath until no further H₂ was formed. Milli-Q water (18.2 MΩ) and ultrapure
120 argon (purity > 99.99%) were used throughout the experimental work. A pH-stat (Metrohm, 719
121 Titrino) was employed for all synthesis to maintain pH at 8.0 via 1 M NaOH injection. All synthesis
122 was conducted in an anoxic chamber (95% N₂ and 5% H₂, Coy Laboratories, Michigan, USA).

123 2.2 Synthesis

124 Single sheet iron oxides (SSI) were synthesized by anion exchanging chloride intercalated GR
125 (GR_{Cl}) with dodecanoate, followed by solid state oxidation and delamination in 0.1 M NaOH.
126 Synthesis of GR_{Cl} followed the method described by Yin²⁴ comprising co-precipitation of Fe²⁺ and
127 Fe³⁺ in the presence of glycine at a constant pH of 8.0 (±0.1). First, 400 ml of 70 mM glycine and
128 245 mM of NaCl solutions were added to a synthesis glass flask followed by capping the flask with
129 a rubber septum and providing in- and outlets for flushing Ar gas (30 ml min⁻¹) to avoid oxidation
130 by air. The synthesis suspension was stirred using a magnetic bar (300 rpm). After adjustment of pH
131 of the solution to 8.0 by dosing 1 M NaOH, 20 ml 0.5 M FeCl₂ stock solution was injected into the
132 synthesis flask and pH re-adjusted to 8.0 using the pH-stat followed by injection of 15 ml 0.1 M
133 FeCl₃ to the synthesis flask at a rate of 10 ml min⁻¹ while pH was controlled at 8.0 using the pH-
134 stat. After synthesis, the precipitated GR_{Cl} was transferred to the anoxic chamber and separated by
135 centrifugation at 4000 g for 5 min.

136 The GR_{Cl} product was transferred to a glass flask containing 200 ml Ar-bubbled 0.1 M
137 dodecanoate dissolved in 40 % ethanol (pH adjusted to 8 using 1 M NaOH). The solution was
138 stirred (300 rpm) for three hours to exchange chloride with dodecanoate. The resulting GR_{C12} was
139 further washed with Ar-bubbled ethanol and water. Then, the GR_{C12} was separated by centrifugation
140 at 8000 g for 5 min, frozen as a suspension at -80°C overnight and transferred to a freeze-dryer
141 (Christ Loc-I) at -40 °C. Finally, the dry GR_{C12} was ground by mortar and pestle and oxidized by O₂
142 by exposing a thin layer (1 mm) of the powder to air for two days. The color changed gradually
143 from green via brown to final brownish-orange.

144 The so obtained oxidized GR_{C12} (1 g) was mixed with 1 L of 0.1 M NaOH in a polyethylene
145 beaker and stirred (300 rpm) for 24 h to achieve delamination. Then the suspension was rinsed to
146 remove dodecanoate by centrifugation at 8000 g for 5 min and re-dispersion of the precipitate in
147 ethanol. This washing and centrifugation procedure was repeated three times followed by a final
148 washing with water, centrifugation and re-dispersion in 20 ml Milli-Q water. Part of the suspension

149 was frozen and freeze-dried to obtain powders for later characterization. Approximately 0.63 g SSI
150 was obtained from 1 g of oxidized GR_{C12}.

151 For reference, feroxyhite was synthesized by the method of Pollard.²⁵ Two-line ferrihydrite and
152 goethite were synthesized using the methods given in Cornell and Schwertmann.¹⁶

153 2.3 Characterization

154 Powder X-ray diffraction (XRD) data were collected using a Siemens D5000 X-ray
155 diffractometer using monochromated Co-K α radiation (wavelength $\lambda = 1.79 \text{ \AA}$) and a scanning rate
156 of $0.6^\circ 2\theta \text{ min}^{-1}$ in the 2θ range $1.5\text{--}80^\circ$. Suspensions of washed and centrifuged GR materials were
157 added as concentrated droplets onto glass plates, dried in the anoxic chamber for 12 h, and
158 subsequently wetted with glycerol to avoid oxidation. For oxidized GR_{C12} and for SSI the dried
159 materials were scanned as unoriented dry packed powders.

160 Crystallite sizes D were estimated from basal reflections (c-axis) by use of the Scherrer
161 equation:²⁶

$$162 \quad D = 0.9\lambda / (\beta \cos\theta)$$

163 where λ is the wavelength of the X-rays, θ is the diffraction angle of the basal reflection, and β is
164 the peak broadening at the half-maximum intensity.

165 The Fe^{II} and Fe^{III} contents in GRs were quantified by a modified phenanthroline method.²⁴ For
166 determination of the Fe^{III} content in the SSI, 50 mg of dry SSI was dissolved completely in 50 ml 6
167 M HCl at 80°C , followed by iron determination by atomic absorption spectroscopy.
168 Thermogravimetric analysis (TGA) was performed using a Pyris 1 DSC, with a heating rate of $20^\circ\text{C min}^{-1}$
169 over a temperature range of 24 to 700°C . Twenty mg of the sample was analyzed in a
170 nitrogen atmosphere.

171 Fourier-transform infrared (FTIR) spectra were recorded by scanning tablets (diameter 13 mm) of
172 samples (0.5 mg) mixed with dry KBr (IR spectroscopy grade, Sigma-Aldrich, 300 mg) using a
173 Fourier transform infrared spectrometer (Perkin–Elmer Frontier TM) in the range of 400 to 4000
174 cm^{-1} (4 cm^{-1} resolution, 3 scans).

175 Atomic force microscopy (AFM) images were acquired in tapping mode using a Si tip cantilever
176 (Olympus AC240) on a mica surface with a force constant of 5 N m^{-1} . Samples were prepared by

177 running droplets of diluted SSI-suspensions over the mica surface and taking the AFM
178 measurements immediately after blow-drying with nitrogen. Transmission electron microscopy
179 (TEM) images were obtained with a Phillips CM-20 with an accelerating voltage of 200 kV. The
180 SSI powder was first redispersed in ethanol, and droplets of the suspension were dried on a
181 microscope copper grid.

182 Elemental analysis and XPS were performed using a Kratos Axis Ultra X-ray photoelectron
183 spectrometer equipped with a monochromated Al α X-ray ($h\nu = 1486.6$ eV) operated at 120 W. The
184 base pressure in the analytical chamber was about 10^{-9} mbar. Spectra were collected at normal take-
185 off angle (90°), and the analysis area was $700 \times 300 \mu\text{m}^2$. Wide scans were recorded using an
186 analyzer pass energy of 160 eV and narrow scans using a pass energy of 20 eV. Survey (broad scan)
187 spectra were collected at 160 eV pass energy and all high-resolution scans (i.e. C1s) were done at
188 20 eV pass energy. The instrument geometry allows about 0.75 eV energy resolution at 20 eV pass
189 energy. Charge compensation was adjusted for each sample to obtain the narrowest linewidths. All
190 binding energies are referenced to adventitious C (284.6 eV). The XPS spectra were fitted using the
191 X-version 2.2.11 software.

192 Mössbauer spectroscopy was performed at 297 K, 130 K, 77 K, 35 K, and 9 K with a constant
193 acceleration Mössbauer spectrometer and 512 multichannel analyzer (Halder Electronic GmbH), and
194 a 50 mCi source of ^{57}Co in Rh maintained at RT. Data were obtained from appropriate amounts (10
195 mg of Fe per cm^2) of solid samples to get optimal experimental conditions. In order to avoid the
196 condensation of oxygen and water on the walls of the cryostat, samples were quickly transferred
197 under inert He atmosphere to a cold-head cryostat manufactured by Advanced Research Systems,
198 equipped with vibration isolation stand and developed in the LCPME Laboratory. Mössbauer
199 spectra were collected in transmission mode. The 50 mCi source of ^{57}Co in Rh matrix was
200 maintained at room temperature and mounted at end of a Mössbauer velocity transducer. The
201 spectrometer was calibrated with a 25 μm foil of α -Fe at RT. Analysis of the Mössbauer spectra
202 consisted of least-square fitting of data with a combination of two-peak quadrupole components
203 (doublets) and, when present, six-peak magnetic hyperfine components (sextets). The Lorentzian-
204 shape lines model from Recoil software (Ottawa University) could not be used to fit experimental
205 data that give rise to the broadened spectra induced by the structural disorder. Therefore, another
206 model based on the Voigt-based fitting method of Rancourt and Ping²⁷ for quadrupole splitting
207 distribution (QSDs) and magnetic hyperfine fields (HFDs), was used to fit spectra.

For high energy X-ray scattering, all samples were loaded in glass capillary tubes and sealed with paraffin. For oxidation-sensitive GR samples, sample loading was performed inside the anaerobic chamber and transferred out of the chamber 4 days before measurement. Previous tests of the sample preparation showed that even rapidly oxidizing samples remain intact in the tubes for at least a week.²⁸ High energy X-ray scattering measurements were performed at beamline 11 ID-B at the Advanced Photon Source, Argonne National Laboratory, using an X-ray energy of 58.66 keV ($\lambda = 0.2113 \text{ \AA}$). The samples were placed approximately 15 cm from a 40 cm by 40 cm, amorphous Si 2D detector. The geometry of the setup was calibrated from the measurement of a CeO_2 standard using the software Fit2D.^{29,30} Fit2D was also used to convert the 2D data into polarization corrected 1D data, from which PDFs was obtained with the software PDFGETX2.^{31,32} Data treatment with PDFGETX2 included subtraction of the background measured for an empty glass capillary tube, subtraction of incoherent scattering, normalization by the average atomic scattering cross-section of the sample, and a correction for non-linear detector efficiency.³³ In the treatment, the composition of the material was assumed to be: GR_{Cl} : $\text{Fe}_4\text{O}_{12}\text{H}_{16}\text{Cl}$; $\text{GR}_{\text{Cl}2}$ and oxidized $\text{GR}_{\text{Cl}2}$: $\text{Fe}(\text{OH})_3\text{C}_4$; SSI; feroxyhite, ferrihydrite: $\text{Fe}(\text{OH})_3$; and goethite: FeOOH . Fourier transform of the $Q[S(Q)^{-1}]$ was performed using a maximum Q value of $24 \text{ \AA}^{-1}$ to yield the reduced pair distribution function, $G(r)$.

Modeling of PDFs was performed with the software PDFgui,³⁴ which is routinely used to fit crystalline material, and DiffPy-CMI, which allows more versatile modeling of PDFs including those for molecules.³⁵ This approach has been applied to simulate the PDFs of a wide variety of nanosystems.^{36,37} In the modeling, an instrumental dampening of 0.047 was refined from the measurement of a well crystalline synthetic goethite using the structure from Hoppe.³⁸ During the PDFgui modeling, the parameters were fitted in the order: 1) scaling, 2) size of spherical coherently scattering as well as correlated atomic movement, δ_2 , 3) unit cell dimensions and 4) atomic isotropic displacement parameters. For the DiffPy-CMI modeling, a minimum Q of $1 \text{ \AA}^{-1}$ was assumed and the value for correlated atomic movement, δ_2 , was set to 3.

3 RESULTS AND DISCUSSION

3.1 Layer Structure of SSI

The powder X-ray diffraction patterns of GR_{Cl} and $\text{GR}_{\text{Cl}2}$ demonstrate the formation of well-crystallized LDH with the hydrotalcite-type structure (Figure 1).^{39,40} The GR_{Cl} is characterized by marked basal reflections, resulting in a basal spacing of GR_{Cl} of $(d_{001} + 2 \times d_{002} + 3 \times d_{003})/3 = 0.79$

238 nm, in agreement with the literature.^{41,42} The additional peak (Figure 1, trace 1 insert)
239 corresponding to a distance of 0.26 nm of the third intense peak of GR_{Cl}. No reflections due to
240 impurities of other Fe^{III} hydroxides are observed. The chemical analysis of GR_{Cl} shows that the
241 Fe^{II}/Fe^{III} ratio in GR_{Cl} is 2.99 ± 0.065, in agreement with the ideal ratio of 3. The exchange of
242 chloride with dodecanoate leads to expansion of the basal spacing from 0.79 nm to 3.5 nm, in line
243 with previous observations of GR_{C12},^{13,43} demonstrating successful intercalation of dodecanoate.
244 The disappearance of the diffraction peak at 0.79 nm after ion-exchange in GR_{C12} demonstrates an
245 almost 100 % conversion of GR_{Cl} to GR_{C12}. By use of the Scherrer equation, the average thickness
246 of the GR_{Cl} crystallite in the c-direction is estimated at 17.2 nm corresponding to 17.2/0.79 or ~22
247 layers in the crystallite. For GR_{C12} a similar calculation gives 77.4/3.5 or ~22 layers, demonstrating
248 that the number of metal hydroxide layers are maintained in the GR during ion-exchange. The
249 GR_{C12} shows a series of up to 5th orders of intense basal reflections, reflecting an equidistant
250 thickness of the layers.

251 After oxidation of the freeze-dried GR_{C12}, the XRD diffraction pattern of oxGR_{C12} is similar to
252 the original GR_{C12}, but it shows a slightly lower first-order basal reflection (3.52 nm reduced to 3.34
253 nm), broadening of diffraction peaks. The decreased basal spacing is due to the smaller ionic radii
254 of Fe^{III} compared with Fe^{II}, and higher charge density of the metal hydroxide sheets after oxidation,
255 causing higher electrostatic forces across layers and interlayers. After exposure of the oxidized
256 GR_{C12} to sodium hydroxide, the disappearance of basal reflections from the XRD patterns shows
257 that the layered structure has disintegrated and that delamination has taken place. It is hypothesized
258 that delamination takes place due to deprotonation of hydroxyl groups in the Fe^{III} hydroxide layers
259 resulting in repulsion and subsequent elimination of interlayer dodecanoate anions.¹² XRD
260 confirmed that the final products did not contain measurable contents of lepidocrocite, magnetite,
261 hematite, feroxyhite or akaganéite impurities. However, small amounts of impurities of goethite
262 could be observed (Figure 1, trace 4 insert).

263

264 **Figure 1.** XRD diffractograms of GR_{Cl} (profile 1), GR_{Cl2} (profile 2), oxidized GR_{Cl2} (profile 3),
 265 and SSI (profile 4). The inserts show a detail of XRD diffraction pattern in the range 10 to 80°.

266 Figure 2 shows the FT-IR spectra for oxidized GR_{Cl2} and SSI. The FT-IR spectrum of oxidized
 267 GR_{Cl2} shows vibrations from C-H (2975-2850 cm⁻¹) and COO⁻ (1567-1547 cm⁻¹) that disappear in
 268 the SSI, demonstrating that the dodecanoate is effectively removed during delamination.^{21,22} The
 269 strong band at ~3425 cm⁻¹ is assigned to the O-H stretching vibration of surface OH groups, which
 270 is similar to that of other delaminated LDHs.^{44,45} A broad absorption of SSI in the low-frequency
 271 region is assigned to OH bending bands at 1641 cm⁻¹, 1045 cm⁻¹, and 885 cm⁻¹, and Fe-O stretching
 272 band at 567 cm⁻¹. None of the two strong O-H stretching vibration (938 cm⁻¹, 892 cm⁻¹) for
 273 goethite^{46,47} can be observed in the spectra of SSI (Figure S1), demonstrating that the signal of the
 274 minor goethite impurity detected by powder XRD in the SSI is below the IR detection limit (≤ 1 %).

275

276 **Figure 2.** FTIR spectra of (a) oxidized GR_{C12} and (b) SSI

277 3.2 Morphology

278 To visualize the morphology of the SSI, TEM and AFM were used. The AFM images (Figure 3),
 279 show two-dimensional platy objects with an average height of about 1 nm, which is more than two
 280 times the theoretical thickness of 0.48 nm for a single Fe^{II}-Fe^{III} hydroxide layer in GR.⁴⁸ The SSI is
 281 morphologically irregular, with lateral dimensions from 20 nm to 100 nm. Thus, they are
 282 dimensionally diminished in comparison with the parent GR crystallites,²⁴ indicating fracturing of
 283 metal hydroxide layers during the synthesis. TEM images of SSI show low-contrast, sheet-like
 284 objects with similar lateral dimensions as those seen in AFM (example in Figure 4). The SSI sheets
 285 are generally agglomerated but zones exist where the particles are well separated. Selected area
 286 electron diffraction (SAED) patterns exhibit hexagonally arranged spots, with the inner spots
 287 representing an atomic rows distance *d* value of ~0.28 nm. This distance is similar to the distance
 288 reported for GR_{SO4}.^{49–52} However, hexagonal patterns also exist for a range of other Fe oxides when
 289 observed perpendicular to the hexagonal oxygen packing.^{51,53}

Figure 3. (A) Tapping-mode AFM image of SSI deposited on mica. (B) Height profile of the SSI. Profiles 1, 2, 3 and 4 correspond to the trajectories shown in Figure 3 (A).

Figure 4. (A) TEM image of SSI nanoparticles. (B) The corresponding selected area electron diffraction (SAED) pattern of SSI. 2.8Å and 1.6 Å corresponds to the distance between atoms from {110} planes or {100} planes.

3.3 Chemical composition of the SSI

The iron content in the SSI is 54 ± 1 % (w/w, $n = 3$). TGA of the SSI shows a gradual weight loss from ambient temperature to 300°C , totaling 20.8 % (Figure S2). The weight of the SSI remains stable at higher temperatures. Attributing the weight loss to water degassing, we reach an approximate composition of $\text{FeO}_{0.82}(\text{OH})_{1.38} \cdot 0.7\text{H}_2\text{O}$ (Equations S1 - S4). Thus, oxidation of Fe^{II} to Fe^{III} in the parent GR ($\text{Fe}^{\text{II}}_{0.75}\text{Fe}^{\text{III}}_{0.25}(\text{OH})_2\text{Cl}_{0.25}$) causes an increase of Fe cationic charge which is compensated by substantial deprotonation. The determined ratio Fe:O is 2.88, close to the theoretical ratio of 3 for LDH layers.

To independently determine SSI composition and characterize the bonding of oxygen, SSI was examined by XPS. The wide scan spectrum of SSI exhibits peaks at binding energies of ~284, 529, 718, and 1070 eV which can be ascribed to C 1s, O 1s, Fe 2p, and Na (Figure S3). The small amount of Na most likely stems from the base used for delamination while the occurrence of C (< 5%) is attributed to the deposition of adventitious hydrocarbons. Figure 5 shows the O 1s spectrum of SSI. The O 1s spectrum has been fitted according to Mullet et al.⁵⁴ comprising three oxygen contributions: (i) lattice oxygen (O^{2-}) that binds to iron detected at 529.3 eV, (ii) oxygen in hydroxyl groups (OH^- , 530.8 eV) that binds to iron, and (iii) oxygen present in water (H_2O , 532.3 eV). The

occurrence of O^{2-} provides direct evidence for deprotonation of the hydroxyl groups when Fe^{II} is oxidized to Fe^{III} , as also reported by Génin et al.⁵⁵ and Huang et al.⁵⁶. Based on XPS, the ratio of O^{2-}/OH^- for SSI is 0.71 (Table S1), which is close to the ratio derived from chemical analysis (0.6) and for oxidized GR_{C12} (0.68)¹², but different from that of 2 line-ferrihydrite (1.34) from this study. The absence of Cl^- anions in SSI is significantly different from akaganéite, in which Cl^- ions is an essential element of the structure.⁴⁷

Figure 5. High-resolution oxygen 1s spectrum of SSI. The spectrum was fitted with three peaks: peak 1 corresponds to the oxygen in O^{2-} , peak 2 to oxygen in OH^- , and peak 3 to oxygen present in H_2O . The ratio of oxygen present in these three groups is $O^{2-}: OH^-: H_2O = 35: 50: 15$.

3.4 Local atomic arrangement

3.4.1 Mössbauer Spectroscopy

Mössbauer spectra of SSI were collected from RT to 9 K to enable thorough comparison of the results with those for other Fe^{III} hydroxides such as 2 line-ferrihydrite or feroxyhite (Figure 6). The spectrum for SSI at room temperature shows a quadrupole doublet which is fitted with a distribution of quadrupole splittings (Table 1). The isomer shift ($\delta = 0.31 \text{ mm s}^{-1}$) indicates the presence of Fe^{III}

330 of SSI is in an octahedral coordination environment⁵⁷. SSI at room temperature shows a
331 paramagnetic behavior with hyperfine parameters similar to those of oxidized GR.⁴⁰ However, the
332 hyperfine parameters at room temperature cannot be used to distinguish SSI from other Fe^{III}
333 hydroxides. Between 150 and 77 K, a significant change induced by the decrease of the thermal
334 relaxation is observed resulting in spectra with asymmetrically broadened sextets and a small
335 remaining paramagnetic doublet (2 to 4 %). Spectra show a gradual evolution from quadrupole
336 doublet and broad sextets to a superposition of six-line spectra at 130 K. Mössbauer spectrum
337 measured at 9 K consists of well-developed sextets, demonstrating that the SSI is magnetically
338 ordered at this temperature. The 9 K spectrum can be fitted by a distribution of three hyperfine
339 fields of 426 kOe, 467 kOe and 476 kOe (Table 1), indicating three distinct Fe^{III} coordination
340 environments in SSI.

341 Comparing the spectrum of SSI at low temperature (9K) with those of the reference Fe^{III}
342 hydroxides, one can see that the low-temperature measurements eliminate all relaxation effects. For
343 SSI the temperature for onset of magnetic ordering is at about 100 K, which is higher than for 2-line
344 ferrihydrite. The temperature for magnetic ordering for synthetic 2-line ferrihydrite ranges from 54
345 K for a sample with an average particle size of about 6 nm⁵⁸ to 45 K for a sample about 5 nm in
346 size⁵⁹ and 10.5 K for a sample 2.8 nm in size⁵⁹. At 9K, the external peaks for the 2-line ferrihydrite
347 are within the range defined by the vertical dashes corresponding to the external peak of SSI (Figure
348 6). Besides, the spectrum of 2-line ferrihydrite can be fitted by one hyperfine field with a much
349 smaller field strength (378 kOe) and asymmetrical broad lines resulting in weaker magnetic
350 interactions than for SSI in agreement with its lower magnetic ordering and poor crystallinity. In the
351 spectrum of synthetic feroxyhite, one of the fitted hyperfine fields in feroxyhite is distinctly higher
352 than 500 kOe, which is consistent with other studies⁶⁰⁻⁶⁴. On the contrary, the three fitted hyperfine
353 fields of SSI are all lower than 500 kOe. Therefore, the obtained SSI is different from ferrihydrite
354 and feroxyhite.

355 At room temperature, the Mössbauer spectra of bulk goethite consist of six Lorentzian shape
356 sharp or broadened peaks, depending on factors like crystal size, isomorphous substitution, the
357 content of excess water and vacancies.^{65,66} Goethite with particle sizes below about 15-20 nm are
358 superparamagnetic at room temperature, and goethite smaller than 8 nm are superparamagnetic at
359 77 K.⁶⁷ A survey of 256 soil goethite samples from various localities around the world indicated of
360 mean coherence lengths perpendicular to 110 of 15-20 nm, and thus goethite formed under ambient

361 conditions are usually superparamagnetic at room temperature.^{68,69} Murad⁷⁰ has shown that a
362 distinction of coexisting goethite from ferrihydrite or feroxyhite using Mössbauer spectra is
363 possible, due to the isomer shift ($\delta=0.37$ mm/s) and quadrupole splitting ($\Delta = -0.25$ mm/s) of
364 goethite at room temperature. Mørup et al⁷¹ have shown that the quadrupole coupling constant ϵ (Δ
365 $= 2\epsilon$) is -0.12 ± 0.02 mm/s at all temperature for both well crystallized and microcrystalline goethite.
366 For comparison, the spectrum of SSI does not show a sextet at room temperature, neither does it
367 show quadrupole splitting (Δ) of -0.25 mm/s at any temperature in any of the fitted components.
368 Therefore, the goethite impurity observed by XRD in the obtained SSI products could be under the
369 detection limit of Mössbauer spectroscopy.

371 **Figure 6.** Mössbauer spectra of SSI obtained at different temperatures together with 9 K spectra of
372 reference Fe^{III} hydroxides, 2-line ferrihydrite and feroxyhite. Data is represented by black dots and
373 lines are due to fitting (parameters in Table 1).

374 **Table 1.** Mössbauer parameters of SSI and other Fe^{III} hydroxides

Sample	T(K)	δ^a (mm/s)	Δ^b (mm/s)	H^c (kOe)	RA ^d (%)	Ref
SSI	300	0.31	0.73			This study
	130	0.46	0.89		20	
		0.48	0.19	219	80	
	77	0.45	0.36		3	
		0.25	0.08	405	11	
		0.5	-0.05	395	48	
		0.42	-0.06	185	38	
	35	0.3	0.08	445	33	
		0.53	-0.09	432	57	
		0.33	0.48	317	10	
	9	0.46	-0.01	426	53	
		0.42	0.15	467	23	
		0.47	-0.2	473	24	
Goethite	295	0.37	-0.26	380		72
	4.2	0.48	-0.25	506		
2-line ferrihydrite	300	0.24	0.79			This study
	9	0.46	-0.03	378		
6-line ferrihydrite	292	0.24	0.72	472		25
	4.2	0.5	-0.03	505	61	
		0.42	-0.04	471	39	
Feroxyhite	295	0.37	-0.06			This study
	10	0.38	0.05	492	37	
		0.51	-0.06	507	32	
		0.58	-0.14	471	31	
Oxidized GR _{Cl}	9	0.5	-0.07	497	33.5	40
		0.49	-0.1	469	28.5	
		0.50	-0.12	441	23.5	
		0.48	-0.06	401	14.6	

375 ^a Isomer shift relative to α -iron at room temperature; ^b Quadrupole splitting or shift; ^c Hyperfine
376 field; ^d relative abundance. The accuracy is ± 0.02 mm/s for the isomer shift δ and the quadrupole
377 splitting Δ and ± 5 kOe for the hyperfine field H .

378 3.4.2 High energy X-ray scattering

379 High energy X-ray scattering data were obtained to determine the local and medium range
380 structure with pair distribution function analysis. The $I(Q)$ and $G(r)$ for the materials examined are
381 shown in Figure 7 and the d values for main peaks, in Table S2.

382 The $I(Q)$ for the GR_{Cl} starting material displays peaks with positions very similar to those
383 reported for this phase.⁷³ For example, the peak at $Q = 0.79 \text{ \AA}^{-1}$ represents the $\sim 7.95 \text{ \AA}$ basal plane
384 distance in GR_{Cl} . For the first $10 \text{ \AA}$ of the corresponding PDF (Figure 7), peak positions and
385 intensities greatly resemble those reported for Na-bearing GR_{SO_4} .²² The first clear peak at $r \approx 2.10$
386 $\text{\AA}$ represents the first neighbor Fe-O pairs. The second peak at $r \approx 3.20 \text{ \AA}$ corresponds with second
387 neighbor Fe-Fe pairs in edge-sharing octahedra. Notably, the peak intensities decay considerably as
388 r -values increase above $10 \text{ \AA}$, showing that the material has coherent scattering domains of
389 relatively small average size (below the instrumental envelope of $\sim 8 \text{ nm}$). Also, the pattern largely
390 lacks the peaks for correlations of electron dense Fe-Fe atomic pairs across interlayers. Inspection
391 of the structure given for fougérite,⁷⁴ which is based on XRD of synthetic GR_{Cl} , and calculations of
392 the expected PDF with PDFGUI shows that correlations of Fe-Fe pairs across interlayers should
393 give rise to peaks at r values of $8.76 \text{ \AA}$ (coordination number, CN, of 6) and $9.32 \text{ \AA}$ (CN of 12). The
394 measured intensity for these peaks is much smaller than expected from calculations (Figure 6),
395 albeit basal plane reflections are clear in the XRD and the $I(Q)$. This indicates that the GR_{Cl}
396 synthesized here has small coherent scattering domain in general as well as turbostratic disorder.

397 Upon intercalation of dodecanoate, the basal plane reflection of GR_{Cl} at $Q = 0.79 \text{ \AA}^{-1}$ is markedly
398 decreased in intensity. Moreover, new peaks develop in the low Q region as would be expected
399 from a change in the interlayer distance between Fe^{II} - Fe^{III} hydroxide layers. In contrast, the PDF for
400 the C12 intercalated GR is practically identical to the pattern for GR_{Cl} , showing that the Fe^{II} - Fe^{III}
401 hydroxide layers remain intact during intercalation. The pattern for the GR_{C12} does show a slight
402 shifting of peaks to lower r values compared to GR_{Cl} . The magnitude of the shift increases with the
403 interatomic distance of the peak. Possibly, the shift arises from contraction of the structure in
404 response to slight oxidation of Fe^{II} .

405 Oxidation of the GR_{C12} produces substantial changes in the $I(Q)$, which now shows only three
406 broad peaks. The first peak varies in Q value from 1.40 to $1.47 \text{ \AA}^{-1}$ for the two samples, whereas the
407 last two peaks are invariably placed at 2.47 and $4.24 \text{ \AA}^{-1}$. Consistent with the broadness of the peaks,
408 the PDFs decay extensively with r and display only minor oscillations above $40 \text{ \AA}$ (Figure 7).
409 Inspection of the PDFs at $r < 10 \text{ \AA}$ shows that the oxidation step has produced significant changes

410 in local and medium range structure. The first peak, which has contributions largely from Fe-O
411 pairs, has decreased in r from ~ 2.10 Å to 1.98 Å, reflecting the smaller ionic radii of oxidized
412 Fe^{III} .⁷⁵ In addition, the patterns display two peaks at $r = 3.03$ Å and ~ 3.41 Å that largely represent
413 Fe-Fe atomic pairs (marked with dotted lines in Figure 7). This shows that the brucite-like
414 hydroxide layer with its equidistant, edge sharing Fe has restructured.

415 The positions of the two peaks for Fe-Fe in oxidized GR_{C12} resemble those for pairs with edge
416 and corner-sharing polyhedra in goethite (3.02 and 3.40 Å) and ferrihydrite (3.04 and 3.44 Å), but
417 differ from those for synthetic feroxyhite (3.00 and 3.50 Å, with a shoulder of significant intensity
418 at ~ 3.76 Å). At larger r values, the peaks for the oxidized GR_{C12} variably are similar to those for
419 ferrihydrite, feroxyhite and goethite. Fitting with PDFGui of ferrihydrite⁷⁶ and goethite structures³⁸
420 to the data yield a relatively good match (Figure 8A). However, the fitted ferrihydrite structure is
421 distorted with cell lengths of $a = 6.03$ and $c = 8.85$ Å and it contains only 25% occupancy for the
422 Fe_2 site. For the fitted goethite structure, the ~ 1 nm size of the coherent scattering domains is
423 exceptionally small. Given that the fitted phases are so unusual in structure, we find it unlikely that
424 they represent separate, distinct phases in the oxidized GR_{C12} samples. Rather, we interpret that the
425 oxidized GR_{C12} contains motifs that resemble those of ferrihydrite and goethite.

426 Ferrihydrite, feroxyhite and goethite are closely related in structure to GR, all containing layers
427 of edge-sharing octahedra. For the Fe^{III} hydroxides the octahedra are partially occupied by Fe, and
428 they are linked to the polyhedra of other layers via corner sharing. In addition, the formation of
429 ferrihydrite and goethite requires the only dislocation of a subset of the edge-sharing Fe octahedra
430 in the GR into its interlayers, and collapse of the interlayer to form the three-dimensional structures.
431 In combination with our observations, this suggests that oxidation of the GR_{C12} results in
432 dislocation of Fe into the interlayers produce a bi- or tri-layered Fe^{III} hydroxide, with Fe linkage
433 through both corner and edge-sharing polyhedra. Notably, a tri-layered model would have a
434 thickness of ~ 1 nm, similar to that observed for the SSI.

435 To probe this hypothesis, a model molecule based on a 4 nm wide Fe^{III} hydroxide layer with 121
436 Fe atoms based on the structure of $\text{Fe}(\text{OH})_2$ ⁷⁷ was fitted to the scattering data using DiffPy-CMI.
437 Two types of starting configurations were tested: one where all Fe resided initially in a single Fe^{III}
438 hydroxide layer (Figure 8B) and one where every fourth Fe atom was displaced 1.8 nm above or
439 below the Fe^{III} hydroxide layer in an ordered manner (Figure 8C). Subsequently, the structures were
440 fitted in 1000 iterations to minimize the misfit between calculated and measured PDFs using a least

square optimizer. During each iteration, four Fe atoms were selected randomly and their z-positions were allowed to change alongside the cell dimension of the model and two isotropic atomic displacement parameters for Fe and O. After this first fitting, O atoms were added within an ABAB packing scheme to the displaced Fe and another iterative fit was performed.

The calculated PDFs and an example of the resulting molecule are shown in Figure 8D. Considering the simplicity of the model, the calculated PDFs agree well with the overall peak positions and intensities that were measured. However, significant misfits exist. The peak at ~ 5.5 Å, for example, is particularly intense in the PDF for goethite. Here, it represents to a large degree second neighbor Fe-Fe distances across double chains of octahedrally coordinated Fe atoms that are twisted slightly with respect to each other. The relatively high intensity of the ~ 5.5 Å peak indicates that this coordination environment, or one resembling it, is likely to be present in the oxidized GR_{C12}. Such a coordination environment cannot be achieved with our modeling, given its rigid O lattice. Similarly, the Fe atoms are not always centered in the octahedra, which could have been achieved for a model allowing moderation of the O lattice. Furthermore, the model does not allow relaxation of Fe in x- or y- dimension, which could produce broadening of higher r peaks and a better match. Never the less, we conclude that a pattern resembling that measured for the oxidized GR_{C12} can be generated through dislocation of Fe up and down from the Fe^{III} hydroxide layer. Interestingly, up- and downward displacement of Fe is predicted to occur as a hole (a Fe^{III} defect) hops as a small polaron through a Fe^{II}(OH)₂ sheet, albeit at smaller length scales.⁷⁸

Upon delamination, the three I(Q) peaks of the oxidized GR_{C12} sharpen, the peak at 2.47 Å⁻¹ becomes asymmetric, and additional peaks appear at $Q = 2.82, 3.66$ and 4.00 Å⁻¹. These peaks coincide with major reflections for goethite. Consistent with the presence of a small amount of goethite (a couple of percents) (Fig. 1, profile 4), the PDF displays slight increases in the intensities at $r \approx 3.4, 5.4$ and 9.4 Å⁻¹, where peaks for the synthetic goethite are intense. Thus, we conclude that a slight amount of goethite was produced during the delamination step, but that structural changes to the tri-layer were small.

467

468 **Figure 7.** High energy X-ray scattering data for the samples. A) $I(Q)$ in the Q range with clear
 469 Bragg reflections ($Q = 2\pi/d$). B) $G(r)$ until 8 nm. The decay of the $G(r)$ at higher r for goethite
 470 values is caused largely by the instrumental resolution. C) Zoom of the $G(r)$. The red lines represent
 471 calculated patterns after fitting. Numbers above peaks refer to the CN of Fe-Fe atomic pairs within
 472 $\text{Fe}^{\text{II}}\text{-Fe}^{\text{III}}$ hydroxide layers (black) and in separate $\text{Fe}^{\text{II}}\text{-Fe}^{\text{III}}$ hydroxide layers (red and marked with
 473 an asterisk). The dotted lines mark the positions of peaks representing largely Fe-Fe pairs with edge
 474 and corner-sharing polyhedral position.

475

477

478 **Figure 8.** The results of the fitting to the PDF for the SSI. Patterns from fitting with A) PDFGui fit
 479 using ferrihydrite and goethite components; B) with DiffPY-CMI using a structure without initial
 480 displacement; C) with DiffPY-CMI using a structure with initial ordered displacement and D) An
 481 example molecule after fitting. Vacancies represent Fe that has moved more than 2 Å away from the
 482 original sheet.

483 3.4.3 Comparison with other ultrathin iron oxides

484 Not only SSI or ferrihydrite, but also other the iron oxides described above can be synthesized
 485 as very small particles, e.g. goethite⁷⁹, hematite,^{80,81} lepidocrocite⁸² and feroxyhite⁸³. Thus, thin
 486 goethite particles (6.8 nm thickness corresponding to [110] plane) has been synthesized as part of a
 487 goethite/graphene oxide composite⁷⁹. Similarly, 2D ultrathin feroxyhite (1.1 nm thick)⁸³ and 2D
 488 lepidocrocite⁸² (2~3 nm thick) has been synthesized. All of these nano-sized iron oxides show up
 489 their typical powder XRD traces demonstrating the presence of coherent scattering domains
 490 consisting of at least several atomic layers. In comparison, SSI is amorphous to powder XRD, while
 491 Fe atoms in the SSI sheets occur in an ordered and regular pattern. Mössbauer and X-ray scattering
 492 analysis indicates that the structure is distinct from other types of Fe^{III} hydroxide nanosheets
 493 however with some similarity to the structure of feroxyhite. In SSI, only edge and corner-sharing
 494 iron octahedra are observed. Interpretation of the feroxyhite structure has given rise to slightly
 495 different structural models^{84,85}, however, sharing the same features for the local atomic
 496 arrangements and comprising both face, edge and corner-sharing iron octahedra, which is consistent
 497 with the PDF observed for feroxyhite in the present study (Figure 7). Sestu et al.⁸⁴ proposed a mean
 498 structure of feroxyhite based on goethite by assuming that the local structures of feroxyhite contain
 499 the same structural elements as for goethite. Thus, conceptually the structures of SSI, goethite and
 500 feroxyhite are related and all may form from the brucitic Fe^{II}-Fe^{III} hydroxide layers of GR, but
 501 where SSI represents the least reorganization of iron octahedra in the parent brucitic sheet, while
 502 goethite represents the highest reorganization. The synthesis pathway for SSI via GR_{C12} and its
 503 oxidation product favors formation of SSI in preference of feroxyhite and goethite. Guyanaite⁸⁶, a
 504 precursor to goethite has been reported sharing similar SAED pattern and broad-peaked XRD
 505 pattern with SSI. Therefore, SSI may be as a possible metastable intermediate during the formation
 506 of feroxyhite and goethite. In GR_{C12} the brucitic Fe^{II}-Fe^{III} hydroxide layers are “insolated” from
 507 neighboring hydroxide layers by dodecanoate interlayers. Thus, during oxidation of the Fe^{II}-Fe^{III}
 508 hydroxide layers no bonding or polymerization can take place between Fe^{III}-O/OH octahedra

509 across the interlayers. Hence, structural alterations can only take place in single layers thus giving
510 rise to the formation of separate single layers. Thus, the presence of the dodecanoate interlayer
511 impedes nucleation of ferroxhyte or goethite during oxidation.

512 Compared with other nanosized Fe^{III} hydroxides, the delamination and structural alteration of
513 the brucitic metal hydroxide layers in GR to form SSI enhances the surface complexation
514 properties, as the surface hydroxyl groups change from being all triply coordinated at [001] faces to
515 singly, doubly and triply coordinated. Singly coordinated sites have a higher affinity for surface
516 complexation compared with triply coordinated sites in metal hydroxide layer in LDHs⁶⁵. In a
517 previous study, the SSI showed a high sorption capacity for phosphate compared with other LDHs
518 such as Mg-Fe LDH and iron oxides¹³. Therefore, SSI is a promising sorbent material. Besides, SSI
519 may show a high catalytic (e.g. at electro- or photocatalysis) capability compared with other nano-
520 sized iron oxides due to particular light absorption, electrical and semiconductor properties. The
521 assembly of SSI with other single sheet materials may also open a new approach to obtain
522 multifunctional nanocomposites.

523 4. CONCLUSIONS

524 Single sheet iron oxide was successfully obtained as a new two-dimensional material with a
525 structure different from other types of iron oxide. The lack of reflections in the SSI powder XRD
526 trace is consistent with a material lacking three-dimensional long-range order. AFM and TEM
527 showed that SSI consists of thin sheet-like objects with an average height of 1 nm, and with a well-
528 ordered hexagonal arrangement in the sheets with an atomic row distance of ~ 0.28 nm. Based on
529 the chemical and thermal analysis, the composition of SSI was $\text{FeO}_{0.82}(\text{OH})_{1.38} \cdot 0.7\text{H}_2\text{O}$.
530 Magnetically ordered Mössbauer spectra of SSI at 9K could be decomposed into three sextets, with
531 hyperfine parameters distinct from other iron oxides. SSI exhibited similar structural elements with
532 other iron oxides, but different in the detailed analysis. PDF analysis of high-energy X-ray
533 scattering data showed that oxidized GR_{C12} and SSI were characterized by two pairs of Fe-Fe
534 nearest neighbors demonstrating that the brucite-type structure of GR with only a single signal for
535 Fe-Fe nearest neighbors altered during oxidation. A model with a partial displacement of iron
536 octahedra out of the brucitic $\text{Fe}^{\text{II}}\text{-Fe}^{\text{III}}$ hydroxide layer results in a calculated PDF that agrees
537 reasonably with the measured pattern. Thus, during oxidation, the GR structure with entire edge-
538 sharing of iron octahedra transformed to SSI comprising both edge and corner-sharing octahedra.
539 The synthesis pathway via GR_{C12} is critical for the formation of SSI as the “insolating” C12

interlayer hinders bonding and polymerization between Fe^{III}-O/OH octahedra across interlayers during oxidation and thus only structural reorganizations of single brucitic Fe^{II}-Fe^{III} hydroxide layers can take place during oxidation.

AUTHOR INFORMATION

Corresponding Author

* E-mail: yin@plen.ku.dk

Notes

The authors declare no competing financial interest.

ACKNOWLEDGMENT

We are thankful for the kind assistance provided by Karina Chapman, Rick Spence, and Kevin A. Beyer at APS beamline 11 ID-B. Use of the Advanced Photon Source was supported by the U.S. Department of Energy, Office of Science, Office of Basic Energy Sciences, under Contract No. DE-AC02-06CH11357. The Danish Council for Independent Research (via DANSCATT) provided support for travel to the synchrotron facility. We are thankful for Martine Mallet, Laboratoire de Chimie Physique et Microbiologie, Université de Lorraine and Center of Modern Analysis and Nanjing University. We also want to give our gratitude to the financial support of the University of Copenhagen and China Scholarship Council.

REFERENCES

- (1) Cavani, F.; Trifirò, F.; Vaccari, A. Hydrotalcite-Type Anionic Clays: Preparation, Properties and Applications. *Catal. Today* **1991**, *11* (2), 173–301.
- (2) Braterman, P. S.; Xu, Z. P.; Yarberr, F. Layered Double Hydroxides (LDHs). *Handb. Layer. Mater.* **2004**, *26* (2), 373–474.
- (3) Song, F.; Hu, X. Exfoliation of Layered Double Hydroxides for Enhanced Oxygen Evolution Catalysis. *Nat. Commun.* **2014**, *5*, 1–9.
- (4) Li, L.; Ma, R.; Ebina, Y.; Iyi, N.; Sasaki, T. Positively Charged Nanosheets Derived via Total Delamination of Layered Double Hydroxides. *Chem. Mater.* **2005**, *17* (17), 4386–4391.
- (5) Sim, H.; Jo, C.; Yu, T.; Lim, E.; Yoon, S.; Lee, J. H.; Yoo, J.; Lee, J.; Lim, B. Reverse Micelle

- 568 Synthesis of Colloidal Nickel-Manganese Layered Double Hydroxide Nanosheets and Their
569 Pseudocapacitive Properties. *Chem. - A Eur. J.* **2014**, 20 (45), 14880–14884.
- 570 (6) Meyn, M.; Beneke, K.; Lagaly, G. Anion-Exchange Reactions of Layered Double Hydroxides. *Inorg.*
571 *Chem.* **1990**, 29 (26), 5201–5207.
- 572 (7) Yu, J.; Liu, J.; Clearfield, A.; Sims, J. E.; Speigle, M. T.; Suib, S. L.; Sun, L. Synthesis of Layered
573 Double Hydroxide Single-Layer Nanosheets in Formamide. *Inorg. Chem.* **2016**, 55 (22), 12036–
574 12041.
- 575 (8) Naik, V. V.; Vasudevan, S. Sol-Gel Transition in Dispersions of Layered Double-Hydroxide
576 Nanosheets. *Langmuir* **2011**, 27 (21), 13276–13283.
- 577 (9) Leroux, F.; Adachi-Pagano, M.; Intissar, M.; Chauvière, S.; Forano, C.; Besse, J.-P. Delamination and
578 Restacking of Layered Double Hydroxides. *J. Mater. Chem.* **2001**, 11 (1), 105–112.
- 579 (10) Funnell, N. P.; Wang, Q.; Connor, L.; Tucker, M. G.; O'Hare, D.; Goodwin, A. L. Structural
580 Characterisation of a Layered Double Hydroxide Nanosheet. *Nanoscale* **2014**, 6 (14), 8032–8036.
- 581 (11) Harrington, R.; Hausner, D. B.; Bhandari, N.; Strongin, D. R.; Chapman, K. W.; Chupas, P. J.;
582 Middlemiss, D. S.; Grey, C. P.; Parise, J. B. Investigation of Surface Structures by Powder
583 Diffraction: A Differential Pair Distribution Function Study on Arsenate Sorption on Ferrihydrite.
584 *Inorg. Chem.* **2010**, 49 (1), 325–330.
- 585 (12) Huang, L.; Fang, L.; Hassenkam, T.; Dalby, K. N.; Scheckel, K. G.; Hansen, H. C. B. A One-Step
586 Delamination Procedure to Form Single Sheet Iron(iii)-(Oxy)hydroxides. *J. Mater. Chem. A* **2013**, 1
587 (43), 13664.
- 588 (13) Fang, L.; Huang, L.; Holm, P. E.; Yang, X.; Hansen, H. C. B.; Wang, D. Facile Upscaled Synthesis of
589 Layered Iron Oxide Nanosheets and Their Application in Phosphate Removal. *J. Mater. Chem. A*
590 **2015**, 3 (14), 7505–7512.
- 591 (14) Huang, L.-Z.; Hassenkam, T.; Hansen, H. C. B.; Bjerrum, M. J. Single Sheet Iron Oxide Based Films:
592 Electrochemical Properties with in Situ UV-Vis Measurement. *J. Mater. Chem. A* **2014**, 2 (11), 4029.
- 593 (15) Huang, L.; Hansen, H. C. B.; Bjerrum, M. J. Electrochemical Reduction of Nitroaromatic Compounds
594 by Single Sheet Iron Oxide Coated Electrodes. *J. Hazard. Mater.* **2016**, 306, 175–183.
- 595 (16) Schwertmann, U.; Cornell, R. *The Iron Oxides in the Laboratory*, 2nd ed.; Wiley-VCH Verlag GmbH
596 & Co. KGaA, 2000.
- 597 (17) Legrand, L.; Mazerolles, L.; Chaussé, A. The Oxidation of Carbonate Green Rust into Ferric Phases:
598 Solid-State Reaction or Transformation via Solution. *Geochim. Cosmochim. Acta* **2004**, 68 (17),
599 3497–3507.
- 600 (18) Wang, X.; Liu, F.; Tan, W.; Feng, X.; Koopal, L. K. Transformation of Hydroxycarbonate Green

- 601 Rust into Crystalline Iron (Hydr)oxides: Influences of Reaction Conditions and Underlying
602 Mechanisms. *Chem. Geol.* **2013**, *351*, 57–65.
- 603 (19) Michel, F. M.; Ehm, L.; Antao, S. M.; Lee, P. L.; Chupas, P. J.; Liu, G.; Strongin, D. R.; Schoonen,
604 M. A. A.; Phillips, B. L.; Parise, J. B. The Structure of Ferrihydrite, a Nanocrystalline Material.
605 *Science* **2007**, *316* (5832), 1726–1729.
- 606 (20) Drits, V. A. Structure of Feroxyhite as Determined by Simulation of X-Ray Diffraction Curves. *Clay*
607 *Miner.* **1993**, *28* (2), 209–222.
- 608 (21) Ghose, S. K.; Waychunas, G. a.; Trainor, T. P.; Eng, P. J. Hydrated Goethite (α -FeOOH) (100)
609 Interface Structure: Ordered Water and Surface Functional Groups. *Geochim. Cosmochim. Acta* **2010**,
610 *74* (7), 1943–1953.
- 611 (22) Christiansen, B. C.; Dideriksen, K.; Katz, A.; Nedel, S.; Bovet, N.; Sørensen, H. O.; Frandsen, C.;
612 Gundlach, C.; Andersson, M. P.; Stipp, S. L. S. Incorporation of Monovalent Cations in Sulfate Green
613 Rust. *Inorg. Chem.* **2014**, *53* (17), 8887–8894.
- 614 (23) Hansen, H. C. B.; Koch, C. B. Reduction of Nitrate to Ammonium by Sulphate Green Rust:
615 Activation Energy and Reaction Mechanism. *Clay Miner.* **1998**, *33* (1), 87–101.
- 616 (24) Yin, W.; Strobel, B. W.; Hansen, H. C. B. Amino Acid-Assisted Dehalogenation of Carbon
617 Tetrachloride by Green Rust: Inhibition of Chloroform Production. *Environ. Sci. Technol.* **2017**, *51*
618 (6), 3445–3452.
- 619 (25) Pollard, R. J. Characterization of FeOOH Polymorphs and Ferrihydrite Using Low-Temperature,
620 Applied-Field, Mössbauer Spectroscopy. *Clay Miner.* **1992**, *27* (1), 57–71.
- 621 (26) Patterson, A. L. The Scherrer Formula for X-Ray Particle Size Determination. *Phys. Rev.* **1939**, *56*
622 (10), 978–982.
- 623 (27) Rancourt, D. G.; Ping, J. Y. Voigt-Based Distributions Methods for Arbitrary-Shape in Mössbauer
624 Spectroscopy Static Hyperfine Parameter. *Nucl. Instruments Methods Phys. Res. B* **1991**, *58* (1), 85–
625 97.
- 626 (28) Dideriksen, K.; Frandsen, C.; Bovet, N.; Wallace, A. F.; Sel, O.; Arbour, T.; Navrotsky, A.; De Yoreo,
627 J. J.; Banfield, J. F. Formation and Transformation of a Short Range Ordered Iron Carbonate
628 Precursor. *Geochim. Cosmochim. Acta* **2015**, *164*, 53–70.
- 629 (29) Hammersley, A. P.; Svensson, S. O.; Thompson, A. Calibration and Correction of Spatial Distortions
630 in 2D Detector Systems. *Nucl. Instruments Methods Phys. Res. Sect. A Accel. Spectrometers, Detect.*
631 *Assoc. Equip.* **1994**, *346* (1–2), 312–321.
- 632 (30) Hammersley, A. *FIT2D: An Introduction and Overview*; Grenoble, France, 1997.
- 633 (31) Chupas, P. J.; Qiu, X.; Hanson, J. C.; Lee, P. L.; Grey, C. P.; Billinge, S. J. L. Rapid-Acquisition Pair

- 634 Distribution Function (RA-PDF) Analysis. *J. Appl. Crystallogr.* **2003**, *36* (6), 1342–1347.
- 635 (32) Qiu, X.; Thompson, J. W.; Billinge, S. J. L. PDFgetX2 : A GUI-Driven Program to Obtain the Pair
636 Distribution Function from X-Ray Powder Diffraction Data. *J. Appl. Crystallogr.* **2004**, *37* (4), 678–
637 678.
- 638 (33) Takeshi, E.; Billinge, S. J. L. Chapter 1 - Structure of Complex Materials. In *Underneath the Bragg*
639 *Peaks Structural Analysis of Complex Materials*; 2012; Vol. Volume 16, pp 1–25.
- 640 (34) Farrow, C. L.; Juhas, P.; Liu, J. W.; Bryndin, D.; Božin, E. S.; Bloch, J.; Proffen, T.; Billinge, S. J. L.
641 PDFfit2 and PDFgui: Computer Programs for Studying Nanostructure in Crystals. *J. Phys. Condens.*
642 *Matter* **2007**, *19* (33), 335219.
- 643 (35) Juhás, P.; Farrow, C. L.; Yang, X.; Knox, K. R.; Billinge, S. J. L. Complex Modeling: A Strategy and
644 Software Program for Combining Multiple Information Sources to Solve Ill Posed Structure and
645 Nanostructure Inverse Problems. *Acta Crystallogr. Sect. A Found. Adv.* **2015**, *71* (6), 562–568.
- 646 (36) Farrow, C. L.; Bediako, D. K.; Surendranath, Y.; Nocera, D. G.; Billinge, S. J. L. Intermediate-Range
647 Structure of Self-Assembled Cobalt-Based Oxygen-Evolving Catalyst. *J. Am. Chem. Soc.* **2013**, *135*
648 (17), 6403–6406.
- 649 (37) Beecher, A. N.; Yang, X.; Palmer, J. H.; Lagrassa, A. L.; Juhas, P.; Billinge, S. J. L.; Owen, J. S.
650 Atomic Structures and Gram Scale Synthesis of Three Tetrahedral Quantum Dots. *J. Am. Chem. Soc.*
651 **2014**, *136* (30), 10645–10653.
- 652 (38) Hoppe, W. Über Die Kristallstruktur von Alpha-AlOOH (Diaspore) Und Alpha-FeOOH
653 (Nadeleisenerz). *Z. Krist.* **1940**, *103*, 73–89.
- 654 (39) Hansen, H. Kinetics of Nitrate Reduction by Green Rusts—effects of Interlayer Anion and
655 Fe(II):Fe(III) Ratio. *Appl. Clay Sci.* **2001**, *18* (1–2), 81–91.
- 656 (40) Refait, P.; Benali, O.; Abdelmoula, M.; Génin, J. M. R. Formation of “Ferric Green Rust” And/or
657 Ferrihydrite by Fast Oxidation of iron(II-III) Hydroxychloride Green Rust. *Corros. Sci.* **2003**, *45* (11),
658 2435–2449.
- 659 (41) O’Loughlin, E. J.; Kemner, K. M.; Burris, D. R. Effects of Ag I , Au III , and Cu II on the Reductive
660 Dechlorination of Carbon Tetrachloride by Green Rust. *Environ. Sci. Technol.* **2003**, *37* (13), 2905–
661 2912.
- 662 (42) Choi, J.; Batchelor, B.; Chung, J. Reductive Dechlorination of Tetrachloroethylene by Green Rusts
663 Modified with Copper. *Water. Air. Soil Pollut.* **2010**, *212* (1–4), 407–417.
- 664 (43) Ayala-Luis, K. B.; Koch, C. B.; Hansen, H. C. B. Intercalation of Linear C9-C16 Carboxylates in
665 Layered FeII-FeIII-Hydroxides (Green Rust) via Ion Exchange. *Appl. Clay Sci.* **2010**, *48* (3), 334–341.
- 666 (44) Kang, H.; Huang, G.; Ma, S.; Bai, Y.; Ma, H.; Li, Y.; Yang, X. Coassembly of Inorganic

- Macromolecule of Exfoliated LDH Nanosheets with Cellulose. *J. Phys. Chem. C* **2009**, *113* (21), 9157–9163.
- (45) Alansi, A. M.; Alkayali, W. Z.; Al-qunaibit, M. H.; Qahtan, T. F.; Saleh, T. A. Synthesis of Exfoliated Polystyrene/anionic Clay MgAl-Layered Double Hydroxide: Structural and Thermal Properties. *RSC Adv.* **2015**, *5* (87), 71441–71448.
- (46) Cambier, P. Infrared Study of Goethites of Varying Crystallinity and Particle Size: I. Interpretation of OH and Lattice Vibration Frequencies. *Clay Miner.* **1986**, *21* (2), 191–200.
- (47) Cornell, R. M.; Schwertmann, U. The Iron Oxides: Structure, Properties, Reactions, Occurrences and Uses. *Techniques* **2003**, *39* (8), 9–12.
- (48) Christian, H.; Hansen, B.; Poulsen, I. F. Interaction of Synthetic Sulphate Green Rust with Phosphate and the Crystallization of Vivianite. *Clays Clay Miner.* **1999**, *47* (3), 312–318.
- (49) Christiansen, B. C.; Balic-Zunic, T.; Petit, P. O.; Frandsen, C.; Mørup, S.; Geckeis, H.; Katerinopoulou, A.; Stipp, S. L. S. Composition and Structure of an Iron-Bearing, Layered Double Hydroxide (LDH) - Green Rust Sodium Sulphate. *Geochim. Cosmochim. Acta* **2009**, *73* (12), 3579–3592.
- (50) Halevy, I.; Alesker, M.; Schuster, E. M.; Popovitz-Biro, R.; Feldman, Y. A Key Role for Green Rust in the Precambrian Oceans and the Genesis of Iron Formations. *Nat. Geosci.* **2017**, *10* (2), 135–139.
- (51) Johnson, C. A.; Murayama, M.; Küsel, K.; Hochella, M. F. Polycrystallinity of Green Rust Minerals and Their Synthetic Analogs: Implications for Particle Formation and Reactivity in Complex Systems. *Am. Mineral.* **2015**, *100* (10), 2091–2105.
- (52) Skovbjerg, L. L.; Stipp, S. L. S.; Utsunomiya, S.; Ewing, R. C. The Mechanisms of Reduction of Hexavalent Chromium by Green Rust Sodium Sulphate: Formation of Cr-Goethite. *Geochim. Cosmochim. Acta* **2006**, *70* (14), 3582–3592.
- (53) Janney, D. E.; Cowley, J. M.; Buseck, P. R. Structure of Synthetic 2-Line Ferrihydrite by Electron Nanodiffraction. *Am. Mineral.* **2000**, *85* (9), 1180–1187.
- (54) Mullet, M.; Guillemin, Y.; Ruby, C. Oxidation and Deprotonation of Synthetic FeII-FeIII (Oxy)hydroxycarbonate Green Rust: An X-Ray Photoelectron Study. *J. Solid State Chem.* **2008**, *181* (1), 81–89.
- (55) Génin, J.-M. R.; Aïssa, R.; Géhin, A.; Abdelmoula, M.; Benali, O.; Ernstsens, V.; Ona-Nguema, G.; Upadhyay, C.; Ruby, C. Fougerite and FeII–III Hydroxycarbonate Green Rust; Ordering, Deprotonation And/or Cation Substitution; Structure of Hydrotalcite-like Compounds and Mythic Ferrosic Hydroxide. *Solid State Sci.* **2005**, *7* (5), 545–572.
- (56) Huang, L. Z.; Ayala-Luis, K. B.; Fang, L.; Dalby, K. N.; Kasama, T.; Bender Koch, C.; Hansen, H. C.

700 B. Oxidation of Dodecanoate Intercalated iron(II)-iron(III) Layered Double Hydroxide to Form 2D
 701 iron(III) (Hydr)oxide Layers. *Eur. J. Inorg. Chem.* **2013**, No. 33, 5718–5727.

702 (57) Ruby, C.; Abdelmoula, M.; Naille, S.; Renard, A.; Khare, V.; Ona-Nguema, G.; Morin, G.; Génin, J.
 703 M. R. Oxidation Modes and Thermodynamics of FeII-III Oxyhydroxycarbonate Green Rust:
 704 Dissolution-Precipitation versus in Situ Deprotonation. *Geochim. Cosmochim. Acta* **2010**, 74 (3),
 705 953–966.

706 (58) Ciani, L.; Mancini, M.; Spina, G.; Tang, H. Mossbauer Spectra of Ferrihydrite:
 707 Superferromagnetic Interactions and Anisotropy Local Energy. *J. Phys. Condens. Matter* **1992**, 4 (8),
 708 2073–2077.

709 (59) Massiot, D.; Dion, P.; Alcover, J. F.; Bergaya, F. 27Al and 29Si MAS NMR Study of Kaolinite
 710 Thermal Decomposition by Controlled Rate Thermal Analysis. *J. Am. Ceram. Soc.* **1995**, 78 (11),
 711 2940–2944.

712 (60) Carlson, L.; Schwertmann, U. Natural Occurrence of Feroxyhite (d'-FeOOH). *Clays Clay Miner.*
 713 **1980**, 28 (4), 272–280.

714 (61) Pollard, R. J.; Pankhurst, Q. A. Ferrimagnetism in Fine Feroxyhite Particles. *J. Magn. Magn. Mater.*
 715 **1991**, 99 (1–3), L39–L44.

716 (62) Polyakov, A. Y.; Goldt, A. E.; Sorkina, T. A.; Perminova, I. V.; Pankratov, D. A.; Goodilin, E. A.;
 717 Tretyakov, Y. D. Constrained Growth of Anisotropic Magnetic δ -FeOOH Nanoparticles in the
 718 Presence of Humic Substances. *CrystEngComm* **2012**, 14 (23), 8097.

719 (63) Nishida, N.; Amagasa, S.; Kobayashi, Y.; Yamada, Y. Synthesis of Superparamagnetic δ -FeOOH
 720 Nanoparticles by a Chemical Method. *Appl. Surf. Sci.* **2016**, 387, 996–1001.

721 (64) Bo Madsen, M.; Mørup, S.; Koch, C. J. W.; Borggaard, O. K. A Study of Microcrystals of Synthetic
 722 Feroxyhite (δ -FeOOH). *Surf. Sci.* **1985**, 156, 328–334.

723 (65) Cornell, R. M.; Schwertmann, U. *The Iron Oxides*; Wiley-VCH Verlag GmbH & Co. KGaA:
 724 Weinheim, FRG, 2003; Vol. 39.

725 (66) Murad, E. The Characterization of Goethite by Mossbauer Spectroscopy. *American Mineralogist*.
 726 1982, pp 1007–1011.

727 (67) Janot, C.; Gilbert, H. Caractérisation de Kaolinites Ferrifères Par Spectrométrie Mössbauer. *Bull. la*
 728 *Société française minéralogie Cristallogr.* **1973**, 96, 281–291.

729 (68) van der Kraan, A. M.; van Loef, J. J. Superparamagnetism in Submicroscopic α -FeOOH Particles
 730 Observed by the Mössbauer Effect. *Phys. Lett.* **1966**, 20 (6), 614–616.

731 (69) Kone, T.; Hanna, K.; Abdelmoula, M.; Ruby, C.; Carteret, C. Reductive Transformation and
 732 Mineralization of an Azo Dye by Hydroxysulphate Green Rust Preceding Oxidation Using H₂O₂ at

- Neutral pH. *Chemosphere* **2009**, 75 (2), 212–219.
- (70) Murad, E. Magnetic Properties of Microcrystalline Iron (III) Oxides and Related Materials as Reflected in Their Mössbauer Spectra. *Phys. Chem. Miner.* **1996**, 23, 248–262.
- (71) Mørup, S.; Bo Madsen, M.; Franck, J.; Villadsen, J.; Koch, C. J. W. A New Interpretation of Mössbauer Spectra of Microcrystalline goethite: “Super-Ferromagnetism” or “super-Spin-Glass” behaviour? *J. Magn. Magn. Mater.* **1983**, 40 (1–2), 163–174.
- (72) Murad, E. Magnetic Properties of Microcrystalline Iron (III) Oxides and Related Materials as Reflected in Their Mössbauer Spectra. *Phys. Chem. Miner.* **1996**, 23 (4), 248–262.
- (73) Refait, P.; Abdelmoula, M.; Génin, J.-M. R. Mechanisms of Formation and Structure of Green Rust One in Aqueous Corrosion of Iron in the Presence of Chloride Ions. *Corros. Sci.* **1998**, 40 (9), 1547–1560.
- (74) Refait, P.; Abdelmoula, M.; Trolard, F.; Génin, M.; Ehrhardt, J.; Bourrié, G. Mössbauer and XAS Study of a Green Rust Mineral ; the Partial Substitution of Fe 2 + by Mg 2. *Am. Mineral.* **2001**, 86 (Taylor 1981), 731–739.
- (75) Shannon, R. D. Revised Effective Ionic Radii and Systematic Studies of Interatomic Distances in Halides and Chalcogenides. *Acta Crystallogr. Sect. A* **1976**, 32 (5), 751–767.
- (76) Michel, F. M.; Ehm, L.; Antao, S. M.; Lee, P. L.; Chupas, P. J.; Liu, G.; Strongin, D. R.; Schoonen, M. A. A.; Phillips, B. L.; Parise, J. B. The Structure of Ferrihydrite, a Nanocrystalline Material. *Science* (80-.). **2007**, 316 (5832), 1726–1729.
- (77) Wyckoff, R. W. G. *Crystal Structures*, Second edi.; Interscience Publishers: New York, 1963.
- (78) Wander, M. C. F.; Rosso, K. M.; Schoonen, M. A. A. Structure and Charge Hopping Dynamics in Green Rust. *J. Phys. Chem. C* **2007**, 111 (30), 11414–11423.
- (79) Wei, Y.; Ding, R.; Zhang, C.; Lv, B.; Wang, Y.; Chen, C.; Wang, X.; Xu, J.; Yang, Y.; Li, Y. Facile Synthesis of Self-Assembled Ultrathin α -FeOOH Nanorod/graphene Oxide Composites for Supercapacitors. *J. Colloid Interface Sci.* **2017**, 504, 593–602.
- (80) Cheng, W.; He, J.; Yao, T.; Sun, Z.; Jiang, Y.; Liu, Q.; Jiang, S.; Hu, F.; Xie, Z.; He, B.; Yan, W.; Wei, S. Half-Unit-Cell α -Fe₂O₃ semiconductor Nanosheets with Intrinsic and Robust Ferromagnetism. *J. Am. Chem. Soc.* **2014**, 136 (29), 10393–10398.
- (81) Shao, P.; Ren, Z.; Tian, J.; Gao, S.; Luo, X.; Shi, W.; Yan, B.; Li, J.; Cui, F. Silica Hydrogel-Mediated Dissolution-Recrystallization Strategy for Synthesis of Ultrathin α -Fe₂O₃ nanosheets with Highly Exposed (1 1 0) Facets: A Superior Photocatalyst for Degradation of Bisphenol S. *Chem. Eng. J.* **2017**, 323, 64–73.
- (82) Yang, Y.; Zhong, Y.; Wang, X.; Ma, Y.; Yao, J. Facile Synthesis of Ultrathin Lepidocrocite

- 766 Nanosheets from Layered Precursors. *Chem. - An Asian J.* **2014**, 9 (6), 1563–1569.
- 767 (83) Chen, P.; Xu, K.; Li, X.; Guo, Y.; Zhou, D.; Zhao, J.; Wu, X.; Wu, C.; Xie, Y. Ultrathin Nanosheets
768 of Feroxyhyte: A New Two-Dimensional Material with Robust Ferromagnetic Behavior. *Chem. Sci.*
769 **2014**, 5 (6), 2251–2255.
- 770 (84) Sestu, M.; Carta, D.; Casula, M. F.; Corrias, A.; Navarra, G. Novel Interpretation of the Mean
771 Structure of Feroxyhyte. *J. Solid State Chem.* **2015**, 225, 256–260.
- 772 (85) Drits, V. A.; Sakharov, B. A.; Manceau, A. Structure of Feroxyhyte as Determined by Simulation of
773 X-Ray Diffraction Curves. *Clay Miner.* **1993**, 28 (2), 209–222.
- 774 (86) Lee, S.; Shen, Z.; Xu, H. Study on Nanophase Iron Oxyhydroxides in Freshwater Ferromanganese
775 Nodules from Green Bay, Lake Michigan, with Implications for the Adsorption of As and Heavy
776 Metals. *Am. Mineral.* **2016**, 101 (9), 1986–1995.
- 777