Open Archive Toulouse Archive Ouverte (OATAO)

OATAO is an open access repository that collects the work of Toulouse researchers and makes it freely available over the web where possible

This is an author's version published in: <http://oatao.univ-toulouse.fr/21769>

Official URL: <https://doi.org/10.1016/j.coelec.2018.03.004>

To cite this version:

Lin, Zifeng and Taberna, Pierre-Louis and Simon, Patrice *Advanced analytical techniques to characterize materials for electrochemical capacitors.* (2018) Current Opinion in Electrochemistry, 9. 18-25. ISSN 2451-9103

Any correspondence concerning this service should be sent to the repository administrator: tech-oatao@listes-diff.inp-toulouse.fr

Advanced analytical techniques to characterize materials for electrochemical capacitors

Zifeng Lin^{1,2}, Pierre-Louis Taberna^{1,2} and Patrice Simon^{1,2,3,*}

This review covers recent developments in advanced analytical techniques to characterize materials for electrochemical capacitors. For double layer capacitors, examples of the use of *in situ* X-ray photoelectron spectroscopy (XPS), pulsed electrochemical mass spectrometry (PEMS) technique, temperature-programmed desorption coupled with mass spectroscopy (TPD-MS) technique, *in situ* NMR spectroscopy, and *in situ* dilatometry measurement are presented, for studying carbon/electrolyte interface with a focus onto electrolyte ions confinement in nanopores and changes during ageing. For the pseudocapacitive system, *in situ* X-ray (neutron) diffraction or scattering, *in situ* dilatometry technique, cavity micro-electrode, *in situ* Raman spectroscopy, TPD-MS technique, and electrochemical quartz crystal microbalance (EQCM) technique have been employed for studying materials structure, electrochemical kinetic, interface interaction, and ions adsorption/desorption. These advanced analytical techniques probe insight into charge storage mechanisms, and guiding the fast development of supercapacitors.

Addresses

¹ Université Paul Sabatier, Laboratoire CIRIMAT UMR CNRS, Toulouse 5085, France

² Réseau sur le Stockage Electrochimique de l'Energie (RS2E), FR CNRS n°3459, France

³ Institut Universitaire de France, 1 rue des Ecoles, Paris 75003, France

*Corresponding author: Simon, Patrice (simon@chimie.ups-tlse.fr)

<https://doi.org/10.1016/j.coelec.2018.03.004>

Introduction

During the past 15 years, major scientific advances have been made in the field of Electrochemical Capacitors (ECs) which led to a 2-fold increase of the energy density of carbon-based (EDLCs) or to the development of high-rate pseudocapacitive materials. These advances

have been mainly achieved thanks to the use of analytical techniques, used in combination with *in situ* electrochemical conventional methods and/or with modeling. In this review, some advanced techniques, as well as their roles in studying charge storage mechanisms are introduced.

Electrochemical double layer capacitors

In Electrical Double Layer Capacitors (EDLCs), capacitive storage is achieved through ion adsorption of an electrolyte onto high surface area porous carbon electrodes [1]. Then, most of the electrochemical process in EDLCs occurs at the carbon/electrolyte interface. The analytical techniques used in EDLCs mainly focus on this interface.

One of the important parameters of ECs is the operating voltage window, which drives the energy density of the system. *In situ* X-ray Photoelectron Spectroscopy (XPS) technique has been used to study the stability of the carbon/electrolyte interface during electrochemical polarization of CDC carbons in ionic liquid electrolyte [2,3]. By tracking the change in the C1s and N1s energy levels, Lust and co-workers identified the reaction mechanism responsible for the electrolyte degradation at high potential (>3.6 V), which involves the oxidative dimerization of the imidazolium cation via N–N bond formation [2]. Another technique recently developed for monitoring gas evolution during the operation of supercapacitors is the pulsed electrochemical mass spectrometry (PEMS) technique [4], as presented in Figure 1. PEMS technique allows for fast quantitative measurement of low gas production during supercapacitor cycling or ageing. Batisse and Raymundo [4] evidenced and quantified the formation of CO, CO₂ and H₂ at the positive and negative electrode during supercapacitor cells ageing at constant voltages in aqueous electrolytes. Furthermore, they could correlate gas production to the change of each electrode potential versus reference during ageing. Ageing mechanisms in porous carbon electrodes strongly depend on the presence of surface functional groups on the carbon surface, as well as the carbon structure (presence of defects) and texture (surface area and pore size distribution). Here also, many advances have been achieved within the past 10 years.

A key technique for analyzing the carbon surface is the temperature-programmed desorption coupled with mass spectroscopy (TPD-MS) technique [4–7]. TPD-MS technique allows for measuring the surface group nature and content as well as the active surface area (ASA)

Figure 1

Observation of gas evolution at electrode/electrolyte interface by a modified pulsed electrochemical mass spectrometry (PEMS) method. Adapted with permission from ref. [4[•]]. Copyright© 2017 American Chemical Society.

which accounts for the presence of carbon active sites: defects such as dislocations, stacking faults or atom vacancies mainly located in the edge planes [7]. Using carbon onions with controlled defect and surface group contents as model materials, a direct correlation was reported between the number of defects on the carbon surface measured by TPD-MS and the capacitance in both aqueous and non-aqueous electrolytes. Surprisingly, the contribution of the surface defects to the capacitance was found to be higher than that of the functional surface groups, even in aqueous electrolytes. These results show that the surface defects content also affects the carbon capacitance.

Besides the carbon structure and surface group content, the electrochemical performances of porous carbons are also controlled by the carbon texture: specific surface area, pore volume, pore size, pore size distribution. Back to 15 years ago, the carbon-specific surface area SSA was mainly calculated from N_2 gas sorption isotherms at 77 K using the Brunauer–Emmett–Teller (BET) equation. The evidence of the capacitance increase in carbon pores less than 1 nm [8–10] highlighted the need for refining the characterization methods to finely measure the porous volume and pore size in the ultra-microporous range (<1 nm).

Following recommendations of the IUPAC, the BET equation is not suitable for the measurement of specific surface area of microporous carbons [11]. Instead, for microporosity assessment, CO_2 sorption at 273 K should be preferred to alleviate kinetics restrictions observed during measurements at low temperature with (77 K with N_2) [11]. In the same way, calculation of the SSA using quenched solid density functional theory (QS-DFT) avoids the fundamental limitations of the BET theory [12]. Finally, the porous volume accessible to ions should be considered, that is the porous volume of pores larger than the size of the desolvated ion [13]. Based on the previous recommendations, Jäckel *et al.* [13] propose to use CO_2 gas for measuring porous volume below 0.9 nm and N_2 gas for pores > 0.9 nm. The change of the capacitance normalized to QS-DFT SSA versus accessible pore size shows a capacitance increase in pores less than 1 nm size for various porous carbons in non-aqueous electrolytes (in acetonitrile- or propylene carbonate-based electrolyte). Initially reported in 2006 using a series of porous carbons with controlled pore size [10], the origin of the capacitance increase in carbon nanopores has been extensively studied since that time mainly by using new or advanced *in situ* techniques. Beyond the capacitance increase, the

Figure 2

In situ NMR spectroscopy experiments carried out at different charge states allow quantification of the number of charges storing species. Adapted with permission from ref. [15]. Copyright© 2013 American Chemical Society.

work was directed toward the understanding of the ion transport and adsorption in confined carbon nanopores (<1 nm), i.e. where there is no room for the building of a diffuse layer. *In situ* NMR spectroscopy experiments during electrochemical polarization of porous carbons in NaF aqueous electrolyte have shown that ions could access subnanometer pores with partial anion dehydration under polarization [14]. Using dedicated electrochemical cell, as shown in Figure 2, *in situ* NMR experiments during polarization also evidenced different charge storage mechanisms depending on the electrode polarity [15–19**]. Counter ion adsorption was found at the negative electrode ($X = 1$) and ion exchange at the positive ($X = 0$) [18], confirming results obtained using electrochemical quartz crystal microbalance technique under a gravimetric mode [20]. In addition, the effective ionic diffusion coefficients inside the carbon nanopores were decreased by two orders of magnitude compared with bulk electrolyte [19**]; this was explained by the increase of the ion population in pores. As a result, the charging mechanism (counter ion adsorption versus ion exchange) affects the ion transport kinetics in confined nanopores.

Conventional techniques have been also developed to study ion transfer in porous carbons. Interestingly, *in situ* dilatometry measurement during electrochemical polarization shows also an asymmetric behavior with respect to the electrode polarization, the electrode thickness change being more important during negative polarization [21]. Recently, Presser *et al.* improved the technique by coupling *in situ* dilatometry together with X-ray absorption spectroscopy (XAS) [22**] [21]. First, they confirmed the asymmetric swelling of porous carbon electrodes during

electrochemical polarization in aqueous electrolytes. Also, thanks to the use of porous carbon with hierarchical microporous/mesoporous structure, most of the volume change could be assigned to the presence of pores less than 1 nm size. The origin of the asymmetry was attributed to the increase of the C–C bonds due to electron injection into the carbon during negative polarization. This echoes the increase in the ion population reported by Forse and co-workers by *in situ* NMR spectroscopy [15], leading to the decrease of the ionic diffusion coefficient in carbon nanopores.

Finally, the development of *in situ* X-ray or neutron scattering techniques has been particularly successful for studying ion adsorption in carbon nanopores [23**–25]. Prehal *et al.* [24] used CsCl aqueous electrolyte to study the ion adsorption in nanoporous carbons under polarization. By coupling SAXS and Monte Carlo modeling, they evidenced the ion partial desolvation when confined in carbon nanopores. The extent of desolvation and confinement was found to increase with the applied potential, in agreement with previous studies [26], which gives hints to explain the capacitance increase in carbon nanopores. Also, Futamura *et al.* recently showed the existence of co-ion pairs when the ionic liquid electrolyte was confined into carbon pores of 0.7 nm size, that is when the ion size is close to the pore size [25]. Such an improved co-ion pairing was the consequence of the partial breaking of the electrostatic Coulombic repulsion interactions between co-ions thanks to the creation of image charges in the carbon. They could confirm the creation of a “super ionic” state such as predicted by Kornyshev and Kondrat from modeling [27].

Figure 3

Schematic of the cavity micro-electrode. Adapted with permission from ref. [40].

As one can see, the more we advance in the understanding of the ion confinement effect in nanopores, the more things get complex. There is still a lot to understand in this field and all these analytical tools will be of great help to keep on moving in this direction.

Pseudocapacitive and high charge–discharge rate materials

Pseudocapacitive materials store the charge through fast, non-diffusion-limited redox reactions. Also, different from amorphous porous carbon materials used in EDLCs, most of the pseudocapacitive materials show organized crystalline structure. So, most of the conventional techniques based on X-ray diffraction or scattering used to characterize battery electrode materials have been employed with pseudocapacitive materials. We will then just briefly mention some examples. *In situ* XRD has been extensively used to study the swelling/contraction of pseudocapacitive materials during ion intercalation/de-intercalation, such as in MnO_2 , NiO_x , or MXene [28–30]. Without surprise, the electrode material volume changes are driven by electrostatic repulsion between the layers or the steric effects coming from ion intercalation/de-intercalation to balance the charge [29]. In monocrystalline Nb_2O_5 operating in non-aqueous electrolytes, the intercalation/de-intercalation process volume change is driven by steric effect (swelling during intercalation, contraction during de de-intercalation) [31]. X-ray absorption was used to evidence the change of the Ti oxidation

state during charge/discharge of $\text{Ti}_3\text{C}_2\text{T}_x$ MXene electrode [32,33], as well as in other materials [34,35].

Differently, micro-electrodes or cavity micro-electrodes tools (Figure 3) are well-suited for the electrochemical characterization of high-rate pseudocapacitive materials. Thanks to the small amount of materials tested, a large range of potential scan rates (v) can be explored—from few mV s^{-1} up to few V s^{-1} —which was extremely useful for studying the electrochemical kinetics of pseudocapacitive reactions [36–38]. The deconvolution of the current into non-diffusion limited surface process (changing with v) and diffusion-limited (changing with $v^{1/2}$) has made it possible to extract the pseudocapacitive contribution to the total current at each potential, which helps in optimizing the structures to design high-rate materials [36–39].

Another original initiative comes from Hu *et al.*, who used Raman spectroscopy to characterize the charge storage during polarization of $\text{Ti}_3\text{C}_2\text{T}_x$ MXene electrodes in SO_4^{2-} ions containing aqueous electrolyte of various cations [41••]. MXenes are 2-Dimensional materials pioneered by Barsoum and co-workers [42], which contains O- and F- surface terminations. Those groups come from the synthesis process, that is etching of MAX phase in the fluorine-containing acidic solutions [33]. It was found that hydronium ions in sulfuric acid could bond with the oxygen-containing terminations of the $\text{Ti}_3\text{C}_2\text{T}_x$ MXene negative electrode upon reduction (oxidation) while debonding occurs upon oxidation (reduction) [41••]. This

process is accompanied by a change in the oxidation state of Ti from Ti (+III) down to Ti(+II). The redox reaction on Ti explains the extremely high capacitance $\text{Ti}_3\text{C}_2\text{T}_x$ MXene can reach in acidic electrolytes [33,43]. In contrast, in neutral electrolytes, only double layer adsorption occurs without charge transfer on Ti atoms [41^{••}]. Broadening the use of *in situ* Raman spectroscopy technique to other materials could bring new insights in the pseudocapacitive charge storage mechanism.

The discovery of 2D MXene materials has boosted the research in pseudocapacitive materials. One of the key features of MXenes is the presence of surface oxygen and fluorine terminations on their surface. The TPD-MS technique has been successfully used to measure the change of the amount and the nature of these groups during hydrazine intercalation into $\text{Ti}_3\text{C}_2\text{T}_x$ MXene material [44]. The capacitance of MXene in the non-aqueous electrolyte is well behind that in the aqueous acidic electrolytes [45] and the charge storage mechanism of MXenes in non-aqueous electrolytes is still unclear [28,46]. *In situ* dilatometry technique, which is well-suited for 2D materials, has been used to measure the swelling/expansion of $\text{Ti}_3\text{C}_2\text{T}_x$ MXene electrode in

imidazolium-based ionic liquid electrolyte [47]. MXene electrode swelling was measured during negative polarization, suggesting the preferential insertion of cations. Under positive polarization, the electrode contracts even further compared to the un-polarized sample, suggesting an ion exchange mechanism. Similar results were obtained from *in situ* XRD measurements [28] and a molecular dynamics simulation study [48], which confirm the difference in the charge storage mechanism with the electrode polarity. Also, the modest capacitance suggests a major contribution from the double layer.

New analytical tools based on the electrochemical quartz crystal microbalance (EQCM) technique have also been developed to study energy storage materials that offer interesting opportunities in the EC area. Differently from the gravimetric EQCM, the EQCM with dissipation monitoring (EQCM-D) operated with multiple overtones of the resonance frequency, thus probing a wide range of penetration depth δ_n [49,50]. The structural parameters of the electrodes can be obtained by measuring the change in the resonance frequency ΔF and the change in the full-width at half-height of the resonance peak ΔW over a wide range of overtone numbers n , and fitting the

Figure 4

Gravimetric and non-gravimetric applications of EQCM-D for the characterization of energy-storage electrodes. (Bottom panel) Acoustic waves for fundamental frequency and its 3rd overtone. Adapted with permission from ref. [49]. Copyright© 2018 American Chemical Society.

hydrodynamic equations. Structural parameters include electrode film density or thickness, permeability length, particles radius and coverage density (Figure 4) [49]. This technique is an efficient tool for tracking in one shot the geometrical change in the electrodes (contraction or swelling, morphological changes) as well as the change in reaction mechanisms (formation of passive layers or electrolyte decomposition) [51**].

Another technique derived from EQCM is called AC-electrogravimetry or AC-EQCM [52]. The AC-EQCM technique consists of achieving gravimetric EQCM measurements at a steady state (constant potential for instance) and over-impose a sinusoidal perturbation to the bias signal such as achieved in electrochemical impedance spectroscopy. Differently from gravimetric EQCM, AC-EQCM allows the deconvolution of a global gravimetric EQCM response into individual cations, anions, and solvent molecules contributions by plotting the dQ/dE (Q : charge, E : potential) or dm/dE (m : mass, E : potential) transfer functions; this is one key advantage of this technique which can track the electrochemical activity of one type of anion (cation) in a mixture of anions (cations) [53]. Some papers have just been published describing the use of AC-EQCM to study pseudocapacitive materials [54*]. The possibility for differentiating the ion contributions present great interest for studying the charge storage reaction mechanisms in various electrolytes.

References and recommended reading

Papers of particular interest, published within the period of review, have been highlighted as:

- Paper of special interest.
- Paper of outstanding interest.

1. Simon P, Gogotsi Y: **Materials for electrochemical capacitors**. *Nat Mater* 2008, **7**(11):845–854.
 2. Kruusma J, Tõnisoo A, Pärna R, Nõmmiste E, Kuusik I, Vahtrus M, Tallo I, Romann T, Lust E: **The electrochemical behavior of 1-ethyl-3-methyl imidazolium tetracyanoborate visualized by in situ X-ray photoelectron spectroscopy at the negatively and positively polarized micro-mesoporous carbon electrode**. *J Electrochem Soc* 2017, **164**(13):A3393–A3402.
 3. Kruusma J, Tõnisoo A, Pärna R, Nõmmiste E, Tallo I, Romann T, Lust E: **Influence of the negative potential of molybdenum carbide derived carbon electrode on the in situ synchrotron radiation activated X-ray photoelectron spectra of 1-ethyl-3-methylimidazolium tetrafluoroborate**. *Electrochim Acta* 2016, **206**:419–426.
 4. Batisse N, Raymundo-Piñero E: **Pulsed electrochemical mass spectrometry for operando tracking of interfacial processes in small-time-constant electrochemical devices such as supercapacitors**. *ACS Appl Mater Interfaces* 2017, **9**(47):41224–41232.
- In this paper, the gas emissions during polarization of a carbon—carbon supercapacitor cell were analyzed as a function of the cell voltage. The data were correlated to the textural changes of the carbon electrodes, giving a complete picture of the processes taking place at the electrode/electrolyte interface.
5. Figueiredo JL, Pereira MFR, Freitas MMA, Órfão JJM: **Modification of the surface chemistry of activated carbons**. *Carbon* 1999, **37**(9):1379–1389.
 6. Ghimbeu CM, Gadiou R, Dentzer J, Vidal L, Vix-Guterl C: **A TPD-MS study of the adsorption of ethanol/cyclohexane mixture on activated carbons**. *Adsorption* 2011, **17**(1):227–233.
 7. Moussa G, Matei Ghimbeu C, Taberna P-L, Simon P, Vix-Guterl C: **Relationship between the carbon nano-onions (CNOs) surface chemistry/defects and their capacitance in aqueous and organic electrolytes**. *Carbon* 2016, **105**:628–637.
 8. Eliad L, Salitra G, Soffer A, Aurbach D: **Ion sieving effects in the electrical double layer of porous carbon electrodes: estimating effective ion size in electrolytic solutions**. *J Phys Chem B* 2001, **105**(29):6880–6887.
 9. Eliad L, Salitra G, Soffer A, Aurbach D: **On the mechanism of selective electroadsorption of protons in the pores of carbon molecular sieves**. *Langmuir* 2005, **21**(7):3198–3202.
 10. Chmiola J, Yushin G, Gogotsi Y, Portet C, Simon P, Taberna PL: **Anomalous increase in carbon capacitance at pore sizes less than 1 nanometer**. *Science* 2006, **313**(5794):1760–1763.
 11. Thommes M, Kaneko K, Neimark Alexander V, Olivier James P, Rodriguez-Reinoso F, Rouquerol J, Sing Kenneth SW: **Physiosorption of gases, with special reference to the evaluation of surface area and pore size distribution (IUPAC Technical Report)**. *Pure Appl Chem* 2015, **87**(9-10):1051–1069.
 12. Gor GY, Thommes M, Cychosz KA, Neimark AV: **Quenched solid density functional theory method for characterization of mesoporous carbons by nitrogen adsorption**. *Carbon* 2012, **50**(4):1583–1590.
 13. Jäckel N, Simon P, Gogotsi Y, Presser V: **Increase in capacitance by subnanometer pores in carbon**. *ACS Energy Lett* 2016, **1**(6):1262–1265.
 14. Luo Z-X, Xing Y-Z, Liu S, Ling Y-C, Kleinhammes A, Wu Y: **Dehydration of ions in voltage-gated carbon nanopores observed by in situ NMR**. *J Phys Chem Lett* 2015, **6**(24):5022–5026.
 15. Wang H, Forse AC, Griffin JM, Trease NM, Trognko L, Taberna P-L, Simon P, Grey CP: **In situ NMR spectroscopy of supercapacitors: insight into the charge storage mechanism**. *J Am Chem Soc* 2013, **135**(50):18968–18980.
 16. Deschamps M, Gilbert E, Azais P, Raymundo-Piñero E, Ammar MR, Simon P, Massiot D, Béguin F: **Exploring electrolyte organization in supercapacitor electrodes with solid-state NMR**. *Nat Mater* 2013, **12**:351.
 17. Griffin JM, Forse AC, Tsai W-Y, Taberna P-L, Simon P, Grey CP: **In situ NMR and electrochemical quartz crystal microbalance techniques reveal the structure of the electrical double layer in supercapacitors**. *Nat Mater* 2015, **14**(8):812–819.
 18. Forse AC, Merlet, Griffin C, Grey JM, New CP: **Perspectives on the charging mechanisms of supercapacitors**. *J Am Chem Soc* 2016, **138**(18):5731–5744.
 19. Forse Alexander AC, Griffin John JM, Merlet C, Carretero-Gonzalez J, Raji A-Rahman RO, Trease Nicole NM, Grey Clare CP: **Direct observation of ion dynamics in supercapacitor electrodes using in situ diffusion NMR spectroscopy**. *Nat Energy* 2017, **2**(3):16216 Article number:.
- In this paper, in-situ pulsed field gradient NMR spectroscopy was used to measure ionic diffusion in porous carbon electrodes. In-pore ionic diffusion coefficients were found to be 2 orders of magnitude below compared to bulk electrolyte. Ionic diffusion coefficient can be affected both by carbon pore size distributions and the electrolyte concentration in pores.
20. Tsai WY, Taberna PL, Simon P: **Electrochemical quartz crystal microbalance (EQCM) study of ion dynamics in nanoporous carbons**. *J Am Chem Soc* 2014, **136**(24):8722–8728.
 21. Hantel MM, Presser V, Kötz R, Gogotsi Y: **In situ electrochemical dilatometry of carbide-derived carbons**. *Electrochem Commun* 2011, **13**(11):1221–1224.

22. Koczwaro C, Rumswinkel S, Prehal C, Jäckel N, Elsässer MS, Amenitsch H, Presser V, Hüsing N, Paris O: **In situ measurement of electrosorption-induced deformation reveals the importance of micropores in hierarchical carbons.** ACS Appl Mater Interfaces 2017, **9**(28):23319–23324.

In this paper, nanometer scale and macroscopic scale dimensional changes in carbon-based supercapacitor electrodes were investigated using a combination of electrochemical dilatometry and in situ small-angle X-ray scattering.

23. Boukhalfa S, Gordon D, He L, Melnichenko YB, Nitta N, Magasinski A, Yushin G: **In situ small angle neutron scattering revealing ion sorption in microporous carbon electrical double layer capacitors.** ACS Nano 2014, **8**(3):2495–2503.

For the first time that *in-situ* small angle neutron scattering (SANS) was utilized to reveal the electroadsorption of organic electrolyte ions in carbon pores of different sizes. Enhanced ion sorption in subnanometer pores under the applied potential was observed.

24. Prehal C, Koczwaro C, Jackel N, Schreiber A, Burian M, Amenitsch H, Hartmann MA, Presser V, Paris O: **Quantification of ion confinement and desolvation in nanoporous carbon supercapacitors with modelling and *in-situ* X-ray scattering.** Nat Energy 2017, **2**(3):16215 Article number.
25. Futamura R, Iiyama T, Takasaki Y, Gogotsi Y, Biggs MJ, Salanne M, Ségolini J, Simon P, Kaneko K: **Partial breaking of the Coulombic ordering of ionic liquids confined in carbon nanopores.** Nat Mater 2017, **16**(12):1225–1232.
26. Merlet C, Pean C, Rotenberg B, Madden PA, Daffos B, Taberna PL, Simon P, Salanne M: **Highly confined ions store charge more efficiently in supercapacitors.** Nat Commun 2013, **4**:2701 Article number.
27. Kondrat S, Kornyshev A: **Superionic state in double-layer capacitors with nanoporous electrodes.** J Phys, vol 23 2011 022201 Article number.
28. Lin Z, Rozier P, Duployer B, Taberna P-L, Anasori B, Gogotsi Y, Simon P: **Electrochemical and *in-situ* X-ray diffraction studies of $\text{Ti}_3\text{C}_2\text{T}_x$ MXene in ionic liquid electrolyte.** Electrochem Commun 2016, **72**:50–53.
29. Ghodbane O, Ataherian F, Wu N-L, Favier F: **In situ crystallographic investigations of charge storage mechanisms in MnO_2 -based electrochemical capacitors.** J Power Sources 2012, **206**:454–462.
30. Cheng J, Cao G-P, Yang Y-S: **Characterization of sol-gel-derived NiO_x xerogels as supercapacitors.** J Power Sources 2006, **159**(1):734–741.
31. Come J, Augustyn V, Kim JW, Rozier P, Taberna P-L, Gogotsi P, Long JW, Dunn B, Simon P: **Electrochemical kinetics of nanostructured Nb_2O_5 electrodes.** J Electrochem Soc 2014, **161**(5):A718–A725.
32. Lukatskaya MR, Bak S-M, Yu X, Yang X-Q, Barsoum MW, Gogotsi Y: **Probing the mechanism of high capacitance in 2D titanium carbide using in situ X-ray absorption spectroscopy.** Adv Energy Mater, vol 5 2015 1500589 Article number.
33. Anasori B, Lukatskaya MR, Gogotsi Y: **2D metal carbides and nitrides (MXenes) for energy storage.** Nat Rev Mater 2017, **2**(2):16098 Article number.
34. Pande P, Deb A, Sleightholme AES, Djire A, Rasmussen PG, Penner-Hahn J, Thompson LT: **Pseudocapacitive charge storage via hydrogen insertion for molybdenum nitrides.** J Power Sources 2015, **289**:154–159.
35. Yeager MP, Su D, Marinković NS, Teng X: **Pseudocapacitive NiO fine nanoparticles for supercapacitor reactions.** J Electrochem Soc 2012, **159**(10):A1598–A1603.
36. Augustyn V, Come J, Lowe MA, Kim JW, Taberna P-L, Tolbert SH, Abruña HD, Simon P, Dunn B: **High-rate electrochemical energy storage through Li^+ intercalation pseudocapacitance.** Nat Mater 2013, **12**(6):518–522.
37. Kim H-S, Cook JB, Lin H, Ko JS, Tolbert SH, Ozolins V, Dunn B: **Oxygen vacancies enhance pseudocapacitive charge storage properties of MoO_{3-x} .** Nat Mater 2017, **16**(4):454–460.

38. Han J, Lin Y-C, Chen L, Tsai Y-C, Ito Y, Guo X, Hirata A, Fujita T, Esashi M, Gessner T, Chen M: **On-chip micro-pseudocapacitors for ultrahigh energy and power delivery.** Adv Sci, vol 2 2015 1500067 Article number.

39. Kim JW, Augustyn V, Dunn B: **The effect of crystallinity on the rapid pseudocapacitive response of Nb_2O_5 .** Adv Energy Mater 2012, **2**(1):141–148.
40. Bozlar M, Miomandre F, Bai J: **Electrochemical synthesis and characterization of carbon nanotube/modified polypyrrole hybrids using a cavity microelectrode.** Carbon 2009, **47**(1):80–84.
41. Hu M, Li Z, Hu T, Zhu S, Zhang C, Wang X: **High-capacitance mechanism for $\text{Ti}_3\text{C}_2\text{T}_x$ MXene by in situ electrochemical Raman spectroscopy investigation.** ACS Nano 2016, **10**(12):11344–11350.

In this paper, authors investigated the charge storage mechanism of $\text{Ti}_3\text{C}_2\text{T}_x$ MXene by *in-situ* Raman technique. It's shown that hydronium in H_2SO_4 electrolyte reversible bonding/debonding with O terminals account for the high capacitance MXene in acidic electrolytes.

42. Naguib M, Kurtoglu M, Presser V, Lu J, Niu J, Heon M, Hultman L, Gogotsi Y, Barsoum MW: **Two-dimensional nanocrystals produced by exfoliation of Ti_3AlC_2 .** Adv Mater 2011, **23**(37):4248–4253.
43. Lukatskaya MR, Kota S, Lin Z, Zhao M-Q, Shpigel N, Levi MD, Halim J, Taberna P-L, Barsoum MW, Simon P, Gogotsi Y: **Ultra-high-rate pseudocapacitive energy storage in two-dimensional transition metal carbides.** Nat Energy 2017, **2**(8):17105 Article number.
44. Mashtalir O, Lukatskaya MR, Kolesnikov AI, Raymundo-Pinero E, Naguib M, Barsoum MW, Gogotsi Y: **The effect of hydrazine intercalation on the structure and capacitance of 2D titanium carbide (MXene).** Nanoscale 2016, **8**(17):9128–9133.
45. Lin Z, Barbara D, Taberna P-L, Van Aken KL, Anasori B, Gogotsi Y, Simon P: **Capacitance of $\text{Ti}_3\text{C}_2\text{T}_x$ MXene in ionic liquid electrolyte.** J Power Sources 2016, **326**:575–579.
46. Dall'Agnese Y, Rozier P, Taberna P-L, Gogotsi Y, Simon P: **Capacitance of two-dimensional titanium carbide (MXene) and MXene/carbon nanotube composites in organic electrolytes.** J Power Sources 2016, **306**:510–515.
47. Jäckel N, Krüner B, Van Aken KL, Alhabeb M, Anasori B, Kaasik F, Gogotsi Y, Presser V: **Electrochemical in situ tracking of volumetric changes in two-dimensional metal carbides (MXenes) in ionic liquids.** ACS Appl Mater Interfaces 2016, **8**(47):32089–32093.
48. Xu K, Lin Z, Merlet C, Taberna PL, Miao L, Jiang J, Simon P: **Tracking ionic rearrangements and interpreting dynamic volumetric changes in two-dimensional metal carbide supercapacitors: a molecular dynamics simulation study.** ChemSusChem 2017. <https://doi.org/10.1002/cssc.201702068>.
49. Shpigel N, Levi MD, Sigalov S, Daikhin L, Aurbach D: **In situ real-time mechanical and morphological characterization of electrodes for electrochemical energy storage and conversion by electrochemical quartz crystal microbalance with dissipation monitoring.** Acc Chem Res 2018, **51**(1):69–79.
50. Levi MD, Daikhin L, Aurbach D, Presser V: **Quartz crystal microbalance with dissipation monitoring (EQCM-D) for *in-situ* studies of electrodes for supercapacitors and batteries: a mini-review.** Electrochem Commun 2016, **67**:16–21.
51. Dargel V, Shpigel N, Sigalov S, Nayak P, Levi MD, Daikhin L, Aurbach D: **In situ real-time gravimetric and viscoelastic probing of surface films formation on lithium batteries electrodes.** Nat Commun 2017, **8**(1):1389 Article number.

In this paper, Electrochemical electrochemical quartz-crystal microbalance with dissipation (EQCM-D) monitoring measurements were performed to probe the formation of surface films on composite $\text{Li}_4\text{Ti}_5\text{O}_{12}$ electrode coupled with lithium ions intercalation into this electrode.

52. Gabrielli C, Keddam M, Perrot H, Pham MC, Torresi R: **Separation of ionic and solvent transport during charge compensation processes in electroactive polymers by a.c. electrogravimetry**. *Electrochim Acta* 1999, **44**(24):4217–4225.
53. Escobar-Teran F, Arnau A, Garcia JV, Jiménez Y, Perrot H, Sel O: **Gravimetric and dynamic deconvolution of global EQCM response of carbon nanotube based electrodes by Ac-electrogravimetry**. *Electrochem Commun.* 2016, **70**(Suppl. C):73–77.
54. Arias CR, Debiemme-Chouvy C, Gabrielli C, Laberty-Robert C, Pailleret A, Perrot H, Sel O: **New insights into pseudocapacitive charge-storage mechanisms in Li-birnessite type MnO_2 monitored by fast quartz crystal microbalance methods**. *J Phys Chem C* 2014, **118**(46):26551–26559.
- AC-electrogravimetry (ac-EQCM) was used for the first time for studying pseudocapacitive charge storage mechanism. Results clearly evidence the de-hydration of different cations when transfer to the electrode/electrolyte interfaces. The reaction kinetics and resistance of charged and noncharged species transferred at the electrode/electrolyte interfaces and the number of water molecules in the hydration shell of the ions were estimated as well as the flux of free water.