Supercontinuum generation in titanium dioxide waveguides

Kamal Hammani, Laurent Markey, Manon Lamy, Bertrand Kibler, Juan Arocas, Julien Fatome, Alain Dereux, Jean-Claude Weeber, Christophe Finot

► To cite this version:

Kamal Hammani, Laurent Markey, Manon Lamy, Bertrand Kibler, Juan Arocas, et al.. Supercontinuum generation in titanium dioxide waveguides. FRENCH-ISRAEL Symposium on Non-Linear & Quantum Optics, FRISNO 2015, Mar 2019, Aussois, France. hal-02056911

HAL Id: hal-02056911

<https://hal.science/hal-02056911>

Submitted on 5 Mar 2019

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Kamal HAMMANI, Laurent MARKEY, Manon LAMY, Bertrand KIBLER, Juan AROCAS, Julien FATOME, Alain DEREUX, Jean-Claude WEEBER and Christophe FINOT

Laboratoire Interdisciplinaire Carnot de Bourgogne, UMR 6303 CNRS-Université de Bourgogne Franche-Comté, 9 avenue, Alain Savary, 21 000 Dijon, France

kamal.hammani@u-bourgogne.fr

INTRODUCTION

Optical supercontinua are a fundamental topic that has stimulated a tremendous practical interest since the early works of Alfano et al. in the 70's in bulk components. Photonic crystal fibers have then brought some remarkable potentialities in tailoring the dispersive properties of a waveguide while maintaining a high level of confinement over significant propagation distances. The next breakthrough is to further reduce the footprint of the nonlinear component and to achieve the generation of optical supercontinuum on a photonic chip. To reach this aim, several platforms have been successfully investigated such as silicon, silicon germanium, silicon nitride, chalcogenide waveguides to cite a few. Each material has obviously specific advantages but also limitations including strong two photon absorption and the associated free carrier absorption, low refractive index, low handling power, etc...

We discuss here the design and fabrication of a new component made on an alternative platform that remains relatively unexplored: **titanium dioxide (TiO₂)**. This material benefits from a transparency window spanning from the visible to the mid-infrared wavelengths. It combines a high linear and nonlinear refractive index with negligible TPA beyond 800 nm. Therefore, recent experimental studies have confirmed these features and reported the spectral broadening of a femtosecond pulse [1], the parametric wavelength conversion of a continuous wave [2] as well as the efficient generation of third harmonic [3].

TiO₂ WAVEGUIDE DESIGN AND FABRICATION

➤ We start from anatase TiO₂ layers with a thickness of 450 nm that are deposited on a 2" silicon wafer.

➤ 2.2 cm-long ridge waveguides with different widths are patterned thanks to an UV lithography.

➤ After the reactive ion etching, the residual mask is stripped from the waveguides.

➤ Propagation losses around 5 dB/cm are obtained.

➤ Reduction of the losses can be reached in the near future.

➤ The high contrast between the TiO₂ (n=2.35) and the silica layer (n = 1.44) or the surrounding air is highly beneficial for a strong light confinement.

Scanning Electron Microscope image of the cleaved strip TiO₂ waveguide

Mode profiles at 1640 nm and associated effective index for the first transverse electric (TE) and transverse magnetic (TM). Numerical simulation using COMSOL Multiphysics.

➤ 4 optical modes can be sustained.

➤ The TE_{0,0} mode has an effective area of 0.54 μm², leading to a nonlinear coefficient of 1.2 /W/m.

Dispersion profiles of the fundamental TE_{0,0} and TM_{0,0} modes of the 1.5 μm wide waveguide.

➤ Operating in the anomalous regime of dispersion is crucial to obtain an energy efficient spectral broadening. However TiO₂ exhibits a material dispersion that is strongly normal : the waveguide dispersion will be crucial.

➤ For a transverse width below 1.5 μm, this condition is met at the pump wavelength for the TE_{0,0} mode.

➤ The TM_{0,0} mode remains strongly normal.

➤ In order to optimize the coupling of light, two 1-mm long tapers have been included in the device.

Optical microscope image of the taper used for the coupling.

EXPERIMENTAL DEMONSTRATION

➤ The first experimental demonstration of an octave spanning supercontinuum in TiO₂.

Visible light emitted from the waveguide.

➤ Third-harmonic generation in the visible due to the existence of phase-matched higher-order modes.

➤ The central part of the supercontinuum is bounded by a self-frequency shifted soliton.

➤ Dispersive waves bound the lower part.

➤ Supercontinuum is only achieved in the TE mode thanks to the anomalous dispersion regime.

Optical supercontinua measured at the output of the TiO₂ waveguide for various coupled energy conditions.

NUMERICAL SIMULATIONS

➤ The experimental results are qualitatively reproduced by numerical simulations of the generalized nonlinear Schrödinger equation taking into account the full dispersion profile and the Raman contribution.

$$\frac{\partial A}{\partial z} = -\frac{\alpha}{2}A + \sum_{k \geq 1} \frac{\beta_k}{k!} \frac{\partial^k A}{\partial z^k} + i \gamma \left(1 + \tau_{\text{shock}} \frac{\partial}{\partial t} \right) \left(A(z, t) \int_{-\infty}^{+\infty} R(t') \times |A(z, t-t')|^2 dt' \right)$$

dispersive effects
Kerr nonlinearity
linear losses
Raman contribution

The nonlinear dynamics is mainly driven by Raman soliton self-frequency shift and generation of dispersive waves induced by the two zero dispersion wavelengths.

Numerical simulations of supercontinuum generation obtained in a 1.5-μm-wide TiO₂ waveguides for different input energies.

EXPERIMENTAL SETUP

➤ Femtosecond input pulses with a kW peak power are used.

➤ Butt coupling and lensed fibers are used for launching and collecting light.

➤ Due to the silica Raman response of the fiber components (polarization controllers, attenuators and lensed fibers), the central wavelength of the ultrashort pulses is shifted up to 1640 nm. The output pulse have a soliton-like profile with a duration of 90 fs.

REFERENCES

- [1] C. C. Evans, K. Shtyrkova, J. D. B. Bradley, O. Reshef, E. Ippen, and E. Mazur, "Spectral broadening in anatase titanium dioxide waveguides at telecommunication and near-visible wavelengths," Opt. Express 21, 18582-18591 (2013).
- [2] X. Guan, H. Hu, L. K. Oxenløwe, and L. H. Frandsen, "Compact titanium dioxide waveguides with high nonlinearity at telecommunication wavelengths," Opt. Express 26, 1055 (2018).
- [3] C. C. Evans, K. Shtyrkova, O. Reshef, M. Moebius, J. D. B. Bradley, S. Griesse-Nascimento, E. Ippen, and E. Mazur, "Multimode phase-matched third-harmonic generation in sub-micrometer-wide anatase TiO₂ waveguides," Opt. Express 23, 7832 (2015).

K. Hammani, L. Markey, M. Lamy, B. Kibler, J. Arocas, J. Fatome, A. Dereux, J.-C. Weeber, C. Finot, « Octave spanning supercontinuum in titanium dioxide waveguides », Applied Sciences, 8, 543 (2018).