Giant hybrid polymer/lipid vesicles (Chapter 27)

Thi Phuong Tuyen Dao, K. Ferji, Fabio Fernandes, Manuel Prieto, Sébastien Lecommandoux, Emmanuel Ibarboure, Olivier Sandre, Jean-François Le Meins

► To cite this version:

Thi Phuong Tuyen Dao, K. Ferji, Fabio Fernandes, Manuel Prieto, Sébastien Lecommandoux, et al.. Giant hybrid polymer/lipid vesicles (Chapter 27). Rumiana Dimova; Carlos Marques. The Giant Vesicle Book, CRC Press - Taylor and Francis group, pp.543-561, 2019, 9781498752176. 10.1201/9781315152516-27 . hal-02314403

HAL Id: hal-02314403

<https://hal.science/hal-02314403>

Submitted on 12 Oct 2019

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

GIANT HYBRID POLYMER/LIPID VESICLES

Thi Phuong Tuyen Dao^{1,2,3}, Khalid Ferji^{1,2}, Fabio Fernandes³, Manuel Prieto³, Sébastien Lecommandoux^{1,2}, Emmanuel Ibarboure^{1,2}, Olivier Sandre^{1,2}, Jean-François Le Meins^{1,2}

1. *Univ. Bordeaux, Laboratoire de Chimie des Polymères Organiques, UMR5629 ENSCBP
16 avenue Pey Berland 33607 Pessac cedex, France*
2. *CNRS, LCPO UMR5629, 33607 Pessac cedex, France*
3. *Centro de Quimica-Fisica Molecular, Complexo Interdisciplinar, IST Universidade de Lisboa, Av. Rovisco Pais 1049-001 Lisbon, Portugal*

Contact Author Email: lemeins@enscbp.fr

Motto:

A compromise is the art of dividing a cake in such a way
that everyone believes he has the biggest piece.

Ludwig Erhard

Index words:

Amphiphilic copolymer
Cell membrane model
Domain formation
Drug delivery
Hybrid membrane
Hybrid vesicle
Hydrophobic mismatch
Line tension
Lipid segregation
Liposome
Membrane properties
Membrane structures
Membrane tension
Microdomain
Multicomponent membrane
Nanodomain
Phase coexistence
Phase separation
Phospholipid
Polymersome

List of abbreviations:

AFM	Atomic-force microscopy
Biotinyl DSPE	1,2-distearoyl- <i>sn</i> -glycero-3-phosphoethanolamine- N-[biotinyl(poly(ethylene glycol))]-2000
Chol	Cholesterol
Ch-PEG- <i>b</i> -hbPG	Cholesteryl-poly(ethylene oxide)- <i>b</i> - poly(glycerol)
DC13PC	2-Ditridecanoyl- <i>sn</i> -glycerophosphocholine
DLPC	1,2-dilauroyl- <i>sn</i> -glycero-3-phosphocholine
DMPC	1,2-dimyristoyl- <i>sn</i> -glycero-3-phosphocholine
DOPC	1,2-dioleoyl- <i>sn</i> -glycero-3-phosphocholine
DPPC	1,2-di-palmitoyl- <i>sn</i> -glycero-3-phosphocholine
DDS	Drug delivery system
Egg Liss Rhod PE	L- α - Egg-phosphatidylethanolamine-N-(Lissamine Rhodamine B-Sulfonyl)
hLUVs	Hybrid large unilamellar vesicles
FITC	Fluorescein isothiocyanate
FRAP	Fluorescence recovery after photobleaching
FRET	Fluorescence resonance energy transfer
hGUVs	Hybrid giant unilamellar vesicles
HSPC	L- α -phosphatidylcholine, hydrogenated (Soy)
Liss-Rhod PE	1,2-dioleoyl- <i>sn</i> -glycero-3-phosphoethanolamine-N-(lissamine rhodamine B sulfonyl)
NBD	nitrobenzoxadiazole
PBd	Poly(butadiene)
PBd- <i>b</i> -PEO	Polybutadiene- <i>b</i> -poly(ethylene oxide)
PC	Egg-phosphatidylcholine
PDMS	Poly(dimethyl siloxane)
PDMS- <i>b</i> -PMOXA	Poly(dimethylsiloxane)- <i>block</i> -poly(methyloxazoline)
PDMS- <i>g</i> -PEO	Poly(dimethylsiloxane)- <i>graft</i> -poly(ethylene oxide)
PE	Egg-phosphatidylethanolamine
PEO	Poly(ethylene oxide)
PIB	Poly(isobutylene)
PIB- <i>b</i> -PEO	Poly(isobutylene)- <i>b</i> -poly(ethylene oxide)
PMOXA	Poly(2-methyloxazoline)
PMOXA- <i>b</i> -PDMS- <i>b</i> -PMOXA	Poly(methyloxazoline)- <i>block</i> -poly(dimethylsiloxane)- <i>block</i> -poly(methyloxazoline)
POPC	1-palmitoyl-2-oleoyl- <i>sn</i> -glycero-3-phosphocholine
ROI	Region of interest
RT	Room temperature
Rh-DHPE	1,2-dihexadecanoyl- <i>sn</i> -glycero-3-phosphoethanolamine-N-(lissamine rhodamine B sulfonyl)
SLS	Static light scattering
SOPC	1-stearoyl-2-oleoyl- <i>sn</i> -glycero-3-phosphocholine

Glossary of symbols:

δ	Hildebrand solubility parameter
K_A	Area compressibility modulus
κ	Bending rigidity of the membrane
c_0	spontaneous curvature
l_{me}	Hydrophobic membrane thickness
T_g	Glass transition temperature
T_m	Melting temperature
τ_D	Time for a probe to diffuse over bleached zone

Outline:

1. INTRODUCTORY WORDS.....	5
2. CRITERIA TO BE FULFILLED TO OBTAIN HYBRID GIANT VESICLES.....	7
2.1. A BRIEF OVERVIEW OF MULTICOMPONENT LIPID VESICLES.....	7
2.2. THE EFFECT OF KEY MOLECULAR PARAMETERS: LIPID FLUIDITY, CHEMICAL INCOMPATIBILITY AND HYDROPHOBIC MISMATCH.....	10
2.3. THE EFFECT OF THE CHEMICAL MODIFICATIONS AND ADDITIVES.....	21
2.4. THE EFFECT OF MACROSCOPIC PARAMETERS: TEMPERATURE, MEMBRANE TENSION	23
3. SPECIFIC ASPECTS OF THE FORMATION OF GIANT HYBRID UNILAMELLAR VESICLES.....	26
4. UNDERSTANDING MEMBRANE PROPERTIES FROM MEMBRANE STRUCTURE	32
4.1. MECHANICAL PROPERTIES, FLUIDITY	33
4.2. PERMEABILITY	44
4.3. SPECIFIC PROPERTIES, BIOFUNCTIONALITY	47
5. CONCLUSION AND PERSPECTIVES	48
REFERENCES	51

1. INTRODUCTION

About 15 years ago, vesicles resulting from the self-assembly of amphiphilic copolymers referred to as “polymersomes” emerged as a potential alternative to liposomes for fundamental research and applications, such as cell membrane models, nano/micro-reactors or drug delivery systems (DDS). (Discher, Won et al. 1999; Discher, Hammer et al. 2000; Discher and Ahmed 2006; LoPresti, Lomas et al. 2009; Le Meins, Sandre et al. 2011; Liao, Wang et al. 2012; Thevenot, Oliveira et al. 2013). Their major characteristics are described and discussed in Chapter 26, to be consulted by readers who are non-specialist in the field before going through the present chapter. This one deals with hybrid, *i.e.* intimately mixed polymer/lipid, vesicles that can be viewed as advanced vesicular structures as compared to their liposome and polymersome forerunners, as they potentially marry in a single membrane the best characteristics of the two separate components. Ideally, these structures could present biocompatibility and bio-functionality of liposomes, as well as robustness, low permeability and functional variability conferred by the copolymer chains. This should be of great interest in pharmaceutical applications for which only a few formulations based on liposomes are commercially available despite decades of research, (e.g. DaunoXome[®], Doxil[®]/Caelyx[®], Visudyne[®]), but also in personal care. In particular such moderate use of liposomes in clinics could be due to their lack of mechanical stability in the high shear rate of blood circulation through tiny vessels. Liposomal DDS can also often exhibit un-controlled leakage phenomena (seen as a “burst release” effect on their pharmacokinetic profiles). As a consequence, the controlled release of encapsulated molecules at the pre-determined biological target (e.g. a tumor site) remains a difficult

Author manuscript version of Chapter 27 published In book: [The Giant Vesicle Book](#), Rumiana Dimova & Carlos Marques Eds. (CRC PRESS Taylor and Francis group, Oct. 7th 2019) challenge. Besides the obvious interest of the association of lipids and amphiphilic copolymers into a single membrane of LUVs for biomedical applications, hybrid giant unilamellar vesicles (hGUVs) can also be an excellent tool to get more insight into molecular and macroscopic parameters that govern the membrane domain formation, fusion or fission. Literature on the subject is still relatively limited (Le Meins, Schatz et al. 2013; Schulz and Binder 2015) although the scientific output is increasing with growing interest from different scientific communities (biophysicists, biologists, physico-chemists). Promising results have been obtained regarding their drug targeting ability and biomolecular recognition properties (Cheng, Elias et al. 2011; Schulz, Werner et al. 2013).

To date, the physical and molecular factors governing the phase separation in these hybrid copolymer/lipid membranes are only partially understood. In addition to the expected chemical incompatibility between copolymer block chains and phospholipids, one also has to consider the respective dimensions of the molecules as well as those of the corresponding bilayers. In order to perfectly benefit from the potential of such systems, the membrane structure must be tuned either towards homogeneous mixing of the molecular components, or on the contrary towards lateral phase separation leading to the presence of nano/micrometric domains. The relationship between membrane structure and physical and bio-functional properties must then be better understood in order to eventually optimize and validate the use of hybrid vesicles in future applications like drug delivery, tumor targeting, bio-recognition or bio-adhesion.

In the present chapter, an overview of hybrid copolymer/phospholipid vesicles will be given with a particular emphasis on hGUVs. The molecular and macroscopic parameters

Author manuscript version of Chapter 27 published In book: [The Giant Vesicle Book](#), Rumiana Dimova & Carlos Marques Eds. (CRC PRESS Taylor and Francis group, Oct. 7th 2019)

necessary to obtain stable hybrid vesicles with different membrane structural levels (homogenous distribution of the components, nano-domain or micro-domain formation) will be first summarized, followed by a description of the different preparation methods used to obtain hGUVs. It has to be noted that hybrid vesicles reported over the last ten years were exclusively prepared by a one-step process by which a film composed of the desired amount of copolymer and phospholipid is hydrated. We will not describe previous approaches based on the modulation of lipid membrane properties by adsorption of amphiphilic polymers onto preformed giant liposomes. Although such a method leads in some cases to a reorganization of the lipid membrane and to the induction of polymer-rich domains – see for instance (Ladavière, Tribet et al. 2002; Tribet and Vial 2007), readers interested by these approaches will find relevant information in Chapter 25 that describes membrane-polymer interactions. Finally, an overview of what is known about membrane properties of hybrid vesicles and especially hGUVs will be proposed. Tips and advices will be given in the two last sections about the preparation protocols of hGUVs and techniques used to characterize their membrane properties.

2. CRITERIA TO BE FULFILLED TO OBTAIN HYBRID GIANT VESICLES

2.1. A BRIEF OVERVIEW OF MULTICOMPONENT LIPID VESICLES

The existing work on hybrid copolymer/lipid vesicle is obviously inspired from all previously acquired knowledge on multicomponent lipid vesicles. These systems have been proposed as tools to understand the structure-properties relationship of biological cell membranes (both of the plasma membrane and that of the internal organelles), which are

Author manuscript version of Chapter 27 published In book: [The Giant Vesicle Book](#), Rumiana Dimova & Carlos Marques Eds. (CRC PRESS Taylor and Francis group, Oct. 7th 2019) constituted of different lipids and membrane proteins ensuring part of the many biological functions of the cell: transport of matter, energy, cell division, signaling pathways...). The lipid composition in the membrane strongly depends on the nature of the cell (eukaryote, prokaryote or archaea) and comprises several classes: glycerophospholipids, sphingolipids, sterols, saccharolipids... This subtle association allows flexibility and fluidity of the membrane and the formation of lipid raft like domains, which can arise from the aggregation of proteins such as clathrin but can also be driven by lipid segregation. Lipid rafts are mainly composed of sphingolipid and cholesterol-rich domains and contain a variety of signaling proteins. It has been established that the lipid rafts play an important role in health and disease (Michel and Bakovic 2007)

Numerous studies have been realized on model GUVs to understand the role of lipid segregation in domain formation (Binder, Barragan et al. 2003; Lipowsky and Dimova 2003), This has been extensively discussed in Chapter 18. We just briefly recall some molecular aspects in phase domain formation. Basically, two types of phase separation in lipid membrane can occur: Lateral phase separation of two lipids into different areas, or orthogonal phase separation between the two leaflets of the lipid bilayer. Orthogonal phase separation can be triggered *via* addition of an external compound (e.g. adsorption of polymer chains...), whereas lateral phase separation can occur through several mechanisms that are mainly through interaction between lipid head groups or tails within the membrane, but also by recruiting mobile “binders” among the lipids into the adhesion area with a substrate (Brochard-Wyart and de Gennes 2002).

Non-ideal mixing or even de-mixing (phase separation) can occur between lipids with

Author manuscript version of Chapter 27 published In book: [The Giant Vesicle Book](#), Rumiana Dimova & Carlos Marques Eds. (CRC PRESS Taylor and Francis group, Oct. 7th 2019) similar structure (e.g. phosphocholine head group with two saturated acyl chains) provided that a sufficient length difference in lipid tails is present (typically four CH₂ groups). In that case, phase separation is obtained below a given temperature of fluid/solid or solid/solid transition. A different nature of the head groups (e.g. charged/neutral) can also lead to phase separation, but in that case the ionic content of the solution is important (e.g. added Ca²⁺ ions, (Cevc and Richardsen 1999)). A strong difference in melting temperatures is generally associated with a strong difference in chemical structures (e.g. sphingolipids and phospholipids) leading to solid/solid or fluid/solid phase separations *versus* temperature. Fluid-fluid phase separation can also occur through weak attractive forces. Cholesterol has been largely employed to modulate the fluidity of membranes and to create phase separation above the main transition temperature of a phosphocholine lipid (e.g. DPPC, DMPC) leading to liquid-ordered and liquid-disordered phase coexistence (Garcia-Saez and Schwille 2010), as seen in Chapter 18. Phase separation leads to lipid/lipid boundaries and possibly to a height mismatch between both phases. Consequently, the membrane elastically deforms at the domain interface to minimize the exposure of hydrophobic tails to water. The height mismatch has an energetic cost proportional to the length of the boundary line, thus defining the line tension. Thermodynamically, the line tension tends to favour domain coalescence (once a nucleation size is reached) to minimize the boundary length. As a consequence, the lipid domains would grow with time into one single large-circular domain in the membrane. However, some distribution of domain sizes can be found in model GUVs and biological membranes. This is due to the fact that the line tension is balanced by other mechanisms such as an “entropic trap” (Frolov, Chizmadzhev et al. 2006)

Author manuscript version of Chapter 27 published In book: [The Giant Vesicle Book](#), Rumiana Dimova & Carlos Marques Eds. (CRC PRESS Taylor and Francis group, Oct. 7th 2019) stabilizing the domains at a nano-metric size, the “elastic interaction” between dimpled domains due to deformation of the surrounding membrane (Ursell, Klug et al. 2009), the long range electrostatic dipolar interaction (Travasset 2006), and the natural vesicle spontaneous curvature c_0 and bending rigidity κ of the membrane (Semrau, Idema et al. 2009; Ursell, Klug et al. 2009; Hu, Weikl et al. 2011).

2.2. THE EFFECT OF KEY MOLECULAR PARAMETERS: LIPID FLUIDITY, CHEMICAL INCOMPATIBILITY AND HYDROPHOBIC MISMATCH

In the case of copolymer and lipid mixtures, a very important parameter controlling the formation of stable hybrid vesicles is the discrepancy of chemical composition and size of hydrophobic segments between polymers and lipids. In the case of lipid mixtures, one has to consider interactions between lipid tails, always constituted of saturated or unsaturated fatty acid chains. However, in the case of polymer/lipid mixture, the nature of monomeric unit may lead to a stronger immiscibility between the hydrophobic copolymer blocks and the lipid tails. In addition, a characteristic thickness of lipid membrane is around 3 to 5nm, well below those commonly observed for polymersomes (~10 nm or more) although this parameter is directly controlled by the polymerization degree (see Chapter 26), and may lead to strong geometric differences between the molecules constituting the membrane and large entropic driving force towards de-mixing. This most often results in phase separation, leading to separate populations of liposomes and polymersomes.

A relatively limited number of amphiphilic copolymers have been used so far to form hGUVs. Hydrophobic blocks were based on poly(dimethyl siloxane) (PDMS) (Chemin, Brun et al. 2012; Chen and Santore 2015), poly(isobutylene) (PIB) (Schulz, Glatte et al. 2011; Schulz,

Author manuscript version of Chapter 27 published In book: [The Giant Vesicle Book](#), Rumiana Dimova & Carlos Marques Eds. (CRC PRESS Taylor and Francis group, Oct. 7th 2019) Werner et al. 2013; Olubummo, Schulz et al. 2014; Schulz, Olubummo et al. 2014) or poly(butadiene) (PBd) (Cheng, Elias et al. 2011; Nam, Beales et al. 2011; Nam, Vanderlick et al. 2012; Lim, de Hoog et al. 2013), while hydrophilic blocks were either made of poly(ethylene oxide) (PEO) or poly(2-methyl oxazoline) (PMOXA). All these polymer blocks possess a low glass transition temperature (T_g), allowing dynamic exchanges of the chains and leading to the formation of membrane with a structure at thermal equilibrium. The low T_g is a criterion which appeared so far as essential, but not unique, to the successful formation of hGUVs. Concerning the choice of lipids, most studies were performed with phosphatidylethanolamine or phosphatidylcholine head groups like POPC (Nam, Beales et al. 2011) (Nam, Vanderlick et al. 2012; Lim, de Hoog et al. 2013), HSPC (Cheng, Elias et al. 2011), DOPC and DLPC (Olubummo, Schulz et al. 2014; Schulz, Olubummo et al. 2014), and the most often used DPPC (Chemin, Brun et al. 2012; Nam, Vanderlick et al. 2012; Schulz, Werner et al. 2013; Schulz, Olubummo et al. 2014; Chen and Santore 2015). An extensive list of systems used so far is given in Table 27-1.

Table 27-1 Composition and membrane structure of hGUVs

Copolymer, molar mass M_n	Lipid	Mass composition Copolymer/Lipid	Membrane structure	Reference
(PMOXA- <i>b</i> -PDMS- <i>b</i> - PMOXA) $M_n=9000 \text{ g}\cdot\text{mol}^{-1}$	PC PE	copolymer/PC/PE: 98%/1%/1%	Homogeneous membranes	(Ruysschaert, Sonnen et al. 2005)
(PBd ₄₆ - <i>b</i> -PEO ₃₀), $M_n=3800 \text{ g}\cdot\text{mol}^{-1}$	POPC	copolymer/POPC: 100%-92%/0%-8%	Homogeneous membranes	(Nam, Beales et al. 2011)
		copolymer/POPC: 90%-73%/10%-27%	No hGUV formation	
		copolymer/POPC: 0% - 68%/100% - 32%	Separated vesicles: liposomes + polymersomes	
		copolymer/POPC/ Biotinyl DSPE: 89%/6%/5%	Heterogeneous vesicles with small lipid domains	
		copolymer/POPC/ Biotinyl DSPE: 64%/28%/8%	Heterogeneous vesicles with large lipid domains	
		copolymer/POPC/ Chol: 84.5%/10.3%/5.2% 76.8%/15.4%/7.8%	Heterogeneous vesicles with micron- sized lipid domains	(Nam, Vanderlick et al. 2012)

		71.4%/23.8%/4.8%		
	DPPC	copolymer/ DPPC: 88.6%/11.4%	-At 50 °C: homogeneous membranes -At room temperature (RT): heterogeneous membranes: lipid domain size and shape depend on cooling rate	
		copolymer/DPPC/ Chol: 86.5%/10%/3.5%	Round DPPC rich domains at RT	
(PBd ₂₂ - <i>b</i> -PEO ₁₄) M _n =1800 g·mol ⁻¹	HSPC	copolymer/HSPC: 95%/5%	Homogeneous vesicles	(Cheng, Elias et al. 2011)
		copolymer/HSPC: 87%/13%		
	POPC	copolymer/POPC: 70%/30%	Homogeneous vesicles	(Lim, de Hoog et al. 2013)
(PIB ₈₇ - <i>b</i> -PEO ₁₇) M _n =5350 g·mol ⁻¹	DOPC	copolymer/DOPC 74%/26% 63%/37%	Homogeneous and stable vesicles	(Schulz, Olubummo et al. 2014)
		copolymer/DOPC 43%/57%	Homogeneous membranes turning into heterogeneous membranes. Budding and fission leading to formation of separated polymersomes and liposomes	
	DPPC	copolymer/DPPC 100%/0%	No hGUVs were formed	(Schulz, Glatte et al. 2011; Schulz, Werner et al. 2013; Schulz, Olubummo et al.
		copolymer/DPPC 92%- 99.85%/8% -0.15%	Homogeneous and small vesicles	
		copolymer/DPPC	Homogeneous vesicles with smooth	

		74%- 91.6%/26% -8.4%	surface	2014)
		copolymer/DPPC 64.6%-74%/35.4%-26%	Heterogeneous vesicles with domains	
		copolymer/DPPC 7%- 54%/93%-46%	Homogeneous membranes with “DPPC aspect”: faceted surface and hole defects	
(PIB ₃₇ - <i>b</i> -PEO ₄₈) M _n =3970 g·mol ⁻¹	DPPC	copolymer/DPPC 57%/43%	Homogeneous vesicle with large holes and “lacerated edges”	(Schulz, Glatte et al. 2011)
		copolymer/DPPC 37.6%/62.4%	Homogeneous membranes but vesicles were neither smooth nor round	
Cholesteryl-poly(ethylene oxide)- <i>b</i> - poly(glycerol) Ch-PEG ₃₀ - <i>b</i> -hbPG ₂₃ M _n = 1100 g·mol. ⁻¹	POPC DLPC DOPC	copolymer/Lipid 1.5%/98.5% 7%/93% 23%/77% 59%/41%	Homogeneous membranes and stable vesicles	(Scholtysek, Shah et al. 2015)
PDMS ₂₂ - <i>g</i> -(PEO ₁₂) ₂ M _n =3200 g·mol ⁻¹	POPC	copolymer/POPC: 86%-97%/14%-3%	Homogeneous vesicles (stable during many days).	(Chemin, Brun et al. 2012)
		copolymer/POPC: 58%- 81%/42%-19%	Unstable biphasic vesicles leading to separated liposomes and polymersomes after a budding and fission process	
	DPPC	copolymer/DPPC: 96%/4%	Homogeneous vesicles membranes	
		copolymer/DPPC: 93%-81%/7%-19%	Stable heterogeneous vesicles with lipid domains	
		copolymer/DPPC:	Separated liposomes and polymersomes	

		59%/41%	and some heterogeneous vesicles containing polymer domains	(Chen and Santore 2015)
		copolymer/DPPC: 99%- 93%/1%-7%	Homogeneous vesicle membranes	
		copolymer/DPPC: 93%-70%/7%-30%	Heterogeneous membranes with hexagonal faceted domains. Shape of domains is independent on cooling rate	
		copolymer/DPPC: 70%-99%/30%-1%/	Heterogeneous membranes at RT. Domain morphologies depend on cooling rate: at 1 °C/min: hexagonal faceted domains at 5°C/min: striped domains	

It is interesting to note that the Hildebrand solubility parameters (δ) (which are derived from the heat of vaporization of a molecule and which reflect its cohesive energy density) of hydrocarbon moieties in hydrophobic polymer blocks and phospholipids are relatively close, that is $\delta = 9.1 \text{ cal}^{1/2}/\text{cm}^{3/2}$ for the fatty acid tail in lipids and $\delta = 7.3 \text{ cal}^{1/2}/\text{cm}^{3/2}$, $7.7 \text{ cal}^{1/2}/\text{cm}^{3/2}$ and $8.32 \text{ cal}^{1/2}/\text{cm}^{3/2}$ respectively for PDMS, PIB and PBd blocks (Roth 1990; King 2002). These relatively close values suggest that the chemical compatibility between the components is indeed a parameter of uppermost importance to enable the formation of such hybrid vesicles even though the lateral phase separation of components inside the membrane still can occur for other reasons, as it will be commented in the following.

In each of the abovementioned contributions, there is no real systematic investigation allowing a clear extraction of molecular and macroscopic parameters necessary to intimately mix the components into stable hGUVs presenting homogeneous distribution of both components, or on the contrary to induce formation of heterogeneous membranes patterned with domains. Moreover, another difficulty arises from the fact that the molar composition of lipid and copolymer in the final hybrid vesicles can be different from the starting composition, as evidenced by fluorescence microscopy, which complicates the analysis of the results. This is inherent to the experimental procedures used so far for the formation of hGUVs which are described in section 3.

The physical state of the lipids, which depends on their main transition temperature (from gel state at $T < T_m$ to fluid state at $T > T_m$, where T_m is the melting temperature) as well as the composition of the lipid / copolymer mixture are among the most relevant parameters. It

seems that at high copolymer content (>70% weight), the formation of homogeneous hybrid vesicles is favored when using a lipid with phosphocholine as head group and fatty chains in a fluid state at room temperature, (Cheng, Elias et al. 2011; Nam, Beales et al. 2011; Nam, Vanderlick et al. 2012; Lim, de Hoog et al. 2013) except in one case where no hGUVs were obtained between 90% and 73% weight fraction of a PBd-*b*-PEO copolymer with a number average molecular weight of 3800 g·mol⁻¹ (Nam, Beales et al. 2011)

Above a critical lipid weight fraction, one generally observes the formation of heterogeneous vesicles presenting lipid-rich micrometric domains, that progressively evolve through a budding and fission phenomenon towards separated liposomes and polymersomes (Chemin, Brun et al. 2012; Schulz, Olubummo et al. 2014). This ultimate phase separation into two pure GUVs occurs for fluid domains in fluid membranes, and is directly linked to a sufficiently high line tension. When the line tension is large enough, the energetic barrier induced by the larger curvature energy associated with membrane budding can be overcome by decreasing the boundary length between the lipid and copolymer domains and the associated excess energy. To get rid of the line energy implies a cost in bending energy, as the curvature of the membrane will increase through the formation of the bud. Therefore line tension between the domains and the bending rigidity of the membrane are two parameters of prime importance.

In copolymer/lipid hybrid vesicles, line tension and bending rigidities can be different to a large extent as compared to their values for lipid/lipid mixtures. The usual membrane (bilayer) thickness is indeed 3–5 nm for liposomes, while it may vary from 5 to 50 nm for polymersomes. In the case of a large size gap, the formation of a lipid domain would result in a high line tension

at the lipid/copolymer boundaries arising from the exposure of hydrophobic polymer segments to water (“hydrophobic mismatch”). To reduce this exposure and the resulting energetic cost of the boundary lines, the two opposite plausible scenarios can be considered. The first one (i) consists in a conformational adaptation through elastic deformation of the polymer chains at the boundary to decrease the line tension (Fig 27-1) in analogy to elastic deformation of membrane at lipid/lipid domain boundary in lipid bilayers (Kuzmin, Akimov et al. 2005). Another possibility (ii) is to decrease the interfacial length and therefore the interfacial energy, by coalescence into fewer domains of a larger area.

In Fig 27-1, which illustrates different properties resulting from the membrane structure and potential applications of hybrid vesicles, it is shown that the conformational adaptation of the polymer implies a collapse of the hydrophobic polymer chains near the lipid interface, therefore reducing the total number of conformations and opposing the entropic elasticity of chains. Therefore, it is clear that the molar mass (or chain length) and the rigidity (or Kuhn length) of the hydrophobic polymer backbone also play a major role. If this adaptation cannot be achieved, then the domain formation is improbable (spontaneously nucleated domains

eventually collapse) and a homogeneous mixture of the components is expected (Fig. 27-1)

Figure 27-1: Illustration of the different membrane structural organization of the membrane in hGUVs and its principal characteristics.

A large hydrophobic mismatch is met in most of the studies performed so far, as the diblock or triblock copolymers most often used, form membranes whose thickness is at least 7nm, and the line tension, although not yet quantified experimentally, is expected to be high and driving the budding and fission of existing fluid domains. However the hydrophobic mismatch is certainly not the only parameter, as the budding and fission of lipid domains have been observed also in a study in which a grafted copolymer, PDMS-*g*-(PEO)₂ well-known to

form vesicles with a membrane thickness close to liposomes (~5nm), was used (Chemin, Brun et al. 2012). In addition to the chemical nature of the hydrophobic block which obviously plays a role in the miscibility with the lipid phase and consequently on the interfacial energy, the architecture of the copolymer may also be an important factor to consider (e.g. *block* copolymer where the different polymers are linearly covalently coupled, vs. *graft* copolymer where polymers chain are distributed along the backbone of another polymer).

The fluidity of the lipid phase is also of significance in the membrane structure of hGUVs. In the case of lipid in the gel state at room temperature, and using a formation protocol described in section 3, the spontaneous formation of micron-sized domains was reported only as a rare event. For instance in one of these studies (Schulz, Glatte et al. 2011), hGUVs presenting stable micrometric domains were spontaneously obtained using DPPC and PIB₈₇-*b*-PEO₁₇, but only in a narrow composition range (65–74 mass% polymer). It is supposed that the large hydrophobic block in that case limited the conformational adaptation at the copolymer–lipid boundary. The large hydrophobic thickness (~10 nm) plays in favor of a statistic distribution of the lipid in the copolymer phase as sketched on Fig 27-1. Interestingly, homogeneous vesicles, at least at the micrometric scale, were observed for all copolymer contents larger than 30 mol%, (or 75 weight%). Below 60 weight%, homogeneous vesicles presenting faceted surfaces were obtained, which is the signature of the DPPC gel phase. As described above, using a copolymer presenting a membrane thickness close to that of liposomes, allows the spontaneous formation of micrometric lipid domains in hGUVs in a large polymer content range (from 10% to 93% in weight). Above 93%, the lipid is apparently

dispersed in the polymer phase and homogenous vesicles can be observed microscopically. Ideally the homogenous or heterogeneous character of the hGUVs can be easily observed under fluorescence microscopy by including a small amount of fluorescently tagged polymer and lipid in the initial mixture, such as Fluorescein modified polymer and Egg Liss Rhod PE for instance. In homogeneous hybrid vesicles, both signal of the fluorescent probes are observed within the entire membrane, whereas in heterogeneous hybrid vesicles, the probes preferentially partition into the polymer and lipid rich phases, as illustrated in Figure. 27-2.

Figure 27 2: Overlay of maximum intensity 3D projection images taken for A: homogeneous hGUV with the homogeneous distribution of both signals; B: de-mixed hGUV with green polymer-rich phase and red lipid rich phase. The scale bars are 5 μm . Acknowledgment to the publication Dao, T. P. T., F. Fernandes, et al. (2017). [Soft Matter](#) **13**(3): 627-637. (Royal Society of Chemistry)

2.3. THE EFFECT OF THE CHEMICAL MODIFICATIONS AND ADDITIVES

Obtaining polymer-rich vesicles with stable lipid-rich domains of controlled micrometric or nanometric size would be of great interest for different kinds of functions in drug-delivery systems, bio-targeting or biophysical fundamental studies, such as the modeling of nanoparticles/membrane interactions and cellular internalization (“artificial endocytosis”). The

use of lipids in the fluid state, which is probably the most interesting, regarding the abovementioned applications, leads only to homogeneous hGUVs (i.e. at the micrometric scale, as appearing under an optical microscope). Other approaches involving the use of additional components have been used to generate a stable phase-separated membrane from a mixture of a copolymer with a mixture of several fluid lipids. For instance, with lipids presenting biotinylated head-groups, stable micrometric domains can be generated in hybrid vesicles by reacting them with streptavidin (in solution). This protein with multivalent binding sites for biotin works as a “zipper” to gather the lipid molecules together in pure lipid phases or “monodomains”. However, such a protein coating prevents further bio-functionalization of the domains (Schulz, Glatte et al. 2011). Another approach consists in using a lipid mixture containing a given amount of cholesterol, which is well-known to promote lateral phase separation into “raft-like” domains within liposomes for particular lipid compositions such as Chol/PC/SM mixtures (Bagatolli and Kumar 2009). This induces the same effects on hybrid copolymer/lipid vesicles in which round-shaped micrometric domains can be obtained with various phospholipids of low melting temperature T_m (DLPC, POPC, DC13PC...). Interestingly, the domain size could be modulated *via* the polymer/lipid/cholesterol composition. However, no domain formation can be obtained when using DOPC, even at high cholesterol content, in agreement with what is commonly observed for DOPC/cholesterol mixtures which are not known to form liquid ordered phase bilayers (Mills, Toombes et al. 2008). Regarding the hydrophobic mismatch, it has also been observed *via* cryo-TEM experiments on LUVs made of mixtures of PDMS-*b*-PMOXA and cholesterol that the vesicles obtained present lower

membrane thickness compared to pure polymersomes. This was explained by an increase of the packing density in the membrane through the support of static light scattering measurements (Winzen, Bernhardt et al. 2013). This approach could be useful to control the hydrophobic mismatch in hybrid lipid/copolymer giant vesicles.

2.4. THE EFFECT OF MACROSCOPIC PARAMETERS: TEMPERATURE, MEMBRANE TENSION

Forming hybrid copolymer/lipid vesicle containing a lipid with a melting temperature above room temperature implies a particular attention towards the process of vesicle formation. Generally, the film hydration method to prepare hGUVs is conducted at a temperature above the melting transition of the lipid. Then the vesicle suspension is cooled down to room temperature. It has been shown that the cooling rate plays a role on the resulting membrane structuration in hGUVs made of PBd-*b*-PEO and DPPC (Nam, Vanderlick et al. 2012). A fast cooling rate results in the formation of numerous small domains, whereas a slow cooling rate favours formation of less numerous domains but larger in size, in agreement with the classical nucleation-growth theory.

In two-component phosphatidylcholine GUVs, it has been shown that membrane tension could affect the fluid-solid phase transition of lipid and consequently the membrane structuration (Chen and Santore 2014). The same effect has been observed recently on hybrid vesicles made of PDMS-*g*-(PEO)₂ and DPPC (Chen and Santore 2015). Using vesicles conditioned in a way that they did not present excess membrane area, the authors were able to tune the membrane tension by using different cooling rates after vesicle formation by electro-formation

at high temperature (see section 3). The cooling causes a contraction of both the water solution and the membrane. As the membrane contracts more than the water in the compartment of the vesicle, a membrane surface tension appears, as estimated by a micropipette pulling experiment. Thereafter the membrane stress obviously relaxes as water diffuses progressively out of the vesicle. The authors were able to measure the membrane tension immediately after cooling to the temperature of interest, and a clear influence of cooling rate was shown on the membrane tension. Actually the membrane tension measured is maximal at intermediate cooling speed: A too small cooling rate allows membrane tension to relax by water diffusion by permeability, while a too fast quench induces stress relaxation through the membrane lysis and leaking by transient pore formation.

Figure 27-3: a) Illustration of the variation of membrane tension resulting from different cooling rates after preparation onto the membrane structuration: examples on vesicles containing 70% mol (39 mass%) DPPC and 30%mol (61% mass) PDMS-*g*-(PEO)₂; b) Images of vesicles submitted to different cooling and osmotic control. (Reproduced from Chen, D. and M. M. Santore (2015), *Soft Matter* 11(13): 2617-2626, with permission, copyright Royal Society of Chemistry).

At low surface tension, patchy domains were generally obtained whereas higher tension leads to striped domains. The physical state of the DPPC phase (ripple phase $P_{\beta'}$, solid or gel phase L_{β}) inside these stripes or patchy domains is still under debate in literature (Gordon, Beales et al. 2006; Bernchou, Brewer et al. 2009) (Chen and Santore 2015)).

Finally, the structure of hGUVs containing high melting temperature lipids (e.g. DPPC) has been rarely commented above the transition temperature T_m . Our team has started to evaluate the behaviour of hGUVs composed of PDMS-*g*-(PEO)₂/DPPC previously studied at room temperature (Chemin, Brun et al. 2012) following an electro-formation process realized at 55°C and storage conditions of the sample at 55°C. The sample was transferred as quickly as possible in a temperature-controlled stage at 55°C, in order to maintain the lipid phase in a continuous fluid (liquid disordered) state. Observations were made after different incubation times at 55°C, from 4h to 20h (Fig 27-4). L- α -phosphatidylethanolamine-N-(lissamine rhodamine B sulfonyl) (Liss-Rhod PE) was used to reveal the lipid-rich phase (0.2% mol), and copolymer grafted with fluorescein was added to reveal the polymer-rich phase (1% mol). It appeared that the fluorescent lipid (Liss Rhod PE) was excluded from the DPPC domains, although they were in the fluid state as attested by the rounded boundary between the polymer and lipid domains. After a long incubation time, the Liss Rhod PE repartitioned entirely into the more disordered polymer phase, which turned from green to yellow-orange. The most interesting feature is that the interface length between the lipid and polymer phases clearly increased, suggesting that a kind of compatibility increase occurred with time, and that such structures are strongly out-of-equilibrium in their early stage of formation.

Figure 27-4: 3D reconstructions of confocal microscopy images of PDMS-g-(PEO)₂/DPPC (90/10 mass) vesicles loaded with Liss-Rhod PE (red) and Fluorescein-PDMS-g-(PEO)₂ (green) observed at 55°C after different incubation times at 55°C. Scale bar is 10µm.

3. SPECIFIC ASPECTS OF THE FORMATION OF GIANT HYBRID UNILAMELLAR VESICLES

Most of the knowledge acquired in the past ten years about hybrid copolymer/lipid vesicles result from studies performed on GUVs formed by the two well-known methods of rehydration or electro-formation (see Chapter 1) from copolymer/lipid mixtures as applied in (Ruysschaert, Sonnen et al. 2005; Cheng, Elias et al. 2011; Nam, Beales et al. 2011; Schulz, Glatte et al. 2011; Chemin, Brun et al. 2012; Nam, Vanderlick et al. 2012; Lim, de Hoog et al. 2013; Schulz, Werner et al. 2013; Schulz, Olubummo et al. 2014; Chen and Santore 2015; Scholtysek, Shah et al. 2015) and summarized in Table 27-2. A few examples report the preparation of hGUVs using mixed suspensions of giant phospholipid liposomes and polymersomes and the triggering of their adhesion followed by membrane fusion, by using temperature-responsive copolymers, or salt addition (Henderson and Paxton 2014; Morimoto, Sasaki et al. 2014). The ability of these methods to be extended to different polymer/lipid mixtures has not been confirmed so far. It has to be noted that simple film rehydration was

Author manuscript version of Chapter 27 published In book: [The Giant Vesicle Book](#), Rumiana Dimova & Carlos Marques Eds. (CRC PRESS Taylor and Francis group, Oct. 7th 2019)

used by Tsourkas and coll. (Cheng and Tsourkas 2008; Cheng, Elias et al. 2011) to obtain hGUVs of HSPC phospholipid and PBd₂₂-*b*-PEO₁₄ block copolymer, with long incubation time (24h) in an aqueous solution of sucrose at 65°C, but electro-formation is definitely the most commonly used technique. Practical tips about the preparation and collecting of hGUVs are described in Box 27-1.

Table 27-2 Preparation methods for obtaining hGUVs (l_{me} : hydrophobic membrane thickness).

Copolymer, molecular weight, membrane thickness	Lipid (phase state)	Preparation technique	Reference
PMOXA- <i>b</i> -PDMS- <i>b</i> -PMOXA $M_n=9000 \text{ g}\cdot\text{mol}^{-1}$ $l_{me}=14 \text{ nm}$	PC (fluid) PE (fluid) $l_{me}=3-4 \text{ nm}$	Electro-formation method ITO coated glass: 5V, 10Hz, 3 hours followed by 5V, 0.5Hz 30 min	(Ruysschaert, Sonnen et al. 2005)
PBd ₄₆ - <i>b</i> -PEO ₃₀ $M_n=3800 \text{ g}\cdot\text{mol}^{-1}$ $l_{me}=9 \text{ nm}$	POPC (fluid)	Electro-formation method platinum electrodes: 3V, 11Hz several hours, at RT in sucrose solution (260 mOsm).	(Nam, Beales et al. 2011)
	DPPC (gel)	Electro-formation method platinum electrodes: 3V, 15Hz, at 50°C, in sucrose solution (260 mOsm)	(Nam, Vanderlick et al. 2012)
PBd ₂₂ - <i>b</i> -PEO ₁₄ $M_n=1800 \text{ g}\cdot\text{mol}^{-1}$ $l_{me}\sim 7 \text{ nm}$	HSPC (fluid)	Film rehydration in sucrose solution (285 mM), incubating at 65 °C during 24h	(Cheng, Elias et al. 2011)
	POPC (fluid)	Electro-formation method ITO coated glass: 3V, 10Hz, at 45°C in sucrose solution (at 300 mM) during 120 min	(Lim, de Hoog et al. 2013)

<p>PIB₈₇-<i>b</i>-PEO₁₇ M_n=5350 g·mol⁻¹ <i>l</i>_{me} = 10 nm</p>	<p>DOPC (fluid) DPPC (gel)</p>	<p>Electro-formation method ITO-coated glass electrodes: 1.3V, 10Hz at 70°C during 4 hours</p>	<p>(Schulz, Glatte et al. 2011; Schulz, Werner et al. 2013; Schulz, Olubummo et al. 2014)</p>
<p>Poly(isobutylene)-<i>b</i>-poly(ethylene oxide) (PIB₃₇-<i>b</i>-PEO₄₈) M_n=3970 g·mol⁻¹</p>			
<p>Poly(dimethylsiloxane)-graft-poly(ethylene oxide) PDMS₁₂-<i>g</i>-(PEO)₂ M_n=2700 g·mol⁻¹ <i>l</i>_{me} =5 nm</p>	<p>POPC (fluid)</p>	<p>Electro-formation method ITO coated glass: 2V, 10Hz, at RT during 20 min</p>	<p>(Chemin, Brun et al. 2012)</p>
	<p>DPPC (gel)</p>	<p>Electro-formation method ITO coated glass: 2V, 10Hz at 50°C during 20 min.</p>	
		<p>Electro-formation method platinum wire electrodes: 3 V, 10 Hz during 1 hour at 52 °C</p>	<p>(Chen and Santore 2014)</p>

PROTOCOL BOX STARTS HERE

Box 27-1 Practical method for obtaining hGUVs *via* electro-formation

Preparation of hGUVs using this method is made in three steps:

Step 1: Solution preparation

Organic solution of lipids and copolymers are prepared and then mixed in order to reach the desired composition. Typically, chloroform or a mixture of chloroform and MeOH (2/1 v/v) are the solvents most often used. The concentration range (copolymer+lipid) is typically around $1\text{mg}\cdot\text{mL}^{-1}$. If hybrid vesicles are meant to be studied with fluorescence or confocal microscopy analyses, a tagged lipid should be included to reveal the lipid phase. Typically the use of Liss-Rhod PE gives good results at 0.2% molar ratio. Co-localization can also be performed using fluorescently tagged copolymers that have to be synthesized. If fluorescein or NBD is used as fluorescent moiety, a larger amount of copolymer probe should be used for visualization, e.g. 1% molar, because of the lower quantum yields and tendency of photo-bleaching of these dyes compared to rhodamine.

Step 2: Film deposition

Films are prepared by spreading around 10 μL of the lipid/copolymer solution slowly over an area of about 2 cm diameter of an electrically conductive surface. Most often used are platinum electrodes and glass plates coated with indium tin oxide (ITO glass plates of surface resistivity $15\text{-}25\Omega/\text{square}$). Surfaces must be cleaned with ethanol and chloroform before use. In the case of ITO plates, a *Hamilton* syringe with tapered needle is used to deposit the solution and also to gently scratch the film and generate irregularities that will help film swelling and

vesicle formation. No additional benefit is observed on the amount of vesicle obtained, size distribution or homogeneity of composition by forming the film by spin-coating. Then the film is dried out under dynamic vacuum for at least 5hrs. A too short drying time can lead, after the hydration step to the formation of vesicles presenting “lipid filaments” on their surface.

Step 3: Electro-swelling

Film rehydration under an alternative electric field is performed most often in a glucose or sucrose solution to set the osmolarity of the buffer, defined as the total amount of soluble species per kg of solution, and checked for instance by a freezing point osmometry measurement. As illustrated in Table 27-2, there is no real tendency that can be extracted in terms of voltage applied or duration of electro-formation. However, from our personal experience, it seems that at least 5V is needed for molar masses of hydrophobic block above 5000 g·mol⁻¹. Temperature is also a parameter of great importance. Obviously electro-formation must be realized above the main chain transition temperature of the lipid used, but even in the case of lipids fluid at room temperature (e.g. POPC), temperature have to be controlled and slightly increased (~30-40°C) when using polymers with long hydrophobic blocks >5000 g·mol⁻¹. To extract a solution containing giant vesicles, it is recommended to use a syringe with at least a 0.8 mm internal diameter (gauge ≤ 21 G) of the needle in order to minimize shear stress. During electro-formation, some vesicles remain stuck on the conductive surfaces. To detach them, two methods are used depending on the type of surfaces employed. In case of platinum electrodes, gently manually shaking the electrode in the hydration medium is sufficient to detach vesicles. However, when ITO glass plates are used, GUVs are detached by

turning (or rolling) around a bubble created in the chamber by taking out a few drops of solution (see image below).

PROTOCOL BOX ENDS HERE

4. UNDERSTANDING MEMBRANE PROPERTIES FROM MEMBRANE STRUCTURE

The purpose of this section is to describe some of the properties of the hybrid giant unilamellar vesicles which were characterized so far, and try to point out a correlation between those properties and their membrane structure at macro- or nanoscale. Considering the intrinsic differences between lipid and copolymer membranes as illustrated in the Chapter 26, in terms of bio-functionality and physical properties, it can be reasonably expected that lipid polymer mixtures provide numerous ways to modulate the membrane properties, provided that a good control of membrane composition and structure is achieved. In this part, the mechanical properties, permeability, fluidity, and bio-functionality will be discussed in priority, while stability and deformability will also be cursory mentioned.

4.1. MECHANICAL PROPERTIES, FLUIDITY

Two essential features are often analyzed on giant vesicles because of their importance in biological events (resistance of cells to osmotic shock, cell fission and fusion, cell motility ...) or drug delivery (resistance in the high shear rate of blood circulation through tiny vessels such as capillaries). They are related to their ability to resist to isotropic area dilation, and to deform from an initially flat surface into a curved structure, see Chapter 5. They are respectively quantified through the area compressibility modulus K_A , which is linked to the interfacial tension at the junction between hydrophilic and hydrophobic moieties of the membrane, and the bending rigidity of the membrane κ (also called bending modulus) that appears in the Helfrich expression of the curvature energy that becomes non-negligible for nearly zero surface tension systems like micro-emulsions and lipid bilayers. As illustrated in Chapter 15 and Chapter 26, K_A and κ from liposomes and polymersomes are rather different (see also Table 15-1 in Chapter 15) and they can be modulated to some extent by the hydrophobic block length and membrane thickness for polymersomes. This is clearly illustrated in Tables 27-3 and 27-4. Another important point to mention is the much larger lysis strain of the polymersomes, ascribed to a higher cohesive energy density between the molecules constituting the membrane. On the contrary, the excess area defined by subtracting the projected area A_p from the total true surface area of the membrane seems to be much lower for giant polymersomes than for giant liposomes, which explains why it is very difficult to extract the bending modulus κ from the very limited “entropic regime” in a micropipette pulling experiment.

Therefore, when mixing copolymer and lipid in a single membrane, a modulation of these properties can be expected, obviously by playing on the lipid/copolymer composition. Subtle modifications can also probably be obtained through precise membrane structuration. Interestingly, the area compressibility modulus has only been measured on hybrid vesicles through the help of the micropipette aspiration technique in recent studies. In their early work on hybrid vesicles in 2011, (Cheng, Elias et al. 2011) Cheng *et al.* reported that homogeneous hybrid vesicles composed of poly(butadiene)-*b*-poly(oxyethylene) (PBD₂₂-*b*-PEO₁₄) and hydrogenated soy phosphatidylcholine (HSPC) exhibited an intermediate elastic stretching modulus between the values of pure lipid and pure polymer vesicles. Similar results for hybrid vesicles composed of PBD₄₆-*b*-PEO₃₀ and POPC were also indicated (Nam, Beales et al. 2011). Although there was a rather large composition range where hybrid vesicles could not be formed, the remaining fractions showed distinctly a gradual decrease in K_A with increasing copolymer content (Fig 27-5). It has to be noted that in the above-mentioned contributions, the hGUVs obtained presented a homogeneous membrane structure, at least at the micron scale studied by optical microscopy. A recent study has focused on hGUVs composed of poly(dimethylsiloxane)-*graft*-poly(ethyleneoxide) PDMS₂₂-*g*-(PEO₁₂)₂ and 1,2-di-palmitoyl-sn-glycero-3-phosphocholine (DPPC) which is at the gel state at room temperature. In this system, it was shown by our group (Chemin, Brun et al. 2012) that heterogeneous membranes (presence of micrometric domains) could be obtained at room temperature in a large composition range. The main results of the Santore group have been described in Section 2.4 of this chapter. However they also performed some mechanical measurements through

micropipette aspiration on these heterogeneous membranes presenting lipid gel domains. In the case of data obtained without having lipid micrometric domains entering in the micropipettes (therefore by stretching the copolymer part of the membrane), they obtained stretching modulus similar to the pure copolymer membrane within the uncertainty of the measurement (Chen and Santore 2015) for hybrid vesicles containing 70 mol% of DPPC (39 mass%). Very interestingly, the lysis strain was still very high and similar to the lysis strain of pure polymersomes, despite the potential fragility that could result from the interfaces at the copolymer/lipid boundaries. This shows clearly that the mechanical properties of hybrid membranes can be directly linked to their lateral structure.

Table 27-3. Area compressibility modulus (K_A) of different liposomes and polymersomes

Lipid	K_A (mN/m)	Copolymer	K_A (mN/m)
POPC, RT	198 ± 8 (Shoemaker and Vanderlick 2003)	PEO- <i>b</i> -PBBdt, RT	102 ± 10 (Bermudez, Brannan et al. 2002)
DOPC, 15°C	310 ± 20 (Rawicz, Smith et al. 2008)	PEO- <i>g</i> -PDMS, RT	95 ± 9 (Chen and Santore 2015)
SOPC, 15°C	290 ± 6 (Rawicz, Smith et al. 2008)	PEO- <i>b</i> -PBd, RT	102 ± 10 (Bermúdez, Hammer et al. 2004) 470 ± 15 (Dimova, Seifert et al. 2002) 112 ± 20 (Nam, Beales et al. 2011)
HSPC, > T _m	206 (Cheng, Elias et al. 2011)	PEO- <i>b</i> -PEE, RT	120 ± 20 (Discher, Won et al. 1999)
DMPC, 29°C	234 (Bermúdez, Hammer et al. 2004)		
DPPC, > T _m	~ 200 (Chen and Santore 2015)		

Table 27-4. Bending modulus (κ) of different liposomes and polymersomes

Lipid	Bending modulus (κ) (10 ⁻¹⁹ J)	Polymer	Bending modulus (κ) (10 ⁻¹⁹ J)
POPC, 25°C	1.58 ± 0.03 (Henriksen, Rowat et al. 2004)	PDMS ₆₀ - <i>b</i> -PMOXA ₂₁ ,	101 ± 23 (Winzen, Bernhardt et al. 2013)
DOPC, 23°C	1.08 ± 0.1 (Gracia, Bezlyepkina et al. 2010)	PDMS ₆₈ - <i>b</i> -PMOXA ₁₁ , RT	70 ± 50 (Jaskiewicz, Makowski et al. 2012)
SOPC, 18°C	0.9 ± 0.06 (Evans and Rawicz 1990)	PEO ₂₆ - <i>b</i> -PBd ₄₆ , RT	1.02 ± 0.46 (Bermúdez, Hammer et al. 2004)
Egg PC, RT	0.3 ± 0.1 (Evans and Rawicz 1990)	PEO ₈₀ - <i>b</i> -PBd ₁₂₅ , RT	19.1 ± 6.4 (Bermúdez, Hammer et al. 2004)
DPPC, RT	10-15 (Jaskiewicz, Makowski et al. 2012)	PEO ₄₀ - <i>b</i> -PEE ₃₇ , RT	1.37 ± 0.29 (Bermúdez, Hammer et al. 2004)
DMPC, 29°C	0.56 ± 0.06 (Evans and Rawicz 1990)	PS ₁₁₅ - <i>b</i> -PAA ₁₅ , RT	716 ± 103 (Chen, Schonher et al. 2009)

Figure 27-5. (a) Areal stretching modulus K_A (■) and lipid lateral diffusion coefficient D (○) for varying compositions of hGUVs. (b) Critical lysis tension (■) and lysis strain (□) of POPC/PBd-*b*-PEO GUVs. HLP-GUVs: Hybrid lipid-diblock copolymer giant unilamellar vesicles. Adapted from Nam, J., P. A. Beales, *et al.* Langmuir 27(1): 1-6. Copyright (2011) American Chemical Society.

Regarding the bending modulus (κ) of hGUVs, quantitative data reported so far in literature are scarce compared to the abundant values for lipid GUVs which are floppier and much more flexible (see previous remark on the reduced excess area of polymersomes). There is only one alternate approach by AFM to measure the κ of hybrid vesicles hLUVs composed of poly(dimethylsiloxane)-*block*-poly(methyloxazoline) and 1,2-dimyristoyl-*sn*-glycero-3-phosphocholine (PDMS₆₀-*b*-PMOXA₂₁/DMPC) with a diameter of ~ 200 nm. The mechanical properties of the vesicles were measured using quantitative forces *versus* distance curves. An intermediate value of κ between liposomes and polymersomes ($62 \cdot 10^{-19}$ J for hybrid PDMS₆₀-*b*-PMOXA₂₁/DMPC at 50/50 mol ratio or 90/10 mass ratio) was reported

Author manuscript version of Chapter 27 published In book: [The Giant Vesicle Book](#), Rumiana Dimova & Carlos Marques Eds. (CRC PRESS Taylor and Francis group, Oct. 7th 2019) (Winzen, Bernhardt et al. 2013). The authors investigated also the modification of the membrane properties using cholesterol instead of DMPC. Interestingly, they observed that the bending modulus of a membrane containing only ~5% in mass of cholesterol was more than four times larger than that of pure polymersomes. It was suggested that this could result from an increase of the packing density in the membrane induced by cholesterol. From the preliminary results, it is clear that the flexibility of hybrid membranes can be tuned on a very large range and in a subtle way. As this parameter and other mechanical properties control many aspects of the behaviour of vesicles such as their formation, stability, fusion and budding processes, further studies need to be performed to concomitantly elucidate the membrane structure and the resulting properties.

Although there are many types of molecular individual and collective motions within membranes, the mobility of molecules inside a membrane has been mostly evaluated through the measurement of the lateral diffusion coefficient, which is directly linked to the surface shear viscosity of the membrane. Such measurement is commonly made by fluorescence recovery after photo-bleaching (FRAP) experiments, see also Chapter 21. In the case of hybrid copolymer lipid hGUVs, one can access either the mobility of the lipid molecules or the copolymer chains depending on the localization of the fluorescent probes. Numerous studies and reviews on liposomal membranes pointed out a strong influence of the lipid physical state and membrane composition on the molecular mobility. Therefore it is expected that the mobility and the fluidity of the membrane could be finely tuned by the association of copolymers and lipids in the membrane. Lateral diffusion coefficients for lipids are indeed in the range $3\text{-}5\ \mu\text{m}^2\cdot\text{s}^{-1}$ and those of copolymer chains in the lower range

Author manuscript version of Chapter 27 published In book: [The Giant Vesicle Book](#), Rumiana Dimova & Carlos Marques Eds. (CRC PRESS Taylor and Francis group, Oct. 7th 2019) 0.0024-0.12 $\mu\text{m}^2\cdot\text{s}^{-1}$ (Lee, Santore et al. 2002). Large differences in surface shear viscosity have also been reported between PBd-*b*-PEO and lipid membranes (Dimova, Seifert et al. 2002; Evans, Heinrich et al. 2003), with even higher values reported for liquid crystalline block copolymers (Mabrouk et al. 2009). Therefore large variations of such parameters are anticipated depending on the lipid / copolymer composition, but subtle modifications could result also from peculiar membrane lateral structuration (presence of domains) (Loura, Fedorov et al. 2005; Loura, Fernandes et al. 2010). Other types of effects can also be invoked, such as in the work of Nam et al. (Nam, Beales et al. 2011) who first indicated that with increasing copolymer content, the diffusion of lipid molecules in hGUVs of POPC/PBd₄₆-*b*-PEO₃₀ becomes slower and in proportion of the copolymer amount incorporated, except at low copolymer fractions where only a weak dependence was observed (see Figs 27-6). Since for this system, none of the hybrid vesicles showed macroscopic domains, the homogeneous insertion of copolymer chains into lipid membrane may somewhat hamper the motion of lipid chains. It is interesting to note that the authors observed a fluorescence recovery shape for hybrid vesicles different from that of the pure components (polymersomes and liposomes), suggesting that dynamics in these hybrid membranes are not ideally described by a standard diffusion model with a single diffusion coefficient.

Figure 27-6 (Nam, Beales et al. 2011). Diffusion coefficient measurements by FRAP for different hGUVs of POPC/ PBd₄₆-*b*-PEO₃₀. Reprinted from Nam, J., P. A. Beales, et al. Langmuir 27(1): 1-6. Copyright (2011) American Chemical Society.

Other authors (Schulz, Werner et al. 2013) obtained information about the mobility of lipid molecules in hybrid membranes composed of DPPC, in the gel state at room temperature, and PIB₈₇-*b*-PEO. For that purpose, they used 1,2-dihexadecanoyl-*sn*-glycero-3-phosphoethanolamine-*N*-(lissamine rhodamine B sulfonyl) (Rh-DHPE) as a diffusion probe. This molecule fails to incorporate ordered membranes and should be localized in the most disordered phase of the hybrid vesicles (Bagatolli and Gratton 2000). Whereas no fluorescence recovery was detected for pure DPPC, above a threshold in copolymer fraction for hGUVs, the data revealed a clear increase in mobility of Rh-DHPE in the hybrid membranes with the copolymer content. The authors interpreted these observations by the breaking up of the rigid DPPC densely packed phase by the copolymer chains. The interpretation of such data is however not obvious as Rh-DHPE is known to exhibit a large preference for disordered domains. Therefore, it is likely that Rh-DHPE inserts into the copolymer phase, which presents a higher mobility compared to the DPPC gel phase.

In these preliminary results, the authors probed the lipid mobility in the entire hybrid systems, where there was no clear evidence of macroscopic domain presence. This does not rule out the existence of domains below the optical resolution, which can act as obstacles hindering the diffusion, in a similar manner as lipid rafts or membrane proteins in the so-called “mosaic membrane” model (Vaz, Goodsaid-Zalduondo et al. 1984; Saxton 1987). Liquid ordered phases within liposomal membranes are indeed suspected for a long time as a factor that significantly impacts on the dynamic of molecules in natural and reconstructed

Figure 27-7 Diffusion coefficients of FITC-PDMS₂₂-*g*-(PEO₁₂)₂ in hybrid PDMS₂₂-*g*-(PEO₁₂)₂: POPC GUVs were plotted *versus* the POPC fraction in the membranes (data originating from the PhD Thesis of T. P. Tuyen Dao, Univ. Bordeaux 2016).

We studied the consequence of the presence of POPC on the mobility of copolymer chains. From our data shown in Fig 27-7, mixtures containing either 30% or 50% of POPC in mass demonstrated a significant reduction of the copolymer lateral diffusion compared to the pure copolymer membranes. It should be noted that 30% and 50% contents of POPC in PDMS₂₂-*g*-(PEO₁₂)₂, POPC mixtures were enough to drive micro-domain formation within the hybrid membranes, and in this situation, the tracer molecule used (FITC-PDMS₂₂-*g*-(PEO₁₂)₂) was localized almost exclusively in the copolymer phase. Apart from the decrease of diffusion coefficient value, the FRAP curve of hybrid PDMS₂₂-*g*-(PEO₁₂)₂: POPC vesicles also clearly indicated the presence of an immobile fraction as shown in Fig 27-8. Indeed, even though the measurement was carried out in polymer-rich domain, we rarely got a full recovery for all fractions of POPC incorporated. These results could be explained by the

Author manuscript version of Chapter 27 published In book: [The Giant Vesicle Book](#), Rumiana Dimova & Carlos Marques Eds. (CRC PRESS Taylor and Francis group, Oct. 7th 2019) presence of nanoscale lipid domains which were below the resolution of confocal microscopy yet hamper the mobility of the copolymer chains. In the Figure 27-8 data were fitted with the circular spot model to extract diffusion coefficient values (Axelrod, Koppel et al. 1976; Soumpasis 1983; Ishikawa-Ankerlhod, Ankerhold et al. 2012)

Figure 27-8. Normalized fluorescence vs time of pure PDMS₂₂-*g*-(PEO₁₂)₂ (○) and hybrid PDMS₂₂-*g*-(PEO₁₂)₂:POPC with 30% POPC in mass (▲) (data originating from the PhD Thesis of T. P. Tuyen Dao)

Box 27-2 summarizes the important points which should be carefully considered for a successful FRAP measurement.

BOX STARTS HERE

Box 27-2. Practical tips for FRAP measurements on hGUVs

- i) Fluorescent probes: The probes should preferably have intermediate photo-stability, since, on the one hand, they should be not too difficult to bleach and, on the other hand, they should be sufficiently photo-stable to allow imaging of the recovery process. Furthermore, the fluorophore concentration should also be considered. Indeed, the

Author manuscript version of Chapter 27 published In book: [The Giant Vesicle Book](#), Rumiana Dimova & Carlos Marques Eds. (CRC PRESS Taylor and Francis group, Oct. 7th 2019) concentration should not be too high in order to avoid e.g. possible self-quenching effects, whereas a too low concentration will result in very weak fluorescence, poor signal/noise ratio and number fluctuations will start to dominate the signal. From our experience, fluorescein, nitrobenzoxadiazole (NBD), dichlorotriazinylamino fluorescein are normally good choices of fluorescent probes for FRAP.

ii) hGUV sample: The vesicles chosen to be measured should be sufficiently large to have a significant excess number of molecules outside the circular bleached spot (ROI - region of interest) to diffuse from. Indeed, since at least 3 μm is usually required for the minimum ROI diameter to get meaningful data, and since the precision of the measurement is improved when a larger bleached ROI is used, we recommend the use of hGUVs larger than 10 μm diameter for FRAP measurement. Another important point is that the vesicles must be fully immobilized during acquisition. The immobilization of hGUVs can be achieved by including a low ratio of biotinylated lipids ($1/10^6$ mol) into the vesicles, which allows for high affinity adhesion to an avidin-coated surface. This low amount is sufficient to fully immobilize the vesicles on the substrate, and larger amounts can lead to collapse of the vesicle on the surface. The avidin coating is realised by incubating the glass slide in an avidin solution at 0.1mg/mL. After removing all the excess amount of non-attached avidin to the glass slide, GUVs can be added in the chamber, and they will adhere to the surface in about 15 minutes. Interestingly, this method initially developed for liposomes (Puech, Askovic et al. 2006; Sarmento, Prieto et al. 2012) was also effective for hGUVs. Another approach consists in diluting suspension of vesicles that have been hydrated in sucrose 0.1M, in a glucose solution of the same concentration, to induce vesicle sedimentation.

iii) Instrument setup: FRAP acquisition is processed in different stages, during which the excitation light intensity acquisition rate, and other parameters have to be tuned individually for each stage. The bleaching duration has to be as short as possible to prevent significant diffusion during this process, which biases the recovery intensity to lower values. On the other hand, the duration of the measurement of fluorescence recovery must be around 7 to 10 τ_D (time for the probe to diffuse over the bleached zone), in order to have statistical confidence in the different parameters recovered from the fit (Klein and Waharte 2010), Furthermore, the illumination during fluorescence recovery has to be as low as possible to avoid photo-bleaching at this stage, while the power laser should be set at maximum for the bleach phase.

The rate of data acquisition during fluorescence recovery should also be relatively high in regard to τ_D in order to acquire a sufficient number of points during the initial stage of the recovery fluorescence curve.

BOX ENDS HERE

4.2. PERMEABILITY

It is also important to evaluate and control how easily the soluble molecules can pass through the semipermeable membrane of hybrid vesicles in the presence of concentration gradients of osmotically active solutes (*i.e.* that cannot pass through the membrane). Permeability is essential for regulation of transmembrane exchange of substances, such as drug release and water transport. The permeability of polymersomes lays far below the value encountered for liposomes (Le Meins, Sandre et al. 2011) therefore the hybrid membrane permeability is expected to strongly depend on the lipid/copolymer fraction; see

Author manuscript version of Chapter 27 published In book: [The Giant Vesicle Book](#), Rumiana Dimova & Carlos Marques Eds. (CRC PRESS Taylor and Francis group, Oct. 7th 2019) also Chapters 20 and 26. Again, so far there are no quantitative data available obtained on hGUVs, but information has been obtained on sub-micrometric hybrid vesicles (hLUVs) whose size was followed *versus* time by dynamic light scattering. Shen et al examined the water permeability of hybrid triblock copolymer PMOXA-*b*-PDMS-*b*-PMOXA/DOPC vesicles with different copolymer/lipid ratios, from 0 to 10 copolymer chains per 100 lipid molecules (Shen, Hu et al. 2014). By using two copolymers with different molar masses (PMOXA₆-*b*-PDMS₃₃-*b*-PMOXA₆ and PMOXA₁₅-*b*-PDMS₆₇-*b*-PMOXA₁₅), they obtained different variation profiles of the permeability with the copolymer/lipid content (Fig 27-9). The hybrid system with the shorter triblock copolymer showed a regular decrease of permeability with an increasing copolymer ratio. The permeability of the hybrid systems obtained with the longer triblock copolymer, according to the authors, would decrease up to 5% of copolymer and then re-increase as the polymer ratio was further increased. These results were explained by the authors by the incorporation of copolymer chains into the defects and voids existing in DOPC membranes, partly due to steric hindrance of unsaturated chains, therefore changing the packing density and decreasing the permeability. In the case of long copolymer chains, due to a large thickness mismatch between the alkyl tails of lipids and the hydrophobic block of the copolymer, an excessive amount of copolymer in the hybrid membranes could cause over-saturated occupation of the filler space and create new void spaces, leading to a reduced packing density again, which would explain the re-increase of permeability at 10 copolymer chains/100 lipids. It is important to mention that according to the error bars, this non-monotonous variation is not obvious to observe. Another possible explanation is that the high hydrophobic mismatch in this system plays a different role, in

Author manuscript version of Chapter 27 published In book: [The Giant Vesicle Book](#), Rumiana Dimova & Carlos Marques Eds. (CRC PRESS Taylor and Francis group, Oct. 7th 2019) the sense that too long copolymer chains could not incorporate in lipid LUVs₇ because of a high curvature energy of the membrane at such size and a large steric hindrance between the hydrophilic blocks confined in the inner compartment of the LUVs (as sketched on Fig 27-9), and therefore would not significantly modify permeability. Anyway, these results once again emphasized the impact of copolymer/lipid thickness mismatch onto the resulting membrane properties which was proven as a key point for structuration of hybrid membranes (Chemin, Brun et al. 2012; Dao, Fernandes et al. 2015) (Le Meins, Schatz et al. 2013). Besides the water permeability, we would like also to mention another work (Lim, de Hoog et al. 2013) in which the release profile of encapsulated hydrophilic molecules in hybrid LUVs has been measured. As shown in Fig 27-10, it was found that the permeability of the hybrid vesicles prepared from PBd₂₂-PEO₁₄/POPC changed clearly with the fraction of copolymer/lipid. The higher the copolymer content introduced, the more significantly delayed molecule release was detected.

Figure 27-9: Water permeability of hybrid vesicles and schematic of different packing of DOPC/PMOXA₆-PDMS₃₃-PMOXA₆ (ABA-S) and DOPC/PMOXA₁₅-PDMS₆₇-PMOXA₁₅ (ABA-L) on hybrid vesicles (Shen, Hu et al. 2014). Reprinted from *Chemical Physics Letters* **600** (2014). Shen, Hu et al. "Impact of amphiphilic triblock copolymers on stability and permeability of phospholipid/polymer hybrid vesicles.", 56-61, Copyright , (2014) with permission of Elsevier.

Figure 27-10 Hydrophilic dye carboxyfluorescein (CF) release from different vesicles PB-PEO/POPC containing 0%, 25%, 50%, 75%, 100% POPC (Lim, de Hoog et al. 2013); Reproduced from Lim, S., H.-P. de Hoog, et al. (2013). "Hybrid, Nanoscale Phospholipid/Block Copolymer Vesicles." *Polymers* **5**(3): 1102-1114.

4.3. SPECIFIC PROPERTIES, BIOFUNCTIONALITY

Besides the basic membrane physical properties mentioned above, the specific properties of hybrid polymer/lipid vesicles will be discussed in this section to illustrate their potential interest regarding biophysics and nanomedicine applications. One of the major advantages of such hybrid lipid-polymer vesicles is the formation of controlled lipid domains. These domains can be exploited to specifically incorporate active biomacromolecules, especially membrane proteins, thus providing specific transport of biorecognition properties to the hybrid systems.

Different successful reconstitutions either of membrane proteins or of specific ligand molecules in hybrid copolymer/lipid membranes shows that bio-functional vesicles can be obtained. For instance, the work of Binder et al proved that hGUVs composed of poly(isobutene)-*b*-poly(ethylene oxide) (PIB₈₇-*b*-PEO₁₇) and DOPC, decorated with ganglioside GM1 receptors, were able to maintain their biological function in binding with cholera toxin B (Schulz, Werner et al. 2013). It should be noted that the recognition of the surface functionalized hGUVs by the protein was observed to be independent on the mixing state of the hybrid membrane. In addition, protein binding to the membranes resulted also in a lateral reorganization, leading to the creation of lipid rich phase domains in the polymer continuous phase of the membrane. However, the binding cannot be achieved at polymer ratios above 40 mol% (~85 mass %) due to a shielding effect of the PEO hydrophilic chains, preventing the binding process.

Author manuscript version of Chapter 27 published In book: [The Giant Vesicle Book](#), Rumiana Dimova & Carlos Marques Eds. (CRC PRESS Taylor and Francis group, Oct. 7th 2019)

Hybrid copolymer/lipid vesicles offer new routes to obtain more complex and efficient bio-inspired and bio-functional nano- or micrometric structures. Liposomes and more recently polymersomes have been widely used for the reconstitution of membrane proteins and for developing complex artificial membranes embedding proteins or new bio-inspired reactors. Hybrid copolymer/lipid vesicles could enable developing stable and versatile platforms that could be easily modified to adapt to different membrane proteins, thanks to the robustness of copolymer membranes and to the “natural” (non-denaturising) protein environment provided by the lipid phase. Although the results were not obtained on “real” membranes or hGUVs, but on copolymer/lipid films deposited onto a surface, successful reconstitution of cyclic nucleotide-modulated potassium channel from MloK1 has recently been achieved (Justyna, Dalin et al. 2015). In this work, the authors clearly showed the possibility to control the protein insertion. By varying the copolymer choice and the degree of saturation of the hydrophobic lipid tails, they could favour a selective localization of proteins within the more fluid domains of the hybrid membranes.

5. CONCLUSION AND PERSPECTIVES

The design of hybrid copolymer/lipid giant vesicles with desired and controlled membrane structure at the micro- and nano-scales remains highly challenging. In particular, it would be of utmost interest to build a vesicular membrane with lipid micrometric domains but also “raft-like” nano-domains (from a few tens to hundreds of nanometers). Such structures could present bio-functional properties (“patchy surface” effect) and the membrane physical properties could be fine-tuned. Lipid rafts naturally occurring in the biological cell membrane, with relatively small size, are indeed well known to play a crucial

Author manuscript version of Chapter 27 published In book: [The Giant Vesicle Book](#), Rumiana Dimova & Carlos Marques Eds. (CRC PRESS Taylor and Francis group, Oct. 7th 2019) role in numerous biological processes (Simons and Ikonen 1997; Sens and Turner 2006). As illustrated in section 2.1 of this chapter, biophysical mechanisms that maintain small lipid domains in equilibrium are not yet completely understood. They involve several parameters that have been briefly described in section 2.1 and have been the subject of many discussions in recent reviews focusing on the stability of lipid domains (Garcia-Saez and Schwille 2010), and phase separation in biological membranes (Elson, Fried et al. 2010). Only few experimental examples of lipid nanodomains (i.e. below the optical microscopy resolution) in model liposomes (De Almeida, Loura et al. 2005; Brown, Towles et al. 2007; Loura, Fernandes et al. 2010; Heberle and Feigenson 2011; Suga and Umakoshi 2013) are available and their existence has been proven on hGUVs or hLUVs only very recently by our group (Dao, Fernandes et al. 2015) (Dao, Fernandes et al. 2017). It is believed that amphiphilic block copolymers with hydrophobic blocks of low T_g, because of their flexibility and of their molar mass tuning during the synthesis, play a role in adjusting the line tension at the lipid–copolymer boundaries.

Finally, an emphasis should be given on the control of the membrane structure through physicochemical routes, such as playing with entropic parameters (copolymer/lipid adaptation at the boundaries), interactions (chemical nature of the copolymer blocks), incorporation of additional reactants and environmental parameters (temperature, pH, redox potential, electric or magnetic fields...). In particular, lipids in gel phase state certainly play a role on the domain morphologies of copolymer/lipid vesicles, as they do for mixed lipid vesicles (Gordon, Beales et al. 2006). In addition, new processes of formation should be developed. Indeed, most of the processes used so far led to compositional variability in the

Author manuscript version of Chapter 27 published In book: [The Giant Vesicle Book](#), Rumiana Dimova & Carlos Marques Eds. (CRC PRESS Taylor and Francis group, Oct. 7th 2019) membranes of different vesicles within the same batch, which prevents a fine characterization of the membrane structuration and *in fine* the understanding of their structure-properties relationship.

Therefore progresses in understanding hGUVs thermodynamics and developing theoretical models for hybrid membranes will probably be necessary to develop new approaches, and could open the way to the design of advanced nano- / micrometric structures with specific functionalities (selective permeability, magnetic properties by incorporating magnetic nanoparticles, membrane disruption with stimuli-responsive copolymer block or lipids, incorporation of channel proteins...) that could be very useful in drug delivery (Cheng, Elias et al. 2011; Lim, de Hoog et al. 2013) and as templating agents (Cheng and Tsourkas 2008), or fundamental systems to understand complex biological behaviors in cells.

REFERENCES

- Axelrod, D., D. E. Koppel, et al. (1976). "Mobility measurement by analysis of fluorescence photobleaching recovery kinetics." *Biophysical Journal* **16**: 1055-1069.
- Bagatolli, L. and P. B. S. Kumar (2009). "Phase behavior of multicomponent membranes: Experimental and computational techniques." *Soft Matter* **5**(17): 3234-3248.
- Bagatolli, L. A. and E. Gratton (2000). "A correlation between lipid domain shape and binary phospholipid mixture composition in free standing bilayers: A two-photon fluorescence microscopy study." *Biophysical Journal* **79**(1): 434-447.
- Bermudez, H., A. K. Brannan, et al. (2002). "Molecular weight dependence of polymersome membrane structure, elasticity, and stability." *Macromolecules* **35**(21): 8203-8208.
- Bermúdez, H., D. a. Hammer, et al. (2004). "Effect of Bilayer Thickness on Membrane Bending Rigidity." *Langmuir*.
- Bernchou, U., J. Brewer, et al. (2009). "Texture of lipid bilayer domains." *J Am Chem Soc* **131**(40): 14130-14131.
- Binder, W. H., V. Barragan, et al. (2003). "Domains and Rafts in Lipid Membranes." *Angewandte Chemie, International Edition* **42**(47): 5802-5827.
- Brochard-Wyart, F. and P. G. de Gennes (2002). "Adhesion induced by mobile binders: Dynamics." *Proceedings of the National Academy of Sciences* **99**(12): 7854-7859.
- Brown, A. C., K. B. Towles, et al. (2007). "Measuring raft size as a function of membrane composition in PC-Based systems: Part 1 - Binary systems." *Langmuir* **23**(22): 11180-11187.
- Cevc, G. and H. Richardsen (1999). "Lipid vesicles and membrane fusion." *Advanced Drug Delivery Reviews* **38**(3): 207-232.
- Chemin, M., P. M. Brun, et al. (2012). "Hybrid polymer/lipid vesicles: fine control of the lipid and polymer distribution in the binary membrane." *Soft Matter* **8**: 2867-2874.
- Chen, D. and M. M. Santore (2014). "Large effect of membrane tension on the fluid–solid phase transitions of two-component phosphatidylcholine vesicles." *Proceedings of the National Academy of Sciences of the United States of America* **111**(1): 179-184.
- Chen, D. and M. M. Santore (2015). "Hybrid copolymer-phospholipid vesicles: Phase separation resembling mixed phospholipid lamellae, but with mechanical stability and control." *Soft Matter* **11**(13): 2617-2626.
- Chen, Q., H. Schonher, et al. (2009). "Mechanical Properties of Block Copolymer Vesicle Membranes by Atomic Force Microscopy." *Soft Matter*.
- Cheng, Z., D. R. Elias, et al. (2011). "Improved Tumor Targeting of Polymer-based Nanovesicles Using Polymer-Lipid Blends." *Bioconjugate Chemistry* **22**(10): 2021–2029.
- Cheng, Z., D. R. Elias, et al. (2011). "Improved Tumor Targeting of Polymer-based Nanovesicles Using Polymer-Lipid Blends." *Bioconjugate Chemistry* **22**(10): 2021–2029.
- Cheng, Z. and A. Tsourkas (2008). "Paramagnetic porous polymersomes." *Langmuir* **24**(15): 8169-8173.
- Mabrouk E., Cuvelier D., Pontani L-L., Xu B., Lévy D., Keller P., Brochard-Wyart F., Nassoy F., Li M-H. (2009). "Formation and material properties of giant liquid crystal polymersomes." *Soft Matter*, **5**(9): 1870-1878

- Dao, T. P. T., F. Fernandes, et al. (2015). "Phase separation and nanodomain formation in hybrid polymer/lipid vesicles." *ACS Macro Letters* **4**(2): 182-186.
- Dao, T. P. T., F. Fernandes, et al. (2017). "Modulation of phase separation at the micron scale and nanoscale in giant polymer/lipid hybrid unilamellar vesicles (GHUVs)." *Soft Matter* **13**(3): 627-637.
- De Almeida, R. F. M., L. M. S. Loura, et al. (2005). "Lipid rafts have different sizes depending on membrane composition: A time-resolved fluorescence resonance energy transfer study." *Journal of Molecular Biology* **346**(4): 1109-1120.
- Dimova, R., U. Seifert, et al. (2002). "Hyperviscous diblock copolymer vesicles." *The European Physical Journal E* **7**(3): 241-250.
- Dimova, R., U. Seifert, et al. (2002). "Hyperviscous diblock copolymer vesicles." *European Physical Journal E* **7**(3): 241-250.
- Discher, B. M., D. A. Hammer, et al. (2000). "Polymer vesicles in various media." *Current Opinion in Colloid & Interface Science* **5**: 125-131.
- Discher, B. M., Y. Y. Won, et al. (1999). "Polymersomes: tough vesicles made from diblock copolymers." *Science* **284**(5417): 1143-1146.
- Discher, B. M., Y. Y. Won, et al. (1999). "Polymersomes: Tough vesicles made from diblock copolymers." *Science* **284**(5417): 1143-1146.
- Discher, D. E. and F. Ahmed (2006). "Polymersomes." *Annual Review of Biomedical Engineering* **8**(1): 323-341.
- Elson, E. L., E. Fried, et al. (2010). Phase separation in biological membranes: Integration of theory and experiment. *Annual Review of Biophysics*. **39**: 207-226.
- Evans, E., V. Heinrich, et al. (2003). "Dynamic Tension Spectroscopy and Strength of Biomembranes." *Biophysical Journal* **85**: 2342-2350.
- Evans, E. and W. Rawicz (1990). "Entropy-Driven Tension and Bending Elasticity in Condensed-Fluid Membranes." *Phys. Rev. Lett* **64**: 2094-2097.
- Frolov, V. A., Y. A. Chizmadzhev, et al. (2006). "'Entropic traps' in the kinetics of phase separation in multicomponent membranes stabilize nanodomains." *Biophys J* **91**(1): 189-205.
- Garcia-Saez, A. J. and P. Schwille (2010). "Stability of lipid domains." *FEBS Letters* **584**: 1653-1658.
- Gordon, V. D., P. A. Beales, et al. (2006). "Lipid organization and the morphology of solid-like domains in phase-separating binary lipid membranes." *Journal of Physics-Condensed Matter* **18**(32): L415-L420.
- Gracia, R. S., N. Bezlyepkina, et al. (2010). "Effect of cholesterol on the rigidity of saturated and unsaturated membranes: fluctuation and electrodeformation analysis of giant vesicles." *Soft Matter* **6**: 1472-1482.
- Heberle, F. A. and G. W. Feigenson (2011). "Phase separation in lipid membranes." *Cold Spring Harbor perspectives in biology* **3**(4).
- Henderson, I. M. and W. F. Paxton (2014). "Salt, Shake, Fuse-Giant Hybrid Polymer/Lipid Vesicles through Mechanically Activated Fusion." *Angewandte Chemie-International Edition* **53**(13): 3372-3376.
- Henriksen, J., A. C. Rowat, et al. (2004). "Vesicle fluctuation analysis of the effects of sterols on membrane bending rigidity." *European Biophysics Journal* **33**: 732-741.
- Hu, J., T. Weigl, et al. (2011). "Vesicles with multiple membrane domains." *Soft Matter* **7**(13): 6092-6102.

- Ishikawa-Ankerlhold, H. C., R. Ankerhold, et al. (2012). "Advanced fluorescence microscopy techniques--FRAP, FLIP, FLAP, FRET and FLIM." *Molecules* **17**: 4047-4132.
- Jaskiewicz, K., M. Makowski, et al. (2012). "Mechanical Properties of Poly(dimethylsiloxane)-block-poly(2-methyloxazoline) Polymersomes Probed by Atomic Force Microscopy." *Langmuir* **28**(34): 12629-12636.
- Justyna, K., W. Dalin, et al. (2015). "Hybrid Polymer-Lipid Films as Platforms for Directed Membrane protein insertion." *Langmuir* **31**(17): 4868-4877.
- King, J. W. (2002). *Supercritical fluid technology for lipid extraction, fractionation and reactions*. Lipid biotechnology. T. M. Kuo and H. W. Gardner. New York, Marcel Dekker: 663-687.
- Klein, C. and F. Waharte (2010). "Analysis of Molecular Mobility by Fluorescence Recovery After Photobleaching in Living Cells." *Microscopy: Science, Technology, Applications and Education*.
- Kuzmin, P. I., S. A. Akimov, et al. (2005). "Line tension and interaction energies of membrane rafts calculated from lipid splay and tilt." *Biophys J* **88**(2): 1120-1133.
- Ladavière, C., C. Tribet, et al. (2002). "Lateral Organization of Lipid Membranes Induced by Amphiphilic Polymer Inclusions." *Langmuir* **18**(20): 7320-7327.
- Le Meins, J.-F., O. Sandre, et al. (2011). "Recent trends in the tuning of polymersomes' membrane properties." *The European Physical Journal E* **34**(2): 1-17.
- Le Meins, J. F., O. Sandre, et al. (2011). "Recent trends in the tuning of polymersomes' membrane properties." *European Physical Journal E* **34**(2): 14.
- Le Meins, J. F., C. Schatz, et al. (2013). "Hybrid polymer/lipid vesicles: state of the art and future perspectives." *Materials Today* **16**(10): 397-402.
- Lee, J. C. M., M. Santore, et al. (2002). "From membranes to melts, rouse to reptation: Diffusion in polymersome versus lipid bilayers." *Macromolecules* **35**(2): 323-326.
- Liao, J. F., C. Wang, et al. (2012). "Recent Advances in Formation, Properties, and Applications of Polymersomes." *Current Pharmaceutical Design* **18**(23): 3432-3441.
- Lim, S., H.-P. de Hoog, et al. (2013). "Hybrid, Nanoscale Phospholipid/Block Copolymer Vesicles." *Polymers* **5**(3): 1102-1114.
- Lipowsky, R. and R. Dimova (2003). "Domains in membranes and vesicles." *Journal of Physics-Condensed Matter* **15**(1): S31-S45.
- LoPresti, C., H. Lomas, et al. (2009). "Polymersomes: nature inspired nanometer sized compartments." *Journal of Materials Chemistry* **19**(22): 3576-3590.
- Loura, L. M. S., F. Fernandes, et al. (2010). "Membrane microheterogeneity: Förster resonance energy transfer characterization of lateral membrane domains." *European Biophysics Journal* **39**(4): 589-607.
- Loura, M. S., A. Fedorov, et al. (2005). "Lipid Rafts have Different Sizes Depending on Membrane Composition : A Time-resolved Fluorescence Resonance Energy Transfer Study." *J. Mol. Biol* **346**(4): 1109-1120.
- Mabrouk E., D. Cuvelier, L-L. Pontani L-L., B. Xu, D. Lévy D., P. Keller, F. Brochard-Wyart P. Nassoy, M-H. Li (2009). "Formation and material properties of giant liquid crystal polymersomes". *Soft Matter* **5**(9):1870-1878
- Michel, V. and M. Bakovic (2007). "Lipid rafts in health and disease." *Biol Cell* **99**(3): 129-140.
- Mills, T. T., G. E. S. Toombes, et al. (2008). "Order parameters and areas in fluid-phase oriented lipid membranes using wide angle x-ray scattering." *Biophysical Journal* **95**(2): 669-681.

- Morimoto, N., Y. Sasaki, et al. (2014). "Temperature-responsive telechelic dipalmitoylglycerol poly(N-isopropylacrylamide) vesicles: real-time morphology observation in aqueous suspension and in the presence of giant liposomes." *Chemical Communications* **50**(61): 8350-8352.
- Nam, J., P. A. Beales, et al. (2011). "Giant Phospholipid/Block Copolymer Hybrid Vesicles: Mixing Behavior and Domain Formation." *Langmuir* **27**(1): 1-6.
- Nam, J., T. K. Vanderlick, et al. (2012). "Formation and dissolution of phospholipid domains with varying textures in hybrid lipo-polymersomes." *Soft Matter* **8**: 7982-7988.
- Olubummo, A., M. Schulz, et al. (2014). "Phase Changes in Mixed Lipid/Polymer Membranes by Multivalent Nanoparticle Recognition." *Langmuir* **30**(1): 259-267.
- Puech, P.-H., V. Askovic, et al. (2006). "Dynamics of vesicle adhesion: spreading versus dewetting coupled to binder diffusion." *Biophysical Reviews and Letters* **1**(01): 85-95.
- Rawicz, W., B. A. Smith, et al. (2008). "Elasticity, Strength, and Water Permeability of Bilayers that Contain Raft Microdomain-Forming Lipids." *Biophys J* **94**: 4725-4736.
- Roth, M. (1990). "Solubility parameter of poly(dimethyl siloxane) as a function of temperature and chain length." *Journal of polymer science. Part B. Polymer physics* **28**(13): 2719.
- Ruysschaert, T., A. F. P. Sonnen, et al. (2005). "Hybrid nanocapsules: Interactions of ABA block copolymers with liposomes." *Journal of the American Chemical Society* **127**(17): 6242-6247.
- Sarmento, M. J., M. Prieto, et al. (2012). "Reorganization of lipid domain distribution in giant unilamellar vesicles upon immobilization with different membrane tethers., ." *Biochim. Biophys Acta*. **1818**: 2605-2615.
- Saxton, M. J. (1987). "Lateral diffusion in an archipelago — the effect of mobile obstacles." *Biophys. J* **52**: 989-997.
- Scholtysek, P., S. W. H. Shah, et al. (2015). "Unusual triskelion patterns and dye-labelled GUVs: Consequences of the interaction of cholesterol-containing linear-hyperbranched block copolymers with phospholipids." *Soft Matter* **11**(30): 6106-6117.
- Schulz, M. and W. H. Binder (2015). "Mixed Hybrid Lipid/Polymer Vesicles as a Novel Membrane Platform." *Macromolecular Rapid Communications*: 10.1002/marc.201500344.
- Schulz, M., D. Glatte, et al. (2011). "Hybrid lipid/polymer giant unilamellar vesicles: Effects of incorporated biocompatible PIB-PEO block copolymers on vesicle properties." *Soft Matter* **7**(18): 8100-8110.
- Schulz, M., A. Olubummo, et al. (2014). "Lateral surface engineering of hybrid lipid-BCP vesicles and selective nanoparticle embedding." *Soft Matter* **10**(6): 831-839.
- Schulz, M., S. Werner, et al. (2013). "Controlling molecular recognition with lipid/polymer domains in vesicle membranes." *Angewandte Chemie - International Edition* **52**(6): 1829-1833.
- Semrau, S., T. Idema, et al. (2009). "Membrane-mediated interactions measured using membrane domains." *Biophys J* **96**(12): 4906-4915.
- Sens, P. and M. S. Turner (2006). "Budded membrane microdomains as tension regulators." *Physical Review E - Statistical, Nonlinear, and Soft Matter Physics* **73**(3).
- Shen, W., J. Hu, et al. (2014). "Impact of amphiphilic triblock copolymers on stability and permeability of phospholipid/polymer hybrid vesicles." *Chemical Physics Letters* **600**: 56-61.

- Author manuscript version of Chapter 27 published In book: [The Giant Vesicle Book](#), Rumiana Dimova & Carlos Marques Eds. (CRC PRESS Taylor and Francis group, Oct. 7th 2019)
- Shoemaker, S. D. and K. T. Vanderlick (2003). "Material Studies of Lipid Vesicles in the La and La-Gel Coexistence Regimes." *Biophysical Journal* **84**.
- Simons, K. and E. Ikonen (1997). "Functional rafts in cell membranes." *Nature* **387**(6633): 569-572.
- Soumpasis, D. M. (1983). "Theoretical analysis of fluorescence photobleaching recovery experiments." *Biophysical Journal* **41**(1983): 95-97.
- Suga, K. and H. Umakoshi (2013). "Detection of Nanosized Ordered Domains in DOPC/DPPC and DOPC/Ch Binary Lipid Mixture Systems of Large Unilamellar Vesicles Using a TEMPO Quenching Method." *Langmuir* **29**(15): 4830-4838.
- Thevenot, J., H. Oliveira, et al. (2013). "Polymersomes for theranostics." *Journal of Drug Delivery Science and Technology* **23**(1): 38-46.
- Travasset, A. (2006). "Effect of dipolar moments in domain sizes of lipid bilayers and monolayers." *J Chem Phys* **125**(8): 084905.
- Tribet, C. and F. Vial (2007). "Flexible macromolecules attached to lipid bilayers: Impact on fluidity, curvature, permeability and stability of the membranes." *Soft Matter* **4**(1): 68-81.
- Ursell, T. S., W. S. Klug, et al. (2009). "Morphology and interaction between lipid domains." *Proc Natl Acad Sci U S A* **106**(32): 13301-13306.
- Vaz, W. L. C., F. Goodsaid-Zalduondo, et al. (1984). "Lateral diffusion of lipids and proteins in bilayer-membranes." *FEBS Lett* **174**(2): 199-207.
- Winzen, S., M. Bernhardt, et al. (2013). "Submicron hybrid vesicles consisting of polymer-lipid and polymer-cholesterol blends." *Soft Matter* **9**(25): 5883-5890.