

Click chemistry on the surface of PLGA-b-PEG polymeric nanoparticles: a novel targetable fluorescent imaging nanocarrier.

Andrea Pucci, Erica Locatelli, Jessica Ponti, Chiara Uboldi, Molinari Valerio, Mauro Comes Franchini

► To cite this version:

Andrea Pucci, Erica Locatelli, Jessica Ponti, Chiara Uboldi, Molinari Valerio, et al.. Click chemistry on the surface of PLGA-b-PEG polymeric nanoparticles: a novel targetable fluorescent imaging nanocarrier.. Journal of Nanoparticle Research, 2013, 10.1007/s11051-013-1818-8. hal-02353932

HAL Id: hal-02353932 https://hal.science/hal-02353932

Submitted on 7 Nov 2019

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Click chemistry on the surface of PLGA-b-PEG polymeric nanoparticles: a novel targetable fluorescent imaging nanocarrier

Andrea Pucci · Erica Locatelli · Jessica Ponti · Chiara Uboldi · Valerio Molinari · Mauro Comes Franchini

Received: 6 May 2013/Accepted: 24 June 2013 © Springer Science+Business Media Dordrecht 2013

Abstract In the quest for biocompatible nanocarriers for biomedical applications, a great deal of effort is put on engineering the nanocomposites surface in order to render them specific to the particular purpose. We developed biocompatible PLGA-b-PEG-based nanoparticles carrying a double functionality (i.e., carboxylic and acetylenic) able to serve as flexible highly selective grafting centers for cancer diagnosis and treatment. As a proof of concept, the nanocarrier was successfully functionalized with a tailored fluorescent molecule by means of click chemistry and with a targeting agent specific for glioblastoma multiforme via amidic bond formation.

Keywords Click · Fluorescein · Functionalized polymers · Nanochemistry · Glioblastoma

Electronic supplementary material The online version of this article (doi:10.1007/s11051-013-1818-8) contains supplementary material, which is available to authorized users.

M. Comes Franchini (🖂)

Dipartimento di Chimica Industriale "Toso Montanari", University of Bologna, Viale del Risorgimento 4, 40136 Bologna, Italy e-mail: mauro.comesfranchini@unibo.it

J. Ponti · C. Uboldi

Introduction

The addition of functional groups to the surface of nanoparticles (NPs) is usually highly required to enable the bioconjugation, and therefore, to obtain multifunctional nanobiomaterials. Generally, linkers with terminal amino, thiol, or carboxylic groups are preferred (Hermanson 2008). However, these functional groups are quite common and abundant in the biomolecules; thus, even though often used, in some cases, they could compromise selective conjugation. Moreover, charged species (NH₂ or COOH) give rise to electrostatic (unspecific) interactions that could lead to particles aggregation.

Nevertheless, the multiple presence of functional groups on nanocarriers would certainly be an important item for the synthesis of biohybrid polymeric nanoparticles (PNPs) (Metallo et al. 2003) and the combination of tracking agents, synthetic polymers, and biomolecules into new classes of nanomaterials has indeed gained much interest in recent years and has now become an important field in diagnostics.

Among the most important synthetic polymers, the poly(lactic-co-glycolic acid)-block-poly(ethyleneglycol) (PLGA-*b*-PEG) deserves a special mention (Gu et al. 2008). Our interest is (Locatelli and Comes Franchini 2012; Gentili et al. 2009) in the PLGA-*b*-PEG–COOH due to special properties, such as amphiphilicity and its simple synthesis. It is indeed a unique biomaterial: it possess both the biodegradability and biocompatibility of PLGA polymer and the stealth

A. Pucci · E. Locatelli · V. Molinari ·

Nanobiosciences Unit, Institute for Health and Consumer Protection, Joint Research Centre, Via E. Fermi 2749, 21027 Ispra, VA, Italy

behavior of PEG. Due to its well-distinct lipophilic (PLGA) and hydrophilic (PEG) portions, it can form micelles displaying internally the hydrophobic PLGA part and externally the hydrophilic PEG, which forms a stabilizing external shell. These unique physicochemical characteristics and behavior make the micelles extremely versatile and able to easy entrap, in the inner core constituted of PLGA chains, lipophilic molecules such as drugs or smaller nanostructures. The residual functional groups on the outer shell linked to the PEG can be further be elaborated from the synthetic point of view.

Taking into consideration, the above mentioned problem related to the common functional groups, there is a well-established combination of functional groups that emerged in the last years. Huisgen 1,3dipolar cycloaddition (1,3-DC), involves the reaction of an azido group to an alkyne group and provide fast access to an enormous variety of robust and stable heterocycles called triazoles (Huisgen 1984). This so called "click-chemistry" is therefore an attractive reaction because these two organic functional groups are hardly present in proteins and oligomers. The application of click-chemistry in bioconjugation reactions works for molecularly dissolved species, but can also be used to functionalize the nanostructured materials, giving thus an easy entry to hybrid multifunctional nanobiomaterials (Opsteen et al. 2008). Moreover, the catalytic effect of Cu(I) ions of this cycloaddition, discovered by Meldal (Tornøe et al. 2002) and Sharpless (Rostovtsev et al. 2002), gave a great stimulus to the application of this reaction (Moses and Moorhouse 2007). Notably, in terms of biological applications, as the bioconjugation, the metal-catalyzed click 1,3-DC proceeds in high yields and occurs at room temperature in aqueous solution at neutral pH.

Therefore, a polymeric nanocarrier based on PLGA-*b*-PEG carrying a double functionality of such kinds at its hydrophilic surface, and so enabling easy docking of diverse organic bioactive species and tracking agents, would represents a perfect support for theranostic purposes or drug delivery.

Concerning the tracking, fluorescence imaging is one of the most powerful technique currently available for continuous observation of dynamic intracellular processes in living cells (Johnson 1998; Agarwal et al. 2008; Urano et al. 2005). Fluorescein was first developed in the nineteenth century (Weber and Teale 1958), and has become widely known as a highly fluorescent molecule that emits longer wavelength light upon excitation at around 500 nm in aqueous media. Bioconjugation on polymeric micelles with fluorescent moieties is still an important challenge (Wang et al. 2009), therefore, the functionalization of the commercially available fluorescein isothiocyanate (FITC) in order to link the fluorescent part onto the surface of PNPs would be an important synthetic goal.

We report an innovative biohybrid nanomaterial based on the copolymer PLGA-*b*-PEG, having multiple outer shell decoration for selective double functionalization. In details, one functional group is an acetylenic group to develop a click-reaction with a synthetic azidofluorescein. The second functional group, the carboxylic group, is used to conjugate the Chlorotoxin (Cltx), a specific peptide for in vitro targeting of the human primary brain tumor glioblastoma U87MG cell line.

Results and discussion

While the PLAG-b-PEG-COOH has been previously fabricated (Cheng et al. 2007) and it was reproduced in this work following a similar methodology, the copolymer ending with an acetylenic (CCH) group PLGA-b-PEG-CCH was synthesized for the first time by readapting the same procedure and replacing the NH₂-PEG-COOH reagent by its acetylenic commercial counterpart NH2-PEG-CCH. The twosteps protocol is straightforward and leads to a clean and stable co-polymer in 85 % yield (Scheme 1). A derivative of fluorescein, which was synthesized for the first time by a common nucleophilic addition reaction between the FITC and the amino group of a *p*-azidoaniline, was chosen as a fluorescent dye. As reported in Scheme 1, the reaction was carried out in N,N-dimethylformamide (DMF) with triethylamine (TEA) giving 1-(4-azidophenyl)-3-(3',6'-dihydroxy-3-oxo-3H-spiro[isobenzofuran-1,9'-xanthen]-5-yl)thiourea 1 in 90 % yield. A similar approach to obtain azido-terminal fluorescein was already pursued exploiting more expensive and hazardous linkers (Lin et al. 2006). The substituted fluorescein 1 carries now a pendant azido group which can react with an acetylenic moiety via the copper-catalyzed cycloaddition (CuAAC) reaction.

Scheme 1 Structures of PLGA-*b*-PEG-based polymers and synthesis scheme of 1-(4azidophenyl)-3-(3',6'dihydroxy-3-oxo-3*H*spiro[isobenzofuran-1,9'xanthen]-5-yl)thiourea 1



The PNPs fabrication was achieved through the nanoprecipitation technique (Comes Franchini et al. 2010) by solubilizing in DMSO a 50:50 blend of the two copolymers PLGA-b-PEG-COOH and PLGA-b-PEG-CCH, and subsequently mixing it with water under vigorous stirring and maintaining the water/ organic ratio 10:1 with constant removal of the solution (Scheme 2). The as-fabricated nanocarrier PNPs-C/CCH presents a hydrodynamic size of 136.4 ± 0.9 nm with a rather small polydispersity (PDI = 0.067 ± 0.018). The bifunctionalized surface of the PNPs leads to a multimodal distribution of the ζ potential with peaks falling in a voltage range lower than -50 mV, indicating very high stability of the NPs (see DLS results in the supporting information). The DLS analyses were repeated over time up to 4 months showing no major changes. Thus, we can assume that the NPs are stable for several months if stored at 4 °C. Next, we focused our attention on the tailoring of the surface functionalities in order to exploit the fertile docking centers. Indeed, the polymeric nanocarriers PNPs-C/CCH represent a perfect support enabling easy docking of diverse organic bioactive species and tracking agents. In order to prove the applicability, the nanocarrier was functionalized with, on one hand, the as-synthesized fluorescent dye 1 and, on the other hand, the peptide Cltx.

The click-reaction ensures high specificity as well as processability in water (Rostovtsev et al. 2002). The water solution of PNPs-C/CCH was mixed with 1 in the presence of a catalytic amount of CuSO₄ and sodium ascorbate (Scheme 2). Upon reacting overnight at room temperature, the fluorescent moiety was linked, creating a triazole ring, onto the surface giving PNPs-C/Fluo, and leaving the COOH group still available. Using the typical 1-ethyl-3-(3-dimethylaminopropyl) carbodiimide (EDC) chemistry, we then chemically linked the commercially available Cltx to the outer surface (COOH, ratio Cltx:COOH 8.5:1) of the PNPs-C/Fluo. The reaction was carried out overnight at room temperature, and after purification we obtained PNPs-Fluo/Cltx. It is worth mentioning that the two organic molecules attached on the surface sparingly decrease the stability of the particle leading to a hydrodynamic size of 180.3 ± 3.1 nm with a PDI of 0.146 \pm 0.014 and a ζ -potential of -38.1 mV at nearly neutral pH.

The sequence of the reaction proved not to be indifferent. Trials were also carried out conjugating the Cltx onto the nanocarrier surface as a first step, prior to the cycloaddition reaction. The as-fabricated nanocarriers presented bigger size as well as higher polydispersity at the DLS (data not shown). Evidently, once the 36-amino acids peptide is linked on the surface, it constitutes an obstacle to the coppercatalyzed click reaction.

The luminescence properties of the PNPs-Fluo/Cltx together with the one of azidofluorescein and of the



Scheme 2 Schematic of the PNPs-Fluo/Cltx fabrication

bare PNPs were monitored using a spectrofluorometer. The excitation and emission spectra are depicted in Fig. 1a, b, respectively. The excitation of the azido-terminal fluorescein occurs at 460 nm and it undergoes a red shift to 491 upon linkage onto the particle surface. The green intense emission falls at 522 and at 516 nm for the *p*-azidofluorescein and the PNPs-Fluo/Cltx, respectively. As expected, the polymeric NPs absorb in the near UV (309 nm), and consequently do not emit when excited in the blue spectral range.

We decided to link the Cltx, a peptide that specifically binds to metalloproteinase 2 (MMP-2), a receptor over-expressed by brain cancer (glioblastoma cells) due to our interest in this research (Comes Franchini et al. 2010; Locatelli et al. 2012), therefore, U87MG cells (a stabilized cell line derived from human glioma) were exposed to 0.88 μ g/mL of PNPs-Fluo/Cltx. This testing concentration is no toxic, as previously observed (Locatelli et al. 2012). In fact, U87MG cells were exposed to 50 μ g/mL of PNPs-Cltx for 72 h, and by trypan blue exclusion dye test, we observed cell viability of 84 % of the unexposed cells (negative control) (Locatelli et al. 2012).

As shown in Fig. 2, PNPs-Fluo/Cltx (in green, in Fig. 2b, e) were internalized by U87MG glioblastoma–astrocytoma cells after both 48 (Fig. 2a–c) and 72 h (Fig. 2d–f) of exposure. Micelles were mainly localized in the cytoplasm and we excluded their internalization in the nuclei analysing each image of the slices obtained by Z-stack (ApoTome slide module, Carl Zeiss, Germany). At the concentrations tested, they did not alter the cell morphology (Fig. 2c–f) showing, also considering the toxicological results, biocompatibility of the system. Our results suggest that the PNPs-Fluo/Cltx, thanks to the presence of both a



Fig. 1 Room temperature excitation (a) and emission (b) spectra of the *p*-azidofluorescein (*solid line*), PNPs-Fluo/Cltx (*dashed line*), and the PNPs–C/CCH (*dotted line*)

fluorescent dye and to the specificity of Cltx for cancer cells, could be potentially used as targeting agent for diagnostic and therapy.



Fig. 2 Intracellular localization of PNPs-Fluo/Cltx in U87MG cells. After 48 h (a-c) and 72 h (d-f) exposure, PNPs-Fluo/Cltx micelles were observed located in the cytoplasm of U87MG

Conclusion

In conclusion, we have developed the synthesis of a simple polymeric NPs based on PLGA-b-PEG having two functional groups on the outer shell. This nanocarrier bears an acetylenic group on which we have linked a fluorescent tag using a click reaction and, moreover, a carboxylic group, that is able to conjugate peptides and proteins through simple amidation chemistry. As already mentioned, the click chemistry is becoming a major pathway among the biological conjugations and many dyes or bioactive molecules carrying an azido pendant are already commercially available. On the other hand, engineering the nanocarrier surface by modifying the pristine polymers instead of venturing on later modification seems to be a preferable approach which can be further expanded to a large variety of terminal groups. Accordingly, this novel targetable nanocarrier has been tested in the in vitro tracking of a glioma cell line, and is therefore currently being investigated in our laboratories for active drug delivery both in vitro and in vivo against glioblastoma.

Experimental section

Synthesis of PNPs-C/CCH

PLGA-*b*-PEG–COOH (10 kDa, 25 mg, 0.0025 mmol) and PLGA-*b*-PEG–CCH (10 kDa, 25 mg, 0.0025 mmol) were solubilized in 5 mL of DMSO. The organic phase

cells. **a**, **d** in *blue* are nuclei stained with Hoechst 33342; **b**, **e** in *green* are PNPs-Fluo/Cltx micelles; and **c**, **f** merge. Size *bar*: 20 μm. (Color figure online)

was mixed to 50 mL of ultrapure water under vigorous stirring, maintaining water/organic ratio 10/1 with a constant removal of the solution. The mixture was kept for 30 min under vigorous stirring. The solution was concentrated to a volume of 10 mL using a tangential flow filter (Pellicon XL filter device, Biomax membrane with 500.000 NMWL, Millipore, USA) following by filtration using a syringe filters SterivexTM-GP of polyethersulfone (0.22 μ m, Millipore, USA). Hydrodynamic size = 136.4 ± 0.9 nm, PDI = 0.067 ± 0.018, and ζ -potential = trimodal, far above the stability threshold.

Synthesis of PNPs-C/Fluo and PNPs-Fluo/Cltx

A water solution of PNPs–C/CCH (2 mL, –COOH and –CCH 1 μ mol) was mixed with the *p*-azidofluorescein **1** (40 mg, 0.076 mmol) together with copper sulfate hydrate (0.7 mg, 0.0028 mmol) and (+)-sodium L-ascorbate (0.3 mg, 0.0015 mmol). The mixture was allowed to stir overnight. The resulting particles were washed with ultrapure water (up. water) using a centrifugal (3000 rpm, 15 min) filter devices (Amicon Ultra, Ultracel membrane with 100.000 NMWL, Millipore, USA) till the washing water resulted in a colorless fluid. Finally, the particles were redispersed in 5 mL of up. water.

To this dispersion, a water solution containing N-hydroxysulfosuccinimide (0.1 mg, 0.46 μ mol) was added together with 1-ethyl-3-(3-dimethylaminopropyl)carbodiimide (EDC, 2 mg, 0.012 mmol) that was

pre-acidified with 0.1 M HCl solution to neutral pH (~7). The solution was shacked for 30 min to permit the activation. Next, the Cltx (0.5 mL of a 0.017 M solution, 0.0085 mmol) was added to the reaction mixture and it was allowed to shake overnight. The resulting particles were washed with up. water using a centrifugal (3000 rpm, 15 min) filter devices (Amicon Ultra, Ultracel membrane with 100.000 NMWL, Millipore, USA). Finally, the particles were filtered through a SterivexTM-GP of polyethersulfone (0.22 µm, Millipore, USA). Hydrodynamic size = 180.3 ± 3.1 nm, PDI = 0.146 ± 0.014 , ζ -potential = -38.1 mV, and pH = 7.04. Polymer concentration obtained by weighing a dried aliquot of the final solution = 1.226 mg/mL.

Intracellular localization of PNPs-Fluo/Cltx

To perform microscopy studies, cells were seeded onto 4-chamber polystyrene vessel tissue culturetreated glass slides (BD Falcon, Italy) in 1 mL of complete cell culture medium and cultured under standard cells culture conditions (37 °C, 5 % CO₂, 95 % humidity). After 24 h, cells were exposed to 0.88 µg/mL of PNPs-Fluo/Cltx for 48 h and 72 h; then fixed with 4 % (v/v) formaldehyde (Sigma Aldrich, Italy) solution in PBS and stained using Hoechst-33342 (Invitrogen, USA) for nuclei. Images were acquired using an Axiovert 200 M inverted microscope (Carl Zeiss, Germany) equipped with ApoTome slide module and AxioVision 4.8 software (Carl Zeiss, Germany), using 40×1.0 objective lens. Images were acquired using a black and white AxioCam MRm (Carl Zeiss, Germany) and pseudo-colors were applied after image acquisition.

Acknowledgments The work was partly supported with the funds of SaveMe EU-FP7 project no. CP-IP 263307-2.

References

- Agarwal A, Tripathi PK, Tripathi S, Jain NK (2008) Fluorescence imaging: applications in drug delivery research. Curr Drug Targets 9:895–898
- Cheng J, Teply BA, Sherifi I, Sung J, Luther G, Gu FX, Levy-Nissenbaum E, Radovic-Moreno AF, Langer R, Farokhzad OC (2007) Formulation of functionalized PLGA–PEG nanoparticles for in vivo targeted drug delivery. Biomaterials 28(5):869–876
- Comes Franchini M, Bonini BF, Camaggi CM, Gentili D, Pession A, Rani M, Strocchi E (2010) Design and synthesis of

novel 3,4-disubstituted pyrazoles for nanomedicine applications against malignant gliomas. Eur J Med Chem 45(5):2024–2033

- Gentili D, Ori G, Comes Franchini M (2009) Double phase transfer of gold nanorods for surface functionalization and entrapment into PEG-based nanocarriers. Chem Commun 39:5874–5876
- Gu F, Zhang L, Teply BA, Mann N, Wang A, Radovic-Moreno AF, Langer R, Farokhzad OC (2008) Biodegradable PLGA-b-PEG polymeric nanoparticles: synthesis, properties and nanomedical applications as drug delivery system. PNAS 105:2586–2591
- Hermanson GT (2008) Bioconjugate techniques, 2nd edn. Elsevier, London
- Huisgen R (1984) 1,3-Dipolar cycloadditions. In: Padwa A (ed) 1,3-Dipolar cycloaddition chemistry. Wiley, New York
- Johnson I (1998) Review: fluorescent probes for living cells. Histochem J 30(3):123–140
- Lin PC, Ueng SH, Tseng MC, Ko JL, Huang KT, Yu SC, Adak AK, Chen YJ, Lin CC (2006) Site-specific protein modification through CuI-catalyzed 1,2,3-triazole formation and its implementation in protein microarray fabrication. Angew Chem Int Ed 45(26):4286–4290
- Locatelli E, Comes Franchini M (2012) Biodegradable PLGAb-PEG polymeric nanoparticles: synthesis, properties, and nanomedical applications as drug delivery system. J Nanopart Res 14(12):1–17
- Locatelli E, Broggi F, Ponti J, Marmorato P, Franchini F, Lena S, Comes Franchini M (2012) Lipophilic silver nanoparticles and their polymeric entrapment into targeted-PEGbased micelles for the treatment of glioblastoma. Adv Healthc Mater 1(3):342–347
- Metallo SJ, Kane RS, Holmlin RE, Whitesides GM (2003) Using bifunctional polymers presenting vancomycin and fluorescein groups to direct anti-fluorescein antibodies to self-assembled monolayers presenting D-alanine-D-alanine groups. J Am Chem Soc 125(15):4534–4540
- Moses JE, Moorhouse AD (2007) The growing applications of click chemistry. Chem Soc Rev 36(8):1249–1262
- Opsteen JA, Ayres L, van Hest JCM (2008) Click chemistry in (bio) materials sciences. Mater Matters 3:62–64
- Rostovtsev VV, Green LG, Fokin VV, Sharpless KBA (2002) Stepwise Huisgen cycloaddition process: copper(I)-catalyzed regioselective "ligation" of azides and terminal alkynes. Angew Chem Int Ed 41(14):2596–2599
- Tornøe CW, Christensen C, Meldal M (2002) Peptidotriazoles on solid phase: [1,2,3]-triazoles by regiospecific copper(I)catalyzed 1,3-dipolar cycloadditions of terminal alkynes to azides. J Org Chem 67(9):3057–3064
- Urano Y, Kamiya M, Kanda K, Ueno T, Hirose K, Nagano T (2005) Evolution of fluorescein as a platform for finely tunable fluorescence probes. J Am Chem Soc 127(13): 4888–4894
- Wang X, Liu L, Luo Y, Zhao H (2009) Bioconjugation of biotin to the interfaces of polymeric micelles via in situ click chemistry. Langmuir 25:744–750
- Weber G, Teale FW (1958) Fluorescence excitation spectrum of organic compounds in solution, part 1. Systems with quantum yield independent of the exciting wavelength. J Trans Faraday Soc 54:640–648