Monitoring the dispersion and agglomeration of silver nanoparticles in polymer thin films using Localized Surface Plasmons and Ferrell Plasmons

Rafael C Hensel, Murilo Moreira, Antonio Riul, Osvaldo N Oliveira, Varlei Rodrigues, Matthias Hillenkamp

► To cite this version:

Rafael C Hensel, Murilo Moreira, Antonio Riul, Osvaldo N Oliveira, Varlei Rodrigues, et al.. Monitoring the dispersion and agglomeration of silver nanoparticles in polymer thin films using Localized Surface Plasmons and Ferrell Plasmons. Applied Physics Letters, 2020, 116 (10), pp.103105. 10.1063/1.5140247 . hal-02497318

HAL Id: hal-02497318

<https://hal.science/hal-02497318>

Submitted on 3 Mar 2020

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Monitoring the dispersion and agglomeration of silver nanoparticles in polymer thin films using Localized Surface Plasmons and Ferrell Plasmons

Rafael C. Hensel¹, Murilo Moreira¹, Antonio Riul Jr¹, Osvaldo N. Oliveira Jr², Varlei Rodrigues¹, Matthias Hillenkamp^{1,3} *

¹ Instituto de Física Gleb Wataghin, UNICAMP, CP 6165, 13083-970 Campinas, SP, Brazil

² São Carlos Institute of Physics (IFSC), University of São Paulo (USP), P.O. Box 369, 13566-590 São Carlos, SP, Brazil

³ Institute of Light and Matter, Univ. Lyon, Université Claude Bernard Lyon 1, CNRS, UMR5306, F-69622, Villeurbanne, France

The ability to disperse metallic nano-objects in a given matrix material is an important issue for the design and fabrication of functional materials. A means to monitor the spatial distribution of the nano-dopants is highly desirable, but often possible only *a posteriori* and with destructive techniques. Here we present a spectroscopic characterization based on different plasmonic responses of silver nanoparticles, their agglomerates and finally the percolated silver film. We demonstrate its usefulness for the specific case of their dispersion in Layer-by-Layer polymeric films but the method is extendable to any other host material transparent in the visible/near UV range. Individual silver nanoparticles display the well-known localized surface plasmon resonance around 400 nm, which is red-shifted upon inter-particle coupling. The transition regime between weakly coupled particles and fully percolated metal films is, however, much harder to evidence unambiguously. We show here how to monitor this transition using the so-called Ferrell plasmon, a plasmonic mode of the thin film in the mid-UV and excitable only under oblique irradiation but without specific coupling precautions. We can thus follow the entire transition from isolated to coupled and finally to fully agglomerated nanoparticles by optical spectroscopy.

* Corresponding author: matthias.hillenkamp@univ-lyon1.fr

Polymers constitute a large class of soft matter materials with a broad range of properties, playing essential and ubiquitous roles in everyday life. Especially when fabricated in alternating structures of polyelectrolytes (“Layer-by-Layer”, LbL), they represent a valuable toolbox for the high precision fabrication and tuning of properties of thin films through the choice of constituents [1]. LbL is based on the sequential adsorption of polyelectrolytes via electrostatic and non-covalent (van der Waals, hydrogen bonding, hydrophobic, charge-transfer, etc.) interactions, endowing multilayers with distinct functionalities and capabilities to address a wide range of applications. They exist e.g. as insulators and conductors or with variable optical and mechanical properties such as transparency, stiffness or porosity (i.e. gas permeability) [2, 3]. The inclusion of metallic aggregates into a polymer matrix has attracted a lot of attention in the last years as it can significantly enhance its mechanical, optical, thermal, electrical or catalytic properties [4, 5, 6, 7], but so far this is achieved mainly through chemical approaches. Typically, chemically fabricated and passivated nanoparticles (NPs) are added to the spin-coating solution or used as one of the polyelectrolytes, leaving crucial parameters like particle concentration and interfaces out of reach. The inclusion of physically fabricated, pure metallic NPs in simpler polymers such as polydimethylsiloxane (PDMS), poly(methyl methacrylate) (PMMA) or polystyrene [8] has, however, demonstrated the feasibility and potential use in applications like stretchable electronics [9], or plasmonic materials [10], actuators [11] and antibacterial materials [12].

One of the most promising applications of thin polymer films with embedded metal NPs is in (bio)sensors. LbL polymer films are widely used as active biocompatible and functionalized layers in sensors based on the impedance response over a large frequency range in combination with data processing methods such as Principal Component Analysis [13]. This multi-dimensional data extraction allows efficient discrimination between trace amounts of different analytes, even in minute quantities. Tuning the impedance of the active layer by controlling the metal loading through NP incorporation is expected to significantly enhance both sensitivity and selectivity of such devices [14], as already demonstrated for an LbL system [15]. The underlying mechanisms remain, however, unclear and the study of systems with controlled architecture is needed. Notably, the NP composition (including surface termination), their size and spatial dispersion inside the polymer matrix are crucial parameters determining the composite’s properties and suitability in applications. In order to better understand the influence of the different parameters the particles should be isolated from each other. In this case the well-known and well-defined individual properties, such as the Localized Surface Plasmon Resonance (LSPR) or superparamagnetism, can be exploited, which are otherwise often masked or complicated by inter-particle interactions, e.g. in spin-glasses. This knowledge is crucial to design composite structures for specific applications in sensors, fuel cell membranes and energy harvesting applications.

The aim of this letter is to demonstrate how to monitor the spatial dispersion and agglomeration of silver NPs in LbL polymer films using optical spectroscopy. We show how to infer the transition from isolated to coupled NPs and finally to a continuous film from the plasmonic response.

Our approach to fabricating benchmark samples of LbL polymer films with embedded metal NPs is based on the fragmentation-free implantation of NPs fabricated in the gas phase. Surfactant-free silver NPs are generated in magnetron cluster sources [16, 17], where silver atoms are sputtered from a wire or disc target. The atomic vapor is quenched in an argon/helium atmosphere, promoting aggregation into NPs, a large fraction of which are positively charged. The whole cluster source is electrically floating with respect to ground, its potential defining the kinetic energy of the silver cluster ions. Time-of-flight mass spectrometry permits in-situ monitoring and adjusting the mean particle size and dispersion. The beam is then focused onto the sample holder. In this study NPs with mean diameter controlled between 2 and 5 nm are implanted at kinetic energies between 100-250 eV.

LbL films with two polyelectrolyte couples were deposited on quartz substrates by sequential dipping [18]. Two different polyelectrolyte couples are used here. Poly(allylamine hydrochloride) (PAH) and poly(sodium 4-styrenesulfonate) (PSS) in (PAH/PSS)_n architecture is a standard system, the films described here typically consist of 150 bilayers with a total thickness of ~300 nm. The second system used is polyethylenimine (PEI) and poly(acrylic acid) (PAA) in (PEI/PAA)_n architecture, which has been shown to grow exponentially [19]. Here films of thickness ~400 and ~3200 nm were grown, corresponding to 3 and 4 bilayers, respectively. The materials were obtained from Sigma-Aldrich and used as received. All solutions were prepared in ultrapure water from a Sartorius Arium Comfort system. PAH and PSS solutions were prepared at 0.5 mg/mL, with the pH adjusted to 7 using 0.1 M HCl or 0.1 M NaOH solutions. The PEI solution was prepared at 1 mg/mL and pH 9, the PAA solution was prepared at 3 mg/mL and pH 3. The absence of degradation when transferring the films into vacuum was verified with optical absorption and Raman spectroscopy; in no case was a significant change in the response evidenced. Both film materials are very soft, a fragmentation-free particle penetration is expected even for the comparably low kinetic energies of ~0.1 eV/atom [8]. The mean penetration depth is defined by the particle material, its size and kinetic energy, as well as by the nature of the polymer material. We do not present a comprehensive quantification of the different parameters, but rather demonstrate the principal feasibility of controlled NP dispersion in the polymer matrix. As the NP beam is focused onto the polymer film, the concentration of NPs continuously varies from the center of the deposition spot towards the edge of the film, permitting concentration dependent measurement series. Optical spectroscopy was performed in a Perkin Elmer Lambda 900 spectrophotometer in transmission mode. Where indicated linear polarizers were used. All spectra were normalized to reference spectra taken for undoped polymer films, outside the NP spot.

It is well known that, with increasing concentration, inter-particle coupling between neighboring NPs leads to a gradual redshift of the LSPR, transforming the optical response from the superposition of many individual NP LSPR signals to a collective response [20, 21]. We have observed this behavior in many samples and spectroscopic geometries. While for weak coupling the (perturbed) LSPR is the spectroscopic fingerprint of choice, for higher metal loadings a simple spectroscopic response is not easily available. In the following, we will introduce a purely plasmonic characterization technique that covers the whole range of interest.

Interestingly, when performing the optical spectroscopy with linearly polarized light (TM) at an oblique angle (55° with respect to the surface normal for all spectra shown), i.e. with a component of the electrical field normal to the surface, an additional, narrow peak appears in the UV for many samples, as shown in Fig. 1. This peak is absent for highly dilute samples (e.g. Ag NPs in silica [22]), but it was observed for many different particle concentrations and different polymer matrices. It is observed up to highest Ag loading, when the films start to turn opaque and mirror-like. At this point the LSPR is no longer measurable. The spectral position and width of this additional signal vary slightly between samples and illuminated spots but to a much lesser extent than the LSPR, which is red-shifted and broadened due to inter-particle interactions. When measuring in the same geometry but with TE polarized light or at perpendicular incidence, only the (red-shifted) LSPR remains and the additional peak in the UV disappears, as shown in Fig. 2. Here the relative blue-shift of the TM LSPR with respect to the TE and perpendicular measurements may be attributed to the formation of anisotropic NP agglomerates but is not central to our argument. Slight variations between curves taken for different geometries are due to the different normalizations. Great care has been taken to ensure that the effects discussed in this letter are independent of and much stronger than these normalization-dependent variations. Note that no size-dependent shifts of the intrinsic LSPR wavelength are expected for Ag NPs in comparable matrices [22]. The underlying mechanism responsible for the additional peak in the UV thus must be independent of the matrix and different from the LSPR.

Figure 1: Optical extinction spectra of Ag NPs in different matrices under TM irradiation. Strongly diluted particles in silica only show the well-known LSPR at 420 nm and the rise below ~ 310 nm due to interband transitions [22] (black curve). Samples with higher concentrations in two different polymer matrices display a red-shifted LSPR and an additional peak around ~ 340 nm, absent at TE illumination. NP diameters were 2.7 nm (SiO_2), 4.9 nm (PAH/PSS) and 2.2 nm (PEI/PAA).

Figure 2: Polarization dependence of the optical response for a sample with 3.5 nm Ag NPs in a PAH/PSS LbL film of ~ 300 nm thickness.

We now show that the additional signal at ~ 340 nm stems from the formation of a continuous thin silver film in the polymer matrix by comparing the samples described above to evaporated silver films. Structural information about the samples is presented in the supporting information. In the case of a continuous silver thin film, a transmission window around 330 nm is well known and best seen in the red curve of Fig. 3. This (negative in extinction) peak is a particularity of silver and appears because of the very close energetic proximity of the volume plasma energy (3.75 eV) and the onset of interband transitions (IB) at ~ 3.8 eV. A

continuous Ag film efficiently reflects light below the plasma frequency but, contrary to simple Drude-type metals, the film then does not become transparent but the IB transitions start absorbing. Between these two regimes lies a narrow window of very high transmittance at approximately the volume plasma frequency [23, 24], depending on the exact nature of the film.

Figure 3: Polarization dependence of the optical response for a thin Ag film of nominal thickness 10 nm. The blue curve is the difference between the TM and TE curves.

A silver film of thickness less than the skin depth can furthermore support several different plasmon modes, the best known being the Surface Plasmon Polaritons (SPP) in their short- and long-range version [25]. But there also exists a localized plasmon very close around the volume plasmon frequency [26]. Here the entire electron density oscillates perpendicular to the surface, comparable to a plane capacitor. These “normal surface plasma oscillation” or Ferrell modes [27, 28] possess an oscillating dipole moment and thus couple directly to light, contrary to both longitudinal volume plasmons and plasmon polaritons. In fact Ferrell modes are the stationary counterpart of the long range propagative plasmon polariton in thin films, on the left side of the light line [26]. They can, however, only be excited with TM polarization, i.e. with a non-negligible component perpendicular to the thin film surface. This polarization dependence is shown for a 10 nm thick Ag film in figure 3. The difference curve in blue clearly shows the Ferrell plasmon resonance at 334 nm, i.e. at the plasma frequency of bulk silver. This Ferrell mode has been largely forgotten in the plasmonics community, except for a small number of publications based on its infrared counterpart (termed Berreman mode) in epsilon-near-zero materials [29, 30, 31]. Note that while closely related to, a Ferrell mode is neither a volume plasmons nor an SPP, none of which can be directly excited by light.

On this basis we can now interpret the optical spectra of our cluster-assembled nanostructures. At lowest NP concentration the intrinsic LSPR is measured. Its spectral position can be described by classical Mie theory taking into account the dielectric properties of the matrix and corrections due to quantum effects at the small sizes investigated here (<5 nm) [22]. For larger particles retardation and multipole excitations have to be considered [20]. Increasing the volume concentration to >5% results in inter-particle coupling and a consecutive red-shift and broadening of the LSPR. Around the percolation a more or less continuous thin silver film is formed and the Ferrell mode appears in TM geometry. The fact that the films are not homogeneous in thickness and possibly discontinuous only slightly broadens and shifts the Ferrell mode. We can thus use the plasmonic response of NP doped films to monitor coupling and agglomeration through the whole range from isolated NPs to continuous films. The second transition, from coupled NPs to the thin film, is demonstrated in figure 4, which shows TM and TE spectra at two different positions of a sample of

3.4 nm Ag NPs implanted into a (PAH/PSS)₁₅₀ LbL film. A deposition energy of 240 eV results in high spatial dispersion. At low particle density, only the LSPR of interacting Ag NPs is visible at ~450 nm at the edge of the area with implanted NPs. Towards the center of the NPs spot the Ferrell plasmon peak appears in TM geometry.

Figure 4: Polarization-dependent plasmonic response curves of a sample with 3.4 nm Ag NPs implanted into a (PAH/PSS)₁₅₀ LbL film at a deposition energy of 240 eV. Only at high NP concentration, inside the particle spot, is the Ferrell plasmon of a continuous film visible.

The LSPR energy and width strongly depend on the shape and environment of the NP in question, thereby justifying their use in sensing applications. The Ferrell mode, on the other hand, is much more insensitive to the local structure. Even comparably ill-defined nanostructured films, like the concentrated ones discussed here, show clear peaks with only slight shifts and broadening. This makes the Ferrell mode a simple fingerprint, easy to realize and measure in various types of nanostructure geometries, especially when compared to more complex optical techniques relying on hot spots or near field excitation [32, 33]. Significantly, it does not require specific coupling through a high-index prism, as do the propagative surface plasmon polaritons [34]. A comprehensive theoretical description of the Ferrell mode in analogy to [29, 35, 36], and in particular for non-ideal systems like the ones presented here, is clearly desirable, but beyond the scope of this letter.

In conclusion, we have shown that the loading of transparent thin films, here LbL fabricated polymer films, with silver nanoparticles, can easily be monitored by plasmon spectroscopy. Depending on the coupling between particles and their agglomeration into continuous metal film structures, a signal in the UV, additional to the well-known localized surface plasmon resonance, appears if a significant fraction of the electric field of the exciting light is normal to the film. This effectively forgotten Ferrell mode, at the volume plasmon frequency, is a fingerprint of a (semi-) continuous thin silver film, easy to realize and detect. Our wide-range plasmonic characterization technique is an important step towards the controlled tuning of nanoparticle doped polymer films for applications in sensors or fuel cell membranes.

Supplementary Material

Complementary structural characterization of thin Ag films and Ag NP doped LbL films can be found in the supplementary material.

The authors are grateful to the São Paulo Research Foundation (FAPESP, 2014/03691-7, 2013/14262-7, 2016/12807-4), CNPq, CAPES and the Brazilian Science Without Borders "Special Visiting Scientist" program (88881.030488/2013-01) for financial support. Experimental support from the Microfabrication Laboratory of the Brazilian Nanotechnology National Laboratory (DB-C1-25094) and (TEM-C1-25093) is acknowledged. This work was partly performed using the Lyon Cluster Research Platform PLYRA. We thank A. Piednoir, O. Boisson, C. Albin and C. Clavier for technical support and J. Bellessa for fruitful discussions.

References

- [1] Richardson, J. J., Björnmalm, M., and Caruso, F. *Science* **348**(6233) (2015).
- [2] Rogers, J. A., Someya, T., and Huang, Y. *Science* **327**, 1603 (2010).
- [3] Pang, C., Lee, C., and Suh, K.-Y. *J. Appl. Polym. Sci.* **130**, 1429 (2013).
- [4] Berry Jr., K. R., Russell, A. G., Blake, P. A., and Roper, D. K. *Nanotechnology* **23**, 375703 (2012).
- [5] Ferreira, J., Teixeira, F. S., Zanatta, A. R., Salvadori, M. C., Gordon, R., and Oliveira, O. N. *Phys. Chem. Chem. Phys.* **14**, 2050 (2012).
- [6] Oliveira, O. N., Iost, R. M., Siqueira, J. R., Crespilho, F. N., and Caseli, L. *ACS Appl. Mater. Interfaces* **6**, 14745 (2014).
- [7] Maurer, T., Marae-Djouda, J., Cataldi, U., Gontier, A., Montay, G., Madi, Y., Panicaud, B., Macias, D., Adam, P.-M., Lévêque, G., Bürgi, T., and Caputo, R. *Front. Mater. Sci.* **9**, 170 (2015).
- [8] Ghisleri, C., Borghi, F., Ravagnan, L., Podestà, A., Melis, C., Colombo, L., and Milani, P. *J. Phys. D: Appl. Phys.* **47**, 015301 (2014).
- [9] Gabriele, C., Cristian, G., Mattia, M., Paolo, M., and Luca, R. *Adv. Mater.* **23**, 4504–4508 (2011).
- [10] Minnai, C. and Milani, P. *Appl. Phys. Lett.* **107**(7), 073106 (2015).
- [11] Yunsong, Y., Tommaso, S., Giacomo, B. L., Chloé, M., Andrea, B., Riccardo, P., Ilaria, D., Gabriele, F., Marco, M., Cristina, L., and Paolo, M. *Adv. Mater.* **29**, 1606109 (2017).
- [12] Popok, V. N., Jeppesen, C. M., Fojan, P., Kuzminova, A., Hanuš, J., and Kylián, O. *Beilstein J. Nanotechnol.* **9**, 861 (2018).
- [13] Riul Jr., A., Dantas, C. A. R., Miyazaki, C. M., and Oliveira Jr., O. N. *Analyst* **135**, 2481 (2010).
- [14] Barsan, M. M. and Brett, C. M. *TrAC, Trends Anal. Chem.* **79**, 286 – 296 (2016).
- [15] Mercante, L. A., Scagion, V. P., Pavinatto, A., Sanfelice, R. C., Mattoso, L. H. C., and Correa, D. S. *J. Nanomater.* , 890637 (2015).
- [16] Hillenkamp, M., Di Domenicantonio, G., and Félix, C. *Rev. Sci. Instrum.* **77**, 025104 (2006).
- [17] de Sá, A. D. T., Oiko, V. T. A., di Domenicantonio, G., and Rodrigues, V. *J. Vac. Sci. Technol. B* **32** (2014).

- [18] Hensel, R. C., Rodrigues, K. L., Pimentel, V. d. L., Riul, A., and Rodrigues, V. *MRS Commun.* **8**, 283–288 (2018).
- [19] Fu, J., Ji, J., Shen, L., Küller, A., Rosenhahn, A., Shen, J., and Grunze, M. *Langmuir* **25**(2), 672–675 (2009).
- [20] Kreibig, U. and Vollmer, M. *Optical properties of metal clusters*. Springer series in materials science. Springer Berlin, (1995).
- [21] Quinten, M. *Optical Properties of Nanoparticle Systems*. Wiley-VCH, (2011).
- [22] Campos, A., Troc, N., Cottancin, E., Pellarin, M., Weissker, H.-C., Lermé, J., Kociak, M., and Hillenkamp, M. *Nat. Phys.* **15**, 275–280 (2019).
- [23] Ehrenreich, H. and Philipp, H. R. *Phys. Rev.* **128**, 1622–1629 (1962).
- [24] Ehrenreich, H. *IEEE Spectr.* **2**(3), 162–170 (1965).
- [25] Raether, H. In *Surface plasmons on smooth and rough surfaces and on gratings*, 4–39. Springer (1988).
- [26] Ritchie, R. *Surf. Sci.* **34**(1), 1 – 19 (1973).
- [27] Ferrell, R. A. *Phys. Rev.* **111**, 1214–1222 (1958).
- [28] McAlister, A. J. and Stern, E. A. *Phys. Rev.* **132**, 1599–1602 Nov (1963).
- [29] Vassant, S., Hugonin, J.-P., Marquier, F., and Greffet, J.-J. *Opt. Express* **20**(21), 23971–23977 (2012).
- [30] Newman, W. D., Cortes, C. L., Atkinson, J., Pramanik, S., DeCorby, R. G., and Jacob, Z. *ACS Photonics* **2**(1), 2–7 (2015).
- [31] Passler, N. C., Razdolski, I., Katzer, D. S., Storm, D. F., Caldwell, J. D., Wolf, M., and Paarmann, A. *ACS Photonics* **6**, 1365–1371 (2019).
- [32] Seal, K., Genov, D., Sarychev, A., Noh, H., Shalaev, V., Ying, Z., Zhang, X., and Cao, H. *Phys. Rev. Lett.* **97**(20), 206103 (2006).
- [33] Borys, N. J., Shafran, E., and Lupton, J. M. *Sci. Rep.* **3**, 2090 (2013).
- [34] Berthelot, A., des Francs, G. C., Varguet, H., Margueritat, J., Mascart, R., Benoit, J.-M., and Laverdant, J. *Nanotechnology* **30**, 015706 (2019).
- [35] Burke, J. J., Stegeman, G. I., and Tamir, T. *Phys Rev B* **33**, 5186–5201 (1986).
- [36] Berini, P. *Phys. Rev. B* **63**, 125417 (2001).