Coherent Mid-Infrared Supercontinuum Sources in Silicon- Germanium Waveguides

Alberto Della Torre, Milan Sinobad, Remi Armand, Barry Luther-Davis, Pan Ma, Stephen Madden, Sukanta Debbarma, Khu Vu, David Moss, Arnan Mitchell, et al.

► To cite this version:

Alberto Della Torre, Milan Sinobad, Remi Armand, Barry Luther-Davis, Pan Ma, et al.. Coherent Mid-Infrared Supercontinuum Sources in Silicon- Germanium Waveguides. Conference on Lasers and Electro-Optics, May 2020, San Jose, United States. 10.1364/CLEO_QELS.2020.FTu3Q.6 . hal-02566013

HAL Id: hal-02566013

<https://hal.science/hal-02566013>

Submitted on 6 May 2020

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Coherent Mid-Infrared Supercontinuum Sources in Silicon-Germanium Waveguides

Alberto Della Torre,^{1,6} Milan Sinobad,^{1,2} Rémi Armand,¹ Barry Luther-Davis,³ Pan Ma,³ Stephen Madden,³ Sukanta Debbarma,³ Khu Vu,³ David J. Moss,⁴ Arnan Mitchell,² Jean-Michel Hartmann,⁵ Jean-Marc Fedeli,⁵ Christelle Monat,¹ and Christian Grillet¹

¹Université de Lyon, Institut des Nanotechnologies de Lyon (INL), 69131 Ecully, France

²School of Engineering, RMIT University, Melbourne, VIC 3001, Australia

³Laser Physics Center, Australian National University, Canberra, ACT 0100, Australia

⁴Centre for Microphotonics, Swinburne University of Technology, Hawthorn, VIC 3122, Australia

⁵Université Grenoble Alpes, CEA-Leti, 38054 Grenoble Cedex 9, France

⁶e-mail : alberto.della-torre@ec-lyon.fr

Abstract: We report coherent mid-infrared supercontinuum generation in silicon-germanium waveguides. We show that the degree of coherence can be controlled by either employing an air clad configuration or a hybrid chalcogenide/silicon-germanium system. © 2020 The Author(s)

OCIS codes: (320.6629) Supercontinuum generation; (190.4390) Nonlinear optics, Integrated optics; (140.3070) Infrared and far-infrared lasers.

1. Introduction

In the last decades, supercontinuum (SC) sources have found numerous applications owing to their unique feature of combining high brightness and ultra-broad spectral bandwidth. Mid-infrared (mid-IR, 2-20 μm) sources have attracted particular interest for spectroscopic and sensing applications, due to the strong molecular fingerprint in this spectral region [1,2]. The integration of mid-IR SC sources in a CMOS compatible platform is a technological challenge that would allow to leverage the already existing manufacturing infrastructure to develop high volume, low cost sensing technology. On-chip SC can be generated via nonlinear effects that broaden the spectrum of a pulse injected in an optical waveguide. By exploiting the promising nonlinear properties and wide transparency window (from 3 to 15 μm) of germanium [3,4], we recently demonstrated SC generation from 3 to 8.5 μm in a silicon-germanium on silicon platform [5]. For many applications, however, in addition to a wide spectral bandwidth, it is crucial that the SC pulses maintain high shot-to-shot stability in both amplitude and phase, i.e. a high degree of temporal coherence [6].

Here, we study the coherence properties of mid-IR SCs that are experimentally generated in silicon-germanium ($\text{Si}_{0.6}\text{Ge}_{0.4}$) on silicon waveguides. We showed that a $3.75 \times 2.7 \mu\text{m}^2$ cross-section air clad waveguide, pumped in the anomalous dispersion regime, maintains high coherence at the extreme parts of the spectrum [7], thereby allowing for pulse stabilization via f -to- $2f$ self-frequency referencing for high precision spectroscopy applications. Yet, many spectroscopy and imaging techniques, such as coherent Raman spectroscopy, anti-stokes Raman spectroscopy and optical coherence tomography, require high coherence across the entire spectrum [6]. We show that we can trim the coherence properties of the SC by simply depositing a chalcogenide cladding layer, generating a fully coherent mid-IR SC.

2. Coherent Supercontinuum generation

$\text{Si}_{0.6}\text{Ge}_{0.4}$ waveguides were pumped in the TE polarization at $\sim 4 \mu\text{m}$ by a MIROPA-fs (Hotlight Systems) optical parametric amplifier delivering nearly transform-limited ~ 200 fs pulses with 63 MHz repetition rate. A $3.75 \times 2.7 \mu\text{m}^2$ cross-section, 7 cm long air clad waveguide was pumped with 2.35 kW coupled peak power pulses in the anomalous dispersion regime (fig. 1(a), left), generating a SC spanning more than one octave (-30dB bandwidth from 2.63 up to 6.18 μm , fig. 1(a), right). The SC generation process was simulated by numerically solving the generalized nonlinear Schrodinger equation and the degree of first-order coherence $g^{(1)}_{12}$ was calculated from 40 independent simulations with random input noise. The right hand side of fig. 1(a) shows the good agreement between experimental and simulated spectra. We attribute the discrepancy beyond 5.5 μm to water vapor absorption [8] that takes place along the free-space path from the chip output to the spectrometer. The coherence is high (>0.99) at the extreme parts of the spectrum, at f ($\lambda=5.8 \mu\text{m}$) and $2f$ ($\lambda=2.9 \mu\text{m}$), but not across its whole bandwidth. The high coherence is preserved thanks to a careful design of the waveguide's dispersion profile, which inhibits the amplification of noise [7].

The same waveguide was then covered with a 1.26 μm thick cladding layer of $\text{Ge}_{11.5}\text{As}_{24}\text{Se}_{64.5}$ chalcogenide glass, shifting the dispersion curve to all-normal (fig. 1(b), left) [9]. This allowed to generate a slightly narrower SC (spanning from 3.1 to 5.5 μm), but fully coherent across the entire spectrum (fig. 1(b), right).

Fig. 1. (a) Left: dispersion profile and cross section (inset) of the $3.75 \times 2.7 \mu\text{m}^2$ air clad waveguide; right: corresponding experimental (blue) and simulated (red) SC at 2.35 kW coupled peak power, water absorbance beyond $5 \mu\text{m}$ (grey) [8] and calculated first-order coherence (green). (b) Left: dispersion profile and cross section (inset) of the $3.75 \times 2.7 \mu\text{m}^2$ chalcogenide clad waveguide; right: corresponding experimental (blue) and simulated (red) SC at 2.32 kW coupled peak power and calculated first-order coherence (green). The black arrows on the spectra indicate the pump wavelengths.

3. Conclusion

In summary, we demonstrate on-demand control of the spectral and coherence properties of on-chip mid-IR SCs. We show that either high coherence at f and $2f$ or full coherence can be achieved in a highly nonlinear SiGe waveguide, with potential spectroscopic, sensing and imaging applications.

Acknowledgments. We acknowledge the support of the International Associated Laboratory in Photonics between France and Australia (LIA ALPhFA), the Agence Nationale de la Recherche (MIRSIOMB, ANR-17-CE24-0028) and the European Research Council (ERC) under the European Union's Horizon 2020 program (GRAPHICS 648546).

References

- [1] M. Vainio *et al.*, "Mid-infrared optical parametric oscillators and frequency combs for molecular spectroscopy", *Physical Chemistry Chemical Physics* **18**(6), 4266-4294 (2016).
- [2] Soref, R., "Mid-infrared photonics in silicon and germanium," *Nature Photonics* **4**, 495-497 (2010).
- [3] N. K. Hon, R. Soref and B. Jalali, "The third-order nonlinear optical coefficients of Si, Ge, and $\text{Si}_{1-x}\text{Ge}_x$ in the midwave and longwave infrared," *J. Appl. Phys.* **110**, 011301 (2011).
- [4] G. Z. Mashanovich *et al.*, "Germanium Mid-Infrared Photonic Devices," *J. Light. Technol.* **35**, 624-630 (2017).
- [5] M. Sinobad *et al.*, "Mid-infrared octave spanning supercontinuum generation to $8.5 \mu\text{m}$ in silicon-germanium waveguides," *Optica* **5**, 360 (2018).
- [6] A. M. Heidt *et al.*, "Limits of coherent supercontinuum generation in normal dispersion fibers," *JOSA B* **34**(4), 764-775 (2017).
- [7] M. Sinobad *et al.*, "High Coherence at f and $2f$ of Mid-Infrared Supercontinuum Generation in Silicon Germanium Waveguides," *JSTQE* **26**, 1-8 (2019).
- [8] L. S. Rothman *et al.*, "The HITRAN2012 molecular spectroscopic database," *J. Quant. Spectrosc. Radiat. Transf.* **130**, 4-50 (2013).
- [9] M. Sinobad *et al.*, "Dispersion trimming for mid-infrared supercontinuum generation in a hybrid chalcogenide/silicon-germanium waveguide," *J. Opt. Soc. Am. B* **36**, 98-104 (2019).