ARTICLE

Molecular Complexes and Main-Chain Organometallic Polymers Based on Janus Bis(carbenes) Fused to Metalloporphyrins

Received 00th January 20xx,
Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

Jean-François Longevial,^{*ab} Mamadou Lo,^{ac} Aurélien Lebrun,^d Danielle Laurencin,^a Sébastien Clément,^a and Sébastien Richeter^{*a}

Janus bis(N-heterocyclic carbenes) composed of a porphyrin core with two N-heterocyclic carbenes (NHCs) heads fused to opposite pyrroles were used as bridging ligands for the preparation of metal complexes. We first focused our attention on the synthesis of gold(I) chloride complexes [(NHC)AuCl] and investigated the substitution of the chloride ligand by acetylides to obtain the corresponding [(NHC)AuC≡CR] complexes. Polyacetylides were then used to obtain molecular multiporphyrinic systems with porphyrins fused to only one NHC ligand, while main-chain organometallic polymers (MCOPs) were obtained when using Janus porphyrin bis(NHCs). Interestingly, MCOPs incorporating zinc(II) porphyrins proved to be efficient as heterogeneous photocatalysts for the generation of singlet oxygen upon visible light irradiation.

Introduction

In the field of organometallic chemistry, N-heterocyclic carbenes (NHCs) occupy a privileged place among all other ligands: (i) they can bind most of the transition metal ions in low and high oxidation states; (ii) their binding strength to metals is stronger than that of phosphines and (iii) their steric and electronic properties can be easily tuned (especially for NHCs belonging to the imidazol-2-ylidenes family).^{1–7} For all these reasons, NHCs are being actively investigated as ancillary ligands in homogeneous catalysis, in which a precise control over the steric and electronic properties is needed.⁸ Nowadays, the success story of NHC-metal complexes in catalysis is still ongoing. Moreover, their application in different research fields such as the development of new metallodrugs⁵ or functional materials⁹ is also underway. In this context, poly(NHCs) ligands containing two or more NHCs have progressively been developed to expand the scope of possible applications. The coordination modes of these poly(NHCs) *i.e.* *chelating mode* or *bridging mode* strongly depends on their backbone structure. The *chelating mode* is when two NHCs bind one metal centre.^{10–13} The *bridging mode* instead is when the two NHCs bind two different metal centres.^{14–18} Many examples of bis(NHCs) acting as chelating ligands can be found in the literature since they

Figure 1. Examples of NHC-based organometallic polymers reported in the literature.

have found useful applications in catalysis.^{11,19–21} On the contrary, examples of non-chelating bis(NHC)s acting as bridging ligands are relatively scarce. For this purpose, rigid

^a ICGM, Univ Montpellier, CNRS, ENSCM, CC 1701, Campus Triolet, Place Eugène Bataillon, Montpellier, France.

^b CINAM, Univ Aix-Marseille, CNRS, Centre Interdisciplinaire de Nanoscience de Marseille, Campus de Luminy, Marseille, France.

^c UFR des Sciences et Technologies, Univ Assane Seck de Ziguinchor, Diabir-Ziguinchor, Sénégal.

^d Laboratoire de Mesures Physiques, Univ Montpellier, Campus Triolet, Place Eugène Bataillon, Montpellier, France.

E-mail: jean-francois.longevial@umontpellier.fr
sebastien.richeter@umontpellier.fr

Electronic Supplementary Information (ESI) available: [details of any supplementary information available should be included here]. See DOI: 10.1039/x0xx00000x

spacers such as π -conjugated systems are often used to obtain bis(NHC)s featuring linearly opposed coordination sites.^{14,22–26}

Poly(NHCs) fused to polyaromatic systems are also interesting ligands because supramolecular interactions such as π -stacking interactions can be used to obtain innovative self-assembled metallosupramolecular architectures,^{24–26} or to modulate the catalytic activities of molecular organometallic complexes.²⁷ These ligands also allow the preparation of luminescent complexes²⁸ and conducting and/or emissive materials.²⁹ They are also of great interest for the preparation of molecular materials such as main-chain organometallic polymers (MCOPs) (Figure 1).^{30–33} Such materials could be obtained with triptycene-based tris(NHCs)³² and tetraphenylmethane tetrakis(NHCs)³¹ ligands through the formation of C_{NHC}-Pd-C_{NHC} bonds, for example. Peris and coworkers prepared MCOPs with triphenylene-based tris(NHCs) ligands through the formation of C_{NHC}-Au-C_{acetylide} bonds.³³ These MCOPs were then used as insoluble materials for heterogeneous catalysis.

We have previously shown that porphyrins fused to imidazolium rings could be used as NHC precursors to anchor different metal ions such as palladium,^{34,35} rhodium,³⁶ silver³⁷ and gold^{38,39} at their periphery. Recently, we reported the synthesis of porphyrins containing two imidazolium rings fused to two opposite pyrrole units.⁴⁰ Here, we show that this Janus bis(NHCs) precursors can be used for the preparation of molecular trinuclear metal complexes (one metal ion in the porphyrin core and two others at the periphery, as illustrated in Figure 2, left side). Furthermore, we synthesized MCOPs containing polyacetylides and used them for photocatalytic applications.

Figure 2. Building blocks used in this study for the synthesis of MCOPs.

Results and discussion

Synthesis and characterization of Janus bis(NHC) gold(I) chloride complexes.

The nickel(II) porphyrin **Ni-Imi₂** containing two imidazole rings fused to two opposite pyrrole units was synthesized in eight steps and 14% global yield, starting from nickel(II) *meso* tetra(4-*tert*-butylphenyl)porphyrin and following our reported procedure.⁴¹ Methylation of the four imidazole nitrogen atoms with an excess of iodomethane in the presence of K₂CO₃ in DMF at room temperature afforded the bis(imidazolium) **Ni-I₂** in 95% yield (Scheme 1). The bis(imidazolium) **Zn-I₂** was obtained in

Scheme 1. Synthetic approach for preparing porphyrins fused to Janus bis-(N-heterocyclic carbene)-gold complexes **[Ni(AuCl)₂]** and **[Zn(AuCl)₂]**.

two steps. First, the bis(imidazole) **Ni-Imi₂** was demetallated with a TFA/H₂SO₄ 4:1 mixture. The obtained free base bis(imidazole) derivative, which appeared to be air- and light-sensitive, was not isolated and was immediately metalated with Zn(OAc)₂·2H₂O in a CHCl₃/MeOH 6:1 mixture at 45 °C for 1 h.⁴² Complexation of zinc(II) was confirmed by UV-Vis absorption spectroscopy showing the two characteristic Q bands of zinc(II)-porphyrin at 535 and 689 nm. Afterwards, the two peripheral imidazole rings of **Zn-Imi₂** were methylated as described above to obtain the corresponding bis(imidazolium) **Zn-I₂** in a global yield of 22% over two steps. For both compounds **Ni-I₂** and **Zn-I₂**, the methylation reaction was confirmed by ¹H NMR spectroscopy. Indeed, a singlet corresponding to the four N-CH₃ groups was observed at δ = 3.20 and 2.83 ppm for **Ni-I₂** and **Zn-I₂**, respectively. Moreover, a sharp singlet corresponding to the two imidazolium protons was observed δ = 10.79 and 10.05 ppm for **Ni-I₂** and **Zn-I₂**, respectively. The **Ni-I₂** and **Zn-I₂** dications were observed by ESI-TOF(+) mass spectrometry at m/z = 516.3 (m/z calc. for C₆₆H₇₀N₈Ni 516.3 Da [M-2]²⁺) and m/z = 519.3 (m/z calc. for C₆₆H₇₀N₈Zn 519.3 Da [M-2]²⁺), respectively.

We have previously shown that porphyrins fused to one imidazolium ring across two neighboring β,β -pyrrolic positions can be used as NHC precursors to synthesize mono(NHC) gold(I) complexes such as **[NiAuCl]**.³⁸ A commonly used synthetic strategy consists in forming the NHC-silver(I) complex followed by a transmetalation with [AuCl(tht)] (tht = tetrahydrothiophene). Janus bis(NHCs) gold(I) complexes **[Ni(AuCl)₂]** and **[Zn(AuCl)₂]** were obtained in 65% and 85% yield, respectively, following a similar procedure. It is worth noting that these complexes are very stable and could be purified by silica gel column chromatography. The characteristic ¹³C NMR signal of the NHCs was observed at δ = 182.7 and 182.0 ppm on

the $^{13}\text{C}\{^1\text{H}\}$ NMR spectra of $[\text{Ni}(\text{AuCl})_2]$ and $[\text{Zn}(\text{AuCl})_2]$, respectively, confirming the formation of the $\text{C}_{\text{NHC}}\text{-AuCl}$ bonds.^{1,43} The parent mass peaks could also be observed in their MALDI-TOF(+) mass spectra at $m/z = 1494.4$ Da (m/z calc. for $\text{C}_{66}\text{H}_{68}\text{Au}_2\text{Cl}_2\text{N}_8\text{Ni}$ 1494.4 Da $[\text{M}]^{++}$) for $[\text{Ni}(\text{AuCl})_2]$ and at $m/z = 1500.3$ Da (m/z calc. for $\text{C}_{66}\text{H}_{68}\text{Au}_2\text{Cl}_2\text{N}_8\text{Zn}$: 1500.4 Da $[\text{M}]^{++}$) for $[\text{Zn}(\text{AuCl})_2]$.

Synthesis and characterization of mono- and bis-(NHC)-gold(I)-acetylide complexes.

Ott⁴⁴ and Peris's³³ groups showed that the reaction between gold(I) complexes $[(\text{NHC})\text{-Au-Cl}]$ and acetylides (generated *in situ* through deprotonation of the corresponding terminal acetylenes with a base) afforded the desired complexes $[(\text{NHC})\text{-Au-C}\equiv\text{C-R}]$. Following a similar strategy, we synthesized the corresponding mono(NHC) gold(I) acetylide complex $[\text{NiAuPh}]$ in 66% yield by reacting $[\text{NiAuCl}]$ with phenylacetylene using slightly modified conditions (*i.e.* KOH, MeOH/THF) (Scheme 2 and Figure 3).^{44,45}

Scheme 2. General scheme for the synthesis of porphyrins fused to NHC gold(I) alkynyl complexes. M = Ni or Zn, n = 1 with porphyrin mono(NHC), n = 2 with porphyrin bis(NHC), R is an aromatic or a polyaromatic scaffold (see Figure 3).

It should be noted that $[\text{NiAuPh}]$ could only be purified by recrystallization from $\text{CH}_2\text{Cl}_2/\text{MeOH}$, because it decomposed on both silica gel and alumina columns. All spectroscopic data were in good agreement with the structure proposed for $[\text{NiAuPh}]$. Its parent mass peak was clearly observed at $m/z = 1620.4597$ (m/z calc. for $\text{C}_{71}\text{H}_{69}\text{AuN}_6\text{Ni}$ 1260.4603 Da $[\text{M}]^{+}$) by ESI-TOF(+) high-resolution mass spectrometry. The presence of the gold(I) phenylacetylide moiety was also confirmed by ^1H and $^{13}\text{C}\{^1\text{H}\}$ NMR spectroscopy. The principal information arises from the presence of a multiplet between $\delta = 7.13\text{-}7.35$ ppm corresponding to the 5H of the phenyl group. Moreover, six new signals appeared in its $^{13}\text{C}\{^1\text{H}\}$ NMR spectrum. Two of them at $\delta = 128.5$ and 105.0 ppm can be attributed to the two hybridized sp carbon atoms $\text{Au-C}\equiv\text{C}$ and $\text{Au-C}\equiv\text{C}$, respectively.^{44,46,47} The sp carbon atom directly linked to the gold(I) atom appeared more downfield shifted which is in accordance with the chemical shifts reported in the literature.⁴⁴ A downfield shift of ~ 16 ppm was also observed for the resonance of the C_{NHC} at $\delta = 198.7$ ppm ($\delta = 182.3$ ppm for $[\text{NiAuCl}]$). Finally, IR spectroscopy revealed the presence of the $\text{C}\equiv\text{C}$ stretching frequency at $\nu = 2114\text{ cm}^{-1}$.

In view of synthesizing MCOPs with the $\text{C}_{\text{NHC}}\text{-Au-C}_{\text{acetylide}}$ structural features, the reactivity of $[\text{NiAuCl}]$ with polyacetylides derived from 1,4-diethynylbenzene⁴⁸ and 1,3,5-

tri(4-ethynylphenyl)benzene⁴⁹ was investigated (Figure 3). Satisfyingly, tetranuclear Ni_2 and hexanuclear Ni_3 complexes were obtained in high yields of 75% and 95%, respectively. For complex Ni_2 , expected parent mass peaks was observed at $m/z = 2442.8$ (m/z calc. for $\text{C}_{136}\text{H}_{132}\text{Au}_2\text{N}_{12}\text{Ni}_2$ 2442.9 Da $[\text{M}]^{++}$) by MALDI-TOF(+) MS. The aromatic protons signal corresponding to the assembling phenyl group was observed as a singlet at $\delta = 7.21$ ppm by ^1H NMR spectroscopy. Similarly to $[\text{NiAuPh}]$, the $^{13}\text{C}\{^1\text{H}\}$ NMR spectrum of complex Ni_2 features the sp carbon atom signal at $\delta = 125.5$ ($\text{Au-C}\equiv\text{C}$) and 104.8 ($\text{Au-C}\equiv\text{C}$) ppm, while the signal of the C_{NHC} was observed at $\delta = 198.6$ ppm. For complex Ni_3 , the expected parent mass peaks was observed at $m/z = 3854.4$ (m/z calc. for $\text{C}_{219}\text{H}_{208}\text{Au}_3\text{N}_{18}\text{Ni}_3$ 3854.4 Da $[\text{M}+\text{H}]^{+}$) by MALDI-TOF(+) MS, and similar observations could be made when comparing ^1H and $^{13}\text{C}\{^1\text{H}\}$ NMR spectra of complexes Ni_3 and Ni_2 . ^1H 2D DOSY NMR spectroscopy was also found to be a useful technique to characterize multiporphyrinic compounds with different sizes and shapes, leading thus to different diffusion coefficients. ^1H 2D DOSY NMR spectra of $[\text{NiAuPh}]$ (blue), Ni_2 (green), and Ni_3 (pink) are superimposed in Figure 4. For each compound, the porphyrin and acetylide moieties were found to diffuse simultaneously as expected for fragments

Figure 3. Scope of the studied reaction and corresponding yields.

Figure 4. Superimposed ^1H 2D DOSY NMR spectra of $[\text{NiAuPh}]$, Ni_2 , Ni_3 measured in CD_2Cl_2 at 400 MHz and 298 K. Blue spectrum is the one of $[\text{NiAuPh}]$.

belonging to the same molecular species. Moreover, the three complexes did not diffuse at the same rate. The smallest dinuclear complex $[\text{NiAuPh}]$ has the highest diffusion coefficient ($D = 5.88 \times 10^{-10} \text{ m}^2\text{s}^{-1}$ in CD_2Cl_2 at 298 K). Tetranuclear and hexanuclear complexes Ni_2 and Ni_3 have lower diffusion coefficients ($D = 3.96 \times 10^{-10}$ and $2.95 \times 10^{-10} \text{ m}^2\text{s}^{-1}$ in CD_2Cl_2 at 298 K, respectively for Ni_2 and Ni_3). The analogous complex Zn_3 , with zinc(II) in place of nickel(II), was also synthesized and fully characterized (see Electronic Supplementary Information) in view of using it as a reference compound when characterizing MCOPs based on porphyrin fused to Janus bis-(NHC)-gold complexes. All spectroscopic data obtained for hexanuclear Zn_3 are in agreement with the proposed structure and its diffusion coefficient measured by ^1H 2D DOSY NMR spectroscopy is close to the one measured for Ni_3 ($D = 2.80 \times 10^{-10} \text{ m}^2\text{s}^{-1}$ in CD_2Cl_2 at 298 K).

Finally, the trinuclear complex $[\text{Ni}(\text{AuPh})_2]$ with two opposed phenylacetylide ligands was obtained in 80% yield by reacting two equivalents of phenylacetylene with one equivalent of trinuclear complex $[\text{Ni}(\text{AuCl})_2]$ in basic conditions. The parent ion peak was found at $m/z = 1626.5 \text{ Da}$ (m/z calc. for $\text{C}_{82}\text{H}_{80}\text{Au}_2\text{N}_8\text{Ni}$ 1628.5 Da $[\text{M}]^{+}$) by MALDI-TOF(+) MS. The presence of the alkynyl moieties was confirmed by ^1H NMR spectroscopy with the signals of the *sp* carbon atoms at $\delta = 125.9$ and 104.9 ppm . The two equivalent C_{NHC} were observed at $\delta = 199.4 \text{ ppm}$ by $^{13}\text{C}\{^1\text{H}\}$ NMR spectroscopy.

Synthesis, characterization and properties of main-chain organometallic polymers (MCOPs).

The data obtained in course of this study suggest that Janus bis(NHCs)-gold(I) complexes $[\text{Ni}(\text{AuCl})_2]$ and $[\text{Zn}(\text{AuCl})_2]$ combined to polyacetylides are suitable building blocks for the synthesis of MCOPs incorporating $\text{C}_{\text{NHC}}\text{-Au-C}_{\text{acetylide}}$ bonds. Indeed, MCOPs Ni_{mat} and Zn_{mat} were synthesized by using the slightly modified conditions developed by Peris *et al* (Scheme 3).³³ The reaction of 1 equivalent of trinuclear complex $[\text{M}(\text{AuCl})_2]$ ($\text{M} = \text{Ni}$ or Zn) with 1.5 equivalent of a trisalkynyl scaffold, namely, 1,3,5-tri(4-ethynylphenyl)benzene⁶ in basic conditions (NaOH in a THF/MeOH mixture at 50°C) afforded insoluble materials in 74% and 83% yield for Ni_{mat} and Zn_{mat} ,

Scheme 3. Synthesis of Main-Chain Microporous Organometallic Polymers Ni_{mat} and Zn_{mat}

respectively. Both materials were fully characterized, as described below for Zn_{mat} (data for Ni_{mat} can be found in Electronic Supplementary Information). The solid material Zn_{mat} showed an amorphous character because no X-Ray diffraction peaks were observed on the X-Ray powder patterns recorded at wide and small angles.³³ Thermal stability of Zn_{mat} was evaluated by thermogravimetric analysis (TGA), showing that Zn_{mat} is stable at least up to 300°C with a degradation point starting at 320°C (Figure 5b). The high thermal stability is due to the porphyrins which are known to be thermally-stable at elevated temperatures.⁵⁰ Chemical composition of Zn_{mat} was determined by elemental analysis and the obtained data C 58.60, H 4.89 N 6.20 are globally in good agreement with the expected values calculated for the MCOP $(\text{C}_{129}\text{H}_{117}\text{Au}_3\text{N}_{12}\text{Zn}_{1.5})_n$

Figure 5. a) Solid state UV-Vis absorption spectrum of Zn_{mat} ; b) Thermogravimetric analysis (TGA) of Zn_{mat} ; c) Energy Dispersive X-Ray analysis (EDX) mapping of Zn_{mat} red: carbon; yellow: nitrogen; blue: zinc; purple: gold.

(C 61.42, H 4.68, N 6.66). To support these data, we also performed elemental mapping by means of energy dispersive X-ray diffraction analysis (EDX). As can be seen in Figure 5c, the elemental mapping confirmed the homogenous distribution of C, N, Zn and Au elements among the sample. Moreover, EDX spectroscopy analysis also allows the determination of elements ratios within the sample. We thus found an Au/Zn ratio of ~1:2, which is in good agreement with the proposed structure of **Zn_{mat}**.

The structure of **Zn_{mat}** at the molecular level was elucidated by combining infrared (IR) spectroscopy and ¹³C solid state NMR spectroscopy. The IR spectrum of **Zn_{mat}** displayed the C≡C stretching frequency at $\nu = 2104\text{ cm}^{-1}$ confirming the presence of C≡C bonds. ¹³C solid state NMR was used to confirm the formation of C_{NHC}-Au bonds (Figure 6). Here, the hexanuclear complex **Zn₃** (described above) was used as a reference compound because (i) it contains similar connections and ligands; (ii) it had been fully characterized in solution. On the ¹³C solution NMR spectrum of **Zn₃**, the signal of the C_{NHC} appears at $\delta = 199.4\text{ ppm}$. Similarly, the signal of the C_{NHC} is clearly visible at $\delta \sim 200\text{ ppm}$ on the ¹³C CP MAS (Cross-Polarization magic Angle Spinning) NMR spectrum. Such a chemical shift $\delta \sim 200\text{ ppm}$ is also observable on the ¹³C CP MAS NMR spectrum of **Zn_{mat}**, confirming the presence of C_{NHC}-Au-C≡C bonds. Moreover, the ¹³C CP MAS NMR spectrum of **Zn_{mat}** also displays the characteristic signal of the Au-C≡C carbon at $\delta \sim 105\text{ ppm}$.^{44–46} The similarities between the ¹³C CP MAS NMR spectra of **Zn_{mat}** and the corresponding model compound **Zn₃** strongly suggest the formation of an insoluble MCOP with porphyrins and acetylides connected by C_{NHC}-Au-C_{acetylide} bonds.

Figure 6. a) ¹³C{¹H} solution NMR spectrum of **Zn₃** in CD₂Cl₂ (recorded on a 500 MHz NMR instrument at 298K); b) ¹³C CP MAS NMR spectrum of **Zn₃** (recorded with a contact time of 6 ms, on a 600 MHz NMR instrument, and spinning at 25 kHz) and c) ¹³C CP MAS NMR spectrum of **Zn_{mat}** (recorded with a contact time of 6 ms, on a 600 MHz NMR instrument, and spinning at 25 kHz).

Then, we evaluated if such MCOPs incorporating zinc(II) porphyrins could be of interest for heterogeneous photocatalysis. Indeed, porphyrins are well known photosensitizers, which can reach the triplet excited state after photoexcitation and intersystem crossing from the singlet excited state.^{51,52} Singlet oxygen (¹O₂) is produced from this triplet excited state by triplet-triplet energy transfer with triplet

oxygen (³O₂).⁵³ Because it is a very strong oxidative agent, ¹O₂ is able to oxidize a great number of surrounding molecules. Consequently, porphyrins can be used to design photoactive materials for photocatalysis, biomedicine or water remediation.^{52,52} Moreover, the presence of a gold(I) atom at the porphyrin periphery could enhance the ¹O₂ production yield by a *heavy atom effect*.^{54–56}

To probe if **Zn_{mat}** could be used as a heterogeneous photocatalyst, we first performed solid state UV-Vis absorption spectrophotometry analyses to see if this MCOP is able to absorb light in the visible region. Satisfyingly, the solid UV-Vis spectrum of **Zn_{mat}** shows a strong absorbance of the MCOP ranging from ~300–700 nm (Figure 5a), an important prerequisite for applications in photocatalysis. Other important issues for developing heterogeneous photocatalysts are the surface area and the porosity of the solid materials. Therefore, a nitrogen (N₂) sorption analysis at 77 K was performed to analyse the surface area and porosity of **Zn_{mat}**. The surface area was found to be ~274 m².g⁻¹ using the Brunauer, Emmett and Teller (BET) equation, in agreement with other MCOPs reported in the literature.³³ A large hysteresis loop associated with a steep N₂ uptake at low relative pressure ($P/P^0 < 0.01$) seems to indicate the presence of micropores according to IUPAC's definitions (see the Electronic Supplementary Information, Figure S49).⁵⁷ However, the average pore-size was evaluated at ~3.1 nm, indicating the presence of both micro- and mesopores in **Zn_{mat}**.^{20,31,58}

Preliminary tests were performed to see if **Zn_{mat}** is able to generate ¹O₂ upon irradiation with visible light. To this aim, 1,3-diphenylisobenzofuran (DPBF, $\lambda_{\text{max}} = 416\text{ nm}$) was used as ¹O₂ quencher, because they react together through a [4+2] cycloaddition leading to the formation of the colourless *o*-dibenzoylbenzene. This reaction can be easily monitored by UV-Vis absorption spectroscopy by measuring the decrease in DPBF

Figure 7. a) Chemical oxidation of DPBF with ¹O₂; b) Evolution of the DPBF absorbance from 0 to 35 minutes under irradiation and in the presence of **Zn_{mat}**; c) Plot of $\ln(A_0/A) = f(t)$ of DPBF alone (black triangles) and DPBF in presence of 3 mol% **Zn_{mat}** (purple squares).

concentration at 415 nm. A DBPF solution in toluene, containing 3 mol% of insoluble and manually ground **Zn_{mat}** was irradiated with a halogen lamp for 35 min. The irradiation undoubtedly caused a time dependent decrease of DPBF concentration (Figure 7a). Plots of $\ln(A_0/A)$ vs. time represented in Figure 7b confirm the first order kinetics of this photooxidation process. A $k^{\text{eff}}/k^{\text{obs}}$ ratio of 5 was found (where k^{eff} and k^{obs} correspond to apparent kinetic constants in presence and absence of **Zn_{mat}**, respectively), showing that the presence of the heterogeneous photocatalyst **Zn_{mat}** significantly accelerates the DPBF oxidation. Interestingly, no significant porphyrin leaching could be observed in toluene after irradiation since no absorption bands belonging to free porphyrin species could be detected after 35 minutes of reaction (Figure 7a). The heterogeneous MCOP **Zn_{mat}** could be recovered by filtration and reused as photocatalyst without any loss of activity. Complementary kinetic and spectroscopic studies will nevertheless be needed to fully assess the recyclability of these heterogeneous MCOPs.

Conclusion

Janus bis(NHCs) ligands with a porphyrin core and two linearly NHC heads fused to two opposite pyrroles were used for the preparation of molecular trinuclear metal complexes (one metal in the porphyrin core and the two others anchored onto the peripheral NHCs). We notably prepared nickel(II) and zinc(II) porphyrins with two peripheral NHC gold(I) chloride complexes. We also investigated the substitution of chloride ligands by acetylides, allowing the preparation of molecular species containing several porphyrins and metal ions without any complex purification procedures. A representative example is the hexanuclear complex **Zn₃** containing three zinc(II) porphyrins and three gold(I) complexes. With these building blocks in hand, we performed the synthesis of heterogeneous main-chain organometallic polymers where metalloporphyrins and polyacetylides are connected through the formation of C_{NHC}-Au-C_{acetylide} bonds. One of these materials, namely **Zn_{mat}**, was used as heterogeneous photocatalyst for the production of ¹O₂ upon irradiation with visible light. These heterogeneous porous materials appear as promising candidates for different applications like water remediation, for example.

Conflicts of interest

There are no conflicts to declare

Acknowledgements

We warmly thank Dr. Simon Pascal for kind proofreading, as well as Dr. Angel Escamilla-Perez, Dr. Clarence Charnay and Dr. Bertrand Rebière for their help in performing BET, UV-Vis and EDX analyses, respectively.

Experimental Section

Materials and methods

Reactions were performed under argon using oven-dried glassware and Schlenk techniques. Gold complex [AuCl(tht)] was prepared with the procedure described in reference.³⁸ Acetone (CHROMASOLV®, for HPLC, ≥99.9%) was purchased from Sigma-Aldrich®. Dry THF and CH₂Cl₂ were obtained by a solvent purification system PureSolve MD5 from Innovative Technology. Preparative purifications were performed by silica gel flash column chromatography (Merck® 40-60 μm). Technical grade solvents were used as eluents in the chromatography and crystallization purifications. ¹H, ¹³C{¹H} as well as ¹H DOSY NMR experiments were recorded on a Bruker Avance III HD 400 MHz spectrometer equipped with BBI probe or on a Bruker Avance III 500 MHz spectrometer equipped with Helium BBO Cryoprobe. ¹H and ¹³C{¹H} NMR spectra were calibrated to TMS on the basis of the relative chemical shift of the solvent used as an internal standard. Abbreviations used for ¹H NMR spectra are as follows: s singlet, d doublet. Solid state NMR experiments were performed at 14.1 T using a VNMRs-600 MHz instrument equipped with a Varian T3 HXY 1.6mm triple resonance probe, spinning at 25 kHz. ¹H-¹³C CPMAS (Cross Polarization Magic Angle Spinning) NMR experiments were performed using a 2.5 μs ¹H excitation pulse, followed by a 6.0 ms contact time, and applying spinal-64 ¹H decoupling during acquisition. The recycle delay was set to 0.8 s, and the number of transients acquired ranged from 4100 to 17110, depending on the sample. ¹³C chemical shifts were referenced externally to adamantane (high-frequency ¹³C shift at 38.5 ppm). UV-Vis absorption spectra in solution were recorded in CH₂Cl₂ with a JASCO V-750 UV-Visible-NIR spectrophotometer in quartz cells of 10 mm (Hellma). UV-Vis absorption spectra in the solid state were recorded using a 60 mm integrating sphere. High-resolution mass spectra (HRMS) were recorded on ESI-TOF Q instruments in positive mode or on a MALDI-TOF spectrometer in positive mode using dithranol as a matrix.

Synthetic procedures

Synthesis of porphyrin Ni-I₂. Porphyrin **Ni-Imi₂** (120 mg, 1.2 × 10⁻⁴ mol, 1 equiv.) was dissolved in 20 mL of DMF. Then, K₂CO₃ (0.034 mg, 2.4 × 10⁻⁴ mol, 2 equiv.) and MeI (10 mL, large excess) were added. The solution was stirred at room temperature for 48h. Afterwards, DMF was removed under reduced pressure, and the crude product was purified by silica gel chromatography (SiO₂; eluent from CH₂Cl₂ to CH₂Cl₂/MeOH 95:5). Crystallization from CH₂Cl₂/*n*-Hexane afforded **Ni-I₂** as red needles in 95% yield (146 mg). ¹H NMR (400 MHz, CD₂Cl₂): δ 10.79 (s, 2H, H_{imidazolium}), 8.60 (s, 4H, H_{pyrr}), 8.13 (d, 8H, H_{Ar meso}, ³J_{H-H} = 8.3 Hz), 7.80 (d, 8H, H_{Ar meso}, ³J_{H-H} = 8.3 Hz), 3.20 (s, 12H, H_{NMe}), 1.56 (s, 36H, H_{tBu}) ppm. ¹³C{¹H} NMR (125.7 MHz, CD₂Cl₂): δ 154.3, 147.0, 145.1, 139.0, 136.8, 135.5, 133.8, 128.6, 126.2, 118.9, 36.3, 35.5, 31.6 ppm. **UV Vis** (CH₂Cl₂): λ_{max} (log ε) = 422 (5.4), 540 (4.2), 574 (3.8 L. mol⁻¹. cm⁻¹) nm. **MS** (ESI-TOF⁺): *m/z* calcd for C₆₆H₇₀N₈Ni [M-2]²⁺ 516.3, found 516.3.

Synthesis of porphyrin Zn-I₂. Porphyrin **Ni-Imi₂** (150 mg, 1.5 × 10⁻⁴ mol, 1 equiv.) was dissolved in a H₂SO₄/TFA mixture (3:10

mL) and stirred at room temperature. The mixture turned green. After 30 minutes, CHCl_3 (100 mL) was added. Then, the mixture was poured on ice and neutralized with K_2CO_3 until the reaction mixture turned purple. Afterwards, the organic layer was washed three times with water and dried over MgSO_4 . The solvent was then evaporated and the residue was dissolved in a $\text{CHCl}_3/\text{MeOH}$ mixture (30:5 mL) and $\text{Zn}(\text{OAc})_2 \cdot 2\text{H}_2\text{O}$ (50 mg, 2.3×10^{-4} mol, 1.5 equiv.) was added. The latter mixture was heated at 45°C for 1 hour. Once the metalation was complete, the solvents were evaporated and the crude product was purified by silica gel chromatography (SiO_2 ; eluent from CHCl_3 to $\text{CHCl}_3/\text{acetone}$ 97:3). Crystallization from CHCl_3/n -hexane afforded **Zn-Imi₂** as a purple powder in 65% yield (98 mg). This compound was directly engaged in the methylation process by dissolving it in a $\text{CHCl}_3/\text{acetone}$ mixture (1:1, 15 mL) with iodomethane (5 mL, large excess) and K_2CO_3 (27 mg, 2.0×10^{-4} mol, 2 equiv.). This reaction was stirred at room temperature for 48 hours. Then, solvents were evaporated and the crude product was purified by silica gel chromatography (SiO_2 ; eluent from CHCl_3 to $\text{CHCl}_3/\text{acetone}$ 3:7). Crystallization from CHCl_3/n -hexane afforded **Zn-I₂** as a green powder in 34% yield (44 mg). **¹H NMR** (500 MHz, CDCl_3 , 298 K): δ 10.05 (s, 2H, $\text{H}_{\text{imidazolium}}$), 8.34 (s, 4H, H_{pyrr}), 8.15 (bs, 8H, $\text{H}_{\text{Ar meso}}$), 7.77 (s, 8H, $\text{H}_{\text{Ar meso}}$), 2.83 (s, 12H, H_{NMe}), 1.56 (s, 36H, H_{tBu}) ppm. **¹³C{¹H} NMR** (125.7 MHz, CDCl_3 , 298 K): δ 152.2, 150.0, 143.1, 140.5, 139.7, 136.7, 132.3, 132.0, 124.8, 118.5, 35.2, 35.1, 31.8 ppm. **UV/Vis** (CHCl_3): λ_{max} (log ϵ) = 449 (5.2), 585 (3.9), 633 (3.8 L mol⁻¹ cm⁻¹) nm. **MS** (ESI-TOF⁺): m/z calcd for $\text{C}_{66}\text{H}_{70}\text{N}_8\text{Zn}$ 519.3 [M-2I]²⁺, found 519.3.

Synthesis of complex [NiAuPh]. A solution of phenylacetylene (4.9×10^{-3} M) was prepared in THF. Then, 3.8 mL (1.8×10^{-5} mol, 1.1 equiv.) of the later solution were added to a Schlenk tube containing porphyrin [**NiAuCl**] (20 mg, 1.7×10^{-5} mol, 1 equiv.). After a final addition of a 0.25 M KOH solution in MeOH (80 μL , 2.0×10^{-5} , 1.1 equiv.), the reaction mixture was stirred at room temperature. After 24h, the solvent was evaporated. Crystallization from $\text{CH}_2\text{Cl}_2/\text{MeOH}$ afforded [**NiAuPh**] in 66% yield as a red powder (14 mg). **¹H NMR** (400 MHz, CD_2Cl_2): δ 8.71 (s, 2H, H_{pyrr}), 8.69 (d, 2H, H_{pyrr} , $^3J_{\text{H-H}} = 5$ Hz), 8.67 (d, 2H, H_{pyrr} , $^3J_{\text{H-H}} = 5$ Hz), 8.07 (d, 4H, $\text{H}_{\text{Ar meso}}$, $^3J_{\text{H-H}} = 8.3$ Hz), 7.97 (d, 4H, $\text{H}_{\text{Ar meso}}$, $^3J_{\text{H-H}} = 8.3$ Hz), 7.79 (d, 4H, $\text{H}_{\text{Ar meso}}$, $^3J_{\text{H-H}} = 8.3$ Hz), 7.75 (d, 4H, $\text{H}_{\text{Ar meso}}$, $^3J_{\text{H-H}} = 8.3$ Hz), 7.35 (m, 2H, H_{Ph}), 7.26-7.13 (m, 3H, H_{Ph}), 3.18 (s, 6H, H_{NMe}), 1.56 (s, 18H, H_{tBu}), 1.54 (s, 18H, H_{tBu}) ppm. **¹³C{¹H} NMR** (125.7 MHz, CD_2Cl_2): δ 198.7 (C_{NHC}), 153.3, 151.7, 145.2, 144.3, 143.7, 141.3, 138.3, 137.7, 135.7, 134.4, 132.9, 132.7, 132.5, 132.4, 130.6, 128.5, 127.8, 126.7, 126.7, 125.6, 124.7, 121.0, 116.7, 105.0, 37.9, 35.5, 35.3, 31.9, 31.8 ppm. **IR** (FT-ATR): $\nu_{\text{C=C}} = 2109$ cm⁻¹. **UV Vis** (CH_2Cl_2): λ_{max} (log ϵ) = 228 (4.8), 280 (4.9), 426 (5.3), 537 (4.3), 571 s (3.9 L mol⁻¹ cm⁻¹) nm. **HR-MS** (ESI-TOF⁺): m/z calcd for $\text{C}_{71}\text{H}_{69}\text{AuN}_6\text{Ni}$ [M]⁺⁺ 1260.4603, found 1260.4597.

Synthesis of complex Ni₂. A solution of 1,4-diethynylbenzene (2.6×10^{-3} M) was prepared in THF. Then, 4.3 mL (1.12×10^{-5} mol, 0.45 equiv.) of the later solution were added to a Schlenk tube containing porphyrin [**NiAuCl**] (30 mg, 2.5×10^{-5} mol, 1 equiv.). After a final addition of a 0.25 M KOH solution in MeOH (224 μL , 5.6×10^{-5} mol, 5 equiv.), the reaction mixture was stirred at room temperature. After 48h the solvent was

evaporated. Crystallization from $\text{CH}_2\text{Cl}_2/\text{MeOH}$ afforded **Ni₂** in 95% yield as a red powder (26.1 mg). **¹H NMR** (400 MHz, CD_2Cl_2): δ 8.71 (s, 4H, H_{pyrr}), 8.69 (d, 4H, H_{pyrr} , $^3J_{\text{H-H}} = 5$ Hz), 8.67 (d, 4H, H_{pyrr} , $^3J_{\text{H-H}} = 5$ Hz), 8.08 (d, 8H, $\text{H}_{\text{Ar meso}}$, $^3J_{\text{H-H}} = 8.3$ Hz), 7.97 (d, 8H, $\text{H}_{\text{Ar meso}}$, $^3J_{\text{H-H}} = 8.3$ Hz), 7.79 (d, 8H, $\text{H}_{\text{Ar meso}}$, $^3J_{\text{H-H}} = 8.3$ Hz), 7.75 (d, 8H, $\text{H}_{\text{Ar meso}}$, $^3J_{\text{H-H}} = 8.3$ Hz), 7.21 (s, 4H, H_{Ph}), 3.18 (s, 12H, H_{NMe}), 1.56 (s, 36H, H_{tBu}), 1.55 (s, 36H, H_{tBu}) ppm. **¹³C{¹H} NMR** (125.7 MHz, CD_2Cl_2): δ 198.6 (C_{NHC}), 153.3, 151.7, 145.2, 144.3, 143.7, 141.3, 138.3, 137.6, 135.7, 134.4, 132.9, 132.7, 132.5, 132.0, 127.8, 125.7, 124.7, 124.4, 120.9, 116.7, 37.9, 35.5, 35.3, 31.9, 31.8 ppm. **IR** (FT-ATR): $\nu_{\text{C=C}} = 2109$ cm⁻¹. **UV Vis** (CH_2Cl_2): λ_{max} (log ϵ) = 311 (4.8), 328 (4.9), 426 (5.5), 537 (4.5), 572 s (4 L mol⁻¹ cm⁻¹) nm. **MS** (MALDI-TOF⁺): m/z calcd for $\text{C}_{136}\text{H}_{132}\text{Au}_2\text{N}_{12}\text{Ni}_2$ [M]⁺⁺ 2242.8736, found 2242.8.

Synthesis of complex Ni₃. A solution of 1,3,5-tri(4-ethynylphenyl)benzene (1.8×10^{-3} M) was prepared in THF. Then, 4.3 mL (2.6×10^{-5} mol, 0.3 equiv.) of the later solution were added to a Schlenk tube containing porphyrin [**NiAuCl**] (30 mg, 2.5×10^{-5} mol, 1 equiv.). After a final addition of a 0.25 M KOH solution in MeOH (188 μL , 4.5×10^{-5} mol, 2 equiv.), the reaction mixture was stirred at room temperature. After 72h a red precipitate appeared. The title compound was isolated after addition of fresh THF (3-5 mL), followed by vacuum filtration in 75 % yield as a red powder (22.6 mg). **¹H NMR** (400 MHz, CD_2Cl_2): δ 8.71 (s, 6H, H_{pyrr}), 8.70 (d, 6H, H_{pyrr} , $^3J_{\text{H-H}} = 5$ Hz), 8.68 (d, 6H, H_{pyrr} , $^3J_{\text{H-H}} = 5$ Hz), 8.10 (d, 12H, $\text{H}_{\text{Ar meso}}$, $^3J_{\text{H-H}} = 8.3$ Hz), 7.97 (d, 12H, $\text{H}_{\text{Ar meso}}$, $^3J_{\text{H-H}} = 8.3$ Hz), 7.81 (d, 12H, $\text{H}_{\text{Ar meso}}$, $^3J_{\text{H-H}} = 8.3$ Hz), 7.76 (s, 3H, H_{Ph}), 7.75 (d, 12H, $\text{H}_{\text{Ar meso}}$, $^3J_{\text{H-H}} = 8.3$ Hz), 7.60 (d, 6H, H_{Ph} , $^3J_{\text{H-H}} = 8.3$ Hz), 7.46 (d, 6H, H_{Ph} , $^3J_{\text{H-H}} = 8.3$ Hz), 3.22 (s, 18H, H_{NMe}), 1.56 (s, 108H, H_{tBu}) ppm. **¹³C{¹H} NMR** (125.7 MHz, CD_2Cl_2): δ 198.8 (C_{NHC}), 153.5, 151.6, 145.2, 144.3, 143.7, 143.5, 142.3, 141.7, 141.3, 139.2(2C), 138.4, 137.6, 135.7, 134.4, 132.8, 132.7, 132.5, 127.8, 127.4, 126, 125.7, 124.7, 123.9, 120.9, 116.7, 38, 35.5, 35.3, 31.9(2C) ppm. **IR** (FT-ATR): $\nu_{\text{C=C}} = 2109$ cm⁻¹. **UV Vis** (CH_2Cl_2): λ_{max} (log ϵ) = 316 (5.1), 425 (5.7), 537 (4.7), 572 s, (4.3 L mol⁻¹ cm⁻¹) nm. **MS** (MALDI-TOF⁺): m/z calcd for $\text{C}_{219}\text{H}_{208}\text{Au}_3\text{N}_{18}\text{Ni}_3$ [M+H]⁺ 3854.3886, found 3854.4.

Synthesis of complex Zn₃. A solution of 1,3,5-tris(4-ethynylphenyl)benzene (1.8×10^{-3} M) was prepared in THF. Then, 4.3 mL (2.6×10^{-5} mol, 0.3 equiv.) of the later solution were added to a Schlenk tube containing porphyrin [**ZnAuCl**] (30 mg, 2.5×10^{-5} mol, 1 equiv.). After a final addition of a 0.25 M KOH solution in MeOH (300 μL , 7.5×10^{-5} mol, 3 equiv.), the reaction mixture was stirred at room temperature. After 72h, a dark purple precipitate appeared. After filtration, the solid was redispersed in fresh MeOH (10 mL) and submitted to ultrasounds for 10 min. The title compound was isolated after vacuum filtration in 85 % yield as a purple powder (27.6 mg). **¹H NMR** (400 MHz, CD_2Cl_2): δ 8.96 (d, 6H, H_{pyrr} , $^3J_{\text{H-H}} = 5$ Hz), 8.95 (s, 6H, H_{pyrr}), 8.90 (d, 6H, H_{pyrr} , $^3J_{\text{H-H}} = 5$ Hz), 8.21 (d, 12H, $\text{H}_{\text{Ar meso}}$, $^3J_{\text{H-H}} = 8.3$ Hz), 8.17 (d, 12H, $\text{H}_{\text{Ar meso}}$, $^3J_{\text{H-H}} = 8.3$ Hz), 7.82 (s, 3H, H_{Ph}), 7.81 (d, 12H, $\text{H}_{\text{Ar meso}}$, $^3J_{\text{H-H}} = 8.3$ Hz), 7.76 (d, 12H, $\text{H}_{\text{Ar meso}}$, $^3J_{\text{H-H}} = 8.3$ Hz), 7.65 (d, 6H, H_{Ph} , $^3J_{\text{H-H}} = 8.3$ Hz), 7.48 (d, 6H, H_{Ph} , $^3J_{\text{H-H}} = 8.3$ Hz), 3.22 (s, 18H, H_{NMe}), 1.62 (s, 54H, H_{tBu}), 1.57 (s, 54H, H_{tBu}) ppm. **¹³C{¹H} NMR** (125.7 MHz, CD_2Cl_2): δ 199.4 (C_{NHC}), 152.9, 151.3, 151, 150.3, 142.4, 142.2, 140.7, 140, 139.2,

136.7, 135.1, 133.4, 132.9(2C), 132.7, 132.5, 132.1, 127.4, 126.1, 125, 124.3, 122.9, 118.4, 110.6, 105.1, 38, 35.5, 35.4, 34.7, 32, 31.9 ppm. **IR** (FT-ATR): $\nu_{\text{C}=\text{C}}$ = 2110 cm^{-1} . **UV Vis** (CH_2Cl_2): λ_{max} (log ϵ) = 316 (5.3), 428 (6.2), 556 (4.8), 596 s, (4.3 L. mol^{-1} . cm^{-1}) nm. **MS** (MALDI-TOF⁺): m/z calcd for $\text{C}_{219}\text{H}_{207}\text{Au}_3\text{N}_{18}\text{Zn}_3$ [M]⁺⁺ 3878.2307, found 3878.3.

Synthesis of complex [Ni(AuCl)₂]. A solution of the porphyrin **Ni-I₂** (60 mg, 4.7×10^{-5} mol, 1 equiv.) was prepared in CH_2Cl_2 (8 mL). Then, Ag_2O (21.6 mg, 9.3×10^{-5} mol, 2 equiv.) was added and the reaction mixture was vigorously stirred at room temperature, under an argon atmosphere protected from light. After 6h, [AuCl(tht)] (29 mg, 9.3×10^{-5} mol, 2 equiv.) was added and the mixture was stirred for an additional 12h period under the same conditions. The reaction was monitored by TLC analysis. When the reaction was complete, the solvent was evaporated and the title compound was purified by column chromatography (SiO_2 ; eluent from $\text{CH}_2\text{Cl}_2/n$ -hexane 7:3 to CH_2Cl_2). Crystallization from $\text{CH}_2\text{Cl}_2/\text{MeOH}$ afforded [Ni(AuCl)₂] as red needles in 66% yield (46.3 mg). **¹H NMR** (400 MHz, CD_2Cl_2): δ 8.52 (s, 4H, H_{pyrr}), 8.13 (d, 8H, $\text{H}_{\text{Ar meso}}$, $^3J_{\text{H-H}}$ = 8.3 Hz), 7.85 (d, 8H, $\text{H}_{\text{Ar meso}}$, $^3J_{\text{H-H}}$ = 8.3 Hz), 3.10 (s, 12H, H_{NMe}), 1.55 (s, 36H, H_{tBu}). **¹³C{¹H} NMR** (125.7 MHz, CD_2Cl_2): δ 182.7, 153.6, 146.8, 140.5, 137.5, 135.6, 132.9, 129.5, 125.9, 118.4, 38.0, 35.4, 34.7 ppm. **UV Vis** (CH_2Cl_2): λ_{max} (log ϵ) = 432 (5.4), 542 (4.2), 576 (3.7 L. mol^{-1} . cm^{-1}) nm. **MS** (MALDI-TOF⁺): m/z calcd for $\text{C}_{66}\text{H}_{68}\text{Au}_2\text{Cl}_2\text{N}_8\text{Ni}$ [M]⁺⁺ 1494.36, found [M]⁺⁺ 1494.4.

Synthesis of complex [Ni(AuPh)₂]. A solution of phenylacetylene (4.9×10^{-3} M) was prepared in THF. Then, 10.2 mL (5.0×10^{-5} mol, 2.5 equiv.) of the later solution were added to a Schlenk tube containing [Ni(AuCl)₂] (30 mg, 2.0×10^{-5} mol, 1 equiv.). After the addition of a 0.25 M KOH solution in MeOH (800 μL , 20.0×10^{-5} , 10 equiv.), the reaction mixture was stirred at room temperature. After 24 hours, the solvent was evaporated. Crystallization from $\text{CH}_2\text{Cl}_2/\text{MeOH}$ afforded [Ni(AuPh)₂] in 80% yield as a red powder (26 mg). **¹H NMR** (400 MHz, CD_2Cl_2 , 298 K): δ 8.56 (s, 4H, H_{pyrr}), 8.14 (d, 8H, $\text{H}_{\text{Ar meso}}$, $^3J_{\text{H-H}}$ = 8.3 Hz), 7.86 (d, 8H, $\text{H}_{\text{Ar meso}}$, $^3J_{\text{H-H}}$ = 8.3 Hz), 7.33 (m, 4H, H_{Ph}), 7.26–7.10 (m, 6H, H_{Ph}), 3.14 (s, 12H, H_{NMe}), 1.55 (s, 36H, H_{tBu}) ppm. **¹³C{¹H} NMR** (125.7 MHz, CD_2Cl_2 , 298 K): δ 198.4 (NHC), 153.4, 146.6, 141.0, 137.7, 135.6, 132.8, 132.2, 130.4, 129.6, 128.4, 126.6, 125.9, 118.3, 104.9, 37.6, 35.4, 31.7 ppm. **UV Vis** (CH_2Cl_2): λ_{max} (log ϵ) = 435 (5.5), 544 (4.4), 584 (4.0 L. mol^{-1} cm^{-1}) nm. **IR** (FT-ATR): $\nu_{\text{C}=\text{C}}$ = 2115 cm^{-1} . **MS** (MALDI-TOF⁺): m/z calcd for $\text{C}_{82}\text{H}_{80}\text{Au}_2\text{N}_8\text{Ni}$ 1628.5 [M]⁺⁺, found 1626.5.

Synthesis of complex [Zn(AuCl)₂]. A solution of the porphyrin **Zn-I₂** (45 mg, 3.9×10^{-5} mol, 1 equiv.) was prepared in a $\text{CH}_2\text{Cl}_2/\text{CHCl}_3$ mixture (10/5 mL). Then, Ag_2O (18 mg, 7.7×10^{-5} mol, 2 equiv.) was added, and the reaction mixture was vigorously stirred at room temperature under an argon atmosphere protected from light. After 6 hours, [AuCl(tht)] (25 mg, 7.7×10^{-5} mol, 2 equiv.) was added and the mixture was stirred for 12 hours under the same conditions. The reaction was monitored by silica gel TLC analysis. When the reaction was complete, the solvent was evaporated and the title compound was purified by column chromatography (SiO_2 ; eluent CHCl_3). Crystallization from CHCl_3/n -hexane afforded [Zn(AuCl)₂] as a green powder in 85% yield (49 mg). **¹H NMR** (500 MHz, CD_2Cl_2 ,

298 K): δ 8.61 (s, 4H, H_{pyrr}), 8.28 (d, 8H, $\text{H}_{\text{Ar meso}}$, $^3J_{\text{H-H}}$ = 8.3 Hz), 7.85 (d, 8H, $\text{H}_{\text{Ar meso}}$, $^3J_{\text{H-H}}$ = 8.3 Hz), 3.04 (s, 12H, H_{NMe}), 1.61 (s, 36H, H_{tBu}). **¹³C{¹H} NMR** (125.7 MHz, CD_2Cl_2 , 298 K): δ 182.0 (C_{NHC}), 152.8, 150.8, 141.3, 140.1, 136.5, 132.8, 132.4, 125.0, 118.9, 37.7, 35.3, 31.8 ppm. **UV/vis** (CHCl_3): λ_{max} (log ϵ) = 444 (5.1), 574 (3.7), 622 (3.5 L. mol^{-1} cm^{-1}) nm. **MS** (MALDI-TOF⁺): m/z calcd for $\text{C}_{66}\text{H}_{68}\text{Au}_2\text{Cl}_2\text{N}_8\text{Zn}$ [M]⁺⁺ 1500.35, found 1500.3 [M]⁺⁺.

Synthesis of material Ni_{mat}. A solution of 1,3,5-tris(4-ethynylphenyl)benzene (1.8×10^{-3} M) was prepared in THF. Then, 7.5 mL (1.3×10^{-5} mol, 1 equiv.) of the later solution were added to a Schlenk tube containing [Ni(AuCl)₂] (30 mg, 2.0×10^{-5} mol, 1.5 equiv.). After the addition of a 0.25 M KOH solution in MeOH (800 μL , 2.0×10^{-4} mol, 15 equiv.), the reaction mixture was stirred for 6 hours at 50°C and a red precipitate appeared. The title compound was isolated by vacuum filtration in 74 % yield as a red powder (25 mg). **Elem. Anal.** calc (%) for $(\text{C}_{129}\text{H}_{117}\text{Au}_3\text{N}_{12}\text{Ni}_{1.5})_n$: C 61.64, H 4.70, N 6.68, found C 60.3, H 4.75, N 6.35. **IR (ATR)**: $\nu_{\text{C}=\text{C}}$ = 2100 cm^{-1} .

Synthesis of material Zn_{mat}. A solution of 1,3,5-tris(4-ethynylphenyl)benzene (1.8×10^{-3} M) was prepared in THF. Then, 7.5 mL (1.3×10^{-5} mol, 1 equiv.) of the later solution were added to a Schlenk tube containing the [Zn(AuCl)₂] porphyrin (30 mg, 2.0×10^{-5} mol, 1.5 equiv.). After the addition of a 0.25 M KOH solution in MeOH (800 μL , 2.0×10^{-4} mol, 15 equiv.), the reaction mixture was stirred for 4 hours at 50°C and a dark purple precipitate appeared. The title compound was isolated by vacuum filtration in 83 % yield as a red powder (28 mg). **Elem. Anal.** calc (%) for $(\text{C}_{129}\text{H}_{117}\text{Au}_3\text{N}_{12}\text{Zn}_{1.5})_n$: C 61.42, H 4.68, N 6.66, found C 58.60, H 4.89, N 6.80. **IR (ATR)**: $\nu_{\text{C}=\text{C}}$ = 2104 cm^{-1} .

Oxidation procedure. A DPBF solution (6×10^{-4} M) was prepared in toluene (200 mL). Then, 3 mg of manually ground **Zn_{mat}** material (3 mol.% of porphyrins) were added. Afterwards, the mixture was vigorously stirred and irradiated (halogen lamp, 500W) for 35 min. Aliquots were analysed using UV-Vis absorption spectroscopy (1 mm quartz cells) every 30 s, 1 min, 3 min or 5 min.

Notes and references

- 1 P. de Frémont, N. Marion and S. P. Nolan, *Coord. Chem. Rev.*, 2009, **253**, 862–892.
- 2 M. N. Hopkinson, C. Richter, M. Schedler and F. Glorius, *Nature*, 2014, **510**, 485–496.
- 3 L. Cavallo, A. Correa, C. Costabile and H. Jacobsen, *J. Organomet. Chem.*, 2005, **690**, 5407–5413.
- 4 C. M. Crudden and D. P. Allen, *Coord. Chem. Rev.*, 2004, **248**, 2247–2273.
- 5 H. Jacobsen, A. Correa, A. Poater, C. Costabile and L. Cavallo, *Coord. Chem. Rev.*, 2009, **253**, 687–703.
- 6 F. E. Hahn, *Chem. Rev.*, 2018, **118**, 9455–9456.
- 7 A. T. Biju, *N-Heterocyclic Carbenes in Organocatalysis*, John Wiley & Sons, 2019.
- 8 W. A. Herrmann and C. Köcher, *Angew. Chem. Int. Ed. Engl.*, 1997, **36**, 2162–2187.
- 9 C. A. Smith, M. R. Narouz, P. A. Lummis, I. Singh, A. Nazemi, C.-H. Li and C. M. Crudden, *Chem. Rev.*, 2019, **119**, 4986–5056.
- 10 Q. Xu, W.-L. Duan, Z.-Y. Lei, Z.-B. Zhu and M. Shi, *Tetrahedron*, 2005, **61**, 11225–11229.

- 11 J. A. Mata, M. Poyatos and E. Peris, *Coord. Chem. Rev.*, 2007, **251**, 841–859.
- 12 D. Munz and T. Strassner, *Angew. Chem. Int. Ed.*, 2014, **53**, 2485–2488.
- 13 P. D. W. Boyd, A. J. Edwards, M. G. Gardiner, C. C. Ho, M.-H. Lemée-Cailleau, D. S. McGuinness, A. Riapanitra, J. W. Steed, D. N. Stringer and B. F. Yates, *Angew. Chem. Int. Ed.*, 2010, **49**, 6315–6318.
- 14 C. D. V. Jr, V. M. Lynch and C. W. Bielawski, *Dalton Trans.*, 2009, 7253–7261.
- 15 D. M. Khranov, A. J. Boydston and C. W. Bielawski, *Angew. Chem. Int. Ed.*, 2006, **45**, 6186–6189.
- 16 D. Tapu, Z. McCarty and C. McMillen, *Chem. Commun.*, 2014, **50**, 4725–4728.
- 17 H. Valdés, M. Poyatos and E. Peris, *Organometallics*, 2015, **34**, 1725–1729.
- 18 D. G. Gusev and E. Peris, *Dalton Trans.*, 2013, **42**, 7359–7364.
- 19 J.-Q. Liu, X.-X. Gou and Y.-F. Han, *Chem. – Asian J.*, 2018, **13**, 2257–2276.
- 20 A. A. Danopoulos and P. Braunstein, *Chem. Commun.*, 2014, **50**, 3055–3057.
- 21 M. G. Gardiner and C. C. Ho, *Coord. Chem. Rev.*, 2018, **375**, 373–388.
- 22 S. Gonell, M. Poyatos and E. Peris, *Chem. – Eur. J.*, 2014, **20**, 9716–9724.
- 23 A. Prades, E. Peris and M. Alcarazo, *Organometallics*, 2012, **31**, 4623–4626.
- 24 F. E. Hahn, C. Radloff, T. Pape and A. Hepp, *Organometallics*, 2008, **27**, 6408–6410.
- 25 A. Gutiérrez-Blanco, S. Ibáñez, F. E. Hahn, M. Poyatos and E. Peris, *Organometallics*, 2019, **38**, 4565–4569.
- 26 N. Sinha and F. E. Hahn, *Acc. Chem. Res.*, 2017, **50**, 2167–2184.
- 27 D. Nuevo, M. Poyatos and E. Peris, *Organometallics*, 2018, **37**, 3407–3411.
- 28 R. Visbal and M. C. Gimeno, *Chem. Soc. Rev.*, 2014, **43**, 3551–3574.
- 29 L. Merics and M. Albrecht, *Chem. Soc. Rev.*, 2010, **39**, 1903–1912.
- 30 K. A. Williams, A. J. Boydston and C. W. Bielawski, *Chem. Soc. Rev.*, 2007, **36**, 729–744.
- 31 K. S. Song, D. Kim, K. Polychronopoulou and A. Coskun, *ACS Appl. Mater. Interfaces*, 2016, **8**, 26860–26867.
- 32 C. Zhang, J.-J. Wang, Y. Liu, H. Ma, X.-L. Yang and H.-B. Xu, *Chem. – Eur. J.*, 2013, **19**, 5004–5008.
- 33 S. Gonell, M. Poyatos and E. Peris, *Chem. – Eur. J.*, 2014, **20**, 5746–5751.
- 34 S. Richeter, A. Hadj-Aïssa, C. Taffin, A. van der Lee and D. Leclercq, *Chem. Commun.*, 2007, 2148–2150.
- 35 J.-F. Lefebvre, J.-F. Longevial, K. Molvinger, S. Clément and S. Richeter, *Comptes Rendus Chim.*, 2016, **19**, 94–102.
- 36 J.-F. Lefebvre, M. Lo, D. Leclercq and S. Richeter, *Chem. Commun.*, 2011, **47**, 2976–2978.
- 37 C. Rose, A. Lebrun, S. Clément and S. Richeter, *Chem. Commun.*, 2018, **54**, 9603–9606.
- 38 J.-F. Longevial, A. Langlois, A. Buisson, C. H. Devillers, S. Clément, A. van der Lee, P. D. Harvey and S. Richeter, *Organometallics*, 2016, **35**, 663–672.
- 39 J.-F. Longevial, K. El Cheikh, D. Aggad, A. Lebrun, A. van der Lee, F. Tielens, S. Clément, A. Morère, M. Garcia, M. Gary-Bobo and S. Richeter, *Chem. – Eur. J.*, 2017, **23**, 14017–14026.
- 40 F. Caporaletti, J. Rubio-Magnieto, M. Lo, J.-F. Longevial, C. Rose, S. Clément, A. van der Lee, M. Surin and S. Richeter, *J. Porphyr. Phthalocyanines*, 2019, DOI 10.1142/S1088424619501128.
- 41 M. Lo, J.-F. Lefebvre, D. Leclercq, A. van der Lee and S. Richeter, *Org. Lett.*, 2011, **13**, 3110–3113.
- 42 M. Lo, J.-F. Lefebvre, N. Marcotte, C. Tonnelé, D. Beljonne, R. Lazzaroni, S. Clément and S. Richeter, *Chem. Commun.*, 2012, **48**, 3460–3462.
- 43 M. Brill, A. Collado, D. B. Cordes, A. M. Z. Slawin, M. Vogt, H. Grützmacher and S. P. Nolan, *Organometallics*, 2015, **34**, 263–274.
- 44 P. Hikisz, Ł. Szczupak, A. Koceva-Chyła, A. Guśpiel, L. Oehninger, I. Ott, B. Therrien, J. Solecka and K. Kowalski, *Molecules*, 2015, **20**, 19699–19718.
- 45 J. Arcau, V. Andermark, E. Aguiló, A. Gandioso, A. Moro, M. Cetina, J. C. Lima, K. Rissanen, I. Ott and L. Rodríguez, *Dalton Trans.*, 2014, **43**, 4426–4436.
- 46 V. Andermark, K. Göke, M. Kokoschka, M. A. Abu el Maaty, C. T. Lum, T. Zou, R. W.-Y. Sun, E. Aguiló, L. Oehninger, L. Rodríguez, H. Bunjes, S. Wölfl, C.-M. Che and I. Ott, *J. Inorg. Biochem.*, 2016, **160**, 140–148.
- 47 J. Schur, A. Lüning, A. Klein, R. W. Köster and I. Ott, *Inorganica Chim. Acta*, 2019, **495**, 118982.
- 48 M.-A. MacDonald, R. J. Puddephatt and G. P. A. Yap, *Organometallics*, 2000, **19**, 2194–2199.
- 49 A. M. McDonagh, M. G. Humphrey, M. Samoc, B. Luther-Davies, S. Houbrechts, T. Wada, H. Sasabe and A. Persoons, *J. Am. Chem. Soc.*, 1999, **121**, 1405–1406.
- 50 C. Guan, Liqing Li, D. Chen, Z. Gao and W. Sun, *Thermochim. Acta*, 2004, **413**, 31–38.
- 51 K. Alenezi, A. Tovmasyan, I. Batinic-Haberle and L. T. Benov, *Photodiagnosis Photodyn. Ther.*, 2017, **17**, 154–159.
- 52 J. R. Darwent, P. Douglas, A. Harriman, G. Porter and M.-C. Richoux, *Coord. Chem. Rev.*, 1982, **44**, 83–126.
- 53 J.-F. Longevial, A. Yamaji, D. Aggad, G. Kim, W. X. Chia, T. Nishimura, Y. Miyake, S. Clément, J. Oh, M. Daurat, C. Nguyen, D. Kim, M. Gary-Bobo, S. Richeter and H. Shinokubo, *Chem. Commun.*, 2018, **54**, 13829–13832.
- 54 E. G. Azenha, A. C. Serra, M. Pineiro, M. M. Pereira, J. Seixas de Melo, L. G. Arnaut, S. J. Formosinho and A. M. d'A. Rocha Gonsalves, *Chem. Phys.*, 2002, **280**, 177–190.
- 55 J.-F. Longevial, A. Langlois, A. Buisson, C. H. Devillers, S. Clément, A. van der Lee, P. D. Harvey and S. Richeter, *Organometallics*, 2016, **35**, 663–672.
- 56 J.-F. Longevial, S. Clément, J. A. Wytko, R. Ruppert, J. Weiss and S. Richeter, *Chem. – Eur. J.*, 2018, **24**, 15442–15460.
- 57 A. D. Jenkins, P. Kratochvíl, R. F. T. Stepto and U. W. Suter, *Pure Appl. Chem.*, 1996, **68**, 2287–2311.
- 58 N. Lalaoui, B. Reuillard, C. Philouze, M. Holzinger, S. Cosnier and A. Le Goff, *Organometallics*, 2016, **35**, 2987–2992.