Synergy of Excitation Enhancement and the Purcell Effect for Strong Photoluminescence Enhancement in a Thin-Film Hybrid Structure based on Quantum Dots and Plasmon Nanoparticles

Victor Krivenkov, Pavel S Samokhvalov, Igor R Nabiev, Yury P Rakovich

► To cite this version:

Victor Krivenkov, Pavel S Samokhvalov, Igor R Nabiev, Yury P Rakovich. Synergy of Excitation Enhancement and the Purcell Effect for Strong Photoluminescence Enhancement in a Thin-Film Hybrid Structure based on Quantum Dots and Plasmon Nanoparticles. *Journal of Physical Chemistry Letters*, 2020, 11 (19), pp.8018-8025. 10.1021/acs.jpcclett.0c02296 . hal-02933842

HAL Id: hal-02933842

<https://hal.science/hal-02933842>

Submitted on 8 Sep 2020

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Synergy of Excitation Enhancement and the Purcell Effect for Strong Photoluminescence Enhancement in a Thin-Film Hybrid Structure based on Quantum Dots and Plasmon Nanoparticles.

Victor Krivenkov, Pavel S. Samokhvalov, Igor R. Nabiev, and Yury P. Rakovich

J. Phys. Chem. Lett., **Just Accepted Manuscript** • DOI: 10.1021/acs.jpcllett.0c02296 • Publication Date (Web): 04 Sep 2020

Downloaded from pubs.acs.org on September 8, 2020

Just Accepted

"Just Accepted" manuscripts have been peer-reviewed and accepted for publication. They are posted online prior to technical editing, formatting for publication and author proofing. The American Chemical Society provides "Just Accepted" as a service to the research community to expedite the dissemination of scientific material as soon as possible after acceptance. "Just Accepted" manuscripts appear in full in PDF format accompanied by an HTML abstract. "Just Accepted" manuscripts have been fully peer reviewed, but should not be considered the official version of record. They are citable by the Digital Object Identifier (DOI®). "Just Accepted" is an optional service offered to authors. Therefore, the "Just Accepted" Web site may not include all articles that will be published in the journal. After a manuscript is technically edited and formatted, it will be removed from the "Just Accepted" Web site and published as an ASAP article. Note that technical editing may introduce minor changes to the manuscript text and/or graphics which could affect content, and all legal disclaimers and ethical guidelines that apply to the journal pertain. ACS cannot be held responsible for errors or consequences arising from the use of information contained in these "Just Accepted" manuscripts.

Synergy of Excitation Enhancement and the Purcell Effect for Strong Photoluminescence Enhancement in a Thin-Film Hybrid Structure based on Quantum Dots and Plasmon Nanoparticles

Victor Krivenkov,^{†,} Pavel Samokhvalov,[†] Igor Nabiev,^{†,‡,§} and Yury P. Rakovich^{¶,‡,*}*

[†] National Research Nuclear University MEPhI (Moscow Engineering Physics Institute),

115409 Moscow, Russian Federation

[‡] Laboratoire de Recherche en Nanosciences, LRN-EA4682, Université de Reims

Champagne-Ardenne, 51100 Reims, France

[§] Sechenov First Moscow State Medical University (Sechenov University), 119146

Moscow, Russian Federation

¶ Centro de Física de Materiales (MPC, CSIC-UPV/EHU), Donostia International

Physics Center (DIPC), and Departamento de Física de Materiales, UPV-EHU, 20018

Donostia - San Sebastian, Spain

IKERBASQUE, Basque Foundation for Science, 48013 Bilbao, Spain

Corresponding Authors

* vkkrivenkov@list.ru (VK) or yury.rakovich@ehu.eus (YR)

ABSTRACT

Reliable control of spontaneous radiation from quantum emitters, such as quantum dots (QDs), is an extremely important problem in quantum science, nanophotonics, and engineering. The QD photoluminescence (PL) may be enhanced near plasmon nanoparticles due to excitation field enhancement or the Purcell effect. However, both of these effects have their specific limitations. The excitation enhancement is usually accompanied by a decrease in the PL quantum yield (QY) due to the plasmon-induced energy transfer, and the Purcell effect cannot significantly enhance the PL of QDs with an initially high QY because of the obvious limitation of the QY by the value of 100%. Here, we have shown that the synergistic combination of excitation enhancement

caused by silver nanospheres and the Purcell effect caused by silver nanoplates in the same QD-in-polymer hybrid thin-film nanostructure permits simultaneous increases in the radiative and excitation rates to be obtained. This overcomes the limitations of each individual effect and yields a synergistic PL increase (+1320%) higher than the sum of the PL enhancements determined by each effect alone (+70% and +360%).

TOC GRAPHIC

KEYWORDS Photoluminescence enhancement, Purcell effect, near-field enhancement, quantum dots, plasmonics.

During recent decades, the use of localized surface plasmons (hereinafter, plasmons) has been gaining momentum in the field of nanophotonics due to some unique near-field effects. In particular, two very interesting features of plasmons may be used to enhance fluorophore photoluminescence (PL): local excitation field enhancement and

1
2 the Purcell effect.^{1,2} The condition for the enhancement of the excitation field near
3
4
5
6 plasmon nanostructures is resonant overlapping of the field frequency with the
7
8
9 eigenfrequency of the plasmons.³ On the other hand, the requirement for accelerating
10
11
12 the radiative recombination (the Purcell effect) is a resonant overlap of the plasmon
13
14
15 frequency with the PL band of the emitter.^{4,5} While the use of optical microcavities is a
16
17
18 common method for increasing the spontaneous emission of quantum emitters,⁶ the
19
20
21 density of photonic states near plasmon nanostructures can be several orders of
22
23
24 magnitude higher. This allows a significant increase in the excitation efficiency
25
26
27 compared with microcavities. Moreover, the limit of the radiative decay acceleration of
28
29
30 the emitter near plasmon nanostructures is two orders of magnitude higher than the
31
32
33 theoretical limit for microcavities.⁷
34
35
36
37
38
39
40

41 The emergence of new emitting nanoscale exciton nanostructures, such as
42
43
44 semiconductor quantum dots (QDs), raises new challenges in the development of
45
46
47 hybrid materials based on plasmon nanostructures. One of the most important
48
49
50 applications of QDs for advanced optoelectronic and optical information devices,⁸⁻¹⁰ as
51
52
53 well as for chemo- and biosensors,¹¹ is the design of fluorescent thin-film coatings using
54
55
56 polymer matrices with integrated QDs and plasmon nanoparticles (PNPs). For these
57
58
59
60

1
2 applications, the most critical parameters of QDs are the PL intensity (brightness) and
3
4
5
6 lifetime. Both of these parameters can be improved through the interaction with
7
8
9 plasmons.¹²
10

11
12
13 In previous studies, it was experimentally shown that an enhancement of the QD PL
14
15
16 intensity by a factor of up to 10 was achievable in the vicinity of plasmon
17
18
19 nanostructures.¹³⁻¹⁵ However, the origin of this effect remained obscure due to poorly
20
21
22 defined resonance conditions; i.e., this effect could be associated with either the Purcell
23
24
25 effect, the enhanced excitation efficiency, or both these factors. At the same time,
26
27
28 designing a nanostructure with a specific position of the plasmon resonance relative to
29
30
31 the excitation or PL wavelength may enable one to separate these two plasmon-
32
33
34 induced effects. Following this strategy, many studies have dealt with the effect of
35
36
37 accelerated radiative recombination of QD excitons near the plasmon nanostructures
38
39
40 (the Purcell effect). However, in this regime, a significant increase in the PL intensity
41
42
43 can occur only for QDs with an initially low PL quantum yield (QY).⁵ A representative
44
45
46 example of this was observed for a QD–Ag film system.¹⁶ In this structure, a 50-fold
47
48
49 increase in the QD PL intensity was observed near the array of circular Ag nanoislands
50
51
52 on an Ag film providing matching the QD emission and plasmon resonance. At the
53
54
55
56
57
58
59
60

1
2 same time, initially, QDs emitted very weakly. It should further be noted that the
3
4
5
6 plasmon-induced Purcell effect may also help to overcome one of the main limitations of
7
8
9 QDs, the presence of a low-luminescent “dark” fraction.¹⁷ Indeed, charging of QDs is a
10
11
12 common problem, which, due to the high-rate nonradiative Auger process, leads to a
13
14
15 decrease in the PL QY of part of the QD ensemble to near-zero values.¹⁸ This is a result
16
17
18 of the high-rate nonradiative Auger process between excitons and excess charge
19
20
21 carriers inside the QD core. The increase in the radiative rate due to the Purcell effect
22
23
24 should decrease the probability of the Auger process and increase in the PL QY of
25
26
27 these “dark” charged QDs.^{19,20}
28
29
30
31
32

33
34 A completely different approach is to increase the PL intensity by enhancing the
35
36
37 excitation efficiency near PNPs. The increase in the excitation efficiency can be as high
38
39
40 as 10- to 24-fold;^{3,21} however, the PL increase associated with this effect is usually only
41
42
43 2- to 4-fold.^{22,23} The reason for this is the reduction of the PL QY due to the plasmon-
44
45
46 induced acceleration of nonradiative recombination caused by energy transfer, which is
47
48
49 not compensated by the Purcell effect, and, hence, restrains the resulting increase in
50
51
52 the PL intensity. Thus, both effects have strong limitations in terms of the control of QD
53
54
55 PL: the Purcell effect cannot significantly increase the PL of QDs with an initially high
56
57
58
59
60

QY, while enhanced excitation is accompanied by a decrease in the QY of the QD ensemble. We assume that the optimal solution would be a regime where the excitation enhancement is accompanied by a simultaneous acceleration of radiative recombination, leading to the compensation for the deficiencies of both effects considered above. In this scenario the acceleration of radiative recombination will increase the PL QY even in the case of plasmon-induced quenching. At the same time, the enhancement of the excitation efficiency will considerably brighten the PL of QDs, even those with an initially high QY.

Some recent studies have attempted to investigate the combination of both effects in a colloidal solution of Au nanorods and QDs.²⁴ However, the properties of QD PL in solutions and thin films can be very different. In another study, a 10-fold increase in the PL intensity in the system consisting of QDs and an array of Au nanorods was explained as a result of an alledged combination of all conceivable plasmon-induced effects.²⁵ However, in this case, the plasmon spectrum was resonantly overlapped with the PL band but not with the excitation line, which implies only one interaction regime. The most representative examples of plasmon-induced PL enhancement, together with resonance conditions, are summarized in Table S1. Nevertheless, it should be noted

that, to provide resonance matching of the plasmon spectrum with both excitation and PL in materials where only one type of PNPs is used, the excitation wavelength should be very close to the PL band. Unfortunately, in this case, one of the main advantages of QDs, the giant Stokes shift of PL from excitation, is lost, as is the possibility of exciting the PL of QDs of different sizes using only one light source with a high photon energy. Here, we fabricated hybrid thin films of QDs integrated into a poly [methyl methacrylate] (PMMA) matrix and studied how *in situ* deposition of PNPs with different plasmon resonance positions relative to the excitation wavelength and the QD PL band affected the PL intensity. As a result, we have shown that the enhancement of QD PL was the highest in the case where the local field enhancement effect led to a higher excitation rate of QDs and, in the same structure, the Purcell effect simultaneously prevented a strong decrease in the QY of QD PL. The resulting PL enhancement (14.2-fold) was much higher than the sum of the PL enhancement factors for the excitation enhancement (1.7-fold) and the Purcell effect (4.6-fold) separately and even higher than their product, for which we have provided rationale.

In our experiments we used QDs with the CdSe(core)/ZnS/CdS/ZnS(multishell) structure with a PL maximum at 560 nm (Figure 1a) and the first exciton peak at 536 nm

(Figure 1b). The PL decay of QDs in a hexane solution (Figure 1c) was near-monoexponential, with a lifetime of 30 ns. The details of QD synthesis and preparation are presented in the Supporting Information (SI) file.

Figure 1. Optical properties of nanoparticles. (a) The extinction spectra of silver nanospheres (blue) and silver nanoplates (red) and the spectrum of QD PL (green line). (b) The extinction spectrum of QD PL. (c) The decay kinetics of QD PL.

It is known that the effect of PNPs on the PL of QDs strongly depends on the distance between the QDs and PNP films.^{21,26} Thus, we used PMMA films of different thicknesses to check whether the observed effects actually resulted from the plasmon–exciton interaction. The QD-in-PMMA films were coated with PNPs *in situ* during PL measurements by drop-casting of PNP solutions onto the QD-in-PMMA films. Thus, the

1
2 time-resolved PL signals were detected from the same areas of QD-in-PMMA films
3
4
5
6 before and after their interaction with PNPs. This allowed us to avoid the possible errors
7
8
9 related to the inhomogeneous distribution of QDs in the film. The details of
10
11
12 spectroscopic measurements are presented in the SI file.

13
14
15
16
17 To cover QD-in-PMMA films, we used two types of PNPs with different spectral
18
19
20 positions of the plasmon band: silver nanospheres (SNSs) and silver nanoplates
21
22
23 (SNPs). Details of the SNS and SNP syntheses, as well as their extinction spectra in
24
25
26 stock solutions, are presented in the SI. Three groups of samples were studied: films
27
28
29 covered with SNSs alone (Figure 2a), films covered with SNPs alone (Figure 2b), and
30
31
32 films covered with a mixture of SNSs and SNPs in equal proportions (Figure 2c). The
33
34
35 photographs and optical microscopy images of PNP solutions and thin films deposited
36
37
38 onto QD-in-PMMA substrates are presented in Figure S7. Each group comprised QD-in-
39
40
41
42 PMMA films with three thicknesses: 5, 10, and 20 nm. Our sample preparation routine
43
44
45 ensured that all QDs were distributed in the plane of the glass substrate and
46
47
48 immobilized there by coating a thin PMMA layer with a thickness of approximately 5 nm.
49
50
51
52 QD-in-PMMA films with thicknesses of 10 and 20 nm were obtained by coating this QD-
53
54
55 in-PMMA film with additional PMMA spacer layers (see the SI). The details of QD-in-
56
57
58
59
60

PMMA films preparation are presented in the SI file. Transmission electron microscopy (TEM) images of all PNPs are presented in Figure 2. Before the main experiments, the extinction spectra of PNPs deposited on “blank” (i.e., not containing QDs) PMMA films were measured. Figure 1a shows that the QD PL band largely overlaps only with the SNP resonance, which is prerequisite for weak light–matter coupling and the Purcell effect. On the other hand, the plasmon band of the SNS film largely overlaps with the excitation wavelength (485 nm), which is a precondition for the plasmon enhancement of the excitation electromagnetic field near the film surface.

Figure 2. Schematic representation of the thin-film structures studied. Panels a, b, and c show the sketches of the samples with different PNPs: SNSs (a), SNPs (b), and a mixture of SNSs and SNPs (c). Panels d, e, and f show the TEM images of the nanoparticles used: SNSs, SNPs, and QDs, respectively.

Figure 3a shows the PL signal collected by scanning a $80 \times 80 \mu\text{m}$ area of a QD-in-PMMA film with a total thickness of 5 nm (black line). 30 μl of the SNS solution was then drop-casted onto the QD-in-PMMA structure placed directly above the objective lens, without any changes in the position of the film or the lens. After the SNS film had dried, the PL signal was measured again from exactly the same area of the sample at the same excitation power (the red line in Figure 3a). It turned out that, in the presence of SNSs, the intensity of QD PL was higher by 150% (which translates into a 2.5-fold enhancement). The same experiments were carried out on QD-in-PMMA films with thicknesses of 10 nm (Figure 3b) and 20 nm (Figure 3c). We should note that the amplitudes of the control PL signals (black lines in the Figure 3) slightly differ for different types of the studied samples because of the differences in the signal collection times, which were optimized for each particular film. However, these variations do not compromise our conclusions about the observed plasmon-induced effects, because the

1
2 signal collection time for each of the studied sample was the same before and after the
3
4
5
6 PNP application on top of the regions of interest. We should also point out that the
7
8
9 plasmon-induced changes in the PL lifetimes (Table S2) were much greater than the
10
11
12 standard deviation of PL lifetime of the control signal, i.e., the standard deviation of 0.7
13
14
15 ns for the mean PL lifetime of 6.6 ns. In the case of 10-nm films, the increase in the total
16
17
18 PL intensity was 70% (Figure 3b); however, in the case of 20-nm films, the total PL
19
20
21 intensity was, conversely, decreased by 15% (Figure 3c). This finding is not surprising,
22
23
24 because the excitation field enhancement can only be efficient at short distances
25
26
27 between the fluorophore and PNPs and the effect of the plasmon-induced quenching
28
29
30 may be more long-range than the field enhancement effect.²⁶ Another effect to be taken
31
32
33 into account is the water-induced PL quenching, which can be due to infiltration of water
34
35
36 through the thin PMMA film (assuming that the PMMA spacer film is a filter-like structure
37
38
39 and the surface density of pores is approximately the same for films 5, 10, and 20 nm in
40
41
42 thickness).²⁷ The combination of these effects led to enhancement of the PL intensity at
43
44
45 the QD-in-PMMA film thicknesses of 5 and 10 nm but to PL quenching in the 20-nm
46
47
48 film. The nonradiative relaxation also manifested itself in a shortening of the PL lifetime
49
50
51 (Table S2 in SI). These results also mean that the observed PL brightness increase was
52
53
54
55
56
57
58
59
60

much lower than expected due to the excitation enhancement and could be much stronger at a higher radiative rate.

Figure 3. Time-resolved PL signals from QD-in-PMMA films before (black lines) and after (red lines) deposition of PNPs for different PNP types and different QD-in-PMMA film thicknesses. (a–c) PL signals from samples with deposited SNSs and different thicknesses: (a) 5 nm, (b) 10 nm, and (c) 20 nm. (d–f) PL signals collected from samples with deposited SNPs and different thicknesses: (d) 5 nm, (e) 10 nm, and (f) 20 nm. (g–i) PL signals collected from samples with a deposited SNS–SNP mixture and different thicknesses: (g) 5 nm, (h) 10 nm, and (i) 20 nm.

The experiments with SNP-containing samples were carried out following the same procedure; i.e., the PL signals from QD-in-PMMA films of different thicknesses were measured from the same areas (Figures 3d–3f) before (black lines) and after (red lines) SNP deposition. Figures 3d–3f clearly show that, at all film thicknesses, the addition of SNPs led to a drastic alteration of the PL decay, which can be seen as the appearance of an ultrafast component with a high signal amplitude and a response time close to the instrument response function (IRF) of the detection system (Table S2). At the same time, the long-time components of the PL decay were shorter for thinner QD-in-PMMA films, which implies the Purcell effect, but their values are still longer than the IRF. This can be explained if we take into account that QD ensembles often contain two types of QDs: bright QDs with a relatively high PL QY and a “dark fraction” of QDs that are in the low- or non-luminescent state. The latter are charged permanently or at least for long periods of time and, consequently, have a high-rate Auger-like nonradiative exciton recombination channel.^{18,28} We were unable to observe the PL response of the QDs from the “dark fraction” before interaction with SNPs due to their initially very low PL QY. However, for QD samples with a lower initial QY (the “dark fraction”), the increase in the radiative recombination rate due to the Purcell effect could cause a substantial

1
2 growth of the PL QY, and, in this case, the total enhancement of QY would be higher
3
4
5
6 than that observed in the case of SNS-covered samples. Thus, a strong Purcell effect
7
8
9 could lead to a considerable increase in the contribution of the brightened “dark” part of
10
11
12 QDs to the overall PL signal. Along with this, such an increased contribution of the
13
14
15
16 originally “dark” fraction of QDs with an initially very short PL lifetime could lead to the
17
18
19 appearance of an ultrafast component in the PL signal.
20
21
22
23

24 To confirm our assumption, we acquired a series of PL images of selected areas of
25
26
27 interest before and after SNP deposition (Figure 4). It can be seen that the addition of
28
29
30 SNSs caused a distinct though moderate increase in the brightness of the QD film
31
32
33 (Figures 4a and 4b). In contrast, the deposition of SNPs led to a substantial growth of
34
35
36 the bright fraction of the image (Figures 4c and 4d). This brightening is consistent with
37
38
39 the assumed increased contribution of initially “dark” QDs, which were previously
40
41
42 undetectable. We believe that the bright and non-uniform patterns observed, which are shown
43
44
45 in Figures 4b, 4d, and 4f, most likely reflect the distribution of the PNP aggregates on the surface
46
47
48 of QD-in-PMMA films.
49
50
51
52
53
54
55
56
57
58
59
60

Figure 4. Confocal microscopy PL images of QD-in-PMMA films with a total thickness of 10 nm before (a, c, e) and after (b, d, f) deposition of PNPs: (a, b) before and after SNS deposition, (c, d) before and after SNP deposition, (e, f) before and after deposition of the mixture of SNSs and SNPs.

Despite the random distribution of SNPs on the surface of the QD-in-PMMA film, the interaction of any individual QD with neighboring SNPs is characterized by a high Purcell factor even at plasmon–exciton distances as long as 135 nm.²⁰ Therefore, the observed PL enhancement is the averaged cumulative result of all individual QD-SNP interactions. It is also worth noting that the increase in the PL intensity of the SNP-covered samples of the QD-in-PMMA structures with thicknesses of 10 and 20 nm (+360% and +370%, respectively) were higher than that observed in the 5-nm sample. We believe that this is a result of the distance-dependent “tug of war” between plasmon-induced energy transfer, which increases the nonradiative recombination rate, and the Purcell effect, which, in turn, raises the radiative recombination rate.^{20,26,29,30} However, in accordance with the theory of plasmon–exciton interaction, for PNPs with morphologies and sizes other than those studied here, the optimal thickness of the spacer will be different. In addition, this parameter could potentially be affected by the density of PNPs on the surface of the QD-in-PMMA film.

The maximum QD PL enhancement (370%), which was observed when the SNPs were used, was much higher than that in the case of the SNSs (150%). The reason for this difference is the SNP capacity for increasing the QY of “dark” QDs. In both cases,

metal-induced PL quenching (an increase in the nonradiative relaxation rate) occurred.

In the case of the SNSs, this leads to a drop of the QY, because the radiative relaxation rate in the presence of the nanospheres was unchanged. Thus, the resultant PL enhancement was the product of the reduced QY and the increased excitation intensity, which limits the PL enhancement for both initially highly luminescent “bright” QDs and non-luminescent “dark” QDs that are present in the sample. As for the SNPs, the roles of the former two factors are additionally increased. Indeed, the increase in the radiative relaxation rate due to the Purcell effect can certainly overwhelm the metal-induced decrease in the PL QY of “bright” QDs and, additionally, switch on the initially non-luminescent “dark” QDs to make them “bright”.

However, the most outstanding results were obtained in experiments carried out before and after deposition of the mixture made of equal amounts of SNSs and SNPs onto the QD-in-PMMA films. The extinction spectrum of the mixed SNS/SNP film is shown in Figure S6 (black solid line). To demonstrate that this spectrum is the result of superposition of two independent plasmon resonances originating from the SNSs and SNPs, we have fitted the experimental spectrum by two Gaussian bands (dashed red and green lines in Figure S6). The sum of these two Gaussian bands (dashed blue line

in Figure S6) is in good agreement with the experimental spectrum. The positions of these two bands are in good agreement with the experimental extinction spectra of both SNS and SNP films (Figure 1a), which proves that the mixed SNS/SNP film exhibits resonances with both PL excitation and the PL emission of the QDs. Time-resolved measurements revealed that, after deposition of the SNS/SNP mixture, PL signals contain combined features caused by the SNS and SNP effects (Figures 3g–3i). First, the high-amplitude ultrafast component of PL decay was observed, as in the case of the effect of deposition of SNPs alone. Moreover, the amplitude of the long-lifetime component of the PL decay increased much more than in the cases when only SNSs or SNPs were deposited (Table S2). This feature can be explained by the fact that, in these samples, the Purcell effect compensates for the plasmon-induced PL quenching and the quenching does not interfere with the excitation enhancement. The PL image of a sample covered with SNS/SNP blend (Figure 4f) is similar to the picture of the SNP sample (Figure 4d), where the “bright” fraction of the image was larger than in the SNS-covered film (Figure 4b). However, the overall brightness of the structure with the PNP blend was significantly higher than in the cases of SNS- and SNP-covered samples. This result implies that the effect caused by the SNS/SNP mixture leads not only to an

increased contribution of the brightened the “dark fraction” of the QD ensemble caused by the Purcell effect, but also to an additional increase in the PL intensity due to the excitation enhancement.

The most outstanding result was obtained for the sample with a QD-in-PMMA film 10 nm in thickness, in which the PL enhancement was as much as +1320%.

Extraordinarily, this value is much higher than the simple sum of the enhancements observed for this thickness in films covered with only SNSs (+70%) or SNPs (+360%).

This finding can be explained by the simultaneous increase in the excitation and radiative recombination rates in the QD-in-PMMA film with an SNS/SNP layer. Indeed, in the case of PL increase in the samples with only SNSs as a surface layer, the excitation intensity I_{ex} can be increased due to the well-known effect of plasmon-induced amplification of the intensity of the electromagnetic field near the SNS surface by the factor κ , and the PL enhancement factor F_{EE} can be expressed by the following equation (for derivation of this and following equations, see SI):

$$F_{EE} \approx \kappa \cdot \frac{k_{rad} + k_{nr}}{k_{rad} + k_{nr} + k_{ET}}, \quad (1)$$

where k_{rad} is the radiative recombination rate, k_{nr} is the rate of internal nonradiative relaxation due to the inner or surface defects, and k_{ET} is the metal-induced nonradiative

energy transfer rate in the proximity of PNPs. Due to the Purcell effect, in the samples covered with SNPs alone, the k_{rad} should be multiplied by the Purcell factor F . Thus, the observed increase in the number of collected photons as a result of the rise of the QY and the PL enhancement factor F_{PE} is

$$F_{PE} \approx \frac{F \cdot k_{rad} + F \cdot k_{nr}}{F \cdot k_{rad} + k_{nr} + k_{ET}} \quad (2)$$

In the most interesting case, when the SNS/SNP mixture is used to cover the QD-in-PMMA films, both the excitation field amplitude will be increased and the Purcell effect will take place. In this case the amplification coefficient can be expressed as

$$F_{sum} \approx \kappa \cdot \frac{F \cdot k_{rad} + F \cdot k_{nr}}{F \cdot k_{rad} + k_{nr} + k_{ET}} \quad (3)$$

From eq 3 it is evident that, for the QD-in-PMMA films covered with the SNS/SNP mixture, the resulting PL enhancement is higher than mere superposition of the above-mentioned individual enhancements. Moreover, the PL amplification factor (eq 3) is higher than the result of simple multiplication of the PL enhancements observed in the cases of excitation enhancement (eq 1) and Purcell effect (eq 2) separately. Thus, the effect the excitation enhancement alone on the PL intensity is limited by lowering of the PL QY, but a substantial increase in the radiative recombination rate not only restrains

the decrease of the QY, but can also lead to its growth. As a result, the total “synergistic” impact of the superposition of both effects is much stronger than the influence of the excitation enhancement or the Purcell effect separately.

In conclusion, we have studied the “synergistic” effect of the plasmon-induced enhancements of excitation and radiative recombination rates on the QD PL brightness. For this purpose, we fabricated thin PMMA films with incorporated QDs and PNPs deposited onto polymer spacers of various thicknesses. For each film thickness, the PL signals from exactly the same areas of these films were studied before and after initiation of QD–PNP interaction. To investigate the effect of spectral overlap, we used two types of deposited PNPs: SNSs, whose plasmon resonance overlapped with the excitation wavelength, and SNPs, with the plasmon band overlapping with the QD PL line. We found that, for samples in which only SNSs covered the QD-in-PMMA films, the plasmon-induced PL increase was up to 150% and was weakening with increasing thickness of the QD-in-PMMA films. In this case, the observed growth of the PL intensity is the result of the excitation enhancement and is restricted by the nonradiative recombination due to the plasmon-induced energy transfer. The effect of SNPs on the PL signal of QDs was more complex. In this case, due to the Purcell effect, a significant

fraction of initially non-luminescent QDs began to contribute to the overall PL signal with an ultrashort lifetime. This led to an expansion of the bright area in PL images and an enhancement of PL of up to 370%. Moreover, in this case, the maximum PL intensification was achieved for thicker QD-in-PMMA films than in the case of the SNS-covered samples. The main and most remarkable result of our study was observed for a composite film where a mixture of SNSs and SNPs served as a cover layer for the QD-in-PMMA structure. In these samples, we observed both an increase in the number of luminescent QDs and an increase in the PL intensity of the initially “bright” QDs. Moreover, the maximum PL increase observed in the samples covered with a blend of SNSs and SNPs was 1320%, which is much higher than the result of a simple superposition of the PL enhancements induced by SNS (70%) and SNP (360%) alone. We explained this result by a simultaneous increase in the QD absorption due to the enhanced excitation and increase in the QY due to the Purcell effect. Thus, the metal-induced quenching, which decreases the PL QY in the case of the use of SNSs alone, was compensated for by the Purcell effect. Moreover, the QDs with an initially high QY were brightened by an excitation enhancement stronger than in the case where only SNPs were used. Finally, we have provide rationale that the synergy of the excitation

enhancement and the Purcell effect leads to a total PL enhancement that is even higher than the result of multiplication of the PL enhancement factors in the cases of using SNSs and SNPs alone. The demonstrated synergy of the excitation enhancement and the Purcell effect as a tool for controlling the efficiency of spontaneous emission of thin hybrid QD–polymer films can be used for numerous applications in the fields of biosensing, optoelectronics, and quantum information. Moreover, optimal combinations of plasmon nanostructures with different plasmon resonances will allow flexible adaptation of the designed systems for the required spectral conditions of excitation and the resulting PL.

ASSOCIATED CONTENT

Supporting Information. A brief review of the examples of plasmon-induced PL enhancement; details of nanocrystal sample synthesis; details of spectroscopic measurements; details of QD-in-PMMA film preparation; details of the AFM profiling measurements of the thicknesses of thin films; details of the biexponential fitting of the PL decay kinetics; analytical explanation of the plasmon-induced enhancement synergy. (PDF)

AUTHOR INFORMATION

Corresponding Authors

Victor Krivenkov: vkrivenkov@list.ru

Yury Rakovich: yury.rakovich@ehu.eus

ORCID

Victor Krivenkov: 0000-0003-0280-2296

Pavel Samokhvalov: 0000-0002-2878-8376

Yury Rakovich: 0000-0003-0111-2920

Igor Nabiev: 0000-0002-8391-040X

Notes

The authors declare no competing financial interests.

ACKNOWLEDGMENTS

The authors thank D. Dyagileva for the help with preparation of the QD-in-PMMA thin films, and I.S. Vaskan for assistance in AFM profiling measurements. The financial support from the Ministry of Science and Higher Education of the Russian Federation through grant no. 14.Y26.31.0011 is acknowledged. Y.R. acknowledges the support from the Basque Government (grant no. IT1164-19). I.N. is grateful to the Université de

Reims Champagne-Ardenne, the Ministry of Higher Education, Research and Innovation, and the Conseil Regional de Grand Est of France for support. We thank Vladimir Ushakov for the help with technical preparation of the manuscript.

REFERENCES

- (1) Maier, S. A. *Plasmonics: Fundamentals and Applications*; Springer: New York, 2007.
- (2) Gaponenko, S. V.; Guzatov, D. V. Colloidal Plasmonics for Active Nanophotonics. *Proc. IEEE* **2020**, *108* (5), 704–720.
- (3) Chen, Y.; Munechika, K.; Plante, J.-L.; Munro, A. M.; Skrabalak, S. E.; Xia, Y.; Ginger, D. S. Excitation Enhancement of CdSe Quantum Dots by Single Metal Nanoparticles. *Appl. Phys. Lett.* **2008**, *93* (5), 053106.
- (4) Chen, Y.; Munechika, K.; Ginger, D. S. Dependence of Fluorescence Intensity on the Spectral Overlap between Fluorophores and Plasmon Resonant Single Silver Nanoparticles. *Nano Lett.* **2007**, *7* (3), 690–696.
- (5) Munechika, K.; Chen, Y.; Tillack, A. F.; Kulkarni, A. P.; Plante, J.-L.; Munro, A. M.; Ginger, D. S. Spectral Control of Plasmonic Emission Enhancement from Quantum Dots near Single Silver Nanoprisms. *Nano Lett.* **2010**, *10* (7), 2598–2603.
- (6) Dovzhenko, D.; Martynov, I.; Samokhvalov, P.; Osipov, E.; Lednev, M.;

- Chistyakov, A.; Karaulov, A.; Nabiev, I. Enhancement of Spontaneous Emission of Semiconductor Quantum Dots inside One-Dimensional Porous Silicon Photonic Crystals. *Opt. Express* **2020**, *28* (15), 22705–22717.
- (7) Bozhevolnyi, S. I.; Khurgin, J. B. Fundamental Limitations in Spontaneous Emission Rate of Single-Photon Sources. *Optica* **2016**, *3* (12), 1418.
- (8) Yang, Z.; Gao, M.; Wu, W.; Yang, X.; Sun, X. W.; Zhang, J.; Wang, H. C.; Liu, R. S.; Han, C. Y.; Yang, H.; Li, W. Recent Advances in Quantum Dot-Based Light-Emitting Devices: Challenges and Possible Solutions. *Mater. Today* **2019**, *24*, 69–93.
- (9) Kim, N. Y.; Hong, S. H.; Kang, J. W.; Myoung, N.; Yim, S. Y.; Jung, S.; Lee, K.; Tu, C. W.; Park, S. J. Localized Surface Plasmon-Enhanced Green Quantum Dot Light-Emitting Diodes Using Gold Nanoparticles. *RSC Adv.* **2015**, *5* (25), 19624–19629.
- (10) Yang, X.; Hernandez-Martinez, P. L.; Dang, C.; Mutlugun, E.; Zhang, K.; Demir, H. V.; Sun, X. W. Electroluminescence Efficiency Enhancement in Quantum Dot Light-Emitting Diodes by Embedding a Silver Nanoisland Layer. *Adv. Opt. Mater.* **2015**, *3* (10), 1439–1445.
- (11) Guan, W.; Zhou, W.; Lu, J.; Lu, C. Luminescent Films for Chemo- and Biosensing. *Chemical Society Reviews* **2015**, *44* (19), 6981–7001.
- (12) Dey, S.; Zhao, J. Plasmonic Effect on Exciton and Multiexciton Emission of Single Quantum Dots. *J. Phys. Chem. Lett.* **2016**, *7* (15), 2921–2929.

- (13) Kulakovich, O.; Strekal, N.; Yaroshevich, A.; Maskevich, S.; Gaponenko, S.; Nabiev, I.; Woggon, U.; Artemyev, M. Enhanced Luminescence of CdSe Quantum Dots on Gold Colloids. *Nano Lett.* **2002**, *2* (12), 1449–1452.
- (14) Biteen, J. S.; Pacifici, D.; Lewis, N. S.; Atwater, H. A. Enhanced Radiative Emission Rate and Quantum Efficiency in Coupled Silicon Nanocrystal-Nanostructured Gold Emitters. *Nano Lett.* **2005**, *5* (9), 1768–1773.
- (15) Ito, Y.; Matsuda, K.; Kanemitsu, Y. Mechanism of Photoluminescence Enhancement in Single Semiconductor Nanocrystals on Metal Surfaces. *Phys. Rev. B* **2007**, *75* (3), 1–4.
- (16) Song, J. H.; Atay, T.; Shi, S.; Urabe, H.; Nurmikko, A. V. Large Enhancement of Fluorescence Efficiency from CdSe/ZnS Quantum Dots Induced by Resonant Coupling to Spatially Controlled Surface Plasmons. *Nano Lett.* **2005**, *5* (8), 1557–1561.
- (17) Yao, J.; Larson, D. R.; Vishwasrao, H. D.; Zipfel, W. R.; Webb, W. W. Blinking and Nonradiant Dark Fraction of Water-Soluble Quantum Dots in Aqueous Solution. *Proc. Natl. Acad. Sci.* **2005**, *102* (40), 14284–14289.
- (18) Krivenkov, V.; Samokhvalov, P.; Zvaigzne, M.; Martynov, I.; Chistyakov, A.; Nabiev, I. Ligand-Mediated Photobrightening and Photodarkening of CdSe/ZnS Quantum Dot Ensembles. *J. Phys. Chem. C* **2018**, *122* (27), 15761–15771.
- (19) Ma, X.; Tan, H.; Kipp, T.; Mews, A. Fluorescence Enhancement, Blinking Suppression, and Gray States of Individual Semiconductor Nanocrystals Close to

- Gold Nanoparticles. *Nano Lett.* **2010**, *10* (10), 4166–4174.
- (20) Krivenkov, V.; Dyagileva, D.; Samokhvalov, P.; Nabiev, I.; Rakovich, Y. Effect of Spectral Overlap and Separation Distance on Exciton and Biexciton Quantum Yields and Radiative and Nonradiative Recombination Rates in Quantum Dots Near Plasmon Nanoparticles. *Ann. Phys. (Berlin)* **2020**, *532* (8), 2000236.
- (21) Jin, S.; DeMarco, E.; Pellin, M. J.; Farha, O. K.; Wiederrecht, G. P.; Hupp, J. T. Distance-Engineered Plasmon-Enhanced Light Harvesting in CdSe Quantum Dots. *J. Phys. Chem. Lett.* **2013**, *4* (20), 3527–3533.
- (22) Sun, D.; Tian, Y.; Zhang, Y.; Xu, Z.; Sfeir, M. Y.; Cotlet, M.; Gang, O. Light-Harvesting Nanoparticle Core-Shell Clusters with Controllable Optical Output. *ACS Nano* **2015**, *9* (6), 5657–5665.
- (23) Liang, H. Y.; Zhao, H. G.; Li, Z. P.; Harnagea, C.; Ma, D. L. Silver Nanoparticle Film Induced Photoluminescence Enhancement of Near-Infrared Emitting PbS and PbS/CdS Core/Shell Quantum Dots: Observation of Different Enhancement Mechanisms. *Nanoscale* **2016**, *8* (9), 4882–4887.
- (24) Trotsiuk, L.; Muravitskaya, A.; Kulakovich, O.; Guzatov, D.; Ramanenka, A.; Kelestemur, Y.; Demir, H. V.; Gaponenko, S. Plasmon-Enhanced Fluorescence in Gold Nanorod-Quantum Dot Coupled Systems. *Nanotechnology* **2020**, *31* (10), 105201.
- (25) Peng, B.; Li, Z.; Mutlugun, E.; Hernández Martínez, P. L.; Li, D.; Zhang, Q.; Gao, Y.; Demir, H. V.; Xiong, Q. Quantum Dots on Vertically Aligned Gold Nanorod

- Monolayer: Plasmon Enhanced Fluorescence. *Nanoscale* **2014**, *6* (11), 5592–5598.
- (26) Guzatov, D. V.; Vaschenko, S. V.; Stankevich, V. V.; Lunevich, A. Y.; Glukhov, Y. F.; Gaponenko, S. V. Plasmonic Enhancement of Molecular Fluorescence near Silver Nanoparticles: Theory, Modeling, and Experiment. *J. Phys. Chem. C* **2012**, *116* (19), 10723–10733.
- (27) Pechstedt, K.; Whittle, T.; Baumberg, J.; Melvin, T. Photoluminescence of Colloidal CdSe/ZnS Quantum Dots: The Critical Effect of Water Molecules. *J. Phys. Chem. C* **2010**, *114* (28), 12069–12077.
- (28) Murthy, A. V. R.; Patil, P.; Datta, S.; Patil, S. Photoinduced Dark Fraction Due to Blinking and Photodarkening Probability in Aqueous CdTe Quantum Dots. *J. Phys. Chem. C* **2013**, *117* (25), 13268–13275.
- (29) Krivenkov, V.; Goncharov, S.; Samokhvalov, P.; Sánchez-Iglesias, A.; Grzelczak, M.; Nabiev, I.; Rakovich, Y. Enhancement of Biexciton Emission Due to Long-Range Interaction of Single Quantum Dots and Gold Nanorods in a Thin-Film Hybrid Nanostructure. *J. Phys. Chem. Lett.* **2019**, *10*, 481–486.
- (30) Song, M.; Wu, B.; Chen, G.; Liu, Y.; Ci, X.; Wu, E.; Zeng, H. Photoluminescence Plasmonic Enhancement of Single Quantum Dots Coupled to Gold Microplates. *J. Phys. Chem. C* **2014**, *118* (16), 8514–8520.