Peculiarities of crystal structures and photophysical properties of Ga III /Ln III metallocrowns with a non-planar [12-MC-4] core

Tu Nguyen, Svetlana Eliseeva, Chun Chow, Jeff Kampf, Stephane Petoud,
Vincent Pecoraro

► To cite this version:

Tu Nguyen, Svetlana Eliseeva, Chun Chow, Jeff Kampf, Stephane Petoud, et al.. Peculiarities of crystal structures and photophysical properties of Ga III /Ln III metallocrowns with a non-planar [12-MC-4] core. *Inorganic Chemistry Frontiers*, 2020, 7 (7), pp.1553-1563. 10.1039/c9qi01647c . hal-02935785

HAL Id: hal-02935785

<https://hal.science/hal-02935785>

Submitted on 16 Nov 2020

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

ARTICLE

Peculiarities of crystal structures and photophysical properties of Ga^{III}/Ln^{III} metallacrowns with a non-planar [12-MC-4] core

Received 00th January 20xx,
Accepted 00th January 20xx

Tu N. Nguyen,^{‡,a,c} Svetlana V. Eliseeva,^{*,‡,b} Chun Y. Chow,^a Jeff W. Kampf,^a Stéphane Petoud,^{*,b} and Vincent L. Pecoraro^{*,a}

DOI: 10.1039/x0xx00000x

A new series of gallium(III)/lanthanide(III) metallacrown (MC) complexes (**Ln-1**) was synthesized by the direct reaction of salicylhydroxamic acid (H₂shi) with Ga^{III} and Ln^{III} nitrates in a CH₃OH/pyridine mixture. X-ray single crystal analysis revealed two types of structures depending on whether the nitrate counterion coordinate or not to the Ln^{III}: [LnGa₄(shi)₄(H₂shi)₂(py)₄(NO₃)](py)₂ (Ln = Gd^{III}, Tb^{III}, Dy^{III}, Ho^{III}) and [LnGa₄(shi)₄(H₂shi)₂(py)₅](NO₃)(py) (Ln = Er^{III}, Tm^{III}, Yb^{III}). The representative **Tb-1** and **Yb-1** MCs consist of a Tb/YbGa₄ core with four [Ga^{III}-N-O] repeating units forming a non-planar ring that coordinates the central Ln^{III} through the oxygen atoms of the four shi³⁻ groups. Two H₂shi⁻ groups bridge the Ln^{III} to the Ga^{III} ring ions. The Yb^{III} in **Yb-1** is eight-coordinated while the ligation of the nine-coordinated Tb^{III} in **Tb-1** is completed by one chelating nitrate ion. **Ln-1** complexes in the solid state showed characteristic sharp f-f transitions in the visible (Tb, Dy) and near-infrared (Dy, Ho, Er, Yb) spectral ranges upon excitation into the ligand-centered electronic levels at 350 nm. Observed luminescence lifetimes and absolute quantum yields were collected and discussed. For **Yb-1**, luminescence data were also acquired in CH₃OH and CD₃OH solutions and a more extensive analysis of photophysical properties was performed. This work demonstrates that while obtaining highly luminescent lanthanide(III) MCs via a direct synthesis is feasible, many factors such as molar absorptivities, triplet state energies, non-radiative deactivations through vibronic coupling with overtones of O-H, N-H, and C-H oscillators and crystal packing will strongly contribute to the luminescent properties and should be carefully considered.

Introduction

Photoluminescence is a light-emitting process based on the absorption of photons, which brings a compound to an excited state that emits light when returning to the ground state. Photoluminescence can be obtained from a variety of compounds, for example, proteins,¹ organic molecules and polymers,^{2, 3} semiconductor nanocrystals (quantum dots),⁴ inorganic pigments,⁵ transition metal complexes,⁶ and lanthanide(III) (Ln^{III}) complexes and nanomaterials.^{7, 8} The unique properties of Ln^{III} compounds that complement those of other luminophores include their characteristic sharp emission bands the wavelengths of which depends on the nature of the Ln^{III} and are non-sensitive to changes in their environments, long luminescence lifetimes, and strong resistance to photobleaching, which make them highly appealing for a broad

variety of applications in materials sciences as well as for bioanalysis and biological imaging.⁹⁻²⁰

Most of Ln^{III} ions are luminescent and exhibit characteristic emission in the visible and/or near-infrared (NIR) ranges due to their electronic transitions within 4f orbitals. However, because of the forbidden nature of most of f-f transitions, Ln^{III} ions are very weak light absorbers, with molar absorptivities (ϵ) in solution often smaller than 10 M⁻¹ cm⁻¹.²¹ Thus, the direct excitation of Ln^{III} ions is rather inefficient. To overcome this limitation, chromophoric organic sensitizing ligands named “antenna” that possess large ϵ are often employed to synthesize luminescent Ln^{III} complexes.²² With this strategy, the excitation light can be efficiently absorbed in the system and the resulting energy can be transferred to the accepting levels of Ln^{III}. The subsequent f-f emission occurs when the system relaxes back to the ground state. The nature of the chromophoric ligands, their molar absorption coefficients, their abilities to protect Ln^{III} ions from non-radiative deactivations and to efficiently sensitize them are main parameters to consider when designing Ln^{III}-containing luminescent compounds.²³

Our group has recently initiated an innovative approach to create highly luminescent Ln^{III}-based probes and materials by utilizing metallacrown complexes.²⁴⁻³⁰ Metallacrowns (MCs) are a unique class of inorganic macrocycles that consist of repeating [Metal-N-O] subunits.³¹ With structural similarity to crown ethers, MCs are capable of binding a central metal ion through

^a Department of Chemistry, Willard H. Dow Laboratories, University of Michigan, Ann Arbor, Michigan 48109, USA. *Email: V. L. Pecoraro, vpec@umich.edu

^b Centre de Biophysique Moléculaire, CNRS UPR 4301, F-45071 Orléans Cedex 2, France. *Emails: S.V. Eliseeva, svetlana.eliseeva@cnrs-orleans.fr; S. Petoud, stephane.petoud@inserm.fr

^c Current address: Helen Scientific Research and Technological Development Co., Ltd, Ho Chi Minh City, Vietnam.

†Electronic Supplementary Information (ESI) available: supplementary tables, figures, and X-ray crystallographic parameters, including CIF files (CCDC 1965633-1965634). See DOI: 10.1039/x0xx00000x

[‡]These authors contributed equally

the hydroximate oxygen atoms. MCs have been extensively explored in the fields of selective ion recognition,^{32–38} molecular magnetism^{39–47} and magnetorefrigeration,⁴⁸ as well as contrast agents for magnetic resonance imaging (MRI).^{49–51} In view of the creation of luminescent Ln^{III}-based compounds, the unique MC scaffolds combine a large number of chromophores able to efficiently absorb and sensitize characteristic Ln^{III} emission in the visible and NIR ranges as well as to protect Ln^{III} from the sources of non-radiative deactivations. Several families of highly luminescent MCs exhibiting characteristic Ln^{III} emission have been described, e.g. Ln^{III}/Zn^{II} MCs with an “encapsulated sandwich” structure^{25, 52} and Ln^{III}/Ga^{III} MCs with monomeric²⁶ or dimeric²⁸ structures assembled using salicylhydroxamic (H₃shi³⁻) and benzoic (HOBz), or isophthalic (H₂iph) acids, respectively. In this work, we present the syntheses, peculiarities of crystal structures and photophysical properties of a new series of Ga^{III}/Ln^{III} MCs assembled using a direct reaction of the H₃shi ligand with Ga^{III} and Ln^{III} nitrates.

Experimental

All reagents and chemicals were purchased from commercial sources and used without further purification. All reactions were carried under aerobic conditions.

Preparation of Complexes Ln-1

H₃shi (153.1 mg, 1.0 mmol), Ln(NO₃)₃·xH₂O (0.25 mmol) (Ln^{III} = Gd^{III}, Tb^{III}, Dy^{III}, Ho^{III}, Er^{III}, Tm^{III}, and Yb^{III}), and Ga(NO₃)₃·xH₂O (255.7 mg, 1.0 mmol) were dissolved in 10 mL methanol. Pyridine (2 mL) and acetic acid (0.1 mL) were added and the mixture was stirred for 20 mins. The solution was filtered and kept undisturbed. X-ray quality crystals form after one day.

[GdGa₄(shi)₄(H₂shi)₂(py)₄(NO₃)₃] · (py)₂ (**Gd-1**). Yield: 131 mg (28%). ESI-MS, calc. for [M]⁺, C₄₂H₂₆N₆O₁₈GdGa₄, 1338.8; found, 1337.9. Anal. Calcd for GdGa₄C₇₂H₅₈N₁₃O₂₁: C, 46.06; H, 3.11; N, 9.70. Found: C, 46.02; H, 3.07; N, 9.33.

[TbGa₄(shi)₄(H₂shi)₂(py)₄(NO₃)₃] · (py)₂ (**Tb-1**). Yield: 153 mg (33%). ESI-MS, calc. for [M]⁺, C₄₂H₂₆N₆O₁₈TbGa₄, 1340.5; found, 1339.8. Anal. Calcd for TbGa₄C₇₂H₅₈N₁₃O₂₁: C, 46.02; H, 3.11; N, 9.69. Found: C, 46.31; H, 3.20; N, 9.64.

[DyGa₄(shi)₄(H₂shi)₂(py)₄(NO₃)₃] · (py)₂ (**Dy-1**). Yield: 151 mg (32%). ESI-MS, calc. for [M]⁺, C₄₂H₂₆N₆O₁₈DyGa₄, 1344.1; found, 1343.9. Anal. Calcd for DyGa₄C₇₂H₅₈N₁₃O₂₁: C, 45.93; H, 3.11; N, 9.67. Found: C, 46.22; H, 3.17; N, 9.49.

[HoGa₄(shi)₄(H₂shi)₂(py)₄(NO₃)₃] · (py)₂ (**Ho-1**). Yield: 147 mg (31%). ESI-MS, calc. for [M]⁺, C₄₂H₂₆N₆O₁₈HoGa₄, 1346.5; found, 1346.8. Anal. Calcd for HoGa₄C₇₂H₅₈N₁₃O₂₁: C, 45.87; H, 3.10; N, 9.66. Found: C, 46.10; H, 3.13; N, 9.48.

[ErGa₄(shi)₄(H₂shi)₂(py)₅(NO₃)₃] · (py) (**Er-1**). Yield: 127 mg (27%). ESI-MS, calc. for [M]⁺, C₄₂H₂₆N₆O₁₈ErGa₄, 1348.9; found, 1347.9. Anal. Calcd for ErGa₄C₇₂H₅₈N₁₃O₂₁: C, 45.82; H, 3.10; N, 9.65. Found: C, 45.68; H, 3.37; N, 9.35.

[TmGa₄(shi)₄(H₂shi)₂(py)₅(NO₃)₃] · (py) (**Tm-1**). Yield: 166 mg (35%). ESI-MS, calc. for [M]⁺, C₄₂H₂₆N₆O₁₈TmGa₄, 1350.5; found,

1350.8. Anal. Calcd for TmGa₄C₇₂H₅₈N₁₃O₂₁: C, 45.78; H, 3.09; N, 9.64. Found: C, 45.48; H, 3.35; N, 9.26.

[YbGa₄(shi)₄(H₂shi)₂(py)₅(NO₃)₃] · (py) (**Yb-1**). Yield: 114 mg (24%). ESI-MS, calc. for [M]⁺, C₄₂H₂₆N₆O₁₈YbGa₄, 1354.6; found, 1353.8. Anal. Calcd for YbGa₄C₇₂H₅₈N₁₃O₂₁: C, 45.68; H, 3.09; N, 9.62. Found: C, 45.85; H, 3.30; N, 9.31.

X-Ray Crystallography

Single-crystal X-ray crystallographic data for the **Tb-1** and **Yb-1** MCs were collected at 85(2) K on an Rigaku AFC10K Saturn 944+ CCD-based X-ray diffractometer equipped with a Micromax007HF Cu-target microfocus rotating anode (λ = 1.54187 Å), operated at 1200 W power (40 kV, 30 mA). The data were processed with the program CrystalClear 2.0 and corrected for absorption. The structure was solved and refined with the program SHELXTL (version 6.12).⁵³ All non-hydrogen atoms were refined anisotropically. Hydrogen atoms were placed in their idealized positions. The structure of **Tb-1** contains large solvent accessible voids totalling 939 Å³ and 107 electrons per unit cell. This region has diffuse electron density and could not be modelled with any chemically reasonable moieties. Thus, the SQUEEZE routine of the PLATON suite of programs⁵⁴ was applied to remove the diffraction contribution from these solvent molecules. Experimental parameters and crystallographic data for **Tb-1** and **Yb-1** are provided in [Table S1](#). For other **Ln-1** compounds, unit cell parameters were collected and showed in [Table S2](#).

Photophysical Measurements

Luminescence data were collected on samples placed into 2.4 mm i.d. quartz capillaries or quartz Suprasil cells. Emission and excitation spectra were measured on a Horiba-Jobin-Yvon Fluorolog 3 spectrofluorimeter equipped with either a visible photomultiplier tube (PMT) (220–800 nm, R928P; Hamamatsu), a NIR solid-state InGaAs detector cooled to 77 K (800–1600 nm, DSS-IGA020L; ElectroOptical Systems, Inc., USA), or a NIR PMT (950–1650 nm, H10330-75; Hamamatsu). All spectra were corrected for instrumental functions. Luminescence lifetimes were determined under excitation at 355 nm provided by a Nd:YAG laser (YG 980; Quantel), the signals in the visible and the NIR ranges were detected by the R928 or H10330-75 PMTs. The output signals from the detectors were then fed into a 500 MHz bandpass digital oscilloscope (TDS 754C; Tektronix), transferred to a PC and data were processed with the program Origin 8[®]. Luminescence lifetimes are averages of three or more independent measurements. Quantum yields were determined with a Fluorolog 3 spectrofluorimeter based on the absolute method using an integration sphere (GMP SA). Each sample was measured several times varying the position of samples. Estimated experimental error for the determination of quantum yields is estimated as ~10 %.

ARTICLE

Figure 1 (Top) X-ray crystal structure of **Tb-1** in side-view (left), top-down view of the bent [12-MC-4] core (middle), and coordination geometry around the central Tb^{III} ion (right). (Bottom) X-ray crystal structure of **Yb-1** in side-view (left), top-down view of the bent [12-MC-4] core (middle), and coordination geometry around the central Yb^{III} ion (right). Hydrogen atoms and solvent molecules have been omitted for clarity. Color code: Tb purple; Yb cyan; Ga yellow; O red; N blue; C grey.

Absorption Spectroscopy

Solid-state UV-Vis spectra were collected with the help of an Agilent-Cary 5000 spectrophotometer equipped with a Praying Mantis diffuse reflectance accessory. Spectra were collected in reflectance (*R*) mode. The signal of BaSO₄ was used as the reference to establish the baseline. Samples (10 wt. %) were mulled in BaSO₄ (90 wt. %). The spectra were then converted into Kubelka-Munk function to represent more accurately the absorption and plotted vs. wavelength. UV-Vis absorption spectra of the compounds dissolved in CH₃OH were recorded on a Cary 100Bio UV-Vis spectrophotometer in absorbance mode.

ESI-Mass Spectrometry

ESI-MS spectra were collected with a Micromass LCT time-of-flight electrospray mass spectrometer in a negative ion mode at cone voltages ranging from -40 to -70 V on samples dissolved in CH₃OH. Samples were injected via syringe pump. Data were processed with the program MassLynx 4.0.

Results

Syntheses

The reaction between H₃shi and nitrates of Ga^{III} and Ln^{III} (Gd^{III}, Tb^{III}, Dy^{III}, Ho^{III}, Er^{III}, Tm^{III}, and Yb^{III}) in a CH₃OH/pyridine mixture in presence of a small amount of acetic acid affords **Ln-1**

complexes. The general reaction is shown in **Scheme 1**. The synthetic conditions were similar for all the Ln^{III} salts used in the reactions. The complexes with early Ln^{III} ions such as Nd^{III}, Sm^{III}, and Eu^{III} were formed together with a mixture of unidentified complexes and could not be isolated individually.

Scheme 1 Synthesis of **Ln-1** complexes.

X-ray crystal structures

Ln-1 complexes crystallize in two different systems as presented in **Table S2**. The X-ray crystal structures of the two representative molecules, **Tb-1** and **Yb-1**, are shown in **Figure 1**. Both **Tb-1** and **Yb-1** crystallized in the triclinic $P\bar{1}$ space group. The molecule **Tb-1** contains a TbGa₄ core with four [Ga^{III}-N-O] repeating units forming a non-planar [12-MC-4] ring that coordinates the central Tb^{III} ion through the oxygen atoms of the hydroxamate groups. The Tb^{III} ion is further bridged to two Ga^{III} ions located in the ring by two mono-deprotonated H₂shi-

groups and its coordination sphere is filled by a chelating nitrate. The 9-coordinate Tb^{III} ion adopts a coordination geometry close to a tricapped trigonal prism as determined by the program SHAPE (Table S3).⁵⁵ **Yb-1** has a similar non-planar [12-MC-4] core as **Tb-1**. The two mono-deprotonated H₃shi groups bridge the central Yb^{III} and two Ga^{III} ions located in the ring and result in an eight-coordinated Yb^{III} ion that adopts a coordination geometry close to triangular dodecahedron (Table S4). The charge of the **Yb-1** complex is balanced by one nitrate counter anion.

Photophysical properties

Ligand-centered photophysical properties. The UV-Vis absorption spectra of H₃shi and **Ln-1** complexes were collected in CH₃OH solutions. Reflectance spectra of **Ln-1** complexes were collected in the solid state. H₃shi exhibits broad absorption bands in solution resulting from $\pi \rightarrow \pi^*$ transitions in the UV region extending up to 340 nm with an apparent maximum of the band centered at ~300 nm ($\epsilon = 3.9 \cdot 10^3 \text{ M}^{-1} \text{ cm}^{-1}$, Figure 2). **Ln-1** complexes display a slight red shift of their corresponding absorption bands in solution, as shown in Figure 2 for the **Gd-1** complex (Figure S1, top for all **Ln-1** complexes) associated with large molar absorptivities ($\epsilon_{\text{Gd-1}} = 3.29 \cdot 10^4 \text{ M}^{-1} \text{ cm}^{-1}$ at 307 nm) due to the combined contribution of the six ligands derived from H₃shi. Diffuse reflectance spectra of the **Ln-1** complexes (Figure S1, bottom) are dominated by broad bands that correspond to the contribution of the ligands. Sharper bands with significantly lower intensities are observed above wavelength values of 400 nm. These narrow bands can unambiguously be assigned to f-f transitions of the corresponding Ln^{III} ions, and are particularly pronounced for Ho^{III} and Er^{III} ions (Figure S1, bottom). UV-Vis absorption and reflectance spectra of the **Ln-1** complexes are nearly superimposable indicating that the nature of the Ln^{III} ions does not significantly affect the electronic structures of the chromophoric ligands and the corresponding positions of the ligand-centered bands.

Figure 2 Absorption spectra of the **Gd-1** MC recorded in CH₃OH solutions (black trace, left scale) and H₃shi (blue trace, right scale).

An important factor that is assumed to play a significant role in the sensitization of luminescent Ln^{III} ions in their complexes is the energy position of the triplet state (³T) of the organic ligands. The energy of the ³T level in **Ln-1** can be estimated from

the phosphorescence spectrum of the corresponding Gd^{III} complex. Phosphorescence intensity is promoted due to heavy-atom and paramagnetic effects induced by the Gd^{III} ion.⁵⁶ In addition, the accepting electronic level of Gd^{III} is located at sufficiently high energy (~32 000 cm⁻¹)⁵⁷ to prevent its population through electronic levels of most organic ligands. **Gd-1** MC exhibits the phosphorescence signal shown in Figure 3. The spectrum was recorded in time-resolved mode in the solid state at 77 K upon excitation at 325 nm and using a 100 μs delay after the excitation flash to remove any fluorescence signal arising from the singlet state. The Gaussian decomposition of the phosphorescence spectrum allowed to estimate the energy of the 0-0 transition, that is located at 461.6 nm (~21 660 cm⁻¹) and represents the energy of the triplet state.

Figure 3 Phosphorescence spectrum of the **Gd-1** MC measured in the solid state under excitation at 325 nm (77 K, 100 μs delay after the excitation flash, black trace) and its Gaussian decomposition (colored traces).

Figure 4 Corrected and normalized excitation spectra of the **Ln-1** MCs in the solid state upon monitoring the main transitions of the corresponding Ln^{III} ions at room temperature.

Lanthanide-centered photophysical properties. Excitation and emission spectra of all **Ln-1** complexes were collected in the solid state. Since Ln^{III} ions exhibit characteristic emission bands, excitation spectra can be obtained by monitoring the specific f-f transitions of the corresponding Ln^{III} ion.

The excitation spectra of the **Ln-1** complexes recorded in the solid state (Figure 4) are similar to the corresponding absorption and reflectance spectra (Figure S1) and exhibit broad bands in the range 250 – 400 nm. This observation indicates that the sensitization of the five Ln^{III} tested here is occurring in each case

through the electronic state located on the organic chromophoric part of the MCs. A slight extension towards longer wavelengths is observed due to the saturation effects (Figure S2).⁵⁸ In addition, sharper bands with lower intensity that can be attributed to f-f transitions are detected

Figure 5 Corrected and normalized emission spectra of the **Ln-1** MCs in the solid state under excitation at 350 nm at room temperature.

for Er^{III} , Ho^{III} , and Dy^{III} MCs. The study of the excitation spectra allows for the determination of the excitation wavelengths of **Ln-1** complexes corresponding to the highest emission intensities, which are ~350 nm for the solid samples. Thus, emission spectra were collected for **Ln-1** samples in the solid state upon excitation at 350 nm at room temperature (Figure 5). Characteristic emissions of Ln^{III} ions in the visible (Tb^{III}), NIR (Ho^{III} , Er^{III} , Yb^{III}) or both (Dy^{III}) regions were observed. Luminescence lifetimes (τ_{obs}) and absolute Ln^{III} -centred quantum yields under ligands excitation (Q_{Ln}^{L}) were also acquired as quantitative luminescence data; the results are summarized in Table 1.

Tb-1 exhibits green emission resulting from the $^5\text{D}_4 \rightarrow ^7\text{F}_j$ ($J = 6 - 0$) transitions. The four prominent bands centered at ~493, 545, 589 and 627 nm correspond to $^5\text{D}_4 \rightarrow ^7\text{F}_{6,5,4,3}$ transitions whereas the other three transitions $^5\text{D}_4 \rightarrow ^7\text{F}_{2,1,0}$ are of significantly lower intensity and observed in the range 640 – 700 nm. The relative integral intensities of different transitions for **Tb-1** are given in Table S2. The solid state sample has a Q_{Tb}^{L} value of 11.3% and a τ_{obs} of 509 μs .

Dy-1 exhibits a number of bands across the visible and the NIR regions arising from the $^4\text{F}_{9/2} \rightarrow ^6\text{H}_j$ ($J = 15/2 - 5/2$) and $^4\text{F}_{9/2} \rightarrow ^6\text{F}_j$ ($J = 9/2 - 3/2$) electronic transitions. In the visible region, the spectrum is dominated by two bands centered at 483 and 574 nm corresponding to the $^4\text{F}_{9/2} \rightarrow ^6\text{H}_{15/2, 13/2}$ transitions. These bands are responsible for the apparent yellow-green emission of this MC. In the NIR region, beside the high-intensity band at 840 nm originating from the $^4\text{F}_{9/2} \rightarrow ^6\text{F}_{9/2}, ^6\text{H}_{7/2}$ transitions, the emission bands at 937, 1005, 1177 and 1269 nm corresponding to $^4\text{F}_{9/2} \rightarrow ^6\text{H}_{5/2}, ^4\text{F}_{9/2} \rightarrow ^6\text{F}_{7/2}, ^4\text{F}_{9/2} \rightarrow ^6\text{F}_{5/2}$ and $^4\text{F}_{9/2} \rightarrow ^6\text{F}_{3/2}$ transitions can be detected. The residual broad ligand-centered emission signal is observed in the 375 – 550 nm range and can be explained by an incomplete energy transfer to Dy^{III} or an

energy back transfer from Dy^{III} to the ligands due to the close energy difference between the $^4\text{F}_{9/2}$ and the ^3T levels. Measured Dy^{III} -centered quantum yield values of the solid state sample in the visible and the NIR regions are 0.22 and 0.013 %, respectively. The total quantum yield of **Dy-1** in the visible range is 0.23 %, so that the ligand contribution to the total emission can be estimated to 3.9 %.

Ho-1 exhibits a NIR emission of relatively low intensity with maxima at 978 and 1188 nm due to the $^5\text{F}_5 \rightarrow ^5\text{I}_7$ and $^5\text{I}_6 \rightarrow ^5\text{I}_8$ transitions, respectively. The Q_{Ho}^{L} value of **Ho-1** in the solid state is $1.6 \cdot 10^{-3}$ % and the observed lifetime is equal to 32 ns.

Er-1 exhibits a relatively broad NIR emission band in the range of 1500 – 1620 nm corresponding to the $^4\text{I}_{13/2} \rightarrow ^4\text{I}_{15/2}$ transition. The Er^{III} -centered quantum yield is similar to the one of **Ho-1**, $1.55 \cdot 10^{-3}$ %. In contrast, the observed lifetime is significantly longer with a value of 220 ns.

Tm-1 does not exhibit any emission due to f-f transitions or the emission signal is too weak to be detected.

Yb-1 exhibits a NIR emission band in the range 900 – 1150 nm arising from the $^2\text{F}_{5/2} \rightarrow ^2\text{F}_{7/2}$ transition. The Q_{Yb}^{L} of the solid state sample is 0.216 %, and the observed luminescence lifetime τ_{obs} is 2.99 μs . Photophysical properties of this sample were also studied in CH_3OH and CD_3OD solutions (Figure 6). It was found that the crystal field splitting of the $^2\text{F}_{5/2} \rightarrow ^2\text{F}_{7/2}$ transition is different for the sample in solution compared to the one in the solid state. Such behavior reflects changes in coordination environment around Yb^{III} between the two phases. Indeed, calculations of the hydration number taking into account the values of observed lifetimes collected in CH_3OH and CD_3OD and using the well-established phenomenological equation⁵⁹ confirmed the coordination of one solvent molecule to Yb^{III} . The quantum yield value in CD_3OD is 12-fold higher (2.55

%) than the one obtained in the solid state, however it decreases to 0.12 % in CH₃OH.

Radiative lifetime, intrinsic quantum yield (Q_{Yb}^{Yb}) and sensitization efficiency (η_{sens}) of Yb-1. Radiative lifetime (τ_{rad}) is the lifetime of an electronic state when only radiative processes depopulate this level.

Figure 6 Corrected and normalized emission spectra of the Yb-1 MC collected in the solid state (λ_{ex} = 350 nm, black trace) and in methanol solutions (λ_{ex} = 320 nm, 0.5 mM, red trace) at room temperature.

In the case of Yb-1, τ_{rad} can be calculated from the absorption spectrum in the range of $^2F_{5/2} \leftarrow ^2F_{7/2}$ transition (Figure 7) using the modified Einstein's equation:⁶⁰

$$\frac{1}{\tau_{rad}} = 2303 \times \frac{8\pi c n^2 \tilde{\nu}_m^2 (2J+1)}{N_A (2J'+1)} \int \epsilon(\tilde{\nu}) d\tilde{\nu} \quad (1a)$$

$$\tilde{\nu}_m = \frac{\int \tilde{\nu} \epsilon(\tilde{\nu}) d\tilde{\nu}}{\int \epsilon(\tilde{\nu}) d\tilde{\nu}} \quad (1b)$$

where c is the speed of light in centimeters per second, n is the refractive index, N_A is the Avogadro's number, J and J' are the quantum numbers for the ground and excited states, respectively, $\int \epsilon(\tilde{\nu}) d\tilde{\nu}$ is the integrated spectrum of the f-f transition, $\tilde{\nu}_m$ is the barycenter of the transition. It is worth noting that the very low molar absorptivity ($< 6 \text{ M}^{-1} \text{ cm}^{-1}$) is characteristic of free Ln^{III} ions. The obtained value of the radiative lifetime of Yb-1 is given in Table 2.

Figure 7 Absorption spectrum of the Yb-1 MC in the range of $^2F_{5/2} \leftarrow ^2F_{7/2}$ transition in CH₃OH (1.8 mM) at room temperature.

Having τ_{rad} values in hand together with the values of observed lifetimes and Q_{Yb}^L , intrinsic quantum yields (Q_{Yb}^{Yb}) and

sensitization efficiencies (η_{sens}) can be calculated using the following equations (2a, 2b):

$$Q_{Yb}^{Yb} = \frac{\tau_{obs}}{\tau_{rad}} \times 100\% \quad (2a)$$

$$\eta_{sens} = \frac{Q_{Yb}^L}{Q_{Yb}^{Yb}} \times 100\% \quad (2b)$$

The results are summarized in Table 2 and compared with the values reported previously for YbGa₄(shi)₄(OBz)₄²⁶ and YbZn₁₆(quinHA)₁₆²⁵ MCs.

Discussion

Syntheses

This work focuses on expanding the available luminescent structure types for Ga^{III}shi metallacrowns and seeks to rationalize the photophysics associated with different Ln^{III} environments in this family of molecules. The direct synthesis of MCs is often not straightforward. Therefore, in this work, the reactions between H₃shi and Ga^{III} and a series of Ln^{III} salts were screened under a variety of experimental conditions: solvent, stoichiometry, presence or absence of simple carboxylic acids, etc. Reactions of Ga(NO₃)₃·xH₂O, Ln(NO₃)₃·yH₂O and H₃shi in a 4:1:4 molar ratio in CH₃OH/pyridine led to the isolation of Ln-1 MCs. The 4:1:4 ratio implies that the Ga^{III} and Ln^{III} salts are in slight excess but the increase of the amount of H₃shi did not improve the yield further. The addition of a small amount of acetic acid was found to be crucial to obtain high quality single crystals of Ln-1 MCs. The reactions also showed differences in behavior between the early and late Ln^{III} ions. With the same synthetic conditions described in the experimental section, the early Ln^{III} ions (Nd^{III}, Sm^{III}, Eu^{III}) did not form pure Ln-1 products. The ions located in the middle of the series (Gd^{III}, Tb^{III}, Dy^{III}, Ho^{III}) form complexes in which the Ln^{III} is nine-coordinated. For the complexes formed with the smallest Ln^{III} of the series (Er^{III}, Tm^{III}, Yb^{III}), the Ln^{III} are eight-coordinated.

Table 1 Photophysical data for Ln-1 complexes at room temperature.^a

Complex	$\Delta E \text{ (cm}^{-1}\text{)}^b$	$\tau_{obs} \text{ (}\mu\text{s)}^c$	$Q_{Ln}^L \text{ (}\%)^d$
Tb-1	1 260	509(7)	11.3(5)
Dy-1	560	3.36(6)	0.222(6) ^e
Ho-1	6 160	0.032(1)	$1.6(1) \cdot 10^{-3}$
Er-1	14 960	0.220(3)	$1.55(3) \cdot 10^{-3}$
Yb-1	11 360	2.99(2)	0.216(6)

^a 2σ values are given between parentheses. Relative errors: τ_{obs} , $\pm 2\%$; Q_{Ln}^L , $\pm 10\%$. ^b $\Delta E(^3T - ^3F_4)$ is the energy gap between the ligand triplet state ($^3T = 21\,660 \text{ cm}^{-1}$) and Ln^{III} emissive states: $E^{Tb}(^5D_4) = 20\,400 \text{ cm}^{-1}$, $E^{Dy}(^4F_{9/2}) = 21\,100 \text{ cm}^{-1}$, $E^{Ho}(^5F_5) = 15\,500 \text{ cm}^{-1}$, $E^{Er}(^4I_{13/2}) = 6\,700 \text{ cm}^{-1}$, $E^{Yb}(^2F_{5/2}) = 10\,300 \text{ cm}^{-1}$.⁶¹⁻⁶³ ^c $\lambda_{ex} = 355 \text{ nm}$. ^d $\lambda_{ex} = 350 \text{ nm}$. ^e Total quantum yield including ligand-centered emission is equal to 0.231(8) %.

Table 2 Photophysical properties of the **Yb-1** MC in solution and comparison with other Yb^{III} MCs.^a

Complex	Solvent	τ_{obs} (μs)	τ_{rad} (ms) ^b	$Q_{\text{Yb}}^{\text{Yb}}$ (%)	Q_{Yb}^{L} (%)	η_{sens} (%)
Yb-1	CD ₃ OD	27.4(1)	0.59	4.6	2.55(5)	55
	CH ₃ OH	1.72(1)	0.59	0.29	0.123(2)	42
YbGa₄ ^c	CD ₃ OD	36.6(1)	0.53	6.9	4.29(1)	62
	CH ₃ OH	2.06(4)	0.53	0.39	0.26(1)	67
YbZn₁₆ ^d	CD ₃ OD	150.7(2)	0.68	22.2	2.88(2)	13
	CH ₃ OH	14.88(1)	0.68	2.2	0.25(1)	11

^a Relative errors: τ_{obs} , $\pm 2\%$; $Q_{\text{Yb}}^{\text{Yb}}$, $\pm 10\%$; τ_{rad} , $\pm 10\%$; Q_{Yb}^{L} , $\pm 12\%$; η_{sens} , $\pm 22\%$. ^b Calculated using eq. 1 according to ref. ⁶⁰. For CD₃OD solutions, τ_{rad} was recalculated taking into account the difference in refractive indexes, $n(\text{CD}_3\text{OD}) = 1.326$. ^c YbGa₄(shi)₄(OBz)₄, From ref. ²⁶. ^d YbZn₁₆(quinHA)₁₆, From ref. ²⁵.

Luminescent properties

Ln-1 complexes formed with Tb^{III}, Dy^{III}, Ho^{III}, Er^{III}, and Yb^{III} in the solid state exhibit characteristic emissions arising from f-f transitions in the visible and/or the NIR ranges upon excitation into ligand-centered levels at 350 nm (Figure 5). In the emission spectrum of the **Dy-1** MC, in addition to the Dy^{III}-centered sharp transitions, the residual broad-band ligands emission is observed reflecting an incomplete $^3\text{T} \rightarrow ^4\text{F}_{9/2}$ chromophore to Dy^{III} energy transfer and/or the existence of a back $^4\text{F}_{9/2} \leftarrow ^3\text{T}$ energy transfer. Indeed, if long-lived triplet states are considered to be the main feeding levels for Ln^{III} ions, the back energy transfer may occur when the ^3T state is too close to the energy of the emitting level of the Ln^{III} ion (E^{Ln}). It is assumed that, when the energy difference $\Delta E(^3\text{T}-E^{\text{Ln}})$ is $< 2000 \text{ cm}^{-1,21}$, there is a high possibility of back energy transfer processes. In the case of **Dy-1**, this energy difference $\Delta E(^3\text{T}-^4\text{F}_{9/2})$ is only 560 cm^{-1} , therefore back energy transfer is highly probable for this MC. The same is true for **Tb-1** with $\Delta E(^3\text{T}-^4\text{D}_4)$ equal to 1260 cm^{-1} . For **Ln-1** MCs formed with all other Ln^{III}, ΔE is $> 6000 \text{ cm}^{-1}$, thus preventing a back energy transfer to the ^3T level. It should be noted that the position of the triplet state in **Ln-1** ($21\,660 \text{ cm}^{-1}$) is very close in energy to those reported previously for the monomeric LnGa₄(shi)₄(OBz)₄ ($^3\text{T} = 22\,170 \text{ cm}^{-1}$)²⁶ and for the dimeric Ln₂Ga₈(shi)₈(iph)₄ ($^3\text{T} = 21\,980 \text{ cm}^{-1}$)²⁸ MCs assembled using salicylhydroxamic acid. Nevertheless, Ln^{III}-centered quantum yield values collected under ligands excitation (Q_{Ln}^{L}) and observed lifetimes (τ_{obs}) (Table 1) of **Ln-1** MCs are lower than these recorded for LnGa₄(shi)₄(OBz)₄²⁶ or Ln₂Ga₈(shi)₈(iph)₄.²⁸ In the case of **Tb-1** and **Dy-1**, such behavior could be explained by the enhanced back energy transfer processes, while for **Ln-1** MCs formed with other Ln^{III}, the reason most probably lies in the structural feature of **Ln-1** as explained below. In general, Ln^{III}-centered quantum yield values collected under ligands excitation (Q_{Ln}^{L}) and observed luminescence lifetimes (τ_{obs}) (Table 1) of **Ln-1** MCs are following the energy gap law, i.e. the smaller the energy gap between the lowest level of the emitting and the highest level of the ground states, the higher is the probability of the quenching of Ln^{III} through overtones of high energy vibrations, like O–H, N–H, C–H.⁶⁴ The highest Q_{Ln}^{L} and the longest τ_{obs} values are observed for **Tb-1** MC, while lower values were measured for **Dy-1**, **Yb-1** and **Er-1**. Ho^{III} ions coordinated in complexes with organic ligands

usually exhibit very weak luminescence intensities.^{65–68} Nevertheless, for the **Ho-1** MC, quantitative parameters could be accurately acquired (Table 1).

If one considers the environment around the Ln^{III} ions in **Ln-1**, the presence of two incompletely deprotonated H₂shi[−] ligands implies N–H and O–H groups being in close proximity to the Ln^{III}. These high-energy oscillators are the main sources of non-radiative deactivations, in particular for Ln^{III} with small energy gaps between the emitting and the ground levels.^{21, 23} Such feature of **Ln-1** MCs could explain their lower Q_{Ln}^{L} and shorter τ_{obs} values compared to the previously reported Ln^{III}/Ga^{III} MCs.^{26, 28} Moreover, the presence of water and methanol solvent molecules in the lattice of **Ln-1** and intermolecular interactions due to π - π stacking ($d = 3.55 \text{ \AA}$ for **Yb-1**, Figure S3) could serve as additional sources of non-radiative deactivations of Ln^{III} ions and induces the lowering of their luminescence.

To quantitatively assess the parameters that affect Q_{Ln}^{L} , sensitization efficiencies and intrinsic quantum yields have to be estimated. Q_{Ln}^{L} can be obtained by the direct excitation of Ln^{III} into f-f transitions; however, such measurements are often tricky due to the low molar absorptivities of f-f transitions. Another method to obtain Q_{Ln}^{L} involves the determination of τ_{obs} and τ_{rad} according to eq. 2a. Observed luminescence lifetime can be routinely measured whereas the determination of τ_{rad} is not as straightforward. It is worth noting here that τ_{rad} is specific for the Ln^{III} coordination environment and the electronic transition involved in the emission.⁶⁹ This parameter is getting an increased attention recently as controlling τ_{rad} has been shown to be a promising strategy to significantly improve efficiencies of visible- and NIR-emitting Ln^{III} complexes.^{70–72} Radiative lifetime can be estimated from the modified Einstein's equation (eq. 1) if the absorption spectrum that corresponds to the emission one is known. Among all studied **Ln-1**, such procedure could be applied only for **Yb-1** in methanol solution. The value of τ_{rad} equal to 0.59 ms was found (Table 2). This parameter is very close to the τ_{rad} value reported for YbGa₄(shi)₄(OBz)₄ (0.53 ms)²⁶ and slightly shorter than the one for YbZn₁₆(quinHA)₁₆.²⁵ Taking into account τ_{obs} and $Q_{\text{Yb}}^{\text{Yb}}$ values in the corresponding solvents, Q_{Yb}^{L} were estimated to be 4.6% in CD₃OD and 0.29% in CH₃OH with sensitization efficiencies of 55% and 42%, respectively. In comparison to the previously reported Yb^{III} MCs,^{25, 26} **Yb-1** exhibits η_{sens} four times higher than the one for YbZn₁₆(quinHA)₁₆ and only slightly lower than the one of YbGa₄(shi)₄(OBz)₄. However, the $Q_{\text{Yb}}^{\text{Yb}}$ value for **Yb-1** is 5–7 times lower than in the case of YbZn₁₆(quinHA)₁₆ and 1.5 times lower than for YbGa₄(shi)₄(OBz)₄. As a result, **Yb-1** has a Q_{Yb}^{L} value in CD₃OD which is only slightly lower than the one for YbZn₁₆(quinHA)₁₆ but 1.7 times smaller than the one for YbGa₄(shi)₄(OBz)₄. In respect to luminescence efficiency, defined as $Q_{\text{Yb}}^{\text{L}} \times \epsilon$, the lower Q_{Yb}^{L} of **Yb-1** in solution compared to YbGa₄(shi)₄(OBz)₄ can be almost fully compensated by the 1.5 times higher molar absorptivity of the former due to the contribution of six ligands instead of four shi^{3−} ligands for the latter.

Conclusions

Via direct synthesis, we have obtained and fully characterized a new series of visible and NIR-emitting LnGa_4 MCs. Factors that affect luminescence intensities such as the energy levels of triplet states, molar absorptivities, non-radiative deactivation through vibronic coupling with overtones of O-H, N-H, and C-H oscillators, and crystal packing were discussed in details. In conclusion, designing MCs is a fully innovative and versatile approach to create lanthanide(III) complexes with high luminescence intensities. With a broad variety of available chromophoric structures, ligands that can be used to form MCs, there is an unprecedented number of possibilities to construct several families of lanthanide(III)-based luminescent MCs with controlled properties that can be used for a broad range of applications such as bioanalysis and bioimaging.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

The research leading to these results have received funding from the European Community's Seventh Framework Program (IRSES Metallacrown - FP7/2007-2013) under grant agreement n° 611488. This research was also supported in part by the National Science Foundation under grant CHE-1361779, La Ligue contre le Cancer and La Région Centre. S.P. acknowledges support from Institut National de la Santé et de la Recherche Médicale (INSERM).

References

1. M. Chalfie, Y. Tu, G. Euskirchen, W. Ward and D. Prasher, *Science*, 1994, **263**, 802-805.
2. X.-F. Zhang, J. Zhang and L. Liu, *J. Fluoresc.*, 2014, **24**, 819-826.
3. J. Yang, Y. Zhang, S. Gautam, L. Liu, J. Dey, W. Chen, R. P. Mason, C. A. Serrano, K. A. Schug and L. Tang, *Proc. Nat. Acad. Sci.*, 2009, **106**, 10086-10091.
4. L. Martínez Maestro, C. Jacinto, U. Rocha, M. Carmen Iglesias-de la Cruz, F. Sanz-Rodríguez, A. Juarranz, J. García Solé and D. Jaque, *J. Appl. Phys.*, 2012, **111**, 023513.
5. S. Banerjee, C. D. Malliakas, J. I. Jang, J. B. Ketterson and M. G. Kanatzidis, *J. Am. Chem. Soc.*, 2008, **130**, 12270-12272.
6. V. W.-W. Yam and K. M.-C. Wong, *Chem. Commun.*, 2011, **47**, 11579-11592.
7. L. Armelao, S. Quici, F. Barigelletti, G. Accorsi, G. Bottaro, M. Cavazzini and E. Tondello, *Coord. Chem. Rev.*, 2010, **254**, 487-505.
8. T. N. Nguyen, F. M. Ebrahim and K. C. Stylianou, *Coord. Chem. Rev.*, 2018, **377**, 259-306.
9. L. D. Carlos, R. A. S. Ferreira, V. de Zea Bermudez, B. Julian-Lopez and P. Escrivano, *Chem. Soc. Rev.*, 2011, **40**, 536-549.
10. J.-C. G. Bünzli, *J. Lumin.*, 2016, **170**, 866-878.
11. J.-C. G. Bünzli and A.-S. Chauvin, in *Handbook on the Physics and Chemistry of Rare Earths*, eds. J.-C. G. Bünzli and V. K. Pecharsky, Elsevier Science, B.V., Amsterdam, 2013, vol. 44, Ch. 261, pp. 169-282.
12. H. Dong, S. R. Du, X. Y. Zheng, G. M. Lyu, L. D. Sun, L. D. Li, P. Z. Zhang, C. Zhang and C. H. Yan, *Chem. Rev.*, 2015, **115**, 10725-10815.
13. K. Binnemans, *Chem. Rev.*, 2009, **109**, 4283-4374.
14. J. Feng and H. J. Zhang, *Chem. Soc. Rev.*, 2013, **42**, 387-410.
15. M. Sy, A. Nonat, N. Hildebrandt and L. J. Charbonniere, *Chem. Commun.*, 2016, **52**, 5080-5095.
16. I. Martinić, S. V. Eliseeva and S. Petoud, *J. Lumin.*, 2017, **189**, 19-43.
17. G. X. Bai, M. K. Tsang and J. H. Hao, *Adv. Funct. Mater.*, 2016, **26**, 6330-6350.
18. J.-C. G. Bünzli, *Chem. Rev.*, 2010, **110**, 2729-2755.
19. T. N. Nguyen, G. Capano, A. Gładysiak, F. M. Ebrahim, S. V. Eliseeva, A. Chidambaram, B. Valizadeh, S. Petoud, B. Smit and K. C. Stylianou, *Chem. Commun.*, 2018, **54**, 6816-6819.
20. F. M. Ebrahim, T. N. Nguyen, S. Shyshkanov, A. Gładysiak, P. Favre, A. Zacharia, G. Itkos, P. J. Dyson and K. C. Stylianou, *J. Am. Chem. Soc.*, 2019, **141**, 3052-3058.
21. J.-C. G. Bünzli and S. V. Eliseeva, in *Comprehensive Inorganic Chemistry II*, ed. V. W.-W. Yam, Elsevier B.V., Amsterdam, 2013, vol. 8, ch. 8.08, pp. 339-398.
22. H. Uh and S. Petoud, *C. R. Chim*, 2010, **13**, 668-680.
23. J.-C. G. Bünzli, *Coord. Chem. Rev.*, 2015, **293-294**, 19-47.
24. J. Jankolovits, C. M. Andolina, J. W. Kampf, K. N. Raymond and V. L. Pecoraro, *Angew. Chem. Int. Ed.*, 2011, **50**, 9660-9664.
25. E. R. Trivedi, S. V. Eliseeva, J. Jankolovits, M. M. Olmstead, S. Petoud and V. L. Pecoraro, *J. Am. Chem. Soc.*, 2014, **136**, 1526-1534.
26. C. Y. Chow, S. V. Eliseeva, E. R. Trivedi, T. N. Nguyen, J. W. Kampf, S. Petoud and V. L. Pecoraro, *J. Am. Chem. Soc.*, 2016, **138**, 5100-5109.
27. J. C. Lutter, S. V. Eliseeva, J. W. Kampf, S. Petoud and V. L. Pecoraro, *Chem. Eur. J.*, 2018, **24**, 10773-10783.
28. T. N. Nguyen, C. Y. Chow, S. V. Eliseeva, E. R. Trivedi, J. W. Kampf, I. Martinić, S. Petoud and V. L. Pecoraro, *Chem. Eur. J.*, 2018, **5**, 1031-1035.
29. I. Martinić, S. V. Eliseeva, T. N. Nguyen, F. Foucher, D. Gosset, F. Westall, V. L. Pecoraro and S. Petoud, *Chem. Sci.*, 2017, **8**, 6042-6050.
30. I. Martinić, S. V. Eliseeva, T. N. Nguyen, V. L. Pecoraro and S. Petoud, *J. Am. Chem. Soc.*, 2017, **139**, 8388-8391.
31. G. Mezei, C. M. Zaleski and V. L. Pecoraro, *Chem. Rev.*, 2007, **107**, 4933-5003.
32. A. D. Cutland, R. G. Malkani, J. W. Kampf and V. L. Pecoraro, *Angew. Chem. Int. Ed.*, 2000, **39**, 2689-2691.
33. C.-S. Lim, J. Jankolovits, P. Zhao, J. W. Kampf and V. L. Pecoraro, *Inorg. Chem.*, 2011, **50**, 4832-4841.
34. J. T. Grant, J. Jankolovits and V. L. Pecoraro, *Inorg. Chem.*, 2012, **51**, 8034-8041.
35. C. Sgarlata, A. Giuffrida, E. R. Trivedi, V. L. Pecoraro and G. Arena, *Inorg. Chem.*, 2017, **56**, 4771-4774.
36. J. Jankolovits, C. S. Lim, G. Mezei, J. W. Kampf and V. L. Pecoraro, *Inorg. Chem.*, 2012, **51**, 4527-4538.
37. J. Jankolovits, A. D. C. Van-Noord, J. W. Kampf and V. L. Pecoraro, *Dalton Trans.*, 2013, **42**, 9803-9808.
38. H. Piotrowski, K. Polborn, G. Hilt and K. Severin, *J. Am. Chem. Soc.*, 2001, **123**, 2699-2700.
39. C. Y. Chow, H. Bolvin, V. E. Campbell, R. Guillot, J. W. Kampf, W. Wernsdorfer, F. Gendron, J. Autschbach, V. L. Pecoraro and T. Mallah, *Chem. Sci.*, 2015, **6**, 4148-4159.
40. T. T. Boron, J. C. Lutter, C. I. Daly, C. Y. Chow, A. H. Davis, A. Nimthong-Roldán, M. Zeller, J. W. Kampf, C. M. Zaleski and V. L. Pecoraro, *Inorg. Chem.*, 2016, **55**, 10597-10607.

41. C. M. Zaleski, S. Tricard, E. C. Depperman, W. Wernsdorfer, T. Mallah, M. L. Kirk and V. L. Pecoraro, *Inorg. Chem.*, 2011, **50**, 11348-11352.
42. C. M. Zaleski, E. C. Depperman, J. W. Kampf, M. L. Kirk and V. L. Pecoraro, *Inorg. Chem.*, 2006, **45**, 10022-10024.
43. C. M. Zaleski, E. C. Depperman, C. Dendrinou-Samara, M. Alexiou, J. W. Kampf, D. P. Kessissoglou, M. L. Kirk and V. L. Pecoraro, *J. Am. Chem. Soc.*, 2005, **127**, 12862-12872.
44. C. M. Zaleski, E. C. Depperman, J. W. Kampf, M. L. Kirk and V. L. Pecoraro, *Angew. Chem. Int. Ed.*, 2004, **43**, 3912-3914.
45. T. T. Boron, J. W. Kampf and V. L. Pecoraro, *Inorg. Chem.*, 2010, **49**, 9104-9106.
46. P. Happ and E. Rentschler, *Dalton Trans.*, 2014, **43**, 15308-15312.
47. P. Happ, C. Plenck and E. Rentschler, *Coord. Chem. Rev.*, 2015, **289-290**, 238-260.
48. C. Y. Chow, R. Guillot, E. Rivière, J. W. Kampf, T. Mallah and V. L. Pecoraro, *Inorg. Chem.*, 2016, **55**, 10238-10247.
49. M. S. Muravyeva, G. S. Zabrodina, M. A. Samsonov, E. A. Kluev, A. A. Khrapichev, M. A. Katkova and I. V. Mukhina, *Polyhedron*, 2016, **114**, 165-171.
50. M. A. Katkova, G. S. Zabrodina, M. S. Muravyeva, A. S. Shavyrin, E. V. Baranov, A. A. Khrapichev and S. Y. Ketkov, *Eur. J. Inorg. Chem.*, 2015, 5202-5208.
51. T. N. Parac-Vogt, A. Pacco, P. Nockemann, S. Laurent, R. N. Muller, M. Wickleder, G. Meyer, L. Vander Elst and K. Binnemans, *Chem. Eur. J.*, 2006, **12**, 204-210.
52. J. Jankolovits, C. M. Andolina, J. W. Kampf, K. N. Raymond and V. L. Pecoraro, *Angew. Chem. Int. Ed.*, 2011, **50**, 9660-9664.
53. G. M. Sheldrick, *Acta. Cryst. A*, 2008, **64**, 112-122.
54. A. L. Spek, *Platon, A Multipurpose Crystallographic Tool*, Utrecht University; Utrecht, The Netherlands, 2001.
55. A. Ruiz-Martinez, D. Casanova and S. Alvarez, *Dalton Trans.*, 2008, DOI: 10.1039/B718821H, 2583-2591.
56. S. Tobita, M. Arakawa and I. Tanaka, *J. Phys. Chem.*, 1985, **89**, 5649-5654.
57. W. T. Carnall, P. R. Fields and K. Rajnak, *J. Chem. Phys.*, 1968, **49**, 4443-4446.
58. M. Ganapathi, S. V. Eliseeva, N. R. Brooks, D. Socol, J. Fransaer and K. Binnemans, *J. Mater. Chem.*, 2012, **22**, 5514-5522.
59. A. Beeby, I. M. Clarkson, R. S. Dickens, S. Faulkner, D. Parker, L. Royle, A. S. de Sousa, J. A. G. Williams and M. Woods, *J. Chem. Soc., Perkin Trans. 2*, 1999, 493-503.
60. M. H. V. Werts, R. T. F. Jukes and J. W. Verhoeven, *Phys. Chem. Chem. Phys.*, 2002, **4**, 1542-1548.
61. W. T. Carnall, P. R. Fields and K. Rajnak, *J. Chem. Phys.*, 1968, **49**, 4450-4455.
62. W. T. Carnall, P. R. Fields and K. Rajnak, *J. Chem. Phys.*, 1968, **49**, 4447-4449.
63. W. T. Carnall, P. R. Fields and K. Rajnak, *J. Chem. Phys.*, 1968, **49**, 4424-4442.
64. J.-C. Bünzli and S. Eliseeva, in *Lanthanide Luminescence*, eds. P. Hänninen and H. Härmä, Springer Berlin Heidelberg, 2011, vol. 7, ch. 3, pp. 1-45.
65. G. L. Law, T. A. Pham, J. D. Xu and K. N. Raymond, *Angew. Chem. Int. Ed.*, 2012, **51**, 2371-2374.
66. Z. Ahmed and K. Iftikhar, *J. Phys. Chem. A*, 2013, **117**, 11183-11201.
67. N. Wartenberg, O. Raccurt, E. Bourgeat-Lami, D. Imbert and M. Mazzanti, *Chem. Eur. J.*, 2013, **19**, 3477-3482.
68. A. F. Martins, S. V. Eliseeva, H. F. Carvalho, J. M. Teixeira, C. T. Paula, P. Hermann, C. Platas-Iglesias, S. Petoud, E. Toth and C. F. Geraldès, *Chem. Eur. J.*, 2014, **20**, 14834-14845.
69. J.-C. G. Bünzli, A.-S. Chauvin, H. K. Kim, E. Deiters and S. V. Eliseeva, *Coord. Chem. Rev.*, 2010, **254**, 2623-2633.
70. C. Doffek and M. Seitz, *Angew. Chem. Int. Ed.*, 2015, **54**, 9719-9721.
71. N. M. Shavaleev, S. V. Eliseeva, R. Scopelliti and J.-C. G. Bünzli, *Inorg. Chem.*, 2015, **54**, 9166-9173.
72. N. M. Shavaleev, R. Scopelliti, F. Gumy and J.-C. G. Bünzli, *Inorg. Chem.*, 2009, **48**, 7937-7946.