Layered Double Hydroxides and LDH-derived materials in chosen environmental applications: a review

Dylan Chaillot^{1,2}, Simona Bennici^{1,2,}, Jocelyne Brendlé^{1,2}*

¹ Université de Haute-Alsace, CNRS, IS2M UMR 7361, F-68100 Mulhouse, France

² Université de Strasbourg, France

*Corresponding author: simona.bennici@uha.fr

Keywords: Hydrotalcite, layered double hydroxides, materials, synthesis, applications, industrial, environmental.

Abstract

With increasing global warming awareness, layered double hydroxides (LDHs), hydrotalcites and their related materials are key components to reduce the environmental impact of human activities. Such materials can be synthesized quickly with high efficiency by using different synthesis processes. Moreover, their properties tunability is appreciated in various industrial processes. Regarding their physical and structural properties, such materials can be applied in environmental applications such as the adsorption of atmospheric and aqueous pollutants, the hydrogen production, or the formation of 5-Hydroxymethylfurfural (5-HMF). After a first part dedicated to the synthesis processes of hydrotalcites, the present review reports on specific environmental applications chosen as example in various fields (green chemistry and depollution) that have gained increasing interest in the last decades, enlightening the links between structural properties, synthesis route and application using the lamellar materials.

Introduction

Layered double hydroxides, also called LDHs or anionic clays, are particular lamellar materials made of octahedral sheets composed of metallic cations in the center of the octahedra. These materials can be found in nature, and present the brucite ($\text{Mg}(\text{OH})_2$) structure with divalent cations M^{II} (Mg^{2+} or Cu^{2+} for example) partly substituted by trivalent cations M^{III} (such as Al^{3+} or Fe^{3+}). This partial substitution induces a positive charge deficit that is compensated by anions, such as carbonates, located in the interlayer space along with water molecules. The easily accessible interlayer is one of the sources of the anion exchange capacity of the compounds, and of its ability to capture and exchange anions. This characteristic is almost unique for inorganic materials, indeed clay minerals exhibit cation exchange capacity. Thanks to these characteristics, they are appreciated for their versatility, simplicity of tailoring and low cost. The general formula of LDHs can be described as follows:

where M^{II} and M^{III} respectively represent the metallic divalent (Mg^{2+} , Cu^{2+} , Zn^{2+}) and trivalent (Al^{3+} , Fe^{3+}) cations, A the compensating anion, and x and m depend on the substitution rate between M^{II} and M^{III} cations.

Hydrotalcites are particular LDHs (characterized by a Mg:Al molar ratio of 3:1) in which magnesium is partly substituted by aluminum. Specific properties such as porosity and surface area can be tailored by varying the synthesis method and conditions, leading to a wide range of materials adapted to targeted applications. The structure can also be modified by changing the combination of the cations and the interlayer anions, in order to confer specific properties, (Homsí et al. 2017; El Rouby et al. 2018; Sheng et al. 2019; Wu et al. 2019a).

LDHs can be synthesized by various techniques depending on the final requirements such as high crystallinity, low time and/or energy consuming reaction, and phase purity. The most common methods used to synthesize these materials are hydrolysis reaction, co-precipitation,

hydrothermal synthesis, steam activation, microwave irradiation, and sol-gel. These fast and environmental-friendly synthesis processes, combined to high sorption capacities, allow the use of hydrotalcites and derived materials in various applications, such as adsorption of various molecules (organic and inorganic pollutants or dyes for example) or catalytic processes (also thanks to the presence of strong basic sites). In particular, these materials have been intensively studied as catalysts and catalyst supports based on their specific physicochemical features.

Mixed oxides, obtained from the calcination of the parent material, are most generally used in catalytic and environmental applications, due to the high temperatures required. The composition of the obtained oxides depend on the initial combination of M^{II} and M^{III} cations (El Rouby et al. 2018; Rahmanian et al. 2018; Sheng et al. 2019; Wu et al. 2019a), but also on the heating temperature and the targeted reaction (dehydration, dehydroxylation, removal of the interlayer anion, and oxide reformation). Considering the rising interest in using synthesized LDHs for various applications, this paper reviews the most common synthesis methods for their preparation and some chosen environmental applications (Fig1). Due to the wide panel of applications involving layered double hydroxides and LDH-derived materials, the list of applications here reported is not exhaustive. Moreover, certain applications have been already extensively reported in the literature and they could represent alone the subject of dedicated review articles (for example in the case of biodiesel production (Helwani et al. 2009; Atadashi et al. 2013)).

Abstract	1
Introduction	2
1. Synthesis techniques for hydrotalcite-like compounds.....	4
1.1. Co-precipitation method	4
1.2. Urea hydrolysis	7
1.3. Sol-gel method.....	9
1.4. Hydrothermal treatment.....	10

78	2. Use of hydrotalcites and derived materials in environmental applications	13
79	2.1. Adsorption of atmospheric pollutants.....	14
80	2.1.1. CO ₂ adsorption – Capture and storage	14
81	2.1.2. NO _x and SO _x adsorption	21
82	2.1.3. VOCs total decomposition	27
83	2.1. Adsorption of aqueous pollutants	30
84	2.2. Other applications.....	36
85	2.2.1. Hydrogen production.....	36
86	2.2.2. 5-Hydroxymethylfurfural formation	39
87	Conclusion.....	42
88	References	43

89 **1. Synthesis techniques for hydrotalcite-like compounds**

90 As previously explained, hydrotalcite (and more generally LDHs) can be of natural origin
91 (alteration minerals) or synthetic. The advantages in synthesizing LDHs are the ability to
92 finely tune the mineral properties in the view of a specific application, by finding the
93 appropriate combination of reactants and the adapted M^{II}/M^{III} molar ratio. The most important
94 factors to be considered are the nature of the metallic cations, the pH, the temperature, the
95 ageing time, and the preparation method. Several synthesis methods have been developed
96 during the last decades, but this review summarizes only those most commonly used and
97 described in the literature.

98

99 **1.1. Co-precipitation method**

100 Co-precipitation is the most common method to synthesize LDHs. It consists in dissolving
101 the inorganic salts in alkaline media, at constant or increasing pH. This reaction allows to
102 control the morphology and particle size, depending on the supersaturation of the solution.
103 Feitknecht reported for the first time in 1942 on the LDH synthesis by co-precipitation. [Mg-
104 Al-CO₃] LDH was synthesized starting from diluted solutions of the reactants. The co-
105 precipitation synthesis process has been then studied years later by Gastuche et al. (1967) and

106 Miyata (1975, 1980) by modifying parameters such as the concentrations of the reactants and
107 the washing conditions. They also introduced the control of the pH as a key parameter for the
108 formation of LDHs. Several studies have been performed later, focusing on the substitution of
109 the type of metallic cations in the structure of the LDHs, as shown by Sato et al. (1988), in
110 order to obtain several LDH with different structural formulas ($M^{II} = Mg^{2+}$, Ni^{2+} or Co^{2+} and
111 $M^{III} = Al^{3+}$ or Fe^{3+}). Co-precipitation allows to finely tune the structure of the synthesized
112 materials by controlling the M^{II}/M^{III} molar ratios, the type of interlayer anion, the synthesis
113 duration, the temperature, and the pH of the solution (Thevenot et al. 1989; Ulibarri 2001;
114 Zhao et al. 2003; Klopogge et al. 2004; Sharma et al. 2007; Klemkaite et al. 2011).

115 Co-precipitation can be performed at low or high supersaturation conditions depending on
116 the desired crystallization state, as long as the initial concentration of the reactants is above
117 the saturation state of the solution (supersaturation conditions). In any case, the pH of the
118 solution must be controlled: a pH value too low does not allow the complete precipitation of
119 all metallic ions, while a too high value leads to the leaching of one or more metallic ions.
120 Basic media are preferred in most cases, but the optimal pH depends mainly on the metal
121 cations used. Fig2. presents the steps involved in the co-precipitation synthesis process. The
122 co-precipitation method performed at low supersaturation conditions has been firstly
123 documented in the '90s by Kannan et al. (1995). This technique is performed by the slow
124 addition of solutions containing the divalent and trivalent cations in the appropriate molar
125 ratio, before adding an aqueous solution of the chosen interlayer anion (Kannan et al. 2004;
126 Climent 2004; Klopogge et al. 2004; Kovanda et al. 2005a; Perez-Lopez et al. 2006; Sharma
127 et al. 2007; Wang et al. 2011; Klemkaite et al. 2011; Balsamo et al. 2012). An alkaline
128 solution is then added in order to fix the pH during the reaction and to promote the co-
129 precipitation of the two metal salts. This synthesis process has been well described by a
130 schematic flow chart edited by El Roubi et al. (2018). The advantage of this method is the

possibility to control the charge density by keeping the pH constant under low supersaturation conditions by the addition of a mixture of NaOH and NaHCO₃ or Na₂CO₃ (Sharma et al. 2007; Wang et al. 2011; Klemkaite et al. 2011; Balsamo et al. 2012; Sheng et al. 2019; Li et al. 2019a). Materials obtained by co-precipitation at low supersaturation present a higher crystallinity than those obtained at high supersaturation conditions thanks to the continuous regulation of the pH of the synthesis solution. In the high supersaturation condition, the concentration of the solutions is continuously increased or the solution containing the dissolved salts is added to a solution containing a small excess of alkali bicarbonates. This process leads to the formation of less crystalline materials than low supersaturation method, but gives rise to a high number of small aggregates due to the interlayer confinement effect of the carbonate ions (Zhang et al. 2008; Abelló et al. 2010; Solovov et al. 2018).

Co-precipitation synthesis can be considered as an efficient method to obtain crystalline materials, particularly thanks to the long synthesis duration time (several days), the controlled synthesis pH, and the addition of post treatments such as hydrothermal treatment for example (Kannan et al. 1995; Klopogge et al. 2004). However, due to the large dimension of the obtained particles the specific surface area values (between 50-100 m².g⁻¹) are lower than those obtained by sol-gel synthesis (150-200 m².g⁻¹), and discussed later in this review (Aramendía 2002; Park et al. 2018). The substitution with other metallic cations, such as Fe, Zn, Cu, and Ni, as demonstrated by Gevers et al. (2019), add the possibility to modify the crystallite dimensions and influence the thermal stability of LDHs. Thermal treatments, such as hydrothermal treatment or microwave irradiation, can be performed to improve crystallinity and/or to reduce the synthesis time. Similar structures are then obtain even with shorter synthesis time (Climent 2004). This progress was reported by Tichit et al. (2002) by comparing microwave and hydrothermal treatments in co-precipitated hydrotalcites. The authors did not find any significant differences in the structural properties of the final

material, despite the shorter synthesis time that represent a clear advantage. The thermal treatment presents a significant impact on the structural properties of the materials: Othman et al. (2006) compared the effect of the hydrothermal treatment on hydrotalcites prepared by coprecipitation and sol-gel methods. They showed that the specific surface area and pore sizes significantly increased in both cases, with a stronger impact on the samples synthesized by sol-gel.

1.2. Urea hydrolysis

Urea is a weak Brönsted base highly soluble in water. It can be used as a precipitating agent instead of sodium hydroxide to increase the pH through its thermal decomposition. The slow decomposition, starting around 90°C, leads to an increase of the pH up to 10 (Costantino et al. 1998; Yang et al. 2004). Since urea decomposes slowly, it leads to a lower degree of supersaturation. Moreover, prolonged hydrolysis results in the formation of CO_3^{2-} anions in basic medium that act as interlayer anions. Therefore, urea enables an efficient pH control and the formation of mono-dispersed LDH materials with high crystallinity through a low-cost method (Adachi-Pagano et al. 2003; Yang et al. 2004; Zeng et al. 2009a; Xu et al. 2016; Park et al. 2018). The purity and crystallinity of hydrotalcite phases can also be optimized by tuning the $\text{M}^{\text{II}}:\text{M}^{\text{III}}$ molar ratio, the urea concentration, and the ageing time (Costantino et al. 1998; Zeng et al. 2009a; Berber et al. 2013; Montañez et al. 2014; Zhang et al. 2014; Bian et al. 2016; Xu et al. 2016; Park et al. 2018). As an example, Berber et al. (2013) identified the optimal synthesis conditions to obtain uniform and highly crystalline hydrotalcite particles by using a urea/metallic cation molar ratio of 2, and 12h of ageing time at 120°C. Secondary phases have been observed with molar ratios lower or greater than 2, leading to lower crystallinity and specific surface areas of the materials. The main steps involved in hydrotalcite synthesis via urea hydrolysis are summarized in Fig3.

Most of the time, this technique is combined to others (in which urea is used only as a precipitating agent), such as co-precipitation or hydrothermal synthesis. The combination of urea hydrolysis and hydrothermal treatment has been well-documented by Berber et al. (2013) and Benito et al. (2006) in order to obtain uniform particles, but also by Rao et al. (2005) to find optimal Mg:Al molar ratios of 1:1 and 2:1 with uniform and small particles' size. In the first article, microwave irradiation was used as heating source in the synthesis process, strongly shortening the synthesis time and the formation of pure and well-crystallized hydrotalcite phases presenting high specific surface areas. Further studies were performed by Montañez et al. (2014) by comparing the properties of mixed oxides obtained by calcination of a series of Ni-Al-Mg hydrotalcites synthesized, either by co-precipitation or by urea hydrolysis. Enhanced redox properties, larger pore sizes and smaller particles (interesting features in catalytic applications) were obtained on calcined samples prepared with urea hydrolysis. In general, the use of microwave irradiation allows to reduce the preparation time without to impact on the structural and physical properties. This methodology is of a great interest for the industrial scaling-up (Yang et al. 2007; Benito et al. 2008). Hibino and Ohya. (2009) combined urea hydrolysis with hydrothermal treatment in order to remove certain by-products (i.e. hydrated magnesium carbonate hydroxide phases). Further studies have been performed by Klopogge et al. (2006) to show the evolution of the intercalated species depending on the hydrothermal treatment: $(\text{NH}_2)\text{COO}^-$ tends to directly form after precipitation, but slowly transforms into carbonated species during the hydrothermal treatment.

As a partial conclusion, urea hydrolysis is a slow reaction that leads to a low degree of supersaturation during the precipitation. It presents the advantage to provide large and thin platelets with a narrow particle size distribution in a shorter ageing time than co-precipitation (Naseem et al. 2019). However, the decomposition of urea leads to the formation of CO_2 that

reacts with water to form carbonates and acting as compensating anions (Thomas 2012). In this case, a further anion exchange may be required depending on the targeted application (Bish 1980; Iyi et al. 2004; Inayat et al. 2011).

1.3. Sol-gel method

The sol-gel method is appreciated for its low cost, low energy and limited time consuming, for the possibility to obtain high purity materials, and for the possibility to tune their composition (Lopez et al. 1996; Paredes et al. 2006; Sharma et al. 2007; Ramos-Ramírez et al. 2009; Lee et al. 2016). This process allows to control the structural properties of the final materials by simply varying the chemical nature of the reactants, the ageing time, and by removing/adding reactant species. This technique consists in dissolving the desired metal sources (inorganic salts or metal organic compounds) in water, at room temperature (Fig4.).

The concentration of the metal cations can be varied to tune the substitution ratio of M^{II} and M^{III} cations and to obtain a wide range of materials (Corma et al. 1994; Valente et al. 2007, 2009; Sharma et al. 2007). The appropriate amount of acid or base is then added to the reactants' solution during hydrolysis to favor the condensation reaction. The solution is finally aged during several hours or days, at room temperature or lightly heated up to 100°C. Prince et al. (2009) proposed a general sol-gel method for the preparation of LDHs that can be adapted to obtain materials containing specific metallic cations and possessing a defined morphology in the view of a specific application. Ramos-Ramírez et al. (2009) also evidenced the formation of small amounts of brucite phase, in addition to hydrotalcite, with a Mg/Al molar ratio of 2 and explained this behavior by the similar structure of the two materials. Synthetic hydrotalcites can also be calcined and rehydrated without losing their lamellar structure. During regeneration, they show a “memory effect”, as evidenced by Climent et al. (2004) by using rehydrated sol-gel hydrotalcites for pharmaceutical applications.

Several parameters can be varied to improve the crystallinity (Kovanda et al. 2005b; Valente et al. 2009) of the particles, to modify their morphology (Valente et al. 2007, 2009, 2010), and to enhance the surface area (Corma et al. 1994; Lopez et al. 1996, 1997a; Climent et al. 2004; Paredes et al. 2006; Valente et al. 2007; Prince et al. 2009). Parameters, as the composition of the aqueous media, the pH, and the ageing time, were considered (Corma et al. 1994; Kovanda et al. 2005b). Lopez et al. (1997b) studied the impact of different alkoxides, such as magnesium ($\text{Mg}(\text{OEt})_2$) and aluminum ($\text{Al}(\text{NO}_3)_3$), used as reactants, on the thermal stability of a series of hydrotalcites. Most of the time, the comparison between the synthesis techniques and the parameters evidences the interest of using one or the other specific method, generally sol-gel or co-precipitation (Jitianu et al. 2000; Prinetto et al. 2000; Bolognini et al. 2003; Othman et al. 2006; Valente et al. 2007, 2010; Smalenskaite et al. 2017). Smalenskaite et al. (2017) compared sol-gel and co-precipitation for the preparation of cerium-substituted Mg-Al LDHs; Othman et al. (2006) studied the impact of the thermal treatment on the structure of similar materials. In many cases, the sol-gel approach is preferred for its simplicity and the high quality of the materials obtained (Ramos et al. 1997; Othman et al. 2006; Valente et al. 2010; Lee et al. 2016; Smalenskaite et al. 2017).

The sol-gel synthesis method is appreciated for its high reproducibility, the high homogeneity and purity of the obtained compounds, the small size of the particles (nanoscale) and their high specific surface area (Prince et al. 2009; Smalenskaite et al. 2017; Valeikiene et al. 2019). However, lower crystallinity is generally observed through this synthesis route (Smalenskaite et al. 2017). Often and depending on the final application of the materials, additional steps such as sonication, microwave irradiation (Benito et al. 2006) or hydrothermal treatment are required.

1.4. Hydrothermal treatment

As previously reported, the synthesis of LDHs by co-precipitation, sol-gel method or urea hydrolysis can be optimized by hydrothermal treatment in order to improve the crystallinity and the size of the crystallites (Kloprogge et al. 2004; Sharma et al. 2007). The treatment generally occurs under mild hydrothermal conditions, up to 200°C, autogenous pressure, with durations between hours to several days. Fig5. displays the hydrothermal synthesis process.

Besides the improvement of the crystallinity, hydrothermal synthesis can be directly used as a synthesis method, in order to form LDH phases with increased particle sizes. It consists in dissolving the metallic salts into a solvent (generally water) before putting the solution into a stainless-steel reactor and heating under hydrothermal conditions, generally under medium temperatures (30-300°C) and steam pressure, with different synthesis times (few hours to several days) (Xu and Lu 2005; Liao et al. 2012; Bontchev et al. 2003; Bankauskaite and Baltakys 2011; Lin et al. 2019; Budhysutanto et al. 2010; Roelofs et al. 2001; Jang et al. 2014). Several reactants such as inorganic salts and minerals can be used as metal sources. Most commonly, metal oxides and hydroxides (Xu and Lu 2005; Budhysutanto et al. 2010; Jang et al. 2014; Labuschagné et al. 2018) or nitrate salts (Roelofs et al. 2001; Bontchev et al. 2003; Lin et al. 2019) are used as reactants, but other sources can be used: Ogawa et Asai (2000) used for example natural minerals (brucite and gibbsite) as starting materials to intercalate organic guests. Liao et al. (2012) also used natural brucite and $\text{Al}(\text{OH})_3$ as synthesis reactants to study the morphology and structural properties of hydrotalcites obtained under different synthesis conditions.

Like for the other synthesis techniques, the Mg:Al molar ratio and the interlayer anions can be modified in order to obtain a wide range of hydrotalcites and LDHs with different structural properties. Bontchev et al. (2003) studied the impact of several interlayer anions (Cl^- , Br^- , I^- , NO_3^-) on the physico-chemical characteristics of hydrotalcites. Moreover, this study showed the possibility to mix two different types of compensating anions to finely tune

the properties of these compounds. The hydrothermal synthesis of hydrotalcites with different soluble and insoluble magnesium and aluminum reactants in water has been studied by Bankauskaite and Baltakys (2011), with a fixed Mg:Al molar ratio of 3:1. The non-formation of hydrotalcite phases was observed in the presence of certain reactants. It was demonstrated that alumina and magnesium aluminum hydroxide were preferentially formed when using $4\text{MgCO}_3 \cdot \text{Mg}(\text{OH})_2 \cdot 5\text{H}_2\text{O}$, even after 24h of hydrothermal treatment at 200°C. The choice of the appropriate metal salts is the most important parameter to be considered. More recently, the impact of the synthesis temperature (from 35 to 140°C) has been tested by Lin et al. (2019) to synthesize CuZnAl hydrotalcite-like catalysts for arsine abatement. The authors concluded on a significant influence of the synthesis conditions on the arsine removal efficiency without clear explanation. The problem comes from the multiplicity of the parameters varied during the synthesis of the catalysts (temperature, calcination, time, molar ratios), making the results difficult to interpret. The most recent studies focus on the green synthesis of hydrotalcites and derived materials for environmental concerns, as demonstrated by Labuschagné et al. (2018) by using untreated magnesium oxide and aluminum hydroxide for hydrothermal dissolution/precipitation in water.

The advantages of using this synthesis process as additional treatment are the higher LDH crystallinity, crystallites dimension, and purity of the samples (Kovanda et al. 2005b; Sharma et al. 2007). In general, a higher content of hydrotalcite is observed by increasing the preparation temperature and the time of the hydrothermal treatment (Kovanda et al. 2005b). Unfortunately, the energy required to heat-up the solution and the long synthesis time (from hours to days) represent drawbacks for the industrial implementation of the hydrothermal treatment.

The recent advancements and progresses on the synthesis methodologies have been reviewed in this section. Moreover, each synthesis method has been detailed in order to enlighten the advantages and drawbacks in terms of structural and textural properties. The modulation of these features is crucial to drive the performances towards specific environmental and industrial applications. Table 1 lists the positive and negative impacts of the various synthesis routes on the structural and textural properties of LDHs.

2. Use of hydrotalcites and derived materials in environmental applications

The depletion of fossil fuels and their environmental impacts (global warming, pollution, health concerns...) are currently boosting the studies on alternative solutions and clean synthetic routes for the production of non-fossil carbon sources. Recent international conventions agreed to the Kyoto Protocol and intended to reduce by 2050 the global emissions up to 50-60% (of those measured in 2006). The necessity in finding alternative environmental applications based on easy-to-use materials becomes more than urgent. Several reactions can be performed on layered materials, but their low thermal stability makes their implementation difficult. Clay minerals are generally stable up to 200°C due to the loss of the interlayer water and the consequent irreversible degradation of the structure at temperatures higher than 200°C. The presence of specific metal elements in the structure of the LDHs can enhance their catalytic properties, depending on the applications, as mentioned by Xu et al. (2011). Moreover, due to their composition (mainly metallic cations), LDHs can be calcined to form mixed oxides presenting enhanced catalytic properties. Even if much more environmental related processes can be carried out in presence of lamellar materials, only few of them are discussed in this review. Some specific environmental application covering various technological fields have been chosen to be reported in the present review article such as the adsorption/decomposition of gaseous pollutants (CO₂, NO_x, and SO_x adsorption, and

elimination of VOCs), the adsorption of pollutants in aqueous media (as the adsorption of heavy metals and dyes), and the production of green energy vectors and/or chemical building blocks (hydrogen production and formation of 5-hydroxymethylfurfural).

2.1. Adsorption of atmospheric pollutants

2.1.1. CO₂ adsorption – Capture and storage

Among the possible uses of hydrotalcite-like compounds and their derived mixed-oxides, CO₂ adsorption gains interest. Methods for safely control and dispose of carbon dioxide emissions are widely studied in the last few years, mainly due to the increase of consciousness in climate changes (Wang et al. 2017). Among all the emitted greenhouse gases, the contribution of carbon dioxide to global warming has been estimated to more than 60%. For example, steam reforming of hydrocarbons (Marquevich et al. 2001; Ashok et al. 2008; Li et al. 2011), that is the most suitable process for hydrogen production, releases high amounts of carbon dioxide. Considering the large field of materials tested for CO₂ capture and storage, zeolites, hydrotalcite and LDH-derived mixed oxides are widely studied thanks to their high surface area, pore structure, and charge density (Mao and Tamaura 1993; Tsuji et al. 1993; Yong et al. 2002; Wang et al. 2010; Dantas et al. 2015; Yang et al. 2019). Several reviews on CO₂ adsorption explain that an appropriate adsorbent should satisfy several criteria such as (1) low-cost materials, (2) fast kinetics, (3) high adsorption capacity and selectivity, and (4) thermal and chemical stability towards several cycles (Yong et al. 2002; León et al. 2010; Wang et al. 2017; Yang et al. 2019). The adsorption of CO₂ requires materials with large specific surface area, but also a high number of accessible basic sites. Regarding the synthesis method adapted to this application, a high number of active sites and large particles are required for better adsorption efficiency. Thus, the co-precipitation method represents the best solution to reach these requirements, especially when the LDHs structure is modified by the

addition of metal cations. The higher the energy of active sites, the stronger CO₂ interacts with the sites and remains trapped. Recently, zeolites are reported as efficient CO₂ adsorbents thanks to their size, charge density, and tunable chemical composition (Jiang et al. 2018; Yu et al. 2018). Hydrotalcite-based materials are thereby interesting alternative materials to zeolites, as their chemical composition can also be finely tuned. CO₂ adsorption performed on these materials is a natural phenomenon, as hydrotalcite can adsorb carbon dioxide thanks to the reaction of atmospheric CO₂ with the compensating ions present in the interlayer space. This has been evidenced by Ishihara et al. (2013) by intercalating ¹³C carbonate anions in the hydrotalcite structure. They were exchanged with carbonate anions derived from atmospheric CO₂ within 1 day, showing the dynamism of the carbon cycle in nature. Moreover, these materials can be regenerated several times, without losing their adsorption capacity and selectivity towards CO₂, are hydrothermally stable, and lead to fast sorption kinetics. A huge amount of studies has been performed on these materials in order to find the most efficient preparation route for CO₂ capture, such as impregnation of commercial hydrotalcites (Bhatta et al. 2015), synthesis of tunable Mg/Al hydrotalcites (Tsuji et al. 1993; Moreira et al. 2006; Dantas et al. 2015), and mixed oxides derived from hydrotalcites (León et al. 2010; Gao et al. 2013; Radha and Navrotsky 2014; Colonna et al. 2018). Table 2 summarizes the synthesis conditions, the specific surface area, and the CO₂ adsorption capacity of the LDHs and related mixed oxides. It shows that the surface area is strongly linked to the CO₂ adsorption capacity: a higher surface area is related to an increase in the sorption capacity.

The preliminary studies of CO₂ adsorption by hydrotalcite, layered double hydroxides and related materials have been performed by Mao and Tamaura (1993) by varying the M(II)/M(III) molar ratio and consequently the layer charge of the synthesized hydrotalcites. The composition tuning resulted in a wide range of materials capable of chemically adsorb CO₂ with different adsorption capacities (from 0.4 to 1.5 mmol.g⁻¹). The same year, Tsuji et

al. (1993) synthesized various LDHs by changing the M(II) cation nature. The selectivity towards carbon dioxide adsorption depended on the cation in the following order: Cu-Al ~ Zn-Al < Co-Al < Mg-Al < Ni-Al, and was related to the thermal behavior of the various compounds. Moreover, the sorption capacities of these materials have been drastically increased by removing the carbonate counterions in the Mg-Al and Co-Al LDHs. Several years later Wang et al. (2010) studied substitution of divalent metal cations M(II) by trivalent metal cations M(III) (Al^{3+} , Ga^{3+} , Fe^{3+} and Mn^{3+}) in CO_2 adsorption at high temperature, performed on calcined samples.

Few years after Tsuji et al. (1993), the studies about CO_2 adsorption were mainly focused on industrial applications and enlightened the influence of structural parameters derived from the thermal treatment of LDHs, leading to the formation of related mixed oxides. Ram Reddy et al. (2006) showed that, depending on the applied treatment temperature, the samples exhibited different sorption capacities and reversibility. The highest sorption capacities were observed on samples pretreated at 400°C and a sorption temperature of 200°C , leading to CO_2 adsorption of $0.486 \text{ mmol.g}^{-1}$. The pretreatment conditions showed also an impact on the regeneration behavior (cycling studies). Two years later, the same team (Ram Reddy et al. 2008) studied high-temperature CO_2 adsorption in industrial conditions. An increase of the sorption efficiency was observed, from 0.61 to 0.71 mmol.g^{-1} , in presence of dry and wet CO_2 respectively, with more than 90% of the original capacity recovered by regeneration. Dadwahl et al. (2008) reported on the influence of the particle size on CO_2 adsorption, and analyzed the formation of large particles by co-precipitation. Mixed oxides generally exhibit higher sorption capacities due to the higher specific surface area than the fresh samples, but the analysis conditions (sorption temperature, mixture of gas, etc...) affect the CO_2 adsorption capacities in the same way than on non-calcined samples, as demonstrated by León et al. (2010). The obtained capacities, in the 0.58 - 1.15 mmol.g^{-1} range at 50°C , and 0.40 - 0.84

405 mmol.g⁻¹ range at 100°C, depend on the pretreatment temperature, 450 or 700°C respectively.
406 Regarding the reversibility of these materials, the co-precipitation method at high
407 supersaturation conditions is more adapted than that at low supersaturation, due to the
408 formation of weaker basic sites for the latter. As previously explained, Wang et al. (2010)
409 studied the influence of M(III) cation type towards high-temperature CO₂ adsorption on
410 calcined samples at different temperatures, from 250 to 400°C. Different phases have been
411 observed depending on the calcination temperature: MgFe₂O₄ and MgMnO₄ with coexistence
412 of MgO with the appropriate M(III) cations, whereas only MgO phases have been observed in
413 MgAl and MgGa LDHs. Moreover, the M(III) cation nature did not affect the sorption
414 capacity (around 0.4 mmol.g⁻¹), except for the calcined MgGa LDH that gave lower values of
415 CO₂ sorption capacity due to its lower thermal stability. Gao et al. (2013) discovered the
416 optimal parameters to obtain hydrotalcites with improved CO₂ adsorption capacity: synthesis
417 by co-precipitation method, at high supersaturation conditions, with a Mg/Al molar ratio
418 between 3 and 3.5, and a pre-calcination temperature of 400°C (The CO₂ adsorption
419 measurements were performed during 5 hours at 200°C). The operating conditions
420 (temperature and pressure) impact the adsorption capacity of CO₂ too: Ramirez-Moreno et al.
421 (2014) stated that high pressures (up to 4350 kPa) and temperatures (30-350°C) are related to
422 higher CO₂ adsorption levels, with a maximum value of 5.76 mmol.g⁻¹ measured at 300°C
423 and 3450 kPa. Higher values can be reached at higher temperatures and pressures, and related
424 to structural changes in the LDHs framework (formation of magnesium oxides and periclase
425 for example).

426 The most recent researches focus on modifications of the structure of LDHs synthesized by
427 co-precipitation in order to increase their CO₂ adsorption capacity. Similar to simple ion-
428 exchange reaction, the potassium impregnation consists in putting the synthesized materials
429 into a solution with a defined concentration of potassium salt during few hours, followed by

the washing of the salt excess. K_2CO_3 impregnation seems to increase the number of surface active sites despite a decrease in the specific surface area. This impregnation leads to high adsorption capacities, as demonstrated by Bhatta et al. (2015): values up to 1.10 mmol.g^{-1} at 300°C for the initial sorption cycle, and of 0.42 mmol.g^{-1} for the following 9 cycles of adsorption/desorption were measured. Polymers addition can modify the textural properties of layered materials and contribute to the enhancement of the CO_2 sorption capacity, as showed by Dantas et al. (2015) by the addition of a co-polymer that increased the CO_2 uptake from 0.72 to 1.36 mmol.g^{-1} . Tang et al. (2018) increased the basal spacing of LDHs by exchanging anions with dodecylsulfonate ions in order to chemically graft (3-aminopropyl)triethoxysilane (APS) and enhance the CO_2 sorption capacity (up to 2.09 mmol.g^{-1} at 50°C). The presence of amino groups in the interlamellar space strongly contributed to the capture of carbon dioxide through the zwitterion mechanism and weak bonding. By optimizing the synthesis parameters, Thouchprasitchaia et al. (2018) obtained a series of calcined teraethylenepentamine (TEPA)-supported hydrotalcites. At first, increasing the TEPA loading led to higher adsorption capacities, explained by the availability of more basic sites with a higher affinity for CO_2 . A too high TEPA content resulted in the decrease of the sorption capacity due to the steric hindrance of TEPA that blocks the access of CO_2 to the sorption sites.

Among the large panel of industrial applications, sorption enhanced reactions processes (SERP) gained huge interest in the last decade, especially thanks to novel modifications introduced into LDHs structure. SERPs have been developed for the efficient conversion of methane to hydrogen. The main drawback of this process is the formation and release of large amounts of CO_2 , then materials with high carbon dioxide sorption capacity are crucial for this application. The first amine modifications of LDHs for CO_2 adsorption performance towards SERP applications have been performed by Wang et al. (2012b, a) via two different routes: anionic surfactant-mediated synthesis and exfoliation. In the first case, low CO_2 adsorption

capacities (up to 0.6 mmol.g^{-1}) have been recorded, mainly due to the presence of Sodium Dodecyl Sulfate (SDS) in the interlayer space. SDS can be then removed using monoethylamine extraction (ion exchange reaction), leading to higher sorption values (between 1.15 and 1.4 mmol.g^{-1}) (Fig6.). On the opposite, the exfoliation route in the presence of toluene allows to graft amine groups on the surface of LDHs giving high sorption capacities towards CO_2 (around 1.7 mmol.g^{-1} at 80°C). The two studies underline the importance of the interlayer space in LDHs: sodium dodecyl sulfate and aminosilanes molecules present in this area cover the main part of the basic sites involved in the CO_2 adsorption, consequently lowering the sorption capacity. It is important to consider the steric hindrance when considering lamellar materials. Most of the time, K-promoted hydrotalcites are interesting adsorbents in SERP, as the potassium presence leads to sorption capacities higher than 1 mmol.g^{-1} , as demonstrated by Wu et al. (2013). Moreover, the adsorption capacity and kinetics were not affected even after 10 cycles, which is interesting for SERP applications. Coenen et al. (2017b, a) also published about K-promoted hydrotalcites in a series of publications for sorption-enhanced water-gas shift. This article points out the importance of chemisorbed CO_2 and H_2O , strongly linked to the specific adsorption sites. The presence of four different adsorption site types was identified: two site types with high affinity for CO_2 , one for H_2O and one on which CO_2 and H_2O can competitively adsorb. The CO_2 adsorption sites can be easily regenerated in presence of N_2 , and the cycling is favored at high temperatures. In the most recent study of the same group (2018), the adsorption processes were studied by infrared spectroscopy, showing once again the presence of the four types of adsorption sites. The presence of water molecules enables the decomposition of the strong bonds with carbonate sites, ameliorating the cycling behavior. The comparison between LDHs and zeolites has been recently performed by Megías-Sayago et al. (2019) and the importance of the surface area was evidenced. While zeolites exhibited surface areas

around 360 m².g⁻¹ and adsorb CO₂ up to 1.142 mmol.g⁻¹, MgAl and CaAl LDHs presented lower specific surface areas (50 and 21 m².g⁻¹) and adsorb carbon dioxide up to 0.68 and 0.10 mmol.g⁻¹, respectively.

Table 3 and Fig7. display the CO₂ adsorption capacities of various LDHs reported in the literature. Non-modified materials exhibit values between 0.5 and 1 mmol.g⁻¹, while modified LDHs present much higher values, up to 6.1 mmol.g⁻¹.

As demonstrated by various studies, LDHs are interesting alternatives to zeolites and activated carbons for CO₂ adsorption and storage. Adsorption capacities between 0.5 and 6 mmol.g⁻¹ could be measured depending on the structural modifications, the pre-treatments performed prior the adsorption, and the configuration of the adsorption experiments (operating temperature and pressure, gas composition, time of adsorption). Older papers stated on the optimal synthesis conditions and co-precipitation performed at high-supersaturation seems to be the most adapted method. More recent researches focus on sorption-enhanced reaction processes, due to the needs of minimize the release of CO₂ while producing hydrogen from methane. Regarding the synthesis process, co-precipitation allows to obtain large and crystalline particles, increasing the amount of basic sites that are required to reach large amounts of CO₂ adsorbed. The calcination of such materials leads to the formation of mixed oxides with higher surface areas, and consequently an increased number of basic sites. One of the most important parameter to take into account in this application is the specific surface area that is strongly related to the CO₂ adsorption capacity. Moreover, Table 2 evidences slightly higher adsorption capacities for the materials synthesized by co-precipitation at high supersaturation conditions than for those prepared at low supersaturation conditions, except in the samples modified with TEPA (up to 6 mmol.g⁻¹), as shown by

Thouchprasitchaia et al. (2018). However, the commercial hydrotalcite tested by Wu et al. (2013) exhibits similar adsorption capacities than the modified LDHs.

2.1.2. NO_x and SO_x adsorption

Among the wide family of atmospheric pollutants, nitrogen and sulfur-based molecules are emitted from power plants, petroleum refinery, and vehicle engines (Yang et al. 2014). Nitrogen oxides (NO_x) and Sulfur oxides (SO_x, a mixture of SO₂ and SO₃) are released into the atmosphere with exhausted gases, causing environmental and climatic concerns such as acid rains, photochemical smog and human diseases (asthma for example) (Corma et al. 1997; Yu et al. 2006; Yang et al. 2014; Wang et al. 2018). The control of these emissions is becoming mandatory due to the increased awareness towards the climate change. Moreover, several laws and strict regulations have been put into place in the last decade, and encourage researches on more efficient ways to reduce them. Several depollution processes have been developed with good results, such as the direct decomposition (Yokomichi et al. 1996; Imanaka and Masui 2012; Gunugunuri et al. 2018; Gunugunuri and Roberts 2019), adsorption (Mahzoul et al. 1999; Sedlmair et al. 2003; Atribak et al. 2009), Selective Catalytic Reduction (SCR) (Lukyanov et al. 1995; Forzatti et al. 2010; Gao et al. 2018; Gramigni et al. 2019; Wu et al. 2019b; Li et al. 2019b), and NO_x Storage and Reduction (NSR) (Castoldi et al. 2006; Breen et al. 2008; Sakano and Kawamura 2018; Umeno et al. 2019). LDHs are interesting due to their efficiency in a wide range of application, as catalysts and adsorbents. In recent years, hydrotalcite-like compounds have exhibited good NO_x and SO_x adsorption capacities. This chapter is dedicated to the adsorption and removal of these atmospheric pollutants by LDHs and related mixed oxides; the synthesis conditions of each LDH are reported in the Table 4 with the associated structural modifications.

The most important part of the emitted NO_x comes from the Fluid Catalytic Cracking (FCC) method employed by refinery processes to convert heavy distillates into lighter ones, such as gasoline and diesel. In this process, the catalyst gets progressively covered with coke and needs to be reactivated by burning and oxidizing the coke in a regenerator unit, NO_x is here produced (Chaparala et al. 2015). The catalysts are reactivated by reduction at 750°C, so most of the studies are focused on experiments under these conditions. The storage and catalytic reduction of NO_x compounds on the surface of LDH catalysts occurs firstly on the catalytic sites to form nitrites and nitrates, as shown in Fig8, and according to the following reactions (Guo et al. 2018):

Nitrites are unstable on the active sites and are then oxidized to nitrate in the presence of O₂ or decomposed via the following reactions:

The stored NO_x is finally converted to N₂ and H₂O by reacting with H₂ at 350°C:

The first catalytic removal of NO_x using copper-containing LDHs-derived mixed oxides has been reported in the late 90s by Corma et al. (1994). The possibility to incorporate the catalyst in the FCC units was explored, because NO_x can be decomposed by the catalyst reduced under a reductive atmosphere at 550°C, conditions close to those present in the regenerator unit of a FCC plant. The simultaneous removal of NO_x and SO_x in conditions close to those of the regenerator unit was investigated: Cu-mixed oxides derived from

hydrotalcite showed to be able to remove both SO₂ (via an oxidation or reduction reaction) and NO (via reduction and/or decomposition) at the same time in the presence of small amounts of O₂ (between 0 and 1.5%). Doping the catalysts with transition metals, such as cobalt, is of great interest on the storage capacity of NO_x in hydrotalcites; Palomares et al. (1999) studied the catalytic activity of CoMgAl mixed oxides derived from hydrotalcites. Besides increasing the surface area by addition of cobalt, the authors concluded that in presence of O₂ (up to 1%) the catalyst is able to efficiently remove the atmospheric pollutants. In presence of oxygen in the feed and at 750°C, cobalt-containing materials showed to be more selective towards NO reduction than Cu-based compounds. Almost 100% of NO conversion was reached in less than 50s and remained stable during time. Yu et al. (2006) prepared a range of Co_xMg_{3-x}/Al hydrotalcite-like compounds, where *x* varied from 0 (pure MgAl hydrotalcite) to 3 (pure CoAl hydrotalcite). Despite the decrease of the specific surface area while increasing the cobalt content, the results showed that higher storage capacities of NO_x were reached at low temperatures with mixed oxides of intermediate Co concentrations (0.22 mmol.g⁻¹ at 100°C for *x* = 0.5). The pure phases exhibited the lowest storage capacities, around 0.14 mmol.g⁻¹ for MgAl and CoAl hydrotalcites. These results are explained by the increase in the pore size, from 11.6 nm in the pure MgAl mixed oxides to 24.8 nm for the samples with the highest cobalt concentration. Similar experiments were performed the next year by the same team (Yu et al. 2007) with two catalysts: Ca₂CoAl-oxide and Ca₂CoLa_{0.1}Al_{0.9}-oxide, derived from their LDH precursors. NO_x storage capacities up to 0.65 mmol.g⁻¹ at 250°C were measured. Noble metals such as platinum, palladium and ruthenium have also been intensively studied towards the storage of NO_x due to their high catalytic redox properties. Cheng et al. (2004) worked on Pt/MgAl oxides: MgAl oxides supports with different molar ratios were obtained by calcination of hydrotalcites, while platinum cations were incorporated by incipient wetness impregnation. The authors concluded that by

increasing the Mg/Al molar ratio in the initial hydrotalcites, the stored amount of NO_x at 350°C was enhanced. Moreover, the addition of platinum as active phase greatly improved the NO_x storage capacity (from 0.06 to 0.50 mmol.g⁻¹). NO_x are stored as nitrates that are more stable over Pt/Mg oxides than over Pt/MgAl oxides. A similar approach has been performed by Silletti et al. (2006) with Pd/MgAl oxides. Additional adsorption sites were created, bringing to an increase of 70% in the adsorption capacity, when compared to the MgAl oxides (according to the reaction $\text{PdO}_{(s)} + \text{NO}_2 \rightarrow \text{Pd}(\text{NO}_3)_{(s)}$). Finally, RuMgAl oxides have been reported by Li et al. (2007) and exhibited good performances, with a maximum storage capacity of 0.22 mmol.g⁻¹ at 350°C.

The most recent researches focus on low temperature storage and release of NO_x between 150 and 300°C, as reported by Cui et al. (2019) with manganese-doped mixed oxides derived from hydrotalcite precursors. The incorporation of manganese provokes changes in the crystal phases with formation of Mn₃O₄ and MgMn₂O₄ spinel besides brucite. These changes result in the increase of the surface area (from 108 to 139 m².g⁻¹) and of the pore size (from 14 to 23 nm), while the presence of manganese favors the oxidation of NO during adsorption. The largest adsorption capacity of 0.426 mmol.g⁻¹ at 300°C was obtained in the presence of 15 wt% of Mn, as reported in Fig9. The efficiency of LDHs containing various metallic elements towards the adsorption of NO_x pollutants has also been reported by Li et al. (2019b) on a novel NiMnTi mixed oxide, showing high surface area and strong reducibility, resulting in strong surface acidity. Moreover, manganese, nickel and titanium give interesting redox properties to LDHs and gained interest in the last years (Wang et al. 2018; Wu et al. 2019b; Li et al. 2019b). The recent study performed by Kameda et al. (2019) presents another approach on the adsorption of NO_x. The employed catalysts were fresh MgAl hydrotalcites that could be simply recycled by anion desorption in a solution of Na₂CO₃. Low NO removal rate was

observed, but the removal of NO₂ was possible, and stable at around 50% removal degree, during 3 cycles.

Concerning SO_x removal for industrial applications, several patents are related to the use of hydrotalcites in FCC units (Pinnavaia et al. 1991, 1992; Vierheilig 2003). These compounds are emitted during the oxidative regeneration process of the catalysts at 700-800°C. The general FCC process applied to the SO_x removal is schematized in Fig10. Regarding the process conditions, several requirements are needed to trap SO_x (Mathieu et al. 2013): (1) a high thermal stability of the adsorbent under FCC conditions, (2) the ability to oxidize SO₂ to SO₃, (3) the possibility to regenerate the adsorbent under a reductive flow of H₂ to release sulfur as H₂S, (4) the possibility to strongly chemisorb SO_x in the regenerator unit, and (5) the absence of negative impact of the adsorbent on the conversion and selectivity of FCC products. LDHs and hydrotalcites can answer to these requirements: they have the ability to form mixed oxides of the desired elements, stable at high temperatures, and are able to be regenerated in water. The catalytic activity of such compounds strongly depends on the surface area (related to the number of active sites) and on the type of metallic cation employed (for their ability to react with SO_x compounds) (Cantú et al. 2005; Valente and Quintana-Solorzano 2011; Mathieu et al. 2013). The first experiments, focused on MgO, Al₂O₃ and MgAl spinels derived from pure MgAl hydrotalcites, showed very low performances; MgO forms stable MgSO₄ compounds and Al₂O₃ forms Al₂(SO₄)₃ that is very unstable at these temperatures, leading to the release of sulfate species in the regenerator (Yoo et al. 1992). Three basic reactions are involved in the removal of SO_x in the FCC regenerators (Yoo et al. 1992):

Based on these equations, several oxides derived from hydrotalcites and LDHs have been tested in the last decade. The most studied samples were prepared by addition of transition metals similar to those used in the NO_x removal processes. Cantú et al. (2005) reported for example on mixed oxides derived from MgAlFeCe hydrotalcites. Despite the lower surface area and low SO₂ adsorption capacity, the oxides containing iron and cerium presented an interesting resistance to deactivation. The addition of cerium increased the adsorption rates and reduced the saturation times, while a limited amount of iron improved the catalytic regeneration of SO_x adsorbents. A similar study was then performed by Valente and Quintana-Solorzano (2011) in partial and full combustion conditions (used for regeneration). The performances of mixed oxides derived from MgAlFeCe hydrotalcites were compared to those of a commercial catalyst. Hydrotalcites showed a lower deactivation rate and the necessity to use 33% less material than the commercial catalyst. However, only very few recent papers report on the adsorption and removal of SO_x by LDHs-based materials. The most recent researches focus on catalysts capable of simultaneously adsorb SO_x and NO_x (Kameda et al. 2011, 2019a, 2020).

NO_x and SO_x are dangerous compounds formed during the regeneration process of the catalysts employed in the FCC units. Due to their toxicity, their removal has been widely studied. Hydrotalcites and mixed oxides derived from LDHs, in particular those containing transition metals (copper or cerium) or noble metals (platinum, palladium or ruthenium) have been considered for this application. High specific surface area, large pore sizes and improved catalytic properties have been obtained by the addition of metallic cations, leading to interesting results in NO_x and SO_x adsorption in regeneration conditions (around 750°C under a reducing atmosphere). Co-precipitation was the most widely used synthesis method for LDHs, allowing to obtain high specific surface areas, pore sizes and a high number of

active sites. Higher adsorption capacities were reached with co-precipitated LDHs (0.10-0.65 mmol.g⁻¹), compared to commercial samples (up to 0.06 mmol.g⁻¹), as shown by the Table 3. The specific surface areas remain in the same range of values (between 100 and 250 m².g⁻¹) thanks to the modifications performed on the commercial LDHs, which evidences that the specific surface area is not the only parameter to be taken into consideration for increasing the performances in this application. Some additional studies have been performed on the simultaneous adsorption of NO_x and SO_x in order to obtain a polyvalent compound stable under the conditions of the FCC regenerator units (Kameda et al. 2011, 2019a, 2020).

2.1.3. VOCs total decomposition

Volatile Organic Compounds (VOCs) give origin to an important class of organic pollutants, such as toluene, ethanol, methanol, acetone and ethylene (Bahranowski et al. 1999; Carpentier et al. 2002; Gennequin et al. 2010a; Mrad et al. 2015; Kamal et al. 2016). They are emitted from various industrial processes and transport vehicles and represent a serious environmental problem. VOCs are the major contributors to air pollution due to their direct toxic and carcinogenic properties, or indirect contribution to ozone formation. The decomposition of VOCs is thereby crucial for an environmental point of view. VOCs removal requires technologies working under hard conditions (temperatures up to 1100°C and presence of toxic products). The possibility to eliminate VOCs at temperatures lower than those reached during classical combustion is of great interest. Catalytic total combustion of VOCs is then one of the most effective and economically attractive treatment explored in the last decades (Bahranowski et al. 1999; Mikulová et al. 2007; Dula et al. 2007; Tanasoi et al. 2009; Palacio et al. 2010; Kamal et al. 2016). Most catalysts used for the total decomposition of VOCs contain noble metals, such as palladium and gold. Mixed oxides based on transition metals have been also successfully tested with similar activity, as cheaper alternative. The

678 catalysts must present a high thermal stability and a large number of active sites. Co-
679 precipitation is once again the most adapted method to obtain the desired properties. It permits
680 to easily substitute cations in the structure and to promote the formation of large platelets with
681 a high number of active sites. The synthesis conditions of all the samples cited in this part
682 have been listed in Table 5.

683
684 Similarly to CO₂ adsorption, the total decomposition of VOCs by hydrotalcites and LDHs
685 has been studied on various catalysts presenting different substitutions, and in different
686 analytical conditions. The tests were mainly focused on the total decomposition of toluene or
687 ethanol. The first experiments focused on the elimination of VOCs by mixed oxides derived
688 from LDHs have been performed in the late 90s, even if the reaction was already known since
689 many decades. Moderated temperatures, around 200°C, are required for this catalytic reaction.
690 The catalysts are mixed oxides and amorphous phases obtained by calcination of LDHs at
691 high temperature. Bahranowski et al. (1999) reported on the impact of Cu(II) and Cr(III)
692 cations in mixed oxides derived from parent LDHs on the total oxidation of toluene and
693 ethanol performed at various temperature. The authors observed that the purity and
694 crystallinity of the materials depends on the initial Cu:Cr molar ratio, and that the catalyst
695 derived from the CuCr hydrotalcite, with an initial Cu:Cr molar ratio of 2, gave the best
696 catalytic performances in both toluene and ethanol oxidations. A similar study, focused on the
697 crystallinity of the LDH precursors, was performed few years later by Mikulova et al. (2007)
698 on calcined NiAl LDHs. The analyses showed slightly lower catalytic activities than for CuCr
699 hydrotalcites-derived oxides synthesized by Bahranowski et al. (1999) towards toluene
700 oxidation. In ethanol oxidation, the formation of reaction intermediates, such as acetaldehyde,
701 could be avoided by increasing the reaction temperature. Cobalt-containing hydrotalcite
702 precursors with different compositions were tested by Gennequin et al. (2009, 2010b). They

showed interesting activities in toluene oxidation, especially the sample containing the highest amount of cobalt, that presented the highest specific surface area, well dispersed oxides and lower presence of cobalt aluminate species. Fig11. shows the impact of the calcination temperature of Co-containing hydrotalcites on the toluene conversion. The same research group also performed studies focused on the memory effect of hydrotalcite (Gennequin et al. 2010a), their ability to regenerate their structure by simple wetting or impregnation. In this case, cobalt impregnation led to the partial regeneration of the LDH structure and improved the toluene oxidation activity.

Palacio et al. (2010) studied the impact of different trimetallic hydrotalcites (ZnCuAl and MnCuAl), after calcination at 450°C, over the oxidation of toluene. The MnCuAl catalysts showed to be the most efficient (Mrad et al. 2015). Dula et al. (2007) performed a similar study on MgAlMn-oxide (obtained from calcination of the parent LDH). The catalyst was more active than MnO₄-impregnated MgAl LDH for the combustion of toluene under air. This behavior can be explained by the enhanced presence of redox sites on the surface of the as-generated mixed oxide particles. Methane is a bit more difficult to oxidize due to its high inertness: its complete oxidation occurs at much higher temperature than toluene and ethanol, as studied by Tanasoi et al. (2009), with 50% of methane decomposition at 480-490°C over a calcined Cu-containing MgAl-LDH catalyst. This work shows that the catalytic activity is dependent of the reducible amount of copper in the catalyst. Aguilera et al. (2011) performed a more complete study on the total oxidation of 3 different VOCs: butanol, ethanol and toluene by copper-manganese and cobalt-manganese catalysts derived from the parent LDHs. The catalytic activity depended on the VOC type, and the activity scale was the following for both catalyst: butanol < ethanol < toluene. Some other studies (Chmielarz et al. (2012)) focused on mono-carbon VOCs (methane, methanol, and formic acid). The calcination temperature had a direct impact on the complete oxidation: the presence of cobalt phases,

obtained at high calcination temperatures (up to 800°C), induced higher catalytic activities in conversions of methanol and formic acid.

Other modifications, such as the type of interlayer anion or the use of a support, can be introduced in the catalyst conception. Carpentier et al. (2002) demonstrated that the substitution of carbonate anions by palladium complexes in the interlayer space of Mg/Al hydrotalcites improves the catalytic activity. Kovanda and Jiráťová (2011a, b) supported several mixed oxides, derived from hydrotalcites, on Al₂O₃/Al or calcined alumina, and resulted in interesting catalytic activities with the production of side products such as acetaldehyde. Spinel phases identified in the calcined samples are also linked to the high conversion values observed.

Similar to CO₂ adsorption, the total elimination of VOCs remains a very important environmental issue to be solved. Most of the LDHs used in this field are synthesized by coprecipitation method that makes possible the structural substitution of metallic cations, such as chromium or copper, in order to increase the catalytic activity. Differently than for the samples used in NO_x and SO_x adsorption, the materials prepared for VOCs elimination, and that contains metal cations in the structure, show similar specific surface area values (between 10 and 250 m².g⁻¹) when obtained at low or high supersaturation conditions (Table 5). The main differences in the samples comes essentially from the inserted metallic cation and the thermal treatment (temperature and duration). According to the literature, the total elimination of VOCs by LDH-based materials is very promising.

2.1.Adsorption of aqueous pollutants

Nowadays the pollution of water is mainly deriving from several industrial effluents (papermaking, textiles and dyeing for example) and agricultural activities (Chuang et al.

2008; Tzompantzi et al. 2011; Ali 2012). Some of the pollutants released in nature can move into soils and plants. Their high mobility provokes a global concern due to their significant impact on the human health, biotoxicity and carcinogenic effects (Lv et al. 2006; Chuang et al. 2008). As water resource is a fundamental resource on earth and remains rare in some regions, the need to find cheap and efficient depollution processes has increased worldwide. The wide family of aqueous pollutants includes inorganic pollutants (toxic heavy metals such as As, Pb, Cd, Ni, Zn and Cr for example (Lehmann et al. 1999; Yang et al. 2005; El-Sayed et al. 2016; Wan et al. 2017)), organic pollutants (mainly dyes from paper and textile industries (Tzompantzi et al. 2011; Ahmed and Gasser 2012; de Sá et al. 2013; Shan et al. 2014), but also drugs and pharmaceuticals (Chuang et al. 2008; Zhao et al. 2015; Yu et al. 2017)). Many approaches have been proposed for water treatment, including coagulation (Zou et al. 2016a, b), precipitation (Barrera-Díaz et al. 2012; Cheng et al. 2015), sedimentation (Rubí et al. 2009; Guo et al. 2009), sorption (Karickhoff 1984; Fosso-Kankeu et al. 2010; Alila et al. 2011), and ion exchange (Leinonen et al. 1994; Mazur et al. 2016). Regarding the literature, sorption is the most versatile process for removing pollutants at relatively low concentrations, and it is environmentally friendly. This process includes the use of lamellar materials such as clay minerals (Milutinović-Nikolić et al. 2014, p. 99; Wang et al. 2015; Yang et al. 2015) and LDHs (Yang et al. 2005; Chuang et al. 2008; Ahmed and Gasser 2012; Zou et al. 2017), but also activated carbons (Beita-Sandí et al. 2016; Bedin et al. 2016), graphene (Li et al. 2012; Song et al. 2015; Sun et al. 2017), and metal oxides (Tzompantzi et al. 2011; Cheng et al. 2015; Zou et al. 2017). The main obstacle using these materials is their relatively low adsorption capacity, so the majority of the studies is focused on increasing their efficiency. This part of the review discusses about the last advances in the use of LDHs and derived mixed oxides in the adsorption and removal of aqueous pollutants in the last decades. The synthesis parameters of the materials described in this part are listed in the Table 6.

778 Inorganic pollutants are mainly constituted of heavy metals such as arsenic, lead, cadmium,
779 nickel, zinc and chromium. Their toxicity has been well documented, and their removal
780 gained large focus in the last decades (Barrera-Díaz et al. 2012). Thanks to their accessible
781 and expansible interlayer space, LDHs are interesting adsorbents and ion exchangers of these
782 pollutants. Their use has been firstly documented in the late '90s and the performances often
783 compared to those of other inorganic sorbents, such as activated carbons and metal oxides
784 (Lehmann et al. 1999). Pure MgAl hydrotalcites generally exhibit interesting removal
785 capacities, up to 50% of Cr(VI) and 100% Zn(II) at pH 4, and are able to act as anion-
786 exchangers (in the interlayer space) and proton-acceptors (presence of carbonate ions CO_3^{2-}).
787 Moreover, an increase of the solution pH leads to a partial dissolution of the LDH structure
788 and causes the precipitation of cationic metal species increasing the overall removal of
789 inorganic pollutants. These materials are also efficient towards the removal of trace levels of
790 pollutants, such as arsenic and selenium for example, as described by Yang et al. (2005) by
791 using calcined and uncalcined MgAl hydrotalcites. The adsorption values of uncalcined
792 samples are strongly influenced by the pH of the solution, while no influence of pH was
793 measured on calcined samples (Fig12). In both cases, the desorption of As(V) and Se(IV)
794 strongly depended on the anion species, with maximum amounts of 100ppm in presence of
795 HPO_4^{2-} and 1000ppm with SO_4^{2-} , and with desorption yields close to 100%. Several
796 parameters influence the removal capacity by LDHs, such as the pH of the solution, the initial
797 pollutant concentration, and the adsorbent dosage (Lv et al. 2006). Similar to other
798 applications previously discussed, the addition of metallic cations in the structure of LDHs
799 and derived mixed oxides increases the specific surface area and the pore volume of these
800 materials, leading to better sorption capacities. El-Sayed et al. (2016) reported the efficiency
801 of MgAlZn mixed oxides derived from calcined hydrotalcites and observed adsorption
802 capacities up to 1.98 and 1.19 mmol.g^{-1} for Co(II) and Ni(II), respectively. A more recent

803 study showed the positive impact of incorporating LDHs onto a matrix of other nature. Once
804 incorporated into biochar (Xue et al. 2016), MgFe LDHs can uptake nitrates with values up to
805 0.4 mmol.g^{-1} , which are higher than those obtained on MgFe LDHs alone (0.08 mmol.g^{-1}) or
806 on activated carbons (0.15 mmol.g^{-1}). Chitosan has also been tested due to the possibility to
807 adsorb large amounts of metal ions. Indeed, TiFe LDHs modified with chitosan can exhibit
808 high removal capacities (close to 100%) for cadmium and phosphate in mono- and multiple-
809 pollutant solutions (Mahmoud et al. 2017). The use of hierarchical $\text{SiO}_2@\text{LDHs}$ on SiO_2
810 spheres has been studied by Yang et al. (2017) to remove uranium (U(VI)) from aqueous
811 solution. Thanks to the complexations and electrostatic interactions with the abundant
812 oxygen-containing functional groups, a maximum sorption capacity of 1.27 mmol.g^{-1} was
813 reported. Similar adsorption capacities have been reported by Zou et al. (2017) using CaMgAl
814 LDHs and derived mixed oxides, with values depending on the calcination temperature of the
815 LDH: from 0.55 (for uncalcined LDH) up to 2.04 mmol.g^{-1} (for calcined LDH at 500°C).

816 Another family of pollutants regroups the organic aqueous pollutants (pharmaceuticals and
817 molecules with high molecular mass) that are released in nature by chemical industries,
818 creating serious environmental issues due to their high toxicity, even at low concentrations
819 (Chuang et al. 2008; Tzompantzi et al. 2011). The interest in finding new sorbent for
820 removing such compounds from water increased in the last ten years, even if the toxicity and
821 the possibility to adsorb these pollutants by natural materials is known since the '80 (Zepp
822 and Schlottzhauer 1981; Karickhoff 1984). Sorption is one of the most common treatment to
823 remove organic pollutants from nature; LDHs and derived mixed oxides are great candidates
824 thanks to the high sorption capacity in the interlayer region, the large specific surface area and
825 the presence of reactive surfaces (Pavan et al. 1999, 2000; Seki and Yurdakoç 2005; Chuang
826 et al. 2008). Phenolic compounds are the most common organic water pollutants and their
827 adsorption has been widely studied. Tzompantzi et al. (2011) reported on the fast

photocatalytic degradation of phenols in the presence of ZnAl mixed oxides derived from LDHs. The photodegradation rate is maximized thanks to the electron transfer from Zn^{2+} to Al^{3+} . The removal of phenol molecules by photocatalysis has also been reported by Seftel et al. (2015) using TiO_2 deposited on various LDHs matrices presenting different cation compositions (Zn^{2+} , Cu^{2+} , Al^{3+} , Fe^{3+} and Ti^{4+}). The specific surface area depended on the cations (from $5 \text{ m}^2.\text{g}^{-1}$ with Cu-substituted LDH to $199 \text{ m}^2.\text{g}^{-1}$ for Fe-substituted LDH), and almost 90% efficiency towards phenol adsorption by all the TiO_2 -modified LDHs was obtained after 5h of UV and visible light irradiation.

Concerning dyes elimination from aqueous solutions, a number of technologies were recently developed, such as the adsorption by activated carbon (Özacar and Şengil 2002) or the nanofiltration (Koyuncu 2002; Lau and Ismail 2009). However, the formation of sludges in large quantities or the high operation cost make them not suitable for industrial and large-scale applications (Ahmed and Gasser 2012). The low cost and regeneration properties of LDHs make the use of such materials interesting, as demonstrated by Ahmed and Gasser (2012) on the removal of Crystal Red, an anionic dye. Fig13 shows the adsorption of the dye; after only 15min, 97% of the dye is removed when starting from a solution with a concentration of 100 mg.L^{-1} . Moreover, LDH can be regenerated and cycled several times. Similar experiments were also performed by de Sá et al. (2013) with the Sunset Yellow FCF, a synthetic dye used to color food. The increase of the interlayer distance was observed, indicating that the adsorption takes place by simple ion exchange in this area. Magnetic materials can also be great sorbents towards organic dyes, as studied by Shan et al. (2014) by using magnetic $\text{Fe}_3\text{O}_4/\text{MgAl}$ hydrotalcites to remove three different red dyes (reactive red, congo red, and acid red 1). The uptake equilibrium was reached after 30 min without significant impact on the solution pH. The different results reported all along this review show that the morphology of the LDHs has a great impact on the specific surface area and plays a

role on the adsorption capacity. A recent study performed by Li et al. (2016) focused on the adsorption of congo red by MgAl hydrotalcite. The specific surface area increased from 24.74 to 165.07 m².g⁻¹ upon calcination of the parent hydrotalcite, due to the enhancement of the microporosity deriving from the dehydroxylation of the layers and the decomposition of carbonate anions. However, only a slight increase of the adsorption capacity (from 0.186 to 0.206 mmol.g⁻¹) was observed. Indeed, the adsorption mechanism implies the anion exchange in the interlayer space and the sorption on the external surface, while the internal surface related to microporosity is not involved in the process due to accessibility problems.

The adsorption of aqueous pollutants, inorganic (toxic heavy metals) and organic (dyes and heavy molecules), by LDHs and derived mixed oxides has been discussed. Due to the increase of industrial and agricultural activities, these dangerous and harmful compounds can be found in high concentrations and need to be removed from aqueous media. Their sorption by lamellar materials, more specifically LDHs, is one of the most investigated solutions. As the adsorption of these pollutants takes place in the interlayer space and on the external surfaces, LDHs and derived mixed oxides with large external specific surface area are required. The co-precipitation method is the most employed because of its ability to form a wide range of LDHs with high crystallinity and reactive surfaces, mainly by substituting magnesium and/or aluminum by other metallic cations in the structure at different molar ratios. According to Table 6, similar specific surface areas were obtained with the samples synthesized by co-precipitation either at low or high supersaturation conditions (between 5 and 230 m².g⁻¹). Other synthesis methods such as the ball milling (Mahmoud et al. 2017) or the ethanol-water mediated solvothermal method (Li et al. 2016) are also interesting alternatives to obtain materials with high surface areas (around 150 m².g⁻¹). Based on the existing literature, the adsorption of aqueous pollutants on LDHs and their derived materials reveals to be a promising alternative.

2.2. Other applications

2.2.1. Hydrogen production

The need of alternative energies to replace fossil fuels is growing since the last decade. Hydrogen is a clean energy vector that can be produced from several processes such as steam reforming, partial oxidation, or Sorption Enhanced Reaction Process (SERP) (Marquevich et al. 2001; He et al. 2009, 2010; Halabi et al. 2012a, b; Chanburanasiri et al. 2013; Cesar et al. 2016; Homsy et al. 2017). Hydrogen production is carried out in presence of CO₂ adsorption processes (as reported in the section “2.1.1 CO₂ adsorption – Capture and storage”). Sikander et al. (2017) reported in a review article the different hydrogen production processes carried out in the presence of hydrotalcite-base catalysts. The feedstock is generally constituted of light hydrocarbons such as ethanol, methanol or methane, even if biomass is a promising environment-friendly hydrogen source being highly available worldwide, relatively cheap and renewable (He et al. 2009, 2010; Contreras et al. 2014; Cesar et al. 2016; Zardin and Perez-Lopez 2017; García-Sancho et al. 2018; Sikander et al. 2018). The hydrogen production reactions are reported in the following equations (de Souza et al. 2012):

(1) $\text{C}_2\text{H}_5\text{OH} + \text{H}_2\text{O} \rightarrow 2\text{CO} + 4\text{H}_2$ in presence of ethanol in water,

(2) $\text{C}_2\text{H}_5\text{OH} \rightarrow \text{CH}_3\text{CHO} + \text{H}_2$

(3) $\text{CH}_3\text{CHO} \rightarrow \text{CH}_4 + \text{CO}$ by decomposition of ethanol and the further decomposition of acetaldehyde,

(4) $\text{CH}_4 + \text{H}_2\text{O} \rightarrow \text{CO} + 3\text{H}_2$ in presence of methane in water,

(5) $\text{CH}_4 + \text{CO}_2 \rightarrow 2\text{CO} + 2\text{H}_2$ in presence of methane in carbon dioxide.

The drawback in using hydrotalcite-derived catalysts for these processes is the high operating temperature needed (up to 900°C) to calcine the layered materials prior to the catalytic reaction. Moreover, the formation of carbon monoxide can lead to the formation of

carbonaceous materials (also named coke) that brings to the progressive deactivation of the active sites, as shown by de Souza et al. (2012) in the Boudouard reaction: $2\text{CO} \rightarrow \text{CO}_2 + \text{C}_{(s)}$. The synthesis conditions of the LDHs and related mixed oxides discussed in this part are summarized in Table 7.

The first experiments using LDHs to produce hydrogen were performed, in the last decade, by steam reforming. Markevich et al. (2001) studied the feasibility with sunflower oil, as feedstock, and Ni/Al mixed oxides derived from calcined LDHs, as catalyst. More recently, steam reforming was studied in the presence of hydrocarbons such as ethanol, methane or ethylene glycol. For each source, the key-point for process development is to identify the most efficient catalysts and synthesize it by varying the synthesis conditions or the chemical composition. Contreras et al. (2014) reported in a review article the various catalysts tested for hydrogen production by steam reforming. Ni-containing catalysts show very good catalytic activity for the conversion of ethanol and ethylene glycol, as shown by He et al. (2009, 2010) and Cesar et al. (2016), respectively. In the first case, the catalytic activity of Co-Ni catalysts decreased by increasing the nickel content. In presence of ethylene glycol, Cesar et al. (2016) showed that Pt-containing catalysts are the most active and selective. Finally, a complete study on the steam reforming process, carried out with methane as feedstock, has been reported by Halabi et al. (2012a, b), using calcined K_2CO_3 -promoted Mg/Al hydrotalcite with in-situ CO_2 capture. A similar study has been performed by Chanburanasiri et al. (2013) by comparing the impact of different commercial K_2CO_3 on the sorption efficiency and H_2 production. The co-precipitation method revealed to be the most adapted for the easy substitution of the cations in the structure. In some syntheses, co-precipitation was performed in the presence of urea in order to improve the crystal size and the number of active sites.

Methane decomposition is the second process largely studied for hydrogen production. Methane is firstly adsorbed on the surface of the catalysts and then decomposed on the active sites. Graphite-like structure or coke can accumulate on the active sites and block them, leading to a progressive deactivation of the catalyst. The presence of transition metals (Ni, Co) in the catalyst structure positively contributes to methane decomposition at low temperatures and with high yields. By varying the Cu/Al molar ratios (maintaining fixed Ni content) of calcined Ni/Cu/Al hydrotalcites, Ashok et al. (2008) identified the ideal composition (Ni/Cu/Al=60/25/15) to obtain the highest hydrogen yield. The amount of Ni in Ni/Mg/Al hydrotalcites can also be modulated; García-Sancho et al. (2017) investigated the influence of the nickel content on hydrogen production. Fig14. shows the methane conversion and the hydrogen production in the presence of hydrotalcites of various nickel content during temperature-programmed tests. 55% of methane conversion with 100% hydrogen selectivity was measured on a catalyst containing 46%_{at} of nickel in the structure. The conversion was not improved by increasing the nickel content, due to the presence of inactive isolated Ni particles among the spinel phases. One year later, the same team (García-Sancho et al. 2018) compared the impact of adding nickel during the synthesis of hydrotalcites prior to the calcination and to form bulk Ni-mixed oxides, or after the calcination of the hydrotalcites (to produce Ni-supported mixed oxides). The two kind of catalysts show similar activities, and only slight differences in the reduction temperatures of the catalysts were observed. The impact of the calcination temperature was studied by Sikander et al. (2018) on Mg/Ni/Al hydrotalcites with different nickel content. The sample containing 40%_{at} nickel showed the best performances after calcination at 500 and 750°C. The presence of spinel-like structures on the catalyst surface favors the diffusion of the deposited carbon, enhancing the overall catalytic activity.

Hydrogen can be produced by various processes, such as steam reforming and methane decomposition. Highly active and selective catalysts exist and are listed in Table 8. The possibility to tune the catalysts composition is fundamental to form mixed oxides with high catalytic activity. Most of the studies discussed in this section are focused on the co-precipitation method for the possibility of operating structural substitutions, particularly to add nickel cations in the LDH structure. Table 7 also shows the interest in using co-precipitated LDHs instead of commercial samples; the specific surface areas of the synthesized samples is higher than that of the commercial ones (between 69 and 156 m².g⁻¹ instead of 15-104 in the commercial hydrotalcites). Urea is also introduced during preparation in order to obtain a high number of active sites and increase the size of the platelets. Moreover, the hydrogen production can be combined with CO₂ adsorption with interesting results. Combining CO₂ capture and H₂ formation in the same process is promising for future industrial applications.

2.2.2.5-Hydroxymethylfurfural formation

Thanks to its natural abundance, biomass is a promising sustainable feedstock: carbohydrates are the largest natural carbon source constituting up to 75% of the annual biomass production, with promising applications in chemistry, food, paper, and pharmaceutical industries (Rosatella et al. 2011; Zakrzewska et al. 2011). Carbohydrates are rich in oxygen and can be easily reduced and dehydrated into a large spectrum of chemicals such as 5-Hydroxymethylfurfural (5-HMF) or levulinic acid. The US Department of Energy listed 5-HMF among the top 10 value-added chemicals; it is generally used as an intermediate to synthesize a wide range of chemicals nowadays derived from petroleum. Unfortunately, 5-HMF is not extensively produced at industrial scale due to the high production cost (van Putten et al. 2013). Fructose and glucose conversion are well-documented reactions that occur

at relatively low temperature (below 150°C). These mild reaction conditions allow the use of clays, hybrids and other lamellar materials as catalysts. The dehydration of fructose leads to the formation of 5-Hydroxymethylfurfural (5-HMF), the main reaction product, and other by-products, such as levulinic acid and formic acid, that are formed by degradation of 5-HMF, as explained in Fig15. The catalysts used in this reaction must present a high specific surface area in order to maximize the catalytic surface and react with the fructose dissolved in the solvent (generally water). These requirements can be fulfilled by LDHs synthesized by the sol-gel method or any other method implying a hydrothermal treatment, and that present high specific surface areas and an improved thermal stability. The synthesis parameters of all the cited samples are reported in Table 9.

The main drawback in using clays, hybrids and other lamellar materials in catalytic reactions is their thermal stability. In typical natural clays, dehydration occurs below 200°C with the removal of interlayer and surface water, while irreversible dehydroxylation with formation of oxides starts already around 350°C, depending on the type of metallic cations in the starting material. Several catalytic reactions occur above 300°C, thus the majority of the studies performed with LDHs is based on mixed oxide catalysts obtained by their calcination. However, few experiments have been performed on modified clay minerals such as montmorillonite; thanks to their expandable layers and swelling properties, these minerals can be easily modified by ion-exchange and pillaring in order to modify their structural properties. Lourvanij and Rorrer (1994) studied the partial dehydration of glucose to organic acids on iron-, chromium-, aluminum-, and non-pillared montmorillonite. Their large pore size (higher than 10Å) allows the diffusion of glucose molecules (equal to 8.6Å) in the interlayer space, as demonstrated by the Fig16. Depending on the reaction path, coke formation, leading to their progressive deactivation, has been observed. Further studies have been performed by Fang et

al. (2014) with a commercial montmorillonite (K-10) to compare the impact of the reaction solvent: dimethyl sulfoxide (DMSO) and butyl-3-methylimidazole chloride ([BMIM]Cl) were used. The results are shown in Fig17. and point out the higher conversion of glucose in presence of higher concentrations of [BMIM]Cl in DMSO. The efficient recycling of the solvent (up to six times) without significant loss of the catalytic activity was also observed.

Beside the well-known basicity of hydrotalcites, LDHs and related materials, only few studies on the dehydration of fructose in 5-Hydroxymethylfurfural have been performed on these materials. However, recent researches pointed out the promising application of these materials in the transformation of biomass-derived monomers (Chheda and Dumesic 2007; Li et al. 2011; Climent et al. 2014). Zeolites are widely employed for such applications, but mixed oxides represent a great alternative thanks to their easy synthesis by sol-gel method or by simple thermal treatment of LDHs and hydrotalcites.

In the case of glucose catalysis, three different reactions can be expected: dehydration, isomerization, and retro-aldol condensation. The first reaction generally allows to form HMF and levulinic acid in the presence of acid catalysts, while the other reactions are favored in the presence of basic materials to form fructose or lactic acid. The bifunctional acid-base properties of Al-Zr mixed oxides bring to different reaction products: HMF and levulinic acid are formed by dehydration on the acid sites, while lactic acid and fructose are obtained by isomerization and retro-aldol condensation in the basic sites.

As explained in this part, the catalytic formation of 5-HMF by dehydration of glucose with the use of hydrotalcites or LDHs is not much documented, but the potential use of their related mixed oxides shows interesting results that may be promising for future researches as zeolite substitutes and needs further investigations. Even if the specific surface areas of the LDHs reported in the Table 9 are similar to those of modified montmorillonites, the catalytic

activity in this application is related to the surface acidity, limiting the potential use of LDHs. Moreover, the sol-gel method or hydrothermal treatment can be easily performed to obtain LDHs adapted to this application.

Conclusion

LDHs, hydrotalcites and their related materials gained huge interest in the last decades thanks to their simple synthesis processes and numerous applications. Even if they are mainly synthesized by co-precipitation or hydrothermal methods, the possibility to combine different M(II) and M(III) cations and interlayer anions in their structure allows to tailor the chemical composition, as well as their structural properties (surface areas, pore sizes, number of active sites), making them potential catalysts in several industrial and environmental processes. Moreover, their memory effect permits to reuse them many times, which is interesting at industrial scales.

In this review, the impact of synthesis methods on the structural and textural properties of LDHs has been discussed in order to identify the most suitable synthesis process for a chosen environmental application. The adsorption of pollutants (atmospheric and aqueous) and hydrogen production are important environmental applications in which LDHs can find their place. The key parameter for implementing the use of LDHs and derived materials is the choice of the appropriate synthesis process. The adsorption of pollutants requires high amount of basic sites and strong thermal stability that can be obtained using the co-precipitation method to synthesize LDHs. On the other side, the formation of 5-HMF takes place on the acid sites that can be potentially obtained by sol-gel or hydrothermal synthesis. Finally, the intercalation, impregnation or addition of appropriate elements (metals) with uniform

dispersion is important for hydrogen production to increase the catalytic activity of hydrotalcites (Fig18.).

Acknowledgements

The authors acknowledge the French Ministry of High Education and Research for the Ph.D.-student fellowship allowed to Dylan Chaillot.

Abbreviations

LDH, Layered Double Hydroxide; 5-HMF, 5-Hydroxymethylfurfural; VOCs, Volatile Organic Compounds; TEPA, TeraEthylenePentAmine; SERP, Sorption Enhanced Reaction Process; HPLC, High Performance Liquid Chromatography; NMR, Nuclear Magnetic resonance; DMSO, DiMethyl SulfOxide.

References

- Abelló S, Mitchell S, Santiago M, et al (2010) Perturbing the properties of layered double hydroxides by continuous coprecipitation with short residence time. *J Mater Chem* 20:5878. <https://doi.org/10.1039/c0jm00088d>
- Adachi-Pagano M, Forano C, Besse J-P (2003) Synthesis of Al-rich hydrotalcite-like compounds by using the urea hydrolysis reaction—control of size and morphology. *J Mater Chem* 13:1988–1993. <https://doi.org/10.1039/B302747N>
- Aguilera DA, Perez A, Molina R, Moreno S (2011) Cu–Mn and Co–Mn catalysts synthesized from hydrotalcites and their use in the oxidation of VOCs. *Appl Catal B Environ* 104:144–150. <https://doi.org/10.1016/j.apcatb.2011.02.019>
- Ahmed IM, Gasser MS (2012) Adsorption study of anionic reactive dye from aqueous solution to Mg–Fe–CO₃ layered double hydroxide (LDH). *Appl Surf Sci* 259:650–656. <https://doi.org/10.1016/j.apsusc.2012.07.092>
- Albuquerque DWS, Costa ES, de Miranda JL, et al (2016) Evaluation of the Behavior of Hydrotalcite Like-Materials for CO₂ Capture. *Appl Mech Mater* 830:3–10. <https://doi.org/10.4028/www.scientific.net/AMM.830.3>

- 1080 Ali I (2012) New Generation Adsorbents for Water Treatment. *Chem Rev* 112:5073–5091.
1081 <https://doi.org/10.1021/cr300133d>
- 1082 Alila S, Aloulou F, Thielemans W, Boufi S (2011) Sorption potential of modified nanocrystals for the
1083 removal of aromatic organic pollutant from aqueous solution. *Ind Crops Prod* 33:350–357.
1084 <https://doi.org/10.1016/j.indcrop.2010.11.010>
- 1085 Aramendía M (2002) Comparative Study of Mg/M(III) (M=Al, Ga, In) Layered Double Hydroxides
1086 Obtained by Coprecipitation and the Sol–Gel Method. *J Solid State Chem* 168:156–161.
1087 <https://doi.org/10.1006/jssc.2002.9655>
- 1088 Ashok J, Subrahmanyam M, Venugopal A (2008) Hydrotalcite structure derived Ni–Cu–Al catalysts for
1089 the production of H₂ by CH₄ decomposition. *Int J Hydrog Energy* 33:2704–2713.
1090 <https://doi.org/10.1016/j.ijhydene.2008.03.028>
- 1091 Atadashi IM, Aroua MK, Abdul Aziz AR, Sulaiman NMN (2013) The effects of catalysts in biodiesel
1092 production: A review. *J Ind Eng Chem* 19:14–26. <https://doi.org/10.1016/j.jiec.2012.07.009>
- 1093 Atribak I, Azambre B, Bueno López A, García-García A (2009) Effect of NO_x adsorption/desorption
1094 over ceria-zirconia catalysts on the catalytic combustion of model soot. *Appl Catal B Environ*
1095 92:126–137. <https://doi.org/10.1016/j.apcatb.2009.07.015>
- 1096 Bahranowski K, Bielanska E, Janik R, et al (1999) LDH-derived catalysts for complete oxidation of
1097 volatile organic compounds. *Clay Miner* 34:67–77
- 1098 Balsamo N, Mendieta S, Oliva M, et al (2012) Synthesis and Characterization of Metal Mixed Oxides
1099 from Layered Double Hydroxides. *Procedia Mater Sci* 1:506–513.
1100 <https://doi.org/10.1016/j.mspro.2012.06.068>
- 1101 Bankauskaite A, Baltakys K (2011) The hydrothermal synthesis of hydrotalcite by using different
1102 partially soluble and insoluble in water manganese and aluminium components. *Sci Sinter*
1103 43:261–275. <https://doi.org/10.2298/SOS1103261B>
- 1104 Barrera-Díaz CE, Lugo-Lugo V, Bilyeu B (2012) A review of chemical, electrochemical and biological
1105 methods for aqueous Cr(VI) reduction. *J Hazard Mater* 223–224:1–12.
1106 <https://doi.org/10.1016/j.jhazmat.2012.04.054>
- 1107 Bedin KC, Martins AC, Cazetta AL, et al (2016) KOH-activated carbon prepared from sucrose spherical
1108 carbon: Adsorption equilibrium, kinetic and thermodynamic studies for Methylene Blue
1109 removal. *Chem Eng J* 286:476–484. <https://doi.org/10.1016/j.cej.2015.10.099>
- 1110 Beita-Sandí W, Ersan MS, Uzun H, Karanfil T (2016) Removal of N -nitrosodimethylamine precursors
1111 with powdered activated carbon adsorption. *Water Res* 88:711–718.
1112 <https://doi.org/10.1016/j.watres.2015.10.062>
- 1113 Benito P, Herrero M, Barriga C, et al (2008) Microwave-Assisted Homogeneous Precipitation of
1114 Hydrotalcites by Urea Hydrolysis. *Inorg Chem* 47:5453–5463.
1115 <https://doi.org/10.1021/ic7023023>
- 1116 Benito P, Labajos FM, Rives V (2006) Uniform Fast Growth of Hydrotalcite-like Compounds. *Cryst*
1117 *Growth Des* 6:1961–1966. <https://doi.org/10.1021/cg0506222>

- 1118 Berber MR, Hafez IH, Minagawa K, et al (2013) Uniform nanoparticles of hydrotalcite-like materials
1119 and their textural properties at optimized conditions of urea hydrothermal treatment. *J Mol*
1120 *Struct* 1033:104–112. <https://doi.org/10.1016/j.molstruc.2012.08.028>
- 1121 Bhatta LKG, Subramanyam S, Chengala MD, et al (2015) Enhancement in CO₂ Adsorption on
1122 Hydrotalcite-based Material by Novel Carbon Support Combined with K₂CO₃ Impregnation.
1123 *Ind Eng Chem Res* 54:10876–10884. <https://doi.org/10.1021/acs.iecr.5b02020>
- 1124 Bian L, Wang W, Xia R, Li Z (2016) Ni-based catalyst derived from Ni/Al hydrotalcite-like compounds
1125 by the urea hydrolysis method for CO methanation. *RSC Adv* 6:677–686.
1126 <https://doi.org/10.1039/C5RA19748A>
- 1127 Bish DL (1980) Anion-exchange in takovite : applications to other hydroxide minerals. *Bull*
1128 *Minéralogie* 103:170–175. <https://doi.org/10.3406/bulmi.1980.7392>
- 1129 Bolognini M, Cavani F, Scagliarini D, et al (2003) Mg/Al mixed oxides prepared by coprecipitation and
1130 sol–gel routes: a comparison of their physico-chemical features and performances in m-
1131 cresol methylation. *Microporous Mesoporous Mater* 66:77–89.
1132 <https://doi.org/10.1016/j.micromeso.2003.09.010>
- 1133 Bontchev RP, Liu S, Krumhansl JL, et al (2003) Synthesis, Characterization, and Ion Exchange
1134 Properties of Hydrotalcite Mg₆Al₂(OH)₁₆(A)_x(A')_{2-x}·4H₂O (A, A' = Cl⁻, Br⁻, I⁻, and NO₃⁻, 2 ≥ x ≥ 0) Derivatives. *Chem Mater* 15:3669–3675. <https://doi.org/10.1021/cm034231r>
- 1136 Breen JP, Burch R, Fontaine-Gautrelet C, et al (2008) Insight into the key aspects of the regeneration
1137 process in the NO_x storage reduction (NSR) reaction probed using fast transient kinetics
1138 coupled with isotopically labelled 15NO over Pt and Rh-containing Ba/Al₂O₃ catalysts. *Appl*
1139 *Catal B Environ* 81:150–159. <https://doi.org/10.1016/j.apcatb.2007.12.016>
- 1140 Budhysutanto WN, Kramer HJM, van Agterveld D, et al (2010) Pre-treatment of raw materials for the
1141 hydrothermal synthesis of hydrotalcite-like compounds. *Chem Eng Res Des* 88:1445–1449.
1142 <https://doi.org/10.1016/j.cherd.2009.10.010>
- 1143 Cantú M, López-Salinas E, Valente JS, Montiel R (2005) SO_x Removal by Calcined MgAlFe
1144 Hydrotalcite-like Materials: Effect of the Chemical Composition and the Cerium Incorporation
1145 Method. *Environ Sci Technol* 39:9715–9720. <https://doi.org/10.1021/es051305m>
- 1146 Carpentier J, Lamonier JF, Siffert S, et al (2002) Characterisation of Mg/Al hydrotalcite with interlayer
1147 palladium complex for catalytic oxidation of toluene. *Appl Catal Gen* 234:91–101.
1148 [https://doi.org/10.1016/S0926-860X\(02\)00201-6](https://doi.org/10.1016/S0926-860X(02)00201-6)
- 1149 Castoldi L, Matarrese R, Lietti L, Forzatti P (2006) Simultaneous removal of NO_x and soot on Pt–
1150 Ba/Al₂O₃ NSR catalysts. *Appl Catal B Environ* 64:25–34.
1151 <https://doi.org/10.1016/j.apcatb.2005.10.015>
- 1152 Cesar DV, Santori GF, Pompeo F, et al (2016) Hydrogen production from ethylene glycol reforming
1153 catalyzed by Ni and Ni–Pt hydrotalcite-derived catalysts. *Int J Hydrog Energy* 41:22000–
1154 22008. <https://doi.org/10.1016/j.ijhydene.2016.07.168>
- 1155 Chanburanasiri N, Ribeiro AM, Rodrigues AE, et al (2013) Simulation of Methane Steam Reforming
1156 Enhanced by *in Situ* CO₂ Sorption Using K₂CO₃-Promoted Hydrotalcites for H₂ Production.
1157 *Energy Fuels* 27:4457–4470. <https://doi.org/10.1021/ef302043e>

1158 Chaparala SV, Raj A, Chung SH (2015) Reaction Mechanism for the Formation of Nitrogen Oxides (NO
1159 x) During Coke Oxidation in Fluidized Catalytic Cracking Units. *Combust Sci Technol*
1160 187:1683–1704. <https://doi.org/10.1080/00102202.2015.1059328>

1161 Cheng H, Chen G, Wang S, et al (2004) NO_x storage-reduction over Pt/Mg-Al-O catalysts with
1162 different Mg/Al atomic ratios. *Korean J Chem Eng* 21:595–600.
1163 <https://doi.org/10.1007/BF02705493>

1164 Cheng Q, Wang C, Doudrick K, Chan CK (2015) Hexavalent chromium removal using metal oxide
1165 photocatalysts. *Appl Catal B Environ* 176–177:740–748.
1166 <https://doi.org/10.1016/j.apcatb.2015.04.047>

1167 Chheda JN, Dumesic JA (2007) An overview of dehydration, aldol-condensation and hydrogenation
1168 processes for production of liquid alkanes from biomass-derived carbohydrates. *Catal Today*
1169 123:59–70. <https://doi.org/10.1016/j.cattod.2006.12.006>

1170 Chmielarz L, Piwowarska Z, Rutkowska M, et al (2012) Total oxidation of selected mono-carbon VOCs
1171 over hydrotalcite originated metal oxide catalysts. *Catal Commun* 17:118–125.
1172 <https://doi.org/10.1016/j.catcom.2011.10.030>

1173 Chuang YH, Tzou YM, Wang MK, et al (2008) Removal of 2-Chlorophenol from Aqueous Solution by
1174 Mg/Al Layered Double Hydroxide (LDH) and Modified LDH. *Ind Eng Chem Res* 47:3813–3819.
1175 <https://doi.org/10.1021/ie071508e>

1176 Climent M (2004) Increasing the basicity and catalytic activity of hydrotalcites by different synthesis
1177 procedures. *J Catal* 225:316–326. <https://doi.org/10.1016/j.jcat.2004.04.027>

1178 Climent MJ, Corma A, Iborra S (2014) Conversion of biomass platform molecules into fuel additives
1179 and liquid hydrocarbon fuels. *Green Chem* 16:516. <https://doi.org/10.1039/c3gc41492b>

1180 Climent MJ, Corma A, Iborra S, Velty A (2004) Activated hydrotalcites as catalysts for the synthesis of
1181 chalcones of pharmaceutical interest. *J Catal* 221:474–482.
1182 <https://doi.org/10.1016/j.jcat.2003.09.012>

1183 Coenen K, Gallucci F, Cobden P, et al (2017a) Chemisorption of H₂O and CO₂ on Hydrotalcites for
1184 Sorption-enhanced Water-gas-Shift Processes. *Energy Procedia* 114:2228–2242.
1185 <https://doi.org/10.1016/j.egypro.2017.03.1360>

1186 Coenen K, Gallucci F, Mezari B, et al (2018) An in-situ IR study on the adsorption of CO₂ and H₂O on
1187 hydrotalcites. *J CO₂ Util* 24:228–239. <https://doi.org/10.1016/j.jcou.2018.01.008>

1188 Coenen K, Gallucci F, Pio G, et al (2017b) On the influence of steam on the CO₂ chemisorption
1189 capacity of a hydrotalcite-based adsorbent for SEWGS applications. *Chem Eng J* 314:554–569.
1190 <https://doi.org/10.1016/j.cej.2016.12.013>

1191 Colonna S, Bastianini M, Sisani M, Fina A (2018) CO₂ adsorption and desorption properties of
1192 calcined layered double hydroxides: Effect of metal composition on the LDH structure. *J*
1193 *Therm Anal Calorim* 133:869–879. <https://doi.org/10.1007/s10973-018-7152-8>

1194 Contreras JL, Salmones J, Colín-Luna JA, et al (2014) Catalysts for H₂ production using the ethanol
1195 steam reforming (a review). *Int J Hydrog Energy* 39:18835–18853.
1196 <https://doi.org/10.1016/j.ijhydene.2014.08.072>

1197 Corma A, Fornés V, Rey F (1994) Hydrotalcites as Base Catalysts: Influence of the Chemical
1198 Composition and Synthesis Conditions on the Dehydrogenation of Isopropanol. *J Catal*
1199 148:205–212

1200 Corma A, Palomares AE, Rey F, Márquez F (1997) Simultaneous Catalytic Removal of SO_x and NO_x with
1201 Hydrotalcite-Derived Mixed Oxides Containing Copper, and Their Possibilities to Be Used in
1202 FCC Units. *J Catal* 170:140–149. <https://doi.org/10.1006/jcat.1997.1750>

1203 Costantino U, Marmottini F, Nocchetti M, Vivani R (1998) New Synthetic Routes to Hydrotalcite-Like
1204 Compounds – Characterisation and Properties of the Obtained Materials. *Eur J Inorg Chem*
1205 1998:1439–1446. [https://doi.org/10.1002/\(SICI\)1099-0682\(199810\)1998:10<1439::AID-](https://doi.org/10.1002/(SICI)1099-0682(199810)1998:10<1439::AID-EJIC1439>3.0.CO;2-1)
1206 [EJIC1439>3.0.CO;2-1](https://doi.org/10.1002/(SICI)1099-0682(199810)1998:10<1439::AID-EJIC1439>3.0.CO;2-1)

1207 Cui, Ma, Wang, et al (2019) High Performance of Mn-Doped MgAlO_x Mixed Oxides for Low
1208 Temperature NO_x Storage and Release. *Catalysts* 9:677.
1209 <https://doi.org/10.3390/catal9080677>

1210 Dadwhal M, Kim TW, Sahimi M, Tsotsis TT (2008) Study of CO₂ Diffusion and Adsorption on Calcined
1211 Layered Double Hydroxides: The Effect of Particle Size. *Ind Eng Chem Res* 47:6150–6157.
1212 <https://doi.org/10.1021/ie701701d>

1213 Dantas TCM, Junior VJF, Santos APB dos, et al (2015) CO₂ Adsorption on Modified Mg–Al-Layered
1214 Double Hydroxides. *Adsorpt Sci Technol* 33:165–173. [https://doi.org/10.1260/0263-](https://doi.org/10.1260/0263-6174.33.2.165)
1215 [6174.33.2.165](https://doi.org/10.1260/0263-6174.33.2.165)

1216 de Sá FP, Cunha BN, Nunes LM (2013) Effect of pH on the adsorption of Sunset Yellow FCF food dye
1217 into a layered double hydroxide (CaAl-LDH-NO₃). *Chem Eng J* 215–216:122–127.
1218 <https://doi.org/10.1016/j.cej.2012.11.024>

1219 de Souza G, Ávila VC, Marcílio NR, Perez-Lopez OW (2012) Synthesis Gas Production by Steam
1220 Reforming of Ethanol over M–Ni–Al Hydrotalcite-type Catalysts; M=Mg, Zn, Mo, Co. *Procedia*
1221 *Eng* 42:1805–1815. <https://doi.org/10.1016/j.proeng.2012.07.575>

1222 Dou Y, Zhou S, Oldani C, et al (2018) 5-Hydroxymethylfurfural production from dehydration of
1223 fructose catalyzed by Aquivion®/silica solid acid. *Fuel* 214:45–54.
1224 <https://doi.org/10.1016/j.fuel.2017.10.124>

1225 Dula R, Janik R, Machej T, et al (2007) Mn-containing catalytic materials for the total combustion of
1226 toluene: The role of Mn localisation in the structure of LDH precursor. *Catal Today* 119:327–
1227 331. <https://doi.org/10.1016/j.cattod.2006.08.060>

1228 El Rouby WMA, El-Dek SI, Goher ME, Noaemy SG (2018) Efficient water decontamination using
1229 layered double hydroxide beads nanocomposites. *Environ Sci Pollut Res*.
1230 <https://doi.org/10.1007/s11356-018-3257-7>

1231 El-Sayed M, Eshaq Gh, ElMetwally AE (2016) Adsorption of heavy metals from aqueous solutions by
1232 Mg–Al–Zn mingled oxides adsorbent. *Water Sci Technol* 74:1644–1657.
1233 <https://doi.org/10.2166/wst.2016.329>

1234 Fang Z, Liu B, Luo J, et al (2014) Efficient conversion of carbohydrates into 5-hydroxymethylfurfural
1235 catalyzed by the chromium-exchanged montmorillonite K-10 clay. *Biomass Bioenergy*
1236 60:171–177. <https://doi.org/10.1016/j.biombioe.2013.12.002>

1237 Forzatti P, Nova I, Tronconi E (2010) New “Enhanced NH₃-SCR” Reaction for NO_x Emission Control.
1238 Ind Eng Chem Res 49:10386–10391. <https://doi.org/10.1021/ie100600v>

1239 Fosso-Kankeu E, Mulaba-Bafubiandi AF, Mamba BB, et al (2010) A comprehensive study of physical
1240 and physiological parameters that affect bio-sorption of metal pollutants from aqueous
1241 solutions. Phys Chem Earth Parts ABC 35:672–678.
1242 <https://doi.org/10.1016/j.pce.2010.07.008>

1243 Gao C, Shi J-W, Fan Z, et al (2018) “Fast SCR” reaction over Sm-modified MnO_x-TiO₂ for promoting
1244 reduction of NO_x with NH₃. Appl Catal Gen 564:102–112.
1245 <https://doi.org/10.1016/j.apcata.2018.07.017>

1246 Gao Y, Zhang Z, Wu J, et al (2013) Comprehensive investigation of CO₂ adsorption on Mg–Al–CO₃
1247 LDH-derived mixed metal oxides. J Mater Chem A 1:12782.
1248 <https://doi.org/10.1039/c3ta13039h>

1249 García-Sancho C, Guil-López R, Pascual L, et al (2017) Optimization of nickel loading of mixed oxide
1250 catalyst ex-hydrotalcite for H₂ production by methane decomposition. Appl Catal Gen
1251 548:71–82. <https://doi.org/10.1016/j.apcata.2017.07.038>

1252 García-Sancho C, Guil-López R, Sebastián-López A, et al (2018) Hydrogen production by methane
1253 decomposition: A comparative study of supported and bulk ex-hydrotalcite mixed oxide
1254 catalysts with Ni, Mg and Al. Int J Hydrog Energy 43:9607–9621.
1255 <https://doi.org/10.1016/j.ijhydene.2018.04.021>

1256 Gastuche MC, Brown G, Mortland MM (1967) Mixed Magnesium-Aluminium Hydroxides I.
1257 Preparation and Characterization of Compounds Formed in Dialysed Systems. Clay Miner
1258 7:177–192

1259 Gennequin C, Barakat T, Tidahy HL, et al (2010a) Use and observation of the hydrotalcite “memory
1260 effect” for VOC oxidation. Catal Today 157:191–197.
1261 <https://doi.org/10.1016/j.cattod.2010.03.012>

1262 Gennequin C, Kouassi S, Tidahy L, et al (2010b) Co–Mg–Al oxides issued of hydrotalcite precursors for
1263 total oxidation of volatile organic compounds. Identification and toxicological impact of the
1264 by-products. Comptes Rendus Chim 13:494–501. <https://doi.org/10.1016/j.crci.2010.01.001>

1265 Gennequin C, Siffert S, Cousin R, Aboukais A (2009) Co–Mg–Al Hydrotalcite Precursors for Catalytic
1266 Total Oxidation of Volatile Organic Compounds. Top Catal 52:482–491.
1267 <https://doi.org/10.1007/s11244-009-9183-7>

1268 Gevers BR, Naseem S, Leuteritz A, Labuschagné FJWJ (2019) Comparison of nano-structured
1269 transition metal modified tri-metal MgMAI-LDHs (M = Fe, Zn, Cu, Ni, Co) prepared using co-
1270 precipitation. RSC Adv 9:28262–28275. <https://doi.org/10.1039/C9RA05452A>

1271 Gramigni F, Selleri T, Nova I, Tronconi E (2019) Catalyst systems for selective catalytic reduction + NO_x
1272 trapping: from fundamental understanding of the standard SCR reaction to practical
1273 applications for lean exhaust after-treatment. React Chem Eng 4:1165–1178.
1274 <https://doi.org/10.1039/C9RE00012G>

1275 Gunugunuri K, Roberts CA (2019) Direct NO_x decomposition catalyst with improved activity and
1276 selectivity

1277 Gunugunuri KR, Peck TC, Ling C, Jia H (2018) Catalyst for direct nox decomposition and a method of
1278 forming and using the catalyst

1279 Guo X, Wu Z, He M (2009) Removal of antimony(V) and antimony(III) from drinking water by
1280 coagulation–flocculation–sedimentation (CFS). *Water Res* 43:4327–4335.
1281 <https://doi.org/10.1016/j.watres.2009.06.033>

1282 Guo Z, Chen Y, Lu NL (2018) Multifunctional Nanocomposites for Energy and Environmental
1283 Applications. John Wiley & Sons

1284 Halabi MH, de Croon MHJM, van der Schaaf J, et al (2012a) High capacity potassium-promoted
1285 hydrotalcite for CO₂ capture in H₂ production. *Int J Hydrog Energy* 37:4516–4525.
1286 <https://doi.org/10.1016/j.ijhydene.2011.12.003>

1287 Halabi MH, de Croon MHJM, van der Schaaf J, et al (2012b) A novel catalyst–sorber system for an
1288 efficient H₂ production with in-situ CO₂ capture. *Int J Hydrog Energy* 37:4987–4996.
1289 <https://doi.org/10.1016/j.ijhydene.2011.12.025>

1290 He L, Berntsen H, Chen D (2010) Approaching Sustainable H₂ Production: Sorption Enhanced Steam
1291 Reforming of Ethanol[†]. *J Phys Chem A* 114:3834–3844. <https://doi.org/10.1021/jp906146y>

1292 He L, Berntsen H, Ochoa-Fernández E, et al (2009) Co–Ni Catalysts Derived from Hydrotalcite-Like
1293 Materials for Hydrogen Production by Ethanol Steam Reforming. *Top Catal* 52:206–217.
1294 <https://doi.org/10.1007/s11244-008-9157-1>

1295 Helwani Z, Othman MR, Aziz N, et al (2009) Technologies for production of biodiesel focusing on
1296 green catalytic techniques: A review. *Fuel Process Technol* 90:1502–1514.
1297 <https://doi.org/10.1016/j.fuproc.2009.07.016>

1298 Hibino T, Ohya H (2009) Synthesis of crystalline layered double hydroxides: Precipitation by using
1299 urea hydrolysis and subsequent hydrothermal reactions in aqueous solutions. *Appl Clay Sci*
1300 45:123–132. <https://doi.org/10.1016/j.clay.2009.04.013>

1301 Homsí D, Rached JA, Aouad S, et al (2017) Steam reforming of ethanol for hydrogen production over
1302 Cu/Co-Mg-Al-based catalysts prepared by hydrotalcite route. *Environ Sci Pollut Res* 24:9907–
1303 9913. <https://doi.org/10.1007/s11356-016-7480-9>

1304 Imanaka N, Masui T (2012) Advances in direct NO_x decomposition catalysts. *Appl Catal Gen* 431–
1305 432:1–8. <https://doi.org/10.1016/j.apcata.2012.02.047>

1306 Inayat A, Klumpp M, Schwieger W (2011) The urea method for the direct synthesis of ZnAl layered
1307 double hydroxides with nitrate as the interlayer anion. *Appl Clay Sci* 51:452–459.
1308 <https://doi.org/10.1016/j.clay.2011.01.008>

1309 Ishihara S, Sahoo P, Deguchi K, et al (2013) Dynamic Breathing of CO₂ by Hydrotalcite. *J Am Chem*
1310 *Soc* 135:18040–18043. <https://doi.org/10.1021/ja4099752>

1311 Iyi N, Matsumoto T, Kaneko Y, Kitamura K (2004) Deintercalation of Carbonate Ions from a
1312 Hydrotalcite-Like Compound: Enhanced Decarbonation Using Acid–Salt Mixed Solution.
1313 *Chem Mater* 16:2926–2932. <https://doi.org/10.1021/cm049579g>

1314 Jang HJ, Lee CH, Kim S, et al (2014) Hydrothermal Synthesis of K_2CO_3 -Promoted Hydrotalcite from
 1315 Hydroxide-Form Precursors for Novel High-Temperature CO_2 Sorbent. ACS Appl Mater
 1316 Interfaces 6:6914–6919. <https://doi.org/10.1021/am500720f>

1317 Jiang Y, Ling J, Xiao P, et al (2018) Simultaneous biogas purification and CO_2 capture by vacuum swing
 1318 adsorption using zeolite NaUSY. Chem Eng J 334:2593–2602.
 1319 <https://doi.org/10.1016/j.cej.2017.11.090>

1320 Jitianu M, Soiu ML, Zaharescu M, et al (2000) Comparative Study of Sol-Gel and Coprecipitated Ni-Al
 1321 Hydrotalcites. J Sol-Gel Sci Technol 19:453–457

1322 Kamal MS, Razzak SA, Hossain MM (2016) Catalytic oxidation of volatile organic compounds (VOCs) –
 1323 A review. Atmos Environ 140:117–134. <https://doi.org/10.1016/j.atmosenv.2016.05.031>

1324 Kameda T, Tochinali M, Kumagai S, Yoshioka T (2019a) Simultaneous treatment of HCl– SO_2 – NO_x gas
 1325 with Mg–Al layered double hydroxide intercalated with CO_3^{2-} and its recycling process. Int J
 1326 Environ Sci Technol. <https://doi.org/10.1007/s13762-019-02529-7>

1327 Kameda T, Tochinali M, Kumagai S, Yoshioka T (2020) Simultaneous treatment of HCl– SO_2 – NO_x gas
 1328 with Mg–Al layered double hydroxide intercalated with CO_3^{2-} and its recycling process. Int J
 1329 Environ Sci Technol 17:1179–1184. <https://doi.org/10.1007/s13762-019-02529-7>

1330 Kameda T, Tochinali M, Kumagai S, Yoshioka T (2019b) Treatment of NO_x using recyclable CO_3^{2-} -
 1331 intercalated Mg–Al layered double hydroxide. Atmospheric Pollut Res 10:1866–1872.
 1332 <https://doi.org/10.1016/j.apr.2019.07.018>

1333 Kameda T, Uchiyama N, Yoshioka T (2011) Removal of HCl, SO_2 , and NO by treatment of acid gas
 1334 with Mg–Al oxide slurry. Chemosphere 82:587–591.
 1335 <https://doi.org/10.1016/j.chemosphere.2010.11.020>

1336 Kannan S, Rives V, Knözinger H (2004) High-temperature transformations of Cu-rich hydrotalcites. J
 1337 Solid State Chem 177:319–331. <https://doi.org/10.1016/j.jssc.2003.08.023>

1338 Kannan S, Velu S, Ramkumar V, Swamy CS (1995) Synthesis and physicochemical properties of cobalt
 1339 aluminium hydrotalcites. J Mater Sci 30:1462–1468. <https://doi.org/10.1007/BF00375249>

1340 Karickhoff SW (1984) Organic Pollutant Sorption in Aquatic Systems. J Hydraul Eng 110:707–735.
 1341 [https://doi.org/10.1061/\(ASCE\)0733-9429\(1984\)110:6\(707\)](https://doi.org/10.1061/(ASCE)0733-9429(1984)110:6(707))

1342 Klemkaite K, Prosycevas I, Taraskevicius R, et al (2011) Synthesis and characterization of layered
 1343 double hydroxides with different cations (Mg, Co, Ni, Al), decomposition and reformation of
 1344 mixed metal oxides to layered structures. Cent Eur J Chem 9:275–282.
 1345 <https://doi.org/10.2478/s11532-011-0007-9>

1346 Klopogge JT, Hickey L, Frost RL (2004) The effects of synthesis pH and hydrothermal treatment on
 1347 the formation of zinc aluminum hydrotalcites. J Solid State Chem 177:4047–4057.
 1348 <https://doi.org/10.1016/j.jssc.2004.07.010>

1349 Klopogge JT, Hickey L, Trujillano R, et al (2006) Characterization of Intercalated Ni/Al Hydrotalcites
 1350 Prepared by the Partial Decomposition of Urea. Cryst Growth Des 6:1533–1536.
 1351 <https://doi.org/10.1021/cg0504612>

1352 Kovanda F, Grygar T, Dorníček V, et al (2005a) Thermal behaviour of Cu–Mg–Mn and Ni–Mg–Mn
1353 layered double hydroxides and characterization of formed oxides. *Appl Clay Sci* 28:121–136.
1354 <https://doi.org/10.1016/j.clay.2004.01.007>

1355 Kovanda F, Jiráťová K (2011a) Supported layered double hydroxide-related mixed oxides and their
1356 application in the total oxidation of volatile organic compounds. *Appl Clay Sci* 53:305–316.
1357 <https://doi.org/10.1016/j.clay.2010.12.030>

1358 Kovanda F, Jiráťová K (2011b) Supported mixed oxide catalysts for the total oxidation of volatile
1359 organic compounds. *Catal Today* 176:110–115. <https://doi.org/10.1016/j.cattod.2011.02.002>

1360 Kovanda F, Koloušek D, Cílová Z, Hulínský V (2005b) Crystallization of synthetic hydrotalcite under
1361 hydrothermal conditions. *Appl Clay Sci* 28:101–109.
1362 <https://doi.org/10.1016/j.clay.2004.01.009>

1363 Koyuncu I (2002) Reactive dye removal in dye/salt mixtures by nanofiltration membranes containing
1364 vinylsulphone dyes: effects of feed concentration and cross flow velocity. *Desalination*
1365 143:243–253. [https://doi.org/10.1016/S0011-9164\(02\)00263-1](https://doi.org/10.1016/S0011-9164(02)00263-1)

1366 Labuschagné FJWJ, Wiid A, Venter HP, et al (2018) Green synthesis of hydrotalcite from untreated
1367 magnesium oxide and aluminum hydroxide. *Green Chem Lett Rev* 11:18–28.
1368 <https://doi.org/10.1080/17518253.2018.1426791>

1369 Lau W-J, Ismail AF (2009) Polymeric nanofiltration membranes for textile dye wastewater treatment:
1370 Preparation, performance evaluation, transport modelling, and fouling control — a review.
1371 *Desalination* 245:321–348. <https://doi.org/10.1016/j.desal.2007.12.058>

1372 Lee G, Kang JY, Yan N, et al (2016) Simple preparation method for Mg–Al hydrotalcites as base
1373 catalysts. *J Mol Catal Chem* 423:347–355. <https://doi.org/10.1016/j.molcata.2016.07.018>

1374 Lehmann M, Zouboulis AI, Matis KA (1999) Removal of metal ions from dilute aqueous solutions: A
1375 comparative study of inorganic sorbent materials. *Chemosphere* 39:881–892.
1376 [https://doi.org/10.1016/S0045-6535\(99\)00031-4](https://doi.org/10.1016/S0045-6535(99)00031-4)

1377 Leinonen H, Lehto J, Mäkelä A (1994) Purification of nickel and zinc from waste waters of metal-
1378 plating plants by ion exchange. *React Polym* 23:221–228. [https://doi.org/10.1016/0923-1137\(94\)90024-8](https://doi.org/10.1016/0923-1137(94)90024-8)

1380 León M, Díaz E, Bennici S, et al (2010) Adsorption of CO₂ on Hydrotalcite-Derived Mixed Oxides:
1381 Sorption Mechanisms and Consequences for Adsorption Irreversibility. *Ind Eng Chem Res*
1382 49:3663–3671. <https://doi.org/10.1021/ie902072a>

1383 Li B, Zhang Y, Zhou X, et al (2016) Different dye removal mechanisms between monodispersed and
1384 uniform hexagonal thin plate-like MgAl–CO₃–LDH and its calcined product in efficient
1385 removal of Congo red from water. *J Alloys Compd* 673:265–271.
1386 <https://doi.org/10.1016/j.jallcom.2016.02.248>

1387 Li D, Wang L, Koike M, et al (2011) Steam reforming of tar from pyrolysis of biomass over Ni/Mg/Al
1388 catalysts prepared from hydrotalcite-like precursors. *Appl Catal B Environ* 102:528–538.
1389 <https://doi.org/10.1016/j.apcatb.2010.12.035>

1390 Li LD, Yu JJ, Hao ZP, Xu ZP (2007) Novel Ru–Mg–Al–O Catalyst Derived from Hydrotalcite-like
 1391 Compound for NO Storage/Decomposition/Reduction. *J Phys Chem C* 111:10552–10559.
 1392 <https://doi.org/10.1021/jp0678352>

1393 Li S, Guo Y, Xiao M, et al (2019a) Enhanced arsenate removal from aqueous solution by Mn-doped
 1394 MgAl-layered double hydroxides. *Environ Sci Pollut Res* 26:12014–12024.
 1395 <https://doi.org/10.1007/s11356-019-04667-4>

1396 Li X, Du Y, Guo X, et al (2019b) Synthesis of a Novel NiMnTi Mixed Metal Oxides from LDH Precursor
 1397 and Its Catalytic Application for Selective Catalytic Reduction of NO_x with NH₃. *Catal Lett*
 1398 149:456–464. <https://doi.org/10.1007/s10562-018-2626-7>

1399 Li Z, Chen F, Yuan L, et al (2012) Uranium(VI) adsorption on graphene oxide nanosheets from
 1400 aqueous solutions. *Chem Eng J* 210:539–546. <https://doi.org/10.1016/j.cej.2012.09.030>

1401 Liao L, Zhao N, Xia Z (2012) Hydrothermal synthesis of Mg–Al layered double hydroxides (LDHs) from
 1402 natural brucite and Al(OH)₃. *Mater Res Bull* 47:3897–3901.
 1403 <https://doi.org/10.1016/j.materresbull.2012.07.007>

1404 Lin Y, Wang X, Hao J, et al (2019) Preparation of CuZnAl hydrotalcite-like catalysts for AsH₃
 1405 abatement at low temperatures. *Catal Commun* 118:51–55.
 1406 <https://doi.org/10.1016/j.catcom.2018.03.028>

1407 Lopez T, Bosch P, Asomoza M, et al (1997a) DTA-TGA and FTIR spectroscopies of sol-gel hydrotalcites:
 1408 aluminum source effect on physicochemical properties. *Mater Lett* 31:311–316

1409 Lopez T, Bosch P, Ramos E, et al (1996) Synthesis and Characterization of Sol–Gel Hydrotalcites.
 1410 Structure and Texture[†]. *Langmuir* 12:189–192. <https://doi.org/10.1021/la940703s>

1411 Lopez T, Ramos E, Bosch P, et al (1997b) DTA and TGA characterization of sol-gel hydrotalcites. *Mater*
 1412 *Lett* 30:279–282. [https://doi.org/10.1016/S0167-577X\(96\)00214-5](https://doi.org/10.1016/S0167-577X(96)00214-5)

1413 Lourvanij K, Rorrer GL (1994) Dehydration of glucose to organic acids in microporous pillared clay
 1414 catalysts. *Appl Catal Gen* 109:147–165. [https://doi.org/10.1016/0926-860X\(94\)85008-9](https://doi.org/10.1016/0926-860X(94)85008-9)

1415 Lukyanov DB, Sill G, d'Itri JL, Hall WK (1995) Comparison of Catalyzed and Homogeneous Reactions of
 1416 Hydrocarbons for Selective Catalytic Reduction (SCR) of NO_x. *J Catal* 153:265–274

1417 Lv L, He J, Wei M, et al (2006) Factors influencing the removal of fluoride from aqueous solution by
 1418 calcined Mg–Al–CO₃ layered double hydroxides. *J Hazard Mater* 133:119–128.
 1419 <https://doi.org/10.1016/j.jhazmat.2005.10.012>

1420 Mahmoud R, Moaty SA, Mohamed F, Farghali A (2017) Comparative Study of Single and Multiple
 1421 Pollutants System Using Ti–Fe Chitosan LDH Adsorbent with High Performance in
 1422 Wastewater Treatment. *J Chem Eng Data* 62:3703–3722.
 1423 <https://doi.org/10.1021/acs.jced.7b00453>

1424 Mahzoul H, Brilhac JF, Gilot P (1999) Experimental and mechanistic study of NO_x adsorption over
 1425 NO_x trap catalysts. *Appl Catal B Environ* 20:47–55. [https://doi.org/10.1016/S0926-3373\(98\)00093-9](https://doi.org/10.1016/S0926-3373(98)00093-9)

- 1427 Mao G, Tamaura Y (1993) SYNTHESIS AND CO₂ ADSORPTION FEATURES OF A HYDROTALCITE-LIKE
1428 COMPOUND OF THE Mg²⁺-Al³⁺-Fe(CN)₆⁴⁻ SYSTEM WITH HIGH LAYER-CHARGE DENSITY.
1429 Clays Clay Miner 41:7
- 1430 Marquovich M, Medina F, Montan D (2001) Hydrogen production via steam reforming of sunflower
1431 oil over Ni/Al catalysts from hydrotalcite materials. Catal Commun 6
- 1432 Mathieu Y, Tzanis L, Soulard M, et al (2013) Adsorption of SO_x by oxide materials: A review. Fuel
1433 Process Technol 114:81–100. <https://doi.org/10.1016/j.fuproc.2013.03.019>
- 1434 Mazur LP, Pozdniakova TA, Mayer DA, et al (2016) Design of a fixed-bed ion-exchange process for the
1435 treatment of rinse waters generated in the galvanization process using Laminaria hyperborea
1436 as natural cation exchanger. Water Res 90:354–368.
1437 <https://doi.org/10.1016/j.watres.2015.12.027>
- 1438 Megías-Sayago C, Bingre R, Huang L, et al (2019) CO₂ Adsorption Capacities in Zeolites and Layered
1439 Double Hydroxide Materials. Front Chem 7:551. <https://doi.org/10.3389/fchem.2019.00551>
- 1440 Mikulová Z, Čuba P, Balabánová J, et al (2007) Calcined Ni—Al layered double hydroxide as a catalyst
1441 for total oxidation of volatile organic compounds: Effect of precursor crystallinity. Chem Pap
1442 61:. <https://doi.org/10.2478/s11696-007-0006-7>
- 1443 Milutinović-Nikolić A, Maksin D, Jović-Jovičić N, et al (2014) Removal of ⁹⁹Tc(VII) by organo-modified
1444 bentonite. Appl Clay Sci 95:294–302. <https://doi.org/10.1016/j.clay.2014.04.027>
- 1445 Miyata S (1975) The Syntheses of Hydrotalcite-like Compounds and their Structures and Physico-
1446 chemical Properties I. The Systems Mg²⁺-Al³⁺-NO₃⁻, Mg²⁺-Al³⁺-Cl⁻, Mg²⁺-Al³⁺-ClO₄⁻, Ni²⁺-
1447 Al³⁺-Cl⁻ and Zn²⁺-Al³⁺-Cl⁻. Clays Clay Miner 23:369–375
- 1448 Miyata S (1980) Physico-Chemical Properties of Synthetic Hydrotalcites in Relation to Composition.
1449 Clays Clay Miner 28:50–56. <https://doi.org/10.1346/CCMN.1980.0280107>
- 1450 Montañez MK, Molina R, Moreno S (2014) Nickel catalysts obtained from hydrotalcites by
1451 coprecipitation and urea hydrolysis for hydrogen production. Int J Hydrog Energy 39:8225–
1452 8237. <https://doi.org/10.1016/j.ijhydene.2014.03.103>
- 1453 Moreira RFPM, Soares JL, Casarin GL, Rodrigues AE (2006) Adsorption of CO₂ on Hydrotalcite-like
1454 Compounds in a Fixed Bed. Sep Sci Technol 41:341–357.
1455 <https://doi.org/10.1080/01496390500496827>
- 1456 Mrad R, Cousin R, Saliba NA, et al (2015) Degradation of VOCs and NO_x over Mg(Cu)–AlFe mixed
1457 oxides derived from hydrotalcite-like compounds. Comptes Rendus Chim 18:351–357.
1458 <https://doi.org/10.1016/j.crci.2014.08.005>
- 1459 Naseem S, Gevers B, Boldt R, et al (2019) Comparison of transition metal (Fe, Co, Ni, Cu, and Zn)
1460 containing tri-metal layered double hydroxides (LDHs) prepared by urea hydrolysis. RSC Adv
1461 9:3030–3040. <https://doi.org/10.1039/C8RA10165E>
- 1462 Ogawa M, Asai S (2000) Hydrothermal Synthesis of Layered Double Hydroxide–Deoxycholate
1463 Intercalation Compounds. Chem Mater 12:3253–3255. <https://doi.org/10.1021/cm000455n>

- 1464 Othman MR, Rasid NM, Fernando WJN (2006) Effects of thermal treatment on the micro-structures
1465 of co-precipitated and sol–gel synthesized (Mg–Al) hydrotalcites. *Microporous Mesoporous*
1466 *Mater* 93:23–28. <https://doi.org/10.1016/j.micromeso.2006.02.007>
- 1467 Özacar M, Şengil İA (2002) Adsorption of Acid Dyes from Aqueous Solutions by Calcined Alunite and
1468 Granular Activated Carbon. *Adsorption* 8:301–308.
1469 <https://doi.org/10.1023/A:1021585413857>
- 1470 Palacio LA, Velásquez J, Echavarría A, et al (2010) Total oxidation of toluene over calcined trimetallic
1471 hydrotalcites type catalysts. *J Hazard Mater* 177:407–413.
1472 <https://doi.org/10.1016/j.jhazmat.2009.12.048>
- 1473 Palomares A, Lopez-Nieto JM, Lazaro FJ, et al (1999) Reactivity in the removal of SO₂ and NO_x on
1474 Co/Mg/Al mixed oxides derived from hydrotalcites. *Appl Catal B Environ* 20:257–266.
1475 [https://doi.org/10.1016/S0926-3373\(98\)00121-0](https://doi.org/10.1016/S0926-3373(98)00121-0)
- 1476 Paredes SP, Fetter G, Bosch P, Bulbulian S (2006) Sol-gel synthesis of hydrotalcite — like compounds.
1477 *J Mater Sci* 41:3377–3382. <https://doi.org/10.1007/s10853-005-5347-4>
- 1478 Park S, Kwon D, Kang JY, Jung JC (2018) Influence of the preparation method on the catalytic activity
1479 of Mg Al hydrotalcites as solid base catalysts. *Green Energy Environ.*
1480 <https://doi.org/10.1016/j.gee.2018.11.003>
- 1481 Pavan PC, Crepaldi EL, de A. Gomes G, Valim JB (1999) Adsorption of sodium dodecylsulfate on a
1482 hydrotalcite-like compound. Effect of temperature, pH and ionic strength. *Colloids Surf*
1483 *Physicochem Eng Asp* 154:399–410. [https://doi.org/10.1016/S0927-7757\(98\)00847-4](https://doi.org/10.1016/S0927-7757(98)00847-4)
- 1484 Pavan PC, Crepaldi EL, Valim JB (2000) Sorption of Anionic Surfactants on Layered Double Hydroxides.
1485 *J Colloid Interface Sci* 229:346–352. <https://doi.org/10.1006/jcis.2000.7031>
- 1486 Perez-Lopez OW, Senger A, Marcilio NR, Lansarin MA (2006) Effect of composition and thermal
1487 pretreatment on properties of Ni–Mg–Al catalysts for CO₂ reforming of methane. *Appl Catal*
1488 *Gen* 303:234–244. <https://doi.org/10.1016/j.apcata.2006.02.024>
- 1489 Pinnavaia TJ, Amarasekera J, Polansky CA (1991) Process using sorbents for the removal of sox from
1490 flue gas and other gas streams
- 1491 Pinnavaia TJ, Amarasekera J, Polansky CA (1992) Process using sorbents for the removal of SO_x from
1492 flue gas
- 1493 Prince J, Montoya A, Ferrat G, Valente JS (2009) Proposed General Sol–Gel Method to Prepare
1494 Multimetallic Layered Double Hydroxides: Synthesis, Characterization, and Envisaged
1495 Application. *Chem Mater* 21:5826–5835. <https://doi.org/10.1021/cm902741c>
- 1496 Prinetto F, Ghiotti G, Graffin P, Tichit D (2000) Synthesis and characterization of sol–gel Mg/Al and
1497 Ni/Al layered double hydroxides and comparison with co-precipitated samples. *Microporous*
1498 *Mesoporous Mater* 39:229–247. [https://doi.org/10.1016/S1387-1811\(00\)00197-9](https://doi.org/10.1016/S1387-1811(00)00197-9)
- 1499 Radha S, Navrotsky A (2014) Energetics of CO₂ Adsorption on Mg–Al Layered Double Hydroxides and
1500 Related Mixed Metal Oxides. *J Phys Chem C* 118:29836–29844.
1501 <https://doi.org/10.1021/jp508678k>

1502 Rahmanian O, Dinari M, Neamati S (2018) Synthesis and characterization of citrate intercalated
 1503 layered double hydroxide as a green adsorbent for Ni²⁺ and Pb²⁺ removal. *Environ Sci Pollut*
 1504 *Res* 25:36267–36277. <https://doi.org/10.1007/s11356-018-3584-8>

1505 Ram Reddy MK, Xu ZP, Diniz da Costa JC (2008) Influence of Water on High-Temperature CO₂
 1506 Capture Using Layered Double Hydroxide Derivatives. *Ind Eng Chem Res* 47:2630–2635.
 1507 <https://doi.org/10.1021/ie0716060>

1508 Ram Reddy MK, Xu ZP, Lu GQ (Max), Diniz da Costa JC (2006) Layered Double Hydroxides for CO₂
 1509 Capture: Structure Evolution and Regeneration. *Ind Eng Chem Res* 45:7504–7509.
 1510 <https://doi.org/10.1021/ie060757k>

1511 Ramírez-Moreno MJ, Romero-Ibarra IC, Hernández-Pérez MA, Pfeiffer H (2014) CO₂ Adsorption at
 1512 Elevated Pressure and Temperature on Mg–Al Layered Double Hydroxide. *Ind Eng Chem Res*
 1513 53:8087–8094. <https://doi.org/10.1021/ie5010515>

1514 Ramos E, Lopez T, Bosch P, et al (1997) Thermal stability of sol-gel hydrotalcites. *J Sol-Gel Sci Technol*
 1515 8:437–442. <https://doi.org/10.1007/BF02436879>

1516 Ramos-Ramírez E, Ortega NLG, Soto CAC, Gutiérrez MTO (2009) Adsorption isotherm studies of
 1517 chromium (VI) from aqueous solutions using sol–gel hydrotalcite-like compounds. *J Hazard*
 1518 *Mater* 172:1527–1531. <https://doi.org/10.1016/j.jhazmat.2009.08.023>

1519 Rao MM, Reddy BR, Jayalakshmi M, et al (2005) Hydrothermal synthesis of Mg–Al hydrotalcites by
 1520 urea hydrolysis. *Mater Res Bull* 40:347–359.
 1521 <https://doi.org/10.1016/j.materresbull.2004.10.007>

1522 Roelofs JCAA, Lensveld DJ, van Dillen AJ, de Jong KP (2001) On the Structure of Activated
 1523 Hydrotalcites as Solid Base Catalysts for Liquid-Phase Aldol Condensation. *J Catal* 203:184–
 1524 191. <https://doi.org/10.1006/jcat.2001.3295>

1525 Rosatella AA, Simeonov SP, Frade RFM, Afonso CAM (2011) 5-Hydroxymethylfurfural (HMF) as a
 1526 building block platform: Biological properties, synthesis and synthetic applications. *Green*
 1527 *Chem* 13:754. <https://doi.org/10.1039/c0gc00401d>

1528 Rubí H, Fall C, Ortega RE (2009) Pollutant removal from oily wastewater discharged from car washes
 1529 through sedimentation–coagulation. *Water Sci Technol* 59:2359–2369.
 1530 <https://doi.org/10.2166/wst.2009.307>

1531 Sakano M, Kawamura S (2018) Method for producing NO_x storage-reduction catalyst

1532 Sato T, Fujita H, Endo T, Shimada M (1988) Synthesis Of Hydrotalcite-Like Compounds And Their
 1533 Physico-Chemical Properties. *React Solids* 5:219–228

1534 Sedlmair Ch, Seshan K, Jentys A, Lercher JA (2003) Elementary steps of NO_x adsorption and surface
 1535 reaction on a commercial storage–reduction catalyst. *J Catal* 214:308–316.
 1536 [https://doi.org/10.1016/S0021-9517\(02\)00085-4](https://doi.org/10.1016/S0021-9517(02)00085-4)

1537 Seftel EM, Niarchos M, Mitropoulos Ch, et al (2015) Photocatalytic removal of phenol and
 1538 methylene-blue in aqueous media using TiO₂@LDH clay nanocomposites. *Catal Today*
 1539 252:120–127. <https://doi.org/10.1016/j.cattod.2014.10.030>

1540 Seki Y, Yurdakoç K (2005) Paraquat adsorption onto clays and organoclays from aqueous solution. J
1541 Colloid Interface Sci 287:1–5. <https://doi.org/10.1016/j.jcis.2004.10.072>

1542 Shan R, Yan L, Yang K, et al (2014) Magnetic Fe₃O₄/MgAl-LDH composite for effective removal of
1543 three red dyes from aqueous solution. Chem Eng J 252:38–46.
1544 <https://doi.org/10.1016/j.cej.2014.04.105>

1545 Sharma SK, Kushwaha PK, Srivastava VK, et al (2007) Effect of Hydrothermal Conditions on Structural
1546 and Textural Properties of Synthetic Hydrotalcites of Varying Mg/Al Ratio. Ind Eng Chem Res
1547 46:4856–4865. <https://doi.org/10.1021/ie061438w>

1548 Sheng T, Zhang Z, Hu Y, et al (2019) Adsorption of phosphorus by using magnetic Mg–Al-, Zn–Al- and
1549 Mg–Fe-layered double hydroxides: comparison studies and adsorption mechanism. Environ
1550 Sci Pollut Res 26:7102–7114. <https://doi.org/10.1007/s11356-019-04191-5>

1551 Sikander U, Samsudin MF, Sufian S, et al (2018) Tailored hydrotalcite-based Mg-Ni-Al catalyst for
1552 hydrogen production via methane decomposition: Effect of nickel concentration and spinel-
1553 like structures. Int J Hydrog Energy. <https://doi.org/10.1016/j.ijhydene.2018.10.224>

1554 Sikander U, Sufian S, Salam MA (2017) A review of hydrotalcite based catalysts for hydrogen
1555 production systems. Int J Hydrog Energy 42:19851–19868.
1556 <https://doi.org/10.1016/j.ijhydene.2017.06.089>

1557 Silletti BA, Adams RT, Sigmon SM, et al (2006) A novel Pd/MgAlO_x catalyst for NO_x storage-reduction.
1558 Catal Today 114:64–71. <https://doi.org/10.1016/j.cattod.2006.02.003>

1559 Silva JM, Trujillano R, Rives V, et al (2017) High temperature CO₂ sorption over modified
1560 hydrotalcites. Chem Eng J 325:25–34. <https://doi.org/10.1016/j.cej.2017.05.032>

1561 Smalenskaite A, Vieira DEL, Salak AN, et al (2017) A comparative study of co-precipitation and sol-gel
1562 synthetic approaches to fabricate cerium-substituted Mg Al layered double hydroxides with
1563 luminescence properties. Appl Clay Sci 143:175–183.
1564 <https://doi.org/10.1016/j.clay.2017.03.036>

1565 Solovov VA, Nikolenko NV, Kovalenko VL, et al (2018) Synthesis of Ni(II)-Ti(IV) Layered Double
1566 Hydroxides using Coprecipitation at High Supersaturation Method. J Eng Appl Sci 13:9652–
1567 9656

1568 Song W, Wang X, Wang Q, et al (2015) Plasma-induced grafting of polyacrylamide on graphene oxide
1569 nanosheets for simultaneous removal of radionuclides. Phys Chem Chem Phys 17:398–406.
1570 <https://doi.org/10.1039/C4CP04289A>

1571 Sun Y, Wang X, Ai Y, et al (2017) Interaction of sulfonated graphene oxide with U(VI) studied by
1572 spectroscopic analysis and theoretical calculations. Chem Eng J 310:292–299.
1573 <https://doi.org/10.1016/j.cej.2016.10.122>

1574 Tanasoi S, Tanchoux N, Urdă A, et al (2009) New Cu-based mixed oxides obtained from LDH
1575 precursors, catalysts for methane total oxidation. Appl Catal Gen 363:135–142.
1576 <https://doi.org/10.1016/j.apcata.2009.05.007>

1577 Tang N, He T, Liu J, et al (2018) New Insights into CO₂ Adsorption on Layered Double Hydroxide
1578 (LDH)-Based Nanomaterials. Nanoscale Res Lett 13:. <https://doi.org/10.1186/s11671-018-2471-z>
1579

1580 Thevenot F, Szymanski R, Chaumette P (1989) PREPARATION AND CHARACTERIZATION OF Al-RICH
1581 Zn-Al HYDROTALCITE-LIKE COMPOUNDS. *Clays Clay Miner* 37:7

1582 Thomas N (2012) Mechanochemical synthesis of layered hydroxy salts. *Mater Res Bull* 47:3568–3572.
1583 <https://doi.org/10.1016/j.materresbull.2012.06.057>

1584 Thouchprasitchaia N, Pintuyothin N, Pongstabodee S (2018) Optimization of CO₂ adsorption capacity
1585 and cyclical adsorption/desorption on tetraethylenepentamine-supported surface-modified
1586 hydrotalcite. *J Environ Sci* 65:293–305. <https://doi.org/10.1016/j.jes.2017.02.015>

1587 Tichit D, Rolland A, Prinetto F, et al (2002) Comparison of the structural and acid–base properties of
1588 Ga- and Al-containing layered double hydroxides obtained by microwave irradiation and
1589 conventional ageing of synthesis gels. *J Mater Chem* 12:3832–3838.
1590 <https://doi.org/10.1039/B203376N>

1591 Tsuji M, Mao G, Yoshida T, Tamaura Y (1993) Hydrotalcites with an extended Al³⁺-substitution:
1592 Synthesis, simultaneous TG-DTA-MS study, and their CO₂ adsorption behaviors. *J Mater Res*
1593 8:1137–1142. <https://doi.org/10.1557/JMR.1993.1137>

1594 Tzompantzi F, Mantilla A, Bañuelos F, et al (2011) Improved Photocatalytic Degradation of Phenolic
1595 Compounds With ZnAl Mixed Oxides Obtained from LDH Materials. *Top Catal* 54:257–263.
1596 <https://doi.org/10.1007/s11244-011-9656-3>

1597 Ulibarri M (2001) Adsorption of anionic species on hydrotalcite-like compounds: effect of interlayer
1598 anion and crystallinity. *Appl Clay Sci* 18:17–27. [https://doi.org/10.1016/S0169-1317\(00\)00026-0](https://doi.org/10.1016/S0169-1317(00)00026-0)

1600 Umeno T, Hanzama M, Hayashi Y (2019) NO_x storage reduction catalyst for purifying exhaust gas and
1601 exhaust gas purification method using said catalyst

1602 Valeikiene L, Paitian R, Grigoraviciute-Puroniene I, et al (2019) Transition metal substitution effects in
1603 sol-gel derived Mg₃-xM_x/Al₁ (M = Mn, Co, Ni, Cu, Zn) layered double hydroxides. *Mater*
1604 *Chem Phys* 237:121863. <https://doi.org/10.1016/j.matchemphys.2019.121863>

1605 Valente JS, Cantú MS, Cortez JGH, et al (2007) Preparation and Characterization of Sol–Gel MgAl
1606 Hydrotalcites with Nanocapsular Morphology. *J Phys Chem C* 111:642–651.
1607 <https://doi.org/10.1021/jp065283h>

1608 Valente JS, Lima E, Toledo-Antonio JA, et al (2010) Comprehending the Thermal Decomposition and
1609 Reconstruction Process of Sol–Gel MgAl Layered Double Hydroxides. *J Phys Chem C*
1610 114:2089–2099. <https://doi.org/10.1021/jp910538r>

1611 Valente JS, Prince J, Maubert AM, et al (2009) Physicochemical Study of Nanocapsular Layered
1612 Double Hydroxides Evolution. *J Phys Chem C* 113:5547–5555.
1613 <https://doi.org/10.1021/jp810293y>

1614 Valente JS, Quintana-Solorzano R (2011) Novel SO_x removal catalysts for the FCC process:
1615 Manufacture method, characterization, and pilot-scale testing. *Energy Environ Sci* 4:4096.
1616 <https://doi.org/10.1039/c1ee01197a>

1617 van Putten R-J, van der Waal JC, de Jong E, et al (2013) Hydroxymethylfurfural, A Versatile Platform
1618 Chemical Made from Renewable Resources. *Chem Rev* 113:1499–1597.
1619 <https://doi.org/10.1021/cr300182k>

1620 Vierheilig A (2003) Compounds, compositions and methods to reduce SO_x emissions from FCC units

1621 Wan S, Wang S, Li Y, Gao B (2017) Functionalizing biochar with Mg–Al and Mg–Fe layered double
1622 hydroxides for removal of phosphate from aqueous solutions. *J Ind Eng Chem* 47:246–253.
1623 <https://doi.org/10.1016/j.jiec.2016.11.039>

1624 Wang J, Stevens LA, Drage TC, et al (2012a) Preparation and CO₂ adsorption of amine modified
1625 layered double hydroxide via anionic surfactant-mediated route. *Chem Eng J* 181–182:267–
1626 275. <https://doi.org/10.1016/j.ces.2011.11.078>

1627 Wang J, Stevens LA, Drage TC, Wood J (2012b) Preparation and CO₂ adsorption of amine modified
1628 Mg–Al LDH via exfoliation route. *Chem Eng Sci* 68:424–431.
1629 <https://doi.org/10.1016/j.ces.2011.09.052>

1630 Wang Q, Tay HH, Ng DJW, et al (2010) The Effect of Trivalent Cations on the Performance of Mg–M–
1631 CO₃ Layered Double Hydroxides for High-Temperature CO₂ Capture. *ChemSusChem* 3:965–
1632 973. <https://doi.org/10.1002/cssc.201000099>

1633 Wang R, Wu X, Zou C, et al (2018) NO_x Removal by Selective Catalytic Reduction with Ammonia over
1634 a Hydrotalcite-Derived NiFe Mixed Oxide. *Catalysts* 8:384.
1635 <https://doi.org/10.3390/catal8090384>

1636 Wang X, Sun Y, Alsaedi A, et al (2015) Interaction mechanism of Eu(III) with MX-80 bentonite studied
1637 by batch, TRLFS and kinetic desorption techniques. *Chem Eng J* 264:570–576.
1638 <https://doi.org/10.1016/j.ces.2014.11.136>

1639 Wang Y, Du T, Liu L, et al (2017) A Review of Layered Double Hydroxides as Intermediate-
1640 temperature CO₂ Adsorbents. In: *Proceedings of the 2017 6th International Conference on*
1641 *Energy, Environment and Sustainable Development (ICEESD 2017)*. Atlantis Press, Zhuhai,
1642 China

1643 Wang Z, Liu F, Lu C (2011) Mg–Al–carbonate layered double hydroxides as a novel catalyst of luminol
1644 chemiluminescence. *Chem Commun* 47:5479. <https://doi.org/10.1039/c1cc10520e>

1645 Wu L, Peng B, Li Q, et al (2019a) Formation of high crystalline LDH sludge for removing Cu and Zn
1646 from wastewater by controlled double-jet precipitation. *Environ Sci Pollut Res* 26:19665–
1647 19675. <https://doi.org/10.1007/s11356-019-05161-7>

1648 Wu X, Wang R, Du Y, et al (2019b) NO_x removal by selective catalytic reduction with ammonia over
1649 hydrotalcite-derived NiTi mixed oxide. *New J Chem* 43:2640–2648.
1650 <https://doi.org/10.1039/C8NJ05280H>

1651 Wu Y-J, Li P, Yu J-G, et al (2013) K-Promoted Hydrotalcites for CO₂ Capture in Sorption Enhanced
1652 Reactions. *Chem Eng Technol* 36:567–574. <https://doi.org/10.1002/ceat.201200694>

1653 Xu S, Liao M, Zeng H, et al (2016) Preparation Behavior of the Mg–Fe Hydrotalcite by Urea Method
1654 and Its Cr(VI) Sorption Property. *J Nanosci Nanotechnol* 16:3122–3131.
1655 <https://doi.org/10.1166/jnn.2016.12411>

1656 Xu ZP, Lu GQ (Max) (2005) Hydrothermal Synthesis of Layered Double Hydroxides (LDHs) from Mixed
1657 MgO and Al₂O₃: LDH Formation Mechanism. *Chem Mater* 17:1055–1062.
1658 <https://doi.org/10.1021/cm048085g>

1659 Xu ZP, Zhang J, Adebajo MO, et al (2011) Catalytic applications of layered double hydroxides and
1660 derivatives. *Appl Clay Sci* 53:139–150. <https://doi.org/10.1016/j.clay.2011.02.007>

1661 Xue L, Gao B, Wan Y, et al (2016) High efficiency and selectivity of MgFe-LDH modified wheat-straw
1662 biochar in the removal of nitrate from aqueous solutions. *J Taiwan Inst Chem Eng* 63:312–
1663 317. <https://doi.org/10.1016/j.jtice.2016.03.021>

1664 Yang D, Song S, Zou Y, et al (2017) Rational design and synthesis of monodispersed hierarchical SiO₂
1665 @layered double hydroxide nanocomposites for efficient removal of pollutants from
1666 aqueous solution. *Chem Eng J* 323:143–152. <https://doi.org/10.1016/j.cej.2017.03.158>

1667 Yang L, Shahrivari Z, Liu PKT, et al (2005) Removal of Trace Levels of Arsenic and Selenium from
1668 Aqueous Solutions by Calcined and Uncalcined Layered Double Hydroxides (LDH). *Ind Eng*
1669 *Chem Res* 44:6804–6815. <https://doi.org/10.1021/ie049060u>

1670 Yang P, Yu J, Wang Z, et al (2004) Urea method for the synthesis of hydrotalcites. *React Kinet Catal*
1671 *Lett* 83:275–282. <https://doi.org/10.1023/B:REAC.0000046087.86802.c2>

1672 Yang R, Gao Y, Wang J, Wang Q (2014) Layered double hydroxide (LDH) derived catalysts for
1673 simultaneous catalytic removal of soot and NO_x. *Dalton Trans* 43:10317.
1674 <https://doi.org/10.1039/c3dt52896k>

1675 Yang S, Ren X, Zhao G, et al (2015) Competitive sorption and selective sequence of Cu(II) and Ni(II) on
1676 montmorillonite: Batch, modeling, EPR and XAS studies. *Geochim Cosmochim Acta* 166:129–
1677 145. <https://doi.org/10.1016/j.gca.2015.06.020>

1678 Yang Z, Choi K-M, Jiang N, Park S-E (2007) Microwave Synthesis of Hydrotalcite by Urea Hydrolysis.
1679 *Bull Korean Chem Soc* 28:2029–2033

1680 Yang Z, Wei J, Zeng G, et al (2019) A review on strategies to LDH-based materials to improve
1681 adsorption capacity and photoreduction efficiency for CO₂. *Coord Chem Rev* 386:154–182.
1682 <https://doi.org/10.1016/j.ccr.2019.01.018>

1683 Yokomichi Y, Nakayama T, Okada O, et al (1996) Fundamental study on the NO_x direct decomposition
1684 catalysts. *Catal Today* 29:155–160. [https://doi.org/10.1016/0920-5861\(95\)00252-9](https://doi.org/10.1016/0920-5861(95)00252-9)

1685 Yong Z, Mata V, Rodrigues A (2002) Adsorption of carbon dioxide at high temperature—a review. *Sep*
1686 *Purif Technol* 26:195–205. [https://doi.org/10.1016/S1383-5866\(01\)00165-4](https://doi.org/10.1016/S1383-5866(01)00165-4)

1687 Yoo JS, Bhattacharyya AA, Radlowski CA, Karch JA (1992) Advanced De-SO_x catalyst: Mixed solid
1688 solution spinels with cerium oxide. *Appl Catal B Environ* 1:169–189.
1689 [https://doi.org/10.1016/0926-3373\(92\)80022-R](https://doi.org/10.1016/0926-3373(92)80022-R)

1690 Yu J, Cheng J, Ma C, et al (2009) NO_x decomposition, storage and reduction over novel mixed oxide
1691 catalysts derived from hydrotalcite-like compounds. *J Colloid Interface Sci* 333:423–30.
1692 <https://doi.org/10.1016/j.jcis.2009.02.022>

1693 Yu JJ, Jiang Z, Zhu L, et al (2006) Adsorption/Desorption Studies of NO_x on Well-Mixed Oxides
1694 Derived from Co–Mg/Al Hydrotalcite-like Compounds. *J Phys Chem B* 110:4291–4300.
1695 <https://doi.org/10.1021/jp056473f>

1696 Yu JJ, Wang XP, Tao YX, et al (2007) Effective NO_x Decomposition and Storage/Reduction over
 1697 Mixed Oxides Derived from Layered Double Hydroxides. *Ind Eng Chem Res* 46:5794–5797.
 1698 <https://doi.org/10.1021/ie0705958>

1699 Yu S, Wang X, Chen Z, et al (2017) Layered double hydroxide intercalated with aromatic acid anions
 1700 for the efficient capture of aniline from aqueous solution. *J Hazard Mater* 321:111–120.
 1701 <https://doi.org/10.1016/j.jhazmat.2016.09.009>

1702 Yu Y, Li X, Krishna R, et al (2018) Enhancing CO₂ Adsorption and Separation Properties of
 1703 Aluminophosphate Zeolites by Isomorphous Heteroatom Substitutions. *ACS Appl Mater*
 1704 *Interfaces* 10:43570–43577. <https://doi.org/10.1021/acsami.8b11235>

1705 Zakrzewska ME, Bogel-Lukasik E, Bogel-Lukasik R (2011) Ionic Liquid-Mediated Formation of 5-
 1706 Hydroxymethylfurfural—A Promising Biomass-Derived Building Block. *Chem Rev* 111:397–
 1707 417. <https://doi.org/10.1021/cr100171a>

1708 Zardin L, Perez-Lopez OW (2017) Hydrogen production by methane decomposition over Co-Al mixed
 1709 oxides derived from hydrotalcites: Effect of the catalyst activation with H₂ or CH₄. *Int J*
 1710 *Hydrog Energy* 42:7895–7907. <https://doi.org/10.1016/j.ijhydene.2017.02.153>

1711 Zeng H-Y, Deng X, Wang Y-J, Liao K-B (2009a) Preparation of Mg-Al hydrotalcite by urea method and
 1712 its catalytic activity for transesterification. *AIChE J* 55:1229–1235.
 1713 <https://doi.org/10.1002/aic.11722>

1714 Zeng W, Cheng D, Chen F, Zhan X (2009b) Catalytic Conversion of Glucose on Al–Zr Mixed Oxides in
 1715 Hot Compressed Water. *Catal Lett* 133:221–226. <https://doi.org/10.1007/s10562-009-0160-3>

1716 Zepp RG, Schlottzhauer PF (1981) Effects of equilibration time on photoreactivity of the pollutant DDE
 1717 sorbed on natural sediments. *Chemosphere* 10:453–460. [https://doi.org/10.1016/0045-](https://doi.org/10.1016/0045-6535(81)90145-4)
 1718 [6535\(81\)90145-4](https://doi.org/10.1016/0045-6535(81)90145-4)

1719 Zhang WH, Guo XD, He J, Qian ZY (2008) Preparation of Ni(II)/Ti(IV) layered double hydroxide at high
 1720 supersaturation. *J Eur Ceram Soc* 28:1623–1629.
 1721 <https://doi.org/10.1016/j.jeurceramsoc.2007.11.016>

1722 Zhang Z-Q, Liao M-C, Zeng H-Y, et al (2014) Mg–Al hydrotalcites as solid base catalysts for alcoholysis
 1723 of propylene oxide. *Fuel Process Technol* 128:519–524.
 1724 <https://doi.org/10.1016/j.fuproc.2014.08.015>

1725 Zhao P, Liu X, Tian W, et al (2015) Adsolubilization of 2,4,6-trichlorophenol from aqueous solution by
 1726 surfactant intercalated ZnAl layered double hydroxides. *Chem Eng J* 279:597–604.
 1727 <https://doi.org/10.1016/j.cej.2015.05.037>

1728 Zhao R, Yin C, Zhao H, Liu C (2003) Synthesis, characterization, and application of hydrotalcites in
 1729 hydrodesulfurization of FCC gasoline. *Fuel Process Technol* 81:201–209.
 1730 [https://doi.org/10.1016/S0378-3820\(03\)00012-2](https://doi.org/10.1016/S0378-3820(03)00012-2)

1731 Zou Y, Wang X, Ai Y, et al (2016a) Coagulation Behavior of Graphene Oxide on Nanocrystalline
 1732 Mg/Al Layered Double Hydroxides: Batch Experimental and Theoretical Calculation Study.
 1733 *Environ Sci Technol* 50:3658–3667. <https://doi.org/10.1021/acs.est.6b00255>

1734 Zou Y, Wang X, Chen Z, et al (2016b) Superior coagulation of graphene oxides on nanoscale layered
 1735 double hydroxides and layered double oxides. Environ Pollut 219:107–117.
 1736 <https://doi.org/10.1016/j.envpol.2016.10.052>

1737 Zou Y, Wang X, Wu F, et al (2017) Controllable Synthesis of Ca-Mg-Al Layered Double Hydroxides and
 1738 Calcined Layered Double Oxides for the Efficient Removal of U(VI) from Wastewater
 1739 Solutions. ACS Sustain Chem Eng 5:1173–1185.
 1740 <https://doi.org/10.1021/acssuschemeng.6b02550>

1741

1742 List of figures

1743

1744 **Fig1.** Environmental applications of hydrotalcites discussed in this review.

1745

1746 **Fig2.** Scheme of the **co-precipitation** method applied to the LDHs synthesis.

1747

1748 **Fig3.** Scheme of the synthesis of hydrotalcites via urea hydrolysis.

1749

1750 **Fig4.** Scheme of the synthesis of hydrotalcites by sol-gel process.

1751

1752 **Fig5.** Hydrothermal synthesis process applied to hydrotalcite synthesis.

1753

1754 **Table 1.** Main structural and textural impacts of different synthesis processes on LDHs.

Synthesis method	Advantages	Drawbacks
Co-precipitation	<ul style="list-style-type: none"> - High crystallinity with post-treatment - Easy insertion of metallic elements 	<ul style="list-style-type: none"> - Large Particles (formation of aggregates) - Low specific surface area
Use of urea	<ul style="list-style-type: none"> - Large thin platelets - Narrow particle size distribution 	<ul style="list-style-type: none"> - Formation of CO₂ by urea decomposition, formation of carbonates as counter-anions
Sol-gel	<ul style="list-style-type: none"> - High homogeneity - High purity - Small particles (nanoscale) = high specific surface area - Short times (hours) 	<ul style="list-style-type: none"> - Low crystallinity - Additional treatments required (microwave irradiation, ultrasonication, or hydrothermal treatment)
Hydrothermal	<ul style="list-style-type: none"> - Increases crystallinity - Increases particle size - Increases purity 	<ul style="list-style-type: none"> - High energy (heating) and time (hours to days) demand - More efficient as an additional treatment of other synthesis methods

1755

1756 **Table 2.** Synthesis parameters of the LDHs and mixed oxides cited in the part “2.1.1. CO₂

1757 adsorption – Capture and storage”.

Reference	Type of material	Surface area (m ² .g ⁻¹)	Adsorption capacity (mmol.g ⁻¹)	Synthesis method / structural modifications
Mao and Tamaura 1993	MgAlFe LDH	—	—	Co-precipitation at various Al/(Mg+Al) molar ratios.
Tsuji et al. 1993	Various LDHs	—	—	Co-precipitation with change of the M(II) cations: Mg ²⁺ , Ni ²⁺ , Zn ²⁺ , Co ²⁺ .

Wang et al. 2010	Mg-M(III) LDHs	82.4 – 148.6	0.050 – 0.462	Co-precipitation with change of the M(III) cations: Al ³⁺ , Ga ³⁺ , Fe ³⁺ , Mn ³⁺ , Cr ³⁺ , Ce ³⁺ , La ³⁺ .
Ram Reddy et al. 2006	Calcined MgAl LDHs	63 – 167	0.231 – 0.486	Co-precipitation and calcination at different temperatures from 200 to 600°C for 4h.
Ram Reddy et al. 2008	Calcined MgAl LDHs	–	–	Co-precipitation and calcination at 400°C for 4h.
Dadwhal et al. 2008	Calcined MgAl LDHs	–	0.7	Co-precipitation and calcination at 500°C for 4h.
León et al. 2010	Calcined MgAl LDHs	62 – 190	0.4 – 1.15	Co-precipitation at low and high supersaturation and calcination at 450 or 700°C for 7h. Anion exchange by K ⁺ or Na ⁺ prior the calcination.
Gao et al. 2013	Calcined MgAl LDHs	154 – 239	0.30 – 0.72	Co-precipitation followed by hydrothermal treatment at 120°C for 6h, urea method, or urea decomposition followed by microwave irradiation at 120°C 200W for 30min.
Ramírez-Moreno et al. 2014	MgAl LDHs	136.6 – 296.3	0.2 – 0.75	Co-precipitation at low supersaturation.
Bhatta et al. 2015	MgAl LDH supported in coal-derived graphitic material	41 – 219.6	0.48 – 1.10	Co-precipitation at low supersaturation.

Dantas et al. 2015	MgAl LDHs expanded with a polymer	50.1 – 61.1	0.72 – 1.36	Co-precipitation at low supersaturation.
Tang et al. 2018	MgAl LDHs enlarged by SDS ions before grafting 3-APS	–	1.55 – 2.09	Co-precipitation at high supersaturation.
Thouchprasitchaia et al. 2018	TEPA-functionalized calcined MgAl LDHs (hydrotalcite)	5.7 – 165.2	2.03 – 6.03	Co-precipitation at low supersaturation.
Wang et al. 2012b, a	Amine-modified MgAl LDHs via exfoliation or anionic surfactant-mediated routes	–	0.75 – 1.8	Co-precipitation at high supersaturation.
Wu et al. 2013	K-promoted hydrotalcite	–	1.15	Commercial hydrotalcite.

Fig6. CO₂ adsorption by amine-modified MgAl hydrotalcites at different temperatures (from Wang et al. (2012b)).

Table 3. CO₂ adsorption by several types of hydrotalcites according to literature.

M(II)/M(III) molar ratio	CO ₂ adsorbed (mmol.g ⁻¹)	Synthesis process	Modifications / improvements	References
3	0.5	Co- precipitation	-	Ram Reddy et al. 2006
2.87	0.7	Co- precipitation	-	Dadwhal et al. 2008
2 – 3	0.7 – 1.5	Co- precipitation	-	Albuquerque et al. 2016
1 – 5	0.4 – 1.5	Co- precipitation	Fe-promoted	Mao and Tamaura 1993
1.2	0.15 – 0.6	Co- precipitation	Different M(II) cations	Tsuji et al. 1993
3	0.6 – 1.15	Co- precipitation	K- or Na-promoted	León et al. 2010

3	1.31	Hydrothermal	K-promoted	Jang et al. 2014
2	0.42 – 1.10	Co-precipitation	K-promoted	Bhatta et al. 2015
2	2.09	Co-precipitation	K-promoted + Ga substitution	Silva et al. 2017
3	2.1	Co-precipitation	TEPA-supported	Thouchprasitchaia et al. 2018
2 – 3	2.04	Co-precipitation	(3-AP)triethoxysilane-grafted	Tang et al. 2018

1763

1764

1765 **Fig7.** Comparison between non-modified (red) and modified (blue) hydrotalcites and derived
 1766 materials on the CO₂ sorption capacity, according to Table 3.

1767

1768 **Table 4.** Synthesis conditions of the LDHs and mixed oxides cited in the part “2.1.2. NO_x
 1769 and SO_x adsorption”.

Reference	Type of	Surface area	Adsorption capacity	Synthesis method /
-----------	---------	--------------	---------------------	--------------------

	material	(m ² .g ⁻¹)	(mmol.g ⁻¹)	structural modifications
Corma et al. 1994	Calcined CuMgAl LDHs	–	–	Co-precipitation with fixed Mg/Al molar ratio at 3 and 10 molar% Cu, then calcination at 750°C for 3h.
Palomares et al. 1999	Calcined CuMgAl and CoMgAl LDHs	117 – 210	–	Co-precipitation similar to Corma et al. 1994b.
Yu et al. 2006	Calcined CoMgAl LDHs	21.6 – 162.7	–	Co-precipitation at low supersaturation with change of the Co/Mg molar ratio, then calcination at 800°C for 4h.
Yu et al. 2007	Calcined CaCoAl and CaCeLaAl LDHs	–	0.602 – 0.651	Co-precipitation at low supersaturation, then calcination at 800°C for 4h.
Cheng et al. 2004	Calcined MgAl LDHs impregnated with Pt	121 – 249	0.061 – 0.505	Co-precipitation at low supersaturation, then calcination at 600°C for 5h and impregnation with Pt(NH ₃) ₄ (OH) ₂ .
Silletti et al. 2006	Pd adsorbed on calcined commercial MgAl LDH	~ 190	0.003 – 0.062	Commercial LDH with a Mg:Al molar ratio of 7:3 calcined at 600°C, then [Pd(acac) ₂] adsorbed on freshly calcined samples.
Li et al. 2007	Calcined MgRuAl LDHs	280	0.220	Co-precipitation at low supersaturation, then calcination at 600°C for 6h.
Cui et al. 2019	Calcined MnMgAl LDHs	108 – 144	0.104 – 0.426	Co-precipitation at low precipitation assisted by CTAB, then calcination at 600°C for 6h.

Kameda et al. 2019a, b	MgAl LDHs	—	—	Co-precipitation at low supersaturation.
Cantú et al. 2005	Calcined MgAl and MgFe LDHs	74 – 204	—	Co-precipitation at low supersaturation.

1770

1771 **Fig8.** Schematic representation of LDH-derived catalysts for NO_x storage and reduction
 1772 (from Yu et al. 2009).

1773

1774 **Fig9.** NOx storage capacity at different temperatures of mixed oxides derived from MnMgAl
1775 LDHs containing 15 wt% Mn (from Cui et al. 2019).

Fig10. Simplified scheme of the Fluid Catalytic Cracking (FCC) process adapted to SO_x removal (from Valente and Quintana-Solorzano 2011).

Table 5. Synthesis parameters of the LDHs and mixed oxides cited in the part “2.1.3. VOCs total decomposition”.

Reference	Type of material	Surface area (m ² .g ⁻¹)	Synthesis method
Bahranowski et al. 1999	Calcined CuCr, ZnCr, and CuAl LDHs	CuCr-LDHs : 10 – 20 ZnCr LDH : 41 CuAl LDH : 56	Co-precipitation at low supersaturation and calcination at 600°C for 3h. The CuCr-LDHs have been synthesized with M(II):M(III) molar ratios of 1:1, 2:1, and 3:1. ZnCr and CuAl were used to investigate separately the role of Cu and Cr.
Mikulová et al. 2007	Calcined NiAl LDH	52 – 161	Co-precipitation at low supersaturation and calcination at 450°C for 4h.

Gennequin et al. 2009, 2010b	Calcined CoMgAl LDHs	72 – 141	Co-precipitation at high supersaturation with varying Co:Mg:Al molar ratio of 6:0:2, 4:2:2, 2:4:2 and 0:6:2, and calcination at 500°C for 4h.
Gennequin et al. 2010a	Co-deposited calcined MgAl LDHs	3 – 233	Co-precipitation at high supersaturation, and calcination at different temperatures: 500, 600, 700, 800, and 900°C. Co was then deposited by aqueous impregnation method.
Palacio et al. 2010	Calcined MnCuAl and ZnCuAl LDHs	45 – 108	Co-precipitation at high supersaturation and calcination at 450 and 600°C.
Dula et al. 2007	Calcined MgMnAl LDHs	137 – 191	Co-precipitation at low supersaturation and calcination at 600°C for 4h. 2 different samples have been prepared with Mn either within the structure or in the ionic form as permanganate anions in the interlayer space.
Tanasoi et al. 2009	Calcined CuMgAl LDHs	114 – 188	Co-precipitation at low supersaturation with various copper content from 1 to 20 at%, and calcination at 750°C for 8h.
Aguilera et al. 2011	Calcined MnMgAl, CuMnMgAl and CoMnMgAl LDHs	75 – 249	Co-precipitation at low supersaturation with varying Cu/Mn and Co/Mn molar ratios of 0.5, 0.25, 0.1, and 0.05, and calcination at 500°C for 16h.
Chmielarz et al. 2012	Calcined CuMgAl, CoMgAl and CuCoMgAl LDHs	60 – 217	Co-precipitation at low supersaturation and calcination at 700 or 800°C. The samples calcined at 800°C were modified with potassium using aqueous impregnation method and calcined again at 600°C.
Carpentier et al. 2002	Calcined MgAl LDH with interlayer Pd complex	33 – 69	Co-precipitation at low supersaturation in presence of H ₂ PdCl ₄ and calcination at 290 and 500°C for 4h.
Kovanda and Jiráťová	Several calcined LDHs	28 – 150 (203 with Ni)	Co-precipitation at low supersaturation and calcination at 500°C for 4h. NiAl,

2011a, b			NiMn, CoAl, CoMn, NiCoAl, NiCoMn, NiCuAl, NiCuMn, CoCuAl, and CoCuMn have been obtained in order to compare with similar mixed oxides deposited on Al ₂ O ₃ /Al support.
----------	--	--	--

1781
1782 **Fig11.** Toluene conversion versus temperature for Co-containing hydrotalcites previously
1783 calcined at various temperatures (from Gennequin et al. (2010a)).

1784
1785 **Table 6.** Synthesis conditions of the LDHs and mixed oxides cited in the part “2.2.
1786 Adsorption of aqueous pollutants”.

Reference	Type of material	Surface area (m ² .g ⁻¹)	Synthesis method
Lehmann et al. 1999	Commercial MgAl LDH (hydrotalcite)	34.8	Commercial hydrotalcite.
Yang et al. 2005	Calcined MgAl LDHs	47 – 198	Co-precipitation at high supersaturation, then calcination at 500°C for 4h.
Lv et al. 2006	Calcined MgAl, ZnAl, and NiAl LDHs	39.9 – 240.6	Synthesis method similar to co-precipitation with the use of urea, then calcination at various

			temperatures (from 200 to 800°C).
El-Sayed et al. 2016	Calcined MgAlZn LDHs	65.1	Co-precipitation with 15 wt% Zn, then calcination at 450°C for 5h.
Xue et al. 2016	Biochar/MgFe LDHs	3.9 (pores filled by biochar)	LDH directly synthesized in presence of the biochar by the liquid-phase deposition method.
Mahmoud et al. 2017	Ti-Fe chitosan LDHs	146.5	Ball milling method for 10h at 300 rpm with titanium isopropoxide, iron nitrate, and chitosan.
Yang et al. 2017	SiO ₂ supported on MgAl LDHs	—	In situ co-precipitation method at high supersaturation.
Zou et al. 2017	Calcined CaMgAl LDHs	43 – 157.8	Hydrothermal synthesis, then calcination at various temperatures (from 200 to 600°C) for 3h.
Tzompantzi et al. 2011	Calcined ZnAl LDHs	155 – 228	Co-precipitation at low supersaturation with different Zn/Al molar ratios, then calcination at 400°C for 12h.
Seftel et al. 2015	Various LDHs containing Zn ²⁺ , Cu ²⁺ , Al ³⁺ , Fe ³⁺ or Ti ⁴⁺	5 – 230	Co-precipitation at low supersaturation with various M(II)/M(III) molar ratios.
Ahmed and Gasser 2012	MgFe LDHs with Cl ⁻ or CO ₃ ²⁻ as compensating anion	—	Separate nucleation and aging method with colloid mill rotating at 5000 rpm for 3min.
de Sá et al. 2013	CaAl LDHs	—	Co-precipitation at high supersaturation.
Shan et al. 2014	Magnetic Fe ₃ O ₄ /MgAl LDHs	133	Co-precipitation at low supersaturation.
Li et al. 2016	MgAl LDHs	uncalcined : 24.7 calcined : 165.1	Low temperature ethanol-water mediated solvothermal method in an autoclave at 190°C for 1h.

1787
 1788 **Fig12.** Effect of pH on the uptake of As(V) and Se(IV) on (a) calcined and (b) uncalcined
 1789 LDHs (from Yang et al. 2005).

1791 **Fig13.** Effect of contact time on percentage of dye removal Mg-Fe-CO₃-LDH (from Ahmed
1792 and Gasser 2012).

1793 **Table 7.** Synthesis conditions of the LDHs and mixed oxides cited in the part “2.3.1.
1794 Hydrogen production”.

Reference	Type of material	Surface area (m ² .g ⁻¹)	Synthesis method
Marquevich et al. 2001	Calcined NiAl hydrotalcite	104	Co-precipitation at high supersaturation, calcination at 400°C for 4h, then reduction under nitrogen steam at 600°C.
He et al. 2009, 2010	Co-NiMgAl hydrotalcite	uncalcined : 73 – 144 calcined : 103 – 180	Co-precipitation at high supersaturation and calcination at 600°C for 6h. The metal loading was fixed at 40% and the Co-Ni composition was varied from 40 to 0, 30-10, to 20-20, 10-30, and 0-40.
Cesar et al. 2016	NiMgAl hydrotalcite	—	Co-precipitation at low supersaturation and calcination at 750°C for 4h.
Halabi et al. 2012a, b	Calcined MgAl LDHs	15.6	Commercial hydrotalcite calcined at 400°C for 4h and loaded with K ₂ CO ₃ by dry impregnation method.
Chanburanasiri et al. 2013	MgAl LDHs	104	Commercial K ₂ CO ₃ -promoted hydrotalcite in cylindrical shape.
Ashok et al. 2008	Calcined NiCuAl LDHs	120 – 182	Co-precipitation at low supersaturation and calcination at 450°C for 5h. Atomic ratio between divalent (Ni ²⁺ + Cu ²⁺) and trivalent (Al ³⁺) cations varied from 2 to 9 but constant nickel metal content.
García-Sancho et al. 2017	Calcined NiMgAl LDHs	69 – 156	Co-precipitation at low supersaturation in presence of urea, and calcination at 850°C for 10h.
Sikander et al. 2018	Calcined NiMgAl LDHs	—	Co-precipitation at low supersaturation, and calcination at different temperatures: 550, 700, and 800°C for 6h.

1796

1797 **Fig14.** Temperature-programmed methane conversion (a) and hydrogen production (b) by
 1798 nickel-containing calcined hydrotalcites (from García-Sancho et al. 2017).

1799

1800 **Table 8.** H₂ production by several types of hydrotalcite-based materials.

M(II)/M(III) molar ratio	Conversion (%)	Selectivity (%)	Synthesis method	Source	References
2	20 – 79.7	66.6 – 72.1	Co- precipitation	Sunflower oil	Marquevich et al. 2001
3	62	70	Co- precipitation	Ethanol	He et al. 2009

-	100	70	Co-precipitation	Ethanol	de Souza et al. 2012
1.56	72 – 99.6	91.3 – 99.8	Commercial	Methane	Halabi et al. 2012b
1	49 – 94	56.1 – 96.5	Co-precipitation	Ethylene glycol	Cesar et al. 2016
M(II)/M(III) molar ratio	Conversion (%)	H ₂ produced (a.u.)	Synthesis method	Source	References
3	15 – 55	246 – 1253	Urea + co-precipitation	Methane	García-Sancho et al. 2017
3	15 – 40	250 – 1100	Urea + co-precipitation	Methane	García-Sancho et al. 2018

Fig15. Scheme of the reactions involved in fructose dehydration and the resulting formation of 5-HMF and byproducts (from Dou et al. 2018).

Table 9. Synthesis parameters of the lamellar materials cited in the part “2.3.2. 5-Hydroxymethylfurfural formation”.

Reference	Type of material	Surface area (m ² .g ⁻¹)	Synthesis method
-----------	------------------	--	------------------

Lourvanij and Rorrer 1994	Pillared Na-montmorillonite	137.7 – 249.6	Na-montmorillonite mixed into the pillaring agent solution.
Fang et al. 2014	Cr-montmorillonite K10	–	K-10 montmorillonite exchanged with Cr cations.
Chheda and Dumesic 2007	Calcined MgAl LDH, MgO/ZrO ₂ and MgO/TiO ₂	~ 300	MgAl LDH synthesized by co-precipitation at low supersaturation, and mixed oxides by sol-gel method. All these samples have been calcined at 450°C for 8h.
Li et al. 2011	Calcined NiMgAl LDH	34 – 117	Co-precipitation at low supersaturation with varying Ni at%, and calcination at 800°C for 5h.
Zeng et al. 2009b	Calcined AlZr LDHs	66 – 281	Co-precipitation at high supersaturation and calcination at 500°C for 6h.

Fig16. Proposed intraparticle diffusion and reaction scheme for glucose and fructose within a pillared clay catalyst. Reaction 1: sequential dehydration of glucose to HMF and organic acid. Reaction 2: isomerization of glucose to fructose. (from Lourvanij and Rorrer 1994).

1812

1813 **Fig17.** Catalytic conversion of glucose into 5-HMF at various [BMIM]Cl concentrations in

1814 DMSO, e = DMSO only (from Fang et al. 2014).

1815

1816 **Fig18.** Relations between structural properties and applications of hydrotalcites and related

1817 materials.