ARTICLE

Synergy Effect Between Photocatalysis and Heterogeneous PhotoFenton Catalysis on Ti-Doped LaFeO₃ Perovskite for High Efficiency Light-Assisted Water Treatment

Received 00th January 20xx,
Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

Patricia Garcia-Muñoz,^{*a} Fernando Fresno,^b Christophe Lefevre,^c Didier Robert,^a Nicolas Keller^{*a}

A strategy combining both heterogenized photo-Fenton and photocatalysis advanced oxidation processes in a single dual catalyst is developed for simultaneously benefiting from the higher reaction rate of photo-Fenton and the higher mineralization yield of photocatalysis in water treatment, while overcoming the strong drawbacks still limiting their viability as single processes. We prepared via a facile Pechini sol-gel route a highly efficient and stable Ti-substituted LaFeO₃ dual catalyst, active simultaneously as reusable photo-Fenton solid catalyst and photocatalyst in water treatment. The partial substitution of La by Ti ions in the crystalline network led to pure heterogeneous surface reactions with an increase in the catalyst robustness by more than two orders of magnitude, symbolized by the absence of any Fe release and the stability of catalytic performance with test cycles. It further strongly enhanced the reaction rates, due to both an increased availability of the photogenerated charge carriers at the surface and the electronic enrichment of surface Fe, and allowed full mineralization of the pollutant to be achieved at circumneutral pH through combined advanced oxidation processes.

Introduction

In addition to increasingly restrictive environmental govern regulations, the emergence of biorecalcitrant refractory pollutants in the water, the heterogeneity of the targets as well as the increase in the volume and concentration of polluted water streams, have created a strong interest for the elaboration of new sustainable and cost-effective water treatment technologies¹⁻⁴. In this frame, Advanced Oxidation Processes (AOPs) – based on the generation of highly active HO_x[•] oxidative radicals that react with the pollutant and further with the reaction intermediates to yield the substrate mineralization –, have been developed for removing a large class of refractory substances that cannot be treated through conventional mechanical, biological or physico-chemical water treatments^{5,6}.

Among them, (i) the homogeneous Fenton process⁷, or its analogous heterogeneous Catalytic Wet Peroxide Oxidation (CWPO)⁸, – that are based on the catalytic decomposition of H₂O₂ in the presence of metallic ions, in most of the cases Fe –, and (ii) photocatalysis⁹, – that uses the redox surface properties developed by an adequately-irradiated semiconductor –, have aroused particular interest because of a high efficiency as well as relatively low investment/running costs, although they

operate via different mechanisms and in different conditions. However, both processes still suffer from strong limitations that reduce their viability.

While heterogeneous semiconductor photocatalysis is an AOP that takes advantage of its ability to reach a total mineralization of a large variety of refractory organic substances and enables working within a large pH range, it unfortunately suffers from far lower reaction rates than homogeneous Fenton-like AOPs, and accordingly from far longer process durations^{5,10,11}.

By contrast, the viability of the Fenton AOP is strongly reduced by the requirement to operate at acidic pH and by the complexation of Fe with short-chain acids that leads to the generation/precipitation of sludge, with the consequent continuous loss of active phase and the non-sustainable production of wastes¹². Heterogeneizing the Fenton AOP by incorporating Fe in a catalytic body partially overcomes these issues, but at the expense of a strong reduction in the reaction rates in comparison to the homogeneous Fenton counterpart, with a drastic decrease of the process ability to reach a complete pollutant mineralization and a continuous Fe release to the water by leaching^{7,12}. Furthermore, although performing CWPO under light in the so-called photo-assisted CWPO or heterogenized photo-Fenton process is a promising approach for increasing the catalyst reactivity by further boosting the rate-limiting Fe^{III} → Fe^{II} conversion in the Fe^{III}/Fe^{II} redox cycle, the above-mentioned drawbacks still limit in a redhibitory way the viability of the heterogenized catalytic process^{5,7,13}.

Therefore, a strategy consisting in combining both heterogenized photo-Fenton and photocatalysis AOPs within a unique catalyst is considered as a promising approach for simultaneously benefiting from a higher mineralization yield

^a Institut de Chimie et Procédés pour l'Energie, l'Environnement et la Santé (ICPEES), CNRS/University of Strasbourg, 25 rue Becquerel, Strasbourg, France

^b Photoactivated Processes Unit, IMDEA Energy Institute. Avda. Ramón de la Sagra, 3, Parque Tecnológico de Móstoles, 28935 Móstoles (Madrid), Spain

^c Institut de Physique et de Chimie des Matériaux de Strasbourg (IPCMS), CNRS/University of Strasbourg, 23 rue du Loess, Strasbourg, France

Electronic Supplementary Information (ESI) available: SEM and TEM characterization; UPS spectra; Crystallographic data of the refined samples (fresh and used); XRD patterns of used samples.

and a higher reaction rate, with as key-features that this unique dual catalyst works in similar reaction conditions as heterogeneous photocatalyst and Fe-based photo-Fenton catalyst without any loss of Fe active phase with time-on-run. Whereas physical mixtures of catalysts have been tested¹⁴⁻¹⁷, the design of a single catalyst combining both AOPs has been scarcely reported, notably using ZnFe₂O₄ spinel ferrite, natural Fe oxide or Ba-doped BiFeO₃ perovskite¹⁸⁻²⁰.

Here, we report on the use of Ti-substituted lanthanum ferrite (LaFeO₃) perovskite catalysts in water treatment acting simultaneously in similar circumneutral pH reaction conditions as heterogeneized photo-Fenton catalyst and photocatalyst for achieving a complete mineralization of the substrate under UV-A light with strongly enhanced reaction rates, while improving the catalyst stability by totally inhibiting the Fe release to water. This new dual catalyst is based on the LaFeO₃ semiconductor that is one of the most common ABO₃ perovskite oxides studied in many research fields such as solid oxide fuel cells, optoelectronics, magnetism, gas sensors or heterogeneous thermal catalysis, for taking advantage of its A_{1-x}A'_xB_{1-y}B'_yO_{3±δ} composition versatility that allows notably its textural, structural or electronic properties to be modified, and as a result its redox and catalytic ability to be tuned through A- and/or B-site cationic partial substitution²¹. Its composition is consequently in agreement with the sustainability need currently in force that requires the use of cheap, abundant, and environmentally non-toxic elements in chemical processes²². While cation-doped LaFeO₃ ferrites have been mainly used till now as photoFenton catalysts, their use also as photocatalysts remained scarce. Here, the removal of 4-chlorophenol (4-CP) has been selected as test reaction in water under UV-A light, as 4-CP is a model molecule used in AOP studies as being representative of industrial waste-water refractory pollutants²³⁻²⁵, while some mineralization tests were also performed using the myclobutanil C₁₅H₁₇ClN₄ triazole as antifungal substrate in order to broaden the scope of the work^{26,27}.

Experimental part

Synthesis of Ti-substituted LaFeO₃

La_{1-x}Ti_xFeO₃ catalysts were prepared by modifying a sol-gel Pechini synthesis. La(NO₃)₃ lanthanum nitrate hexahydrate (108.3 g/L, 99.9%, Sigma Aldrich) and Fe(NO₃)₃ iron nitrate nonahydrate (133 g/L, 99.95%, Sigma Aldrich) were dissolved in stoichiometric amounts in distilled water (30 mL), and the metallic ions underwent complexation by subsequent addition of citric acid ((C₆H₈O₇·xH₂O, 70 g/L, 99.5%, Sigma Aldrich) in a stoichiometric molar ratio with respect to the metallic ions.

A titanium source was introduced under stirring into the aqueous sol and the resulting suspensions were maintained at 80 °C for 48 h (2 °C/min heating rate) in order to induce the complete gel formation. The calcination of the dried gel was performed using a heating cycle as reported by Gosavi et al.²⁸ with heating rates of 5 °C/min, consisting in holding the temperature at 600 °C for 2 h, before subsequently maintaining a temperature plateau at 800 °C for 2 h.

In the synthesis of the P25-LFO catalyst, commercial TiO₂ Aeroxide ©P25 powder (hydrophilic fumed titanium dioxide, ≥ 99.50%, Evonik, Germany) that consists of a mixture of anatase and rutile crystalline phases in 80/20 molar ratio, was used as titanium source.

In the synthesis of the SG-LFO catalyst, dried amorphous titania was used as titanium source. It was obtained according to a sol-gel synthesis method under basic conditions using titanium tetraisopropoxide (TTIP, 97%, Sigma-Aldrich) as precursor. In a typical synthesis, 17.8 g of TTIP was first added to a 40 mL ethanolic solution, before a similar volume of water was added dropwise to the solution. After rectification of the pH to 9 by adding ammonia (Carlo Erba, 30% aqueous solution), the solution was left under agitation at room temperature until a dry paste was obtained. The resulting powder was further dried at 110 °C for 12 h to get the dried amorphous titania used as titanium source in the modified sol-gel Pechini synthesis.

Whatever the titanium source, the titanium added during the Pechini synthesis corresponded to a nominal amount of 10 wt.% in terms of TiO₂ with respect to the theoretical amount of LaFeO₃ perovskite obtained. Non-modified lanthanum ferrite powders have been synthesized as reference materials via the same protocol without any addition of titanium source, with a similar calcination procedure.

The stoichiometric reaction forming the LaFeO₃ perovskite is as follows (Eq.1)²⁹:

The reference titanium-free material was labelled as LFO, while the Ti-modified materials were labelled as P25-LFO and SG-LFO when using Aeroxide© TiO₂ P25 and dried amorphous titania as titanium source, respectively.

Characterisation techniques

The reference X-ray diffraction (XRD) pattern have been recorded at room temperature in a θ/θ mode on a Brucker D8 Advance diffractometer equipped with a monochromatic copper radiation source ($K\alpha = 1.54056 \text{ \AA}$) with a scan step of 0.02°. Some patterns have been investigated by Rietveld refinement with the Fullprof software for which the modified Thompson-Cox-Hasting function was chosen to generate the line shape of the diffraction peaks. Instrumental broadening has been previously determined by measuring the scattering from corundum (NIST standard SRM 1976b)^{30,31}.

Scanning electron microscopy (SEM) was performed in secondary electron mode on JEOL JSM-6700 F FEG microscope.

Transmission electron microscopy (TEM) was performed using a JEOL 2100F with a 0.2 nm point resolution. A copper grid covered by a holey carbon membrane was used for observation. The interplanar spacings were calculated using ImageJ software.

UV-vis diffuse reflectance spectra were acquired in a UV/Vis/NIR Perkin Elmer Lambda 1050 spectrometer, recording the reflectance between 250 and 800 nm. Band gaps were estimated from Tauc plots by representing $(\alpha h\nu)^2$ vs. photon

energy, where $\alpha = -\ln(\text{Reflectance})$, in accordance with the direct semiconductor character of LaFeO_3 .³²

Fluorescence spectra of the powdered samples were recorded in a Fluorescence Spectrometer Perkin Elmer LS55, using an excitation wavelength of 450 nm and a cut-off filter at 515 nm. Fluorescence lifetime measurements by time-correlated single photon counting (TCSPC) were carried out with a Mini- τ equipment from Edinburgh Instruments using as excitation source a laser diode (model EPL375) with a wavelength of 445.2 nm and a pulse width of 90.7 ps, at repetition rate of 1 MHz, and including a band pass filter at 600 ± 25 nm. The decay profiles were fitted to a bi-exponential decay curve, with lifetimes obtained as the average of both components, calculated as $\langle \tau \rangle = [\sum(A_i \tau_i^2)] / \sum(A_i \tau_i)$, where A_i is the amplitude and τ_i the lifetime of each component.

X-ray photoelectron spectroscopy (XPS) analysis was performed on a ThermoVG Multilab ESCA3000 spectrometer (Al K_{α} anode at $h\nu = 1486.6$ eV). The energy shift due to electrostatic charging was subtracted using the contamination sp^2 carbon C 1s band at 284.6 eV. Contributions with Doniach–Sunjic shape³³ and a S-shaped Shirley type background³⁴ were used.

Degradation test protocol

The 4-CP and myclobutanil degradation tests were performed in a batch beaker-type glass reactor at atmospheric pressure, at a constant temperature of $20^\circ\text{C} \pm 2^\circ\text{C}$ (using a cooling bath) and using H_2O_2 as main oxidant. In a typical reaction procedure, 50 mg of catalyst was dispersed under stirring in a 100 mL aqueous solution of 4-chlorophenol at concentration of 25 mg/L, corresponding to an initial organic carbon concentration of 14.8 ppm and to a catalyst load of 0.5 g/L. For the reactions with myclobutanil, starting concentration of 20 mg/L of the pollutant was selected. Prior to irradiation, the catalyst suspension has been stirred for 1 h in the dark to ensure the establishment of the adsorption/desorption equilibrium. After adding H_2O_2 at the stoichiometric concentration corresponding to a complete mineralization of the initial pollutant (125 mg/L), or substoichiometric in some cases (31.25 and 62.50 mg/L), the tests were performed under UV-A (60 W/m²; $\lambda = 365$ nm, Philips 24W/10/4P lamps). At each time interval, 8 mL of solution has been sampled and then filtered through 0.20 μm porosity filter to remove the photocatalyst powder if any, before the concentration of 4-chlorophenol or myclobutanil was determined by UV-Visible spectrophotometry by following the disappearance of the main absorption peak at $\lambda = 224$ nm³⁵. Total Organic Carbon measurements were carried out using a Shimadzu TOC-L analyzer to determine the organic carbon load. H_2O_2 concentration was measured by colorimetric titration using the TiOSO_4 method³⁶ and the Fe leached during time-course of reaction was quantified by the ortho-phenanthroline method³⁷.

Tests with myclobutanil as substrate were performed following a similar test protocol, at a myclobutanil concentration of 20 mg/L. The myclobutanil concentration was determined by UV-visible spectrophotometry by monitoring the disappearance of the main absorption peak at $\lambda = 220$ nm.

Results and discussion

Catalyst characterization

Figure 1 shows the XRD patterns of the pristine and Ti-modified LaFeO_3 materials with their corresponding Rietveld refinement profiles. Table 1 and Table S1 show the refined cationic distribution in the LaFeO_3 structure and the crystallographic data, respectively. The XRD patterns of the pristine catalyst exhibited the most intense diffraction peaks at 22.6° , 32.2° , 39.7° , 46.1° , 57.4° and 67.3° in 2θ , corresponding to the diffraction of the (100), (110), (111), (200), (210) and (220) planes of the LaFeO_3 phase, respectively. $\alpha\text{-Fe}_2\text{O}_3$ in small amount (11%) with a mean crystallite size of 35 nm was observed as extra phase. In the Ti-doped samples, independently of the Ti source, all the patterns can be indexed in the Pbnm orthorhombic unit cell of LaFeO_3 , with no change in terms of $\alpha\text{-Fe}_2\text{O}_3$ additional phase. Neither La_2O_3 nor TiO_2 are observed as extra phases. Elemental chemical analysis reveals a 3.2 at.% Ti content in the Ti-modified LaFeO_3 catalyst prepared using the crystalline TiO_2 nanopowder as precursor, further increased up to 4.0 at.% using the dried amorphous precursor, while the Ti/Fe molar ratio remains unchanged (Table 2).

Figure 1. Observed (black), calculated (red full line), and difference (blue full line) x-ray powder diffraction patterns of (a) LFO, (b) P25-LFO and (c) SG-LFO catalysts recorded on a D8 diffractometer ($\lambda = 1.54056$ Å). The positions of the Bragg reflections are represented by vertical bars, in blue for the reflexes indexed in the Pbnm orthorhombic unit cell of LaFeO_3 and in green for those of the $\alpha\text{-Fe}_2\text{O}_3$ extra phase.

Table 1. Refined cationic distribution in the $\text{La}_{1-x}\text{Ti}_x\text{FeO}_3$ perovskite catalysts and weight percentage of extra phases obtained after Rietveld refinement.

Catalyst	La site distribution ^[a]		Fe site distribution ^[a]	$\alpha\text{-Fe}_2\text{O}_3$, %	TiO_2 , %
	La	Ti	Fe		
LFO	1	0	1	11	0
P25-LFO	0.95	0.05	1	15	0
SG-LFO	0.89	0.11	1	18	0
SG-LFO #1 ^[b]	0.88	0.12	1	12	0
SG-LFO #3 ^[b]	0.88	0.12	1	11	0
SG-LFO #3 ^[b]	0.88	0.12	1	12	0

[a] the determination of the cationic distribution within the structures was performed considering that titanium can move towards both cationic sites. [b] SG-LFO #1 #3 and #5 correspond to the SG-LFO catalyst after tests #1, #3 and #5, respectively.

The separate refinement of both Ti/Fe and Ti/La site occupations evidences that titanium atoms preferentially occupy exclusively the La A-site and substitute only the La atoms, so that the catalysts can be labelled as $\text{La}_{1-x}\text{Ti}_x\text{FeO}_3$. A partial $\text{Ti} \rightarrow \text{La}$ substitution rate of 5 at.% was achieved within the perovskite network in the A-site using the crystalline TiO_2 nanopowder as titanium precursor, while it increases up to 11 at.% using the dried amorphous precursor (Table 1). The exclusive La A-site occupation is rather unexpected when considering the involved cationic sizes – $(r_{\text{Fe}^{3+}})_{\text{CN}=6} = 0.64$, $(r_{\text{La}^{3+}})_{\text{CN}=12} = 1.46$ and $(r_{\text{Ti}^{4+}})_{\text{CN}=6} = 0.76$ ³⁸. Both A- and B-site substitutions have been reported for the LaFeO_3 structure depending on the doping element, although high valence metal ions usually occupy the Fe^{3+} sites^{39,40}. However, there is no empirical rule on the location of the substituting element depending on electronic or steric criterion, and many extrinsic parameters are known to affect the cationic distribution in oxides, like eg. the cooling rate or the synthesis temperature^{41,42}. Here, we suggested that the partial substitution resulted from a temperature-driven solid-solid diffusion that is proposed to occur between the amorphous LaFeO_3 network– before it

crystallizes – and the TiO_2 crystallites, allowing the Ti atoms to distribute in the LaFeO_3 network. Consequently, replacing the well-crystallized TiO_2 nanoparticles with a 22 nm average size by an amorphous network increased further the substitution rate by favouring the atomic titanium diffusion in the amorphous LaFeO_3 perovskite network. In addition, this partial substitution hindered the growth of large crystallites during the temperature-driven crystallization at 800°C when compared to the undoped counterpart (20–21 nm vs. 46 nm), as previously observed for Li- or Cu-doped LaFeO_3 materials^{43,44}. An increase in the specific surface area from 8 to 28 m^2/g was simultaneously observed for the P25-LFO catalyst as a result of the decrease in mean crystallite size, as shown in Table 2. However, the SG-LFO catalyst displayed a low specific surface area of 5 m^2/g , although it displayed a smaller mean crystallite size of 20 nm. This was attributed to the existence of more grain boundaries within the SG-LFO materials compared to the P25-LFO counterpart.

While the SEM images shown in Figure S1 evidenced the overall powder morphology of the catalysts, the TEM images shown in Figure S2 and in Figure 2 confirmed the structural features of both the pristine LFO and the SG-LFO catalysts, respectively. Whether the

Table 2. Main physico-chemical properties of the pristine and the Ti-substituted LaFeO_3 perovskite catalysts.

Catalyst	TiO_2 precursor	Fe (at.%) ^[a]	Ti (at.%) ^[a]	Ti/Fe molar ratio	S_{BET} ($\text{m}^2 \text{g}^{-1}$) ^[b]	D (nm) ^[c]
LFO	-	23.0	-	-	8	46(1)
P25-LFO	Crystalline anatase/rutile	16.0	3.2	0.23	28	21(1)
SG-LFO	Amorphous hydroxyde	22.7	4.0	0.21	5	20(1)

[a] The iron and titanium contents in the catalysts were determined by Inductively coupled plasma optical emission spectroscopy (ICP-OES) carried out on an Optima 7000 DV spectrometer (Perkin Elmer), after a microwave-assisted acidic dissolution in aqua regia at 185°C under autogenic pressure. [b] The Brunauer-Emmett-Teller (BET) specific surface area has been calculated from the N_2 adsorption isotherm recorded on a Micrometrics Tristar 3000 using N_2 as adsorbent at -196°C with a prior outgassing at 250°C overnight to desorb the impurities or moisture. [c] The mean crystallite size defined as the average size of the coherent diffracting domains, was derived from the whole XRD patterns after refinement and determined from the Scherrer equation with the usual assumption of spherical crystallites taking into account the intrinsic broadening of the peaks due to the instrumentation.

catalyst was doped or not with titanium, interplanar spacings of 0.39 nm, 0.28 nm and 0.23 nm consistent with the (110), (100) and (111) planes characteristic of the LaFeO_3 structural crystallographic features were observed.

Figure 2. TEM images of the SG-LFO catalyst. The interplanar distances of 0.39 nm, 0.28 nm and 0.23 nm corresponded to the (110), (100) and (111) planes of the LFO structure, respectively.

The ability of $\text{La}_{1-x}\text{Ti}_x\text{FeO}_3$ materials to be used as photocatalyst under UV-A light is confirmed by the UV-vis absorbance spectra, that reveals a broad absorption band in the UV-vis range, and a band-gap estimated graphically from Tauc plots at 2.1 eV whether the catalyst contained substitutional titanium or not (Figure 3).

Figure 3. UV-vis diffuse reflectance spectra (a) and Tauc plots(b) of LFO, P25-LFO and SG-LFO catalysts. The numeric values in (b) indicate the band gap energies estimated from the Tauc plots.

In order to shed light on the effects of $\text{Ti} \rightarrow \text{La}$ substitution, further characterization of doped and undoped samples was performed. The fluorescence spectra displayed in the inset of Figure 4 showed an emission profile of LaFeO_3 with a main contribution centered at ca. 485 nm, similarly to what has been reported for lanthanum ferrite⁴⁵, which can be associated to the direct radiative de-excitation of electrons from high-energy levels within the conduction band to the valence band.^{45,46} Lower intensity emission at energies lower than the band gap reflects excitonic photoluminescence which is usually associated with sub-band-gap transitions from electronic states related to surface defects or oxygen vacancies⁴⁶.

Upon titanium doping, the positions of the emission bands remain, while some changes in the intensity are visible, depending on the involved feature. Thus, the high-energy emission is somewhat quenched in the presence of the dopant, which has been associated to a first approximation with decreased direct recombination rate due to improved charge separation within the semiconductor structure, and consequently with enhanced photocatalytic activity.^{47,48} On the contrary, the reverse effect of doping is found on the intensity the sub-band-gap features, which can be related to a higher content of surface vacancies/defects in the doped systems.⁴⁶ Fluorescence lifetime should nevertheless give more accurate information than steady-state spectra about recombination kinetics.⁴⁹ The fluorescence decay curves for the different samples between 550 and 600 nm, corresponding to the band gap energy and shown in the main body of Figure 4, give fluorescence lifetimes of the same order as previously reported values for LaFeO_3 and related structures.^{47,50} As observed in the curves and the average lifetime values from curve fittings, the P25-LFO sample gives rise to a slightly higher lifetime than the pristine LFO ferrite, while the SG-LFO sample is characterized by a considerably longer fluorescence lifetime, indicative of slower radiative recombination kinetics, which can be ascribed to an enhanced charge separation and therefore a larger availability of photogenerated electrons and holes for the subsequent surface redox reactions^{47,49,51}.

Figure 5. XPS profiles recorded on both the Ti-free LFO and the SG-LFO catalysts, (A) wide scan survey spectrum, (B) La 3d, (C) Fe 2p and (D) Ti 2p orbitals.

Figure 4. Fluorescence decay curves of pristine and Ti-doped LaFeO_3 samples between 575 and 625 nm. The green lines correspond to the decay curves fitted to each dataset. $\langle\tau\rangle$ represents the average fluorescence lifetimes. The instrument response function (IRF) has been included for comparison. Inset: fluorescence spectra of the same samples; the signal marked with (*) corresponds to the lamp emission as confirmed by recording the emission spectra with different excitation wavelengths.

Figure 5 shows the influence of the partial substitution of La ions by Ti ions in the LFO structure on the surface state of the SG-LFO catalyst. The XPS analysis revealed the presence of both cations as La^{3+} and Fe^{3+} ions at the surface of the pristine LFO and the SG-LFO catalyst. Indeed, the La 3d core level spectra recorded on the pristine LFO material exhibited a La $3d_{5/2-3/2}$ orbital doublet contribution at 833.4 eV and 850.1 eV, with a 16.7 eV spin orbit splitting⁵²⁻⁵⁴ and a 3.8 eV multiplet splitting⁵⁵, that is characteristic of La^{3+} species. The binding energies of Fe $2p_{3/2-1/2}$ orbital doublet contribution at 710.3 eV and 723.7 eV, with a spin orbit coupling of 13.4 eV^{54,55} and with the broad and low intensity shake-up satellite peak at about 718 eV characteristic of Fe^{3+} ^{56,57}, confirmed the presence of Fe^{3+} ions at the surface of the pristine LFO.

After the $\text{Ti} \rightarrow \text{La}$ partial substitution in the LFO perovskite, the XPS Ti 2p profile of the SG-LFO catalyst displayed a single contribution, with the doublet related to Ti $2p_{3/2-1/2}$ spin-orbit components at 457.3 eV and 463.0 eV. This revealed the stabilization of Ti cations at the surface as lower oxidation state Ti^{3+} in substitution of La^{3+} in the perovskite structure⁵⁵, or as $\text{Ti}^{4+}\text{-O-M}$ with a strongly lower binding energy than Ti^{4+} in an usual TiO_2 network environment (Figure 5)⁵⁸. Further, this led

also to a slight downward (-0.7 eV) shift for the binding energies of the Fe 2p orbital doublet contribution at 709.7 eV and 723.2 eV, and simultaneous in a slight upward ($+0.8$ eV) shift for the La 3d orbital doublet contribution at 834.2 eV and 850.9 eV, both cations remaining present at the surface in the formal $+3$ oxidation state.

According to the electrostatic model, in the Ti-O-La configuration, the upward shift observed for La^{3+} compared to the La-O-La reference configuration results from the higher electronegativity of Ti vs. La, that causes a $\text{O} \rightarrow \text{Ti}$ shift of the electronic density, and consequently a $\text{La} \rightarrow \text{O}$ shift of the La-O bond electronic density, that corresponds to a higher binding energy of La core electrons. So, oppositely, the downward shift of the Fe^{3+} binding energy was assigned to an electronic enrichment of Fe cations, resulting in the lower binding energy of Fe core electrons.

In addition, by combining UV-vis diffuse reflectance and UPS data, it can be assumed that the partial cationic substitution did not significantly alter neither the potential of the conduction band edge, nor the valence band maximum, determined by UPS (He I, $h\nu = 21.2$ eV) at $ca. 2.2 \pm 0.1$ eV vs. Fermi level whether the surface is modified or not by titanium (Figure S3).

Catalytic activity

Combined photo-assisted CWPO and photocatalysis

The evolution with time under irradiation of the main features followed during the reaction is shown in Figure 6. First, although the titanium-free LaFeO_3 catalyst showed ability to decompose fully H_2O_2 and to remove 4-CP within 150 min of test, it only allowed a mineralization of 75% to be achieved. Further, the catalyst suffered from a strong iron leaching, with an iron release to the solution of 0.5 mg L^{-1} . The low stability of the catalyst resulted in a high contribution of the homogeneous photoFenton reaction to the H_2O_2 decomposition, and consequently to both 4-CP and TOC removal rates, so that the apparent kinetic rate constants obtained could not be ascribed to a pure heterogeneous process and were therefore overestimated. This homogeneous contribution was responsible for the low H_2O_2 efficiency value of 0.75, and the resulting uncomplete mineralization of the substrate, as typically observed in CWPO-like reactions. Indeed, iron in solution is known to react with the latest degradation intermediates, that are short-chain acids like oxalic, acetic or formic acids, to form highly stable iron complexes that photodegrade very slowly and consequently stop the reaction (Eq. 2) ⁵⁹⁻⁶¹.

In the case of the $\text{La}_{1-x}\text{Ti}_x\text{FeO}_3$ catalysts, the incorporation of titanium atoms into the perovskite network with the $\text{Ti} \rightarrow \text{La}$ partial substitution increases considerably the robustness of the catalyst by more than two orders of magnitude. This was evidenced by a strong decrease in the iron release to 0.05 mg L^{-1}

¹ for a 5% substitution (P25-LFO), and by a further reduction down to non-detectable level (below 0.001 mg L^{-1} , i.e. lower than 0.0009% relative to the catalyst Fe content) for the SG-LFO catalyst with a 11% substitution rate. This increase in stability is accompanied by a strong enhancement of the catalytic activity, more pronounced as the substitution rate increases. Thus the duration necessary for achieving a full removal of 4-CP is reduced to 120 min and 60 min on the P25-LFO and SG-LFO catalysts, respectively, while both catalysts achieve complete mineralization within 125 min and 90 min of reaction, respectively. This very good behaviour is reflected in a strong increase in the apparent kinetic constants for 4-CP degradation, TOC conversion and H_2O_2 decomposition (Table 3). The absence of any detectable release of iron demonstrates that the strong increase in the catalytic activity can be ascribed to pure heterogeneous surface reactions, without any homogeneous contribution.

Figure 6. Evolution with time under irradiation of A) the relative 4-CP concentration, B) the relative TOC concentration, C) the H_2O_2 decomposition yield and D) the concentration of leached Fe in the solution, during the combined photo-Fenton and photocatalytic degradation of 4-CP over the pristine and the Ti-substituted LaFeO_3 catalysts. Conditions: $[\text{4-CP}]_0 = 25 \text{ mg/L}$; $[\text{H}_2\text{O}_2]_0 = 125 \text{ mg/L}$; $T = 25^\circ\text{C}$; $[\text{cat}] = 0.5 \text{ g/L}$; UV-A irradiance of 60 W m^{-2} .

Further, both $\text{La}_{1-x}\text{Ti}_x\text{FeO}_3$ catalysts exhibit a H_2O_2 efficiency ξ greater than 1, which reflects the fact that they allow full TOC conversion to be achieved at uncomplete H_2O_2 conversion. This evidences that the $\text{La}_{1-x}\text{Ti}_x\text{FeO}_3$ catalysts can act as a dual catalyst, by working simultaneously as heterogenized photo-Fenton catalyst and photocatalyst. This dual behaviour was confirmed by the evolution of the TOC conversion with the H_2O_2 conversion shown in Figure 7A. While the curve obtained for the titanium-free LaFeO_3 catalyst is distorted by the strong homogeneous Fenton contribution, the clear distribution of the whole data set for both catalysts above the unity diagonal confirms that the heterogeneous photo-Fenton process cannot be considered as the sole AOP operating for converting the TOC. Additional experiments performed using non-stoichiometric H_2O_2 doses underlined further that the TOC conversion is obtained simultaneously through both photo-Fenton and photocatalysis AOPs (Figure 7B). Indeed, complete TOC conversion was achieved following a zero-order kinetic and with a similar apparent kinetic rate constant independently of the H_2O_2 dose at 25% or 50%, while decomposition of H_2O_2 was already completed. This confirms that pure photocatalysis was taken place for allowing full TOC conversion to be obtained.

Figure 7. A) TOC conversion vs. H_2O_2 conversion for the combined photo-Fenton and photocatalytic degradation of 4-CP over the pristine and the Ti-substituted LaFeO_3 catalysts. Conditions: $[\text{4-CP}]_0 = 25 \text{ mg/L}$; $[\text{H}_2\text{O}_2]_0 = 125 \text{ mg/L}$; $T = 25^\circ\text{C}$; $[\text{cat}] = 0.5 \text{ g/L}$; UV-A irradiance of 60 W m^{-2} . B) Influence of the H_2O_2 dose on the relative TOC concentration time-evolution and the H_2O_2 conversion obtained on the SG-LFO catalyst. Conditions: $[\text{4-CP}]_0 = 25 \text{ mg/L}$; $[\text{H}_2\text{O}_2]_0 = 31.25\text{--}125.00 \text{ mg/L}$, corresponding to the 25–100% range; $T = 25^\circ\text{C}$; $[\text{cat}] = 0.5 \text{ g/L}$; UV-A irradiance of 60 W m^{-2} .

Taking into account that the experiments were carried out using the stoichiometric amount of H_2O_2 to mineralize TOC, the linear curve with a unity slope reflects the implementation of an heterogenized photo-Fenton process with no occurrence of scavenging reactions.

Although the incorporation of Ti atoms into the LFO network strongly increases the activity in pure photocatalysis, - more pronounced as the $\text{Ti} \rightarrow \text{La}$ partial substitution increases -, the activity remains far lower than that obtained using H_2O_2 , (Figure 8, Table 4). This corroborates the fact that, in the combined AOPs, the dual $\text{La}_{1-x}\text{Ti}_x\text{FeO}_3$ catalyst is acting predominantly as heterogeneous photo-Fenton catalyst at the beginning of the

Table 3. Kinetic rate constants of H_2O_2 decomposition, 4-CP oxidation, and mineralization through combined photo-Fenton and photocatalysis AOPs. Fe leached, H_2O_2 depletion percentage, TOC conversion and H_2O_2 efficiency parameters. Conditions: $[\text{4-CP}]_0 = 25 \text{ mg/L}$; $[\text{H}_2\text{O}_2]_0 = 125 \text{ mg/L}$; $T = 25^\circ\text{C}$; $[\text{cat}] = 0.5 \text{ g/L}$; UV-A irradiance of 60 W m^{-2} .

Catalyst	$k(\text{H}_2\text{O}_2)$, min^{-1} [a]	$k(4\text{-CP})$, min^{-1} [a]	$r_0(\text{TOC})$, $\text{mg L}^{-1} \text{ min}^{-1}$ [b]	[Fe] leached, mg L^{-1}	$X(\text{H}_2\text{O}_2)$, %	$X(\text{TOC})$, %	$\xi(\text{H}_2\text{O}_2)$ [c]
LFO	0.010	0.020	0.12	0.5	100	75	0.75
P25-LFO	0.017	0.017	0.18	0.05	90	100	1.11
SG-LFO	0.043	0.033	0.28	<0.001 [d]	89	100	1.12
1-5# reuse of SG-LFO	-	$33.3 \pm 0.3 \cdot 10^{-3}$	0.28 ± 0.01	<0.001 [d]		100	

[a] the H_2O_2 and 4-CP concentration evolution curves were fitted by a pseudo first-order kinetic as usually admitted, [b] the TOC concentration evolution curve was fitted with a zero-order kinetic model as usually admitted, [c] a theoretical $\xi=1$ efficiency of H_2O_2 use in Fenton-like processes reflects the fact that H_2O_2 and the formed radicals do not suffer any detrimental scavenger reactions, [d] the detection limit of Fe leached to the solution has been measured at 0.001 ppm

process, so that high reaction rates can be obtained, while it subsequently operates as photocatalyst for mineralizing the short chain acids, and consequently allows full TOC conversion to be achieved by hindering the detrimental formation of stable Fe complexes.

Table 4. Kinetic rate constants of 4-CP oxidation and mineralization rate through pure photocatalysis. Operating conditions: [4-CP]₀ = 25 mg/L; T=25°C; [cat] = 0.5 g/L; UV-A irradiance of 60 W m⁻².

Catalyst	k(4-CP), min ⁻¹ [a]	r ₀ (TOC), mg L ⁻¹ min ⁻¹ [b]
LFO	0.4 10 ⁻³	0.2 10 ⁻³
P25-LFO	1.8 10 ⁻³	0.3 10 ⁻³
SG-LFO	2.8 10 ⁻³	0.5 10 ⁻³

[a] the 4-CP concentration evolution curve was fitted by a pseudo first-order kinetic as usually admitted, [b] the TOC concentration evolution curve was fitted with a zero-order kinetic model as usually admitted.

Figure 8. Time-evolution of both the C/C_0 and TOC/TOC_0 relative concentrations during the pure photocatalytic degradation of 4-CP over the pristine and Ti-substituted $LaFeO_3$ catalysts. Conditions: [4-CP]₀ = 25 mg/L; T=25°C; [cat] = 0.5 g/L; UV-A irradiance of 60 W m⁻².

It is worth noting that, although the P25-LFO catalyst might take advantage from an enhanced surface area of 28 m²/g for exposing more surface iron active in the decomposition of H₂O₂, the specific surface area of the catalysts cannot be the key factor driving the catalytic activity, since the most active SG-LFO catalyst displays a low surface area of 5 m²/g. We propose therefore that a combination of surface and electronic modifications modulates the activity of $La_{1-x}Ti_xFeO_3$ catalysts and leads the SG-LFO catalyst to exhibit the best catalytic results. On the one hand, electron-rich surface iron enables a faster H₂O₂ decomposition by the Fe surface sites, and therefore the production of higher concentrations of active radicals during the Fe^{III}/Fe^{II} redox cycle (Eqs. 3-5). We may assume that the photoassisted Fe³⁺ to Fe²⁺ reduction in (4) might be accompanied by a Ti³⁺ to Ti⁴⁺ oxidation as a plausible way of compensating the charge. The Ti⁴⁺ species might further be reduced back to Ti³⁺ by a photogenerated electron.

Further, the degradation of the short-chain acids – and consequently the mineralization of the carboxylic acids –, might be favored by the electronic enrichment of the surface Fe according to Eq. 6, with the simultaneous Fe^{III} → Fe^{II} surface reduction, known as the rate limiting step in the Fe redox cycle.

On the other hand, the enhanced availability of the photogenerated charge carriers also enables a more efficient photocatalytic decomposition of H₂O₂, with the production of HO[•] radicals (Eqs. 7-9), as well as a more efficient production of OH[•] radicals from adsorbed water (Eq. 10).

The stabilization of Fe³⁺ cations within the orthorhombic $La_{1-x}Ti_xFeO_3$ nanocrystals – both in the bulk and at the surface, as revealed by XRD and XPS – explains the strong gain in the robustness of the substituted catalysts that leads essentially to the suppression of iron leaching. We cannot rule out that the α-Fe₂O₃ minority phase is subjected to a negligible Fe leaching^{62,63}, nevertheless remaining below the detection threshold, so that its role in the catalytic performance can be discarded.

Finally, degradation of myclobutanil was studied in order to broaden the scope of the study and confirm further the interest of this new dual SG-LFO catalyst. Similarly, Table 5 clearly evidences the superiority of the SG-LFO catalyst in terms of both myclobutanil and TOC removal rates, as well as of catalyst robustness.

Table 5. Kinetic rate constants of myclobutanil oxidation and mineralization rate through the combined catalytic photo-Fenton and photocatalytic AOP over the pristine and the Ti-substituted $LaFeO_3$ catalysts. The concentration of the leached Fe is also reported. Conditions: [myclobutanil]₀ = 20 mg/L; [H₂O₂]₀ = 125 mg/L; T=25°C; [cat] = 0.5 g/L; UV-A irradiance of 60 W m⁻².

Catalyst	k(myclobutanil), min ⁻¹ [a]	r ₀ (TOC), mg L ⁻¹ min ⁻¹ [a]
LFO	0.18	2.3 10 ⁻²
P25-LFO	0.25	2.4 10 ⁻²
SG-LFO	0.38	5.8 10 ⁻²

[a] the myclobutanil and the TOC concentration evolution curves were fitted by a pseudo first-order and a zero-order kinetic model as usually admitted; [b] the detection limit of Fe leached to the solution has been measured at 0.001 ppm

Stability tests of the SG-LFO catalyst

Considering the robustness of the SG-LFO catalyst in the first test cycle, its stability was further studied in terms of activity,

iron release and structural features during recycling tests. Actually, the refinement of the XRD patterns of the used catalysts reveals the structural stability of the $\text{La}_{1-x}\text{Ti}_x\text{FeO}_3$ catalysts during recycling tests (Table 1, Figure S4 and Table S2). Thus, no extra-phase formation occurred under UV-A during the reaction, and no change in terms of $\text{Ti} \rightarrow \text{La}$ substitution rate within the LaFeO_3 network and of mean crystallite size has been observed. Regarding the activity, the results of recycling tests shown in Figure 9 and Table 3 demonstrate the very good stability and consequently the reusability of the SG-LFO catalyst. Indeed, apparent kinetic constants for 4-CP and TOC removal remained essentially unchanged after five consecutive runs, and the Fe release to the solution was below the detection threshold (ie. lower than 0.0009% relative to the catalyst Fe content).

Figure 9. Catalyst recycling efficiency expressed in terms of time-evolution of both the C/C_0 and TOC/TOC_0 relative concentrations during 5 consecutive runs in the combined photo-Fenton and photocatalytic degradation of 4-CP with the reused SG-LFO catalyst. Conditions: $[\text{4-CP}]_0 = 25 \text{ mg/L}$; $[\text{H}_2\text{O}_2]_0 = 125 \text{ mg/L}$; $T = 25^\circ\text{C}$; $[\text{cat}] = 0.5 \text{ g/L}$; UV-A irradiance of 60 W m^{-2} . The catalyst recovery was achieved by powder filtration.

Conclusions

To sum up, we have highlighted the interest of using a new and highly robust Ti-substituted LaFeO_3 dual catalyst, active in water treatment as reusable heterogeneized photo-Fenton catalyst and photocatalyst. The $\text{La}_{1-x}\text{Ti}_x\text{FeO}_3$ dual catalyst with a 11% substitution degree was prepared by modifying a facile Pechini sol-gel route using a dried amorphous titania as titanium source. The strategy combining both AOPs within a single dual catalyst allowed the $\text{La}_{1-x}\text{Ti}_x\text{FeO}_3$ catalyst to simultaneously take advantage from the higher reaction rate of photo-assisted

CWPO and the higher mineralization yield of photocatalysis. The partial $\text{Ti} \rightarrow \text{La}$ cation substitution in the LaFeO_3 perovskite network led to pure heterogeneous surface reactions with an increase in the catalyst robustness by more than two orders of magnitude, evidenced by the complete inhibition of the Fe release to water and the stability of the catalytic performance over five test cycles. It further strongly increased the reaction rates, due to both an enhanced availability of the photogenerated charge carriers at the surface and the electronic enrichment of the surface iron, and allowed full mineralization of the pollutant to be achieved at circumneutral pH through combined AOPs.

Forthcoming works are concerned with the use of solar light for taking advantage of the narrow band gap of the dual $\text{La}_{1-x}\text{Ti}_x\text{FeO}_3$ catalysts, as well as with downsizing the $\text{La}_{1-x}\text{Ti}_x\text{FeO}_3$ crystallites for increasing further the availability of Fe ions at the catalyst surface. conclusions section should come in this section at the end of the article, before the acknowledgements.

Conflicts of interest

There are no conflicts to declare

Acknowledgements

The authors want to thank the European Fund for regional development (EFRE/FEDER) for funding the project PHOTOPUR which is performed within the framework of Interreg V program and Offensive Sciences call. F. Fresno thanks financial support from project SOLPAC: ENE2017-89170-R from the Ministry of Science, Innovation and Universities. T. Dintzer (ICPEES) and D. Ihiwakrim (IPCMS) are thanked for performing SEM and TEM characterization, respectively. V. Papaefthimiou and S. Zafeiratos (ICPEES) are thanked for performing XPS and UPS measurements.

Notes and references

- 1 Y. Chen, G. Zhang, H. Liu and J. Qu, Confining Free Radicals in Close Vicinity to Contaminants Enables Ultrafast Fenton-like Processes in the Interspace of MoS_2 Membranes, *Angew.Chem.Int.Ed.*, 2019,58,8134-8138.
- 2 A. M. Braun, Photochemical Purification of Water and Air., *Angew. Chem. Int. Ed.*, 2003,42,5117-5117.
- 3 L. Ma, Y. Liu, Y. Liu, S. Jiang, P. Li, Y. Hao, P. Shao, A. Yin, X. Feng and B. Wang, Ferrocene-Linkage-Facilitated Charge Separation in Conjugated Microporous Polymers, *Angew. Chem. Int. Ed.*, 2019,58,4221-4226.
- 4 S. Navalon, R. Martin, M. Alvaro and H. Garcia, Gold on Diamond Nanoparticles as a Highly Efficient Fenton Catalyst, *Angew.Chem.Int.Ed.*, 2010,49,8403-8407.
- 5 M. Sun, C. Chu, F. Geng, X. Lu, J. Qu, J. Crittenden, M. Elimelech and J. Kim, Reinventing Fenton Chemistry: Iron Oxychloride Nanosheet for pH-Insensitive H_2O_2 Activation, *Environ. Sci. Technol. Lett.*, 2018,5,186-191.
- 6 P. Bautista, A. F. Mohedano, J. A. Casas, J. A. Zazo and J. J. Rodriguez, An overview of the application of Fenton oxidation to industrial wastewaters treatment, *J. Chem. Technol. Biotechnol.*, 2008,83,1323-1338.

- 7 R. Chen and J. J. Pignatello, Role of Quinone Intermediates as Electron Shuttles in Fenton and Photoassisted Fenton Oxidations of Aromatic Compounds, *Environ. Sci. Technol.*, 1997, 31, 2399-2406.
- 8 J. A. Zazo, J. A. Casas, A. F. Mohedano, M. A. Gilarranz and J. J. Rodríguez, Chemical pathway and kinetics of phenol oxidation by Fenton's reagent, *Environ. Sci. Technol.*, 2005, 39, 9295-9302.
- 9 S. Malato, P. Fernández-Ibáñez, M. I. Maldonado, J. Blanco and W. Gernjak, Decontamination and disinfection of water by solar photocatalysis: Recent overview and trends, *Catal. Today*, 2009, 147, 1-59.
- 10 A. Verma, D. Dixit, A. Toor and J. Srivastava, Heterogeneous photocatalytic degradation of 2-chloro-4-nitrophenol using slurry and fixed bed reactor, *Environ. Prog. Sustainable Energy*, 2015, 34, 380-386.
- 11 A. Goi and M. Trapido, Hydrogen peroxide photolysis, Fenton reagent and photo-Fenton for the degradation of nitrophenols: a comparative study, *Chemosphere*, 2002, 46, 913.
- 12 J. A. Zazo, J. A. Casas, A. F. Mohedano and J. J. Rodríguez, Catalytic wet peroxide oxidation of phenol with a Fe/active carbon catalyst, *App. Cat. B: Env.*, 2006, 65, 261-268.
- 13 M. Hartmann, S. Kullmann and H. Keller, Wastewater treatment with heterogeneous Fenton-type catalysts based on porous materials, *J. Mater. Chem.*, 2010, 20, 9002-9017.
- 14 M. E. Zarazua-Morin, L. M. Torres-Martinez, E. Moctezuma, I. Juarez-Ramirez and B. B. Zermeno, Synthesis, characterization, and catalytic activity of FeTiO₃/TiO₂ for photodegradation of organic pollutants with visible light, *Res. Chem. Intermed.*, 2016, 42, 1029-1043.
- 15 A. Sivakumar, A. Selvaraj, A. Ramasamy and Balasubramanian V., Enhanced Photocatalytic Degradation of Reactive Dyes over FeTiO₃/TiO₂ Heterojunction in the Presence of H₂O₂, *Water Air Soil Pollut.*, 2013, 224, 5.
- 16 R. Dhinesh Kumar, R. Thangappan and R. Jayavel, Synthesis and characterization of LaFeO₃/TiO₂ nanocomposites for visible light photocatalytic activity, *J. Physics and Chemistry of Solids*, 2017, 101, 25-33.
- 17 S. Yu, Y. Wang, F. Sun, R. Wang and Y. Zhou, Novel mpg-C₃N₄/TiO₂ nanocomposite photocatalytic membrane reactor for sulfamethoxazole photodegradation, *Chem. Eng. J.*, 2018, 337, 183-192.
- 18 C. Cai, Z. Zhang, J. Liu, N. Shan, H. Zhang and D. D. Dionysiou, Visible light-assisted heterogeneous Fenton with ZnFe₂O₄ for the degradation of Orange II in water, *App. Cat. B: Env.*, 2016, 182, 456-468.
- 19 H. Mechakra, T. Sehili, M. A. Kribeche, A. A. Ayachi, S. Rossignol and C. George, Use of natural iron oxide as heterogeneous catalyst in photo-Fenton-like oxidation of chlorophenylurea herbicide in aqueous solution: Reaction monitoring and degradation pathways, *J. Photochem. Photobiol. A-Chem.*, 2016, 317, 140-150.
- 20 T. Soltani and B. Lee, Improving heterogeneous photo-Fenton catalytic degradation of toluene under visible light irradiation through Ba-doping in BiFeO₃ nanoparticles, *J. Mol. Catal. A-Chem.*, 2016, 425, 199-207.
- 21 W. Wang, M. Xu, X. Xu, W. Zhou and Z. Shao, Perovskite Oxide-Based Electrodes for High-Performance Photoelectrochemical Water Splitting: A Review, *Angew. Chem. Int. Ed.*, 2019, 0.
- 22 M. Monai, M. Melchionna and P. Fornasiero, Chapter One - From metal to metal-free catalysts: Routes to sustainable chemistry, Academic Press, 2018.
- 23 E. J. Rosenfeldt and K. G. Linden, Degradation of Endocrine Disrupting Chemicals Bisphenol A, Ethinyl Estradiol, and Estradiol during UV Photolysis and Advanced Oxidation Processes, *Environ. Sci. Technol.*, 2004, 38, 5476-5483.
- 24 J. Matos, J. Laine and J.-M. Herrmann, Effect of the Type of Activated Carbons on the Photocatalytic Degradation of Aqueous Organic Pollutants by UV-Irradiated Titania, *J. Catal.*, 2001, 200, 1, 10-20.
- 25 E. Tütem, R. Apak and Ç. F. Ünal, Adsorptive removal of chlorophenols from water by bituminous shale, *Water Res.*, 1998, 32, 2315-2324.
- 26 D. A. Haith, Ecological risk assessment of pesticide runoff from grass surfaces, *Environ. Sci. Technol.*, 2010, 44, 6496-6502.
- 27 P. Garcia-Muñoz, W. Dachtler, B. Altmayer, R. Schulz, D. Robert, F. Seitz, R. Rosenfeldt and N. Keller, Reaction pathways, kinetics and toxicity assessment during the photocatalytic degradation of glyphosate and myclobutanil pesticides: Influence of the aqueous matrix, *Chem. Eng. J.*, 2020, 384, 1233152020.
- 28 P. V. Gosavi and R. B. Biniwale, Pure phase LaFeO₃ perovskite with improved surface area synthesized using different routes and its characterization, *Mater. Chem. Phys.*, 2010, 119, 324-329.
- 29 X. Qi, J. Zhou, Z. Yue, Z. Gui and L. Li, A simple way to prepare nanosized LaFeO₃ powders at room temperature, *Ceramics Int.*, 2003, 29, 347-349.
- 30 L. B. McCusker, R. B. Von Dreele, D. E. Cox, D. Louër and P. Scardi, Rietveld refinement guidelines, *J. Appl. Cryst.*, 1999, 32, 36-50.
- 31 J. Rodríguez-Carvajal, Recent advances in magnetic structure determination by neutron powder diffraction, *Physica B: Condensed Matter*, 1993, 192, 1, 55-69.
- 32 J. Luo, R. Li, Y. Chen, X. Zhou, X. Ning, L. Zhan, L. Ma, X. Xu, L. Xu and L. Zhang, Rational design of Z-scheme LaFeO₃/SnS₂ hybrid with boosted visible light photocatalytic activity towards tetracycline degradation, *Sep. Pur. Tech.*, 2019, 210, 417-430.
- 33 M. S. S. Doniach and, Many-electron singularity in X-ray photoemission and X-ray line spectra from metals, *J. of Physics C: Solid State Physics*, 1970, 3, 285.
- 34 D. A. Shirley, High-Resolution X-Ray Photoemission Spectrum of the Valence Bands of Gold, *Phys. Rev. B*, 1972, 5, 4709-4714.
- 35 M. Pera-Titus, V. García-Molina, M. A. Baños, J. Giménez and S. Esplugas, Degradation of chlorophenols by means of advanced oxidation processes: a general review, *App. Cat. B: Env.*, 2004, 47, 219-256.
- 36 G. Eisenberg, Colorimetric Determination of Hydrogen Peroxide, *Industrial & Engineering Chemistry Analytical*, 1943.
- 37 E. B. Sandell, Colorimetric Determination of Traces of Metals, *The Journal of Physical Chemistry*, 1945.
- 38 R. D. Shannon, Revised effective ionic radii and systematic studies of interatomic distances in halides and chalcogenides, *Acta Cryst. A*, 1976, 32, 751-767.
- 39 T. S. Jamil, H. A. Abbas, R. A. Nasr and R. Vannier, Visible light activity of BaFe_{1-x}Cu_xO_{3-δ} as photocatalyst for atrazine degradation, *Ecotoxicol. Environ. Saf.*, 2018, 163, 620-628.
- 40 S. K. Rashmi, H. S. Bhojya Naik, H. Jayadevappa, R. Viswanath, S. B. Patil and M. Madhukara Naik, Solar light responsive Sm-Zn ferrite nanoparticle as efficient photocatalyst, *Mat. Sci. Eng.: B*, 2017, 225, 86-97.
- 41 M. R. De Guire, R. C. O'Handley and G. Kalonji, The cooling rate dependence of cation distributions in CoFe₂O₄, *J. Appl. Phys.*, 1989, 65, 3167-3172.
- 42 Z. J. Zhang, Z. L. Wang, B. C. Chakoumakos and J. S. Yin, Temperature Dependence of Cation Distribution and Oxidation State in Magnetic Mn²⁺/Fe Ferrite Nanocrystals, *J. Am. Chem. Soc.*, 1998, 120, 1800-1804.
- 43 T. T. N. Phan, A. N. Nikoloski, P. A. Bahri and D. Li, Heterogeneous photo-Fenton degradation of organics using highly efficient Cu-doped LaFeO₃ under visible light, *Journal of Industrial and Engineering Chemistry*, 2018, 61, 53-64.

- 44 L. Hou, G. Sun, K. Liu, Y. Li and F. Gao, Preparation, characterization and investigation of catalytic activity of Li-doped LaFeO_3 nanoparticles, *J. Sol. Gel Sci. Technol.*, 2006, 40, 9-14.
- 45 Y. Ye, H. Yang and R. Li, Enhanced photocatalytic performance and mechanism of Ag-decorated LaFeO_3 nanoparticles, *J. Sol. Gel Sci. Technol.*, 2017, 82, 509-518.
- 46 J. Liqiang, Q. Yichun, W. Baiqi, L. Shudan, J. Baojiang, Y. Libin, F. Wei, F. Honggang and S. Jiazhong, Review of photoluminescence performance of nano-sized semiconductor materials and its relationships with photocatalytic activity, *Solar Energy Materials and Solar Cells*, 2006, 90, 12, 1773-1787.
- 47 S. Bharathkumar, M. Sakar and S. Balakumar, Experimental Evidence for the Carrier Transportation Enhanced Visible Light Driven Photocatalytic Process in Bismuth Ferrite (BiFeO_3) One-Dimensional Fiber Nanostructures, *J. Phys. Chem. C*, 2016, 120, 18811-18821.
- 48 L. Collado, A. Reynal, F. Fresno, M. Barawi, C. Escudero, V. Perez-Dieste, J. M. Coronado, D. P. Serrano, J. R. Durrant and I. P. de, Unravelling the effect of charge dynamics at the plasmonic metal/semiconductor interface for CO_2 photoreduction, *Nature Communications*, 2018, 9, 4986.
- 49 A. Charanpahari, S. S. Umare and R. Sasikala, Effect of Ce, N and S multi-doping on the photocatalytic activity of TiO_2 , *Applied Surface Science*, 2013, 282, 408-414.
- 50 S. Y. Smolin, A. K. Choquette, J. Wang, S. J. May and J. B. Baxter, Distinguishing Thermal and Electronic Effects in Ultrafast Optical Spectroscopy Using Oxide Heterostructures, *J. Phys. Chem. C*, 2018, 122, 115-123.
- 51 R. Sasikala, A. R. Shirole, V. Sudarsan, K. G. Girija, R. Rao, C. Sudakar and S. R. Bharadwaj, Improved photocatalytic activity of indium doped cadmium sulfide dispersed on zirconia, *J. Mater. Chem.*, 2011, 21, 16566-16573.
- 52 S. Phokha, S. Pinitsoontorn, S. Rujirawat and S. Maensiri, Polymerized complex synthesis and effect of Ti dopant on magnetic properties of LaFeO_3 nanoparticles, *J. Nanosci. Nanotechnol.*, 2015, 15, 9171-9177.
- 53 S. Thirumalairajan, K. Girija, V. Ganesh, D. Mangalaraj, C. Viswanathan and N. Ponpandian, Novel Synthesis of LaFeO_3 Nanostructure Dendrites: A Systematic Investigation of Growth Mechanism, Properties, and Biosensing for Highly Selective Determination of Neurotransmitter Compounds, *Crystal Growth & Design*, 2013, 13, 291-302.
- 54 M. Humayun, N. Sun, F. Raziq, X. Zhang, R. Yan, Z. Li, Y. Qu and L. Jing, Synthesis of ZnO/Bi-doped porous LaFeO_3 nanocomposites as highly efficient nano-photocatalysts dependent on the enhanced utilization of visible-light-excited electrons, *App. Catal. B: Env.*, 2018, 231, 23-33.
- 55 S. Petrović, A. Terlecki-Baričević, L. Karanović, P. Kirilov-Stefanov, M. Zdujić, V. Dondur, D. Paneva, I. Mitov and V. Rakić, LaMO_3 ($M=\text{Mg, Ti, Fe}$) perovskite type oxides: Preparation, characterization and catalytic properties in methane deep oxidation, *App. Catal. B: Env.*, 2008, 79, 2, 186-198.
- 56 T. Yamashita and P. Hayes, Analysis of XPS spectra of Fe^{2+} and Fe^{3+} ions in oxide materials, *Appl. Surf. Sci.*, 2008, 254, 2441-2449.
- 57 D. D. Hawn and B. M. DeKoven, Deconvolution as a correction for photoelectron inelastic energy losses in the core level XPS spectra of iron oxides, *Surf. Interface Anal.*, 1987, 10, 63-74.
- 58 J. C. Yu, Yu, Ho, Jiang and Zhang, Effects of F- Doping on the Photocatalytic Activity and Microstructures of Nanocrystalline TiO_2 Powders, *Chem. Mater.*, 2002, 14, 3808-3816.
- 59 D. L. Sedlak and A. W. Andren, Oxidation of Chlorobenzene with Fenton's Reagent, *Environ. Sci. Technol.*, 1991, 25, 777-782.
- 60 M. E. Balmer and B. Sulzberger, Atrazine degradation in irradiated iron/oxalate systems: Effects of pH and oxalate, *Environ. Sci. Technol.*, 1999, 33, 2418-2424.
- 61 G. Pliego, J. A. Zazo, P. Garcia-Muñoz, M. Munoz, J. A. Casas and J. J. Rodriguez, Trends in the Intensification of the Fenton Process for Wastewater Treatment: An Overview, *Crit. Rev. Environ. Sci. Technol.*, 2015, 45, 2611-2692.
- 62 R. Prucek, M. Hermanek and R. Zbořil, An effect of iron(III) oxides crystallinity on their catalytic efficiency and applicability in phenol degradation—A competition between homogeneous and heterogeneous catalysis, *App. Cat. A: Gen.*, 2009, 366, 2, 325-332.
- 63 G. Carraro, C. Maccato, A. Gasparotto, T. Montini, S. Turner, O. I. Lebedev, V. Gombac, G. Adami, G. Van Tendeloo, D. Barreca and P. Fornasiero, Enhanced Hydrogen Production by Photoreforming of Renewable Oxygenates Through Nanostructured Fe_2O_3 Polymorphs, *Adv. Funct. Mater.*, 2014, 24, 372-378.