Metal and Metal Oxide Nanoparticles in the Voltammetric Detection of Heavy Metals: A Review

Simona Sawan^{1,2}, Rita Maalouf^{2*}, Abdelhamid Errachid¹, Nicole Jaffrezic-Renault^{1*}

¹Institute of Analytical Sciences, University of Lyon, 5 rue de la Doua, 69100 Villeurbanne, France.

²Department of Sciences, Faculty of Natural and Applied Sciences, Notre Dame University - Louaize, Zouk Mosbeh, Lebanon

Corresponding authors' email address : rita.maalouf@ndu.edu.lb, nicole.jaffrezic@univ-lyon1.fr

Keywords : Heavy metals ; Voltammetry ; Metal nanoparticles ; Metal oxide nanoparticles

ABSTRACT

Most heavy metal ions are known to be toxic and carcinogenic when present in high amounts. Thus, rapid and reliable on-site detection of these ions is crucial. Voltammetry is a highly sensitive electrochemical method that has been widely used for heavy metal detection offering the advantages of sensitivity and rapidity. On the other hand, nanoparticles offer the advantages of high surface area and high selectivity. Thus, this review aims to highlight the application of metallic and metallic oxide nanoparticles for the voltammetric detection of heavy metals. The nanoparticles used were either applied solely on the electrode or as modifiers with various materials. In all cases, the synthesized devices showed an enhanced analytical performance, such that the limits of detection were lowered and the sensitivities were increased as compared to voltammetric systems not using nanoparticles. Moreover, the applicability of some of these systems was investigated in real samples.

1. Introduction

Heavy metals are defined as naturally occurring elements having a density or specific gravity greater than 5 g.cm⁻³ and atomic weights between 63.5 and 200.6 g.mol⁻¹ [1]. Ions of heavy metals, even at trace levels, have been detected in different sources including food, beverages, soil, plants, natural waters, etc. The use of pesticides and fertilizers, burning of fossil fuels, mining, smelting and leaching from eating utensils and cookware are all sources of heavy metal contamination [2, 3]. In addition to human activities, natural sources of heavy metals include: weathering of metal-bearing rocks, volcanic eruptions and forest fires.

Upon their release into the environment, whether through natural or anthropogenic sources, and since they are non-biodegradable, heavy metals accumulate and become toxic when present at high concentrations [4]. They are also known to hinder the developmental activity, yielding capacity and growth of plants. Moreover, heavy metals cause soil pollution and continuous exposure is very harmful to aquatic and terrestrial plants and animals [5]. In addition to their adverse impact on the environment, heavy metals are dangerous to the human health. They enter natural waters and start accumulating in sediments and living organisms, until they reach the final consumers in the food chain, which are human beings [6]. Continued exposure to heavy metals over a prolonged period of time can cause chronic poisoning, growth and developmental abnormalities, nephrotoxicity, encephalopathy, cardiovascular diseases and cancer.

For this reason, for each heavy metal, especially those considered as toxic, several agencies including the World Health Organization (WHO), Environmental Protection Agency (EPA) and Food and Drug Administration (FDA) [7, 8] have set guideline values for the allowable intake and exposure of humans to these heavy metals. Some of these limits are summarized in Table 1.

Table 1: Comparison between the allowable levels of some heavy metals in drinking water following the EPA, WHO and EU guidelines.

Heavy metal	EPA Guideline value in drinkable water (µg/L)	WHO Guideline value in drinkable water (µg/L)	EU Guideline value in foodstuff (µg/Kg)
Antimony	20	5	40
Arsenic	10	10	2
Cadmium	3	3	50
Chromium	50	50	250
Copper	2000	2000	36
Lead	10	10	20
Mercury	6	1	1.6
Nickel	70	20	n/a

Conventional methods that have been used so far for the detection of heavy metals include Inductively Coupled Plasma- Mass Spectrometry (ICP-MS), Liquid Chromatography (LC) [9], UV-vis Spectrometry [10], Atomic Absorption Spectroscopy (AAS), Atomic Emission Spectrometry (AES) [11], Atomic Fluorescence Spectrometry (AFS) [12], Cold Vapor Atomic Fluorescence Spectrometry (CV-AFS) [13], Capillary Electrophoresis (CE) and

Laser-Induced Breakdown Spectroscopy (LIBS) [14]. Even though these techniques are highly sensitive and selective, there still exists several challenges for their use in heavy metal detection [15]. These include high cost, complex operational procedures, long detection time and difficulty in achieving the detection in real environments [14].

On the other hand, electrochemical methods are gaining wide recognition in heavy metal detection. These methods offer the same sensitivity with a lower cost, less complex operational procedures and fast on-site detection. Different electrochemical platforms have been developed for heavy metal detection. Specifically, nanomaterials have brought several advantages in this area due to their unique electronic, chemical and mechanical properties. Accordingly, different electrochemical sensors using nanoparticles have been constructed for the detection of heavy metals [16, 17].

To the best of our knowledge, recent reviews focus on the detection of heavy metals using either a specific technique, or a specific type of nanoparticles [15, 17]. This review mainly discusses the use of voltammetry in the past fifteen years for heavy metal detection that can be applied to water samples using metal or metal oxide nanoparticles.

2. Voltammetric Techniques

Among the different known electrochemical methods, voltammetry is the most used in the detection of heavy metal ions. Voltammetry in general describes all electrochemical systems which are based on potential-dependent current measurements. A three-electrode electrochemical set-up typically consists of a working electrode, a counter electrode and a reference electrode. The potential is applied between the working and the reference electrodes, while the current is measured between the working and the counter electrodes. Upon varying the method of potential change, one ends up with different techniques. Linear sweep voltammetry (LSV) is the simplest technique such that the potential is swept linearly with time [18]. Cyclic voltammetry (CV) consists of linearly scanning the potential in one direction followed by reversing the potential of a working electrode [17]. In other words, a single or multiple triangular potential waveform [19] are involved.

The use of a pulse of voltage signal is the main concept behind pulsed voltammetry. By varying the shape and amplitude of the pulses, different types of pulsed voltammetry exist [17]. Differential pulse voltammetry (DPV) uses fixed magnitude pulses superimposed on a linear potential ramp [19]. Square wave voltammetry (SWV) is when a waveform of a symmetrical square wave is superimposed on a base staircase potential and applied to the working electrode [19].

Stripping voltammetry, and more specifically, anodic stripping voltammetry (ASV) is based on a two-step process. The first step is a pre-concentration or electrodeposition of the heavy metal at the electrode surface through the reduction of the metal ions. The second step is the stripping step, where the metal is oxidized back to give the ion. Having taken the 2 steps into consideration, several factors are known to influence the analysis, such as electrode material, deposition potential, deposition time [20] ... When the preconcentration step is non-electrolytic, the analyte accumulates at the surface of the electrode by physical adsorption, a different method is obtained: Adsorptive Stripping Voltammetry (AdSV) [21]. Figure 1 summarizes how the potential is varied with time for CV, LSV, DPV, SWV and ASV to produce a signal.

A combination of some of these techniques results in increased sensitivities and limits of detection. The combinations include differential pulse anodic stripping voltammetry (DPASV), square wave anodic stripping voltammetry (SWASV) and linear sweep anodic stripping voltammetry (LSASV).

Figure 1: The graphs of potential vs time for some voltammetry techniques to produce a signal.

3. Metal Nanoparticles

Nanoparticles, specifically metal nanoparticles, present several advantages in the electrochemical sensing field. Due to their small sizes, nanoparticles can increase the surface area of the electrode being used. Moreover, metallic nanoparticles can increase the mass-transport rate and offer a fast electron transfer, both increasing the sensitivity of the used electrodes [16]. In this section, we will present the use of different types of metallic nanoparticles for the detection of the majority of heavy metals.

3.1. Silver Nanoparticles

Silver nanoparticles (Ag NPs) are one of the most well-developed nanoparticles because they are relatively inexpensive and they have unique chemical and physical properties that make them useful in different catalytic, optical and chemical applications. Silver nanoparticles have been combined with different materials for the detection of Cd^{2+} , Cr^{6+} , Cu^{2+} , Hg^{2+} and Sb^{3+} . Two different ways have been employed for the synthesis of spherical Ag NPs: reduction and electrodeposition. When the NPs were used along with graphene oxide, reduction of silver nitrate (AgNO_3) was employed, either hydrothermally to produce Ag NPs with an average size of 10 – 20 nm [22] or using hydrogen iodide HI as a reducing agent to yield Ag NPs with an average particle size of 9.7 nm [23]. The resultant nanoparticles in both reports were homogeneously distributed on the reduced graphene oxide network. On the other hand, the electrodeposition of silver nanoparticles [24, 25] produced larger particles with sizes ranging between 30 and 50 nm.

Most recently, Cheng et al. synthesized reduced graphene oxide/silver nanoparticles composites for the simultaneous detection of several ions. Trace levels of Cu^{2+} , Cd^{2+} and Hg^{2+} , using cyclic voltammetry were detected with detection limits of 10^{-15} M, 10^{-21} M and 10^{-29} M respectively [22]. Although reporting exceptionally low LODs not reported elsewhere, specifically for mercury, this method could detect 1 atom in 166 m^3 of water! The detection mechanism is different than all other papers such that it relies on the area of the entirety of the CV curve instead of using that of a peak. Moreover, the paper lacks important data on the analytical performance such as the linear range, sensitivity and reproducibility. Han et al. also used silver nanoparticles with reduced graphene oxide to detect Hg^{2+} ions by differential square wave anodic stripping voltammetry. The synthesized nanoparticles were spherical and uniformly distributed on the graphene sheet. The signal and analytical performance were compared with and without the nanoparticles, and it was shown that the presence of nanoparticles enhanced the signal significantly (figure 2). A linear concentration range was obtained between 0.1 and $1.8 \mu\text{M}$, the limit of detection was calculated to be $0.11 \mu\text{M}$ and the sensitivity was $8 \mu\text{A}/\mu\text{M}$. Moreover, no interferences were detected from Cd (II) and Cu (II) [23].

Xing et al. modified a glassy carbon electrode with Nafion and electrodeposited silver nanoparticles on its surface for the direct detection of Cr (VI) using linear sweep voltammetry. A linear range was obtained between 2 and 230 ppb and the limit of detection was 0.67 ppb with no interference from different ions. The applicability of this sensor was studied using wastewater from a textile factory and the concentration of Cr (VI) was found to be $6.58 \pm 0.04 \mu\text{g/L}$ with a recovery of $99 \pm 5\%$ for spiked samples [24]. Renedo et al. also conducted a study using silver nanoparticles modified screen printed electrodes for the detection of Sb by anodic stripping voltammetry. Differential pulse anodic stripping voltammetry was used and the linear concentration range was between 9.9×10^{-8} M and 9.09×10^{-7} M, whereas the LOD in case of silver nanoparticles was 6.79×10^{-10} M. Three different seawater samples were analyzed, and the amount of Sb (III) in all cases was below the detection limit and hence was not detected [25].

Figure 2: (a) Scanning electron microscopy (SEM) image and (b) energy dispersive spectroscopy (EDS) spectrum with elemental mapping of Ag NPs/reduced graphene oxide. (c) Schematic diagram of the Ag NPs/reduced graphene oxide structure. (d) Cyclic voltammetry of pure reduced graphene oxide and Ag NPs/reduced graphene oxide. (e) Schematic representation of the electrochemical detection towards Hg (II) ions. (f) and (g) SWASV response of pure reduced graphene oxide and Ag NPs/reduced graphene oxide towards Hg (II) at different concentrations in a 0.1 M NH_3 solution; the insets correspond to the calibration plots, respectively [23].

3.2. Gold Nanoparticles

The most used nanoparticles for the electrochemical detection of heavy metals are gold nanoparticles (Au NPs). Their properties vary depending on their size, but whatever the size, gold nanoparticles are known to be biocompatible and of low toxicity [26]. Table 2 summarizes the different voltammetric studies done to detect heavy metals using gold nanoparticles. Only a few reports focus on the use of gold nanoparticles alone; nonetheless, different materials have been associated with gold nanoparticles for the detection of heavy metals, and especially mercury and lead.

Similar to Ag NPs, the most common methods utilized for the synthesis of Au NPs are either electrodeposition or reduction. However, different synthesis conditions lead to different shapes and sizes of the gold nanoparticles. The most common shape used in the electrochemical detection of heavy metals is spherical. Most groups have successfully synthesized spherical Au NPs of sizes ranging between 4 and 298 nm. Hassan et al. reported the synthesis and use of different gold nanostructures for the detection of As (III). The synthesis involved the reduction of chloroauric acid using ibuprofen in a basic medium. They investigated the effect of different heating times on the shape of the produced nanoparticles, and the results indicated that with increased heating time, nanoflowers formed along with other structures [27]. Ouyang et al. used a more complex method for the synthesis of nanoflowers. In brief, they modified a glassy carbon electrode with a layer of gold nanoparticles, followed by a layer of 3-mercaptopropyl-trimethoxysilane. Then, the electrode was immersed in a solution containing Au NPs to form a second layer of nanoparticles and pyridinium was attached to the NPs after dipping in 4-pyridineethanethiol hydrochloride solution [28]. Dutta et al. synthesized gold nanostars and spherical gold nanoparticles and compared their performances in the detection of As (III), Hg (II) and Pb (II). The nanostars were prepared by mixing an auric chloride solution with 4-(2-hydroxyethyl)-1-piperazineethanesulfonic acid (HEPES) without stirring or shaking. Boiling the resultant nanostars for 5 minutes yielded spherical nanoparticles. Using these 2 structures, they modified a screen-printed electrode and optimized some conditions to conclude that the gold nanostar shape improved the

detection of arsenic compared to the spherical shape (figure 3) [29]. Later on, different studies used the same procedure for the gold nanostars synthesis to detect Cr (II), Cd (II), As (III) and Se (IV) [30, 31].

It is worthy to note that the use of gold nanoparticles associated with different sensors is gaining wide recognition. Even though the inhibition of enzymatic activity by heavy metals has been extensively studied, only one study uses enzyme-based biosensors with gold nanoparticles to detect mercury ions. The presence of gold nanoparticles considerably increased the analytical response [32]. Some researchers focus on the use of gold nanoparticles with amino acid- based biosensors. Amino acids and peptides (amino acid chains) have a high affinity towards some heavy metals which can be tuned by altering the peptide sequence [33]. Amino acids are known to bind heavy metal ions through cooperative metal-ligand interactions [34]. The use of gold nanoparticles with these biosensors amplifies the signal, improving the analytical performance [35]. The majority of authors focus on DNA-based biosensors with an emphasis on certain interactions between the DNA bases and certain heavy metal ions. Specifically, silver ion and mercury ion are well known to interact with cytosine-cytosine mismatch and thymine-thymine mismatch, respectively, to form stable base pairs [36 – 40].

Figure 3: Modification of carbon paste screen-printed electrodes by Au NPs for the detection of As^{3+} , Hg^{2+} and Pb^{2+} [29].

Table 2: Comparison between the different studies using gold nanoparticles for heavy metal detection.

HM	Technique	Electrode	LOD (μM)	Sensitivity ($\mu\text{A}/\mu\text{M}$)	Linear range (μM)	Addition to Au NPs	Real sample	Ref
Ag^+	DPV	Au	3×10^{-5}	124.6	$10^{-4} - 0.12$	Oligonucleotide sequences		36
As^{3+}	SWV	GCE	10^{-3}	71.7			River water	41
	SWV	GCE	8.89×10^{-4}	1985		Multiwalled Carbon nanotubes		42
	ASV	CuF	67.43	1318	0.067 – 0.8		Tap, well water	43
	SWASV	GNEE	1.78×10^{-4}	0.7492	0 – 0.2	3-(mercaptopropyl)trimethoxy silane		44
	SWASV	SPE	6.53×10^{-3}				River water	31
	SWASV	GCE	1.06×10^{-3}	113.9	0.01 – 0.67			45
	SWASV	SPE	0.01		0.03 – 10.2		Ground water	29
	LSV	GCE	0.024		0 – 1.2			47
	LSV	GCE	5.34×10^{-3}	32.8		Multiwalled Carbon nanotubes		42
	LSV	GCE	2×10^{-3}	14.2			River water	41
	LSASV	GCME	0.01		0.01 – 10.01	Carbon nanotube		48
	LSASV	GCE	3.7×10^{-3}	940	0.005 – 3	Pt NPs	Tap, spring, river water	49
	LSASV	GCE	2.9×10^{-3}	230	0.005 – 1	Porous graphitic carbon nitride	Tap, spring, river water	50
	DPV	GCE	0.2	0.8075	4 – 40	Crystal violet	Drinking water	51

	DPSV	SPCE	8.01×10 ⁻⁴		Up to 53.4	Poly(L-lactide)	Ground, surface water	52
	CV	Basal-plane pyrolytic praphite	0.8			Glassy carbon microsphere		53
	CV	SPCE	2.4×10 ⁻⁴		1.3×10 ⁻³ – 24	Ibuprofen	Drinking, tap, river, ground water	27
Cd²⁺	DPV	SPCE	0.023	26.19	0.07 – 4448		River, tap water	54
	DPV	GCE	0.022		0.05 – 300	Reduced graphene oxide, Tetraphenylporphyrin	Lake water	55
	DPASV	GCE	0.3	3.24	0 – 1.4			56
	SWV	GCE	8.89×10 ⁻⁴		4.4×10 ⁻³ – 0.35	Graphene, cysteine	Spring water	35
	SWASV	GCE	0.1	1.88	0.1 – 1	Carbon nanofibers		57
	SWASV	SPE	0.015				River water	31
	SWASV	GCE	6×10 ⁻⁵	2.2×10 ³	10 ⁻³ – 0.01	L-cysteine, reduced graphene oxide	Lake, tap, sewage, ground water	58
Cr³⁺	SWV	GCE			100 – 400			59
Cr⁶⁺	SWV	SPE	0.096		0.19 – 96		River water	60
	SWV	GCE	1.92×10 ⁻⁴	5.98	2.5×10 ⁻³ – 0.86		Sewage, tap water	61
	SWCSV	GCE	5.58×10 ⁻⁵		1.9×10 ⁻⁴ – 23	3-mercaptopropyl-trimethoxysilane		28
	AdSV	Graphene	0.02	1.94×10 ⁻⁴	0.48 – 5.77	Reduced graphene oxide, 4-pyridylethylmercaptan hydrochloride	Waste water	73
	DPV	SPCE	0.4	2.01×10 ⁻⁸	0.4 – 30		Tap, sea water	74
	CV	Indium tin oxide	2	0.3025	5 – 100		Tap, sea, stream water	75
	LSV	SPE	0.067		0.19 - 1442		Ground water	30
	LSV	SPCE	0.1	0.0572	0.38 – 3.8		River water	76
Cu²⁺	DPV	SPCE	0.126		0.79 – 157	L-cysteine		33
	DPASV	GCE	0.3	4.18	0 – 1.4			56
	ASV	GCE	5×10 ⁻⁵	3690	Logarithmic	Graphene quantum dots, cysteamine		68
	SWV	Au	10 ⁻⁷	0.29435×10 ⁻⁶	10 ⁻⁴ – 10	4-aminothiophenol, DNAzymes	Lake, tap water	37
	SWASV	SPE	0.025	4.368	0.31 – 4.72			70
	SWASV	GNEE	2.22×10 ⁻³		6.67×10 ⁻³ – 0.2	3-(mercaptopropyl)trimethoxy silane		44
	SWASV	GCE	0.1	4.41	0.1 – 1	Carbon nanofibers		57
Hg²⁺	SWASV	GNEE	9.97×10 ⁻⁵	2.006	0 – 0.07	3-(mercaptopropyl)trimethoxy silane		44
	SWASV	SPE	2.49×10 ⁻³		7.5×10 ⁻³ – 2.69		Ground water	29
	SWASV	GCE	2.99×10 ⁻⁵	708.3 7.37	3.99×10 ⁻⁵ – 2.49×10 ⁻⁴ 4.98×10 ⁻⁴ – 0.3	Chitosan graphene	River water	77
	SWASV	SPCE	3.99×10 ⁻³		2.49×10 ⁻⁵ – 10 ⁻⁴		Rain, river water	78
	SWASV	GCE	4.2×10 ⁻⁴	1370	0.64×10 ⁻³ – 4×10 ⁻³			79

	SWASV	Pencil graphite	4×10^{-15}		$10^{-13} - 10^{-4}$	DNA, L-methionine	Sea water, fish	80
	SWV	Au	5×10^{-4}		0.09-1.99	MSO, linker probes		81
	SWV	Carbon ionic liquid	2.3×10^{-3}		0.01 – 20	Thiolated amino acids	Waste, tap water	34
	SWV	SPE	9.97×10^{-4}	47.54	$2.5 \times 10^{-3} - 0.25$	Carbon nanotubes	Tap, river water	71
	DPV	GCE	3×10^{-5}	35.88	$10^{-4} - 0.02$	Multi-walled C nanotubes, DNA	Tap, lake water	39
	DPV	GCE	7.48×10^{-6}	1603.6	$4.98 \times 10^{-5} - 4.98 \times 10^{-3}$	Reduced graphene oxide, thymine-1-acetic acid, cysteamine	Tap water	62
	DPV	Au	5×10^{-4}		$10^{-3} - 0.1$	DNA, methylene blue	Tap, river water	38
	DPV	Indium tin oxide	7.8×10^{-4}		$5 \times 10^{-3} - 0.11$	Graphene oxide, 5-methyl-2-thiouracil	Tap, lake, bottled water	63
	DPV	Au	7.38×10^{-6}	333	$5 \times 10^{-5} - 2.5 \times 10^{-3}$	Thiolated probe DNA	Tap water	40
	DPASV	GCE	8×10^{-5}	749	$4 \times 10^{-4} - 0.096$	Single walled C nanotubes, poly(2-mercaptobenzothiazole)	River, tap water	65
	DPASV	GCE	0.3	3.39	0 – 1.4			56
	DPASV	GCE	10^{-4}	0.09	$5 \times 10^{-4} - 1.25$	Carbon nanotubes		82
	DPASV	Indium tin oxide	1.49×10^{-4}		$4.98 \times 10^{-4} - 0.05$		Tap, lake water, milk, soil	66
	ASV	GCE	0.16		0.79 – 3.15		River water	77
	ASV	GCE	7.48×10^{-7}		Up to 0.25		Drinking water	67
	ASV	GCE	2×10^{-5}	2470	$2 \times 10^{-5} - 0.1$	Graphene quantum dots, cysteamine		68
	CV	Au	0.01			MSO, ss-DNA		69
Pb²⁺	SWASV	GCE	4×10^{-5}	3.2×10^3	$10^{-3} - 0.01$	L-cysteine, reduced graphene oxide	Lake, tap, sewage, ground water	58
	SWASV	SPE	0.02		0.06 – 1.56		Ground water	29
	SWASV	SPE	0.0106	31.91	0.096 – 0.96			70
	SWASV	GCE	0.1	19.08	0.1 – 1	Carbon nanofibers		57
	SWV	SPE	4.34×10^{-4}	17.612	0.01 – 1.2		Tap, river water	71
	SWV	GCE	2.4×10^{-4}		$2.41 \times 10^{-3} - 0.19$	Graphene, cysteine	Spring water	72
	SWV	GCE	800	455.83	0.01 – 0.15	Graphene oxide	Tap water	83
	CV	Au	2.8×10^{-5}			DNA		32
	DPASV	GCE	0.3	17.63	0 – 1.4			56
	DPASV	GCE	4.83×10^{-5}	24.86	$2.41 \times 10^{-3} - 0.48$	Graphene oxide, chitosan	River water	84
	DPV	Au	10^{-3}		$5 \times 10^{-3} - 0.1$	DNAzymes		64
	DPV	GCE	4.3×10^{-9}		$10^{-8} - 5 \times 10^{-5}$	Multi-walled carbon nanotubes, DNA	Tap, river, spring water	85
Sb³⁺	DPASV	SPE	9.44×10^{-4}		$9.9 \times 10^{-2} - 0.909$		Sea water, drugs	86
Se⁴⁺	SWASV	SPE	0.01				River water	31

184 Abbreviations: Au gold, GCE glassy carbon electrode, CuF carbon ultra-microfiber, GNEE gold nanoelectrode
185 ensembles, SPE screen printed electrode, GCME carbon nanotube flow-through membrane electrode, SPCE
186 screen printed carbon electrode.

187 From the above table, it can be concluded that the best analytical performance for the detection of As (III)
188 is obtained using gold nanoparticles modified carbon nanotubes [42]. The process of electrode modification and
189 arsenic detection using square wave voltammetry can be achieved within minutes producing a very high sensitivity
190 and low LOD compared to similar studies. Although the authors claim that this sensor can be used for the detection
191 of arsenic in natural waters, to the best of our knowledge, the study has not been conducted. The modification of a
192 glassy carbon electrode with gold nanoparticles, L-cysteine and reduced graphene oxide showed a superior

performance in the detection of Cd (II) by square wave voltammetry (figure 4). The modified electrode was used to assess the concentrations of cadmium in different water sources (lake, sewage, tap and ground water) and the obtained results were comparable with those of AAS [58]. The same electrode exhibited the highest reported sensitivity for the detection of Pb (II) as well; however, a better LOD was obtained by Zhu et al. [85] using differential pulse voltammetry. The latter team modified a glassy carbon electrode with gold nanoparticles, cysteine, graphene and bismuth film which exhibited a low LOD and good repeatability and reproducibility along with the possible usage in real water samples such as spring water. However, the preparation procedure was too complex compared with other studies. The modification of a GCE with graphene quantum dots and Au NPs is the method of choice for the detection of Cu (II) using anodic stripping voltammetry. Both the LOD and sensitivity are better than those obtained with different modifications, unfortunately the electrode was not tested with real samples [68]. This same electrode showed the highest sensitivity for the detection of Hg (II), while an outstanding LOD was obtained by Hasanjani et al. [80] who used DNA and L-methionine along with Au NPs for the modification of a pencil graphite electrode. Interestingly, for the detection of Cr (VI), the sensitivities are either not reported, or are very small, with the best limit of detection obtained by Ouyang et al. [28] who modified a glassy carbon electrode with Au NPs and 3-mercaptopropyltrimethoxysilane. It should be noted that the focus of most of the papers using gold nanoparticles was on the synthesis of the nanoparticles and not on testing the applicability of the sensor in real samples. However, it was implied in some of the studies that their fabricated sensors can be used in real samples.

Figure 4: Schematic diagram of the possible interactions of Cd (II) and Pb (II) with gold nanoparticles, L-cysteine and reduced graphene oxide modified GCE electrode leading to the simultaneous analysis of the heavy metals [58]. Reproduced with permission from Elsevier

3.3. Bismuth Nanoparticles

The use of bismuth in different areas of chemistry (catalysis, organic synthesis, clusters...) has grown in the past decade. In electroanalytical chemistry, bismuth is used as an electrode coating, replacing the mercury electrode, because of its low toxicity and excellent peak resolution.

Lee et al. used bismuth nanopowder modified electrode to detect Zn, Cd and Pb ions using square wave anodic stripping voltammetry. Spherical bismuth was prepared with different particle size distribution in order to investigate its effect on the sensitivity and limit of detection of the studied metals. It was concluded that as the particle size decreases from 406 to 166 nm, both the sensitivity and the limit of detection are improved [87]. In another work, the same group modified a thick-film graphite electrode with bismuth nanopowder for the detection of thallium (Tl). Applying the same procedure, a limit of detection of 0.03 μg/L was obtained with the possibility to overcome any interference from divalent ions through the addition of EDTA [88]. Rico et al. [89] adopted the method of Lee et al. [87], to modify a screen-printed carbon electrode and detect the heavy metals. Optimization of the method included the accumulation configuration; both convective and flow configurations were tested. The limits of detection that were obtained at the flow cell for Zn (II), Cd (II) and Pb (II) were better than those at the convective cell. Those limits were 2.6, 1.3 and 0.9 ng/mL, respectively. Moreover, the reproducibility and sensitivity of the method were good after analyzing a certified reference sample and tap water, but further tests showed that high concentrations of Cu (II) interfered with the results. Saturno et al. modified a glassy carbon electrode with micro-nanoparticles/bismuth film for the determination of cadmium and lead by differential pulse voltammetry. The shape

and size of the nanoparticles were irregular, but they still obtained LODs of 11 µg/L for Cd (II) and 18 µg/L for Pb (II) with the response being highly reproducible [90]. Sahoo et al. modified a carbon paste electrode with graphene oxide and bismuth nanoparticles of diameter between 40 and 100 nm for the determination of zinc, cadmium, lead and copper ions using differential pulse anodic stripping voltammetry. A linear concentration range was obtained from 20 to 120 µg/L with limits of detection of 2.8, 0.55, 17 and 26 µg/L for Cd²⁺, Pb²⁺, Zn²⁺ and Cu²⁺, respectively. The performance of the electrode was tested in two different water samples, ground and lake water, and the concentrations of the divalent metals were determined [91]. The obtained LODs were comparable in the different studies for lead and cadmium ions. However, the problem of Cu (II) interference was faced in more than one study.

3.4. Platinum Nanoparticles

Platinum metal has received a lot of attention in the catalysis industry. Platinum nanoparticles (Pt NPs) have also found a lot of applications in electrochemical analyses due to their stability and conductivity [92]. Hrapovic et al. electrodeposited spherical platinum nanoparticles on a glassy carbon electrode and on a boron doped diamond electrode for the detection of Arsenite (As (III)). The electrodeposition resulted in a non-homogenous and non-uniform distribution of the Pt NPs. Using linear sweep voltammetry, the boron-doped electrode was proven to have a superior performance with a limit of detection of 0.5 ppb without interference from copper (II) ions. Moreover, the analysis of drinking water and river water from Montreal confirmed that As (III) concentrations can be determined without any interference [93]. Spherical platinum nanoparticles of diameters between 105 and 180 nm were also electrodeposited on a glassy carbon electrode by Dai et al. for the detection of Arsenic (III) ions. Cyclic voltammetry was applied and the measured limit of detection was 35 ppb. The performance of this electrode was compared using different techniques (square wave voltammetry and differential pulse voltammetry) all giving the same results. Moreover, possible interfering ions were investigated and the results still showed a clear peak for arsenic [94]. Both studies rely on the oxidation of As (III) to As (V) electrocatalyzed by Pt on a BDD electrode. Dai et al. obtained a LOD that is higher than recommended guidelines for water. Moreover, even though Hrapovic et al. obtained a lower LOD, the electrodeposited Pt NPs were not uniform in size.

3.5. Other metal nanoparticles

Owing to the advantages of nanoparticles in the modification of electrodes in electrochemical analysis, different metal nanoparticles have been used for the electrochemical detection of cadmium, copper, mercury and lead.

Two groups have reported the use of palladium nanoparticles (Pd NPs) for the detection of heavy metals. Both groups synthesized porous activated carbon (PAC), followed by the decoration of PAC with palladium nanoparticles via a one-step thermal reduction method (with slightly different conditions). Spherical 20 – 30 nm Pd NPs were used by Zhang et al. for the simultaneous and individual determination of Cd²⁺, Pb²⁺ and Cu²⁺ by applying square wave anodic stripping voltammetry (figure 5). The obtained limits of detection for individual determinations were 13.33, 6.6 and 11.92 nM for Cd²⁺, Pb²⁺ and Cu²⁺, while for simultaneous determinations the values were 20.9, 9.19 and 14.78 nM, respectively. The applicability of the sensor was successfully tested in practical water, without specifying what this water is. [95]. Veerakumar et al. were able to obtain smaller crystals with an average size of 4 – 5 nm. They used differential pulse voltammetry for the detection of Cd²⁺, Pb²⁺, Cu²⁺ and Hg²⁺. Results showed superior performance for both individual and simultaneous detections. For simultaneous detection of Cd²⁺, Pb²⁺, Cu²⁺ and Hg²⁺, a linear response in the ion concentration ranges of 0.5 – 5.5, 0.5 – 8.9, 0.5 – 5.0 and 0.24 – 7.5 µM, with sensitivities of 66.7, 53.8, 41.1 and 50.3 µA µM⁻¹.cm⁻², and detection limits of 41, 50, 66 and 54 nM, respectively, were observed [96].

Lee et al. have used tin nanoparticles (Sn NPs) with reduced graphene oxide on glassy carbon electrode for the determination of Cd²⁺, Pb²⁺ and Cu²⁺. The Sn NPs of 50 nm diameter were synthesized using the electrochemical reduction of Sn²⁺ with graphene oxide solution. Individual analysis of metal ions using square wave anodic stripping voltammetry showed a high stability and detection limits of 0.63 nM, 0.60 nM and 0.52 nM, respectively. However, simultaneous analysis of the heavy metal increased the detection limits to 7.56 nM, 6.77 nM and 5.62 nM, respectively due to the possible formation of intermetallic compounds. The feasibility of the sensor was tested in tap water samples with and without spiking. No peaks were observed before spiking, while recoveries ranged between 97 and 102% after spiking [97].

Toghill et al. modified a BDD electrode with Sb nanoparticles for the detection of Cd²⁺ and Pb²⁺ using linear sweep anodic stripping voltammetry. The nanoparticles were electrochemically deposited on the electrode, with an average size of 108 ± 70 nm, but due to the toxicity of Sb, the team tried to use the smallest possible concentration of antimony. Based on this study, the addition of Sb nanoparticles didn't improve the individual detection of each analyte as compared to the bare BDD. On the other hand, simultaneous detection of cadmium and lead was improved and Pb did not inhibit Cd from nucleating on the electrode surface like previous works [98].

Figure 5: (a) and (b) TEM and HR-TEM images of Pd@Pac. (c) SWASV curves for 500 nM each of Cd^{2+} , Pb^{2+} and Cu^{2+} on the bare, PAC-modified and Pd@PAC-modified GCEs in 0.1 M acetate buffer solution (pH 4.8). Conditions: deposition potential: 2.1 V; deposition time: 210 s; room temperature; amplitude: 50 mV; increment potential: 4 mV; and frequency: 15 Hz. (d) SWASV curves of the Pd@PAC/GCE for the individual analysis of Cd^{2+} [95]. Reproduced with permission from Elsevier

4. Metal oxide nanoparticles

Metal oxide nanoparticles are being extensively studied in electrochemical detection these past few years. They have been synthesized using different methods to obtain different sizes, stability, and morphology. These differences allow them to exhibit various electrical and photochemical properties resulting in different applications [99]. Various oxides of metals, mainly transition metals, have been used in the modification of electrodes for the detection of different analytes including heavy metals. Even though these oxides have been synthesized using almost all transition metals, only a few were used for the detection of heavy metals.

4.1. Iron oxide Nanoparticles

The most common metal oxide used for the detection of heavy metals is iron oxide in different forms (MnFe_2O_4 , Fe_2O_3 and Fe_3O_4). While iron in the first 2 species is found as Fe^{3+} , both Fe^{2+} and Fe^{3+} are present in Fe_3O_4 , which permits an electron hopping process between the 2 ions, and thus increasing the electrical conductivity compared to MnFe_2O_4 and Fe_2O_3 .

Lee et al. were the first group to report the use of iron oxide in the form of Fe_2O_3 . Briefly, graphene oxide was prepared and reduced, after which Fe_2O_3 /graphene composites were prepared using a solvent-less method by mixing iron (III) acetylacetonate and oleic acid with the prepared graphene. The synthesized spherical maghemite nanoparticles had an average size of 30 nm and uniformly decorated the graphene sheets. Prior to be used in the detection of Pb^{2+} , Zn^{2+} and Cd^{2+} in tap water, the nanoparticles with graphene oxide were deposited on a cleaned glassy carbon electrode and dried under infrared heat lamp, and the electrode was modified with bismuth. Differential pulse anodic stripping voltammetry was applied and the analysis showed a linear range of detection between 1 and 100 $\mu\text{g.L}^{-1}$ for all the ions, and limits of detection of 0.11 $\mu\text{g.L}^{-1}$ for Zn (II), 0.08 $\mu\text{g.L}^{-1}$ for Cd (II) and 0.07 $\mu\text{g.L}^{-1}$ for Pb (II) [100]. Li et al. later reported the synthesis of 2 different morphologies (nanorods and nanocubes) of Fe_2O_3 for the electroanalysis of Pb (II) by anodic stripping voltammetry. The limit of detection of Pb (II) by nanorods was much smaller (0.0034 μM) than that with nanocubes (0.083 μM). Moreover, Fe_2O_3 nanorods proved to be much more sensitive (109.67 $\mu\text{A}.\mu\text{M}^{-1}$) compared to nanocubes (17.68 $\mu\text{A}.\mu\text{M}^{-1}$). The practicability of the proposed sensor was evaluated in drinking water, and good recoveries were observed with a slightly decreased sensitivity for lead that could be the result of interfering ions [101].

On the other hand, Fe_3O_4 is the most common form of iron oxide used to detect heavy metals. Most recently, Fe_3O_4 nanoparticles have been investigated for heavy metal detection. Fe_3O_4 is known for having a high

affinity for heavy metal ions, but only a few reports that use iron oxide alone are available. This is due to the fact that iron oxide nanoparticles have the tendency to aggregate and become non-conductive units [102]. Most studies use either functionalized Fe_3O_4 or Fe_3O_4 combined with other materials. Table 3 summarizes the different studies done using Fe_3O_4 to detect heavy metals. Most of the magnetic nanoparticles used in heavy metal detection were spherical or quasi-spherical with sizes ranging between 5.8 nm and 200 nm. Sun et al. synthesized different Fe_3O_4 shapes by varying the ratio of Fe^{2+} to Fe^{3+} ions. They used a one-step coprecipitation method with the following molar ratios of $\text{Fe}^{2+}/\text{Fe}^{3+}$: 2/5 to obtain spherical nanoparticles, 4/0 to get rod Fe_3O_4 (20 – 50 nm in width and 200 – 300 nm in length) and 5/4 to obtain band Fe_3O_4 (80 – 120 nm in width and 300 – 400 nm in length) (Figure 6). Along with reduced graphene oxide, the iron oxide nanoparticles were used for the detection of Pb (II) and it was shown that the sensitivity is best with the band nanoparticles followed by spherical nanoparticles and then rod nanoparticles (the results are shown in decreasing order in Table 3). On the other hand, the limit of detection did not differ much between the three structures. Band NPs were also used for the detection of Cu (II) and Cd (II) [103].

Figure 6: Synthesis of Fe_3O_4 nanoparticles, nanorods and nanobands done by Sun et al. [103]

Table 3: Comparison between the different studies using Fe_3O_4 to detect heavy metals.

HM	Technique	Electrode	LOD (μM)	Sensitivity ($\mu\text{A}/\mu\text{M}$)	Linear range (μM)	Addition to iron oxide NPs	Real sample	Ref
Pb^{2+}	SWV	GCE	2.41×10^{-4}		0 – 0.24	DMSA	Urine	104
Ag^+ Hg^{2+}	SWV	GCE	3.4×10^{-3} 1.7×10^{-3}		0.01 – 0.15 0.01 – 0.1	Au NPs, DNA	Natural water, orange juice, wine	105
As^{3+}	SWASV	GCE	1.29×10^{-4}	1015	1.33×10^{-3} – 0.27	Au NPs	Natural water	106
Pb^{2+}	SWASV	GCE	0.15	10.07	0.5 – 8	Amine	Waste water	107
Pb^{2+} Cd^{2+}	SWASV	GCE	1.4×10^{-5} 9.2×10^{-5}	235 196	5×10^{-3} – 0.6 0.02 – 0.59	polydopamine	Aqueous effluent	108
Cd^{2+}	SWASV	GCE	0.056	14.82	0 – 0.8	Reduced graphene oxide		109
Pb^{2+}	SWASV	GCE	0.17 0.073 0.033 0.05 0.04	13.6 7.4 2.4 10.1 4.35	0.4 – 1.5 0.7 – 1.2 0.8 – 1.2 0.5 – 1.5 0.4 – 1.1	Reduced graphene oxide		103
Cu^{2+} Cd^{2+} Cu^{2+}	SWASV	CPE	1.78×10^{-3} 0.014			Macrocyclic Schiff-base ligand	Carrot, fish, rice,	117

Hg²⁺			4.98×10 ⁻³				different waters	
Pb²⁺	SWASV	GCE	0.119	14.9	0.3 – 1.3		River water	110
Cd²⁺			0.154	3.18	0.3 – 1.3			
Hg²⁺			0.0839	7.67	1.3 – 1.8			
Cu²⁺			0.0765	4.73	0.3 – 1.7			
Pb²⁺	SWASV	GCE	0.0422	50.6	0.1 – 1.3	Chitosan	River water	111
Hg²⁺			0.0957	9.65	0.4 – 1.1			
Cu²⁺			0.0967	4.24	0.3 – 1.2			
Cd²⁺			0.0392	8.11	1.2 – 1.7			
Cd²⁺	SWASV	GCE	0.2	12.15	0.4 – 1.1	Terephthalic acid	River water	102
Pb²⁺			0.04	8.56	0.4 – 1.1			
Hg²⁺			0.3	13.81	0.4 – 1.1			
Cd²⁺	SWASV	GCE	1.52×10 ⁻³	8.4	4.4×10 ⁻³ – 0.89	Glutathione	Natural water	112
Pb²⁺			8.78×10 ⁻⁴	27.37	2.41×10 ⁻³ – 0.48			
Ni²⁺	LSV	Pt	3.5×10 ⁻³		5×10 ⁻² – 1	Chitosan	Sewage water, urine	113
					3 – 100			
Cr⁶⁺	LSV	SPCE	0.01		0.5 - 10	Au NPs, Sephadex G-150	Lake water	114
Ag⁺	DPV	GCE	0.059		0.117 – 17.7	Au NPs	Lake, tap, synthesized water	115
Cu²⁺	DPV	GCE	0.5×10 ⁻³			Multi-walled carbon nanotubes, poly-3-nitroaniline		116

Abbreviations: CPE carbon paste electrode

Lead and cadmium are the most studied heavy metal ions with Fe₃O₄ NPs. The lowest LODs and highest sensitivities for both ions were detected by Song et al. who coated the magnetic nanoparticles with polydopamine. Additionally, the proposed method that uses SWASV was applied for the determination of lead in aqueous effluents of a factory. The method proved to be successful and comparable with ICP-AES [108]. Moreover, it is worthy to note that square wave voltammetry and glassy carbon electrodes are the most commonly used when working with Fe₃O₄ NPs.

Recent studies have reported that the addition of another metal to iron oxide to produce spinel ferrites can enhance its electrochemical behavior towards some heavy metals. All the groups relied on a solvothermal method for the synthesis of MnFe₂O₄ along with surface modifications when applicable. The ferrite nanoparticles prepared had a spherical morphology with sizes ranging between 200 and 400 nm.

In this regard, one group has done different studies on MnFe₂O₄ to detect different heavy metals. Zhou et al. successfully synthesized MnFe₂O₄ nanocrystals and used them to modify a gold electrode and detect As (III) using SWASV. A linear response was obtained at As concentrations between 10 and 100 ppb with a limit of detection of 1.95 ppb and a sensitivity of 0.295 µA/ppb. The sensor was successfully applied in tap water for the detection of arsenic in tap water with a recovery of 95.6% [118]. In another attempt to detect As (III), they modified a glassy carbon electrode with MnFe₂O₄ and gold nanoparticles. Using SWASV, the electrode showed a sensitivity of 0.315 µA/ppb and a LOD of 3.37 ppb with the sensor also being used to test tap water [119], proving that a similar sensitivity and lower LOD for the detection of As (III) were obtained without modification with gold nanoparticles. Then, the same group modified a glassy carbon electrode with these nanoparticles for the selective determination of Pb²⁺. Using SWASV, a sensitivity of 19.9 µA.µM⁻¹ and LOD of 0.054 µM were obtained under optimized conditions, while the response to Cd²⁺, Hg²⁺, Cu²⁺ and Zn²⁺ was poor. The modified electrode was successfully used to detect a spiked lead concentration in river water [120].

In a later study, and in attempt to obtain a better analytical performance, Zhou et al. also used MnFe₂O₄ and graphene oxide to modify a glassy carbon electrode for the detection of Pb (II), Cd (II), Cu (II) and Hg (II). Using square wave anodic stripping voltammetry, the best electrochemical response was obtained for Pb (II) with a sensitivity of 33.9 mA/mM and a LOD of 0.0883 mM. The sensitivities for Cd (II), Cu (II) and Hg (II) were 13.5 mA/mM, 13 mA/mM and 5.79 mA/mM, respectively. Moreover, the limits of detection were calculated to be 0.778 mM, 0.0997 mM and 1.16 mM, respectively, with a successful application in the analysis of river water [121]. They also tried modifying a glassy carbon electrode with L-cysteine functionalized MnFe₂O₄ to detect Pb (II), Hg (II), Cu (II) and Cd (II) by SWASV. The developed sensor was particularly selective towards lead, with sensitivities of 57 µA/µM and 35.3 µA/µM and LODs of 0.0843 µM and 0.0607 µM under individual and simultaneous conditions of detection. The sensor was also successfully used to monitor the concentration of lead in river water [122]. Thus, all attempts to modify MnFe₂O₄ nanoparticles to detect different heavy metal ions have showed a higher selectivity and preference for Pb (II). Moreover, although all studies have checked the practicability of the different modified sensors in real water samples, more experimentation should be done in this regard by monitoring the ions in water samples other than tap and river water.

4.2. Other metal oxide nanoparticles

Co_3O_4 nanoparticles are one of the most versatile transition metal oxides mainly because of their high reactivity, superior stability and excellent electrocatalytic activity. Salimi et al. electrodeposited cobalt oxide nanoparticles on a glassy carbon electrode in order to detect Arsenic (III) using cyclic voltammetry. The nanoparticles were small in size (100 nm) and uniformly distributed on the surface of the electrode. The results exhibited a detection limit of 0.6 μM and no interferences in presence of other heavy metal ions with a linear range of 10 – 50 μM . The possibility to use this sensor for the analysis of water samples was tested on drinking water from a village in Kurdistan and a concentration of 2.1 μM of As was found in water and confirmed by atomic absorption spectrometry [123].

On the other hand, titanium oxide nanoparticles have attracted attention due to their biocompatibility, high conductivity, stability and low cost. TiO_2 nanoparticles were used to detect Hg (II) by Zhou et al. Titanium oxide nanoparticles were prepared using sol-gel process. Briefly, tetrabutyl titanate was dissolved in ethanol and acetic acid, after which water was added dropwise with vigorous stirring until a white transparent sol was formed. The sol was transformed into a gel, dried and calcinated to obtain TiO_2 powder. The nanoparticles, along with gold nanoparticles, were used to modify a gold electrode with the help of chitosan as a binder. Characterization showed that TiO_2 nanoparticles had a size range between 5 and 15 nm, with gold nanoparticles on their surface. In a medium buffered at a pH of 5 and using differential pulse anodic stripping voltammetry, the sensor showed a wide linear concentration range of Hg (II) from 5 to 400 nM and a low detection limit of 1 nM with a sensitivity of 3.133 $\mu\text{A} \cdot \mu\text{M}^{-1}$ and no interference from different ions. Moreover, the sensor was tested for Hg (II) in some water samples, and the recoveries were between 98 and 106% for all samples [124]. Zhang et al. used purchased titanium oxide nanoparticle to modify a gold strip electrode to detect As (III) by linear sweep voltammetry. The linear range of analysis was obtained between 10 $\mu\text{g/L}$ and 80 $\mu\text{g/L}$ with a limit of detection of 10 $\mu\text{g/L}$ and the possibility to use it for arsenic determination in real samples. Moreover, the stability of the electrodes was investigated and 96% of the initial response current was retained after 15 days [125]. Mao et al. incorporated TiO_2 nanoparticles into multiwalled carbon nanotubes and a cationic surfactant to modify a glassy carbon electrode. LSASV was used for the determination of mercury (II) and a linear range of 0.1 – 100 μM with a limit of detection of 0.025 μM were obtained. The potential applicability of the sensor was evaluated in spiked and non-spiked samples of river and industrial wastewater, and the sensor was able to successfully detect mercury in the wastewater even before spiking [126]. Ramezani et al. constructed an electrochemical sensor using spherical TiO_2 nanoparticles intermixed with graphite powder and 1,2-bis-[o-aminophenyl thio] ethane. Using DPASV, and under optimum conditions, Cd (II) was detected in a linear concentration range of 2.9 nM – 4.6 μM with a limit of detection of 2 nM. A spiked concentration of Cd (II) ions in tap water was successfully detected without requiring any treatment of the water [127]. Liu et al used an Fe_3O_4 - TiO_2 core-shell nanoparticles on a glassy carbon electrode for the detection of Pb (II). Using square wave voltammetry (SWV), the limit of detection of the proposed sensor was calculated to be 7.5×10^{-13} M with a linear range of 4×10^{-13} M – 2.5×10^{-8} M. Different concentrations of Pb (II) were evaluated in river and rain water samples with recoveries ranging between 99 and 110% [128]. Each one of these modifications with TiO_2 NPs presents its advantages, from outstanding limit of detection of 7.5×10^{-13} M for Pb (II) [128] to the wide linear range of detection of 2.9 nM – 4.6 μM for Cd (II) [127]; nevertheless, more experimentation is required in order to be able to compare between the different methods.

Different forms of manganese oxide nanoparticles have been explored due to properties like low cost, non-toxicity and high activity (mainly in alkali media). Zhang et al. focused on investigating the difference between various MnO_2 structures, including nanoparticles, nanotubes and nanobowls on the mutual interference of Cd^{2+} , Pb^{2+} and Zn^{2+} (figure 7). The nanoparticles were prepared by dissolving potassium permanganate in ethanol, washing the product with water and drying it. The nanotubes were prepared by dissolving $\text{MnSO}_4 \cdot \text{H}_2\text{O}$ and KMnO_4 in water, heating the mixture for 12 hours, washing the product with water and drying it. The nanobowls were hydrothermally prepared by dissolving $\text{MnSO}_4 \cdot \text{H}_2\text{O}$ and $(\text{NH}_4)_2\text{S}_2\text{O}_8$ in water, heating the mixture for 24 h, washing the product with water and drying it. The group modified a glassy carbon electrode with MnO_2 and square wave anodic stripping voltammetry was applied. The individual response was studied for Cd (II) and Zn (II) and the higher sensitivities were observed with Cd (II) (18.05 $\mu\text{A}/\mu\text{M}$ for the nanoparticles, 12.36 $\mu\text{A}/\mu\text{M}$ for the nanotubes and 18.69 $\mu\text{A}/\mu\text{M}$ for the nanobowls). However, the interference mechanism was not clearly understood and demonstrated. Upon fixing the concentration of Zn (II), the trend in the mutual interference between Cd (II) and Zn (II) was similar on the three morphologies of MnO_2 . On the other hand, when fixing the Cd (II) concentration, the interference between Cd (II) and Zn (II) on MnO_2 nanoparticles was different from that on the other structures. Similarly, the interference between Cd (II) and Pb (II) on MnO_2 nanotubes was different from the other morphologies [129]. Fayazi et al. used MnO_2 nanotubes for the detection of Hg (II) using differential pulse voltammetry. A simple chemical precipitation followed by a hydrothermal method were used for the fabrication of halloysite nanotubes – iron oxide – manganese oxide nanocomposite. The electrode displayed a limit of detection of 0.2 $\mu\text{g} \cdot \text{L}^{-1}$ in a linear range of 0.5 – 150 $\mu\text{g} \cdot \text{L}^{-1}$. The proposed sensor was validated for mercury determination in well and aqueduct water where the concentration of Hg (II) before spiking was below the detection limit and the recoveries after spiking were close to 100%. [130]. Salimi et al. investigated the use of yet another form of manganese oxide nanoparticles: nanoflakes. A glassy carbon electrode was first modified with chitosan and multiwalled carbon nanotubes followed by the electrodeposition of manganese oxide. Using cyclic voltammetry, Cr (III) was detected in a linear range of

40 – 360 μM , and the electrode was used for the detection of chromium ions in drinking water samples such that the calculated Cr (III) concentration agreed with that measured by AAS [131]. All these studies were nicely elaborated, but at the same time each one of them still misses some important data on the analytical performance of each electrode.

Figure 7: SEM images of (a) MnO_2 nanoparticles, (b) MnO_2 nanobowls and (c) MnO_2 nanotubes. SWASV responses of MnO_2 (d and g) nanoparticles, (e and h) nanobowls and (f and i) nanotubes modified electrode towards Cd (II) and Zn (II) at different concentrations in 0.1 M NaAc–HAc (pH 5.0), respectively. The insets are plots of current vs concentration of Cd (II) and Zn (II), respectively [129]. Reproduced with permission from Elsevier

Wei et. al used tin oxide nanoparticles with reduced graphene oxide for the determination of Cd^{2+} , Pb^{2+} , Cu^{2+} and Hg^{2+} by square wave anodic stripping voltammetry. SnO_2 nanoparticles are known to have a high electric conductivity and chemical sensitivity, along with the ability to adsorb heavy metal ions. The nanoparticles were prepared by a one-step wet chemical method after the preparation of reduced graphene oxide. This step involved mixing graphene oxide with $\text{SnCl}_4 \cdot 5\text{H}_2\text{O}$ in water. After stirring and centrifuging, the product was heated to improve its crystallinity. The obtained nanoparticles were uniformly distributed on the graphene network, with an average diameter of 4 – 5 nm. Individual and simultaneous determination of these ions were done, and the limits of detection of the ions were 1.015×10^{-10} M, 1.839×10^{-10} M, 2.269×10^{-10} M and 2.789×10^{-10} M, respectively, with an enhanced sensitivity for Cu (II) and Hg (II) when analyzed simultaneously. The authors reported that even though the sensitivities and LODs are not the best, but the electrode can be used without needing regeneration [132]. Yang et al. synthesized an amino-based porous SnO_2 nanowires and modified a glassy carbon electrode for the detection of Cd (II) by means of SWASV. The sensor displayed a sensitivity of $124.03 \mu\text{A} \cdot \mu\text{M}^{-1}$ and a limit of detection of

0.0054 μM , with an effective determination of cadmium ions in water samples [133]. Cui and coworkers synthesized a 2-amino benzothiazole and 2-amino-4-thiazoleacetic acid derivative graphene enhanced with fluorine, chlorine and iodine on SnO_2 nanoparticles for the detection of Cu (II), Cd (II) and Hg (II). The nanoparticles were nearly spherical and well distributed on the graphene sheet. Using cyclic voltammetry, it was shown that the fluorine- SnO_2 sensor is the best suited for the detection of Cu (II), and thus differential pulse voltammetry was used. A linear range from 2 to 1000 nM and a LOD of 0.3 nM were obtained. The electrode was later used for the simultaneous detection of Cd (II), Cu (II) and Hg (II) such that all the linear ranges were between 20 and 2000 nM and the LODs were 5 nM, 3 nM and 5 nM, respectively, and hence the electrode was successfully evaluated for these ions in lake water, with results in agreement with those of AAS [134].

In addition to the general properties of nanoparticles, CeO_2 has a strong adsorption ability. Li et al. used a glassy carbon electrode modified with cerium oxide (CeO_2) nanoparticles, multi-wall carbon nanotubes, 1-ethyl-3-methylimidazolium tetrafluoroborate (EMIMBF_4) and DNA to detect Pb (II). Differential pulse voltammetry was applied and the linear range for Pb (II) was between 10^{-8} and 10^{-5} M with the detection limit being 5×10^{-9} M hardly exhibiting any interference from five different metal ions with a practical application for the detection of lead in tap water [135].

Yukrid et al. used thermal pyrolysis for the synthesis of ZnO nanorods mixed with graphene solution through colloidal coagulation for the modification of a screen-printed carbon electrode. Anodic stripping voltammetry was used for the concurrent determination of Cd^{2+} and Pb^{2+} . The limits of detection obtained were $0.6 \mu\text{g.L}^{-1}$ for Cd (II) and $0.8 \mu\text{g.L}^{-1}$ for Pb (II) in a linear range of 10 – 200 $\mu\text{g.L}^{-1}$, respectively. These heavy metal ions were simultaneously determined in wastewater samples, with measurements in accordance with those obtained by ICP-OES [136]. Yuan-Yuan et al. prepared a ZnO nanotubes/reduced graphene modified glassy carbon electrode via electrospinning and thermal decomposition of zinc acetate-polyacrylonitrile-polyvinyl pyrrolidone. SWASV was used for the analysis of Pb (II). A linear concentration range of 2.4×10^{-9} – 4.8×10^{-7} M and the limit of detection was 4.8×10^{-10} M [137].

MgO nanoflowers were also used for the detection of Pb (II) and Cd (II). Their synthesis involved mixing a magnesium precursor with potassium carbonate and heating the mixture to obtain a white precipitate that was later collected and calcinated. These nanoflowers along with Nafion® were used to modify a glassy carbon macroelectrode and SWASV was used under optimized conditions. The results for Pb (II) and Cd (II) detection showed linear ranges between 1 and 30 nM for lead and between 20 and 140 nM for cadmium, sensitivities of 0.706 and $0.077 \mu\text{A.nM}^{-1}$ and limits of detection of 2.1×10^{-12} M and 8.1×10^{-11} M, respectively. The sensor was successfully tested for Pb (II) in Reservoir water samples from China [138].

5. Summary and Perspectives

Electrochemical methods have been extensively used for the detection of heavy metals. However, the use of metal and metal oxide nanoparticles for modifying electrochemical sensors, for the voltammetric detection of heavy metals, proves to be more promising. Taking advantage of the unique properties of nanoparticles along with the advantages of electrochemical detection over conventional detection techniques, the analytical performance of all the reported electrodes was enhanced. The result was a rapid response time, increased sensitivity, very low limits of detection, simplified operational procedures and enhanced reproducibility.

In this review, the emphasis was on electrochemical sensors that could be applied for water samples. However, different water systems exist, from sea water, river water, tap water, drinking water to wastewater. Thus, these matrices are considered complex, some more than others, with the presence of different heavy metals either free or complexed, cations and anions, organic and inorganic materials... Despite the claims that some of the fabricated sensors were tested in these complex matrices, transition to commercialization remains shy. Moreover, most of these sensors require significant improvements, especially in the selectivity and capability of simultaneous analysis, before they can be applied for commercial use. Besides, commercialization also presents the challenges of reusability and mass production, which question the simplicity and cost-effectiveness of some of the sensors. For example, great focus has been given to gold nanoparticles and some excellent electrochemical sensors have been developed for the detection of heavy metals with LODs much lower than those obtained with Fe_3O_4 NPs for instance. Nonetheless, noble metals such as gold and silver are known to be costly, and hence an alternative that presents high selectivity and can detect limits lower than the guidelines such as Fe_3O_4 NPs would be convenient. On the other hand, several materials were used along with the nanoparticles for the modification of the electrodes. However, with the use of all these nanoparticles, a few inconveniences, including toxicity and non-biocompatibility during the synthesis of the modified electrodes, still exist.

Recently, bimetallic nanoparticles are emerging as promising candidates that can overcome the challenges faced by mono-metallic nanoparticles. These materials are the result of combining two different metals, thus offering the advantages of each metal alone, along with new characteristics that arise from blending the two metals. Hence, we expect to see in the near future a major increase in research using bimetallic nanoparticles dedicated for the electrochemical detection of heavy metal ions.

Acknowledgements

The authors acknowledge the financial support of the EU H2020 research and innovation program entitled KardiaTool grant #768686.

Declaration of interests:

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

*References:

- [1] Tchounwou, P. B., Yedjou, C. G., Patlolla, A. K., & Sutton, D. J. (2012). Heavy metal toxicity and the environment. *Exp Suppl*, 101, 133-164. https://doi:10.1007/978-3-7643-8340-4_6
- [2] Barton, J., García, M. B. G., Santos, D. H., Fanjul-Bolado, P., Ribotti, A., McCaul, M., ... & Magni, P. (2016). Screen-printed electrodes for environmental monitoring of heavy metal ions: a review. *Microchimica Acta*, 183(2), 503-517. <https://doi:10.1007/s00604-015-1651-0>
- [3] Ariño, C., Serrano, N., Díaz-Cruz, J. M., & Esteban, M. (2017). Voltammetric determination of metal ions beyond mercury electrodes. A review. *Analytica chimica acta*, 990, 11-53. <https://doi:10.1016/j.aca.2017.07.069>
- [4] Kumar, P., Kim, K. H., Bansal, V., Lazarides, T., & Kumar, N. (2017). Progress in the sensing techniques for heavy metal ions using nanomaterials. *Journal of industrial and engineering chemistry*, 54, 30-43. <https://doi:10.1016/j.jiec.2017.06.010>
- [5] Sabine Martin, W. G. (2009). Human Health Effects of Heavy Metals. *Environmental Science and Technology Briefs for Citizens*.
- [6] Turdean, G. L. (2011). Design and Development of Biosensors for the Detection of Heavy Metal Toxicity. *Int. J. Electrochem.*, 2011, 1-15. <https://doi:10.4061/2011/343125>
- [7] Verma, N., & Singh, M. (2005). Biosensors for heavy metals. *BioMetals*, 18(2), 121-129. <https://doi:10.1007/s10534-004-5787-3>
- [8] WHO. *Guidelines for Drinking-water Quality* (4th ed.). 2011
- [9] Corr, J. J., & Larsen, E. H. (1996). Arsenic speciation by liquid chromatography coupled with ionspray tandem mass spectrometry. *J. Anal. At. Spectrom.*, 11(12), 1215. <https://doi:10.1039/ja9961101215>
- [10] Yin, C., Iqbal, J., Hu, H., Liu, B., Zhang, L., Zhu, B., & Du, Y. (2012). Sensitive determination of trace mercury by UV-visible diffuse reflectance spectroscopy after complexation and membrane filtration-enrichment. *J. Hazard. Mater.*, 233-234, 207-212. <https://doi:10.1016/j.jhazmat.2012.07.016>
- [11] Pohl, P. (2009). Determination of metal content in honey by atomic absorption and emission spectrometries. *TrAC Trends Anal. Chem.*, 28(1), 117-128. <https://doi:10.1016/j.trac.2008.09.015>
- [12] Gomez-Ariza, J. L., Lorenzo, F., & Garcia-Barrera, T. (2005). Comparative study of atomic fluorescence spectroscopy and inductively coupled plasma mass spectrometry for mercury and arsenic multispeciation. *Anal. Bioanal. Chem.*, 382(2), 485-492. <https://doi:10.1007/s00216-005-3094-7>
- [13] Aranda, P. R., Pacheco, P. H., Olsina, R. A., Martinez, L. D., & Gil, R. A. (2009). Total and inorganic mercury determination in biodiesel by emulsion sample introduction and FI-CV-AFS after multivariate optimization. *J. Anal. At. Spectrom.*, 24(10). <https://doi:10.1039/b903113h>
- [14] Chen, S.-H., Li, Y.-X., Li, P.-H., Xiao, X.-Y., Jiang, M., Li, S.-S., Liu, W.-Q. (2018). Electrochemical spectral methods for trace detection of heavy metals: A review. *TrAC Trends Anal. Chem*, 106, 139-150. <https://doi:10.1016/j.trac.2018.07.005>
- [15] Lu, Y., Liang, X., Niyungeko, C., Zhou, J., Xu, J., & Tian, G. (2018). A review of the identification and detection of heavy metal ions in the environment by voltammetry. *Talanta*, 178, 324-338. <https://doi:10.1016/j.talanta.2017.08.033>
- [16] Aragay, G., & Merkoçi, A. (2012). Nanomaterials application in electrochemical detection of heavy metals. *Electrochim. Acta*, 84, 49-61. <https://doi:10.1016/j.electacta.2012.04.044>

573 [17] Bansod, B., Kumar, T., Thakur, R., Rana, S., & Singh, I. (2017). A review on various electrochemical techniques
574 for heavy metal ions detection with different sensing platforms. *Biosens. Bioelectron.*, 94, 443-455.
575 <https://doi:10.1016/j.bios.2017.03.031>

576 [18] Lu, Y., Liang, X., Niyungeko, C., Zhou, J., Xu, J., & Tian, G. (2018). A review of the identification and detection
577 of heavy metal ions in the environment by voltammetry. *Talanta*, 178, 324-338.
578 <https://doi:10.1016/j.talanta.2017.08.033>

579 [19] Hoyos-Arbeláez, J., Vázquez, M., & Contreras-Calderón, J. (2017). Electrochemical methods as a tool for
580 determining the antioxidant capacity of food and beverages: A review. *Food Chemistry*, 221, 1371-1381.
581 <https://doi:10.1016/j.foodchem.2016.11.017>

582 [20] Borrill, A., Reily, N. E., & Macpherson, J. V. (2019). Addressing the Practicalities of Anodic Stripping
583 Voltammetry for Heavy Metal Detection: A Tutorial Review. *The Analyst*. <https://doi:10.1039/c9an01437c>

584 [21] Barek, J., Fogg, A. G., Muck, A., & Zima, J. (2001). Polarography and Voltammetry at Mercury Electrodes.
585 *Critical Reviews in Analytical Chemistry*, 31(4), 291-309. <https://doi:10.1080/20014091076776>

586 [22] Cheng, Y., Li, H., Fang, C., Ai, L., Chen, J., Su, J., Fu, Q. (2019). Facile synthesis of reduced graphene
587 oxide/silver nanoparticles composites and their application for detecting heavy metal ions. *J. Alloys Compd.*, 787,
588 683-693. <http://doi:10.1016/j.jallcom.2019.01.320>

589 [23] Han, T., Jin, J., Wang, C., Sun, Y., Zhang, Y., & Liu, Y. (2017). Ag Nanoparticles-Modified 3D Graphene Foam
590 for Binder-Free Electrodes of Electrochemical Sensors. *Nanomaterials (Basel)*, 7(2).
591 <https://doi:10.3390/nano7020040>

592 [24] Xing, S., Xu, H., Chen, J., Shi, G., & Jin, L. (2011). Nafion stabilized silver nanoparticles modified electrode
593 and its application to Cr(VI) detection. *J. Electroanal. Chem.*, 652(1-2), 60-65.
594 <https://doi:10.1016/j.jelechem.2010.03.035>

595 [25] Renedo, O. D., & Julia Arcos Martínez, M. (2007). A novel method for the anodic stripping voltammetry
596 determination of Sb(III) using silver nanoparticle-modified screen-printed electrodes. *Electrochem. Commun.*, 9(4),
597 820-826. <https://doi:10.1016/j.elecom.2006.11.016>

598 [26] Zeng, S., Yong, K.-T., Roy, I., Dinh, X.-Q., Yu, X., & Luan, F. (2011). A Review on Functionalized Gold
599 Nanoparticles for Biosensing Applications. *Plasmonics*, 6(3), 491-506. <https://doi:10.1007/s11468-011-9228-1>

600 [27] Hassan, S. S., Sirajuddin, Solangi, A. R., Kazi, T. G., Kalhor, M. S., Junejo, Y., Kalwar, N. H. (2012). Nafion
601 stabilized ibuprofen-gold nanostructures modified screen printed electrode as arsenic(III) sensor. *J. Electroanal.*
602 *Chem.*, 682, 77-82. <https://doi:10.1016/j.jelechem.2012.07.006>

603 [28] Ouyang, R., Bragg, S. A., Chambers, J. Q., & Xue, Z. L. (2012). Flower-like self-assembly of gold nanoparticles
604 for highly sensitive electrochemical detection of chromium(VI). *Anal. Chim. Acta*, 722, 1-7.
605 <https://doi:10.1016/j.aca.2012.01.032>

606 [29] Dutta, S., Strack, G., & Kurup, P. (2018). Gold Nanostar Electrodes for Heavy Metal Detection. *Sensors and*
607 *Actuators B: Chemical*. <https://doi:10.1016/j.snb.2018.10.111>

608 [30] Dutta, S., Strack, G., & Kurup, P. (2019). Gold nanostar-based voltammetric sensor for chromium(VI).
609 *Microchim. Acta*, 186(11). <https://doi:10.1007/s00604-019-3847-1>

610 [31] Lu, D., Sullivan, C., Brack, E. M., Drew, C. P., & Kurup, P. (2020). Simultaneous voltammetric detection of
611 cadmium(II), arsenic(III), and selenium(IV) using gold nanostar-modified screen-printed carbon electrodes and
612 modified Britton-Robinson buffer. *Analytical and Bioanalytical Chemistry*. <https://doi:10.1007/s00216-020-02642-4>

613 [32] Yang, X., Xu, J., Tang, X., Liu, H., & Tian, D. (2010). A novel electrochemical DNAzyme sensor for the
614 amplified detection of Pb²⁺ ions. *Chem. Commun. (Camb)*, 46(18), 3107-3109. <https://doi:10.1039/c002137g>

615 [33] Pooi See, W., Nathan, S., & Yook Heng, L. (2011). A Disposable Copper (II) Ion Biosensor Based on Self-
616 Assembly of L-Cysteine on Gold Nanoparticle-Modified Screen-Printed Carbon Electrode. *Journal of Sensors*,
617 2011, 1-5. <https://doi:10.1155/2011/230535>

618 [34] Safavi, A., & Farjami, E. (2011). Construction of a carbon nanocomposite electrode based on amino acids
619 functionalized gold nanoparticles for trace electrochemical detection of mercury. *Anal. Chim. Acta*, 688(1), 43-48.
620 <https://doi:10.1016/j.aca.2010.12.001>

[35] Zhu, L., Xu, L., Huang, B., Jia, N., Tan, L., & Yao, S. (2014). Simultaneous determination of Cd(II) and Pb(II) using square wave anodic stripping voltammetry at a gold nanoparticle-graphene-cysteine composite modified bismuth film electrode. *Electrochim. Acta*, 115, 471-477. <https://doi.org/10.1016/j.electacta.2013.10.209>

[36] Xu, G., Wang, G., He, X., Zhu, Y., Chen, L., & Zhang, X. (2013). An ultrasensitive electrochemical method for detection of Ag(+) based on cyclic amplification of exonuclease III activity on cytosine-Ag(+)-cytosine. *Analyst*, 138(22), 6900-6906. <https://doi.org/10.1039/c3an01320k>

[37] Chen, Z., Li, L., Mu, X., Zhao, H., & Guo, L. (2011). Electrochemical aptasensor for detection of copper based on a reagentless signal-on architecture and amplification by gold nanoparticles. *Talanta*, 85(1), 730-735. <https://doi.org/10.1016/j.talanta.2011.04.056>

[38] Kong, R. M., Zhang, X. B., Zhang, L. L., Jin, X. Y., Huan, S. Y., Shen, G. L., & Yu, R. Q. (2009). An ultrasensitive electrochemical "turn-on" label-free biosensor for Hg²⁺ with AuNP-functionalized reporter DNA as a signal amplifier. *Chem. Commun. (Camb)*(37), 5633-5635. <https://doi.org/10.1039/b911163h>

[39] Lu, X., Dong, X., Zhang, K., & Zhang, Y. (2012). An ultrasensitive electrochemical mercury(II) ion biosensor based on a glassy carbon electrode modified with multi-walled carbon nanotubes and gold nanoparticles. *Analytical Methods*, 4(10). <https://doi.org/10.1039/c2ay25634g>

[40] Tang, X., Liu, H., Zou, B., Tian, D., & Huang, H. (2012). A fishnet electrochemical Hg²⁺ sensing strategy based on gold nanoparticle-bioconjugate and thymine-Hg(2+)-thymine coordination chemistry. *Analyst*, 137(2), 309-311. <https://doi.org/10.1039/c1an15908a>

[41] Xuan Dai, O. N., Michael E. Hyde, and Richard G. Compton. (2004). Anodic Stripping Voltammetry of Arsenic(III) Using Gold Nanoparticle-Modified Electrodes. *Anal. Chem.*, 76, 5924-5929. <https://doi.org/10.1021/ac049232x>

[42] Xiao, L., Wildgoose, G. G., & Compton, R. G. (2008). Sensitive electrochemical detection of arsenic (III) using gold nanoparticle modified carbon nanotubes via anodic stripping voltammetry. *Anal. Chim. Acta*, 620(1-2), 44-49. <https://doi.org/10.1016/j.aca.2008.05.015>

[43] Carrera, P., Espinoza-Montero, P. J., Fernández, L., Romero, H., & Alvarado, J. (2017). Electrochemical determination of arsenic in natural waters using carbon fiber ultra-microelectrodes modified with gold nanoparticles. *Talanta*, 166, 198–206. <https://doi.org/10.1016/j.talanta.2017.01.056>

[44] Raj, B. K. J. a. C. R. (2008). Gold Nanoelectrode Ensembles for the Simultaneous Electrochemical Detection of Ultratrace Arsenic, Mercury, and Copper. *Anal. Chem.*, 80, 4836–4844.

[45] Zhao, G., & Liu, G. (2018). Electrochemical Deposition of Gold Nanoparticles on Reduced Graphene Oxide by Fast Scan Cyclic Voltammetry for the Sensitive Determination of As(III). *Nanomaterials*, 9(1), 41. <https://doi.org/10.3390/nano9010041>

[46] Ehsan Majid, S. H., Yali Liu, Keith B. Male, and John H. T. Luong. (2006). Electrochemical Determination of Arsenite Using a Gold Nanoparticle Modified Glassy Carbon Electrode and Flow Analysis. *Anal. Chem*, 78, 762-769. <https://doi.org/10.1021/ac0513562>

[47] Hossain, M. M., Islam, M. M., Ferdousi, S., Okajima, T., & Ohsaka, T. (2008). Anodic Stripping Voltammetric Detection of Arsenic(III) at Gold Nanoparticle-Modified Glassy Carbon Electrodes Prepared by Electrodeposition in the Presence of Various Additives. *Electroanalysis*, 20(22), 2435-2441. <https://doi.org/10.1002/elan.200804339>

[48] Buffa, A., & Mandler, D. (2019). Arsenic(III) detection in water by flow-through carbon nanotube membrane decorated by gold nanoparticles. *Electrochimica Acta*. <https://doi.org/10.1016/j.electacta.2019.06.114>

[49] Bu, L., Liu, J., Xie, Q., & Yao, S. (2015). Anodic stripping voltammetric analysis of trace arsenic(III) enhanced by mild hydrogen-evolution at a bimetallic Au–Pt nanoparticle modified glassy carbon electrode. *Electrochemistry Communications*, 59, 28–31. <https://doi.org/10.1016/j.elecom.2015.06.015>

[50] Bu, L., Xie, Q., & Ming, H. (2020). Gold nanoparticles decorated three-dimensional porous graphitic carbon nitrides for sensitive anodic stripping voltammetric analysis of trace arsenic(III). *Journal of Alloys and Compounds*, 153723. <https://doi.org/10.1016/j.jallcom.2020.153723>

[51] Muniyandi Rajkumar, S. T., Shen-Ming Chen. (2011). Electrochemical Detection of Arsenic in Various Water Samples. *Int. J. Electrochem. Sci.*, 6, 3164 - 3177.

[52] Song, Y.-S., Muthuraman, G., Chen, Y.-Z., Lin, C.-C., & Zen, J.-M. (2006). Screen Printed Carbon Electrode Modified with Poly(L-Lactide) Stabilized Gold Nanoparticles for Sensitive As(III) Detection. *Electroanalysis*, 18(18), 1763-1770. <https://doi.org/10.1002/elan.200603634>

[53] Baron, R., Šljukić, B., Salter, C., Crossley, A., & Compton, R. G. (2007). Electrochemical detection of arsenic on a gold nanoparticle array. *Russ. J. Phys. Chem. A*, 81(9), 1443-1447. <https://doi.org/10.1134/s003602440709018x>

674 [54] Lei Zhang, Da-Wei Li, Wei Song, Lei Shi, Yang Li, & Yi-Tao Long. (2010). High Sensitive On-Site Cadmium
675 Sensor Based on AuNPs Amalgam Modified Screen-Printed Carbon Electrodes. *IEEE Sensors Journal*, 10(10),
676 1583–1588. <https://doi:10.1109/jsen.2010.2046408>

677 [55] Si, Y., Liu, J., Chen, Y., Miao, X., Ye, F., Liu, Z., & Li, J. (2018). rGO/AuNPs/tetraphenylporphyrin
678 nanoconjugate-based electrochemical sensor for highly sensitive detection of cadmium ions. *Analytical Methods*,
679 10(29), 3631-3636. <https://doi:10.1039/c8ay01020j>

680 [56] Xu, X., Duan, G., Li, Y., Liu, G., Wang, J., Zhang, H., Cai, W. (2014). Fabrication of gold nanoparticles by laser
681 ablation in liquid and their application for simultaneous electrochemical detection of Cd²⁺, Pb²⁺, Cu²⁺, Hg²⁺. *ACS*
682 *Appl. Mater. Interfaces*, 6(1), 65-71. <https://doi:10.1021/am404816e>

683 [57] Zhang, B., Chen, J., Zhu, H., Yang, T., Zou, M., Zhang, M., & Du, M. (2016). Facile and green fabrication of
684 size-controlled AuNPs/CNFs hybrids for the highly sensitive simultaneous detection of heavy metal ions.
685 *Electrochim. Acta*, 196, 422-430. <https://doi:10.1016/j.electacta.2016.02.163>

686 [58] Priya, T., Dhanalakshmi, N., Thennarasu, S., Karthikeyan, V., & Thinakaran, N. (2019). Ultra sensitive
687 electrochemical detection of Cd²⁺ and Pb²⁺ using penetrable nature of graphene/gold nanoparticles/modified L-
688 cysteine nanocomposite. *Chemical Physics Letters*, 731, 136621. <https://doi:10.1016/j.cplett.2019.136621>

689 [59] Welch, C. M., Nekrassova, O., Dai, X., Hyde, M. E., & Compton, R. G. (2004). Fabrication, characterisation
690 and voltammetric studies of gold amalgam nanoparticle modified electrodes. *ChemPhysChem*, 5(9), 1405-1410.
691 <https://doi:10.1002/cphc.200400263>

692 [60] Guodong Liu, Y.-Y. L., Hong Wu, and Yuehe Lin. (2007). Voltammetric Detection of Cr(VI) with Disposable
693 Screen-Printed Electrode Modified with Gold Nanoparticles. *Environ. Sci. Technol.*, 41, 8129–8134.
694 <https://doi:10.1021/es071726z>

695 [61] Benzhi Liu, L. L., Min Wang and Yanqin Zi. (2008). A study of nanostructured gold modified glassy carbon
696 electrode for the determination of trace Cr(VI). *J. Chem. Sci.*, 120(5), 493–498. [https://doi:10.1007/s12039-008-](https://doi:10.1007/s12039-008-0077-1)
697 [0077-1](https://doi:10.1007/s12039-008-0077-1)

698 [62] Wang, N., Lin, M., Dai, H., & Ma, H. (2016). Functionalized gold nanoparticles/reduced graphene oxide
699 nanocomposites for ultrasensitive electrochemical sensing of mercury ions based on thymine-mercury-thymine
700 structure. *Biosens. Bioelectron.*, 79, 320-326. <https://doi:10.1016/j.bios.2015.12.056>

701 [63] Zhou, N., Chen, H., Li, J., & Chen, L. (2013). Highly sensitive and selective voltammetric detection of mercury(II)
702 using an ITO electrode modified with 5-methyl-2-thiouracil, graphene oxide and gold nanoparticles. *Microchim.*
703 *Acta*, 180(5-6), 493-499. <https://doi:10.1007/s00604-013-0956-0>

704 [64] Li Shen, Z. C., Yihan Li, Shali He, Shubao Xie, Xiaodong Xu, Zhongwei Liang, Xin Meng, Qing Li, Zhiwei Zhu,
705 Meixian Li, X. Chris Le, and Yuanhua Shao. (2008). Electrochemical DNAzyme Sensor for Lead Based on
706 Amplification of DNA-Au Bio-Bar Codes. *Anal. Chem.*, 80, 6323–6328. <https://doi:10.1021/ac800601>

707 [65] Fu, X. C., Wu, J., Nie, L., Xie, C. G., Liu, J. H., & Huang, X. J. (2012). Electropolymerized surface ion imprinting
708 films on a gold nanoparticles/single-wall carbon nanotube nanohybrids modified glassy carbon electrode for
709 electrochemical detection of trace mercury(II) in water. *Anal. Chim. Acta*, 720, 29-37.
710 <https://doi:10.1016/j.aca.2011.12.071>

711 [66] Lin, Y., Peng, Y., & Di, J. (2015). Electrochemical detection of Hg(II) ions based on nanoporous gold
712 nanoparticles modified indium tin oxide electrode. *Sens. Actuators, B* 220, 1086-1090.
713 <https://doi:10.1016/j.snb.2015.06.064>

714 [67] O. Abollino; A. Giacomino; M. Malandrino; G. Piscionieri; E. Mentasti. (2007), Determination of mercury by
715 anodic stripping voltammetry at a gold nanoparticle-modified glassy carbon electrode pp. 182-182.
716 <https://doi:10.1002/elan.200704044>

717 [68] Ting, S. L., Ee, S. J., Ananthanarayanan, A., Leong, K. C., & Chen, P. (2015). Graphene quantum dots
718 functionalized gold nanoparticles for sensitive electrochemical detection of heavy metal ions. *Electrochim. Acta*,
719 172, 7-11. <https://doi:10.1016/j.electacta.2015.01.026>

720 [69] Miao, P., Liu, L., Li, Y., & Li, G. (2009). A novel electrochemical method to detect mercury (II) ions. *Electrochem.*
721 *Commun.*, 11(10), 1904-1907. <https://doi:10.1016/j.elecom.2009.08.013>

722 [70] Wan, H., Sun, Q., Li, H., Sun, F., Hu, N., & Wang, P. (2015). Screen-printed gold electrode with gold
723 nanoparticles modification for simultaneous electrochemical determination of lead and copper. *Sens. Actuators, B*,
724 209, 336-342. <https://doi:10.1016/j.snb.2014.11.127>

725 [71] Martín-Yerga, D., González-García, M. B., & Costa-García, A. (2012). Use of nanohybrid materials as
726 electrochemical transducers for mercury sensors. *Sens. Actuators, B* 165(1), 143-150.
727 <https://doi:10.1016/j.snb.2012.02.031>

728 [72] Zhu, L., Xu, L., Huang, B., Jia, N., Tan, L., & Yao, S. (2014). Simultaneous determination of Cd(II) and Pb(II)
 729 using square wave anodic stripping voltammetry at a gold nanoparticle-graphene-cysteine composite modified
 730 bismuth film electrode. *Electrochim. Acta*, 115, 471-477. <https://doi.org/10.1016/j.electacta.2013.10.209>

731 [73] Yiwei, X., Wen, Z., Xiaowei, H., Jiyong, S., Xiaobo, Z., Zhihua, L., & Xueping, C. (2019). Adsorptive stripping
 732 voltammetry determination of hexavalent chromium by a pyridine functionalized gold nanoparticles/three-
 733 dimensional graphene electrode. *Microchemical Journal*, 104022. <https://doi.org/10.1016/j.microc.2019.104022>

734 [74] Dominguez-Renedo, O., Ruiz-Espelt, L., Garcia-Astorgano, N., & Arcos-Martinez, M. J. (2008). Electrochemical
 735 determination of chromium(VI) using metallic nanoparticle-modified carbon screen-printed electrodes. *Talanta*,
 736 76(4), 854-858. <https://doi.org/10.1016/j.talanta.2008.04.036>

737 [75] Tsai, M. C., & Chen, P. Y. (2008). Voltammetric study and electrochemical detection of hexavalent chromium
 738 at gold nanoparticle-electrodeposited indium tin oxide (ITO) electrodes in acidic media. *Talanta*, 76(3), 533-539.
 739 <https://doi.org/10.1016/j.talanta.2008.03.043>

740 [76] Tu, J., Gan, Y., Liang, T., Wan, H., & Wang, P. (2018). A miniaturized electrochemical system for high sensitive
 741 determination of chromium(VI) by screen-printed carbon electrode with gold nanoparticles modification. *Sens.*
 742 *Actuators, B*, 272, 582-588. <https://doi.org/10.1016/j.snb.2018.06.006>

743 [77] Gong, J., Zhou, T., Song, D., & Zhang, L. (2010). Monodispersed Au nanoparticles decorated graphene as an
 744 enhanced sensing platform for ultrasensitive stripping voltammetric detection of mercury(II). *Sensors and Actuators*
 745 *B: Chemical*, 150(2), 491-497. <https://doi.org/10.1016/j.snb.2010.09.014>

746 [78] Bernalte, E., Marín Sánchez, C., & Pinilla Gil, E. (2012). Gold nanoparticles-modified screen-printed carbon
 747 electrodes for anodic stripping voltammetric determination of mercury in ambient water samples. *Sens. Actuators,*
 748 *B*, 161(1), 669-674. <https://doi.org/10.1016/j.snb.2011.10.088>

749 [79] Hezard, T., Fajerweg, K., Evrard, D., Collière, V., Behra, P., & Gros, P. (2012). Gold nanoparticles
 750 electrodeposited on glassy carbon using cyclic voltammetry: Application to Hg(II) trace analysis. *J. Electroanal.*
 751 *Chem.*, 664, 46-52. <https://doi.org/10.1016/j.jelechem.2011.10.014>

752 [80] Akbari Hasanjani, H. R., & Zarei, K. (2019). An electrochemical sensor for attomolar determination of
 753 mercury(II) using DNA/poly-L-methionine-gold nanoparticles/pencil graphite electrode. *Biosens. Bioelectron.*, 128,
 754 1-8. <https://doi.org/10.1016/j.bios.2018.12.039>

755 [81] Zhu, Z., Su, Y., Li, J., Li, D., Zhang, J., Song, S., Fan, C. (2009). Highly sensitive electrochemical sensor for
 756 mercury(II) ions by using a mercury-specific oligonucleotide probe and gold nanoparticle-based amplification. *Anal.*
 757 *Chem.*, 81(18), 7660-7666. <https://doi.org/10.1021/ac9010809>

758 [82] Xu, H., Zeng, L., Xing, S., Shi, G., Xian, Y., & Jin, L. (2008). Microwave-radiated synthesis of gold
 759 nanoparticles/carbon nanotubes composites and its application to voltammetric detection of trace mercury(II).
 760 *Electrochem. Commun.*, 10(12), 1839-1843. <https://doi.org/10.1016/j.elecom.2008.09.030>

761 [83] Lee, P. M., Wang, Z., Liu, X., Chen, Z., & Liu, E. (2015). Glassy carbon electrode modified by graphene-gold
 762 nanocomposite coating for detection of trace lead ions in acetate buffer solution. *Thin Solid Films*, 584, 85-89.
 763 <https://doi.org/10.1016/j.tsf.2015.03.017>

764 [84] Lu, Z., Yang, S., Yang, Q., Luo, S., Liu, C., & Tang, Y. (2013). A glassy carbon electrode modified with
 765 graphene, gold nanoparticles and chitosan for ultrasensitive determination of lead(II). *Microchim. Acta*, 180(7-8),
 766 555-562. <https://doi.org/10.1007/s00604-013-0959-x>

767 [85] Zhu, Y., Zeng, G. M., Zhang, Y., Tang, L., Chen, J., Cheng, M., Zhang, L.H., He, L., Guo, Y., He, X.X., Lai,
 768 M.Y. & He, Y. B. (2014). Highly sensitive electrochemical sensor using a MWCNTs/GNPs-modified electrode for
 769 lead (II) detection based on Pb(2+)-induced G-rich DNA conformation. *Analyst*, 139(19), 5014-5020.
 770 <https://doi.org/10.1039/c4an00874>

771 [86] Dominguez Renedo, O., & Arcos Martinez, M. J. (2007). Anodic stripping voltammetry of antimony using gold
 772 nanoparticle-modified carbon screen-printed electrodes. *Anal. Chim. Acta*, 589(2), 255-260.
 773 <https://doi.org/10.1016/j.aca.2007.02.069>

774 [87] Lee, G.-J., Kim, C. K., Lee, M. K., & Rhee, C. K. (2010). Simultaneous Voltammetric Determination of Zn, Cd
 775 and Pb at Bismuth Nanopowder Electrodes with Various Particle Size Distributions. *Electroanalysis*, 22(5), 530-
 776 535. <https://doi.org/10.1002/elan.200900356>

777 [88] Lee, G.-J., Lee, H. M., Uhm, Y. R., Lee, M. K., & Rhee, C.-K. (2008). Square-wave voltammetric determination
 778 of thallium using surface modified thick-film graphite electrode with Bi nanopowder. *Electrochem. Commun.*, 10(12),
 779 1920-1923. <https://doi.org/10.1016/j.elecom.2008.10.01>

780 [89] Rico, M. A., Olivares-Marin, M., & Gil, E. P. (2009). Modification of carbon screen-printed electrodes by
781 adsorption of chemically synthesized Bi nanoparticles for the voltammetric stripping detection of Zn(II), Cd(II) and
782 Pb(II). *Talanta*, 80(2), 631-635. <https://doi:10.1016/j.talanta.2009.07.039>

783 [90] Saturno, J., Valera, D., Carrero, H., & Fernández, L. (2011). Electroanalytical detection of Pb, Cd and traces
784 of Cr at micro/nano-structured bismuth film electrodes. *Sens. Actuators, B*, 159(1), 92-96.
785 <https://doi:10.1016/j.snb.2011.06.055>

786 [91] Sahoo, P. K., Panigrahy, B., Sahoo, S., Satpati, A. K., Li, D., & Bahadur, D. (2013). In situ synthesis and
787 properties of reduced graphene oxide/Bi nanocomposites: as an electroactive material for analysis of heavy metals.
788 *Biosens. Bioelectron.*, 43, 293-296. <https://doi:10.1016/j.bios.2012.12.031>

789 [92] Campbell, F. W., & Compton, R. G. (2009). The use of nanoparticles in electroanalysis: an updated review.
790 *Analytical and Bioanalytical Chemistry*, 396(1), 241–259. <https://doi:10.1007/s00216-009-3063-7>

791 [93] Sabahudin Hrapovic, Y. L., and John H. T. Luong. (2007). Reusable Platinum Nanoparticle Modified Boron
792 Doped Diamond Microelectrodes for Oxidative Determination of Arsenite. *Anal. Chem.*, 79, 500-507.
793 <https://doi:10.1021/ac061528a>

794 [94] Dai, X., & Compton, R. G. (2006). Detection of As(III) via oxidation to As(V) using platinum nanoparticle modified
795 glassy carbon electrodes: arsenic detection without interference from copper. *Analyst*, 131(4), 516-521.
796 <https://doi:10.1039/b513686e>

797 [95] Zhang, T., Jin, H., Fang, Y., Guan, J., Ma, S., Pan, Y., Zhang, M., Zhu, H., Liu, X. & Du, M. (2019). Detection
798 of trace Cd²⁺, Pb²⁺ and Cu²⁺ ions via porous activated carbon supported palladium nanoparticles modified
799 electrodes using SWASV. *Mater. Chem. Phys.*, 225, 433-442. <https://doi:10.1016/j.matchemphys.2019.01.010>

800 [96] Veerakumar, P., Veeramani, V., Chen, S.-M., Madhu, R., & Liu, S.-B. (2016). Palladium Nanoparticle
801 Incorporated Porous Activated Carbon: Electrochemical Detection of Toxic Metal Ions. *ACS Applied Materials &*
802 *Interfaces*, 8(2), 1319–1326. <https://doi:10.1021/acsami.5b10050>

803 [97] Lee, P. M., Chen, Z., Li, L., & Liu, E. (2015). Reduced graphene oxide decorated with tin nanoparticles through
804 electrodeposition for simultaneous determination of trace heavy metals. *Electrochim. Acta*, 174, 207-214.
805 <https://doi:10.1016/j.electacta.2015.05.092>

806 [98] Toghill, K. E., Xiao, L., Wildgoose, G. G., & Compton, R. G. (2009). Electroanalytical Determination of
807 Cadmium(II) and Lead(II) Using an Antimony Nanoparticle Modified Boron-Doped Diamond Electrode.
808 *Electroanalysis*, 21(10), 1113-1118. <https://doi:10.1002/elan.200904547>

809 [99] George, J. M., Antony, A., & Mathew, B. (2018). Metal oxide nanoparticles in electrochemical sensing and
810 biosensing: a review. *Mikrochim Acta*, 185(7), 358. <https://doi:10.1007/s00604-018-2894-3>

811 [100] Lee, S., Oh, J., Kim, D., & Piao, Y. (2016). A sensitive electrochemical sensor using an iron oxide/graphene
812 composite for the simultaneous detection of heavy metal ions. *Talanta*, 160, 528-536.
813 <https://doi:10.1016/j.talanta.2016.07.03>

814 [101] Li, S.-S., Zhou, W.-Y., Jiang, M., Li, L.-N., Sun, Y.-F., Guo, Z., Liu, J.-H. & Huang, X.-J. (2018). Insights into
815 diverse performance for the electroanalysis of Pb(II) on Fe₂O₃ nanorods and hollow nanocubes: Toward analysis
816 of adsorption sites. *Electrochimica Acta*. <https://doi:10.1016/j.electacta.2018.08.069>

817 [102] Deshmukh, S., Kandasamy, G., Upadhyay, R. K., Bhattacharya, G., Banerjee, D., Maity, D., Roy, S. S. (2017).
818 Terephthalic acid capped iron oxide nanoparticles for sensitive electrochemical detection of heavy metal ions in
819 water. *J. Electroanal. Chem.*, 788, 91-98. <https://doi:10.1016/j.jelechem.2017.01.064>

820 [103] Sun, Y., Zhang, W., Yu, H., Hou, C., Li, D., Zhang, Y., & Liu, Y. (2015). Controlled synthesis various shapes
821 Fe₃O₄ decorated reduced graphene oxide applied in the electrochemical detection. *Journal of Alloys and*
822 *Compounds*, 638, 182–187. <https://doi:10.1016/j.jallcom.2015.03.061>

823 [104] Yantasee, W., Hongsirakarn, K., Warner, C. L., Choi, D., Sangvanich, T., Toloczko, M. B., Timchalk, C. (2008).
824 Direct detection of Pb in urine and Cd, Pb, Cu, and Ag in natural waters using electrochemical sensors immobilized
825 with DMSA functionalized magnetic nanoparticles. *Analyst*, 133(3), 348-355. <https://doi:10.1039/b711199a>

826 [105] Miao, P., Tang, Y., & Wang, L. (2017). DNA Modified Fe₃O₄@Au Magnetic Nanoparticles as Selective Probes
827 for Simultaneous Detection of Heavy Metal Ions. *ACS Appl. Mater. Interfaces*, 9(4), 3940-3947.
828 <https://doi:10.1021/acsami.6b14247>

829 [106] Cui, H., Yang, W., Li, X., Zhao, H., & Yuan, Z. (2012). An electrochemical sensor based on a magnetic Fe₃O₄
830 nanoparticles and gold nanoparticles modified electrode for sensitive determination of trace amounts of arsenic(iii).
831 *Analytical Methods*, 4(12). <https://doi:10.1039/c2ay25913c>

832 [107] Xiong, S., Wang, M., Cai, D., Li, Y., Gu, N., & Wu, Z. (2013). Electrochemical Detection of Pb(II) by Glassy
833 Carbon Electrode Modified with Amine-Functionalized Magnetite Nanoparticles. *Anal. Lett.*, 46(6), 912-922.
834 <https://doi:10.1080/00032719.2012.747094>

835 [108] Song, Q., Li, M., Huang, L., Wu, Q., Zhou, Y., & Wang, Y. (2013). Bifunctional polydopamine@Fe₃O₄ core-
836 shell nanoparticles for electrochemical determination of lead(II) and cadmium(II). *Anal. Chim. Acta*, 787, 64-70.
837 <https://doi:10.1016/j.aca.2013.06.010>

838 [109] Sun, Y.-F., Chen, W.-K., Li, W.-J., Jiang, T.-J., Liu, J.-H., & Liu, Z.-G. (2014). Selective detection toward Cd²⁺
839 using Fe₃O₄/RGO nanoparticle modified glassy carbon electrode. *J. Electroanal. Chem.*, 714-715, 97-102.
840 <https://doi:10.1016/j.jelechem.2013.12.030>

841 [110] Fan, H.-L., Zhou, S.-F., Gao, J., & Liu, Y.-Z. (2016). Continuous preparation of Fe₃O₄ nanoparticles through
842 Impinging Stream-Rotating Packed Bed reactor and their electrochemistry detection toward heavy metal ions. *J.*
843 *Alloys Compd.*, 671, 354-359. <https://doi:10.1016/j.jallcom.2016.02.062>

844 [111] Zhou, S.-F., Han, X.-J., & Liu, Y.-Q. (2016). SWASV performance toward heavy metal ions based on a high-
845 activity and simple magnetic chitosan sensing nanomaterials. *J. Alloys Compd.*, 684, 1-7.
846 <https://doi:10.1016/j.jallcom.2016.05.152>

847 [112] Baghayeri, M., Amiri, A., Maleki, B., Alizadeh, Z., & Reiser, O. (2018). A simple approach for simultaneous
848 detection of cadmium(II) and lead(II) based on glutathione coated magnetic nanoparticles as a highly selective
849 electrochemical probe. *Sens. Actuators, B* 273, 1442-1450. <https://doi:10.1016/j.snb.2018.07.063>

850 [113] Rasha A. Ahmed, A. M. F. (2013). Preparation and Characterization of a Nanoparticles Modified Chitosan
851 Sensor and Its Application for the Determination of Heavy Metals from Different Aqueous Media. *Int. J. Electrochem.*
852 *Sci.*, 8, 6692 - 6708.

853 [114] Filik, H., & Avan, A. A. (2019). Dextran modified magnetic nanoparticles based solid phase extraction coupled
854 with linear sweep voltammetry for the speciation of Cr(VI) and Cr(III) in tea, coffee, and mineral water samples.
855 *Food Chemistry*, 292, 151–159. <https://doi:10.1016/j.foodchem.2019.04.058>

856 [115] Yang, H., Liu, X., Fei, R., & Hu, Y. (2013). Sensitive and selective detection of Ag⁺ in aqueous solutions using
857 Fe₃O₄@Au nanoparticles as smart electrochemical nanosensors. *Talanta*, 116, 548-553.
858 <https://doi:10.1016/j.talanta.2013.07.041>

859 [116] Dedelaite, L., Kizilkaya, S., Incebay, H., Ciftci, H., Ersoz, M., Yazicigil, Z., Ramanavicius, A. (2015).
860 Electrochemical determination of Cu(II) ions using glassy carbon electrode modified by some nanomaterials and 3-
861 nitroaniline. *Colloids Surf., A*, 483, 279-284. <https://doi:10.1016/j.colsurfa.2015.05.054>

862 [117] Afkhami, A., Moosavi, R., Madrakian, T., Keypour, H., Ramezani-Aktij, A., & Mirzaei-Monsef, M. (2014).
863 Construction and Application of an Electrochemical Sensor for Simultaneous Determination of Cd(II), Cu(II) and
864 Hg(II) in Water and Foodstuff Samples. *Electroanalysis*, 26(4), 786-795. <https://doi:10.1002/elan.201300619>

865 [118] Zhou, S.-F., Han, X.-J., Fan, H.-L., Zhang, Q.-X., & Liu, Y.-Q. (2015). Electrochemical detection of As(III)
866 through mesoporous MnFe₂O₄ nanocrystal clusters by square wave stripping voltammetry. *Electrochim. Acta*, 174,
867 1160-1166. <https://doi:10.1016/j.electacta.2015.06.036>

868 [119] Zhou, S., Han, X., Fan, H., & Liu, Y. (2016). Electrochemical Sensing toward Trace As(III) Based on
869 Mesoporous MnFe₂O₄/Au Hybrid Nanospheres Modified Glass Carbon Electrode. *Sensors (Basel)*, 16(6).
870 <https://doi:10.3390/s16060935>

871 [120] Han, X.-J., Zhou, S.-F., Fan, H.-L., Zhang, Q.-X., & Liu, Y.-Q. (2015). Mesoporous MnFe₂O₄ nanocrystal
872 clusters for electrochemistry detection of lead by stripping voltammetry. *Journal of Electroanalytical Chemistry*, 755,
873 203–209. <https://doi:10.1016/j.jelechem.2015.07.054>

874 [121] Zhou, S.-F., Han, X.-J., Fan, H.-L., Huang, J., & Liu, Y.-Q. (2018). Enhanced electrochemical performance for
875 sensing Pb(II) based on graphene oxide incorporated mesoporous MnFe₂O₄ nanocomposites. *J. Alloys Compd.*,
876 747, 447-454. <https://doi:10.1016/j.jallcom.2018.03.037>

877 [122] Zhou, S.-F., Wang, J.-J., Gan, L., Han, X.-J., Fan, H.-L., Mei, L.-Y., Liu, Y.-Q. (2017). Individual and
878 simultaneous electrochemical detection toward heavy metal ions based on L-cysteine modified mesoporous
879 MnFe₂O₄ nanocrystal clusters. *J. Alloys Compd.*, 721, 492-500. <https://doi:10.1016/j.jallcom.2017.05.321>

880 [123] Salimi, A., Mamkhezri, H., Hallaj, R., & Soltanian, S. (2008). Electrochemical detection of trace amount of
881 arsenic(III) at glassy carbon electrode modified with cobalt oxide nanoparticles. *Sens. Actuators, B*, 129(1), 246-
882 254. <https://doi:10.1016/j.snb.2007.08.017>

883 [124] Zhou, L., Xiong, W., & Liu, S. (2014). Preparation of a gold electrode modified with Au–TiO₂ nanoparticles as
884 an electrochemical sensor for the detection of mercury(II) ions. *J. Mater. Sci.* 50(2), 769-776.
885 <https://doi:10.1007/s10853-014-8636-y>

- [125] Zhang, X., Zeng, T., Hu, C., Hu, S., & Qiulin Tian, Q. (2016). Studies on fabrication and application of arsenic electrochemical sensors based on titanium dioxide nanoparticle modified gold strip electrodes. *Analytical Methods*, 8(5), 1162-1169. <https://doi:10.1039/c5ay02397a>
- [126] Mao, A., Li, H., Cai, Z., & Hu, X. (2015). Determination of mercury using a glassy carbon electrode modified with nano TiO₂ and multi-walled carbon nanotubes composites dispersed in a novel cationic surfactant. *Journal of Electroanalytical Chemistry*, 751, 23–29. <https://doi:10.1016/j.jelechem.2015.04.034>
- [127] Ramezani, S., Ghobadi, M., & Bideh, B. N. (2014). Voltammetric monitoring of Cd (II) by nano-TiO₂ modified carbon paste electrode sensitized using 1,2-bis-[o-aminophenyl thio] ethane as a new ion receptor. *Sensors and Actuators B: Chemical*, 192, 648–657. <https://doi:10.1016/j.snb.2013.11.033>
- [128] Liu, F., Zhang, Y., Yin, W., Hou, C., Huo, D., He, B., Qian, L. & Fa, H. (2017). A high-selectivity electrochemical sensor for ultra-trace lead (II) detection based on a nanocomposite consisting of nitrogen-doped graphene/gold nanoparticles functionalized with ETBD and Fe₃O₄@TiO₂ core-shell nanoparticles. *Sensors and Actuators B: Chemical*, 242, 889–896. <https://doi:10.1016/j.snb.2016.09.167>
- [129] Zhang, Q.-X., Wen, H., Peng, D., Fu, Q., & Huang, X.-J. (2015). Interesting interference evidences of electrochemical detection of Zn(II), Cd(II) and Pb(II) on three different morphologies of MnO₂ nanocrystals. *J. Electroanal. Chem.*, 739, 89-96. <https://doi:10.1016/j.jelechem.2014.12.023>
- [130] Fayazi, M., Taher, M. A., Afzali, D., & Mostafavi, A. (2016). Fe₃O₄ and MnO₂ assembled on halloysite nanotubes: A highly efficient solid-phase extractant for electrochemical detection of mercury(II) ions. *Sensors and Actuators B: Chemical*, 228, 1–9. <https://doi:10.1016/j.snb.2015.12.107>
- [131] Salimi, A., Pourbahram, B., Mansouri-Majd, S., & Hallaj, R. (2015). Manganese oxide nanoflakes/multi-walled carbon nanotubes/chitosan nanocomposite modified glassy carbon electrode as a novel electrochemical sensor for chromium (III) detection. *Electrochimica Acta*, 156, 207–215. <https://doi:10.1016/j.electacta.2014.12.146>
- [132] Wei, Y., Gao, C., Meng, F.-L., Li, H.-H., Wang, L., Liu, J.-H., & Huang, X.-J. (2011). SnO₂/Reduced Graphene Oxide Nanocomposite for the Simultaneous Electrochemical Detection of Cadmium(II), Lead(II), Copper(II), and Mercury(II): An Interesting Favorable Mutual Interference. *The Journal of Physical Chemistry C*, 116(1), 1034–1041. <https://doi:10.1021/jp209805c>
- [133] Yang, M., Jiang, T.-J., Guo, Z., Liu, J.-H., Sun, Y.-F., Chen, X., & Huang, X.-J. (2017). Sensitivity and selectivity sensing cadmium(II) using amination functionalized porous SnO₂ nanowire bundles-room temperature ionic liquid nanocomposite: Combined efficient cation capture with control experimental conditions. *Sensors and Actuators B: Chemical*, 240, 887–894. <https://doi:10.1016/j.snb.2016.09.060>
- [134] Cui, X., Fang, X., Zhao, H., Li, Z., & Ren, H. (2018). Fabrication of thiazole derivatives functionalized graphene decorated with fluorine, chlorine and iodine@SnO₂ nanoparticles for highly sensitive detection of heavy metal ions. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*, 546, 153–162. <https://doi:10.1016/j.colsurfa.2018.03.004>
- [135] Li, Y., Liu, X. R., Ning, X. H., Huang, C. C., Zheng, J. B., & Zhang, J. C. (2011). An ionic liquid supported CeO₂ nanoparticles-carbon nanotubes composite-enhanced electrochemical DNA-based sensor for the detection of Pb(2). *J. Pharm. Anal.*, 1(4), 258-263. <https://doi:10.1016/j.jpha.2011.09.001>
- [136] Yukird, J., Kongsittikul, P., Qin, J., Chailapakul, O., Rodthongkum, N. (2018) ZnO@graphene nanocomposite modified electrode for sensitive and simultaneous detection of Cd (II) and Pb (II). *Synth. Met.* 245, 251–259. <https://doi.org/10.1016/j.synthmet.2018.09.012>
- [137] Yuan-Yuan, L., Meng-Ni, C., Yi-Li, G., Jian-Mao, Y., Xiao-Yu, M.A., Jian-Yun, L. (2015) Preparation of zinc oxide-graphene composite modified electrodes for detection of trace Pb(II). *Chinese J. Anal. Chem.* 43, 1395–1401. [https://doi.org/10.1016/s1872-2040\(15\)60862-3](https://doi.org/10.1016/s1872-2040(15)60862-3)
- [138] Wei, Y., Yang, R., Yu, X.-Y., Wang, L., Liu, J.-H., & Huang, X.-J. (2012). Stripping voltammetry study of ultra-trace toxic metal ions on highly selectively adsorptive porous magnesium oxide nanoflowers. *The Analyst*, 137(9), 2183. <https://doi:10.1039/c2an15939b>