Layer-by-layer functionalization of gold nanorods by polyelectrolytes to control surface spacer and precisely tune the surface plasmon resonance position

Céline Jégat, Guillaume Laurent

► To cite this version:

Céline Jégat, Guillaume Laurent. Layer-by-layer functionalization of gold nanorods by polyelectrolytes to control surface spacer and precisely tune the surface plasmon resonance position. *Chemistry Letters*, 2020, 10.1246/cl.200687 . hal-03065980

HAL Id: hal-03065980

<https://hal.science/hal-03065980>

Submitted on 23 Nov 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Layer-by-layer functionalization of gold nanorods by polyelectrolytes to control surface spacer and precisely tune the surface plasmon resonance position

Céline Jégat and Guillaume Laurent*

Université Paris-Saclay, ENS Paris-Saclay, CNRS, PPSM, 91190 Gif-sur-Yvette, France

E-mail: guillaume.laurent@ens-cachan.fr

We present a layer-by-layer functionalization of gold nanorods (GNRs) by polyelectrolytes in order to control precisely the spacer surrounding the metallic nanoparticles but also to modulate its plasmonic properties. Alternate functionalization with negatively and positively charged polyelectrolytes ensures a 2 nm step control of the spacer from 0 nm up to 10 nm, depending on the number of layers. Such process changes the local refractive index and thus induces a red shift of the surface plasmon resonance. Both solution and solid samples were studied.

Keywords: gold nanoparticles functionalization, polyelectrolytes layers, spacer thickness control, plasmonic properties modulation

The enhancement of the metallic nanoparticles synthesis protocols impacts since many years the field of materials science.¹⁻³ In fact, controlling precisely the size, shape and the core metal gives access to specific plasmonic properties. Numerous studies describe them and their various applications in designing new meta-materials, sensing and biomedicine⁴⁻⁸ each underlying that the control of the direct environment of the metallic nanoparticle is mandatory whatever we consider inter-particles coupling or targeted organic compound functionalized on the metallic nanoparticles.⁹ Different methods experienced the change of their initial surfactant coating by other appropriate spacer. Two of the most commonly used are the DNA linker¹⁰ and the silica shell coating.¹¹ The first one shows the advantage of having a precise length for the linker and allows designing either hybrid organic / metallic system or dimer nanoparticles. Despite it is quite easy to use; DNA linker is still expensive and does not allow a good surface coverage in case of organic functionalization. Moreover, the stability of the hybrid system is not optimized. On the other hand, silica shell surrounding metallic nanoparticles increases the stability of the system and exhibits a potentially high surface coverage with further functionalization with organic compound using click chemistry. However, it is hard to control the shell thickness for value below 10 nm; which is a huge drawback because the value of the enhanced electromagnetic field for plasmonic nanoparticles decreases as the inverse of the cube distance from the surface, enforcing a spacer thickness smaller than 10 nm.¹²

Considering the different drawbacks of the previous spacers, using polyelectrolytes could represent a new way in the functionalization of metallic nanoparticles. In fact, as polyelectrolytes are organic polymers where the initial monomer is positively or negatively charged, specific electrostatic interactions afford an easy control of the spacer thickness and at the same time increase the colloidal stability of the system.¹³⁻¹⁶ Moreover, controlling the direct

environment of the metallic nanoparticles means controlling the local refractive index and thus enables the modulation of the localized surface plasmon resonance (LSPR).¹⁷⁻¹⁹

In this paper, negative and positive polyelectrolytes are sequentially used to functionalize GNRs. Using such layer-by-layer process ensures a perfect control of the spacer surrounding the metallic nanoparticles, an increase of its colloidal stability and a higher density when deposited on glass substrate. Zetametry measurements are performed to characterize the layer-by-layer deposition and the evolution of the colloidal stability over the process. Extinction spectroscopy is used to show the spectral shift observed over the LSPR bands during the layer-by-layer process.

Gold nanorods with specific aspect ratio were prepared by a modified “seed mediated growth method” using binary surfactant mixtures.²⁰ In this synthesis procedure, sodium oleate (NaOL) is combined with CTAB and thus achieves a greater tunability of GNRs dimensions. This anionic surfactant has a double bond that allows the reduction of the gold salt in the absence of other reducers, in this case ascorbic acid (AA), so a lower molar ratio of gold:AA is used compared to the original method. The mixture of CTAB and NaOL also enables the use of lower concentration of surfactant in the reaction.¹⁵

The reaction has two steps. First, a small quantity of gold salt is reduced using sodium borohydride as a strong reducing agent in order to create small gold nanospheres called “seeds”, which will be used as cores of the gold nanorods. Secondly, a growth solution provides the gold salt and the other reactants for the growth of these seeds with the desired size and shape. These reactions are prepared as follows.

Seed Solution: 5 mL of 0.5 mM HAuCl₄ is mixed with 5 mL of 0.2 M CTAB solution in a beaker. 0.6 mL of fresh NaBH₄ is diluted to 1 mL with water and then injected to the Au(III)-CTAB solution under vigorous stirring. The solution color changes from yellow to brownish yellow and the stirring is stopped after 2 min. The seed solution is aged at room temperature for (at least) 30 min before use.

Growth solution: 3.5 g of CTAB and 0.617 g of NaOL are dissolved in 125 mL of water in a 0.5 L Erlenmeyer flask. 12 mL of AgNO₃ solution (4 mM) is added. The mixture is kept undisturbed at 30°C for 15 min after which 125 mL of 1 mM HAuCl₄ solution is added. The solution becomes colorless after 90 min of stirring (700 rpm) and 2 mL of HCl (37 wt. % in water, 12.1 M) is then introduced to adjust the pH. After another 15 min of slow stirring (400 rpm), 0.625 mL of 0.064 M AA is added and the solution is vigorously stirred for 30 s. Finally, 0.2 mL of the seed solution is injected into the growth solution. The resultant

1 mixture is stirred for 30 s and left undisturbed at 30°C for
2 12-15 h for GNRs growth.

3 The synthesized GNRs were characterized using
4 extinction spectroscopy and scanning electron microscopy
5 (SEM) (Figure 1). They show two different LSPR bands:
6 the transversal one is located at 525 nm and the longitudinal
7 one at 881 nm. The spectrum is related to the original
8 synthesized solution, within the GNRs are surrounded by a
9 double layer of surfactant (mainly CTAB) and the solvent
10 which contains an excess of surfactant. The size distribution
11 of the GNRs was measured thanks to the SEM images over
12 one thousand nanoparticles. The average values are 97 nm
13 for the long axis and 21 nm for the short one, which gives
14 an aspect ratio around 4.6.

15 In order to use gold nanoparticles for enhanced
16 spectroscopies, the control of the distance between the
17 metallic surface and the molecules under interest is
18 mandatory. To achieve this goal, polyelectrolytes are under
19 great interest due to the layer-by-layer process which
20 ensures a precise control of the functionalization. Before
21 deposition of the polyelectrolytes, surfactants surrounding
22 the GNRs (CTAB and NaOL) need to be removed. So 10

Figure 1. a) Extinction spectrum of synthesized gold nanorods. Insert shows the size distribution measured on 1034 nanoparticles; b) SEM image of the corresponding gold nanorods. Scale bar represents 100 nm.

23 mL of GNRs solution are centrifugated at 6 000 rpm during
24 20 min (relative centrifugal force RCF = 3 461 g) and then
25 the pellet is dispersed in 10 mL of milliQ water. This cycle
26 is done two more times.

27 Assuming that naked GNRs are slightly positively
28 charged, the first layer needs to be a negatively charged
29 polyelectrolyte; we choose sodium polystyrene sulfonate
30 (PSS, M = 70 000 g/mol), purchased from Sigma-Aldrich
31 and used without further purification. So 10 mL of naked
32 GNRs solution is mixed with 3 mL of PSS solution (10
33 mg/mL in water) under 2 min of gentle stirring. The mixed
34 solution is kept undisturbed for 45 min to allow the
35 electrostatic interactions between the GNRs and the
36 polyelectrolytes thanks to the natural Brownian motion. To
37 remove the excess of polyelectrolytes, centrifugation is
38 performed at 12 000 rpm during 10 min (RCF = 15 455 g)
39 and the pellet is dispersed in 10 mL of NaCl solution (0.5
40 mM) to prevent the flocculation of the hybrid nanoparticles
41 (gold nanorods with one layer, GNRs-1L). **The addition of
42 NaCl increases the ionic strength of the solution which
43 stabilizes the polyelectrolyte layer in water. Without NaCl,
44 the functionalized GNRs precipitate within few hours.**

45 To set the second polyelectrolyte layer, we choose the
46 poly(diallyldimethylammonium chloride) (PDADMAC, M
47 < 100 000 g/mol) which is positively charged. The same
48 process is used for the second layer. Briefly, 10 mL of
49 GNRs-1L are mixed with 3 mL of PDADMAC solution
50 (purchased from Sigma-Aldrich and used without further
51 purification or dilution). After 2 min of gentle stirring and
52 45 min at rest, the same centrifugation parameters are used.
53 The final pellet is dispersed in 10 mL of NaCl solution. The
54 use of NaCl solution instead of milliQ water is very
55 important to prevent the flocculation of the gold nanorods
56 with two layers of polyelectrolytes (GNRs-2L).

57 We can continue the layer-by-layer process deposition
58 by alternating between PSS and PDADMAC
59 polyelectrolytes, depending on the main charged surface of
60 the hybrids. Because the centrifugation step is more and
61 more critical as the number of layer increases, the rotation
62 speed (or even the RCF) needs to be adjusted in

Figure 2. Evolution of the zeta potential of hybrid nanoparticles, starting from naked GNRs (0 layer) to three layers of polyelectrolytes.

consequence to prevent full aggregation of the pellet (which makes it very difficult to disperse in NaCl solution). Furthermore, the molecular weight of the different polyelectrolytes were chosen depending on the size (and aspect ratio) of the gold nanorods. If their size increases, longer polyelectrolyte chains are needed.

During the layer-by-layer process, each step was controlled by zetametry. Measuring the GNRs zeta potential, formerly the electrokinetic potential, is an easy way to check if each layer is correctly deposited and at the same time to measure the stability of the hybrid system. Figure 2 shows the variation of the zeta potential when the GNRs are functionalized with up to three layers of polyelectrolytes. First of all, we clearly see the sign alternation of the zeta potential as long as we increase the number of layers. It is positive for the naked GNRs, then negative for the first layer of PSS, positive again for the second layer of PDADMAC and then negative again for the third layer of PSS which is in accordance with the main charge of the last polyelectrolyte deposited. Secondly, as the number of layer increases, the absolute value of the zeta potential increases also, indicating that the stability behavior of the hybrid nanoparticles in solution is more efficient. It starts from 20 mV for naked GNRs to increase to 60 mV for a three layers system. Considering that each polyelectrolyte layer thickness is around 2 nm,²¹ this layer-by-layer process allows to perfectly controlling the spacer between the surface of the metallic nanoparticle and the future studied organic compound to perform efficient enhanced spectroscopies. This layer-by-layer process is also a good way to prevent aggregation of the gold nanoparticles in solution.

Addition of polyelectrolytes layers around GNRs would also affect their optical plasmonic properties. In fact, LSPR bands are very sensitive to their direct environment, meaning the local refractive index in solution. Thus, putting more layers of polyelectrolytes surrounding the GNRs would change the average value of the refractive index,

Figure 3. Extinction spectra of functionalized GNRs from 1 to 4 layers of polyelectrolytes. S0 is referred to the synthesized GNRs. Insert shows the evolution of the observed spectral shift with the estimated refractive index.

inducing LSPR bands spectral shifts. Figure 3 shows the evolution of the extinction spectra of the GNRs as long as we do the layer-by-layer process. We mainly observe a spectral red-shift of the LSPR bands which is small in the case of the transverse one but very important (up to 80 nm) for the longitudinal one. The way we estimate the average value of the local refractive index is based on the assumption that the surface plasmon effect is mainly efficient in the first 10 nm closed to the surface of the metallic nanoparticles.^{12, 22} Surfactants or polyelectrolytes layers are localized within this small area and need to be taken into account, in addition to the solvent, to estimate the relative value of the refractive index directly surrounding the GNRs. The complete calculation assumptions are described in the supporting information but simply the equation used is:

$$RI = 1,33 \times \frac{V_{tot} - \sum_i V_{layer}}{V_{tot}} + \sum_i RI_{layer} \times \frac{V_{layer}}{V_{tot}} \quad (1)$$

where **RI** is the refractive index (1.33 is the value of the water solvent), V_{tot} the total volume considered, V_{layer} the volume of a considered layer and i the number of layers. Considering equation 1, we clearly observe a linear dependence between the optical shift of the LSPR bands and the value of the refractive index (insert of Figure 3). This allows at the same time a precise control of the layer-by-layer deposition process by spectroscopic measurements but also a fine modulation tuning of the LSPR bands. So a quick and simple prediction can be done on the modulation of the LSPR bands' position when considering further layers of polyelectrolytes. Therefore, using polyelectrolytes is an efficient way to both functionalize metallic nanoparticles and tune the LSPR bands position, which could be mandatory for enhanced spectroscopies when a good spectral overlap with other absorption band is needed.

Figure 4. Left: AFM imaging of deposited GNRs-1L. Right: corresponding gap measurements between 2 GNRs-1L.

To go further than these results obtained in solution we considered solid substrates to see how polyelectrolytes can be used to ensure space between GNRs. So we prepared GNRs-1L and deposited a diluted solution by the droplet method on a silicon wafer to perform atomic force microscopy (AFM). Keep in mind that a single PSS layer is 2 nm thickness. Figure 4 shows the distance measurement between side-by-side and head-to-head dimers. The average gap value between two GNRs is 8 nm which clearly indicates that the PSS layer induces repulsive forces between the nanoparticles. It means that polyelectrolytes functionalization prevents the aggregation in solution but also modulates the gap between deposited nanoparticles which is very important when dealing with inter-nanoparticles' coupling. AFM measurement with more than one layer was not possible due to the quantity of polymer surrounding the GNRs which pollutes the AFM tip and makes imaging complicated. Looking at the study of Möhwald and co-workers²¹, a single layer of polyelectrolyte is 2 nm thick, two layers are 4 nm thick and three layers are 6 nm thick. Considering these layers thickness and the repulsive forces, we can estimate the distance between two GNRs-2L and two GNRs-3L to be over 8 and 12 nm respectively, when deposited on substrate.

To go further, multi-layered GNRs were deposited on glass substrates to allow absorption measurements on solid sample. Prior to the deposition, the glass slide was washed using first ethanol and secondly oxygen plasma cleaner. Then we deposit 50 μ L of high concentrated solution of layered GNRs by the droplet method and we waited until the complete solvent evaporation. Figure 5 shows the absorption spectra obtained on different glass slides where GNRs from zero layer to four layers of polyelectrolytes were deposited. There are two main observations. First of all, we observed the same behavior as the solution samples. The longitudinal LSPR band is optically red-shifted as long as we increase the number of polyelectrolytes layers surrounding the GNRs, meaning as long as the local refractive index increases. In contrast with the solution

Figure 5. Extinction spectra of functionalized GNRs deposited on glass slides. Number of polyelectrolytes goes from 0 to 4 layers.

samples, it is rather difficult to estimate the value of the local refractive index on deposited sample. In fact, in solution you can consider each GNR individually so only the solvent and the layers have to be considered. When deposited on glass substrate, the direct environment of each GNR is composed of air, glass and other GNRs. So estimating an average value of the local refractive index cannot be efficiently achieved. The second observation is the broadening of both transverse and longitudinal LSPR bands for samples with higher number of layers. This observation is explained by the high density of GNRs that are deposited on the glass substrate. To characterize the GNRs' packing, SEM imaging was performed on GNRs-1L deposited on silicon wafer. Due to vacuum and electron gun source condition, an extra step of oxygen plasma cleaner was done to remove organic compounds like polyelectrolytes and possible rest of surfactant. The main advantage of this extra step is to increase the SEM imaging resolution. But the drawback is that destroying the polyelectrolyte layers changes the distance between the GNRs, especially for high number of layers or when GNRs are closely packed. That is why SEM measurements are only used to characterize the close packing and not the inter-particle distances. SEM imaging, in supporting information, clearly show wide areas of high density packing of GNRs. Regarding absorption spectroscopy, these closed packed nanorods induce the broadening of the LSPR bands but also a specific band that appears around 660 nm, due to transverse coupling between GNRs allowed by the short inter-particles distance.²³ Thus increasing the number of polyelectrolytes layers allows to tune the LSPR bands position but also to modulate the inter-particles coupling by controlling the distance between GNRs.

In conclusion, control of the distance between metallic nanoparticles and targeted organic dye is mandatory for enhanced spectroscopies. Different spacers can be used like silica shell or DNA but polyelectrolytes show many advantages. First of all, as it is a layer-by-layer process, you can control precisely the thickness of the spacer with a 2 nm single layer precision and also increase the colloidal stability of the functionalized gold nanoparticles. Then, as any modification of the GNRs' surface, putting some electrolytes modulates the position of the LSPR bands, but its linear dependence makes it easily predictable. Finally, for surface deposition, functionalized GNRs can grant access to selection of the gap between nanoparticles which govern the strength of inter-particles coupling and thus, the local field enhancement. To summarize, polyelectrolytes offer new possibilities in term of spacer control and further metallic nanoparticle's functionalization, especially with charged organic compounds.

Co-authors would like to thank François Brisset from ICMO laboratory, Université Paris-Saclay, France for the scanning electronic microscopy measurements.

Supporting Information is available on http://dx.doi.org/10.1246/cl.*****

1 References and Notes

- 2 1 W. L. Barnes, A. Dereux, T. W. Ebbesen, *Nature* **2003**, *424*, 824.
- 3 2 J. Pérez-Juste, I. Pastoriza-Santos, L. M. Liz-Marzan, P.
- 4 Mulvaney, *Coordination Chemistry Reviews* **2005**, *249*, 1870.
- 5 3 C. Louis and O. Pluchery, in *Gold nanoparticles for physics,*
- 6 *chemistry and biology*, ed. by Imperial College Press, **2012**.
- 7 4 M. Salbini, T. Stomeo, C. Ciraci, R. Fiammengo, V. Mangini, A.
- 8 Toma, F. Pisano, F. Pisanello, T. Verri, D. R. Smith, M. DE
- 9 Vittorio, *Optical Materials Express* **2020**, *10*, 1264.
- 10 5 X. Fu, L. Chen, J. Li, M. Lin, H. You, W. Wang, *Biosensors &*
- 11 *Bioelectronics* **2012**, *34*, 227.
- 12 6 Z. Zhang, Z. Chen, F. Cheng, Y. Zhang, L. Chen, *Biosensors &*
- 13 *Bioelectronics* **2017**, *89*, 932.
- 14 7 Z. Zhang, Z. Chen, S. Wang, F. Cheng, L. Chen, *ACS Applied*
- 15 *Materials & Interfaces* **2015**, *7*, 27639.
- 16 8 Z. Zhang, Z. Chen, C. Qu, L. Chen, *Langmuir* **2014**, *30*, 3625.
- 17 9 M. Focsan, A. M. Gabudean, A. Vulpoi, S. Astilean, *J. Phys.*
- 18 *Chem. C* **2014**, *118*, 25190.
- 19 10 S. Vial, D. Nykypanchuk, F. L. Deepak, M. Prado, O. Gang,
- 20 *Journal of Colloid and Interface Science* **2014**, *433*, 34.
- 21 11 A. Guerrero-Martinez, J. Pérez-Juste, L. M. Liz-Marzan, *Adv.*
- 22 *Mater.* **2010**, *22*, 1182.
- 23 12 P. Reineck, D. Gomez, S. Hock Ng, M. Karg, T. Bell, P.
- 24 Mulvaney, U. Bach, *ACS Nano* **2013**, *7*, 6636.
- 25 13 D. I. Gittins, F. Caruso, *J. Phys. Chem. B* **2001**, *105*, 6846.
- 26 14 G. Schneider, G. Decher, *Langmuir* **2008**, *24*, 1778.
- 27 15 L. L. Rouhana, J. A. Jaber, J. B. Schlenoff, *Langmuir* **2007**, *23*,
- 28 *12799*.
- 29 16 J. Casas, M. Venkataramasubramani, Y. Wang, L. Tang, *Elsevier*
- 30 **2013**, *49*, 525.
- 31 17 B. N. Khlebtsovabandrey, M. Burovanikolai, G. Khlebtsov,
- 32 *Applied Materials* **2019**, *15*, 67.
- 33 18 D. A. Boyne, M. H. Griep, *Plasmonics* **2018**, *13*, 1227.
- 34 19 F. Kang, J. He, T. Sun, Z. Yong, B. Feng, W. Dang, Y. Lei,
- 35 *Advanced Functional Materials* **2017**, *27*, 1701842.
- 36 20 X. Ye, C. Zheng, J. Chen, Y. Gao, C. B. Murray, *Nano Letters*,
- 37 **2013**, *13*, 765.
- 38 21 G. B. Sukhorukov, E. Donath, H. Lichtenfeld, E. Knippel, M.
- 39 Knippel, A. Budde and H. Möhwald, *Colloids Surfaces A:*
- 40 *Physiochem Eng. Aspects* **1998**, *137*, 253.
- 41 22 P. Anger, P. Bharadwaj, L. Novotny, *Phys. Rev. Lett.* **2006**, *96*,
- 42 *113002*.
- 43 23 M. Funston, C. Novo, T. J. Davis, P. Mulvaney, *Nano Letters*
- 44 **2009**, *9*, 1651.