Three-way catalytic activity of alumina-supported copper catalysts modified by rhodium

Xavier Courtois, Vincent Perrichon, Michel Primet

► To cite this version:

Xavier Courtois, Vincent Perrichon, Michel Primet. Three-way catalytic activity of alumina-supported copper catalysts modified by rhodium. *Comptes rendus de l'Académie des sciences. Série IIc, Chimie*, 2000, 3 (6), pp.429-436. 10.1016/S1387-1609(00)01143-9 . hal-03123136

HAL Id: hal-03123136

<https://hal.science/hal-03123136>

Submitted on 27 Jan 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Comptes Rendus Acad. Sci. Série IIc., 3 (2000) 429-436.
DOI: 10.1016/S1387-1609(00)01143-9

THREE-WAY CATALYTIC ACTIVITY OF ALUMINA SUPPORTED COPPER CATALYSTS MODIFIED BY RHODIUM.

Xavier Courtois, Vincent Perrichon*, Michel Primet

Laboratoire d'Application de la Chimie à l'Environnement (LACE), Université Claude Bernard Lyon 1, 43 bd du 11 Novembre 1918, 69622 Villeurbanne Cédex. (France).

Abstract

The three-way catalytic activity of a 4.7% Cu/Al₂O₃ catalyst modified by addition of small amounts of rhodium (from 100 to 2000 ppm) was measured up to 550°C, in steady state or oscillatory conditions (0.1 Hz), using a synthetic gas containing N₂, O₂, CO, C₃H₆ and NO. No synergetic effect in the catalytic properties has been observed between Cu and Rh, as the CO, NO and C₃H₆ conversions at low temperature increase with rhodium concentration. At high temperature, the use of copper which exhibits oxygen storage properties improves the CO and NO conversion by moving up the limitations observed in the conversion under oscillatory conditions.

Keywords: rhodium, copper, three-way catalysts, oscillatory conditions, Cu/Al₂O₃, CuRh/Al₂O₃, oxygen storage.

* Correspondence and reprints. Tel: 334 72 43 15 87, Fax: 334 72 44 81 14, Vincent.Perrichon@univ-lyon1.fr

ACTIVITE EN CATALYSE TROIS-VOIES DE CATALYSEURS AU CUIVRE SUPPORTE SUR ALUMINE MODIFIES PAR AJOUT DE RHODIUM.

Version française abrégée.

L'influence de faibles ajouts de rhodium sur l'activité en catalyse trois-voies d'un catalyseur 4.7% Cu/Al₂O₃ avec des teneurs en rhodium de 100, 500, 1000 et 2000 ppm. L'activité catalytique a été mesurée entre 50 et 550°C, en régime stationnaire et transitoire (0,1 Hz), sur un mélange synthétique contenant N₂, O₂, CO, C₃H₆ et NO.

Aucun effet de synergie entre le cuivre et le rhodium n'a été observé sur les propriétés catalytiques. En régime stationnaire et à basse température, la conversion de NO augmente avec la concentration en Rh. On observe en parallèle une légère amélioration de la conversion en oxydation de C₃H₆ et CO. Comparé au rhodium, le cuivre améliore l'oxydation de CO à basse température. A température plus élevée, C₃H₆ est oxydé préférentiellement à CO jusqu'à conversion totale. En régime transitoire, CO et NO ont des conversions limitées par suite de l'épuisement temporaire de l'un des réactifs durant les oscillations de composition "mélange riche - mélange pauvre". La présence de cuivre qui présente des propriétés de stockage d'oxygène permet d'augmenter la conversion de CO et NO à haute température.

Mots clefs : rhodium, cuivre, catalyseurs trois voies, régime transitoire, Cu/Al₂O₃, CuRh/Al₂O₃, stockage d'oxygène.

1. INTRODUCTION

The precious metals (Pt, Rh, Pd) constitute the active phase of the current three-way catalysts used for the automotive exhaust gas treatment. Their cost and their availability in the future constitute a revolving problem and it would be highly valuable to find substitutes of lower costs. Recently, it was shown that a perovskite type mixed oxide such as La_2CuO_4 was active in the CO+NO reaction [1-2]. Under reaction conditions, there was an activation and it was deduced that metallic copper species were the active sites for the reaction [2]. However, copper seems not active enough to be used alone for real applications without promoter addition. Therefore, looking for new types of three-way catalysts, we have investigated in this study how the addition of rhodium which is known to be a key component in the NO_x conversion can influence the catalytic properties of copper in alumina supported catalysts. Conversely, copper was found an excellent promoter of the oxygen storage capacity (OSC) of a Rh/CeO₂ catalyst [3]. In this work, the catalytic data obtained with the CuRh/Al₂O₃ systems in steady state or cycled feed stream are presented and discussed.

2. EXPERIMENTAL

The alumina support (Rhodia 531P) had a BET surface area of 115 m²g⁻¹. It was co-impregnated with copper and rhodium nitrate solutions in order to obtain catalysts with a 4.7 wt% copper content and 0, 100, 500, 1000 and 2000 ppm rhodium content. A monometallic catalyst with 1000 ppm Rh was also prepared. After drying under air for one night at 110°C, the solids were ground and calcined for 6 h at 400°C under a 6 l h⁻¹ O₂ flow (1°C min⁻¹ heating rate). Finally, the catalysts were reduced at 500°C under hydrogen (7 l h⁻¹) for 6 h. After cooling under H₂ to room temperature, the samples were put under nitrogen and then slowly under air. The samples are referred as CuRh_x/Al, where x indicates the Rh content in ppm.

The three-way catalytic activity was measured in the simultaneous conversion of CO, NO_x and C₃H₆. The experimental device [4-5], is constituted by two independent ramps in which mixtures of different compositions can be prepared using mass controllers for each gas diluted in nitrogen (CO, NO, C₃H₆, O₂). Thus, it is possible to work either with only one ramp in steady state conditions, i.e. with a unique composition mixture, or in oscillatory conditions, using the two ramps with two mixtures of different composition. In the latter case, each mixture goes alternately through the catalytic bed. This allows to simulate the rich/lean oscillations of the mixture occurring in the real conditions of a catalytic converter. A by-pass system allows to verify the composition of the initial mixture before the catalytic test. At the exhaust of the reactor, the gases are cooled and then analysed in series by paramagnetism for O₂ and by infrared spectrometry for CO, CO₂, NO, N₂O and C₃H₆.

The tests were performed on 20 mg catalyst diluted in 180 mg SiC, in order to limit the possible temperature increase due to highly exothermic reactions, like propene combustion. It was verified that SiC alone was not active. Before the measurement of the activity itself, the catalyst was first activated in steady state operation under a stoichiometric mixture having the composition given in Table I. The solid was heated at 10°C min⁻¹ under this mixture up to

550°C, kept 1 h at this temperature and cooled to rt under N₂ flow. At this stage, the state of the metals was undetermined, even if we can assume that it was metallic, in accordance with the results obtained with La₂CuO₄ [2]. Then the reaction mixture was introduced and one can think that the metals were partially oxidised by O₂ and NO present in the mixture, at least during the first heating minutes. The catalytic activity test was performed up to 550°C (heating rate 5°C min⁻¹), either under stoichiometric or oscillating mixture (compositions in Table I). The cycling frequency between the two ramps was low (0.1 Hz) to insure at the catalytic bed the effective variation of composition programmed in each ramp in spite of the mixing of the gaseous front. In both conditions (steady state or oscillatory) the flow rate was 12 l h⁻¹, which corresponded approximately to a VVH of 500,000 h⁻¹. It must be remarked that, due to the mixing of the gaseous fronts before and after the catalytic bed, the amplitude of the variations of composition was lower at the level of the analysers than that imposed initially in the ramps. However, it has been verified that with this frequency, the catalyst sees effectively the nominal changes in composition [4].

Table I: Composition of the gaseous mixtures used in steady state and oscillatory conditions.

	Steady state	Oscillatory		
		Lean mixture	Rich mixture	Variation
O ₂ / ppm	5600	7820	3380	± 2220
CO / ppm	6200	1620	10780	± 4580
NO / ppm	1000	1000	1000	0
C ₃ H ₆ / ppm	667	667	667	0
S	1	2,18	0,46	

All the gases are used diluted in nitrogen. "s" represents the oxidant/reductant ratio. It is calculated from the concentrations of each component by the expression:

$$s = \frac{2[O_2] + [NO]}{[CO] + 9[C_3H_6]}$$

3. RESULTS

3.1. Catalytic activity in steady state conditions.

The two monometallic catalysts, Cu/Al and Rh1000/Al, were compared to the CuRh2000/Al sample. The alumina support alone was inactive in our conditions. Figure 1 gives the conversions for each reactant between 50 and 550°C. In a general description, all the catalysts exhibit a sigmoidal activity profile. In the case of Rh1000/Al, the CO, NO and propene conversions begin at 215, 240 and 270°C, respectively. For T > 400°C, the three pollutants are fully converted. Cu/Al is always less active, except for the CO oxidation which starts at lower temperature, at around 120°C. CuRh2000/Al is a little more active than Rh1000/Al and, as for Cu/Al, its activity in CO oxidation starts at around 120°C.

Figure 1: Activity in steady state conditions for CO, NO and C₃H₆ and for a) Cu/Al, b) Rh1000/Al and c) CuRh2000/Al catalysts

It must be noted that the NO conversion at low temperature does not produce only nitrogen. There is also formation of N₂O, which is also a pollutant. For Rh1000/Al and below 300°C, the N₂O selectivity is 100%. Then the selectivity drops quickly and for T > 400°C, N₂O is practically not observed. In the case of Cu/Al, the NO conversion occurs at higher temperature and the maximum selectivity in N₂O is only 6 % at 470°C. For CuRh2000/Al, the maximum N₂O selectivity is 37 % at 292°C.

3.2. Catalytic activity in oscillatory conditions.

The influence of the Cu/Rh ratio was studied in more details in oscillatory conditions. Since strong differences appear between Rh and the other copper based catalysts for the CO and NO conversion curves, we examine first the case of the Rh sample and then the copper and bimetallic catalysts. Because of the fluctuations in the concentration of CO and O₂ at the reactor inlet, the actual conversions given in the figures were calculated on a mean concentration basis, i.e. with the steady state composition (see Table I).

Rh1000/Al₂O₃ catalyst.

Figure 2 gives the conversion curves in oscillatory conditions. The comparison with the steady state data shows that the conversions are similar at low temperature but greatly differ at high temperature for CO and NO.

The CO conversion begins near 170°C, goes through a maximum at 315°C where 75% CO is oxidised, and then drops down and stabilises at 47% for T > 450°C. In this temperature domain, the oscillations between the rich and lean composition ($\Delta_{\text{comp.}}$) are then scarcely attenuated ($\Delta_{\text{comp.}} = 925$ ppm at rt., $\Delta_{\text{comp.}} = 780$ ppm at 450-550°C).

The NO conversion starts at 220°C. For $T > 350^\circ\text{C}$, the NO conversion remains limited to about 60% and even decreases at the end of the test to 56%. The N_2O selectivity goes through a maximum (80%) at 297°C, the maximum N_2O concentration (150 ppm) being obtained at about 315°C. For higher temperatures, the N_2O production decreases to zero.

The propene conversion starts only at around 260°C, but with a higher activation energy than for CO or NO ($E_a = 204 \text{ kJ mol}^{-1}$). When the conversion is higher than 50 %, the increase in activity slows down, but the propene is entirely eliminated for $T > 430^\circ\text{C}$.

CuRh/Al₂O₃ catalysts.

As shown in Fig.3, the CO conversion is favoured upon addition of rhodium to copper. The temperature of the beginning of reaction slightly decreases. The light off temperature (T_{50}), temperature for which 50% of the pollutants are converted, decreases from 350°C for Cu/Al to 275°C for CuRh2000/Al. Also, at high temperature, the maximum of conversion increases with rhodium but is always much higher than that obtained with Rh1000/Al alone.

The NO conversion curves are more complex since they present like an intermediate plateau in the sigmoidal profile. This peculiar shape will be discussed below. However, it is evident in Fig.4, that the higher the rhodium content, the more active the catalyst. More than 200°C difference is obtained for T_{50} between Cu/Al and CuRh2000/Al. At 550°C, all the bimetallic catalysts are more active than Rh1000/Al.

The propene conversion curves are given in Fig.5. They are almost sigmoidal but rather close between each other (difference in T_{50} lower than 50°C for the extreme curves). Nevertheless the increase in the activity upon addition of Rh is clearly evidenced.

Figure 2: Activity in oscillatory conditions for Rh1000/Al. a) CO, b) NO, c) C_3H_6 and d) O_2 .

Figure 3: Conversion of CO in oscillatory conditions on monometallic Cu/Al, Rh1000/Al and bimetallic CuRh100/Al, CuRh500/Al, CuRh1000/Al and CuRh2000/Al catalysts.

Figure 4: Conversion of NO in oscillatory conditions on monometallic Cu/Al, Rh1000/Al and bimetallic CuRh100/Al, CuRh500/Al, CuRh1000/Al and CuRh2000/Al catalysts.

Figure 5: Conversion of C_3H_6 in oscillatory conditions on monometallic Cu/Al, Rh1000/Al and bimetallic CuRh100/Al, CuRh500/Al, CuRh1000/Al and CuRh2000/Al catalysts.

4. DISCUSSION

4.1 Influence of rhodium in the bimetallic CuRh catalysts.

The copper-alumina catalyst exhibits some three-way catalytic activity. However as evidenced in Fig.3 to 5, it is clear that this activity is improved upon addition of small amounts of rhodium. Rhodium itself is very active in the three reactions, and it must be noted that there is no great difference in the activity curves between Rh1000/Al and CuRh1000/Al, mainly for conversions < 50%. Thus, an addition of the properties of each metal is sufficient to explain the obtained conversions and no synergetic effect is deduced which would have strongly increase the activity of both metals.

Conversely, because the addition of the properties of each metal, the CuRh/Al bimetallic catalysts exhibit slight improvements in the catalytic properties compared to Rh1000/Al. It is well shown in Fig.1 for the CO and C_3H_6 conversions at low temperature (steady state conditions) and also in Fig.3-4 for the CO and NO transformation at high conversions (oscillatory conditions). This can be attributed to the redox properties of copper. Indeed, copper is an oxidation catalyst which favours the beginning of the CO and propene oxidation at lower temperature than rhodium. Concerning the improvement at high conversion, it involves the property of copper to store oxygen. The relation of this oxygen storage capacity (OSC) with the CO and NO conversion is explained hereafter.

4.2. Effect of OSC on the catalytic activity in oscillatory conditions.

In order to explain the limitations observed in oscillatory conditions for Rh1000/Al in the CO and NO conversion curves at high temperatures, we have to consider that in our

working conditions, a very low cycling frequency and a large cycling amplitude may result in the succession of incomplete conversions either of the oxidants or the reductants. For example, if the propene oxidation is complete as it is observed, the conversion for CO will be limited during the rich half-cycle, because there will not be enough oxygen. Thus, we have calculated for each mixture, rich or lean, what is the maximum possible conversion for each pollutant. However, for the calculation, it is necessary to define a hierarchical order in the competitive reactions. Considering the experimental results, (Fig. 2), it is clear that at high conversion, propene oxidation is favoured compared to CO oxidation. Moreover, the reduction of NO by CO is strongly inhibited by oxygen [6]. Consequently, we have assumed the following decreasing reactivity sequence: $C_3H_6 + O_2 > CO + O_2 > CO + NO$. The oxidation of CO and C_3H_6 by NO as oxidant was not considered for simplification. Indeed, the total conversion of NO would allow to oxidise only 11% of propene in CO_2 and the reduction of CO by NO would be limited to 16%. Finally, in the present case (Rh1000/Al), the OSC is very low and was neglected. Therefore, the succession of the reactions is the following:

In lean mixture:

- $C_3H_6 + 9/2 O_2 \rightarrow 3 CO_2 + 3 H_2O$: the hydrocarbon conversion is total, and O_2 (≈ 4800 ppm) is available for the CO oxidation.
- $CO + 1/2 O_2 \rightarrow CO_2$: the CO conversion is total, and it still remains ≈ 4000 ppm O_2 .
- $CO + NO \rightarrow CO_2 + 1/2 N_2$: the reaction is not possible, because there is no more CO.

In rich mixture

- $C_3H_6 + 9/2 O_2 \rightarrow 3 CO_2 + 3 H_2O$: the hydrocarbon conversion is again complete and it remains ≈ 380 ppm O_2 for the CO oxidation.
- $CO + 1/2 O_2 \rightarrow CO_2$: the conversion of O_2 is total, and this time, it remains ≈ 10000 ppm CO.
- $CO + NO \rightarrow CO_2 + 1/2 N_2$: the NO conversion is complete, it remains ≈ 9000 ppm CO.

Table II gives the theoretical maximum conversions and their average obtained in oscillatory conditions for each mixture and with each pollutant. For CO, NO, C_3H_6 and O_2 , the mean maximum conversions are 27%, 50%, 100% and 64%, respectively. These values are in agreement with the experimental results, the observed differences being explained by the unavoidable mixing of the gaseous fronts before passing through the catalytic bed. Therefore, these results clearly show that the rich-lean oscillations are the reason of the limitations of the conversions in CO and NO for the Rh1000/Al catalyst. They are in agreement with previous transient CO and NO experiments performed with different frequencies on a Rh/Al solid [7].

Consequently, the catalytic activity at high conversion must be strongly influenced by the oxygen storage capacity of the solids. It must be underlined that in steady state operation there is no excess of oxidant or reductant, and that the conversions are total at high temperature for the three reactants. In oscillatory operation, a component having an OSC is able to store and release oxygen during the oscillations and thus allows to attenuate the

amplitude of the oscillations responsible of the CO and NO conversion limitations. Copper is present with a relatively high content (0.74 mmol g^{-1}). Therefore it may act as an OSC component, and effectively it moves up the conversion limits, as it is evidenced in Fig.3 and 4. This positive effect of OSC components under transient feed stream conditions is well documented in the literature [8].

The C_3H_6 conversion is little influenced by the presence of copper and the testing conditions. This appears quite normal, since the oxidation of C_3H_6 by O_2 is the most favoured reaction as it was shown above, in agreement with literature [9]. As long as there is enough oxygen to oxidise the hydrocarbon, there will be no influence of the mixture composition.

Table II: Remaining compositions and theoretical conversions for each mixture, calculated assuming the following reactivity order: $\text{C}_3\text{H}_6 + \text{O}_2 > \text{CO} + \text{O}_2 > \text{CO} + \text{NO}$. Comparison with the experimental results.

	Lean mixture		Rich mixture		Average rich-lean		Experimental results
	remaining concentration (ppm)	Conversion (%)	remaining concentration (ppm)	conversion (%)	remaining concentration (ppm)	conversion (%)	conversion (%)
CO	0	100	9026	16	4513	27	47
NO	1000	0	0	100	500	50	56
C_3H_6	0	100	0	100	0	100	100
O_2	4008	49	0	100	2004	64	76

4.3. Effect of copper on the NO conversion curves in the bimetallic CuRh catalysts.

In steady state conditions, the NO conversion curve vs temperature for Cu/Al exhibits a temporary constant level at around 400°C (Fig.1). A more pronounced intermediate plateau is observed for CuRh/Al in oscillatory conditions, with conversion percentage and temperature range depending on Rh content (Fig.4). For Rh1000/Al, the plateau at 56% was explained above by the limitations resulting from the rich-lean oscillations. For the CuRh/Al, the presence of copper attenuates the amplitude of the oscillations and thus favours the conversion at high temperature. The copper oxygen storage capacity may also account for the existence of the plateau at lower conversion, i.e. for C_3H_6 and CO partial conversion. For $T > 300^\circ\text{C}$, the oxidation of copper by gaseous O_2 is a fast reaction involving both the surface and the bulk of copper particles. Then the formed copper oxide constitutes an oxygen reservoir, which participates to the CO and C_3H_6 oxidation according to the reactions:

Therefore, during a cycle, as long as there is oxygen left in the reactor or stored by copper, unreacted CO and C₃H₆ react preferentially with this oxygen rather than with NO, and the NO conversion remains nearly constant. In parallel, the conversions for CO and C₃H₆ increase and the curves effectively exhibit inflexion points which correspond to the intervention of this stored oxygen in the oxidation reactions. It is important to note that, at higher temperature, the conversion of NO with the residual CO increases again precisely when oxygen becomes depleted, i.e. when the O₂ conversion is nearly complete (not shown). The fact that the NO conversion at the plateau increases with Rh content must be attributed to the own activity of rhodium.

CONCLUSION

The study of CuRh/alumina catalysts has evidenced no synergetic effect between Cu and Rh for the activity in three-way catalysis. For each reaction, the conversion at low temperature increases with the rhodium concentration. However, compared to rhodium alone, the CO and C₃H₆ oxidation begins at lower temperature in presence of copper.

When the catalytic tests are performed under oscillatory conditions, differences are observed at high conversions between the catalysts of different composition. The analysis of the conversion curves as resulting from the succession of competitive reactions in reducing and oxidising mixtures easily explains the incomplete CO and NO conversions at high temperature by the alternate depletion of one of the reactants during the oscillations "rich mixture-lean mixture". However, in presence of copper, which alternately is able to adsorb and release oxygen, the regular fluctuations of the mixture composition are attenuated at the catalyst level and the NO and CO conversions become less limited. The propene oxidation is much less sensible to the composition fluctuations because, under oxygen deficient mixture, the hydrocarbon is preferentially oxidised compared to CO at high temperature. It may be concluded that, in this bimetallic catalyst, the important role of copper appears more related to its oxygen storage capacity than its own catalytic properties.

REFERENCES

- [1] : Guilhaume N, Peter S.D., M. Primet M., Appl. Catal. B, 10 (1996) 325.
- [2] : Peter S.D., Garbowski E., Guilhaume N., Perrichon V., Primet M., Catal. Letters, 54 (1998) 79.
- [3] : Kacimi S., Barbier Jr. J., Taha R., Duprez D., Catal. Letters, 22 (1993) 343.
- [4] : Weibel M., thesis 10/1991, Université Louis Pasteur, Strasbourg, France.
- [5] : Howitt C., Pitchon V., Garin F., Maire G., Stud.Surf.Sci.Catalysis, 96 (1995) 149.
- [6] : Howitt C., Pitchon V., Maire G., J. Catal., 154 (1995) 47.
- [7] : Cho B.K., J. Catal., 131 (1991) 74.
- [8] : Silveston P.L., Catal. Today, 25 (1995) 175.
- [9] : Muraki H., Sobukawa H., Fujiyama Y., Nippon Kagaku Kaishi, 4 (1986) 532.