New Mn-TiO₂ aerogel catalysts for the low-temperature selective catalytic reduction of NO_x

Jihene Arfaoui, Abdelhamid Ghorbel, Carolina Petitto, Gerard Delahay

► To cite this version:

Jihene Arfaoui, Abdelhamid Ghorbel, Carolina Petitto, Gerard Delahay. New Mn-TiO₂ aerogel catalysts for the low-temperature selective catalytic reduction of NO_x. *Journal of Sol-Gel Science and Technology*, 2021, 97, pp.302-310. 10.1007/s10971-020-05451-4 . hal-03133561

HAL Id: hal-03133561

<https://hal.science/hal-03133561>

Submitted on 6 Feb 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

New Mn-TiO₂ aerogel catalysts for the low-temperature selective catalytic reduction of NO_x

Jihene Arfaoui^{*a}, Abdelhamid Ghorbel^a, Carolina Petitto^b, Gerard Delahay^b

^aUniversité Tunis El Manar, Laboratoire de Chimie des Matériaux et Catalyse, Département de Chimie, Faculté des Sciences de Tunis, Campus Universitaire Farhat Hached d'El Manar, 2092, Tunis, Tunisia.

^bICGM, University of Montpellier, ENSCM (MACS), CNRS, Montpellier, France

* Corresponding author: E-mail address: jihene.arfaoui@fst.utm.tn; jihenar@yahoo.fr

Tel: +216 23020273, Fax: +216 71 875 008

Abstract

A new series of Mn-based catalysts (Mn-TiO₂, Ce-Mn-TiO₂, Mn-TiO₂-SO₄²⁻ and Ce-Mn-TiO₂-SO₄²⁻) were successfully elaborated using the sol gel method associated to supercritical drying approach for the low temperature NO-SCR by NH₃. The physicochemical properties of aerogel powders were examined by XRD, N₂-Physisorption at 77 K, NH₃-TPD, H₂-TPR, and DRUV-Vis spectroscopy. It was shown that all the catalysts develop essentially the diffraction peaks of TiO₂ anatase phase and are characterized by a nanometer size (ranging between ~ 5 and 9 nm), developed mesoporous texture, high surface area ($S_{\text{BET}} > 104 \text{ m}^2/\text{g}$) and large porosity ($V_{\text{PT}} > 0.24 \text{ cm}^3/\text{g}$). The incorporation of Ce and/or SO₄²⁻ influences differently the structural, textural, acidic and redox properties of Mn derived sol gel catalysts and consequently affects their SCR activity. High NO conversions (> 75 %) into essentially N₂O are obtained at low temperatures (150-270 °C) over Mn-TiO₂ and Ce-Mn-TiO₂ aerogel systems. The addition of sulfate modifies the nature of Mn species and noticeably reduces the low temperature reactivity of catalysts (T < 300 °C). However, it induces, thanks to the contribution of many strong acid sites, a substantial increase of the NO conversion into N₂ at higher temperatures (T > 300 °C) leading to highly active and N₂-selective Mn-TiO₂-SO₄²⁻ and Ce-Mn-TiO₂-SO₄²⁻-sulfated catalysts. Above 90 % NO conversion into N₂ (100 %) was reached, in the NO-SCR by NH₃, over the new Ce-Mn-TiO₂-SO₄²⁻ aerogel catalyst, in the 450-500 °C temperature range.

Key words: Sol Gel method, Aerogel, Mn-TiO₂, Cerium, Sulfate, Low temperature NO-SCR by NH₃

1. Introduction

“Aerogels” are an exceptional class of mesoporous/macroporous materials derived from organic, inorganic or hybrid molecular precursors and usually prepared via the sol-gel method associated to an appropriate drying process, mainly supercritical one, which preserve both the three-dimensional arrangement and highly

porous texture of solids. The unique and exclusive properties of these materials such as low density ($0.003\text{--}0.5\text{ g cm}^{-3}$), considerably high surface area ($500\text{--}1200\text{ m}^2/\text{g}$), large porosity ($80\text{ \%--}99.8\text{ \%}$) and adjustable surface chemistry with the ability to be processed into a variety of morphologies and sizes [1] made them suitable for various applications extending from thermal and acoustic insulation to biomedical and pharmaceutical applications [2]. In recent years, major interest has been devoted to aerogels as heterogeneous catalysts, photocatalysts or catalyst supports for air and water cleaning reactions such as: VOCs oxidation, Methane reforming, Preferential oxidation of CO, Fenton and Fenton-like processes, Ozonation and deNO_x applications (NO-SCR) [2].

Selective catalytic reduction of NO by NH₃ (NO-SCR) is until now considered the most efficient and economic technology for controlling NO_x emissions from stationary sources and diesel vehicles [3]. The commercially used catalysts are principally WO₃ or MoO₃ doped V₂O₅/TiO₂ [4] which exhibit excellent SCR performances between 300 and 400 °C but it has several drawbacks such as: narrow reaction temperature range, production of N₂O at high temperature, volatility and toxicity of vanadium [5-6]. Hence, there has been a lot of interest to develop environmentally friendly and highly active free vanadium catalysts for the low-temperature SCR process (< 200 °C).

A variety of supported transition metal oxides (e.g., V₂O₅, NiO, Co₃O₄, Fe₃O₄, MnO₂, etc.) and transition metals (e.g., Co, V, Cu, Fe, Mn, etc.), have been developed for the NO-SCR process [7,8]. Particularly, manganese-containing catalysts [8,9], such as: MnO_x/TiO₂ [10], MnO_x/CeO₂ [11], MnO_x/Al₂O₃ [12], MnO_x/zeolite [13,14] and MnO_x/active carbon [15], has attracted much attention due to the excellent redox ability of Mn [8]. Peña et al. [16] showed that among various transition metal oxides supported on TiO₂, manganese based catalyst is the best candidate for the low-temperature SCR reaction and the activity decreases following this order: Mn > Cu ≥ Cr >> Co > Fe >> V >> Ni. Nevertheless, Smirniotis et al. [17] examined the effect of support (TiO₂, SiO₂ and γ-Al₂O₃) on the NO-SCR activity of various metal oxides (MnO_x, VO_x, NiO_x, CuO_x and CrO_x) and demonstrated that MnO_x/TiO₂ system exhibits the best catalytic performance.

Recently, much attention was devoted to Mn-Ce/TiO₂ SCR catalysts due to their nontoxicity and exceptional low-temperature activity. These systems showed extraordinary SCR-activity between 100 and 200 °C [18-22] because manganese oxides (MnO_x) have many types of oxidative states and possesses several kinds of active oxygen which is necessary to complete the SCR reaction cycle [23]. Meanwhile, ceria (CeO₂) has been proved as promoter on the SCR catalysts due to its unique oxygen storage capacity (OSC) and redox properties: this element can store and release oxygen via the redox shift between Ce⁴⁺ and Ce³⁺ under the oxidizing and reducing conditions, respectively [24,25]. It has been verified that the SCR activity of Mn species is strongly

influenced by the Mn oxidation state, crystallinity, specific surface area and morphology of catalyst [26] which are strongly affected by the preparation method. Kaptejin et al. [27] reported that the SCR activity of Mn species decreases in this order $\text{MnO}_2 > \text{Mn}_5\text{O}_8 > \text{Mn}_2\text{O}_3 > \text{Mn}_3\text{O}_4 > \text{MnO}$. Furthermore, Kang et al. [28] correlated the excellent activity of MnO_x catalyst for the low temperatures selective catalytic reduction of NO_x with its high surface area and amorphous framework structure.

It is recognized that the use of the sol-gel procedure combined to supercritical drying can produce a highly structured aerogel materials with superior textural properties (high specific surface area and porosity) which can provide more active sites in the catalyst surface [29]. On the other hand, in our previous works [30,31] we have demonstrated that the addition of SO_4^{2-} groups to the composition of $\text{V}_2\text{O}_5\text{-CeO}_2\text{-TiO}_2$ and $\text{V}_2\text{O}_5\text{-MoO}_3\text{-TiO}_2$ aerogel catalysts enhances both the NO conversion and N_2 selectivity at high temperatures. However, the NO-SCR activity of $\text{Ce-Mn-TiO}_2\text{-SO}_4^{2-}$ aerogel system has not yet been studied. In this work, we investigate the SCR activity of a new series of unsulfated and sulfated Mn based aerogel catalysts (Mn-TiO_2 , Ce-Mn-TiO_2 , $\text{Mn-TiO}_2\text{-SO}_4^{2-}$ and $\text{Ce-Mn-TiO}_2\text{-SO}_4^{2-}$), in a wide temperature range (100-500 °C) under O_2 rich conditions and at relatively high gas hourly space velocity “ GHSV ” (120.000 h^{-1}).

2. Experimental

2. 1. Catalysts elaboration

The aerogel samples (TiO_2 , Mn-TiO_2 , Ce-Mn-TiO_2 , $\text{Mn-TiO}_2\text{-SO}_4^{2-}$ and $\text{Ce-Mn-TiO}_2\text{-SO}_4^{2-}$) were synthesized via the one step sol-gel method using the same procedure reported in our previous works [30,31]. Cerium nitrate ($\text{Ce}(\text{NO}_3)_3 \cdot 6\text{H}_2\text{O}$, Aldrich) and manganese nitrate ($\text{Mn}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$, Aldrich) were used as Ce and Mn precursors. Theoretical loading of Mn and Ce were fixed to 8 and 10 % wt., respectively. The sulfated samples were prepared according to the molar ratio $\text{S/Ti} = 0.2$. All the aerogel samples were calcined for 3 h at 500 °C under O_2 flow ($30 \text{ mL} \cdot \text{min}^{-1}$).

2. 2. Catalysts characterization and activity test

The textural properties of aerogel catalysts were determined by N_2 -adsorption-desorption analysis, which was carried out at 77 K on a Micromeritics ASAP 2020 apparatus. Prior to N_2 adsorption, the samples were degassed at 200 °C for 6 h to desorb moisture adsorbed on their surfaces and inside their porous networks. The specific surface areas were calculated by the Brunauer-Emmett-Teller (BET) equation in 0.05-0.35 partial pressure range, while, the pore volumes, average pore diameters and pore size distributions were determined by Barrett-Joyner-Halenda (BJH) method from the desorption branches of the isotherms.

The catalyst structures were examined by powder X-ray diffraction on a Brüker AXS D8 diffractometer equipped with CuK α radiation ($\lambda = 1.5406 \text{ \AA}$), using a scan range from $2\theta = 2$ to 80° with a step size of 0.02° . The crystallites size (D) of titania was calculated by the Scherrer formula applied to the most intense peak of the TiO $_2$ anatase phase ($2\theta \sim 25^\circ$): $D = 0.89 (\lambda/\beta \cos\theta)$ [32], where θ is the peak position, β is the corrected peak width at half-maximum intensity (FWHM in radians) and λ is the wavelength of XR radiation.

Diffuse Reflectances Ultraviolet visible spectroscopy (DR-UV-vis) was carried out over the aerogels powder, at room temperature, in the 200-900 nm range with a speed of 960 nm min^{-1} and an aperture of 4 nm. PerkinElmer spectrophotometer type lambda 45 equipped with an integrating sphere type RSA-PE-20 was used as apparatus.

Temperature Programmed Desorption by Ammonia (NH $_3$ -TPD) was performed using an AUTOCHEM 2920 (Micromeritics) equipped with a TCD detector. Prior to NH $_3$ adsorption, the catalyst powder ($m = 0.05 \text{ g}$) was activated under air flow (30 mL min^{-1}) at 500°C (ramp $10^\circ\text{C min}^{-1}$) for 30 min. After cooling to 100°C , the sample was saturated with ammonia (5 vol% NH $_3$ in He, flow rate = 30 mL min^{-1}) for 45 min. Then, it was flushed with He (30 mL min^{-1}) during 2 h to remove physisorbed NH $_3$. Finally, the ammonia was desorbed in He flow (30 mL min^{-1}) from 100°C to 600°C using a heating rate of $10^\circ\text{C min}^{-1}$.

Temperature Programmed Reduction by Hydrogen (H $_2$ -TPR) was realized on a Micromeritics AUTOCHEM 2910 equipped with a TCD detector. Briefly, the aerogel powder ($m = 0.05 \text{ g}$) was pre-treated under 5 vol % O $_2$ in He (flow rate = 30 mL min^{-1}) at 500°C (ramp $10^\circ\text{C min}^{-1}$) for 30 min. After being cooled down to 50°C in the same atmosphere, the sample was flushed with He (30 mL min^{-1}) then exposed to a flow containing 5 vol % H $_2$ in Ar (30 mL min^{-1}) and heated between 50 and 800°C ($10^\circ\text{C min}^{-1}$).

The selective Catalytic Reduction (SCR) tests over the powder aerogel catalysts were carried out in a fixed-bed quartz flow reactor operating at atmospheric pressure. The reaction conditions were controlled as follows: 400 ppm NO, 400 ppm NH $_3$, 8 % O $_2$ in He as a balance gas and 100 mL min^{-1} total flow rate yielding a gas hourly space velocity (GHSV) of $120,000 \text{ h}^{-1}$. Before measurements, the catalyst (0.05 g) was activated in situ at 200°C for 30 min under O $_2$ /He (20/80, v/v) flow then cooled to 100°C . Afterward, the NO conversion curves were recorded between 100 and 500°C with the heating rate of 6°C min^{-1} . The reactants and products gases were continuously analyzed by an online Pfeiffer Omnistar quadruple mass gas spectrometer equipped with Channeltron and Faraday detectors (0-200 amu).

3. Results and discussion

3. 1. Textural properties of aerogel catalysts

The N₂ adsorption-desorption isotherms at 77 K and pores size distribution curves of samples, are illustrated in Fig. 1 A and 1 B, respectively. As it can be seen, the isotherms of all the catalysts belong to type IV which is typical of mesoporous materials according to the IUPAC classification [33]. The hysteresis loops of TiO₂ and Mn-TiO₂-SO₄²⁻ correspond to H2 type, indicating, based on the literature reports [34-36], the presence of ink-bottle pores. However, the H1 type, obtained for Mn-TiO₂, Ce-Mn-TiO₂ and Ce-Mn-TiO₂-SO₄²⁻ systems, reveals, in agreement with similar previous results [37-38], the presence of cylindrical mesoporous channels. On the other hand, the curves displayed in Fig. 1B demonstrate that all the solids are characterized by a unimodal pores distribution with a medium average pore diameter < 200 Å.

Figure 1. (A) N₂ Adsorption-desorption isotherms and (B) Pore size distribution curves of nanostructured mesoporous aerogel catalysts.

As the catalytic reactions take place on the surface, a high surface area of catalyst can stabilize the supported active phases and consequently provides more active sites for heterogeneous catalytic reactions [2]. The N₂ physisorption results listed in table 1, show that all the aerogel catalysts calcined at 500 °C exhibit a high surface area ($104 \leq S_{\text{BET}} \leq 132 \text{ m}^2/\text{g}$) and large porosity ($0.24 \leq V_{\text{PT}} \leq 0.47$) revealing their developed texture and high thermo-stability. This highlights the appropriate choice of the preparation method (sol-gel procedure-supercritical drying) for adjusting the textural properties of the final aerogel products used as catalytic systems. In fact, it is recognized that large specific surface area implies more active sites exposed on the surface of catalyst and more contact opportunities with gas molecules, which can promote the SCR activity [28].

Table 1. Textural properties of nanostructured mesoporous aerogel catalysts.

Sample	BET surface area (m^2/g)	Total pore volume (cm^3/g)	Average Pore diameter (Φ_{pore} , Å)
TiO ₂	122	0.33	79
Mn -TiO ₂	113	0.43	121
Mn -TiO ₂ -SO ₄ ²⁻	104	0.24	75
Ce-Mn-TiO ₂	132	0.45	109
Ce-Mn-TiO ₂ -SO ₄ ²⁻	106	0.47	164

3. 2. Structural properties of aerogel catalysts

The results of X-ray diffraction analysis are presented in Fig. 2 and table 2. Based on the obtained XRD patterns (Fig. 2), it could be confirmed the successful synthesis of well-structured aerogel materials developing essentially the reflections of TiO₂ anatase phase; at $2\theta \approx 25.3^\circ$ (hkl:101); 36.9° (103); 37.8° (004); 38.6° (112); 48.2° (200); 53.9° (105); 55.2° (211); 62.7° (204); 69.0° (116); 70.4° (220) and 75.2° (215) [ICSD 01-083-2243]. These new aerogel systems are constituted by a nano-cristallites with a size ranging between ~ 5 and 9 nm (table 2). Noting that some weak diffraction peaks, which cannot be attributed to a one type of Mn-oxide, Mn-sulfate and/or Ce-sulfate, are observed in the diffractograms of sulfated samples, in particular, in that of Ce-Mn-TiO₂-SO₄²⁻. The probable formation of the previously cited compounds in a trace amount on Mn-TiO₂-SO₄²⁻ and Ce-Mn-TiO₂-SO₄²⁻ surfaces and their absence in the case of unsulfated solids make evidence about the highly dispersion state of Mn and Ce species on the catalysts surface. This is consistent with the results already obtained by Know et al. [39]. The authors have showed the absence of characteristic peaks of manganese and cerium oxides in the XRD pattern of Mn/Ce/Ti SCR catalyst, containing 20 wt. % Mn and 4 wt. % Ce.

Figure 2. Powder XRD patterns of nanostructured mesoporous aerogel catalysts.

Table 2. XRD phases and TiO₂ crystallites size of nanostructured mesoporous aerogel catalysts.

Sample	Major XRD phases	FWHM (°)	TiO ₂ crystallite size D (nm)
TiO ₂	Anatase	0.892	8.6
Mn -TiO ₂	Anatase	0.892	8.7
Mn -TiO ₂ -SO ₄ ²⁻	Anatase	1.106	7.0
Ce-Mn-TiO ₂	Anatase	0.928	8.3
Ce-Mn-TiO ₂ -SO ₄ ²⁻	Anatase	1.566	4.9

3.3. Active species characterization

The valence states of active species had an important impact on the SCR reaction. Diffuse-Reflectance UV-vis spectroscopy was employed to explore the valence states and environment coordination of Ce and Mn species at TiO₂ surface. Usually, cerium exhibits two oxidation states (+3 and +4) which are characterized by O²⁻ → Ce³⁺ and O²⁻ → Ce⁴⁺ charge transfer bands (CT) in the 220-250 and 280-400 nm range [30], respectively. However, the most common oxidation states of manganese are: Mn²⁺, Mn³⁺ and Mn⁴⁺. The charge transfer and d-d transitions of Mn species are identified based on the literature reports and listed in table 3 [40-46].

The UV-vis spectra of all the samples (Fig. 3) show the typical absorption bands of TiO_2 in the 200-400 nm range [47]. The increase of the intensity of these bands after Mn and Ce addition can be associated with the absorptions of Ce (probably Ce^{3+} and Ce^{4+} [30]) and Mn (mainly Mn^{2+} and Mn^{3+} [40-45]) species at the same region than those of titanium. Markedly, a new absorption bands are appeared for $\lambda > 400$ nm in the case of Mn- TiO_2 and Ce-Mn- TiO_2 samples. The bands located at ~ 420 and 550 nm can be ascribed to $\text{O}^{2-} \rightarrow \text{Mn}^{4+}$ [40, 44, 46] and new $\text{O}^{2-} \rightarrow \text{Mn}^{3+}$ [40,41] CT transitions, respectively. Nevertheless, those located at $\lambda \geq 500$ nm can be attributed to d-d transitions of Mn (II and III) [40-42, 46]. Remarkably, these bands disappear after sulfation of catalysts implying that sulfate groups affect extremely the nature of Mn surface species, perhaps due to the existence of strong Mn-SO_4^{2-} interactions. The formation of manganese sulfate compounds cannot be also excluded in this case.

Figure 3. DRUV-Vis spectra of nanostructured mesoporous aerogel catalysts.

Table 3. Characteristic UV absorption bands ($O^{2-} \rightarrow Mn^{n+}$ charge transfer (CT) and d-d) of manganese species.

Mn^{n+}	Compound/Coordination	λ (nm)	Assignment	References
Mn^{2+}	MnO	500-610	d-d	[40-42]
	Mn_3O_4	255	$O^{2-} \rightarrow Mn^{2+}$	[42]
	Mn_3O_4	500	d-d	[40,41]
Mn^{3+}	Tetrahedral coordination	210-280	$O^{2-} \rightarrow Mn^{3+}$	[40,43,40]
	Octahedral coordination	311-350	$O^{2-} \rightarrow Mn^{3+}$	[40-45]
Mn^{3+}	Mn_2O_3	450-550	$O^{2-} \rightarrow Mn^{3+}$	[40,41]
		720-750	d-d	[42,46]
Mn^{4+}	MnO_2	350-420	$O^{2-} \rightarrow Mn^{4+}$	[40]
		420	$O^{2-} \rightarrow Mn^{4+}$	[46]
		400-500	$O^{2-} \rightarrow Mn^{4+}$	[44]

3.4. Acidity and reducibility of aerogel catalysts

The acidity and reducibility of catalysts were evaluated by NH_3 -TPD and H_2 -TPR techniques. The recorded curves are displayed in Fig. 4 and Fig. 5, respectively.

As shown in Fig. 4, a broad desorption peak is registered from 100 to 400 °C for all the samples and is assigned to NH_3 desorbed from weak and medium acid sites [30,48-50]. The intensity of this peak is higher in the case of the Mn-TiO₂ sample indicating that the addition of manganese improves significantly the surface acidity of catalytic support. This is in agreement with the results previously obtained by You et al. [51]. The authors concluded that the increase of Mn amount had a positive effect on the acidity of MnOx-CeO₂/GR catalysts and contributes greatly to its high NO-SCR by NH_3 activity. After sulfation of Mn-TiO₂ catalyst, a new peak belonging to NH_3 -desorbed from strong acid sites, generated by sulfate groups, has appeared at high temperature ~ 500 °C [30,31]. It should be mentioned that the addition of cerium induces a decrease of the total acidity (mainly medium and strong ones) of the unsulfated and sulfated Mn based solids. This could be explained by the existence of Mn-Ce and Ce-SO₄²⁻ interactions which inhibits some acidic sites of catalysts.

Figure 4. NH₃-TPD profiles of nanostructured mesoporous aerogel catalysts.

As illustrated in Fig. 5, the H₂-TPR profile of Mn-TiO₂ catalyst shows a single hydrogen consumption peak centered at around 290 °C with a shoulder at ~ 434 °C. According to the literature, the major peak is related to the reduction of surface MnO₂ to Mn₂O₃, while, the shoulder can be ascribed to the reduction of surface Mn₂O₃ to Mn₃O₄ [39]. This means that Mn⁴⁺ species are the most predominant species of manganese at Mn-TiO₂ surface. For Ce-Mn-TiO₂ system, the peak was shifted to higher temperature (~ 325 °C) and its area slightly increases revealing the reduction of manganese at higher temperature in the presence of cerium species. These species seem to be reduced at the same temperature range than manganese and affects its reducibility. The addition of sulfate completely hidden the reduction of other species, since, only one intense peak, corresponding to the reduction of sulfate groups, is detected at ~ 620 °C [30,31,52] in the H₂-TPR profiles of sulfated aerogel catalysts. It is worth noting that the intensity of the peak attributed to the reduction of SO₄²⁻ groups is higher in the case of Ce-Mn-TiO₂-SO₄²⁻ catalyst compared to that of Mn-TiO₂-SO₄²⁻ sample. This can confirm, in line with the UV-vis and NH₃-TPD results, the existence of strong interactions Mn-SO₄²⁻ which most likely affects the nature and oxidation state of Mn species, the dispersion degree of sulfate groups and thereby the NO-SCR activity of the new aerogel catalysts.

Figure 5. H₂-TPR profiles of nanostructured mesoporous aerogel catalysts.

3. 5. SCR performance evaluation

The NO-SCR activity of catalysts were measured as function of temperature and the products were analyzed by a quadruple mass gas spectrometer. It is worth mentioning that N₂O was the major product detected over the unsulfated samples. Nevertheless, the sulfated catalysts are completely selective into N₂.

Fig. 6 shows the NO conversion versus reaction temperature over all the aerogel catalysts. It is clearly seen that TiO₂ support is inactive in the low temperature NO-SCR by NH₃ ($T < 300$ °C) and exhibits a maximum of ~ 50 % NO conversion into N₂ at 500 °C. By contrast, above 75 % of NO conversions into essentially N₂O are obtained, in the 150-270 °C temperature range, over Mn-TiO₂ catalyst. The high catalytic behaviour of this aerogel catalyst in reducing NO into N₂O can be correlated with the predominance of Mn⁴⁺ species at its surface, as suggested from the H₂-TPR and UV-vis results. In fact, it is established that α -Mn₂O₃ is preferred for SCR reaction due to its high selectivity toward N₂ formation. In addition, Liu et al. [26] reported that β -MnO₂ with lower Mn-O bond energy compared to α -Mn₂O₃, can cleave more N-H bonds under NH₃ to form more N-species, resulting in higher selectivity to N₂O. Moreover, Tang et al. [53] showed that higher NO conversion and N₂O selectivity are achieved over β -MnO₂ with respect to α -Mn₂O₃. The addition of cerium slightly increases the NO conversion at

low temperatures which imply that, in this case, manganese are the most active species and their reactivity, in converting NO to N₂O, is slightly affected by the presence of cerium. For these two catalysts, the strong drop of NO conversion above 280°C is due to the ammonia oxidation side reaction. Conversely, the sulfation of catalysts strongly affects their catalytic performances in the NO-SCR reaction. It induces a substantial decrease of the NO conversion at low temperatures (NO conversion < 9 % below 300 °C) but improves obviously the high temperatures SCR activity (NO conversion and N₂- selectivity) of sulfated Mn-TiO₂-SO₄²⁻ and Ce-Mn-TiO₂-SO₄²⁻ catalysts. These systems exhibit approximately a similar catalytic behavior and above 90 % NO conversions into N₂ (100 %) are achieved, between 450 and 500 °C, over the Ce-Mn-TiO₂-SO₄²⁻ aerogel catalyst (Table 4). Noting that, the substantial decrease of the NO conversion at low temperatures accompanied by its notable increase (into N₂) at higher temperatures, observed with sulfate addition, may be attributed to (i) the change of the nature of manganese species, mostly the oxidation state (from Mn⁴⁺ to other forms), which is mainly due to existence of strong interactions Mn-SO₄²⁻, as it was revealed by UV-vis and H₂-TPR techniques, and (ii) the creation of new strong acid sites able to retain NH₃ adsorbed at high temperature, as it was showed by NH₃-TPD analysis. In fact, in NO-SCR by NH₃, it is admitted that NH₄⁺ adsorbed on the Brönsted acid sites plays a major role in NH₃ - SCR reaction at high temperature [9].

Figure 6. NO removal efficiencies over the nanostructured mesoporous aerogel catalysts: [NO] = [NH₃]

= 0.04 % ; [O₂] = 8.00 % and balance with He, (GHSV) = 120 000 h⁻¹.

Table 4. Catalytic behaviour of Mn-TiO₂-SO₄²⁻ and Ce-Mn-TiO₂-SO₄²⁻ nanostructured mesoporous aerogel catalysts calcined at 500 °C in NO-SCR by NH₃: [NO] = [NH₃] = 0.04 %, [O₂] = 8.00 % balance with He and (GHSV) = 120 000 h⁻¹.

Aerogel catalyst	Temperature (°C)	NO Conversion (%)	Selectivity (%)		
			N ₂	N ₂ O	NO ₂
Mn-TiO ₂ -SO ₄ ²⁻	200	2	100	0	0
	250	2	100	0	0
	300	2	100	0	0
	350	28	100	0	0
	400	82	100	0	0
	450	97	100	0	0
	500	100	95	5	0
Ce-Mn-TiO ₂ -SO ₄ ²⁻	200	9	100	0	0
	250	5	100	0	0
	300	6	100	0	0
	350	30	100	0	0
	400	70	100	0	0
	450	91	100	0	0
	500	93	100	0	0

4. Conclusion

In this study, a new series of nanostructured and mesoporous Mn-based catalysts were successfully prepared via the sol gel method combined to supercritical drying for the NO-SCR by NH₃ in a wide temperature range (100-500 °C), under a high GHSV (120 000 h⁻¹). The results reveal that all the obtained aerogel catalysts (Mn-TiO₂, Ce-Mn-TiO₂, Mn-TiO₂-SO₄²⁻ and Ce-Mn-TiO₂-SO₄²⁻) show a developed texture with a good cristallinity of TiO₂ anatase phase. Mn, Ce and SO₄²⁻ were found highly dispersed on the catalyst surfaces and their presence extremely influences the physicochemical and catalytic properties of aerogel solids. Mn-TiO₂ and Ce-Mn-TiO₂ systems display high NO conversions into N₂O at low temperatures, which was correlated with the predominance of Mn⁴⁺ form on their surface. The addition of sulfate modifies the nature of Mn species, acidity and reducibility of Mn-based catalysts and strongly affects their NO-SCR reactivity. High NO conversions into N₂ (above 90 %) are obtained at high temperature over the suflated catalysts.

There are no conflicts of interest to declare

Acknowledgements

The authors wish to express their sincere thanks to Thomas Cacciaguerra for XRD analysis. Financial support by Laboratory of Chemistry of Materials and Catalysis (LCMC) of Tunisia and FrancoTunisian Cooperation (French Institute of Tunisia, SSHN grant) are gratefully acknowledged.

References

- [1] Maleki H, (2016) Recent advances in aerogels for environmental remediation applications. A review Chem Eng J 300: 98-118
- [2] Maleki H, Hüsing N, (2018) Current status, opportunities and challenges in catalytic and photocatalytic applications of aerogels: Environmental protection aspects. Appl Catal B Environ 221: 530-555
- [3] Li J, Chang H, Ma L, Hao J, Yang RT (2011) Low-temperature selective catalytic reduction of NO_x with NH₃ over metal oxide and zeolite catalysts A Review Catal Today 175: 147-156.
- [4] Boningari T, Koirala R, Smirniotis PG, (2012) Low-temperature selective catalytic reduction of NO with NH₃ over V/ZrO₂ prepared by flame-assisted spray pyrolysis: Structural and catalytic properties. Appl Catal B Environ 127: 255-64.
- [5] Liu BT, Huang CJ, Ke YX, Wang WH., Kuo HL, Lin D, Lin V, Lin SH, (2017) Enhanced selective catalytic reduction of NO over Mn-Ce catalysts with the acetic-acid-chelated titania support at low temperature. Appl Catal A Gen 538: 74-80.
- [6] Nam KB, Kwon DW, Hong S C, (2017) DRIFT study on promotion effects of tungsten-modified Mn/Ce/Ti catalysts for the SCR reaction at low-temperature. Appl Catal A Gen 542: 55-62.
- [7] Damma D, Ettireddy PR, Reddy BM, Smirniotis PG, (2019) A Review of Low Temperature NH₃-SCR for Removal of NO_x. Catalysts 9: 349-384.
- [8] Gholami F, Tomas M, Gholami Z, Vakili M, (2020) A Review Technologies for the nitrogen oxides reduction from flue gas. Sci Total Environ 714 :136712-136738
- [9] Gao F, Tang X, Yi H, Zhao S, Li C, Li J, Shi Y, Meng X, (2017) A Review on Selective Catalytic Reduction of NO_x by NH₃ over Mn-Based Catalysts at Low Temperatures , Mechanisms, Kinetics and DFT Calculations. Catalysts 7: 199-231.
- [10] Deng SC, Meng TT, Xu BL, Gao F, Ding Y H, Yu L, Fan YN, (2016) Advanced MnO_x/TiO₂ Catalyst with Preferentially Exposed Anatase {001} Facet for Low-Temperature SCR of NO, ACS catal. 6 : 5807-5815.

- [11] Yao X, Kong T, Chen L, Ding S, Yang F, Dong L, (2017) Enhanced low-temperature NH_3 -SCR performance of $\text{MnO}_x/\text{CeO}_2$ catalysts by optimal solvent effect. *Appl Surf Sci* 420 : 407-415.
- [12] Kijlstra WS, Biervliet M, Poels EK, Blik A, (1998) Deactivation by SO_2 of $\text{MnO}_x/\text{Al}_2\text{O}_3$ catalysts used for the selective catalytic reduction of NO with NH_3 at low temperatures. *Appl Catal B Environ* 16: 327-337.
- [13] Lou XR, Liu PF, Li J, Li Z, He K, (2014) Effects of calcination temperature on Mn species and catalytic activities of Mn/ZSM-5 catalyst for selective catalytic reduction of NO with ammonia. *Appl Surf Sci* 307: 382-387.
- [14] Xu W, Zhang G, Chen H, Zhang G, Han Y, Chang Y, Gong P, (2018) Mn/beta and Mn/ZSM-5 for the low-temperature selective catalytic reduction of NO with ammonia: Effect of manganese precursors. *Chinese J Catal* 39: 118-127.
- [15] Su Y, Fan B, Wang L, Liu Y, Huang B, Fu M, Chen L, Ye D, (2013) MnO_x supported on carbon nanotubes by different methods for the SCR of NO with NH_3 . *Catal Today* 201: 115-121.
- [16] Peña DA, Uphade BS, Smirniotis PG, (2004) TiO_2 -supported metal oxide catalysts for low-temperature selective catalytic reduction of NO with NH_3 : I. Evaluation and characterization of first row transition metals. *J Catal* 221: 421-431.
- [17] Smirniotis PG, Sreekanth PM, Peña DA, Jenkins RG, (2006) Manganese Oxide Catalysts Supported on TiO_2 , Al_2O_3 , and SiO_2 : A Comparison for Low-Temperature SCR of NO with NH_3 , *Ind. Eng. Chem. Res.* 45 : 6436-6443.
- [18] Wu ZB, Jin RB, Liu Y, Wang HQ, (2008) Ceria modified $\text{MnO}_x/\text{TiO}_2$ as a superior catalyst for NO reduction with NH_3 at low-temperature. *Catal Commun* 9:2217-2220.
- [19] Wu ZB, Jin RB, Wang HQ, Liu Y, (2009) Effect of ceria doping on SO_2 resistance of Mn/ TiO_2 for selective catalytic reduction of NO with NH_3 at low temperature. *Catal Commun* 10: 935-939.
- [20] Sheng ZY, Hu YF, Xue JM, Wang XM, Liao WP, (2012) SO_2 poisoning and regeneration of Mn-Ce/ TiO_2 catalyst for low temperature NO_x reduction with NH_3 , *J. Rare Earths* 30: 676-682.
- [21] Sheng ZY, Hu YF, Xue JM, Wang XM, Liao WP, (2012) A novel co-precipitation method for preparation of Mn-Ce/ TiO_2 composites for NO_x reduction with NH_3 at low temperature. *Environ. Technol.* 33:2421-2428.
- [22] Zhou A, Yu D, Yang L, Sheng Z, (2016) Combined effects Na and SO_2 in flue gas on Mn-Ce/ TiO_2 catalyst for low temperature selective catalytic reduction of NO by NH_3 simulated by Na_2SO_4 doping. *Appl Surf Sci* 378: 167-173.

- [23] Wu ZB, Jiang BQ, Liu Y, Zhao WR, Guan BH, (2007) Experimental study on a low-temperature SCR catalyst based on $\text{MnO}_x/\text{TiO}_2$ prepared by sol-gel method. *J Hazard Mater* 145: 488-494.
- [24] Tang C, Zhang H, Dong L, (2016) Ceria-based catalysts for low-temperature selective catalytic reduction of NO with NH_3 . *Catal Sci Technol* 6:1248-1264.
- [25] Xu H, Liu S, Wang Y, Lin Q, Lin C, Lan L, Wang Q, Chen Y, (2018) Promotional effect of Al_2O_3 on $\text{WO}_3/\text{CeO}_2\text{-ZrO}_2$ monolithic catalyst for selective catalytic reduction of nitrogen oxides with ammonia after hydrothermal aging treatment. *Appl Surf Sci* 427: 656-669.
- [26] Liu C, Shi JW, Gao C, Niu C, (2016) Manganese oxide-based catalysts for low-temperature selective catalytic reduction of NO_x with NH_3 A review. *Appl Catal A Gen* 522: 54-69.
- [27] Kapteijn F, Singoredjo L, Andreini A, Moulijn JA, (1994) Activity and selectivity of pure manganese oxides in the selective catalytic reduction of nitric oxide with ammonia. *Appl Catal B Environ.* 3: 173-169
- [28] Kang M, Yeon TH, Park ED, Yie JE, Kim JM, (2006) Novel MnO_x Catalysts for NO Reduction at Low Temperature with Ammonia. *Catal Lett* 106: 77-80.
- [29] Engweiler J, Baiker A, (1994) Vanadia supported on titania aerogels-morphological properties and catalytic behaviour in the selective reduction of nitric-oxide by ammonia. *Appl Catal A Gen* 120:187-205.
- [30] Arfaoui J, Ghorbel A, Petitto C, Delahay G, (2018) Novel $\text{V}_2\text{O}_5\text{-CeO}_2\text{-TiO}_2\text{-SO}_4^{2-}$ nanostructured aerogel catalyst for the low temperature selective catalytic reduction of NO by NH_3 in excess O_2 . *Appl Catal B Environ* 224: 264-275.
- [31] Arfaoui J, Ghorbel A, Petitto C, Delahay G, (2020) A new $\text{V}_2\text{O}_5\text{-MoO}_3\text{-TiO}_2\text{-SO}_4^{2-}$ nanostructured aerogel catalyst for Diesel DeNO_x technology. *New J Chem* 44: 16119-16134.
- [32] Noreen Z, Khalid NR, Abbasi R, Javed S, Ahmad I, Bokhari H, (2019) Visible light sensitive Ag/TiO_2 /graphene composite as a potential coating material for control of *Campylobacter jejuni*. *Mater Sci Eng C* 98 :125-133.
- [33] IUPAC (1985) Reporting physisorption data for gas/solid systems with special reference to the determination of surface area and porosity. *Pure Appl Chem* 57: 603-619.
- [34] Lopez T, Rojas F, Katz RA, Galindo F, Balankin A, Buljanc A, (2004) Porosity, structural and fractal study of sol-gel $\text{TiO}_2\text{-CeO}_2$ mixed oxides, *J. Solid. State Chem.* 177:1873-1885.
- [35] Morishige K, Tateishi N, (2003) Adsorption hysteresis in ink-bottle pore *J Chem Phys* 119: 2301-2306.
- [36] Nguyen PT, Fan C, Do D, Nicholson D, (2013) On the cavitation-like pore blocking in ink-bottle pore: evolution of hysteresis loop with neck size. *J. Phys. Chem. C* 117: 5475-5484.

- [37] López-Mendoza MA, Nava R, Peza-Ledesma C, Millán-Malo B, Huirache-Acuña R, Skewes, Rivera-Muñoz EM, (2016) Characterization and catalytic performance of Co-Mo-W sulfide catalysts supported on SBA-15 and SBA-16 mechanically mixed. *Catal Today* 271: 114-126.
- [38] Awoke Y, Chebude Y, Díaz I, (2020) Controlling Particle Morphology and Pore Size in the Synthesis of Ordered Mesoporous Materials *Molecules* 25 : 4909-4921.
- [39] Know DW, Nam KB, Hong SC, (2015) Influence of tungsten on the activity of a Mn/Ce/W/Ti catalyst for the selective catalytic reduction of NO with NH₃ at low temperatures. *Appl Catal A Gen* 497:160-166.
- [40] Tang Q, Hu S, Chen Y, Guo Z, Hu Y, Chen Y, Yang Y, (2010) Highly dispersed manganese oxide catalysts grafted on SBA-15 Synthesis, characterization and catalytic application in trans-stilbene epoxidation. *Micropor Mesopor Mater* 132: 501-509.
- [41] Mahdavi V, Mardani M, (2015) Preparation of manganese oxide immobilized on SBA-15 by atomic layer deposition as an efficient and reusable catalyst for selective oxidation of benzyl alcohol in the liquid phase. *Mater Chem Phys* 155:136-146.
- [42] Lopez-Benitez A, Berhault G, Guevara-Lara A, (2017) NiMo catalysts supported on Mn-Al₂O₃ for dibenzothiophene hydrodesulfurization application. *Appl Catal B Environ* 213 : 28-41.
- [43] Imran G, Maheswari R, (2015) Mn-incorporated SBA-1 cubic mesoporous silicates: Synthesis and characterization, *Mater. Chem. Phys.* 161 237-242.
- [44] Zhong W, Robert Kirk S, Yin D, Li Y, Zou R, Mao L, Zou G, (2015) Solvent free selective oxidation of toluene by oxygen over MnOx/SBA-15 catalysts: Relationship between catalytic behavior and surface structure. *Chem Eng J* 280: 737-747.
- [45] Anbazhagan N, Imran G, Qurashi A, Pandurangan A, Manimaran S, (2017) Confinement of Mn³⁺ redox sites in Mn-KIT-6 and its catalytic activity for styrene epoxidation. *Micropor Mesopor Mater* 247:190-197.
- [46] Liu G, Sun L, Liu J, Wang F, Guild C, (2017) Aerobic oxidation of primary amines into corresponding nitriles over Mn_xCe_{1-x}O₈ catalysts prepared by co-impregnation method. *J Mol Catal* 440:148-157.
- [47] Larrubia MA, Ramis G, Busca G, (2000) An FT-IR study of the adsorption of urea and ammonia over V₂O₅-MoO₃-TiO₂ SCR catalysts. *Appl Catal B Environ* 72:145-151.
- [48] Jia B, Guo J, Luo H, Shu S, Fang N, Li J, (2018) Study of NO removal and resistance to SO₂ and H₂O of MnOx/TiO₂, MnOx/ZrO₂ and MnOx/ZrO₂-TiO₂. *Appl Catal A Gen* 553: 82-90.
- [49] Ismail R, Arfaoui J, Ksibi Z, Ghorbel A, Delahay G, (2020) Ag/ZrO₂ and Ag/Fe-ZrO₂ catalysts for the low temperature total oxidation of toluene in the presence of water vapor. *Transit Met Chem* 45: 501-509.

- [50] Ismail R, Arfaoui J, Ksibi Z, Ghorbel A, Delahay G, (2020) Effect of the iron amount on the physicochemical properties of Fe-ZrO₂ aerogel catalysts for the total oxidation of toluene in the presence of water vapor. *J Porous Mat* 27: 1847-1852.
- [51] You X, Sheng Z, Yu D, Yang L, Xiao X, Wang S, (2017) Influence of Mn/Ce ratio on the physicochemical properties and catalytic performance of graphene supported MnO_x-CeO₂ oxides for NH₃-SCR at low temperature *Appl. Surf. Sci.* 423: 845-854.
- [52] Liu J, Guo RT, Li MY, Sun P, Liu SM, Pan WG, Liu SW, (2018) Sun X, Enhancement of the SO₂ resistance of Mn/TiO₂ SCR catalyst by Eu modification A mechanism study. *Fuel* 223: 385-393.
- [53] Tang XF, Li JH, Sun L, Hao JM, (2016) Manganese oxide-based catalysts for low-temperature selective catalytic reduction of NO_x with NH₃ A review. *Appl Catal A Gen* 522: 54-69.