Copper disodium tetrahydroxide

A. Riou, Yannick Cudennec, Y. Gerault

► To cite this version:

A. Riou, Yannick Cudennec, Y. Gerault. Copper disodium tetrahydroxide. Acta Crystallographica Section C: Crystal Structure Communications [1968-2013], 1989, 45, pp.374 - 376. 10.1107/s0108270188012508 . hal-03190067

HAL Id: hal-03190067

<https://hal.science/hal-03190067>

Submitted on 6 Apr 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

<https://doi.org/10.1107/S0108270188012508>

Copper Disodium Tetrahydroxide

By A. Riou, Y. Cudennec and Y. Grault

*Laboratoire de Chimie des Matriaux Inorganiques et de Cristallographie, 20 avenue des Buttes de Cosmes
35043 Rennes CEDEX, France*

(Received 18 July 1988, accepted 14 October 1988)

Abstract. $\text{CuNa}_2(\text{OH})_4$, $M_r = 177.55$, orthorhombique, $Pna2_1$, $a = 6.750(3)$, $b = 6.726(5)$, $c = 8.993(5)$ Å, $V = 408.3(7)$, $Z = 4$, $D_x = 2.888$ Mg.m⁻³, $Mo\ K\alpha$, $\lambda = 0.71069$ Å, $\mu = 5.442$ mm⁻¹, $F(000) = 348$, room temperature, $R = 0.030$ for 549 reflections. The structure contains $[\text{NaO}_6]$ octahedra and $[\text{CuO}_4]$ square plane. It can be described as deriving from the NaCl type. 3/4 of the octahedral sites formed by O atoms are occupied by Na or Cu atoms, 1/4 by H atoms. A study of the hydrogen bonds shows that they are very weak.

Introduction. In 1933, Scholder described several new compounds belonging to the ternary system Na_2O , MO , H_2O (M: divalent metal). Since then, several papers have been published; the synthesis was published in 1966 (Scholder and Schwochow, 1966). In all the previous studies, the syntheses gave rise to powders and no crystallographic study has never been mentioned. The chemical formula of these compounds, mostly $\text{Na}_2\text{M}(\text{OH})_4$, was deduced only from chemical analysis. These compounds, which are unstable in air, have never been obtained for other alkali metals.

In a recent paper (Cudennec, Lecerf, Riou and Gerault, 1988), we proposed a new method of synthesis for one compound belonging to these systems: $\text{Na}_2\text{Cu}(\text{OH})_4$. This method made possible the growth of crystals; therefore a complete crystallographic study became possible. This paper reports the results of the structure determination and discusses peculiar properties.

Experimental. As stated in our previous publication, crystals of $\text{Na}_2\text{Cu}(\text{OH})_4$ were prepared from a system containing 1 mol of CuO , 10 mol of NaOH and 40 mol of H_2O . The mixture was placed in a dry box using KOH at room temperature for several weeks to be slowly dehydrated and protected from CO_2 . Well formed blue octahedral-shaped crystals appeared, of average size about 0.1 mm. Crystals could not be isolated and washed because of their instability; therefore, for all the crystallographic studies, small single crystals were quickly sealed inside a 0.3 mm Lindemann-glass capillary. A suitable crystal (0.1 x 0.1 x 0.1 mm) was mounted on an Enraf-Nonius CAD-4 diffractometer. Unit-cell constants were determined from a preliminary study by the photographic method and then refined on the basis of 25 carefully centred reflections in the angular range $2 < 2\theta < 32^\circ$. Data were collected in the ω - 2θ scan mode, with ω scan width $(2.00 + 0.45 \tan\theta)^\circ$ and scan amplitude $(1.00 + 0.35 \tan\theta)$ mm; $\theta_{\text{max}} = 25^\circ$. 1603 reflections were measured which were merged to a unique set of 860, $R_{\text{int}} = 0.031$, of these, 549 were regarded as observed reflections according to $I > \sigma(I)$. Data were corrected for Lorentz and polarization effects, no absorption correction was applied. A periodic check of 3 standard reflections showed no significant intensity variation. The

hkl range was $0 \leq h \leq 10$; $0 \leq k \leq 10$; $0 \leq l \leq 13$. The structure was solved by direct methods and the positions of one Cu, one Na and three O atoms belonging to the asymmetric unit were deduced from one of the most probable E maps. The structure was completed from successive Fourier and difference Fourier maps. Full-matrix least-squares refinement was based on F and the function minimized was $\Sigma w(|F_o| - |F_c|)^2$, where $w(F) = 1/\sigma^2(F)$. For the seven non-H atoms, which were assigned anisotropic thermal parameters, the refinement converged to $R = 0.050$ and $wR = 0.056$ for all observed data. At this stage a difference Fourier map revealed the positions of the four H atoms. Further refinement including the H atoms led to a final R value of 0.030 and $wR = 0.031$. The H atoms were refined isotropically. The weighting scheme was a non-Poisson contribution with $p = 0.050$. Corrections were made for anomalous-dispersion and secondary-extinction effects, $g = 1.86 \times 10^{-7}$. During the last refinement cycle, the r.m.s. shift/e.s.d. was 0.05. The final difference Fourier map showed no features higher than $0.8 \text{ e } \text{\AA}^{-3}$. All crystal structure analyses and refinements were carried out on a PDP 11/60, using the SDP package (Frenz, 1978). Scattering factors were from Cromer & Waber (1965)*.

Discussion. *Coordination polyhedra.* Final atomic coordinates and equivalent isotropic temperature factors are given in Table 1. Fig. 1 shows a view of the unit cell of $\text{Na}_2\text{Cu}(\text{OH})_4$. Bond lengths and angles are given in Table 2. The structure contains one crystallographic Cu site and two distinct Na sites. The coordination of the Cu atom in the structure is fourfold square planar.

Cu is coordinated by four O atoms belonging to OH groups. The average distance is 1.964 Å with values in the range 1.929–2.021 Å. Two O atoms, more distant from Cu, complete a very distorted octahedron. Nevertheless, these two O atoms, whose distances from Cu are 2.749 and 2.883 Å, are very weakly linked. Na(1) and Na(2) atoms are each coordinated by six atoms in the form of distorted octahedra. Na(1) displays Na–O distances in the range 2.286–2.569 Å with a mean value of 2.403 Å. Na(2) shows a less-distorted octahedron than Na(1). The average Na(2)–O distance is 2.461 Å with values in the range 2.404–2.537 Å.

Hydrogen bonding. The geometrical features of expected H bonds are given in Table 2. Distances and angles involving the H atoms are satisfactory. H(O1), which is attached to O(1), forms an H bond with O(2) which is 2.05 Å distant from it. This H bond, which deviates significantly from linearity [$\text{O}(1)\text{--H}(\text{O}1)\text{---O}(2) = 160^\circ$], must be considered as relatively weak. Nevertheless, this is the strongest one in the structure. H(O2) forms a very weak H bond with O(1) which is 2.18 Å distant from it. As shown in Table 2, H(O3) and H(O4) are too far from their nearest neighbours O(1) and O(2) to allow H-bond formation. The present results are in good agreement with the IR study. The IR spectrum displays effectively four absorption bands corresponding to the four distinct hydroxyl groups. Of these, two are slightly shifted to the low frequencies (3525 and 3490 cm^{-1}) whereas the two other bands are not significantly shifted (3600 and 3570 cm^{-1}).

Crystal packing. As suggested in Fig. 1, the four distinct O atoms present in the $\text{Na}_2\text{Cu}(\text{OH})_4$ structure are also sixfold coordinated in the form of very distorted octahedra. These octahedra are built of Na, Cu and H cations. O(1) and O(2) environments are similar; their nearest neighbours are one Cu, three Na and two H atoms. One of the H atoms surrounding O(1) or O(2) corresponds to an H bond where the atoms O(1) and O(2) are acceptors. The distorted octahedra surrounding O(3) and O(4) involve two Cu, three Na and one H atoms. In this case, one of the two Cu atoms is very weakly linked to the corresponding O(3) or O(4) atom. The similarity between Na, Cu and O octahedral environments suggests that $\text{Na}_2\text{Cu}(\text{OH})_4$ is derived from the NaCl-type structure.

The structure is built of atomic rows parallel to $|110|$, $|1\text{--}10|$ and $|001|$ axes. These rows form networks respectively parallel to (100), (1-10) and (001) planes. They are constituted of cations alternating with O atoms. There are three types of rows forming the networks parallel to (110) or (1-10) planes. In this case, the atoms appear in the following order:

...Cu...O...Cu...O...
 ...Na...O... $\square$...O...
 ...Na...O...Na...O...

On the other hand, the networks parallel to (001) involve two types of rows corresponding to:

...Cu...O...Na...O...

...Na...O...□...O...

The symbol □ represents an octahedral site occupied by four H atoms.

Each atom occupies an octahedral site as in the NaCl structure, but an important difference is the presence here of an "octahedral hole" occupied by four H atoms. All the H atoms are thus confined inside an octahedral hole. So if we consider the four octahedral sites reserved for the cations, three are occupied by Cu or Na atoms and the fourth by the H atoms. If we now compare the structure of Na₂Cu(OH)₄ with that of NaOH, it appears that the new compound is more nearly the NaCl type. The structure of NaOH, stable at room temperature, is built up of slices of the NaCl structure in which Na has five nearest neighbours at five of the vertices of an octahedron, whereas Na₂Cu(OH)₄ contains sixfold-coordinated Na atoms. Another difference between these structures is that Na-O-H bonds are collinear in NaOH while the mean angle for Na-O-H bonds in Na₂Cu(OH)₄, is 144°.

Structural instability. One of the principal features of the compound studied is its poor stability. There are probably several explanations for this but the presence of four H atoms confined to a narrow octahedral site is undoubtedly the main reason. Moreover, it is probable that the ionic radius, and consequently the nature of the alkali atom, determines the size of the "octahedral hole", available to the H atoms. This could be the reason why alkali hydroxymetallates M₂^IM^{II}(OH)₄ have been obtained only for sodium.

* Lists of structure factors and anisotropic thermal parameters have been deposited with the British Library Document Supply Centre as Supplementary Publication No. SUP 51496 (6 pp.). Copies may be obtained through The Executive Secretary, International Union of Crystallography, 5 Abbey Square, Chester CH1 2HU, England.

References

- CROMER, D. T. & WABER, J. T. (1965). *Acta Cryst.* **18**, 104–109.
CUDENNEC, Y., LECERF, A., RIOU, A. & GERAULT, Y. (1988). *Eur. J. Solid State Inorg. Chem.* In the press.
FRENZ, B. A. (1978). *The Enraf-Nonius CAD-4 SDP – A Real-Time System for Concurrent X-ray Data Collection and Crystal Structure Solution*. In *Computing in Crystallography*, edited by H. SCHENK, R. OLTROP-HAEZKAMP, H. VAN KONINGSVELD & G. C. BASSI, pp. 64–71. Delft Univ. Press.
SCHOLDER, R. & SCHWOCHOW, F. (1966). *Angew. Chem. Int. Ed. Engl.* **5**(12), 1047.

Table 1. *Final atomic coordinates and equivalent isotropic temperature factors for Na₂Cu(OH)₄*

$$B_{eq} = \frac{1}{3} \sum_i \sum_j \beta_{ij} a_i \cdot a_j$$

	x	y	z	$B_{eq}(\text{\AA}^2)$
Cu	0.26417 (5)	0.00723 (6)	0.000	0.793 (6)
Na(1)	0.5007 (3)	0.7148 (3)	0.7539 (3)	1.26 (3)
Na(2)	0.2558 (2)	0.0060 (2)	0.4950 (4)	1.25 (2)
O(1)	0.2623 (4)	0.0113 (4)	0.7753 (4)	1.37 (6)
O(2)	0.2827 (5)	0.9925 (4)	0.2137 (4)	1.43 (6)
O(3)	0.0538 (4)	0.8078 (4)	0.0044 (4)	1.08 (4)
O(4)	0.4643 (4)	0.2164 (4)	0.0059 (3)	1.05 (4)
H(O1)	0.58 (1)	0.96 (1)	0.240 (9)	4.0*
H(O2)	0.25 (1)	0.33 (1)	0.74 (1)	4.0*
H(O3)	0.499 (9)	0.24 (1)	0.60 (1)	4.0*
H(O4)	0.50 (1)	0.25 (1)	0.91 (1)	4.0*

* Atoms refined isotropically, $B = 4.0 \text{ \AA}^2$.

Table 2. *Selected bond distances (Å) for Na₂Cu(OH)₄ and hydrogen-bonding geometry*

Cu—O(1)	2.021 (3)	Na(2)—O(1)	2.522 (5)	
Cu—O(2)	1.929 (3)	Na(2)—O(2)	2.537 (5)	
Cu—O(3)	1.954 (3)	Na(2)—O(3)	2.438 (3)	
Cu—O(3)	2.883 (3)	Na(2)—O(3)	2.404 (3)	
Cu—O(4)	1.951 (3)	Na(2)—O(4)	2.412 (3)	
Cu—O(4)	2.749 (3)	Na(2)—O(4)	2.452 (3)	
Na(1)—O(1)	2.569 (3)	O(1)—H(O1)	1.12 (9)	
Na(1)—O(1)	2.339 (3)	O(2)—H(O2)	1.13 (10)	
Na(1)—O(2)	2.479 (4)	O(3)—H(O3)	1.04 (10)	
Na(1)—O(2)	2.455 (4)	O(4)—H(O4)	0.94 (10)	
Na(1)—O(3)	2.286 (5)			
Na(1)—O(4)	2.291 (4)			
O—H...O	O—H (Å)	H...O (Å)	O—H...O (°)	O...O (Å)
O(1)—H(O1)...O(2)	1.12 (9)	2.05 (9)	160. (6)	3.121 (5)
O(2)—H(O2)...O(1)	1.13 (10)	2.18 (10)	170. (7)	3.298 (5)
O(3)—H(O3)...O(2)	1.04 (10)	2.39 (7)	147. (7)	3.313 (5)
O(4)—H(O4)...O(1)	0.94 (10)	2.67 (8)	137. (6)	3.421 (5)

Fig. 1. The unit cell of $\text{CuNa}_2(\text{OH})_4$.