ON-state reliability of GaN-on-Si Schottky Barrier Diodes: Si₃N₄ vs. Al₂O₃/SiO₂ GET dielectric

Eliana Acurio, Lionel Trojman, Brice de Jaeger, Benoit Bakeroort, Stefaan Decoutere

► To cite this version:

Eliana Acurio, Lionel Trojman, Brice de Jaeger, Benoit Bakeroort, Stefaan Decoutere. ON-state reliability of GaN-on-Si Schottky Barrier Diodes: Si₃N₄ vs. Al₂O₃/SiO₂ GET dielectric. IEEE International Reliability Physics Symposium (IRPS 2021), Mar 2021, Monterey (virtual conference), United States. pp.1-6, 10.1109/IRPS46558.2021.9405163 . hal-03218246

HAL Id: hal-03218246

<https://hal.science/hal-03218246>

Submitted on 5 May 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

ON-state reliability of GaN-on-Si Schottky Barrier Diodes: Si_3N_4 vs. $\text{Al}_2\text{O}_3/\text{SiO}_2$ GET dielectric

Eliana Acurio
Physics Department, IMNE
Escuela Politécnica Nacional,
Universidad San Francisco de Quito
Quito, Ecuador
eliana.acurio@epn.edu.ec

Lionel Trojman
LISITE, IMNE
Institut d'Electronique de Paris Isep,
Universidad San Francisco de Quito
Paris, France; Quito, Ecuador
lionel.trojman@isep.fr

Brice de Jaeger
imec
Leuven, Belgium
Brice.DeJaeger@imec.be

Benoit Bakeroot
CMST
imec & Ghent University
Ghent, Belgium
Benoit.Bakeroot@ugent.be

Stefaan Decoutere
imec
Leuven, Belgium
Stefaan.Decoutere@imec.be

Abstract—The degradation of Schottky Barrier Diodes (SBDs) with a Gated Edge Termination (GET) under on-state stress conditions is studied for a 650 V GaN-on-Si technology. Reliability metric techniques previously used in MOS-HEMTs are applied in this work due to similar MIS gate stack architecture in GET-SBDs. In these techniques, the density of traps (ΔN_{OT}) is analyzed in GET structures where the dielectric is either Si_3N_4 (nitride-based) or a stack of $\text{Al}_2\text{O}_3/\text{SiO}_2$ (oxide-based). Statistical analysis across both wafers indicates some systematic differences in turn-on voltage degradation (ΔV_{TON}) depending on wafer location, likely caused by process-related variations. Under 1000 s stress time and ON-state voltage, the number of trapped charges in nitride-based dielectric devices keeps increasing. This suggests an ongoing dielectric degradation. On the other hand, $\text{Al}_2\text{O}_3/\text{SiO}_2$ dielectric devices with an Al-based interfacial layer (IL) exhibit less process-induced variability across the wafer along with a lower density of trapped charges compared with nitride-based dielectric diodes under the same stress conditions suggesting better reliability and process improvement.

Index Terms-- de-trapping, GaN, interfacial layer, nitride, on-state, oxide, trapping rate.

I. INTRODUCTION

The rapid development of power electronics applications requires advanced devices to improve the efficiency and the power density of conversion systems. In the last years, devices based on gallium nitride (GaN) have been considered attractive and promising in this field due to their wide bandgap (~ 3.4 eV) and high values of breakdown voltage ($\sim 3\text{MV/cm}$), saturation velocity, sheet carrier density, and electron mobility in the 2-D electron gas (2-DEG) quantum well formed at the AlGaIn/GaN heterojunction [1]. Despite the potential of this material, its widespread adoption in the power market is still limited due to reliability issues that are not yet fully understood. Several studies have been performed in different GaN-based structures to comprehend the degradation phenomena and to analyze long-term reliability [2], [3], [4].

However, the lack of consensus about the failure mechanisms needs more research on this topic.

Some of the requirements of GaN-based power diodes include high breakdown voltage (V_{BD}) and low values of turn-ON voltage (V_{TON}), specific ON-resistance ($R_{\text{ON,sp}}$), and reverse leakage current. Therefore, several processing approaches have been implemented to improve the performance of GaN-on-Si rectifiers. One of these is the introduction of a Si_3N_4 layer at the corner of the Schottky contact to create a gated edge termination (GET) that reduces the electric field peak in this corner and the reverse current [5]. Reliability improvements under OFF-state stress conditions have been obtained in this structure by thinning the passivation layer and by employing a more aggressive pre-clean process based on sulfuric acid and hydrogen peroxide mixture (SPM) and ammonia and hydrogen peroxide mixture (APM) [6]. This improved structure was fabricated in a 200-V GaN-on-Si platform and tested under ON-state stress conditions. The results demonstrated a recoverable behavior with better reliability and longer lifetime expectation compared to previous works in 200-V technology [7]. Although promising results were obtained, a clear method to link the process to the reliability in ON-state regime is missing. This makes the analysis highly dependent on the fabrication instead of physics mechanisms.

This paper aims to study the reliability of the aforementioned improved structure for 650V GaN technology. It is worth reminding that the GET resembles a metal-insulator-semiconductor structure bringing about material compatibility concerns at the semiconductor AlGaIn-barrier/dielectric interface. In-situ defects at this interface may be critical as in MOS-like devices (MOSFET or MOS-HEMT) [2], [8]. Therefore, it is reasonable to apply reliability techniques (e.g. positive bias temperature instability-PBTI) and metrics like the ones successfully applied to MOSFETs. By using these metrics, it is possible to assess the number of defect centers in the insulator/oxide layer or far from the interface. More specific estimation of interface defects require

Fig. 1. Simplified schematics of (a) GET-SBDs used for ON-state stress analysis. Gate stack architecture with Si₃N₄ (b) and Al₂O₃/SiO₂ (c).

other techniques [9], [10], and are not included in this work. We also show a comparative study of this architecture by using a nitrogen-based dielectric made of 45 nm of Si₃N₄ and an oxide-based dielectric made of 35 nm of SiO₂ deposited onto an interfacial layer of Al₂O₃ (2.5 nm).

The remainder of this paper is organized as follows. Section II presents details of the devices under test. Section III explains the experimental procedure. ON-state stress results are discussed in Section IV. Finally, the conclusions of this paper are summarized in Section V.

II. DEVICE FABRICATION

The schematic structure of the AlGaIn/GaN diodes studied in this paper is depicted in Fig. 1(a). The epitaxial stack is grown on a Si (111) substrate by means of metal-organic chemical vapour deposition (MOCVD). It features a thick superlattice buffer designed for a 650-V platform technology with a 300-nm-thick GaN channel, a 0.5-nm-thick AlN spacer, a 10-nm-thick Al_{0.25}Ga_{0.75}N barrier, and a 5-nm-thick SiN cap. The epitaxial stack is passivated with a SiO₂ layer using high-temperature oxide deposition.

In the anode region, the passivation layer is removed by dry etch and the barrier is recessed by about ~6nm using atomic layer etching. The GET reference structure has a nitrogen (N)-based dielectric, which is formed by depositing a 45-nm-thick Si₃N₄ layer by means of plasma-enhanced atomic layer deposition (PEALD). A subsequent opening by dry etching in the central region defines the actual Schottky contact with a length L_{sc} = 4 μm, an edge termination length L_{g1} = 2 μm and an anode-to-cathode distance L_{ac} = 16 μm as illustrated in Fig. 1(b). An Au-free TiN-based metal stack is then deposited and etched to form the Schottky contact at the anode region [5]. Finally, the ohmic contacts are processed using a Ti/Al-based metal stack with an alloying temperature of 565 °C.

For this comparative study, a second wafer was fabricated with a bilayer in the GET region, which includes an oxide (O)-based dielectric as shown in Fig. 1(c). For this structure, a 2.5-nm-thick interfacial layer (IL) of Al₂O₃ was deposited by atomic layer deposition followed by a 35-nm-thick layer of SiO₂ deposited by means of plasma-enhanced chemical vapour deposition (PECVD).

Fig. 2. Total ΔV_{TON} after 1000s of stress at 150°C and the recovery of the initial state after a thermal de-trapping (TD) process at 300°C in Si₃N₄ and Al₂O₃/SiO₂ dielectric devices.

Fig. 3. Schematic model to obtain C_{eff} which is 0.18 μF/cm² and 0.13 μF/cm² for Si₃N₄ and Al₂O₃/SiO₂, respectively.

III. EXPERIMENTAL PROCEDURE

The technique to assess the dielectric reliability for GET-SBDs starts with an initial stabilization phase in which a voltage (6V) is applied at high temperature (150 °C) followed by a thermal de-trapping (TD) with floating contacts at 300 °C. This procedure releases charges originally trapped in defect centers within the GET dielectric and captures the real degradation under the stress conditions. It is worth noting that the I-V curves almost overlap the fresh I-V curves (not shown for the sake of brevity) after the stabilization for the Al₂O₃/SiO₂ devices, which indicates lower amount of initially trapped charges. Subsequently, during the stress phase, the devices are biased with a positive anode-to-cathode stress voltage (V_{stress}) ranging between 4 V and 7 V. To capture the degradation, the stress was interrupted at fixed time intervals (Measure-Stress-Measure technique MSM) up to 1000 s. An I-V curve was measured and compared with the fresh (reference) one obtained in the stabilization phase to calculate the ON-state threshold voltage shift (ΔV_{TON}), which for these structures is always positive indicating an electron trapping process. Finally, the thermal-de-trapping process (300 °C) is applied again to release the trapped charges during the stress and to prepare devices for subsequent experiments. It is worth highlighting that after the thermal de-trapping (TD) process following the stress phase, the diodes can almost completely recover from the stress-induced degradation during the experiments. A small non zero ΔV_{TON} is observed in Fig. 2 and could be explained by a permanent component residue. This procedure was performed in 64 diodes across the wafers.

The ΔV_{TON} is directly related to the trapped charge density ΔN_{OT} through:

Fig. 4. Weibull distributions of ΔV_{TON} at $V_{stress}=6V$ and $T=150^\circ C$ in Si_3N_4 dielectric devices. Two trends are observed depending on the wafer location.

Fig. 5. Weibull scale parameter of ΔV_{TON} ($\Delta V_{TON,\eta}$) obtained under different stress voltages as function of the stress time for (a) Si_3N_4 and (b) Al_2O_3/SiO_2 diodes, respectively. These measurements were performed at $150^\circ C$.

$$\Delta N_{OT} = (C_{eff} * \Delta V_{TON})/q \quad (1)$$

where C_{eff} is the effective capacitance per unit area that has been obtained with the electrical model in Fig. 3 and q is the elementary charge. This model focuses on the region around V_{TON} where the capacitance remains fixed [11].

IV. RESULTS AND DISCUSSION

The degradation results under ON-state stress show two different probability trends according to the wafer location. An approximately twice higher degradation is observed on the west side compared to the east side of the wafer, which can be attributed to process-induced or systematic variability under large forward stress. Indeed, stress voltages from 4V to 7V were applied to the anode-cathode contact which is well above the usual operating forward voltage for these devices, namely $V_F=1.83$ V and 1.74V for the N-based and O-based dielectric devices, respectively. More explanation about this observation was reported in our previous work [7]. In both cases, a Weibull distribution is found to fit well the data. Fig. 4 shows

Fig. 4. (a) Time exponent n and (b) ΔN_{OT} as a function of the $V_{OV, stress}$.

an example for a stress voltage $V_{stress}=6V$. Similar results were obtained for all experiments.

A. Nonlinear dependence model

From the Weibull distributions, the scale parameter (η) is plotted vs. stress time in Fig. 5 ($\Delta V_{TON,\eta}$) for different stress conditions. Large forward stress in the ON-state regime produces ΔV_{TON} shifts in the range from 5 to 100 mV. $\Delta V_{TON,\eta}$ was observed to follow a power law of the stress time and stress overdrive voltage and the data fit well with the model proposed in [8]:

$$\Delta V_{TON,\eta} = A_0 \cdot V_{OV, stress}^\gamma \cdot t_{stress}^n \quad (2)$$

where A_0 is the prefactor, n is the time exponent, γ is the voltage dependence exponent and $V_{OV, stress}$ is the difference between the stress voltage and the initial measured V_{TON} :

$$(V_{OV, stress} = |V_{stress} - V_{TON, initial}|). \quad (3)$$

As depicted in Fig. 6 (a), the extracted time exponent n exhibits a decreasing behavior with $V_{OV, stress}$ independently of the GET dielectric Si_3N_4 or Al_2O_3/SiO_2 . Moreover, its range agree with BTI reports in different technologies [8], [12], [13].

The trapped charge density ΔN_{OT} is extracted after 1-s stress in Fig 6 (b), by using (1). The value of the voltage dependence exponent γ about 1 (east side) and 1.15 (west side) suggests the existence of a wide distribution of defect levels centered around the channel Fermi level [8]. This indicates similar accessibility to the dielectric defects in both types of GET dielectrics.

It is worth mentioning that ΔV_{TON} evolution during the stress can also be expressed by using a semi empirical model [13]:

Fig. 7. Arrhenius plots of ΔV_{TON} on (a) west- and (b) east-side devices. The ΔV_{TON} values were extrapolated when the devices were stressed at 4V for 1s.

Fig. 8. ΔN_{OT} as a function of temperature on (a) west- and (b) east-side devices.

$$\Delta V_{TON,\eta} \approx \exp(-E_A/k_B T) (V_{OV, stress}/t_{ox})^\gamma t_{stress}^n \quad (4)$$

The apparent ΔV_{TON} activation energies are extracted by fitting an exponential trend in the Arrhenius plots as depicted in Fig. 7. To assess the mean activation energy of the charge capture process, it is necessary to consider the time to reach a given ΔV_{TON} . Therefore, the apparent activation energy is divided for the time exponent n . The mean activation energies

Fig. 9. ΔN_{OT} as a function of stress voltage on (a) west- and (b) east-side devices.

in west-side devices were estimated to be -0.072/-0.014 eV (n is 0.139/0.140) for Si_3N_4 and $\text{Al}_2\text{O}_3/\text{SiO}_2$ GET dielectrics, respectively. In the case of east-side devices, the values were 0.384/0.073 eV (n is 0.130/0.138).

By considering the database of the deep levels in GaN- and AlGaN-based devices [14], such low values can be ascribed to nitrogen vacancies. The relatively high value of 0.384 eV in Si_3N_4 devices in the east side can be possibly related to AlGaN surface.

Temperature and stress voltage conditions in Fig. 8 and 9, respectively, show different reliabilities and variabilities depending on the GET dielectric. For the Si_3N_4 GET-SBDs, ΔN_{OT} is lowered for the east-side devices suggesting a de-trapping phenomenon enhanced by temperature while the west-side devices show the opposite trend. On the other hand, the temperature has a low influence in the trapping and de-trapping process in $\text{Al}_2\text{O}_3/\text{SiO}_2$ dielectric independently of the side of the wafer. As a result, the Si_3N_4 dielectric produces more trapping phenomena with larger variability than $\text{Al}_2\text{O}_3/\text{SiO}_2$ devices under the same stress conditions (Fig. 8 and 9), yet with similar activation energies as previously shown in Fig. 7.

B. Trapping rate parameter analysis

To gain insight into the ΔV_{TON} behavior for these different devices, the time exponent n is evaluated as a function of the stress time:

$$n(t_{stress}) = b = \partial \log \Delta V_{TON} / \partial \log t_{stress} \quad (5)$$

where b is the so-called *trapping rate* or *b-parameter* [2].

The b -parameter measures the evolution of the ratio between the trapping and de-trapping mechanisms under

Fig. 10. b -parameter as a function of the ΔN_{OT} in (a) Si_3N_4 and (b) $\text{Al}_2\text{O}_3/\text{SiO}_2$ GET-SBDs. Stress voltage and stress temperature experiments were performed at 150 °C and 4V, respectively.

given stress voltage and temperature conditions. This parameter is plotted in Fig. 10 as a function of the defect density (ΔN_{OT}) for all stress conditions. As illustrated in Fig. 10 (a), the Si_3N_4 devices have a significant variability across the wafer. The west-side devices exhibit larger trapping density compared to the east side (maximum of around $4 \cdot 10^{10} \text{ cm}^{-2}$) and this density even increases with larger stress voltages (6-7V) and temperatures, which indicates further trapping of charges under these stress conditions. This different behavior between east- and west-side devices confirms the variability of the wafer observed in the first place.

For $\text{Al}_2\text{O}_3/\text{SiO}_2$ devices, Fig. 10 (b) shows much more uniformity or less variability across the wafer. The ΔN_{OT} is limited to a fixed value of about $2\text{-}3 \cdot 10^{10} \text{ cm}^{-2}$. A somewhat lower density of traps is reached for the east-side devices.

It is important to mention that an important ΔN_{OT} increase (kink) under harsh stress conditions, especially in Si_3N_4 -devices located on the west side, is observed in Fig. 10 (a). This indicates that the amount of trapping keeps increasing with the stress time, voltage, and temperature. In this case, this ongoing increase could suggest either deeper trapping in the dielectric material or creation of defects at the dielectric interface or within the dielectric. Although the devices exhibit an apparent recoverable behavior, where the creation of defects is not conceived, we cannot discard the possibility of a permanent degradation component that under high temperature (from 300 °C) of the thermal de-trapping process can be reversed or “baked away” [15].

Fig. 11. ΔN_{OT} comparison between wafer sides under stress voltage conditions between Si_3N_4 and $\text{Al}_2\text{O}_3/\text{SiO}_2$ dielectric GET-SBDs. Lower density of traps and variability are observed for the metal-oxide bilayer.

On the contrary, for the $\text{Al}_2\text{O}_3/\text{SiO}_2$ devices on the west side, the ΔN_{OT} kink is less prominent suggesting that the deep trapping in the oxide is limited by the temperature de-trapping process which is more efficient than for the Si_3N_4 devices (Fig. 8 (a)).

In the east-side devices independently of the GET dielectric, ΔN_{OT} saturates at high-stress voltages and decreases at high temperatures (Fig. 8 and 9). Therefore, it is possible to say that pre-existing defects at the interface/dielectric can be saturated with electrons. The longer the stress time applied, the larger the number of trapped charges. At some point, the dielectric interface cannot trap any more electrons due to the de-trapping process enhanced by temperature or trapped electrons that prevent further trapping of charges within or at the border of the dielectric [16], [17].

Fig. 11 proposes a metric summarizing the specificity of the two different dielectric materials: stress voltage dependence, trapping/de-trapping rate and interface quality. It shows important correlations between the ΔN_{OT} increase, the trapping rate, and the variability across the wafer. For the same b -parameter values, ΔN_{OT} is lower for $\text{Al}_2\text{O}_3/\text{SiO}_2$ compared to Si_3N_4 GET dielectric. From low to large stress conditions, it can be noted that the variability is increased as demonstrated by the increased data scattering for large ΔN_{OT} , especially for the Si_3N_4 dielectric. Also, and more importantly, under larger stress voltage (7V), the $\text{Al}_2\text{O}_3/\text{SiO}_2$ devices do not increase ΔN_{OT} as it is the case of the Si_3N_4 devices, especially in west-side devices. It is worth mentioning that the amount of trapping for both dielectrics remains low: even for the Si_3N_4 with larger variability, ΔN_{OT} stays below 10^{11} cm^{-2} under large forward stress voltage.

For both types of dielectrics, we assume that the defects are mostly located at the dielectric /AlGaN interface. Indeed, we can suggest that the increase of trapped electrons indicates deeper trapping in the dielectric or a generation of defects that must be located in a region of the gate dielectric which exhibits weak atomic bonds. This can be a material defect where the atomic compatibility is not fully ensured. For instance, the trapped electrons on the interface could build a

Fig. 12. Line profile of the absolute electric field within the AlGaIn barrier (3 nm below the top surface in the recessed portion) for N-based and O-based dielectric GET-SBDs. The IL helps reducing the electric field at the gate.

potential barrier preventing deep trapping inside the dielectric. Therefore, we can also speculate that a constant increase of the amount of defects is present at the bottom of the gate dielectric (namely the interface with the AlGaIn Barrier). Although these defects may be located at the interface between two materials, they are still considered as bulk or dielectric defects since they are far from the place where the current (AlGaIn/GaN) is flowing. In the case of an oxide-base dielectric, an interfacial layer (IL) of Al_2O_3 is deposited on the AlGaIn. Based on the reliability results in Fig. 11, we speculate that the Al_2O_3 IL deposited before the SiO_2 may enable better compatibility between the SiO_2 and the AlGaIn barrier, and this is likely related to the use of Al. This explains again why for large stress voltages, there is almost no generation of defects or deeper dielectric trapping at the $\text{Al}_2\text{O}_3/\text{AlGaIn}$ interface compared to the $\text{Si}_3\text{N}_4/\text{AlGaIn}$ one.

Finally, the use of O-based IL seems also to reduce the peak of the electric field intensity at the AlGaIn barrier according to the TCAD simulation as shown in Fig. 12. It may somewhat also improve the b-parameter reduction under large stress voltage. This can also be related to the use of higher-k value IL as suggested in the case of MOS-HEMTs [18].

V. CONCLUSIONS

In this paper, we have presented the results of ON-state stress degradation in AlGaIn/GaN SBDs fabricated in a 650 V technology with either N-based or O-based GET dielectrics. A nonlinear dependence model and the change in density of traps (ΔN_{OT}) are used as reliability metrics in this work. The choice of the GET dielectric and the resulting properties of the GET dielectric/AlGaIn interface are proven to be critical. Results suggest that the GET dielectric region is where the generation of defects or deeper charge trapping under high voltage stress conditions could take place. A reduced ΔN_{OT} for the process involving the O-based dielectric with Al_2O_3 IL is observed compared to the N-based dielectric. Better uniformity of the results across the wafer and a more stable maximum of ΔN_{OT} for large stress voltage (up to 7V) are also observed. Therefore, $\text{Al}_2\text{O}_3/\text{SiO}_2$ dielectric yields better

reliability and lower variability across the wafer suggesting a better quality of the AlGaIn-barrier/dielectric interface and more uniform process control than with Si_3N_4 dielectric. It makes ALD $\text{Al}_2\text{O}_3/\text{PECVD SiO}_2$ dielectric a more attractive option for the 650V AlGaIn/GaN SBDs technology.

REFERENCES

- [1] O. Ambacher *et al.*, "Two-dimensional electron gases induced by spontaneous and piezoelectric polarization charges in N- and Ga-face AlGaIn/GaN heterostructures," *J. Appl. Phys.*, vol. 85, no. 6, pp. 3222–3233, Mar. 1999, doi: 10.1063/1.369664.
- [2] E. Acurio, F. Crupi, P. Magnone, L. Trojman, G. Meneghesso, and F. Lucolano, "On recoverable behavior of PBTI in AlGaIn/GaN MOS-HEMT," *Solid. State. Electron.*, vol. 132, pp. 49–56, Jun. 2017, doi: 10.1016/j.sse.2017.03.007.
- [3] E. Acurio *et al.*, "Reliability in GaN-based devices for power applications," in *2018 IEEE Third Ecuador Technical Chapters Meeting (ETCM)*, 2018, pp. 1–6, doi: 10.1109/ETCM.2018.8580263.
- [4] M. Meneghini *et al.*, "Extensive Investigation of Time-Dependent Breakdown of GaN-HEMTs Submitted to OFF-State Stress," *IEEE Trans. Electron Devices*, vol. 62, no. 8, pp. 2549–2554, Aug. 2015, doi: 10.1109/TED.2015.2446032.
- [5] S. Lenci *et al.*, "Au-Free AlGaIn/GaN Power Diode on 8-in Si Substrate With Gated Edge Termination," *IEEE Electron Device Lett.*, vol. 34, no. 8, pp. 1035–1037, Aug. 2013, doi: 10.1109/LED.2013.2267933.
- [6] E. Acurio *et al.*, "Reliability Improvements in AlGaIn/GaN Schottky Barrier Diodes With a Gated Edge Termination," *IEEE Trans. Electron Devices*, vol. 65, no. 5, pp. 1765–1770, May 2018, doi: 10.1109/TED.2018.2818409.
- [7] E. Acurio, L. Trojman, F. Crupi, T. Moposita, B. De Jaeger, and S. Decoutere, "Reliability Assessment of AlGaIn/GaN Schottky Barrier Diodes under ON-state stress," *IEEE Trans. Device Mater. Reliab.*, pp. 1–1, 2020, doi: 10.1109/TDMR.2020.2969638.
- [8] T.-L. Wu *et al.*, "Toward Understanding Positive Bias Temperature Instability in Fully Recessed-Gate GaN MISFETs," *IEEE Trans. Electron Devices*, vol. 63, no. 5, pp. 1853–1860, May 2016, doi: 10.1109/TED.2016.2539341.
- [9] C. Mizue, Y. Hori, M. Miczek, and T. Hashizume, "Capacitance–Voltage Characteristics of $\text{Al}_2\text{O}_3/\text{AlGaIn/GaN}$ Structures and State Density Distribution at $\text{Al}_2\text{O}_3/\text{AlGaIn}$ Interface," *Jpn. J. Appl. Phys.*, vol. 50, no. 2, p. 021001, Feb. 2011, doi: 10.1143/JJAP.50.021001.
- [10] C. M. Jackson, A. R. Arehart, E. Cinkilic, B. McSkimming, J. S. Speck, and S. A. Ringel, "Interface trap characterization of atomic layer deposition $\text{Al}_2\text{O}_3/\text{GaN}$ metal-insulator-semiconductor capacitors using optically and thermally based deep level spectroscopies," *J. Appl. Phys.*, vol. 113, no. 20, p. 204505, May 2013, doi: 10.1063/1.4808093.
- [11] J. Hu *et al.*, "Statistical Analysis of the Impact of Anode Recess on the Electrical Characteristics of AlGaIn/GaN Schottky Diodes With Gated Edge Termination," *IEEE Trans. Electron Devices*, vol. 63, no. 9, pp. 3451–3458, Sep. 2016, doi: 10.1109/TED.2016.2587103.
- [12] J. Franco *et al.*, "Understanding the suppressed charge trapping in relaxed- and strained-Ge/SiO₂/HfO₂/pMOSFETs and implications for the screening of alternative high-mobility substrate/dielectric CMOS gate stacks," in *2013 IEEE International Electron Devices Meeting*, 2013, pp. 15.2.1–15.2.4, doi: 10.1109/IEDM.2013.6724634.
- [13] M. Cho *et al.*, "Insight Into N/PBTI Mechanisms in Sub-1-nm-EOT Devices," *IEEE Trans. Electron Devices*, vol. 59, no. 8, pp. 2042–2048, Aug. 2012, doi: 10.1109/TED.2012.2199496.
- [14] D. Bisi *et al.*, "Deep-Level Characterization in GaN HEMTs-Part I: Advantages and Limitations of Drain Current Transient Measurements," *IEEE Trans. Electron Devices*, vol. 60, no. 10, pp. 3166–3175, Oct. 2013, doi: 10.1109/TED.2013.2279021.
- [15] T. Grasser *et al.*, "The 'permanent' component of NBTI revisited: Saturation, degradation-reversal, and annealing," in *2016 IEEE International Reliability Physics Symposium (IRPS)*, 2016, vol. 2016-Sept, pp. 5A-2-1–5A-2-8, doi: 10.1109/IRPS.2016.7574504.
- [16] P. Lager, C. Ostermaier, and D. Pogany, "Enhancement of V_{th} drift

- for repetitive gate stress pulses due to charge feedback effect in GaN MIS-HEMTs,” in *2014 IEEE International Reliability Physics Symposium*, 2014, no. c, pp. 6C.3.1-6C.3.6, doi: 10.1109/IRPS.2014.6861110.
- [17] P. Lagger, M. Reiner, D. Pogany, and C. Ostermaier, “Comprehensive Study of the Complex Dynamics of Forward Bias-Induced Threshold Voltage Drifts in GaN Based MIS-HEMTs by Stress/Recovery Experiments,” *IEEE Trans. Electron Devices*, vol. 61, no. 4, pp. 1022–1030, Apr. 2014, doi: 10.1109/TED.2014.2303853.
- [18] H. Hanawa, H. Onodera, A. Nakajima, and K. Horio, “Numerical Analysis of Breakdown Voltage Enhancement in AlGaIn/GaN HEMTs With a High- κ Passivation Layer,” *IEEE Trans. Electron Devices*, vol. 61, no. 3, pp. 769–775, Mar. 2014, doi: 10.1109/TED.2014.2298194.