Effects of water vapour on 2-mercaptobenzothiazole corrosion inhibitor films deposited on copper

Xiaocui Wu, Frédéric Wiame, Vincent Maurice, Philippe Marcus

► To cite this version:

Xiaocui Wu, Frédéric Wiame, Vincent Maurice, Philippe Marcus. Effects of water vapour on 2-mercaptobenzothiazole corrosion inhibitor films deposited on copper. *Corrosion Science*, 2021, 189, pp.109565. 10.1016/j.corsci.2021.109565 . hal-03249395

HAL Id: hal-03249395

<https://hal.science/hal-03249395>

Submitted on 4 Jun 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Effects of water vapour on 2-mercaptobenzothiazole corrosion inhibitor films deposited on copper

Xiaocui Wu¹, Frédéric Wiame*, Vincent Maurice, Philippe Marcus*

Université PSL, CNRS - Chimie ParisTech, Institut de Recherche de ChimieParis, Groupe Physico-Chimie des Surfaces, 75005 Paris, France

Abstract

The effects of water on 2-mercaptobenzothiazole (2-MBT) film pre-formed on copper at low pressure and room temperature was investigated in situ by X-ray photoelectron spectroscopy. Upon exposure to water vapour at 5×10^{-6} mbar, the 2-MBT molecules not directly bonded to copper desorb, until only one monolayer remains adsorbed. Further exposure leads to cleavage of the bond between exocyclic sulphur and copper, whereas nitrogen remains bonded to copper. Dissociative adsorption of water is observed, without copper oxidation for exposure up to 3×10^6 L. This work brings new molecular scale insight into corrosion inhibition mechanisms in water-containing environments.

Keywords: A. 2-MBT, A. Copper, A.H₂O, C.Corrosion inhibition, B. XPS

1. Introduction

Given the extensive use of copper in industrial and civil sectors, its corrosion degradation plays a significant role in economics and safety, thus rising the importance of corrosion protection. The use of corrosion inhibitors is considered as one of the most effective ways to protect copper from corrosion. Their inhibition efficiency is directly related to their adsorption properties, which then depend on the nature of the copper surface and the

¹Present address: Institut für Physik, Technische Universität Ilmenau, D-98693 Ilmenau, Germany

*Corresponding authors

Email addresses: frederic.wiame@chimieparistech.psl.eu (Frédéric Wiame),
philippe.marcus@chimieparistech.psl.eu (Philippe Marcus)

structure of the inhibitors. Among the existing corrosion inhibitors, benzotriazole and its derivatives, notably 2-MBT, are the mostly used ones with high inhibition efficiency [1–8].

2-mercaptobenzothiazole (2-MBT, $\text{C}_6\text{H}_4(\text{NH})\text{SC}=\text{S}$) is an organic compound showing wide application in a large spectrum of industries for the production of lubricant and additives, the sulphur vulcanization of rubber [9], the biological activities [10], and most importantly, the corrosion inhibition of metals and alloys [11–14]. More specifically, 2-MBT contains heteroatoms with high electron density, such as nitrogen and sulphur, which are considered as reactive sites for its adsorption on surfaces [7, 15–18].

In most phenomena, copper is exposed to water. So the understanding of the effect of water on the corrosion inhibition properties of 2-MBT on copper is the first step to further grasp its corrosion protection mechanisms in real conditions. Numerous studies have been performed to characterize the interaction between copper and 2-MBT in aqueous solution [8, 11, 19–22]. The molecule was found to coordinate with the copper substrate through sulphur and nitrogen atoms, leading to the formation of a protective barrier organic film on copper surface, thus preventing the metal from further degradation. However, for these studies carried out directly in liquid phase, it is difficult to control and follow each step of interaction between the inhibitor, copper and water. Moreover, surface contamination is a problem for ex situ analysis.

In this work, a surface science approach on a model system, innovative in the context of corrosion inhibition, was applied in order to gain detailed information on the interaction of water with the 2-MBT molecular layer formed on copper. More precisely, 2-MBT was deposited on copper in clean metallic state through sublimation at ultra-low pressure. This allows the formation of a chemically and structurally well characterized molecular layer. The sample was then exposed to water vapour at low pressure and room temperature, and the surface state was monitored in situ by X-ray photoelectron spectroscopy (XPS). This model approach enables a precise control of the interaction between the protective organic molecular layer and water. Although far from real conditions, the results allow us to understand in details the origin of the corrosion inhibition alterations that are essential to further understand the behaviour in real conditions.

2. Material and methods

2.1. Materials

A high purity (99.999 %) Cu(111) single-crystal was used. It was prepared clean in the metallic state under ultra-high vacuum (UHV) by repeated cycles of ion sputtering ($P_{\text{Ar}} = 5 \times 10^{-6}$ mbar, 600 V, 10 mA, 10 min) and annealing (600 °C, 10 min). The surface state was verified systematically until no contamination was detected by XPS, and a sharp (1×1) low energy electron diffraction pattern, indicative of a well-ordered surface termination, was observed.

The 2-MBT used was 99 % pure (Sigma-Aldrich). It is a yellow powder at room temperature. The powder was placed in a vacuum sealed glass tube which is connected to the preparation chamber of the UHV system for the *in situ* deposition of 2-MBT. The 2-MBT vapour pressure is about 10^{-9} mbar at room temperature.

2.2. Methods

The UHV system, equipped with preparation chambers for surface preparation, 2-MBT deposition and water vapour exposure, as well as an XPS spectrometer (Thermo Electron Corporation, ESCALAB 250) for chemical analysis, is pumped continuously to keep a base pressure below 10^{-10} mbar under normal conditions. A monochromatic Al K_{α} X-ray source (1486.6 eV) was used for the analysis. The binding energy was calibrated by referring to the Fermi level of the sample. Reference samples were used to calibrate the transmission of the analyser. The survey spectrum was recorded with a pass energy of 100 eV corresponding to an overall resolution of 1.8 eV, and the high resolution core level spectra were recorded with a pass energy of 20 eV corresponding to an overall resolution of 360 meV. The analysed photoelectrons were collected with a take-off angle of 90°, and the XPS spectra were analysed using the CasaXPS software (version 2.3.19) [23].

The clean Cu(111) surface was exposed to 2-MBT vapour at partial pressure of about 10^{-9} mbar at room temperature (RT). The sample and the 2-MBT powder were kept at RT during the entire deposition process, and the surface after exposure was characterized by XPS. The molecular exposure is expressed in langmuir ($1 \text{ L} = 10^{-6}$ torr s). The effect

of water on the pre-adsorbed molecular layer was studied by introducing water vapour progressively into the preparation chamber at partial pressure up to 5×10^{-6} mbar and RT until saturation.

The clean Cu(111) surface was exposed to water vapour under the same conditions as above until saturation, and the results were compared to those obtained on Cu(111) covered by the pre-deposited 2-MBT layer.

3. Results and discussion

Previously, we have studied the growth kinetics of 2-MBT on Cu(111) at ultra-low pressure and RT [2, 3]. A complete monolayer of thickness of about 0.2 nm was formed at low exposure, followed by the formation of multilayer of thickness of about 0.6 nm. In this work, the same conditions were applied to firstly grow 2-MBT layers on Cu(111). The sample was then exposed to water vapour at low pressure and RT, and the surface was characterized in situ by XPS.

3.1. 2-MBT multilayer exposed to water vapour

Fig. 1 shows the S 2p spectra obtained on the metallic Cu(111) surface covered by a 2-MBT multilayer before and after different exposures to water vapour at 5×10^{-6} mbar and RT. The S 2p spectra were decomposed using three spin-orbit doublets S 2p_{1/2} and S 2p_{3/2}, with a branching ratio of 0.51 and spin-orbit splitting of 1.18 eV [8, 24]. Before exposure to water vapour, an intense peak S₃ was observed, with the S 2p_{3/2} at a binding energy of 161.6 eV, corresponding to S bonded to copper, in atomic or intact molecular form [2, 3]. Two other components of equal intensity, S₁ (S 2p_{3/2} at 164.2 eV) and S₂ (S 2p_{3/2} at 162.6 eV), were observed, each representing 30 % of the total intensity of the S 2p spectrum. These two components were assigned to endocyclic and exocyclic sulphur in the molecule not bonded to copper, respectively [2, 3, 25]. This is in agreement with the formation of a 2-MBT multilayer as observed previously [2, 3], the molecules in the first monolayer being bonded to copper while those in the upper layer are not interacting directly with the copper substrate.

After exposure to water vapour, the intensities of S_1 and S_2 decreased gradually, as well as a decrease in the N 1s spectra, which could be explained by the desorption of the molecules in the multilayer not bonded to Cu. At the same time, the intensity of S_3 increased, which is explained by a reduced attenuation of the signal originating from molecules directly bonded to copper, due to the decrease of the 2-MBT layer thickness. Taking into account the signal attenuation, we calculated the thickness of the molecular layer at different water exposures. Since the intensity of oxygen was calculated to be only 10 % of that obtained on Cu(111) covered by two-dimensional oxide of characteristic “29” superstructure after exposing to oxygen under the same conditions [3, 26], and no evidence of copper oxide was observed on the Cu LMM spectra as discussed below, a homogeneous layer of 2-MBT was assumed while neglecting the presence of oxygen. Before exposure to water vapour, the thickness of the 2-MBT multilayer was calculated to be about 0.8 ± 0.1 nm, which is in good agreement with that obtained previously [3]. After exposure to water vapour, the thickness of the molecular layer decreased gradually, and was calculated to be 0.6 ± 0.1 nm for an exposure of 2.9×10^5 L, confirming the desorption of the 2-MBT molecule as suggested above. Given this desorption kinetics, in order to reach the monolayer (thickness of about 0.2 nm [3]), an exposure of more than 1×10^6 L is needed, which corresponds to at least 89 h of exposure at 5×10^{-6} mbar. This hypothesis will be confirmed as shown below. Since we are limited by the pressure of the water vapour in the UHV system as well as the deposition time to not deteriorate the UHV environment, slightly more than a monolayer was prepared directly on Cu(111) for further studies. The exact coverage is not crucial since the molecule in the multilayer will continue to desorb when exposed to water vapor.

3.2. 2-MBT monolayer exposed to water vapour

In this part, in order to confirm the previous hypothesis on the continuous desorption of water and then to study the effect of water on 2-MBT pre-deposited on Cu(111) in the monolayer range, the copper covered by slightly more than one 2-MBT monolayer was prepared by exposing the metallic substrate to 20 L of 2-MBT vapour and subsequently exposed to water vapour at 5×10^{-6} mbar and RT.

Fig. 2 shows the S 2p, N 1s, and O 1s spectra obtained on Cu(111) covered by slightly more than one monolayer of 2-MBT before and after different exposures to water vapour at 5×10^{-6} mbar and RT. Before exposure to water vapour, the S 2p spectrum is mainly composed of the S_3 component. Meanwhile, the two other components S_1 and S_2 are also observed with equal intensity, each representing 16 % of the total intensity of the S 2p spectrum. Due to the high surface sensitivity of XPS and the previous work on the growth of 2-MBT multilayer [3], this indicates the formation of slightly more than a monolayer of 2-MBT, with the molecules in the second layer not interacting directly with the copper substrate. The N 1s spectrum is composed of two components N_1 and N_2 at binding energies of 400.1 eV and 398.9 eV, corresponding to nitrogen bonded and not bonded to copper, respectively [3]. By assuming a homogeneous layer of 2-MBT, the molecular layer thickness was calculated to be about 0.3 nm. Compared to the thickness of one 2-MBT monolayer of about 0.2 nm [3], this confirms the adsorption of slightly more than one 2-MBT monolayer on copper.

After exposure to 456 L of water vapour, the intensities of S_1 and S_2 each decreased down to 10 % of the total intensity of the S 2p spectrum, and the intensity of S_3 increased by 21 %, with the full width at half maximum (FWHM) almost unchanged for each peak (0.9 ± 0.1 eV), suggesting the continuation of the desorption of the molecule in the second layer. As for the N 1s spectrum, the intensity of N_1 (N bonded to copper) increases by 45 %, and that of N_2 (N not bonded to copper) decreases by 54 %, confirming the desorption of 2-MBT molecules not bonded to copper. This confirms the hypothesis made at the end of the previous section.

At higher exposure, up to 2.1×10^6 L, as the organic layer continues to be exposed to water vapour, the non-bonded molecules continue to desorb (decrease of S_1 and S_2). However, a new component designated, S_4 , appeared in the S 2p spectrum, with the S $2p_{3/2}$ at a binding energy of 162.8 eV, accompanied by a decrease in the intensity of S_3 , indicating a change in the sulphur environment. The FWHM of S_1 , S_2 and S_3 are varying less than 13 %. The evolution of the S_3 and S_4 components after different exposures to water vapour was analysed in detail, and the results are shown in Fig. 3. The total area of the S 2p core level

peaks were normalized by the transmission of analyser, the photoionization cross section and the inelastic mean free path. The normalized area is proportional to the density of sulphur atoms. The component S_4 appears from an exposure of 6×10^5 L. Then its intensity increases with increasing exposure, while that of S_3 decreases accordingly so that the sum of S_3 and S_4 remained unchanged. We can thus conclude that there is a transformation of the S 2p spectra from S_3 to S_4 . The binding energy of S_4 is shifted only by 0.3 eV compared to that of S_2 (exocyclic sulphur not bonded to copper), suggesting a breakdown of the bond between exocyclic sulphur and copper in the monolayer, which could be explained by the catalytic effect of metallic copper, as also observed previously [27]. Meanwhile, the intensity of N_1 component decreases, accompanied with the presence of a new component designated, N_3 , at binding energy of 399.9 eV, which is shifted only by 0.2 eV compared to that of N_1 (nitrogen bonded to copper). This suggests that nitrogen remains bonded to copper, and the shift in binding energy could also be explained by the cleavage of the bond between sulphur and copper in 2-MBT as suggested above. Since the total intensity of sulphur and nitrogen remained unchanged, there is no further desorption of the molecule in the monolayer. The FWHM of N_1 increase by 50 % compared to that obtained before exposure to water, which could be explained by the change in the structure of the layer as disorder may appear and induce slightly different configurations associated with slightly different chemical shifts resulting in the broadening of the peak.

As for the O 1s spectra, there is no increase in the O 1s intensity for exposure up to 456 L of water vapour on Cu(111) with pre-adsorbed 2-MBT at RT. When increasing the exposure to 2.1×10^6 L, a small peak of oxygen was observed, with the presence of two components O_1 and O_2 , at binding energies of 532.6 eV and 531.4 eV, respectively. The component O_1 may be assigned to molecular H_2O , and the component O_2 could be explained by the adsorption of OH groups, possibly due to the dissociative adsorption of water [28–31]. No significant change was observed in the Cu LMM spectra upon exposure to water vapour as shown in Fig. 4, indicating no copper oxide formation. The O 1s spectra obtained on Cu(111) exposed to water vapour or to gaseous oxygen at RT until saturation are also shown for comparison. When exposing the clean Cu(111) to water vapour, the two components O_1

and O_2 were slightly shifted to a lower binding energy (0.4 eV), which could be explained by the influence of the absence of pre-adsorbed 2-MBT molecules, and no formation of copper oxide was observed in the Cu LMM spectrum (Fig. 4). Finally, when exposing metallic Cu(111) to oxygen at 5×10^{-6} mbar and RT, the two components were shifted by 1.3 eV to lower binding energy, confirming the difference in the nature of the oxygen. The FWHM of O_1 and O_2 are varying less than 16 %. The new component O_3 at binding energy of 529.7 eV is usually attributed to the formation of bulk oxide [30, 32]. Moreover, the decrease of the intensities of peaks 1 and 2 at lower binding energies (characteristic for metallic copper) in the Cu LMM spectrum compared to those of peaks 3 and 4 at higher binding energies (characteristic for copper oxide) indicates the formation of copper oxide, confirming the oxidation of copper when exposing to oxygen.

Finally, the intensity of oxygen was measured and compared to that obtained on metallic Cu(111) exposed to water vapour under the same conditions, and the results are shown in Fig. 5. The area of the O 1s spectra were normalized relatively to the background. On metallic Cu(111) without 2-MBT, the normalized O 1s peak area increases rapidly with increasing exposure, confirming the dissociative adsorption of water on the Cu(111) surface when exposed to water vapour. A decrease in the O 1s growth rate was then observed, and a saturation regime was reached after an exposure of about 10^4 L, which gave a normalized peak area of about 0.5. On Cu(111) covered by 0.3 nm of 2-MBT, the normalized O 1s area increased much slower, and remains below 0.2 after an exposure of 3.4×10^6 L. On Cu(111) covered by a 2D oxide after exposing to oxygen under the same conditions [3], a rapid increase in the oxygen intensity was observed until reaching the saturation regime at an exposure of only 600 L, with the normalized O 1s peak area equal to 1. So the amount of oxygen observed on copper with and without 2-MBT after exposure to water vapour only represents 20 % and 50 % compare to a complete 2D oxide layer, respectively. The absence of oxide signal in the Cu LMM spectra shows that water adsorption is partially dissociative without leading to copper oxide formation in these room temperature exposure conditions, in contrast with the dissociative adsorption of oxygen that leads to the surface oxidation of copper. This result confirms that atomic oxygen, and thus the dissociation of hydroxyl

groups, is required for the surface oxidation of copper. In the presence of pre-adsorbed 2-MBT, water dissociative adsorption is considerably slow down while altering the bonding of the inhibitor with the copper surface.

4. Conclusions

In this work, the effects of water on corrosion inhibition films of 2-MBT pre-formed on metallic copper was investigated. In order to allow a precise control of the interaction mechanisms, a surface science approach on a model system was employed, with exposure to water vapour in gaseous phase at low pressure and RT of Cu(111) single crystal surface pre-covered by a well-characterized 2-MBT layer, and in situ surface chemical analysis by XPS.

When exposing to water vapour, a desorption of 2-MBT molecules in the multilayer (not directly bonded to copper) was observed, indicating that even extremely low amount of water already have a significant effect on the inhibitor layer. This desorption of 2-MBT continues until only a monolayer remains on the surface. Further exposure to water vapour led to the cleavage of the bond between exocyclic sulphur and copper in the monolayer, whereas nitrogen remains bonded to the copper surface. Dissociative adsorption of water is observed, without desorption of 2-MBT. No copper oxide formation was observed, and water uptake was markedly slow down by the pre-adsorbed organic layer.

Although far from real conditions, this study provides an effective approach to investigate in details the interaction mechanisms between water, organic inhibitor molecules and copper, which is of great importance for the understanding of the mechanisms governing the corrosion inhibition efficiency of organic inhibitors in real conditions.

5. Acknowledgments

This work was supported by the European Research Council (ERC) under the European Union’s Horizon 2020 research and innovation program (ERC Advanced Grant CIMNAS no. 741123). We also thank Région Île-de-France for partial funding of the XPS equipment.

6. Data availability

The data that support the findings of this study are available from the corresponding authors upon reasonable request.

References

- [1] S. B. Sharma, V. Maurice, L. H. Klein, P. Marcus, Local inhibition by 2-mercaptobenzothiazole of early stage intergranular corrosion of copper, *Journal of the Electrochemical Society* 167 (16) (2020) 161504.
- [2] X. Wu, F. Wiame, V. Maurice, P. Marcus, Adsorption and thermal stability of 2-mercaptobenzothiazole corrosion inhibitor on metallic and pre-oxidized Cu(111) model surfaces, *Applied Surface Science* 508 (2020) 145132.
- [3] X. Wu, F. Wiame, V. Maurice, P. Marcus, 2-mercaptobenzothiazole corrosion inhibitor deposited at ultra-low pressure on model copper surfaces, *Corrosion Science* 166 (2020) 108464.
- [4] X. Wu, F. Wiame, V. Maurice, P. Marcus, Moiré structure of the 2-mercaptobenzothiazole corrosion inhibitor adsorbed on a (111)-oriented copper surface, *The Journal of Physical Chemistry C* 124 (29) (2020) 15995–16001.
- [5] K. Marczevska-Boczkowska, M. Kosmulski, 2-mercaptobenzothiazole as a corrosion inhibitor in low temperature ionic liquids, in: *Trends in Colloid and Interface Science XXIV*, Springer, 2011, pp. 165–171.
- [6] M. Gholami, I. Danaee, M. H. Maddahy, M. RashvandAvei, Correlated ab initio and electroanalytical study on inhibition behavior of 2-mercaptobenzothiazole and its thiole–thione tautomerism effect for the corrosion of steel (API 5L X52) in sulphuric acid solution, *Industrial & Engineering Chemistry Research* 52 (42) (2013) 14875–14889.
- [7] E. Vernack, D. Costa, P. Tingaut, P. Marcus, DFT studies of 2-mercaptobenzothiazole and 2-mercaptobenzimidazole as corrosion inhibitors for copper, *Corrosion Science* 174 (2020) 108840.
- [8] M. Finšgar, D. K. Merl, An electrochemical, long-term immersion, and XPS study of 2-mercaptobenzothiazole as a copper corrosion inhibitor in chloride solution, *Corrosion Science* 83 (2014) 64–175.
- [9] H. Engels, H. Weidenhaupt, M. Pieroth, W. Hofmann, K. Menting, T. Mergenhagen, R. Schmoll, S. Uhrlandt, Rubber, 9. Chemicals and Additives, *Ullmann’s Encyclopedia of Industrial Chemistry*, Wiley-VCH: Weinheim, 2011.
- [10] M. A. Azam, B. Suresh, Biological activities of 2-mercaptobenzothiazole derivatives: A review, *Scientia Pharmaceutica* 80 (4) (2012) 789–824.

- [11] D. Chadwick, T. Hashemi, Electron spectroscopy of corrosion inhibitors: Surface film formed by 2-mercaptobenzothiazole and 2-mercaptobenzimidazole on copper, *Surface Science* 89 (1-3) (1979) 649–659.
- [12] A. C. Balaskas, M. Curioni, G. E. Thompson, Effectiveness of 2-mercaptobenzothiazole, 8-hydroxyquinoline and benzotriazole as corrosion inhibitors on AA 2024-T3 assessed by electrochemical methods, *Surface and Interface Analysis* 47 (11) (2015) 1029–1039.
- [13] J. Zhang, Q. Zhang, H. Ren, W. Zhao, H. Zhang, Inhibition performance of 2-mercaptobenzothiazole derivatives in CO₂ saturated solution and its adsorption behavior at Fe surface, *Applied Surface Science* 253 (18) (2007) 7416–7422.
- [14] H. Cen, J. Cao, Z. Chen, X. Guo, 2-mercaptobenzothiazole as a corrosion inhibitor for carbon steel in supercritical CO₂-H₂O condition, *Applied Surface Science* 476 (2019) 422 – 434.
- [15] C. M. Whelan, M. R. Smyth, C. J. Barnes, N. M. D. Brown, C. A. Anderson, An XPS study of heterocyclic thiol self-assembly on Au (111), *Applied Surface Science* 134 (1998) 144–158.
- [16] B. Trachli, M. Keddama, H. Takenouti, A. Shiri, Protective effect of electropolymerized 2-mercaptobenzimidazole upon copper corrosion, *Progress in Organic Coatings* 44 (2002) 17–23.
- [17] S. Sun, Y. Geng, L. Tian, S. Chen, Y. Yan, S. Hu, Density functional theory study of imidazole, benzimidazole and 2-mercaptobenzimidazole adsorption onto clean Cu(111) surface, *Corrosion Science* 63 (2012) 140–147.
- [18] F. Chiter, D. Costa, V. Maurice, P. Marcus, Dft investigation of 2-mercaptobenzothiazole adsorption on model oxidized copper surfaces and relationship with corrosion inhibition, *Applied Surface Science* 537 (2021) 147802.
- [19] J. C. Marconato, L. O. Bulhões, M. L. Temperini, A spectroelectrochemical study of the inhibition of the electrode process on copper by 2-mercaptobenzothiazole in ethanolic solutions, *Electrochimica Acta* 43 (7) (1998) 771–780.
- [20] M. Ohsawa, W. Suëtaka, Spectro-electrochemical studies of the corrosion inhibition of copper by mercaptobenzothiazole, *Corrosion Science* 19 (7) (1979) 709–722.
- [21] R. Woods, G. A. Hope, K. Watling, A SERS spectroelectrochemical investigation of the interaction of 2-mercaptobenzothiazole with copper, silver and gold surfaces, *Journal of Applied Electrochemistry* 30 (2000) 1209–1222.
- [22] L. P. Kazansky, I. A. Selyaninov, Y. I. Kuznetsov, Adsorption of 2-mercaptobenzothiazole on copper surface from phosphate solutions, *Applied Surface Science* 258 (2010) 6807–6813.
- [23] Casaxps manual 2.3.15, Casa Software Ltd (2009).
- [24] J. Jia, A. Kara, L. Pasquali, A. Bendounan, F. Sirotti, V. A. Esaulov, On sulfur core level binding energies in thiol self-assembly and alternative adsorption sites: An experimental and theoretical study,

- The Journal of Chemical Physics 143 (2015) 104702.
- [25] Y. S. Tan, M. P. Srinivasan, S. O. Pehkonen, S. Y. M. Chooi, Self-assembled organic thin films on electroplated copper for prevention of corrosion, *Journal of Vacuum Science & Technology A* 22 (4) (2004) 1917–1925.
 - [26] F. Wiame, V. Maurice, P. Marcus, Initial stages of oxidation of Cu(111), *Surface Science* 601 (2007) 1193–1204.
 - [27] G. Xue, X.-Y. Huang, J. Dong, J. Zhang, The formation of an effective anti-corrosion film on copper surfaces from 2-mercaptobenzimidazole solution, *J. Electroanal. Chem.* 310 (1991) 139–148.
 - [28] A. Spitzer, H. Lüth, An XPS study of the water adsorption on Cu(110), *Surface Science* 160 (2) (1985) 353–361.
 - [29] A. De Asha, J. Critchley, R. Nix, Molecular adsorption characteristics of lanthanum oxide surfaces: the interaction of water with oxide overlayers grown on Cu(111), *Surface science* 405 (2-3) (1998) 201–214.
 - [30] S. Yamamoto, H. Bluhm, K. Andersson, G. Ketteler, H. Ogasawara, M. Salmeron, A. Nilsson, In situ x-ray photoelectron spectroscopy studies of water on metals and oxides at ambient conditions, *Journal of Physics: Condensed Matter* 20 (18) (2008) 184025.
 - [31] K. Andersson, G. Ketteler, H. Bluhm, S. Yamamoto, H. Ogasawara, L. G. Pettersson, M. Salmeron, A. Nilsson, Autocatalytic water dissociation on Cu(110) at near ambient conditions, *Journal of the American Chemical Society* 130 (9) (2008) 2793–2797.
 - [32] F. Wiame, F.-R. Jasnot, J. Świątowska, A. Seyeux, F. Bertran, P. L. Fèvre, A. Taleb-Ibrahimi, V. Maurice, P. Marcus, Oxidation of α -brass: A photoelectron spectroscopy study, *Surface Science* 641 (2015) 51–59.

Figure 1: XPS spectra of the S 2p core level of a 2-MBT multilayer on Cu(111) before and after different exposures to water vapour at 5×10^{-6} mbar and RT. The decomposition of the S 2p spectrum after 2.9×10^5 L exposure to water vapour is shown.

Figure 2: XPS spectra of the S 2p, N 1s, and O 1s core levels obtained on metallic Cu(111) covered by 0.3 nm of 2-MBT layer before and after different exposures to water vapour at 5×10^{-6} mbar and RT. The O 1s spectra obtained on metallic Cu(111) after exposure to water vapour (1.2×10^5 L) and to oxygen (600 L) under the same conditions until saturation are shown for comparison.

Figure 3: Evolution of S_3 and S_4 with exposure to water vapour at 5×10^{-6} mbar and RT.

Figure 4: Cu LMM spectra obtained on metallic Cu(111) covered by 0.3 nm of 2-MBT layer before and after different exposures to water vapour at 5×10^{-6} mbar and RT. The Cu LMM spectra obtained on metallic Cu(111) after exposure to water vapour (1.2×10^5 L) and to oxygen (600 L) under the same conditions until saturation are shown for comparison.

Figure 5: Oxidation kinetics of Cu(111) with and without 2-MBT monolayer exposed to water vapour at 5×10^{-6} mbar and RT.