Structural and Vibrational Study of CsSbGe₃O₉, a New Germanate in the ASbGe₃O₉ Family (A = Alkali Metal)

Monique Tillard, Abel Haidoux, Dominique Granier, Léa Daenens, Pascale Armand

► To cite this version:

Monique Tillard, Abel Haidoux, Dominique Granier, Léa Daenens, Pascale Armand. Structural and Vibrational Study of CsSbGe₃O₉, a New Germanate in the ASbGe₃O₉ Family (A = Alkali Metal). Inorganic Chemistry, 2021, 60 (14), pp.10361 - 10370. 10.1021/acs.inorgchem.1c00747 . hal-03293686

HAL Id: hal-03293686

<https://hal.science/hal-03293686>

Submitted on 23 Aug 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Structural and vibrational study of CsSbGe₃O₉, a new germanate in the ASbGe₃O₉ family (A = alkali metal).

**Monique Tillard ^o, Abel Haidoux, Dominique Granier,
Léa Daenens, Pascale Armand*^o**

ICGM, Univ. Montpellier, CNRS, ENSCM, Montpellier, France

Corresponding author

*E-mail: pascale.armand@umontpellier.fr ; Tel: +33 (0)4 67 14 33 19

^o ORCID: P. Armand 0000-0001-8921-5427, M. Tillard 0000-0002-0609-7224

Abstract:

The germanate $\text{CsSbGe}_3\text{O}_9$, grown spontaneously *via* the high-temperature solution method from $\text{Cs}_2\text{Mo}_4\text{O}_{13}$ used as a flux, crystallizes in the orthorhombic system $a = 12.3636(2)$, $b = 13.8521(2)$, $c = 31.4824(5)$ Å, $V = 5391.73(2)$ Å³. Its structure, determined from single-crystal X-ray diffraction data, is most probably non-centrosymmetric despite our choice to report it in the centro-symmetric maximal supergroup $Pnma D_{2h}^{16}$ (n° 62) in which agreement factors $R1 = 0.0371$ and $wR2 = 0.0706$ (all data) were obtained. The unit cell contains 24 formulas $\text{CsSbGe}_3\text{O}_9$. The 3-dimensional network is built up with regular germanate tetrahedra at nine crystallographically independent Ge sites. The Sb atoms (four independent positions) adopt octahedral coordination with O atoms and the Cs^+ cations are located in the channels of the 3-D network. A more in-depth analysis of the structure of $\text{CsSbGe}_3\text{O}_9$ is carried out in the light of the structures previously determined for the compounds ASbGe_3O_9 ($A = \text{K}, \text{Rb}$) having the same chemical formula but significantly different atomic arrangements. The structural characteristics are discussed related to literature and the nature of the monovalent cation A^+ .

KEYWORDS: oxides, crystal growth, X-ray diffraction, Raman spectroscopy, crystal structure

I. Introduction

In our search for new oxide materials with a non-centrosymmetric structure for piezoelectric and non-linear optical applications, we took an interest first in the germanium dioxide GeO_2 which adopts α -quartz-like structure and later in some ternary oxides¹⁻⁴. The ternary phases ASbGe_3O_9 with $A = \text{K}, \text{Rb}$ display a structural relationship with the Benitoite-type structure associated with the mineral $\text{BaTiSi}_3\text{O}_9$ ⁵⁻⁷. The ABX_3O_9 ternary oxides of Benitoite-type are made up of X_3O_9 cyclic units with $X = \text{Si}, \text{Ge}$. They include a post-transition or main group element B that can easily adopt octahedral coordination such as Ti, Ge, Sn, Ta... and a large mono or divalent cation taken from alkaline or alkaline earth as K, Rb, Ba, or even Tl (8-12). Synthetic germanates isostructural with the natural Benitoite $\text{BaTiSi}_3\text{O}_9$ ($P\overline{6}c2$ space group) are few to be reported in the literature^{5, 13, 14}.

In earlier crystallographic works dealing with X-ray diffraction studies of flux-grown single-crystals, we have shown that KSbGe_3O_9 is isostructural to Benitoite while, despite many similarities, the compound $\text{RbSbGe}_3\text{O}_9$ is not isostructural^{5, 6}. In this context, it seemed very attractive to establish the crystal structure of $\text{CsSbGe}_3\text{O}_9$, hitherto unknown. This is the first reason why attempts have been made to synthesize this phase by the same slow cooling method using the flux technique. Besides, having good quality crystals is also useful to explore the vibrational characteristics and, in this particular case, to complement the study of the oxides of the ASbGe_3O_9 series with $A = \text{K}, \text{Rb}, \text{Cs}$ and assess the role played by the monovalent cation A^+ in this family of structures.

This paper presents the synthesis of sub-millimeter-sized crystals having the chemical composition $\text{CsSbGe}_3\text{O}_9$, the X-ray crystal structure determination, and a study of their optical properties in the visible range through IR and Raman spectroscopy. The crystallographic and vibrational experimental data are analyzed comparatively to those

already obtained for KSbGe_3O_9 and $\text{RbSbGe}_3\text{O}_9$ with the idea of better understand how the identity of the alkaline element may influence the compound formation and crystallization.

II. Experimental section

The high-temperature flux technique with the slow cooling crystal growth method was used to spontaneously nucleate crystals of $\text{CsSbGe}_3\text{O}_9$ using $\text{Cs}_2\text{Mo}_4\text{O}_{13}$ as a flux. The starting reagents were commercial Alfa Aesar products MoO_3 (99.95%), Cs_2CO_3 (99%), and Yb_2O_3 (99.9%). They were used as received. The flux $\text{Cs}_2\text{Mo}_4\text{O}_{13}$ (100g) was prepared from powders Cs_2CO_3 (38.5 g) and MoO_3 (67.1g) *via* a solid-state reaction at 465 °C for two weeks. A total amount of 15g of an intimate mixture of 3g of Yb_2O_3 and 12g of $\text{Cs}_2\text{Mo}_4\text{O}_{13}$ in a weight ratio of 20/80 was added in a 5 cm³ Pt crucible with a lid. The crucible was placed in an electrical furnace and heated at 970 °C in the air for 6 hours to ensure the complete dissolution of the solute. Then, the temperature was slowly lowered at a rate of 1 °/h down to 745 °C for crystal growth, then the furnace was turned off.

The compound was characterized using differential scanning calorimetry (DSC), powder X-ray diffraction (XRD), and room-temperature infrared and non-polarized Raman spectroscopy. Details on the experimental procedures can be found in a previous paper ⁶.

The analysis by Energy Dispersive X-ray (EDX) spectroscopy of the grown crystals, using an Electron Scanning Environmental Microscope (ESEM) equipped with an Inca micro analyzer (Oxford Instruments), determined the content of Cs, Ge, and Sb elements. Three independent measures were made at the surface of the same as-grown crystal in order to check the homogeneity of the results.

Crystals with suitable quality and size were selected for X-ray diffraction experiments on a Bruker D8 Venture diffractometer (Mo micro source and Photon II CPAD detector). The data

collected were handled with the Apex suite¹⁵ and the structural solutions searched and refined with the SHELX programs^{16, 17}.

III. Results

3.1. Compound characterization.

The visually colorless and transparent platelets with sub-millimeter sizes that were obtained from the melt have hexagonal shapes and sharp edges. Their chemical EDX analysis gave atomic concentrations of 6.8 ± 0.2 at.% for Sb, 6.9 ± 0.2 at.% for Cs, and 21.1 ± 0.2 at.% for Ge. With a Cs:Sb:Ge ratio of 1:1:3, the nominal composition is CsSbGe₃O₉. No phase transition was observed during the DSC experiment where 44.3 mg of crystals were heated from room temperature, at a heating rate of 5 °/min, up to 1200 °C. The melting point was detected at 1080 ± 1 °C, which indicates good thermal stability of the material in a large range of temperatures.

The room temperature XRD pattern recorded for a powdered sample of CsSbGe₃O₉ is rather complex and does not match any reference in the X'Pert HighScore database¹⁸.

3.2. Structure determination.

Two as-grown crystals, selected under polarized light for singularity, were used in this structural study. For each of them, the diffracted data are complex, and indexing the reciprocal lattice was not obvious. In the first stages, taking into account only the "main" diffraction spots allowed an indexation of the data with orthogonal axes $a = 12.4$, $b = 13.8$, $c = 5.2$ Å. Such data processing only led to incomplete/incoherent structural models from which no satisfactory refinement could be achieved. Subsequently, a new indexation was carried out by taking into account all the diffraction spots, which required to multiply by 6 the c -parameter. Thus, the data sets were indexed within an orthorhombic lattice of parameters $a = 12.3636(2)$, $b = 13.8521(2)$, $c = 31.4824(5)$ Å (crystal 1) and $a = 12.3813(3)$, $b = 13.8699(5)$,

$c = 31.5109(8)$ Å (crystal 2). Using these lattice dimensions and symmetry, a very good profile fitting was obtained for the XRD powder pattern recorded at room temperature in standard conditions (PANalytical X'Pert Pro II diffractometer, Cu K α radiation, 10 - 50° angular 2 θ range) for the CsSbGe₃O₉ compound. The main parameters, related to the recording of diffraction data and the refinement of the structural model, are collected in Table 1.

Table 1. Crystal data and structure refinement parameters for CsSbGe₃O₉.

System	Orthorhombic	
Space group	<i>Pnma</i> (n° 62)	
Temperature, K	298(2)	
Unit cell dimensions, Å	$a = 12.3636(2)$	$a = 12.3813(3)$
	$b = 13.8521(2)$	$b = 13.8699(5)$
	$c = 31.4824(5)$	$c = 31.5109(8)$
Volume, Å ³	5391.73(2)	5411.3(3)
Z	24	
Calculated density, Mg/m ³	4.556	4.540
F(000)	6576	
Diffractometer, source	Bruker D8 Venture, X-rays	
Radiation, wavelength (Å)	K α Mo, 0.7107	
Absorption coefficient, mm ⁻¹	16.929	
Absorption correction	multi-scan SADABS	
Crystal size, mm	0.127×0.069×0.037	0.131×0.088×0.067
Theta range, °	2.095 - 31.000	2.092 - 31.000
Index ranges	$-17 \leq h \leq 17, -20 \leq k \leq 20, -45 \leq l \leq 45$	
Reflections collected	107272	138961
Independent reflections	8882 ($R_{\text{int}} = 0.0295$)	8908 ($R_{\text{int}} = 0.0330$)
Refinement type	full-matrix least-squares on F^2	
Goodness-of-fit on F^2	1.106	1.029
Final R 1 ($I > 2\sigma(I)$)	0.0324	0.0198
w R 2 ($I > 2\sigma(I)$)	0.0687	0.0449
R 1, w R 2 indices (all data)	0.0371, 0.0706	0.0237, 0.0462
Extinction coefficient	0.00076(2)	0.000311(6)
Fourier residuals $\Delta\rho$, e.Å ⁻³	3.204 / -3.747	3.250 / -2.967

Several orthorhombic space groups were considered to find the structural solution. The extinction conditions identified in the two recorded crystal data sets ($0kl$, $k+l=2n+1$ and $hk0$, $h=2n+1$) are fully compatible with $Pnma$ (n° 62) and $Pna2_1$ (n° 33) space groups. Nevertheless, the structure solution was also searched within other space groups as $Pmn2_1$ (31), $Pmc2_1$ (26), and $P2_12_12_1$ (19) in which extinction conditions are less severe. After the data have been corrected for the effects of absorption, the refinement of the structural solutions in each of these groups was carried out to fairly good RI values close to 3.5%. Note that anisotropic displacement parameters have been refined for all the atoms.

For both sets of data, the structural refinement within the space groups $Pnma$ ($a\ b\ c$ setting), $Pmn2_1$ ($b\ a\ \bar{c}$ setting) and $Pmc2_1$ ($b\ c\ a$ setting) was slightly better than in $Pna2_1$ ($\bar{a}\ c\ b$ setting) and $P2_12_12_1$ ($a\ b\ c$ setting). Refinement of the structural model within the centrosymmetric $Pnma$ space group converged to RI factors of 3.26 (crystal 1) and 3.54% (crystal 2) but residual density peaks of somewhat high intensity ($\sim 6.3 - 6.7\ \text{e}/\text{\AA}^3$) are observed very close to the heaviest atoms. Very similar characteristics were observed for the refinements in the space groups $Pna2_1$ and $P2_12_12_1$ but these residuals are significantly reduced, to about $3\ \text{e}/\text{\AA}^3$, when the resolution limit is changed to $\theta \leq 32$. With the only extinction conditions $h00$, $h=2n+1$, $0k0$, $k=2n+1$ and $00l$, $l=2n+1$, the space group $P2_12_12_1$ could be dismissed.

On the other hand, slightly weaker residual peaks ($3.8 - 5.1\ \text{e}/\text{\AA}^3$) were found near the Cs positions in the density difference maps when the structure is refined in the non-centrosymmetric space groups $Pmn2_1$ and $Pmc2_1$ leading to RI factors in the range 3.43 - 3.56%. Thus, if we consider the best density residuals and the best reliability factors, and even if it is impossible to exclude the other space groups, the quality of the refinements (standard deviations on the parameters of the atom ...) would also be in favor of these two space groups which seem the most likely for the compound. All these results tend to indicate non-

centrosymmetry for the structure of CsSbGe₃O₉. Yet, the careful inspection of statistical tests on diffracted intensities, in which the heavy atoms contribute to most, shows a trend but does not provide clear evidence of an inversion center. Moreover, the Flack parameter which refines to values close to 0.5 could indicate an inversion twinning leading then to the centrosymmetric *Pnma* space group. Under these conditions, it is quite hard to decide and state what is the true symmetry and the space group to assign to the structure. Finally, because we cannot unequivocally attest to the lack of inversion center in CsSbGe₃O₉ and we want to avoid a bad choice of space group, we decide deliberately to give its structural description in the centrosymmetric space group *Pnma* (n° 62).

The results of the refinement in this space group, using the data sets collected for each of the two crystals, are available at the Cambridge Crystallographic Data Center ¹⁹. The corresponding CIF files can be obtained indicating the following numbers: CSD 2068035 for crystal 1 ($a = 12.3636$, $b = 13.8521$, $c = 31.4824$ Å) and CSD 2068034 for crystal 2 ($a = 12.3813$, $b = 13.8699$, $c = 31.5109$ Å).

3.3. Structural description.

The structural model is built up with 49 crystallographically independent atoms of which four antimony atoms ($1 \times 4a$ ($0\ 0\ 0$), $1 \times 4b$ ($0\ 0\ \frac{1}{2}$) and $2 \times 8d$ ($x\ y\ z$) sites), six cesium atoms at $4c$ ($x\ \frac{1}{4}\ z$) sites, nine germanium atoms at $8d$ general sites and 30 oxygen atoms ($6 \times 4c$ and $24 \times 8d$ sites). The orthorhombic unit cell contains 336 atoms, which corresponds to 24 units of formula CsSbGe₃O₉ and agrees with the EDX measurements performed on the crystals. The structure representation given in Figure 1 has been drawn using the program Diamond ²⁰. It shows that the CsSbGe₃O₉ structure consists of a three-dimensional arrangement of polyhedra SbO₆ and GeO₄, in which three-dimensional channels host the Cs⁺ cations.

The four independent Sb^V atoms of the unit cell are 6-fold coordinated through Sb–O bonds in the range 1.953 to 1.972 Å, Table 2. The average of the six Sb–O distances of an octahedron

only varies from 1.963 to 1.966 Å for the four SbO_6 units. The O–Sb–O angle values, in the range 177.8 - 180.0° (*trans*) and 84.2 - 96.2° (*cis*), give a measure of the distortion from the ideal octahedral geometry with point group O_h . Each SbO_6 octahedron shares all its vertices with six GeO_4 tetrahedra, Figure 1.

Figure 1. The orthorhombic structure of $\text{CsSbGe}_3\text{O}_9$ projected on *a*- the (011) plane, *b*- the (101) plane, see Figure 8g for the (110) projection. The SbO_6 octahedra (brown) are interconnected through GeO_4 tetrahedra (blue) within a 3-D framework. The Cs^+ cations are drawn as green spheres.

The 4-fold coordinated germanium Ge^{IV} atoms (9 independent atoms) are involved in Ge–O bonds ranging from 1.724 to 1.766 Å within more or less regular GeO_4 tetrahedral units (1.738 - 1.745 Å for the average of Ge–O distances within a tetrahedron), Table 2. Each GeO_4 tetrahedron shares its vertices with two GeO_4 and two SbO_6 units, Figure 1.

Table 2. Main bond lengths (Å) for $\text{CsSbGe}_3\text{O}_9$.

Sb1	2 × O8	1.965(2)	Sb3	O20	1.953(2)	Sb4	O12	1.961(2)
	2 × O6	1.968(2)		O4	1.958(2)		O9	1.961(2)
	2 × O3	1.969(2)		O15	1.964(2)		O24	1.965(2)
				O1	1.970(2)		O19	1.968(2)
Sb2	2 × O14	1.957(2)		O17	1.971(2)		O5	1.969(2)
	2 × O2	1.967(2)		O10	1.972(2)		O7	1.971(2)
	2 × O11	1.972(2)						
			Ge4	O5	1.736(2)	Ge7	O28	1.729(1)
Ge1	O9	1.726(2)		O10	1.738(2)		O24	1.730(2)
	O20	1.729(2)		O18	1.745(1)		O3	1.736(2)
	O26	1.746(2)		O26	1.755(2)		O25	1.757(2)
	O16	1.757(2)						
				O15	1.724(2)	Ge8	O17	1.737(2)
Ge2	O14	1.726(2)		O12	1.739(2)		O2	1.738(2)
	O6	1.736(2)		O22	1.752(2)		O13	1.739(2)
	O25	1.745(2)		O21	1.754(2)		O27	1.756(1)
	O27	1.757(2)						
			Ge6	O19	1.733(2)	Ge9	O29	1.732(1)
Ge3	O30	1.736(1)		O23	1.740(1)		O8	1.733(2)
	O4	1.738(2)		O1	1.741(2)		O7	1.736(2)
	O11	1.739(2)		O16	1.763(2)		O21	1.766(2)
	O22	1.752(2)						

Consequently, two types of bridging oxygen atoms are encountered in this structure, either between two germanium atoms (Ge–O–Ge) or between a germanium atom and an antimony atom (Ge–O–Sb). The space remaining between the polyhedra is occupied by cesium (Cs^+ ions) which are surrounded by oxygen neighbors located beyond 3.04 Å (either 7 or 13 for the only distances shorter than 3.80 Å). The tilt in the orientation of the polyhedra along the *c*-direction, easily visible for the SbO_6 octahedra with the structure projection on (*101*) plane given in Figure 1b, accounts for the superstructure mentioned above.

3.4 Optical characterization.

The FT-IR spectrum over the range 450 - 1100 cm^{-1} and the Raman spectrum over the range 100 - 1100 cm^{-1} both registered for $\text{CsSbGe}_3\text{O}_9$ at room temperature are given in Figures 2a and 2b, respectively.

Figure 2. Non-polarized infrared transmission (a) and Raman (b) spectra registered at room temperature for $\text{CsSbGe}_3\text{O}_9$. Frequency positions are only given for the main bands.

The main factors that are responsible for the features of the spectra are the vibrations of both GeO_4 tetrahedra and SbO_6 coordinated groups, the deviation of these polyhedra away from the perfect T_d and O_h symmetry, and the interactions between groups in the unit cell. The vibration modes can be assigned to movements of the GeO_4 tetrahedra and lattice modes including motions of Sb^V in its octahedral coordination.

Classically, the Raman and infrared modes in the range of 600 - 1000 cm^{-1} are assigned in this structure to the $\nu(\text{Ge-O})$ stretching motions of both the GeO_4 tetrahedra and their

interconnecting Ge–O–Ge bridges. The bending vibrations of GeO_4 groups and Ge–O–Ge bridges are expected at lower frequencies^{21, 22}. The stretching vibration modes of the SbO_6 octahedra are encountered in the wavenumber range 450 - 850 cm^{-1} while both symmetric and antisymmetric bending vibration modes of the octahedral units are observed in the wavenumber range 250 - 600 cm^{-1} ^{23 - 26}. Despite the occurrence of mode-coupling and mode-mixing which hardens the separation of lattice modes that involves the Sb and Ge units, the oxygen bending motion in SbO_6 octahedra should be observed in the 400 - 500 cm^{-1} domain. At this stage, polarized Raman experimental data associated with theoretical calculations would be greatly helpful to go further in the identification and assignment of vibrational modes in the entire 50 - 1000 cm^{-1} domain for $\text{CsSbGe}_3\text{O}_9$.

IV. Discussion

A more in-depth analysis of the structure of the new compound $\text{CsSbGe}_3\text{O}_9$ deserves to be carried out in the light of the structures previously determined for the iso-formulated compounds ASbGe_3O_9 ($A = \text{K, Rb}$)^{5, 6}. Although there is a metric parentage for the lattices, important differences in the structural arrangements must be underlined. Moreover, a general comparison of this compound family with other types of germanate structures seems useful.

4.1 Structural hierarchy in the ASbGe_3O_9 family.

It is interesting to examine comparatively the structural arrangements within the antimony-germanate family ASbGe_3O_9 ($A = \text{K, Rb, Cs}$). The tendency towards the highest symmetry (principle of symmetry) is often mentioned as a goal to be achieved for crystalline solids, so the relation of symmetry that exists between their structures is worth investigating^{35, 36}. In addition to the strictly geometry-based analysis of the atomic arrangements, they can be described including the relationship between their respective space groups. This can be shown graphically with a tree of group-subgroup relations^{35 - 37}.

The compound KSbGe_3O_9 is described within the hexagonal symmetry and adopts the Benitoite-type structure. It crystallizes in the non-centrosymmetric space group $P\overline{6}c2$ with lattice dimensions $a = 6.94$ and $c = 9.99 \text{ \AA}$ ($V = 419 \text{ \AA}^3$) (5). Also displaying a non-centrosymmetric structure, $\text{RbSbGe}_3\text{O}_9$ conforms to the lower $P31c$ trigonal symmetry in a three times larger lattice, $3 \times V$, with $a = 12.14$ and $c = 9.96 \text{ \AA}$ (6). This supercell can be obtained from the basic cell of KSbGe_3O_9 by applying the transformation operation $(1 \ \overline{1} \ 0 \ 1 \ 2 \ 0 \ 0 \ 1)$ as shown in Figure 3.

Figure 3. Metric relationships between the KSbGe_3O_9 hexagonal base cell (V , black) and the $\text{RbSbGe}_3\text{O}_9$ trigonal ($3 \times V$, blue) and $\text{CsSbGe}_3\text{O}_9$ orthorhombic ($3 \times c$, $12 \times V$, red) supercells.

By looking now at the symmetry, the trigonal structure of the Rb-germanate can be considered to derive from that of the K-germanate, itself from $P6_3/mcm$ supergroup as represented in Figure 4. This diagram illustrates the reduction in symmetry of the space group from a highly symmetrical structure-type or "aristotype". In the case of germanate materials studied here, the symmetry $P6_3/mcm$ is the highest symmetry for which, to our knowledge, no experimental example has been found up to now. Starting from $P6_3/mcm$, the first *translationengleiche* transition of index 2 leads to $P\overline{6}c2$, then the unit cell is enlarged through a *klassengleiche* transition of index 3 (cell volume multiplied by 3) to $P\overline{6}2c$, and finally a second *translationengleiche* transition of index 2 leads to the symmetry $P31c$. This correlation

path passing through the structure of KSbGe_3O_9 towards that of $\text{RbSbGe}_3\text{O}_9$ establishes a symmetry relationship of the group-subgroup type which allows to refer to a structural hierarchy even it includes a step for which no example is known.

Figure 4. Group-subgroup scheme in the Bärnighausen formalism mentioning *klassengleiche* (k) and *translationengleiche* (t) indices, symmetry and unit cell transformations.

The structure of $\text{CsSbGe}_3\text{O}_9$ given here in the orthorhombic space group $Pnma$ (see § 3.2), is indicative of a further lowering in symmetry. With $a = 12.36$, $b = 13.85$, $c = 31.48$ Å, the supercell ($12 \times V$) of $\text{CsSbGe}_3\text{O}_9$ can be obtained from the basic cell of KSbGe_3O_9 by applying the $(1\ 2\ 0\ 2\ 0\ 0\ 0\ \bar{3})$ transformation matrix (Figure 3).

In this case, it is not so easy to establish a relation to formalize this new decrease in symmetry from the trigonal Rb- to the orthorhombic Cs-germanate, especially since the atomic arrangements are also very different (rings vs. chains). It may therefore be inappropriate to speak here of a hierarchical relationship and preferable to see only a metric relationship between unit cells.

The structures of the $ASbGe_3O_9$ ($A = K, Rb, Cs$) room temperature phases are built up with the same type of polyhedra (GeO_4 tetrahedra and SbO_6 octahedra) assembled in a 3-D open-framework displaying large channels. In the structures of compounds with $A = K$ and Rb , a sort of oligomerization of GeO_4 tetrahedra should be mentioned with the existence of trimeric units $(Ge_3O_9)^{6-}$, Figure 5. These trimers can be viewed as a central Ge_3O_3 ring, perfectly planar in the hexagonal structure of $KSbGe_3O_9$ (5), with six outwardly directed $Ge-O$ bonds on each side of the mean plane of the ring (approximately the ab plane).

Figure 5. The $(Ge_3O_9)^{6-}$ trimer with its Ge_3O_3 central-ring and its six $Ge-O$ external bonds.

Even if the K- and Rb-structures are similar by the general organization of the polyhedra, some distortions occur in $RbSbGe_3O_9$ ($3 \times V$) which no longer complies with the hexagonal symmetry and thus, with the Benitoite type. In the hexagonal $P\bar{6}c2$ structure, $1 \times Ge$ and $1 \times O$ atoms located on special positions $6k$ ($x y \frac{1}{4}$) form planar rings on mirror planes perpendicular to the hexagonal axis (Figure 6, left). Instead, central rings in the trigonal $P31c$ structure involve $3 \times Ge$ and $3 \times O$ placed at general independent positions $6c$ ($x y z$), so that their z -coordinate can move out of the plane $z = \frac{1}{4}$ and cause distortions of the ring (Figure 6, right).

Figure 6. Geometry of the Ge_3O_3 central ring with respect to the mean plane constructed with the atoms of the ring ($\approx ab$ plane): *left*-planar in KSbGe_3O_9 , *right*-twisted in $\text{RbSbGe}_3\text{O}_9$.

The deviation from flatness of the Ge_3O_3 central-ring in the Rb-compound typically reflects this symmetry lowering which allows twists in the position of the GeO_4 units and modifications in the $\text{Ge}-\text{O}-\text{Ge}$ angles⁶. Though built up with the same polyhedral units SbO_6 and GeO_4 , the structure of $\text{CsSbGe}_3\text{O}_9$ ($12 \times V$) stands out from those of compounds with $A = \text{K}$ and Rb . As substantial changes take place in the organization of these polyhedra in $\text{CsSbGe}_3\text{O}_9$, it is therefore that only a metric relationship exists between its lattice parameters and those of the other two compounds. The polyhedra still share all their vertices, the SbO_6 with six tetrahedra and the GeO_4 with two tetrahedra and two octahedra, but there is no more (Ge_3O_9) oligomer. The arrangement of polyhedra within the unit cell is rather regular but variations in their orientation along the c -axis, Figure 1, account for the large dimension of this lattice parameter. The structure of $\text{CsSbGe}_3\text{O}_9$ is characterized by one-dimensional chains of GeO_4 tetrahedra, roughly aligned along the b -axis of the orthorhombic lattice, Figure 7, and cross-linked along the c -axis through SbO_6 octahedra, Figure 1.

Figure 7. The infinite chains of GeO_4 tetrahedra in $\text{CsSbGe}_3\text{O}_9$ (inset in $\text{LiGeGe}_3\text{O}_9$ ²⁷).

4.2 The ASbGe_3O_9 compounds amongst germanate materials.

To place the discussion in a more general context, let us compare the ASbGe_3O_9 compounds with the germanate family of formula $\text{A}_2\text{Ge}_4\text{O}_9$ ^{27, 28}. On the strict basis of their formula, the $\text{A}_2\text{Ge}_4\text{O}_9$ compounds, or else $\text{A}_2\text{GeGe}_3\text{O}_9$, must be considered with a higher alkaline content than ASbGe_3O_9 in which the formal replacement of Sb^{V} by Ge^{IV} would lead to AGeGe_3O_9 . However, since both $\text{A}_2\text{GeGe}_3\text{O}_9$ and ASbGe_3O_9 structures consist of tetrahedral-octahedral three-dimensional open-frameworks where the alkaline cations are hosted in voids between the polyhedra, the comparison can be further continued. The symmetry relationships that connect these compounds (space groups deriving from a common supergroup) are shown in Figure 4. Most $\text{A}_2\text{GeGe}_3\text{O}_9$ structures also contain three-membered units $(\text{Ge}_3\text{O}_9)^{6-}$ connected through isolated GeO_6 octahedra²⁸, similarly as found in the ASbGe_3O_9 ($\text{A} = \text{K}, \text{Rb}$) structures *via* SbO_6 octahedra^{5, 6}, Figures 8e and 8f. This is the case of compounds $\text{A}_2\text{GeGe}_3\text{O}_9$ that are formed with the alkaline elements Na, K, and Rb²⁸ and crystallize in the trigonal $P\bar{3}c1$ symmetry. Instead, $\text{CsSbGe}_3\text{O}_9$ displays the orthorhombic symmetry (Figure 8g), and its structural resemblance with $\text{Li}_2\text{GeGe}_3\text{O}_9$ ($P2_1ca$, Figure 8a), recently described for

ferroelectric behavior, deserves to be reported ²⁷. The infinite chains of GeO₄ tetrahedra are corrugated (winkle), cross-linked by SbO₆ octahedra in CsSbGe₃O₉, and they are "crumpled crankshaft-like", and interconnected *via* GeO₆ octahedra in Li₂GeGe₃O₉, see inset in Figure 7. Thus, the crystal symmetry increases ($P2_1ca \rightarrow P\bar{3}1c$) in A₂GeGe₃O₉ ^{27, 28} with the size of the alkaline cation from Li⁺ to Na⁺, K⁺ or Rb⁺ and, on the contrary, decreases from $P\bar{6}2c$ to $P31c$ and next to $Pnma$ (see § 3.2) in the ASbGe₃O₉ family by changing K⁺ by Rb⁺ then by Cs⁺. The first step in lowering the symmetry, from hexagonal to trigonal, is associated with the disappearance of planarity for the Ge₃O₃ central ring.

Looking along the *c*-axis, two layers of octahedra and two layers of tetrahedra are alternately stacked in the trigonal lattices of RbSbGe₃O₉ (6) and A₂GeGe₃O₉ (A = Na, K, Rb) tetragermanates ^{28, 29}. Likewise, the hexagonal unit cell of the Benitoite-type KSbGe₃O₉ structure ⁵ contains two distinct layers of (Ge₃O₉)⁶⁻ oligomers with Ge₃O₃ rings. However, the A₂GeGe₃O₉ structure differs from those of ASbGe₃O₉ compounds by an offset of these layers perpendicular to the *c*-axis, so that the Ge₃O₃ rings from two successive layers no longer overlap ^{10, 29} as shown in the structure projections, Figure 8b.

At this stage, an analogy with the Wadeite structure has also to be pointed out. This structure may be placed on a new branch of the group-subgroup tree given in Figure 4 as it also results from the highest $P6_3/mcm$ symmetry through a t_2 *translationengleiche*. This natural silicate, K₂ZrSi₃O₉, displays layers based on trimeric units of SiO₄ tetrahedra, connected *via* ZrO₆ octahedra, Figure 8d ³⁰. The successive layers of tetrahedra are also staggered, such as the Si₃O₃ central rings do not overlap, but rings are planar in agreement with the $P6_3/m$ hexagonal symmetry of the Wadeite structure ²⁸⁻³⁰. To our knowledge, no germanate has been reported to date with this structure. On the contrary, several germanates and silicates containing cyclic trimers X₃O₉ (X = Si, Ge) have been described either within the BaTiSi₃O₉ Benitoite-type structure or within the BaGeGe₃O₉ tetragermanate structural type ^{5, 10, 28, 29}. As shown in

Figures 8c and 8e, these structural types bear very strong resemblances, and details about their relationships can be found in earlier works ^{10, 14, 31, 32}. These structures highly depend on the relative size of the constituting elements as reported particularly for the $AGeX_3O_9$ ($A = Ba$ and $X = Si, Ge$) family where the geometrical ratio of the ionic radii of B and X has been stated to condition the relative stability of the structures ¹⁰.

Figure 8. Various structures built with XO_6 octahedra (brown), MO_4 tetrahedra (blue) and electropositive cations (yellow, green or violet). *a*- $Li_2GeGe_3O_9$ (orthorhombic ²⁷, $P2_1ca$, (101) projection), *b*- $A_2GeGe_3O_9$ $A = Na, K, Rb$ (trigonal ²⁸, $P\bar{3}c1$), *c*- $BaGeGe_3O_9$ (trigonal ^{11, 32}, $P321$), *d*- $K_2ZrSi_3O_9$ Wadeite-type ^{30, 33} (hexagonal, $P6_3/m$), *e*- $KSbGe_3O_9$ (hexagonal ⁵, $P\bar{6}c2$, Benitoite-type), *f*- $RbSbGe_3O_9$ (trigonal ⁶, $P31c$), *g*- $CsSbGe_3O_9$ (orthorhombic, (110) projection ^{this work}). The representations were drawn from the structure data available in the literature.

4.3 Local structural aspects.

Although the geometry of the SbO_6 and GeO_4 polyhedra deviates respectively from the ideal O_h and T_d symmetry, the mean distances remain close to 1.95 Å for Sb–O and 1.74 Å for Ge–O along with the ASbGe_3O_9 ($A = \text{K, Rb, Cs}$) family. In the compounds with $A = \text{K}$ or Rb , the Ge–O bonds in the Ge_3O_3 central rings are a little longer than the outwardly directed Ge–O bonds towards SbO_6 octahedra. In KSbGe_3O_9 , these are atoms on a mirror plane m (at $x y \frac{1}{4}$ or $x y \frac{3}{4}$ special positions) which form the Ge_3O_3 ring as in the Wadeite-type structure^{30, 33}. Instead, in $\text{RbSbGe}_3\text{O}_9$, the mean plane through the atoms of the central-ring (at general $x y z$ positions) is tilted by 2.6° to the (001) plane, a value which remains rather weak compared to that in the $\text{A}_2\text{GeGe}_3\text{O}_9$ and $\text{BaGeGe}_3\text{O}_9$ structures. The Ge_3O_3 rings are distorted and tilted by $\sim 27^\circ$ in $\text{BaGeGe}_3\text{O}_9$ (11, 32) and by $\sim 22 - 25^\circ$ in the $\text{A}_2\text{Ge}_4\text{O}_9$ ($A = \text{Na, K, Rb, Tl, Ag}$) tetragermanate structures⁸⁻¹².

Another way to evaluate the structural distortion is to measure the Ge–O–Ge angles inside the Ge_3O_3 rings. Reported in the range $123 - 129^\circ$ for the trigonal $\text{A}_2\text{GeGe}_3\text{O}_9$ compounds^{28, 29, 31}, around 125° in $\text{BaGeGe}_3\text{O}_9$ ^{11, 32}, the Ge–O–Ge angle is 110.7° in KSbGe_3O_9 ⁵ and 109.6° in $\text{RbSbGe}_3\text{O}_9$ ⁶, close to the ideal T_d geometry. Note for comparison the Si–O–Si angle of 107.2° in the Wadeite structure³³. In other words, the distortions within the $(\text{Ge}_3\text{O}_9)^{6-}$ trimers and the subsequent changes in the Ge–O–Ge angles accommodate the size of the alkaline cations²⁸. Accordingly, the angle values of O–Ge–O bridges between outwardly directed Ge–O bonds, ranging between 110° and 112° , are lower than the corresponding angles measured close to 125° in the tetragermanate structures²⁸.

Regarding now the alkaline cations, they are enclosed in regular cages made of four trimers in the Wadeite-type structure. It has been specified that the enthalpies of formation become more exothermic with the size of the alkaline cation, thus the stability of the compound increases³³. In the $\text{A}_2\text{GeGe}_3\text{O}_9$ and $\text{BaGeGe}_3\text{O}_9$ tetragermanates, the cation environment is less regular

(i.e. with less uniform distribution of distances around the *A* or Ba position) due to the twist and the tilt of the Ge_3O_3 rings. Conversely, in the ASbGe_3O_9 family, the most regular environment around the *A* cation is observed for KSbGe_3O_9 , where the overlapping of the Ge_3O_3 central rings allows the formation of channels. It becomes less regular for $A = \text{Rb}$, due to the ring deformation (atoms slightly out of the *ab* plane), and distorted in $\text{CsSbGe}_3\text{O}_9$, which still contains channels but no more three-membered cycles. The size, but also the polarizability, of the *A* element present as a cation, is responsible for these structural modifications. The effective cationic radius increases from K^+ to Rb^+ and Cs^+ (1.52, 1.66, and 1.81 Å respectively for *CN*6 environments³⁴), and the polarizing power changes accordingly. Nevertheless, as Cs^+ cations are surrounded by 12 to 15 oxygen neighbors (between 3.2 and 4.1 Å), it is preferable to consider the *CN*12 value of 2.02 Å for the ionic radius. Likely, the ASbGe_3O_9 homologs with $A = \text{Li}$ or Na can never be obtained because the Li^+ and Na^+ cations are too small (ionic radii 0.90 and 1.16 Å for *CN*6, respectively) and too polarizing. On the contrary, the large and weakly polarizing Cs^+ cation, which lies at a distance of 3.04 Å from its closest oxygen neighbors in $\text{CsSbGe}_3\text{O}_9$ (vs. 2.87 - 2.92 Å for K^+ and Rb^+ ^{5,6}), provides the GeO_4 units an additional degree of freedom to position themselves relative to the surrounding tetrahedra. Therefore, the GeO_4 tetrahedra form chains (~ along *b*-axis) interconnected through SbO_6 octahedra within a 3-D framework with channels occurring along the *c*-axis, Figures 1 and 7.

Furthermore, bicyclic $(\text{Ge}_2\text{O}_3)_2\text{Sb}$ units, Figure 9, are present in the orthorhombic $\text{CsSbGe}_3\text{O}_9$ structure and the mean plane through the atoms of the SbGe_2O_3 rings is almost the equatorial plane of the SbO_6 octahedron. These units can be also formulated as $\text{Sb}(\text{Ge}_2\text{O}_3)_2\text{O}_{10}$ by taking into account the outward connections, $2 \times \text{Sb}-\text{O}$ and $8 \times \text{Ge}-\text{O}$.

Figure 9. The bicyclic $(\text{Ge}_2\text{O}_3)_2\text{Sb}$ units in the orthorhombic structure of $\text{CsSbGe}_3\text{O}_9$.

4.4 Spectroscopic features.

To close the discussion, let us return to the vibrational signature of $\text{CsSbGe}_3\text{O}_9$. Its IR and Raman spectra are different from the shape of the spectra obtained for both KSbGe_3O_9 and $\text{RbSbGe}_3\text{O}_9$ compounds, Figure 10.

Figure 10. (a) IR and (b) Raman spectra recorded at room temperature for compounds of the ASbGe_3O_9 family, $A = \text{K}, \text{Rb}, \text{Cs}$.

The 565 and 937 cm^{-1} frequency bands which are both IR and Raman active in K- and Rb-phases, are respectively due to Ge–O–Ge intra-cycle bending motions and to Ge–O symmetric stretching, both occurring in the Ge_3O_3 central-rings⁵. Both O and Ge atoms participate in

these vibration modes. These typical bands attributed to the three-membered rings do not appear in the spectra of the Cs-compound, which agrees with the lack of rings in its structure. Other significant changes can be expected based on the structural differences noted along with the ASbGe₃O₉ series and related to both the arrangement and symmetry of the polyhedra. A broadening, or even a splitting, of the bands associated with bending or stretching vibration modes that involve Ge–O–Ge bridges, is expected for CsSbGe₃O₉ as the dispersion of the angular values from 105 to 156° (average value of 133.5°) is slightly higher than in the trigonal structures with A = K and Rb ^{5, 6}. Likewise, the Ge–O–Sb angles display a large dispersion in the range 121 to 136° and their average value of 124.6° greatly deviates from the average values of ~134° measured for the K- and Rb- compounds ^{5, 6}.

The vibrational differences observed in the IR and Raman spectra of the compound CsSbGe₃O₉ and those with the same formula and A = K and Rb find their origin in all the structural specificities underlined above in the discussion part.

V. Conclusion

Transparent and colorless CsSbGe₃O₉ crystals have been spontaneously grown using a high-temperature flux method. No phase transition was observed up to their melting point detected at 1080 °C, which indicates good thermal stability in a large temperature range. The structure, determined from single-crystal X-ray diffraction data is most probably non-centrosymmetric despite our choice to report it in the centrosymmetric maximal supergroup *Pnma*. Physical characterizations as piezoelectric measurements could unambiguously answer this point as soon as CsSbGe₃O₉ single-crystals with a centimeter size could be obtained. The X-ray orthorhombic structure shows a 3-D open-framework built up of GeO₄ tetrahedra and SbO₆ distorted octahedra leading to inter-polyhedral Ge-O-Ge and Ge-O-Sb bridges. With infinite chains of regular tetrahedra GeO₄, it highly differs from the structures of the iso-formulated KSbGe₃O₉ and RbSbGe₃O₉ compounds. The increase in the size of the element A leads to a

loss of crystal symmetry in the $ASbGe_3O_9$ family, from $P\overline{6}c2$ (K) to $P31c$ (Rb), responsible for the disappearance of the Ge_3O_3 central-ring planarity, and from hexagonal/trigonal (K, Rb) to orthorhombic (Cs) which causes the disappearance of the (Ge_3O_9) trimers. The structural analysis mainly based on geometrical features and supported by literature reports tends to prove that the nature of the alkaline cations and the relative size of the constitutive elements play a dominant role in the formation and the stability of these compounds.

Acknowledgment

The EDX experiments were conducted at the Plateau Technique Microscopie à Balayage at the IEM Institute in Montpellier, France. IR, Raman and DSC measurements were done at the Platform of Analysis and Characterization (PAC) of the Pôle Chimie Balard in Montpellier, France. The X-ray diffraction experiments were done using the X-ray and gamma-ray network of the technological resource of Univ. Montpellier, France.

Supporting information

Table gathering the main bond lengths and angles around Sb and Ge atoms in $CsSbGe_3O_9$.

Funding information

Funding for this research was provided by the French Ministry of Higher Education, Scientific Research and Innovation, and the French National Center of Scientific Research (CNRS).

REFERENCES

- (1) Lignie A., Ménaert B., Armand P., Peña A., Debray J., Papet P., Top-Seeded Solution Growth and Structural Characterizations of α -Quartz-like Structure GeO_2 Single Crystal, *Cryst. Growth Des.*, **2013**, 13 4220-4225.
- (2) Papet P., Bath M., Haidoux A., Ruffle B., Menaert B., Peña A., Debray J., Armand P., High-temperature piezoelectric properties of flux-grown α - GeO_2 single crystal, *J. Appl. Phys.*, **2019**, 126, 144102.
- (3) Hermet P., Fraysse G., Lignie A., Armand P., Papet P., Density Functional Theory Predictions of the Nonlinear Optical Properties in α -Quartz-type Germanium Oxide, *J. Phys. Chem. C*, **2012**, 116, 8692-8698.
- (4) Lignie A., Granier D., Armand P., Haines J., Papet P., Modulation of quartz-like GeO_2 structure by Si substitution: an X-ray diffraction study of $\text{Ge}_{1-x}\text{Si}_x\text{O}_2$ ($0 \leq x < 0.2$) flux-grown single-crystals, *J. Appl. Cryst.*, **2012**, 45, 272-278.
- (5) Armand P., Hermet P., Tillard M., Haidoux A., Granier D., The open-framework structure of KSbGe_3O_9 flux-grown crystals investigated by X-ray diffraction, vibrational spectroscopy, and DFT calculations, *J. Solid State Chem.*, **2021**, 295, 121925.
<https://doi.org/10.1016/j.jssc.2020.121925>
- (6) Armand P., Tillard M., Haidoux A., Daenens L., Single-crystal growth, structure, and optical properties of a new non-centrosymmetric germanate, $\text{RbSbGe}_3\text{O}_9$, *J. Solid State Chem.*, **2020**, 286, 121290.
DOI: 10.1016/j.jssc.2020.121290
- (7) Zachariasen W. H., The Crystal Structure of Benitoite, $\text{BaTiSi}_3\text{O}_9$, *Z. Kristallogr. Cryst. Mater.*, **1930**, 74, 139-146.
- (8) Choisnet J., Deschanvres A., Tarte P., Spectres vibrationnels des silicates et germanates renfermant des anneaux, M_3O_9 ($\text{M}=\text{Si}, \text{Ge}$)-I. Attribution des fréquences caractéristiques de l'anneau M_3O_9 dans les composés de type bénitoïte, wadéïte et tétragermanate, *Spectrochim. Acta A*, 1975, 31, 1023-1034.
- (9) Choisnet J., Deschanvres A., Tarte P., Spectres vibrationnels des silicates et germanates renfermant des anneaux, M_3O_9 ($\text{M}=\text{Si}, \text{Ge}$)-II. Etude des spectres vibrationnels des silicogermanates de type bénitoïte : mise en évidence des anneaux mixtes (GeSi_2O_9) et (Ge_2SiO_9), *Spectrochim. Acta A*, 1976, 32, 57-66.
- (10) Goreaud M., Choisnet J., Deschanvres A., Raveau B., Synthèse et évolution structurale de nouveaux silicogermanates $\text{BaGe}(\text{Ge}_{3-x}\text{Si}_x)\text{O}_9$ de type benitoïte et de structure apparentée, *Mat. Res. Bull.*, **1973**, 8, 1205-1214.

- (11) Robbins C., Perloff A., Block S., Crystal Structure of BaGe(Ge₃O₉) and its Relation to Benitoite, *J. Res. Natl. Bur. Stand.*, **1966**, 70A, 385-391.
- (12) Takahashi Y., Iwasaki K., Masai H., Fujiwara T., Raman spectroscopic study of Benitoite-type compounds, *J. Ceram. Soc. Jpn.*, **2008**, 116, 1139-1142.
- (13) Robbins C. R., The Compound BaTiGe₃O₉, *J. Am. Ceram. Soc.*, **1960**, 4311, 610-610.
doi.org/10.1111/j.1151-2916.1960.tb13626.x
- (14) Choisnet J., Deschanvres A., Raveau B., Sur de nouveaux germanates et silicates de type Bénitoïte, *J. Solid State Chem.*, **1972**, 4, 209-2018.
- (15) APEX3. Version 2017.3-0, Bruker AXS, Inc., Madison, Wisconsin, USA, **2017**.
- (16) Sheldrick G. M., Crystal structure refinement with *SHELXL*, *Acta Cryst. C*, **2015**, 71, 3-8.
DOI : 10.1107/S2053229614024218
- (17) Sheldrick G. M., SHELXT - Integrated space-group and crystal-structure determination, *Acta Cryst. A*, **2015**, 71, 3-8.
DOI: 10.1107/S2053273314026370
- (18) Degen T., Sadki M., Bron E., König U., Nénert G., The HighScore suite, Powder Diff., **2014**, 29(S2), S13-S18.
- (19) <http://www.ccdc.cam.ac.uk/conts/retrieving.html> (or from the CCDC, 12 Union Road, Cambridge CB2 1EZ, UK; Fax: +44 1223 336033; E-mail: deposit@ccdc.cam.ac.uk).
- (20) Putz H., Brandenburg GbR K., Diamond - Crystal and Molecular StructureVisualization, Crystal Impact, *Kreuzherrenstr.* 102, 53227 Bonn, Germany
<http://www.crystalimpact.com/diamond>
- (21) Frayssé G., Lignie A., Hermet P., Armand P., Bourgogne D., Haines J., Ménaert B., Papet P., Vibrational origin of the thermal stability in the highly distorted α -quartz-type material GeO₂, an experimental and theoretical study, *Inorg. Chem.*, **2013**, 52, 7271-7279.
DOI: 10.1021/ic4009416
- (22) Cavalli E., Zannoni E., Bettinelli M., Speghini A., Tonelli M., Toncelli A., Vibrational properties of Ca₃Sc₂Ge₃O₁₂, a garnet host crystal for laser applications, *J. Phys.: Condens. Matter*, **2000**, 12, 4665- 4674.
- (23) Charton P., Armand P., Glasses in the TeO₂–Sb₂O₄ binary system, *J. Non-Cryst. Solids*, **2003**, 316, 189-197.

(24) Zhao H., Tan D., Tian Y., He Y., Li Y., Li X., Yang K., Chen B., Xiao W., Studies on Im-3-type KSbO₃ using high-pressure X-ray diffraction and Raman spectroscopy, *High Press. Res.*, **2018**, 38, 232-242.

<https://doi.org/10.1080/08957959.2018.1477941>

(25) Carvalho Castro Jr M., Viana Carvalho E. F., Paraguassu W., Pedro Ayala A., Snyder F. C., Lufasod M. W., William de Araujo Paschoal C., Temperature-dependent Raman spectra of Ba₂BiSbO₆ ceramics, *J. Raman Spectrosc.*, **2009**, 40, 1205–1210.
DOI 10.1002/jrs.226

(26) R. L. Frost, S. Bahfenne, A Review of the Vibrational Spectroscopic Studies of Arsenite, Antimonite, and Antimonate Minerals, *Appl. Spectrosc. Rev.*, **2010**, 452, 101-129.

(27) Redhammer G.J., Tippelt G., The polar phase of Li₂Ge₄O₉ at 298, 150, and 90 K, *Acta Cryst. C*, **2013**, 69, 1091-1095.

(28) Redhammer G.J., Tippelt G., The tetragermanates A₂Ge₄O₉ (A = Na, K and Rb), *Acta Cryst. C*, **2013**, 69, 995-1001

(29) Hazen R. M., Downs R. T., High-temperature and high-pressure crystal chemistry, *Reviews in Mineralogy & Geochemistry*, Book 41, **2018**, Eds Walter de Gruyter GmbH & Co KG

(30) Henshaw D. E., The structure of Wadeite, *Mineral. Mag. J. Mineral. Soc.*, **1955**, 30, 585-595.

(31) Goreaud M., Raveau B., Structure Cristalline de Rb₂Ge₄O₉ et Rb₂TiGe₃O₉ de Type 'tetragermanate' et Etude Structurale Comparée de Germanates en Anneaux, *Acta Cryst. B*, **1976**, 32, 1536.

(32) Shashkov A.Y., Rannev N.V., Venevtsev Y.N., Atomic Structure of Crystals of α-PbGe₄O₉, BaGe₄O₉, and Pb_{2/3}Sr_{1/3}Ge₄O₉ and Features of the Coordination of Germanium Atoms in Framework Tetragermanates, *Sov. J. Coord. Chem.*, **1984**, 10, 787-794.

(33) Xu H., Navrotsky A., Balmer M.L., Su Y., Crystal-chemical and energetic systematics of Wadeite-type phases A₂BSi₃O₉ (A = K, Cs; B = Si, Ti, Zr), *Phys. Chem. Miner.*, **2005**, 32, 426-435.

(34) Shannon R.D., Revised Effective Ionic Radii and Systematic Studies of Interatomic Distances in Halides and Chalcogenides, *Acta Cryst. A*, **1976**, 32, 751-767.

(35) Bärnighausen H., Group-subgroups relations between space groups: a useful tool in crystal chemistry *MATCH, Commun. Math. Chem.*, **1980**, 9, 139-175.

- (36) Müller U, Inorganic Structural Chemistry, ISBN 978-0-470-01865-8 Wiley, 2007
- (37) Ivantchev, S., Kroumova, E., Madariaga, G., Pérez- Mato, J.M., Aroyo, *SUBGROUPGRAPH*: a computer program for analysis of group–subgroup relations between space groups, *J. Appl. Cryst.* **2000**, 33, 1190-1191.

For Table of Contents Only

The germanate $CsSbGe_3O_9$, grown spontaneously from a high-temperature solution of $Cs_2Mo_4O_{13}$ used as a flux, is characterized by X-ray diffraction and IR-Raman spectroscopies. Regular GeO_4 tetrahedra and SbO_6 octahedra arranged in a 3-D orthorhombic lattice leave channels hosting the Cs^+ cations. The structural evolution within the family $ASbGe_3O_9$ is discussed related to the literature and the nature of the monovalent alkaline cation A (K, Rb, Cs).