Cineole-containing nanoemulsion: Development, stability, and antibacterial activity

Tayonara Lima, Maria Fátima S. Silva, Xirley Nunes, Andrea Colombo, Helinando Oliveira, Patrícia Goto, Henrique Piva, Antonio Tedesco, Marigilson Siqueira-Moura, Muriel Blanzat

► To cite this version:

Tayonara Lima, Maria Fátima S. Silva, Xirley Nunes, Andrea Colombo, Helinando Oliveira, et al.. Cineole-containing nanoemulsion: Development, stability, and antibacterial activity. Chemistry and Physics of Lipids, 2021, 239, pp.105113. 10.1016/j.chemphyslip.2021.105113 . hal-03341888

HAL Id: hal-03341888

<https://hal.science/hal-03341888>

Submitted on 18 Oct 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Cineole-containing nanoemulsion: development, stability, and antibacterial activity

Tayonara S. Lima^a, Maria Fátima S. Silva^a, Xirley P. Nunes^{a,b}, Andrea V. Colombo^{a,b},
Helinando P. Oliveira^c, Patrícia L. Goto^d, Muriel Blanzat^d, Henrique L. Piva^e, Antonio C.
Tedesco^e, Marigilson P. Siqueira-Moura^{a,b}

^aGraduate Program in Biosciences (PPGB), Federal University of the São Francisco
Valley (UNIVASF), Petrolina, Pernambuco 56304-205, Brazil

^bCollege of Pharmaceutical Sciences (CFARM), Federal University of the São Francisco
Valley (UNIVASF), Petrolina, Pernambuco 56304-205, Brazil

^cGraduate Program in Materials Science (PPGCM), Federal University of the São
Francisco Valley (UNIVASF), Juazeiro, Bahia 48902-300, Brazil

^dIMRCP Laboratory, UMR 5623 CNRS, Paul Sabatier University, 31062 Toulouse,
France

^eDepartment of Chemistry, Center of Nanotechnology and Tissue Engineering -
Photobiology and Photomedicine Research Group, Faculty of Philosophy, Sciences and
Letters of Ribeirão Preto (FFCLRP), University of São Paulo (USP), Ribeirão Preto, São
Paulo 14040-901, Brazil

*Corresponding author:

Prof. Marigilson Pontes de Siqueira Moura, Ph.D.

College of Pharmaceutical Sciences – UNIVASF

Prédio dos Colegiados, Av. José de Sá Maniçoba, S/N, 56304-917, Centro, Petrolina-PE,
Brazil. Phone: +55 87 21016862, E-mail address: marigilson.moura@univasf.edu.br

Abstract

1,8-cineole is a monoterpene commonly used by the food, cosmetic, and pharmaceutical industries owing to its flavor and fragrances properties. In addition, this bioactive monoterpene has demonstrated bactericidal and fungicidal activities. However, such activities are limited due to its low aqueous solubility and stability. This study aimed to develop nanoemulsion containing cineole and assess its stability and antibacterial activity in this context. The spontaneous emulsification method was used to prepare nanoemulsion (NE) formulations (F1, F2, F3, F4, and F5). Following the development of NE formulations, we chose the F1 formulation that presented an average droplet size (in diameter) of about 100 nm with narrow size distribution (PdI <0.2) and negative zeta potential (~ -35 mV). According to the analytical centrifugation method with photometric detection, F1 and F5 formulations were considered the most stable NE with lower droplet migration velocities. In addition, F1 formulation showed high incorporation efficiency (> 80 %) and TEM analyses demonstrated nanosized oil droplets with irregular spherical shapes and without any aggregation tendency. Antibacterial activity assessment showed that F1 NE was able to enhance the cineole action against *Staphylococcus aureus*, *Enterococcus faecalis*, and *Streptococcus pyogenes*. Therefore, using a simple and reproducible method of low energy emulsification we designed a stable nanoemulsion containing 1,8-cineole with improved antibacterial activity against Gram-positive strains.

Keywords: 1,8-cineole, Spontaneous emulsification, Nanoemulsion, Stability, Antibacterial activity.

1. Introduction

In nature, bioactive oils based on terpene (isoprene) and terpenoid compounds are synthesized by aromatic plants as secondary metabolites, commonly known as essential oils (EO) or volatile oils. Monoterpenes are formed by two isoprene units (10 carbon atoms) and constitute more than 80 % of EO composition (Asbahani et al., 2015; Bakkali et al., 2008; Bilia et al., 2014; Matos et al., 2019; Slamenova and Horvathova, 2013). According to each plant source, EO comprise widely varied monoterpenes, sesquiterpenes, and phenylpropenes combinations. There is a terpenic oxide among such monoterpenes, namely 1,8-cineole ($C_{10}H_{18}O$; M.W. 154.25 g mol⁻¹), which is a cyclic ether found as the main constituent in EO obtained from eucalyptus species. This monoterpene is a limpid and colorless oily liquid with a strong camphor-like odor and also called 1,8-epoxy-p-menthane, eucalyptol, and cajeputol (Adak et al., 2020; Ali et al., 2015; De Vincenzi et al., 2002; Salehi et al., 2019; Slamenova and Horvathova, 2013). Owing to its bactericidal and fungicidal activities as well as flavor and fragrances properties, 1,8-cineole has been used by food, cosmetic, and pharmaceutical industries. However, despite all these applications, the use of 1,8-cineole or EO containing this terpene is limited due to its limited thermal stability, substantial volatility, and low water solubility (Adak et al., 2020; Hammoud et al., 2019; Prakash et al., 2018a; Prakash et al., 2018b).

In order to prevent terpenes and phenylpropanoid derivatives volatilization or oxidation, as well as their degradation by light and for improving the chemical stability, the encapsulation of these compounds into nanostructured systems has been commonly used. Several nanocarriers have been well designed to entrap EO or their main compounds in this context. Among these carriers, the choice covers polymeric nanocapsules or nanoparticles, liposomes, phytosomes, nanoemulsions, microemulsions, solid lipid

nanoparticles, and nanostructured lipid carriers (Asbahani et al., 2015; Bilia et al., 2014; Harwansh et al., 2019; Matos et al., 2019; Prakash et al. 2018a; Prakash et al., 2018b; Zhao et al., 2016).

Oil-in-water nanoemulsion is the most often-used colloidal lipid carrier to incorporate EO. According to recent review conducted by Matos et al. (2019), almost half of all nanostructured systems containing EO was represented by nanoemulsified dispersions. Nanoemulsions (NE) are ultrafine dispersions constituted of two immiscible liquids (organic and aqueous phases) stabilized by surfactant(s). Despite being considered nonequilibrium systems (thermodynamically unstable), nanoemulsions are metastable or kinetically stable colloidal dispersions (Anton and Vandamme, 2011; Gupta et al., 2016; Helgeson, 2016; Komaiko and McClements, 2016; Singh et al., 2017; Solans and Solé, 2012).

In general, nanoemulsions are produced using low or high-energy methods. High-energy emulsification approaches, i.e., work-based emulsification methods, usually require sophisticated and expensive devices, namely high-pressure homogenizers, ultrasound generators, and microfluidizers. On the other hand, low-energy methods or thermodynamic methods are easy production processes based on simple stirring and changing some formulation parameters, e.g., surfactant concentration and type, oil-water ratio, temperature, etc. Usually low-energy emulsification methods have been categorized as phase inversion composition, phase inversion temperature, emulsion inversion point, and spontaneous emulsification (Anton and Vandamme, 2009; Gupta et al., 2016; Helgeson, 2016; Komaiko and McClements, 2016; Safaya and Rotliwala, 2020; Singh et al., 2017; Solans and Solé, 2012).

The main reason for incorporating EO or their major constituents into the lipid core of nanoemulsion is directly related to bioactive molecules improving their stability and

subsequent enhanced bioefficacy (Asbahani et al., 2015; Bilia et al., 2014; Harwansh et al., 2019; Matos et al., 2019). Also, EO-based nanoemulsion formulations have received increasing attention as effective nanocarriers improving antimicrobial activity of bioactive components (Prakash et al., 2018a; Prakash et al., 2018b). Nevertheless, available information about preparation, stability, and biological activities of nanoemulsions containing isolated bioactive compounds from EO is still scarce, requiring more investigations. Therefore, this study aimed to develop cineole-containing nanoemulsion formulation using an isothermal low-energy emulsification method and assess its accelerated stability and antibacterial activity.

2. Materials and methods

2.1 Materials

1,8-Cineole (Eucalyptol 99 %, $d = 0.921 \text{ g mL}^{-1}$ at 25°C), sorbitan monooleate (SMO), polyoxyethylen-20 sorbitan monolaurate (SML-20), polyoxyethylen-20 sorbitan monooleate (SMO-20), sodium phosphate monobasic, and sodium phosphate dibasic were purchased from Sigma-Aldrich Co. (St. Louis, MO, USA). Medium-chain triglycerides (MCT, $d = 0.94 \text{ g mL}^{-1}$ at 20°C) oil was kindly supplied from Brasquim (Porto Alegre-RS, Brazil).

2.2 Nanoemulsion preparation

Nanoemulsions (NE) were prepared using a method based on a spontaneous emulsification procedure described by Saberi et al. (2014) with slight modifications. Briefly, spontaneous emulsification was carried out by addition of an organic phase consisting of carrier oil (MCT), 1,8-cineole, and surfactant(s), to an aqueous phase

(phosphate buffer solution pH 7.4) under magnetic stirring (200 rpm) and ambient temperature kept constant throughout process. Initially, different ratios between phases and surfactant mixtures were assessed to find more suitable formulations resulting in final composition (wt. %) of the five nanoemulsions reported in Table 1. Thus, both carrier oil-to-cineole and surfactant-to-oil weight ratios were kept constant at 1.0 and 2.0, respectively. The proportion of surfactant:oil:water was set at 10:10:80 (wt. %), respectively, and for F1, F3, and F5 formulations the surfactant combinations were maintained at HLB 12 (Table 1). All formulations were prepared three times (n=15) and stored at 4 °C (± 2). Unloaded NE (F5 formulation) was obtained from organic phase composed only of carrier oil (MCT) and surfactants using the same spontaneous emulsification process.

Table 1.

Composition (wt. %) of NE formulations.

NE	SML-20	SMO-20	SMO	MCT	Cin	PBS
F 1	6.2	-	3.8	5.0	5.0	80
F 2	10	-	-	5.0	5.0	80
F 3	-	7.2	2.8	5.0	5.0	80
F 4	-	10	-	5.0	5.0	80
F 5	6.2	-	3.8	10	-	80

SML-20: polyoxyethylen-20 sorbitan monolaurate; SMO-20: polyoxyethylen-20 sorbitan monooleate; SMO: sorbitan monooleate; MCT: medium-chain triglycerides; Cin: 1,8-cineole; PBS: 10 mM phosphate buffer solution pH 7.4.

2.3 Droplet size measurement

The hydrodynamic diameter of droplets and polydispersity index (PdI) of the NE formulations were determined by photon correlation spectroscopy (PCS) at 25 °C and a scattering angle of 173° (Zetasizer® Nano ZS, Malvern PCS Instruments, UK). All samples were diluted (1/100) with ultra-purified water. The reported values are average $\pm$ SEM of three different batches of each colloidal dispersion.

2.4 Zeta potential measurement

Zeta (ζ) potential of NE was measured by electrophoretic mobility using a Zetasizer® Nano ZS apparatus (Malvern PCS Instruments, UK). The Smoluchowski model was used to estimate ζ potential from electrophoretic mobility. The analyses were conducted at 25 °C, and the samples were appropriately diluted (1/100) with ultra-purified water. Values reported are average $\pm$ SEM of three different batches of each colloidal dispersion.

2.5 Forced stability study

Stability study was performed using the analytical centrifugation method with photometric detection at 865 nm (LUMiSizer® 611, LUM GmbH, Germany). The samples of NE formulations were incorporated into polycarbonate cell and equilibrated to 25 °C before analyses. Measurements were carried out at 3,618 rpm for 4.5 h resulting in accelerated migration of the droplets and integration of transmission profiles within a selected region of the holding cell allowed to get information about dispersion stability. The analyses were carried out using specific cuvettes with a radius position of 129.5 mm and based on results, it was possible to predict the shelf life of the NE samples from following equation (1) (Goto et al., 2017):

$$\text{Shelf life (seconds)} = \text{Measurement time} \times \text{Relative Centrifugal Force} \quad (1)$$

2.6 Incorporation efficiency

1,8-cineole was determined using a UV spectrophotometric method described by Yin et al. (2021), with slight modifications. Calibration curves were constructed for 1,8-cineole in n-hexane at different concentrations (w/v) and their absorbances detected at 250 nm using an Even UV/VIS spectrophotometer (Ionlab, Paraná, Brazil). Total monoterpene amount in the F1 formulation was assessed with the addition of an aliquot of the formulation in n-hexane (1:3, v/v). This mixture was put in an ultrasonic bath at 30 °C for 30 min, and then centrifuged at 4,000 rpm for 20 min. Next, the amount of 1,8-cineole was determined in the upper phase using UV spectrophotometric method as mentioned above. Free 1,8-cineole amount was determined by measuring the non-incorporated monoterpene present in a clear ultrafiltrate obtained through separation of aqueous phase using an ultrafiltration/ultracentrifugation procedure (Microcon Ultracel YM-100, Millipore, Ireland) at 10,583 x g for 60 min at 4 °C (*novatecnica*, Microcentrifuge NT 805, Piracicaba-SP, Brazil). The same procedure used to determine 1,8-cineole in NE formulation was applied to quantify free monoterpene fraction in the dispersion medium (aqueous phase). All analyses were performed in triplicate and the incorporation efficiency (IE %) of 1,8-cineole in F1 formulation was calculated from following equation (2) (Rodrigues et al., 2018):

$$IE (\%) = (TCin - FCin / ThCin) \times 100 \quad (2)$$

Where, TCin is the total 1,8-cineole amount; FCin, free 1,8-cineole amount; ThCin, theoretical 1,8-cineole amount.

2.7 Electron microscopy analysis

NE formulation was analyzed using transmission electron microscopy (TEM) technique. Aliquots (~ 100 µL) of cineole nanoemulsion (F1 formulation) were put onto copper TEM

195 grids and negatively stained with 1 % (w/v) sodium phosphotungstate solution; the excess
196 sample was thoroughly removed by filter paper. After that, the samples were dried at
197 room condition before analyses. Transmission electron micrographs of the samples were
198 taken using a Microscope HT7700 Hitachi (Fukuoka, Japan) operated at accelerating
199 voltage of 80 KV and emission 12 μ A.

201 **2.8 Antibacterial activity assay**

202 The minimal bactericidal concentration of free 1,8-cineole and cineole nanoemulsion (F1
203 formulation) were determined by microdilution techniques in Mueller-Hinton broth
204 (MHB) (CLSI, 2018). Briefly, serial twofold dilutions of free 1,8-cineole and F1
205 formulation were carried out in MHB using 96-well microplates. Bacterial suspension
206 (10^8 CFU mL⁻¹) cultured in TSB at 37 °C for 24 h were inoculated onto wells (200 μ L
207 final volume). Microplates were incubated at 35 °C for 24 h. Bacterial growth control
208 (MHB+ strain + DMSO 10 %), sterility control (MHB), and positive controls with
209 gentamicin and chlorhexidine digluconate were performed simultaneously on assays. An
210 aliquot of 10 μ L of each well was inoculated on Mueller-Hinton Agar (MHA) at 37 °C
211 for 24 h for colonies growth. Minimal bactericidal concentration was defined as the
212 lowest 1,8-cineole or F1 concentration that did not allow visible growth on MHA agar.
213 Experiments were performed three times.

215 **2.9 Statistical analysis**

216 All experiments were performed three times and data are expressed as average value
217 ($\pm$ SEM). Statistical analysis was performed by One-way ANOVA followed by Tukey's
218 pairwise comparisons using the Prism GraphPad Software. The statistical significance
219 was set at $p < 0.05$.

3. Results and discussion

In this study, cineole nanoemulsions were prepared using the spontaneous emulsification method as an isothermal approach applied to volatile and hydrophobic organic compounds. In order to prepare colloidal dispersions containing 1,8-cineole, as aqueous phase was used PBS (pH 7.4) while organic phase consisted of a mixture of cineole and MTC (1:1 w/w), and different types of surfactants.

For emulsions obtained herein, there was a variation of visual appearance among the fluid nanoemulsified dispersions from slightly turbid with bluish reflection to milky opaque dispersion reflecting directly the dispersed phase formed in each colloidal formulation. As shown in Table 2, the main properties of nanoemulsified systems were dependent on both surfactant types and organic phase composition. The types of nonionic surfactants used in the formulations demonstrated a considerable influence over droplet average diameter and size distribution of the colloidal dispersions. Hence, the smallest droplets (<115 nm) and with the narrowest size distribution (PdI <0.2 and monomodal) were observed for F1 formulation ($p < 0.05$), which was prepared containing SML-20 and SMO as pair of nonionic surfactants. In contrast, the largest droplets with broader size distribution were noticed from dispersion prepared with SMO-20 and SMO surfactants (F3 formulation). Likewise, for those formulations containing only SML-20 or SMO-20 as a surfactant, i.e., F2 and F4 formulations, respectively, the droplet average sizes were higher than 150 nm and the droplet size distribution was bimodal with PdI values above 0.2. Moreover, when the organic phase composition was altered to contain only MCT carrier oil, the droplet average diameter and size distribution were significantly larger than other NE formulations, as can be particularly observed comparing F1 and F5 formulations ($p < 0.05$). Similarly, the organic phase composition also influenced both

droplet size e PDI of NE formulations, e.g., F5 formulation, whose organic phase consisted entirely of MCT oil presented relatively large droplets ($p < 0.05$). This result is in accord with earlier research developed by Saberi et al. (2013) in which the increasing MCT oil concentrations resulted in larger droplets from mini-emulsions. Such influence might be explained by the significant impact of the MCT carrier oil on surfactant spontaneous curvature and solubility affecting directly formation of small droplets (Komaiko and McClements, 2016; Saberi et al., 2014).

The mechanism assigned to the formation of small-sized droplets using spontaneous emulsification is directly connected to the fast displacement of surfactant(s) from organic phase into aqueous phase. Afterward, both phases come into contact; this mixture results in the rapid diffusion of surfactant(s) from organic to aqueous phase producing turbulence at oil/water interface and consequent formation of fine droplets (Anton and Vandamme, 2009; Komaiko and McClements, 2016; Saberi et al., 2013). It is commonly recognized that some factors can affect the formation and stability of nanodroplets designed from spontaneous emulsification approach. Among such factors are organic phase composition, type and concentration of surfactant(s) and/or cosurfactant(s), and conditions related to emulsifying process (Helgeson, 2016; Komaiko and McClements, 2016).

Zeta (ζ) potential reflects surface charge of droplets and it has been related to stability of colloidal formulations. High surface charge density may imply NE's long-term physical stability due to relevant repulsive electrostatic forces among the droplets preventing rapid aggregation and flotation of dispersed phase (McClements and Gumus, 2016; Singh et al., 2017). All NE formulations presented significant negative values of zeta potential (< -20 mV, Table 2) which may be related to free ionized groups from components of organic phase. It is worth mentioning that additionally electrostatic stabilization of the

dispersed phase, the nanoemulsion physical stability is also a result of van der Waals, hydrophobic, and steric interactions among droplets (Gupta et al., 2016; Helgeson, 2016; McClements and Gumus, 2016; Singh et al., 2017).

Table 2.

Droplet size (hydrodynamic diameter), polydispersity index (PdI), and ζ potential of NE formulations (average $\pm$ SEM, n = 3).

NE	Size (nm)	PdI	ζ potential (mV)
F1	111.5 ($\pm$ 0.79) ^a	0.182 ($\pm$ 0.007) ^b	– 36.75 ($\pm$ 0.33)
F2	203.4 ($\pm$ 6.68)	0.303 ($\pm$ 0.017)	– 29.43 ($\pm$ 0.54)
F3	212.8 ($\pm$ 8.67)	0.223 ($\pm$ 0.004)	– 38.60 ($\pm$ 0.17)
F4	159.3 ($\pm$ 1.28)	0.240 ($\pm$ 0.015)	– 19.75 ($\pm$ 0.36) ^c
F5	264.5 ($\pm$ 1.17)	0.321 ($\pm$ 0.014)	– 42.02 ($\pm$ 0.42)

^ap <0.05 compared to F2, F3, F4, and F5 formulations concerning size.

^bp <0.05 compared to F2, F3, F4, and F5 formulations concerning PdI.

^cp <0.05 compared to F1, F2, F3, and F5 formulations concerning ζ potential.

Once nanosized oil droplets are formed, it is essential that their stability can be assessed throughout the formulation lifetime. In this study, centrifugal separation analysis with photometric detection enabled physical stability assessment of the NE formulations. The analytical photocentrifugation method is based on the measurement of droplet migration by applying a centrifugal force and photometric detection using near-infrared (NIR) light. This light passes throughout the sample and then the transmitted light intensity is detected by sensors forming profiles of light transmission as a function of time and position. The shape and gradual change process of the light transmission profiles through tested

samples allow the analysis of separation kinetics of dispersed phase from continuous phase in colloidal dispersions enabling a comparison of long-term stability among NE formulations (Fernandes et al., 2017). For each NE sample, 255 transmission profiles were recorded in intervals of 65 s, and flotation velocities of oil droplets from undiluted samples of the NE were determined at 25 °C (Table 3).

Fig. 1 shows NIR transmission profiles obtained for F1 and F5 formulations while Fig. 2 shows transmission profiles for F2, F3, and F4 formulations. F1 and F5 formulations presented similar transmission profiles (Fig. 1) with the lowest clarification process, i.e., minimal phase separation due to the dispersed phase's flotation. These results were confirmed by flotation velocity obtained for F1 and F5; for these two formulations, the flotation velocities were the lowest among all samples as well as a narrower velocity distribution was also observed with only slight speed variation of droplet migration between D10 % and D90 % as shown in Table 3. Thus, we considered that F1 and F5 were the most stable NE formulations. Moreover, this result confirms that the inclusion of 1,8-cineole in the nanoemulsified system could not alter long-term formulation stability. Meanwhile, F2, F3, and F4 formulations showed a strong clarification behavior (Fig. 2) resulting in a significant creaming separation process and a wider distribution of droplet flotation velocity when compared with F1 and F5. These findings indicate that a substantial droplet aggregation might take place during the storage period for F2, F3, and F4 formulations resulting in more fast flotation due to larger oil droplets and/or their aggregates in the colloidal dispersion. In spite of different droplet sizes between F1 and F5 formulations, the packing of surfactant molecules adsorbed could result in a shielding coating in the oil droplets preventing aggregation of the dispersed phase and consequent improvement physical stability of these formulations. Therefore, such an outcome may be attributed to the surfactant monolayer's optimum curvature formed at oil/water

interface of droplets in the F1 and F5 nanoemulsions (Komaiko and McClements, 2015; Saberi et al., 2013).

Fig. 1. Normalized NIR transmission profiles obtained with cineole-containing NE (F1) and unloaded NE (F5) formulations by accelerated stability analysis during analytical centrifugation. The first and the last registered profiles are shown in red and in green, respectively.

The main destabilization mechanisms of nanoemulsified systems are related to close contact among droplets which may result in flocculation, Ostwald ripening, coalescence, and lastly phase separation. Thus, any aggregation process of the dispersed phase may trigger such instabilities and, consequently, the coarsening of the colloidal formulations (Gupta et al., 2016; Helgeson, 2016; Singh et al., 2017). In this study, it seems reasonable to assume that the adsorbed layer of SML-20 and SMO surfactants on the oil droplets

increased the steric stabilization of F1 and F5 formulations avoiding oil droplet aggregation. It is also important to note that the addition of MCT carrier oil to formulation could prevent droplets' growth caused by instability primary mechanism of nanoemulsions known as Ostwald ripening, which is characterized as the mass transfer from smaller to the larger oil droplets (Gupta et al., 2016; Helgeson, 2016). Furthermore, considering that there was no signal of instability for F1 and F5 formulations as well as this analysis at 3,618 rpm for 4.5 h corresponded to a predicted shelf life of 12 months, we could consider F1 and F5 NE as stable formulations for a such period of time. Accordingly, in view of all results described above, concerning NE formulation having the smallest oil droplets and narrow size distribution along with improved physical stability, we selected F1 formulation for further studies. Moreover, as expected the assessment of the incorporation efficiency of 1,8-cineole in NE formulation (F1) confirmed high entrapment (86.3 % $\pm$ 0.87) into dispersed phase mainly due to limited water solubility of this monoterpene.

Table 3.

Distribution (D) of velocity ($\mu\text{m s}^{-1}$) from droplet flotation of NE formulations measured at 25 °C using analytical photocentrifugation.

NE	D10 % ($\mu\text{m s}^{-1}$)	D50 % ($\mu\text{m s}^{-1}$)	D90 % ($\mu\text{m s}^{-1}$)	Mean velocity ($\pm$ S.D.)
F1	1.280	1.619	2.290	1.634 ($\pm$ 0.377)
F2	1.605	89.190	260.551	4.462 ($\pm$ 104.703)
F3	1.510	3.106	199.099	3.140 ($\pm$ 82.126)
F4	1.820	168.326	268.696	8.540 ($\pm$ 94.195)
F5	1.291	1.641	2.279	1.645 ($\pm$ 0.364)

348

349 **Fig. 2.** Normalized NIR transmission profiles obtained with F2, F3, and F4 NE
 350 formulations by accelerated stability analysis during analytical centrifugation. The first
 351 and the last registered profiles are shown in red and in green, respectively.

352

353 Transmission electron microscopy (TEM) has been considered a successful technique in
 354 order to analyze size and shape droplets, size distribution, and agglomeration tendency of
 355 the dispersed phase in nanoemulsified systems (Falsafi et al., 2020). TEM analyses were

carried out for F1 formulation and images are depicted in Fig. 3. As can be noted from photomicrographs, throughout F1 formulation non-aggregated oil droplets with irregular spherical shapes were observed. Furthermore, oil droplet sizes viewed by TEM technique were similar to those measured by dynamic light scattering analysis. All these findings confirm the presence of nanosized oil droplets with uniform size distribution in the F1 formulation and its enhanced physical stability as previously related.

Fig. 3. TEM photomicrographs of cineole-containing NE (F1 formulation). Magnifications (A) x7.0K, (B) x12.0K, and (C) x20.0K.

The potential activity of free 1,8-cineole and cineole NE (F1 formulation) against *Staphylococcus aureus*, *Enterococcus faecalis*, and *Streptococcus pyogenes* strains was assessed using the broth microdilution method. As depicted in Table 4, the bactericidal concentrations of nanoemulsion containing 1,8-cineole were 2-fold lower than those found for free 1,8-cineole. More specifically, *S. aureus* and *E. faecalis* were more sensitive to the cineole NE when compared to free monoterpene, i.e., nanoemulsified cineole was the most effective in killing these two bacteria. Meanwhile, cineole nanoemulsion was only slightly more active against *S. pyogenes* in comparison with free cineole (Table 4). Both gentamicin (1.66 mg mL^{-1}) and chlorhexidine digluconate (1.2

mg mL⁻¹) were found to be more active than pure cineole or cineole-NE against Gram-positive bacteria.

Unlike these findings herein about free and nanoemulsified cineole against Gram-positive strains, Harkat-Madouri et al. (2015) found that the essential oil of *Eucalyptus globulus*, in which the major compound was 1,8-cineole, was more active against Gram-negative strains. Despite this, it is claimed that EO are relatively less active against Gram-negative than Gram-positive microorganisms due to the uppermost layer of lipopolysaccharide present on Gram-negative bacteria, thus limiting the diffusional process of lipophilic molecules (Harkat-Madouri et al., 2015; Prakash et al., 2018a). Furthermore, the enhanced antibacterial activity from nanoemulsified cineole could mainly be related to the increased surface area from ultra-small sized droplets in the nanoemulsion formulation allowing passive transport through the outer cell membrane (Prakash et al., 2018a).

Table 4.

Minimal bactericidal concentrations of free cineole and cineole-containing nanoemulsion (F1 NE formulation) against Gram-positive bacteria.

Bacterial strains	Free cineole (mg mL ⁻¹)	Cineole-NE (mg mL ⁻¹)
<i>Staphylococcus aureus</i>	28.6	14.0
<i>Enterococcus faecalis</i>	28.6	14.0
<i>Streptococcus pyogenes</i>	28.6	24.0

4. Conclusions

In summary, we have designed nanoemulsions containing 1,8-cineole using low energy emulsification, which is commonly known as spontaneous emulsification method. The

most stable nanoemulsion formulation (F1) consisted mainly of very small sized droplets with monomodal size distribution, and negative zeta potential. Stability study demonstrated that F1 formulation could be considered stable with lower droplet migration velocity. In addition, high incorporation efficiency of 1,8-cineole into F1 formulation was demonstrated and also the photomicrographs from TEM analysis confirmed that F1 formulation was formed by nanosized droplets and no aggregation tendency. Antibacterial activity of cineole nanoemulsion against *S. aureus* and *E. faecalis* was enhanced (2-fold) compared to free 1,8-cineole. Hence nanoemulsified dispersions could be considered like a relevant lipid nanocarrier applied for inclusion of hydrophobic terpenic compounds. Moreover, these results encourage further studies about antibacterial activity of nanoemulsified cineole on preservation of food, cosmetic, and pharmaceutical products.

Acknowledgments

This study was supported by CAPES/COFECUB agreement (#Ph-C 859-15).

References

- Adak, T., Barik, N., Patil, N.B., Govindharaj, G.-P.-P., Gadratagi, B.G., Annamalai, M., Mukherjee, A.K., Rath, P.C., 2020. Nanoemulsion of eucalyptus oil: An alternative to synthetic pesticides against two major storage insects (*Sitophilus oryzae* (L.) and *Tribolium castaneum* (Herbst)) of rice. *Ind. Crop. Prod.* 143, Article 111849. <https://doi.org/10.1016/j.indcrop.2019.111849>.
- Ali, B., Ali Al-Wabel, N., Shams, S., Ahamad, A., Alam Khan, S., Anwar, F., 2015. Essential oils used in aromatherapy: A systemic review. *Asian Pac. J. Trop. Biomed.* 5, 601–611. <http://dx.doi.org/10.1016/j.apjtb.2015.05.007>.

422 Anton, N., Vandamme, T.F., 2009. The universality of low-energy nano-emulsification.
 423 Int. J. Pharm. 377, 142–147. <http://dx.doi.org/10.1016/j.ijpharm.2009.05.014>.
 424 Anton, N., Vandamme, T.F., 2011. Nano-emulsions and Micro-emulsions: Clarifications
 425 of the Critical Differences. Pharm. Res. 28, 978–985. [http://dx.doi.org/10.1007/s11095-](http://dx.doi.org/10.1007/s11095-010-0309-1)
 426 [010-0309-1](http://dx.doi.org/10.1007/s11095-010-0309-1).
 427 Asbahani, A.E., Miladi, K., Badri, W., Sala, M., Aït Addi, E.H., Casabianca, H.,
 428 Mousadik, A.E., Hartmann, D., Jilale, A., Renaud, F.N.R., Elaissari, A., 2015. Essential
 429 oils: From extraction to encapsulation. Int. J. Pharm. 483, 220–243.
 430 <http://dx.doi.org/10.1016/j.ijpharm.2014.12.069>.
 431 Bakkali, F., Averbeck, S., Averbeck, D., Idaomar, M., 2008. Biological effects of
 432 essential oils – A review. Food Chem. Toxicol. 46, 446–475.
 433 <http://dx.doi.org/10.1016/j.fct.2007.09.106>.
 434 Bilia, A.R., Guccione, C., Isacchi, B., Righeschi, C., Firenzuoli, F., Bergonzi, M.C., 2014.
 435 Essential Oils Loaded in Nanosystems: A Developing Strategy for a Successful
 436 Therapeutic Approach. Evid.-Based Complementary Altern. Med. Article 651593.
 437 <http://dx.doi.org/10.1155/2014/651593>.
 438 CLSI, (2018). Clinical and Laboratory Standards Institute (CLSI). Methods for dilution
 439 antimicrobial susceptibility tests for bacteria that grow aerobically. 11th ed. CLSI
 440 standard M07. Wayne, PA USA.
 441 De Vincenzi, M., Silano, M., De Vincenzi, A., Maialetti, F., Scazzocchio, B., 2002.
 442 Constituents of aromatic plants: eucalyptol. Fitoterapia 73, 269–275.
 443 [https://doi.org/10.1016/S0367-326X\(02\)00062-X](https://doi.org/10.1016/S0367-326X(02)00062-X).
 444 Falsafi, S.R., Rostamabadi, H., Assadpour, E., Jafari, S.M., 2020. Morphology and
 445 microstructural analysis of bioactive-loaded micro/ nanocarriers via microscopy

446 techniques; CLSM/SEM/TEM/AFM. *Adv. Colloid Interface Sci.* 280, Article 102166.
 447 <https://doi.org/10.1016/j.cis.2020.102166>.

448 Fernandes, A.R., Ferreira, N.R., Fanguero, J.F., Santos, A.C., Veiga, F.J., Cabral, C.,
 449 Silva, A.M., Souto, E.B., 2017. Ibuprofen nanocrystals developed by 2² factorial design
 450 experiment: A new approach for poorly water-soluble drugs. *Saudi Pharm. J.* 25, 1117–
 451 1124. <http://dx.doi.org/10.1016/j.jsps.2017.07.004>.

452 Goto, P.L., Siqueira-Moura, M.P., Tedesco, A.C., 2017. Application of aluminum
 453 chloride phthalocyanine-loaded solid lipid nanoparticles for photodynamic inactivation
 454 of melanoma cells. *Int. J. Pharm.* 518, 228–241.
 455 <https://doi.org/10.1016/j.ijpharm.2017.01.004>.

456 Gupta, A., Eral, H.B., Hatton, T.A., Doyle, P.S., 2016. Nanoemulsions: formation,
 457 properties and applications. *Soft Matter* 12, 2826–2841.
 458 <https://doi.org/10.1039/c5sm02958a>.

459 Hammoud, Z., Gharib, R., Fourmentin, S., Elaissari, A., Greige-Gerges, H., 2019. New
 460 findings on the incorporation of essential oil components into liposomes composed of
 461 lipoid S100 and cholesterol. *Int. J. Pharm.* 561, 161–170.
 462 <https://doi.org/10.1016/j.ijpharm.2019.02.022>.

463 Harkat-Madouri, L., Asma, B., Madani, K., Said, Z.B.-O.S., Rigou, P., Grenier, D.,
 464 Allalou, H., Remini, H., Adjaoud, A., Boulekbache-Makhlouf, L., 2015. Chemical
 465 composition, antibacterial and antioxidant activities of essential oil of Eucalyptus
 466 globulus from Algeria. *Ind. Crop. Prod.* 78, 148–153.
 467 <http://dx.doi.org/10.1016/j.indcrop.2015.10.015>.

468 Harwansh, R.K., Deshmukh, R., Rahman, M.A., 2019. Nanoemulsion: Promising
 469 nanocarrier system for delivery of herbal bioactives. *J. Drug. Deliv. Sci. Tec.* 51, 224–
 470 233. <https://doi.org/10.1016/j.jddst.2019.03.006>.

471 Helgeson, M.E., 2016. Colloidal behavior of nanoemulsions: Interactions, structure, and
 472 rheology. *Curr. Opin. Colloid Interface Sci.* 25, 39–50.
 473 <http://dx.doi.org/10.1016/j.cocis.2016.06.006>.
 474 Komaiko, J., McClements, D.J., 2015. Low-energy formation of edible nanoemulsions
 475 by spontaneous emulsification: Factors influencing particle size. *J. Food Eng.* 146, 122–
 476 128. <http://dx.doi.org/10.1016/j.jfoodeng.2014.09.003>.
 477 Komaiko, J.S., McClements, D.J., 2016. Formation of Food-Grade Nanoemulsions Using
 478 Low-Energy Preparation Methods: A Review of Available Methods. *Compr. Rev. Food*
 479 *Sci. Food Saf.* 15, 331–352. <https://doi.org/10.1111/1541-4337.12189>.
 480 Matos, S.P., Lucca, L.G., Koester, L.S., 2019. Essential oils in nanostructured systems:
 481 Challenges in preparation and analytical methods. *Talanta* 195, 204–214.
 482 <https://doi.org/10.1016/j.talanta.2018.11.029>.
 483 McClements, D.J., Gumus, C.E., 2016. Natural emulsifiers — Biosurfactants,
 484 phospholipids, biopolymers, and colloidal particles: Molecular and physicochemical
 485 basis of functional performance. *Adv. Colloid Interface Sci.* 234, 3–26.
 486 <http://dx.doi.org/10.1016/j.cis.2016.03.002>.
 487 Prakash, A., Baskaran, R., Paramasivam, N., Vadivel, V., 2018a. Essential oil based
 488 nanoemulsions to improve the microbial quality of minimally processed fruits and
 489 vegetables: A review. *Food Res. Int.* 111, 509–523.
 490 <https://doi.org/10.1016/j.foodres.2018.05.066>.
 491 Prakash, B., Kujur, A., Yadav, A., Kumar, A., Singh, P.P., Dubey, N.K., 2018b.
 492 Nanoencapsulation: An efficient technology to boost the antimicrobial potential of plant
 493 essential oils in food system. *Food Control* 89, 1–11.
 494 <https://doi.org/10.1016/j.foodcont.2018.01.018>.

495 Rodrigues, F.V.S., Diniz, L.S., Sousa, R.M.G., Honorato, T.D., Simão, D.O., Araújo,
 496 C.R.M., Gonçalves, T.M., Rolim, L.A., Goto, P.L., Tedesco, A.C., Siqueira-Moura, M.P.,
 497 2018. Preparation and characterization of nanoemulsion containing a natural
 498 naphthoquinone. *Quim. Nova* 41, 756–761. [http://dx.doi.org/10.21577/0100-](http://dx.doi.org/10.21577/0100-4042.20170247)
 499 [4042.20170247](http://dx.doi.org/10.21577/0100-4042.20170247).
 500 Saberi, A.H., Fang, Y., McClements, D.J., 2013. Fabrication of vitamin E-enriched
 501 nanoemulsions: Factors affecting particle size using spontaneous emulsification. *J.*
 502 *Colloid Interface Sci.* 391, 95–102. <http://dx.doi.org/10.1016/j.jcis.2012.08.069>.
 503 Saberi, A.H., Fang, Y., McClements, D.J., 2014. Stabilization of vitamin E-enriched
 504 mini-emulsions: Influence of organic and aqueous phase compositions. *Colloids Surf. A*
 505 *Physicochem. Eng. Asp.* 449, 65–73. <http://dx.doi.org/10.1016/j.colsurfa.2014.02.042>.
 506 Safaya, M., Rotliwala, Y.C., 2020. Nanoemulsions: A review on low energy formulation
 507 methods, characterization, applications and optimization technique. *Mater. Today-Proc.*
 508 27, 454–459. <https://doi.org/10.1016/j.matpr.2019.11.267>.
 509 Salehi, B., Sharifi-Rad, J., Quispe, C., Llaique, H., Villalobos, M., Smeriglio, A.,
 510 Trombetta, D., Ezzat, S.M., Salem, M.A., Zayed, A., Castillo, C.M.S., Yazdi, S.E., Sen,
 511 S., Acharya, K., Sharopov, F., Martins, N., 2019. Insights into Eucalyptus genus chemical
 512 constituents, biological activities and health-promoting effects. *Trends Food Sci.*
 513 *Technol.* 91, 609–624. <https://doi.org/10.1016/j.tifs.2019.08.003>.
 514 Singh, Y., Meher, J.G., Raval, K., Khan, F.A., Chaurasia, M., Jain, N.K., Chourasia,
 515 M.K., 2017. Nanoemulsion: Concepts, development and applications in drug delivery. *J.*
 516 *Control. Release* 252, 28–49. <http://dx.doi.org/10.1016/j.jconrel.2017.03.008>.
 517 Slamenova, D., Horvathova, E., 2013. Cytotoxic, anti-carcinogenic and antioxidant
 518 properties of the most frequent plant volatiles. *Neoplasma* 60, 343–354.
 519 https://doi.org/10.4149/neo_2013_046.

520 Solans, C., Solé, I., 2012. Nano-emulsions: Formation by low-energy methods. Curr.
521 Opin. Colloid Interface Sci. 17, 246–254. <https://doi.org/10.1016/j.cocis.2012.07.003>.
522 Yin, H., Wang, C., Yue, J., Deng, Y., Jiao, S., Zhao, Y., Zhou, J., Cao, T., 2021.
523 Optimization and characterization of 1,8-cineole/hydroxypropyl- β -cyclodextrin inclusion
524 complex and study of its release kinetics. Food Hydrocoll. 110, 106159.
525 <https://doi.org/10.1016/j.foodhyd.2020.106159>.
526 Zhao, T., Maniglio, D., Chen, J., Chen, B., Migliaresi, C., 2016. Development of pH-
527 sensitive self-nanoemulsifying drug delivery systems for acid-labile lipophilic drugs.
528 Chem. Phys. Lipids 196, 81–88. <https://doi.org/10.1016/j.chemphyslip.2016.02.008>.