Hydrothermally stable Pd/SiO₂@Zr Core@Shell catalysts for diesel oxidation applications

Chih-Han Liu, Junjie Chen, Todd Toops, Jae-Soon Choi, Cyril Thomas,
Michael Lance, Eleni Kyriakidou

► To cite this version:

Chih-Han Liu, Junjie Chen, Todd Toops, Jae-Soon Choi, Cyril Thomas, et al.. Hydrothermally stable Pd/SiO₂@Zr Core@Shell catalysts for diesel oxidation applications. Chemical Engineering Journal, 2021, 425, pp.130637. 10.1016/j.cej.2021.130637 . hal-03343231

HAL Id: hal-03343231

<https://hal.science/hal-03343231>

Submitted on 14 Sep 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Hydrothermally Stable Pd/SiO₂@Zr Core@Shell Catalysts for Diesel Oxidation Applications

Chih-Han Liu^{a,+}, Junjie Chen^{a,+}, Todd J. Toops^b, Jae-Soon Choi^{b,1}, Cyril Thomas^c, Michael J.
Lance^b, and Eleni A. Kyriakidou^{a,*}

^a Department of Chemical and Biological Engineering, University at Buffalo, The State University of New York,
Buffalo, NY 14260, USA

^b Oak Ridge National Laboratory, Oak Ridge, TN 37831, USA

^c Sorbonne Université, CNRS, Laboratoire de Réactivité de Surface (LRS), 4 Place Jussieu, F-75252 Paris, France

⁺These authors contributed equally to this work

¹Present address: Catalyst Development Center, Basic Materials and Chemicals R&D, LG Chem,
Daejeon, Korea.

*Corresponding author at: elenikyr@buffalo.edu (E.A. Kyriakidou)

This manuscript has been authored by UT-Battelle, LLC under Contract No. DE-AC05-00OR22725 with the U.S. Department of Energy. The United States Government retains and the publisher, by accepting the article for publication, acknowledges that the United States Government retains a non-exclusive, paid-up, irrevocable, world-wide license to publish or reproduce the published form of this manuscript, or allow others to do so, for United States Government purposes. The Department of Energy will provide public access to these results of federally sponsored research in accordance with the DOE Public Access Plan (<http://energy.gov/downloads/doe-public-access-plan>).

Abstract

Hydrothermally stable diesel oxidation catalysts (DOCs) with improved low-temperature activity are desired for the abatement of emissions from diesel vehicles. Herein, novel palladium(Pd)/SiO₂(core)@Zr(shell) structured DOCs were developed. SiO₂ was completely covered by an 8.4 nm thickness Zr-based shell using a hard template method. The SiO₂@Zr support was decorated by Pd and evaluated under a simulated diesel exhaust stream. Degreened 1 wt.% Pd/SiO₂@Zr achieved 90% CO and total hydrocarbon conversion at 178 and 372 °C, respectively (feed: 6% CO₂, 12% O₂, 6% H₂O, 400 ppm H₂, 2000 ppm CO, 100 ppm NO, 1667 ppm C₂H₄, 1000 ppm C₃H₆, 333 ppm C₃H₈; HCs in C₁ basis and GHSV = 113,000 h⁻¹). After hydrothermal aging, only a minor deactivation was observed, while the surface area of 1 wt.% Pd/SiO₂@Zr was as high as 104 m²/g. The hydrothermal stability of 1 wt.% Pd/SiO₂@Zr was attributed to the poor crystallinity of SiO₂@Zr, possibly due to the formation of Si-O-Zr bonds. This work highlights the promising potential of utilizing durable Pd/SiO₂@Zr catalysts for diesel oxidation applications.

Keywords: diesel oxidation catalyst; heterogeneous catalysis; hydrothermal stability; oxidation; core@shell

1. Introduction

Future aftertreatment systems will need to perform efficiently at increasingly low exhaust temperatures [1-3]: this so-called “150 °C challenge [4]” (i.e., achieve over 90% conversion below 150 °C) arises from continued improvements in engines efficiency and increasingly strict emission standards. An aftertreatment system normally consists of a diesel oxidation catalyst (DOC) for the oxidation of CO and hydrocarbons (HCs), a diesel particulate filter for the oxidation of particulate matter, and a selective catalytic reduction (SCR) catalyst for the reduction of NO_x to N₂ [5-7]. A DOC is required to survive hydrothermal aging at 800 °C/50 h under a feed of 10% O₂, 5% H₂O, 5% CO₂ that represents the in-use durability of a catalyst based on the low temperature aftertreatment protocol defined by U.S. DRIVE [8-10]. Under this severe aging condition, active metals tend to sinter resulting in loss of their catalytic activity [11-13]. Enhancing the metal-support interaction has shown to prevent active metal sintering [14-16]. For example, Kim et al. pretreated Pt-TiO₂ under a H₂ atmosphere at various reduction temperatures, and the results showed that pretreatment at 600 °C led to a higher CO conversion (100%) compared to a lower CO conversion (10%) achieved at room temperature when the catalyst was pretreated at 300 °C [16]. This behavior was attributed to the strong metal (Pt)-support (TiO₂) interaction (SMSI) occurring after pretreatment at temperatures > 500 °C, evidenced by the formation of smaller Pt particles (2.2-4.4 nm) compared to larger Pt particles (4.7-5.9 nm) formed after pretreatments at temperatures < 500 °C. ZrO₂ was reported to have SMSI with platinum group metals (PGMs), commonly used in DOCs [17-19]. SMSI between PGMs and ZrO₂ lead to high PGM dispersion and thus an improved DOC activity. Specifically, the T_{50,90}'s (temperature of 50 and 90% conversion) over 1 wt.% Pd/ZrO₂ were as low as 160, 180 °C for CO and 180, 195 °C for propylene (C₃H₆), respectively [20]. However, Pd/ZrO₂ suffers from a severe surface area loss from 93 m²/g

(500 °C/2 h, 10% H₂/Ar) to 24 m²/g (hydrothermal aging, 800 °C/16 h, 10% O₂, 5% H₂O/Ar) due to the growth of the mean ZrO₂ crystallite size [20]. The ZrO₂ surface area loss can be prevented by incorporating oxides with higher crystallization temperature than ZrO₂ (~150 °C [21]), e.g. Al₂O₃ (850-900 °C [22]) or SiO₂ (1000-1400 °C [23, 24]) [25]. Specifically, Al₂O₃-ZrO₂ and ZrO₂-SiO₂ have a crystallization temperature of 700 and 800 °C, respectively [21, 26]. Thus, ZrO₂-SiO₂ mixed oxide supports were utilized considering the exhaust temperature (500-700 °C) of diesel engines at 100% load [20, 27, 28]. Specifically, Kim et al. showed that hydrothermally aged (HTA) (800 °C/16 h) Pd/ZrO₂-SiO₂ had a T₅₀ and T₉₀ for CO at 280 and 320 °C and for C₃H₆ at 307 and 332 °C, respectively [20]. Furthermore, incorporation of SiO₂, as an acidic support, is known to improve the sulfur tolerance of the catalyst compared to bare ZrO₂ [20]. However, uncontrolled synthesis of ZrO₂-SiO₂ by a sol-gel method resulted in segregation of SiO₂ and ZrO₂, leading to formation of large Pd particles on exposed SiO₂ surfaces due to weak Pd-SiO₂ interaction. Specifically, the Pd particle size over Pd/ZrO₂, Pd/ZrO₂-SiO₂, Pd/SiO₂ increased from 1.1 nm to 1.9 nm to 4.1 nm, respectively [20]. Therefore, a complete coverage of SiO₂ by a Zr-based shell is required to prevent Pd deposition on SiO₂ and thus enhance the diesel oxidation performance of Pd/ZrO₂-SiO₂ catalysts.

Herein, SiO₂(core)@Zr(shell) supports were synthesized, where SiO₂ spheres were covered by a Zr-based shell. This was achieved by a hard template method as reported previously (Fig. 1) [3], where the SiO₂ core acted as a scaffold for the growth of the Zr-based shell layer. Pd was deposited on the SiO₂@Zr support by wet-impregnation resulting to 1, 2 and 4 wt.% Pd/SiO₂@Zr catalysts that were evaluated for their diesel oxidation activity and hydrothermal stability.

2. Experimental procedure

Reagents and materials, and characterizations are listed in the Supplementary material.

2.1. Catalysts preparation

The $\text{SiO}_2@\text{Zr}$ core@shell support was synthesized, with some modifications, as reported previously [3]. The synthesis schematic is shown in Fig. 1. Briefly, monodisperse silica spheres were prepared following the Stöber process [29]. The SiO_2 spheres formed were dispersed in 100 g of ethanol and kept at 30 °C. Afterwards, 0.5 mL of Brij30 solution was added to the SiO_2 suspension and kept stirring for 1 h. Then, 1.8 mL $\text{Zr}(\text{BuO})_4$ was added and the solution was stirred overnight at 30 °C. The liquid phase of the colloid was then exchanged for 100 mL DI water (4 times) and aged at room temperature for 3 days. Finally, the $\text{SiO}_2@\text{Zr}$ spheres were collected after centrifugation followed by drying at 110 °C overnight and calcination at 500 °C for 2 h (10 °C/min).

The resulting $\text{SiO}_2@\text{Zr}$ support was impregnated with 2.8, 5.6, 11.4 mL $\text{Pd}(\text{NH}_3)_4(\text{NO}_3)_2$ solution (0.0344 M) by wet-impregnation where the pH of the slurry was adjusted to 4 with 0.1 M HNO_3 , leading to Pd loadings of 1, 2, and 4 wt.%. The liquid phase of the slurry was then evaporated at room temperature. After the impregnation, the catalyst was dried at 110 °C in air and calcined at 500 °C for 2 h.

2.2 Catalyst evaluation

The performance of the as-synthesized catalysts was evaluated in a customized fixed-bed U-shaped quartz reactor (I.D. = 8 mm) as reported previously [30]. The reactor was placed in a cylindrical furnace surrounded by quartz wool to eliminate heat gradients. A K-type thermocouple was attached outside the reactor, close to the top of the catalyst bed, to allow the PID temperature controller control the furnace temperature. Catalyst powders were pressed and sieved and a final pellet size range between 250 to 500 μm was used to avoid pressure effects during the reaction.

100 mg of catalyst was loaded in the reactor stabilized by two loosely packed quartz wool plugs. Another K-type thermocouple was inserted through the reactor U-tube to the upper quartz wool plug for measuring the inlet gas temperature.

The catalysts were first degreened (DG) (700 °C/4 h) under feed gas composition of 10% O₂, 5% H₂O, 5% CO₂/Ar. Before evaluation, the catalysts were pretreated at 600 °C with 12% O₂, 6% H₂O, 6% CO₂/Ar for 20 min. Diesel oxidation evaluation experiments were performed using the low temperature combustion of diesel (LTC-D) gas composition defined by U.S. DRIVE (Table S1) [8]. The total flow rate was 333 sccm that corresponds to a gas hourly space velocity (GHSV) of 113,000 h⁻¹. CO₂, O₂, H₂, CO, NO, C₂H₄, C₃H₆, C₃H₈ and Ar (UHP, Airgas) were regulated by a set of MKS mass flow controllers. Water was supplied by a D-series pump (Teledyne Isco), evaporated to steam in a tube furnace (200 °C) and carried by Ar to the reactor. Light-off tests were conducted from 100 to 500 °C at a heating rate of 2 °C /min. The effluent gas concentrations were analyzed by an MKS MultiGas 2030 FTIR gas analyzer with a gas cell at 191 °C. The reactor exhaust was diluted with 667 sccm Ar to reduce the response time of the gas analyzer. To avoid water condensation, all the gas lines were heated to 170 °C. Hydrothermal aging (HTA) treatment (800 °C /10 h) was conducted under feed gas composition of 10% O₂, 5% H₂O, 5% CO₂/Ar. Pretreatment and evaluation of the HTA catalysts were performed under the same conditions as the DG catalysts.

3. Results and Discussion

The high-angle annular dark-field scanning transmission electron microscopy (HAADF-STEM) images and energy dispersive X-ray spectroscopy (EDS) elemental maps of fresh (calcined at 500 °C/2 h) 1, 2 and 4 wt.% Pd/SiO₂@Zr catalysts are shown in Fig. 2. Moreover, a 3D tomography video of 1 wt.% Pd/SiO₂@Zr is shown (Video S1). The 3D tomography suggests the

complete coverage of SiO₂ core by Zr-based shell with Pd dispersed on the surface. A spherical structure was confirmed for all studied catalysts (Fig. 2). The EDS elemental maps of Si in Fig. 2a.2, 2b.2 and 2c.2 reveal the successful synthesis of nano-spherical SiO₂ (diameter of about 150 nm) as a support core. The higher density Zr presented as a shell layer (thickness: ~8.4 nm) (Fig. 2a.3, 2b.3 and 2c.3) indicates the successful deposition of Zr species on the SiO₂ core. Palladium is well-dispersed over 1 wt.% Pd/SiO₂@Zr (Fig. 2a.4). However, as Pd loading increased to 2 (Fig. 2b.4) and 4 wt.% (Fig. 2c.4), larger Pd clusters (~5 and 7 nm, respectively) can be observed, possibly due to Pd sintering.

Fig. S1 shows the X-ray diffraction (XRD) patterns of fresh SiO₂@Zr, fresh and HTA (800 °C/10 h, 10% O₂, 5% H₂O, 5% CO₂/Ar) 1 wt.% Pd/SiO₂@Zr. All samples display only one broad peak centered at ~23°, assigned to SiO₂ [31]. No peaks were detected for ZrO₂ over all analyzed samples, suggesting that the majority of Zr in SiO₂@Zr is not present in a ZrO₂ crystalline phase (monoclinic, tetragonal, cube). Moreover, presence of amorphous ZrO₂ is excluded since the samples analyzed by XRD are either fresh (calcined at 500 °C) or HTA (exposed to 800 °C/10 h) and amorphous ZrO₂ can readily crystallize at T > 300 °C [32]. Furthermore, no metallic Pd or PdO peaks were observed over fresh and HTA 1 wt.% Pd/SiO₂@Zr, which might be due to the low loading and the dispersed nature of Pd (Fig. 2a.4).

The surface properties (Brunauer-Emmett-Teller (BET) surface areas and Barrett-Joyner-Halenda (BJH) pore volumes) of SiO₂ core, SiO₂@Zr, and 1 wt.% Pd/SiO₂@Zr are summarized in Table 1. The surface area of fresh SiO₂ core was as low as 2.3 m²/g. Fresh SiO₂@Zr and 1 wt.% Pd/SiO₂@Zr had improved surface areas of 226.7 and 207.1 m²/g, respectively. Considering the low surface area of SiO₂ core, the improved surface areas of SiO₂@Zr and 1 wt.% Pd/SiO₂@Zr can be attributed to the Zr-based shell. Furthermore, the surface area loss after HTA was greater

over 1 wt.% Pd/ZrO₂ (fresh: 93 m²/g, HTA (16 h): 24 m²/g) [20] than 1 wt.% Pd/SiO₂@Zr (fresh: 226.7 m²/g, HTA (16 h): 112 m²/g). The surface area of 1 wt.% Pd/SiO₂@Zr after 10 h of HTA was 104 m²/g and it remained the same when the HTA time was extended to 16 h (112 m²/g). This observation suggests that the surface area of Pd/SiO₂@Zr does not change after HTA for 10 h. Moreover, the surface area of Pd/SiO₂@Zr is 4.5 times greater than the one of Pd/ZrO₂ after 16 h of HTA. The significant surface area loss of 1 wt.% Pd/ZrO₂ when exposed to elevated temperatures was attributed to the grain growth of crystalline ZrO₂ [33]. Therefore, the high surface area of SiO₂@Zr and 1 wt.% Pd/SiO₂@Zr after HTA can be attributed to the non-crystalline nature of the Zr-based shell (see XRD data (Fig. S1)). The N₂ adsorption-desorption isotherms of fresh and HTA 1 wt.% Pd/SiO₂@Zr are shown in Fig. S2. Both samples have a type IV isotherm, characteristic of mesoporous materials [34].

Fig. 3 shows the catalytic evaluation results of degreened (DG) 1 wt.% Pd/SiO₂@Zr. 1 wt.% Pd/SiO₂@Zr can achieve 50 and 90% conversions at 168 and 178 °C for CO and 228 and 372 °C for total HCs (THCs), respectively (Fig. 3a). Moreover, 1 wt.% Pd/SiO₂@Zr can reach 50 and 90% conversions at 245 and 362 °C for C₂H₄ and at 192 and 216 °C for C₃H₆, respectively (Fig. 3b). C₃H₈ was converted at a higher temperature (T₅₀= 376 °C, T₉₀= 428 °C) compared to C₂H₄ and C₃H₆, attributed to its stable C-H bonds [35]. The negative conversion of C₃H₈ observed between 180 and 340 °C (Fig. 3b) can be attributed to the desorption of C₃H₈ from PdO [36]. The inflection in CO conversion at 190 °C (Fig. 3a) can be attributed to competition of CO and HCs for active sites and mass transfer limitations [37]. Moreover, the inflection observed in C₂H₄ conversion (Fig. 3b) can be attributed to the adsorption of intermediates formed during C₂H₄ oxidation on Pd active sites (discussed later). These intermediate species can inhibit C₂H₄ adsorption and its further oxidation. Fig. 3c shows the concentrations of NO, NO₂ and N₂O and

1
2
3
4 their total concentration ($= [\text{NO}] + [\text{NO}_2] + 2[\text{N}_2\text{O}]$) during the evaluation of DG 1 wt.%
5
6 Pd/SiO₂@Zr. The total concentration of NO, NO₂, and N₂O indicates that most N-containing
7
8 species were in the form of NO, NO₂, and N₂O. The small negative peak observed at 165 °C can
9
10 be attributed to N₂ formation (not detectable by the MKS IR). There are three NO consumption
11
12 peaks at 165, 206 and 471 °C. NO consumed at 165 and 206 °C was converted to N₂ and N₂O,
13
14 respectively, suggesting that a HC-SCR reaction took place [38]. The third broad NO consumption
15
16 peak at temperature ~ 471 °C can be attributed to the catalytic NO oxidation over Pd [39] and
17
18 homogeneous (gas phase) NO oxidation [30].
19
20
21
22

23
24 A hydrothermal aging treatment (800 °C/10 h) was conducted to verify the durability of 1
25
26 wt.% Pd/SiO₂@Zr (Fig. 4). Compared to DG 1 wt.% Pd/SiO₂@Zr, HTA 1 wt.% Pd/SiO₂@Zr
27
28 showed similar T₅₀ (168 °C) and T₉₀ (178 °C) for CO, while minor deactivation was observed for
29
30 HC oxidation. Specifically, the T₅₀ (207 °C) and T₉₀ (372 °C) for THC_s was increased by only 21
31
32 and 9 °C, respectively, after hydrothermal aging of 1 wt.% Pd/SiO₂@ZrO₂. The ability of 1 wt.%
33
34 Pd/SiO₂@Zr to achieve a similar performance under DG and HTA conditions highlights the
35
36 hydrothermal stability of the catalyst. Similarly, the negative conversion of C₃H₈ observed
37
38 between 180 and 340 °C (Fig. 4b) can be attributed to the desorption of C₃H₈ from PdO [36].
39
40 Formaldehyde (CH₂O) was formed at the same temperature range that the inflection in C₂H₄
41
42 conversion was observed (Figs. S3a, 4b). The inflection in C₂H₄ conversion was also observed
43
44 when CO, NO, C₃H₆ and C₃H₈ were removed from the reactor feed (1667 ppm C₂H₄ (C₁ basis),
45
46 6% CO₂, 6% H₂O, 12% O₂, and 400 ppm H₂) (Fig. S3b). This observation indicates that
47
48 intermediates (e.g. CH₂O, CO) formed during C₂H₄ oxidation can be adsorbed on the Pd active
49
50 sites. The adsorbed intermediates can inhibit C₂H₄ adsorption and thus its further oxidation.
51
52 Similar NO conversion pattern was observed over both DG and HTA 1 wt.% Pd/SiO₂@Zr (Fig.
53
54
55

4c). The decrease in the total concentration of NO, NO₂, and N₂O can be attributed to HC-SCR reactions [38], as discussed previously.

The effect of Pd loading was investigated by comparing the catalytic performance of 1, 2, and 4 wt.% Pd/SiO₂@Zr (Fig. 5). The CO T₅₀/T₉₀'s were similar at 168/178, 168/179 and 158/172 °C over DG 1, 2 and 4 wt.% Pd/SiO₂@Zr, respectively (Fig. 5a). However, the THC T_{50,90}'s decreased as Pd loading increased. Specifically, the THC T₅₀/T₉₀'s decreased from 228/372 °C to 211/355 °C to 191/316 °C over DG 1, 2 and 4 wt.% Pd/SiO₂@Zr, respectively. After hydrothermal aging the T₅₀/T₉₀'s for CO slightly decreased from 165/178 to 163/176 to 163/172 °C with increasing Pd loading from 1 to 2 to 4 wt.% (Fig. 5b). Similarly, the T_{50,90}'s for THCs decreased with increasing Pd loading from 1 to 2 to 4 wt.% as follows: 207/381 °C to 202/343 °C to 190/325 °C, respectively.

Fourier transform infrared (FT-IR) spectra were collected over SiO₂ spheres and SiO₂@Zr supports to investigate the support composition and thus the origin of the Pd/SiO₂@Zr thermal stability (Fig. S4). Two peaks at 1101 and 802 cm⁻¹ were detected over both SiO₂ spheres and SiO₂@Zr supports, attributed to Si-O-Si bonds [40]. The decrease observed in the transmittance at 965 cm⁻¹ over SiO₂@Zr suggested the formation of Si-O-Zr bonds after Zr coating [41]. Moreover, Schüth et al. reported that the bulk and surface Zr/Si molar ratio of the core@shell support was 0.2 and 1, respectively [42]. Si-O-Zr bond formation can hinder the crystallization of the Zr-based shell [43]. Therefore, the improved hydrothermal stability of Pd/SiO₂@Zr can be attributed to the presence of Si-O-Zr.

NO_x-TPD provided an additional indication of the presence of Si-O-Zr bonds over SiO₂@Zr supports. Law et al. showed that there is a linear relationship between NO_x uptake and the accessible ZrO₂ surface area [44, 45]. Thus, NO_x-TPD was conducted to titrate the accessible

surface area of ZrO_2 in $\text{SiO}_2@\text{Zr}$. The amount of desorbed NO_x was calculated to be $0.17 \mu\text{mol NO}_x/\text{m}^2_{\text{SiO}_2@\text{Zr}}$ (Fig. 6), which is much lower than that of bare ZrO_2 ($5.8 \mu\text{mol NO}_x/\text{m}^2_{\text{ZrO}_2}$) [44, 45]. This result indicates that bare ZrO_2 presence on the $\text{SiO}_2@\text{Zr}$ surface is minimal. This observation is consistent with the $\text{SiO}_2@\text{Zr}$ XRD data (Fig. S1) where crystallized ZrO_2 was not detected. Moreover, $\text{SiO}_2@\text{Zr}$ (Fig. 6) and ZrSiO_4 (Fig. S5), that contains Si-O-Zr bonds, showed similar NO_x desorption temperatures and NO_x uptake ($0.43 \mu\text{mol NO}_x/\text{m}^2_{\text{ZrSiO}_4}$) indicating that the samples have a similar surface composition [46]. Therefore, the low NO_x uptake over $\text{SiO}_2@\text{Zr}$ can be attributed to the formation of Si-O-Zr bonds on its surface.

4. Conclusions

In this work, a series of hydrothermal stable Pd-based DOCs on a novel $\text{SiO}_2@\text{Zr}$ support were synthesized. Degreened 1 wt.% Pd/ $\text{SiO}_2@\text{Zr}$ was able to reach 90% CO and THC conversion at 178 and 372 °C, respectively (feed: 6% CO_2 , 12% O_2 , 6% H_2O , 400 ppm H_2 , 2000 ppm CO, 100 ppm NO, 1667 ppm C_2H_4 , 1000 ppm C_3H_6 , 333 ppm C_3H_8 ; HC in C_1 basis and GHSV=113,000 h^{-1}). Only a minor decrease in the THC conversion was observed after hydrothermal aging at 800 °C for 10 h (HTA). As the Pd loading increased from 1 to 2 to 4 wt.%, the T_{90} 's for THCs decreased from 372 to 346 to 316 °C, respectively. A similar trend was observed for Pd/ $\text{SiO}_2@\text{Zr}$ after HTA, where the THC T_{90} 's decreased from 381 to 343 to 325 °C with increasing Pd loading from 1 to 2 to 4 wt.% Pd/ $\text{SiO}_2@\text{Zr}$. The high surface area of Pd/ $\text{SiO}_2@\text{Zr}$ compared to Pd/ ZrO_2 before and after HTA was attributed to the poor crystallinity of $\text{SiO}_2@\text{Zr}$ support. The poor crystallinity of $\text{SiO}_2@\text{Zr}$ further contributes to the improved hydrothermal stability of Pd/ $\text{SiO}_2@\text{Zr}$ under conditions of low temperature combustion of diesel (LTC-D). Overall, this study revealed the potential of developing high surface area Pd/ $\text{SiO}_2@\text{Zr}$

catalysts with improved low temperature diesel oxidation performance and enhanced hydrothermal stability.

References:

- [1] J. Lee, J.R. Theis, E.A. Kyriakidou, Vehicle emissions trapping materials: Successes, challenges, and the path forward, *Appl. Catal. B* 243 (2019) 397-414. <https://doi.org/10.1016/j.apcatb.2018.10.069>.
- [2] A.P. Wong, E.A. Kyriakidou, T.J. Toops, J.R. Regalbuto, The catalytic behavior of precisely synthesized Pt-Pd bimetallic catalysts for use as diesel oxidation catalysts, *Catal. Today* 267 (2016) 145-156. <https://doi.org/10.1016/j.cattod.2016.02.011>.
- [3] E. Kyriakidou, T.J. Toops, J.-S. Choi, M.J. Lance, J.E. Parks II, Exhaust treatment catalysts with enhanced hydrothermal stability and low-temperature activity, US Patents 10,42,137 B2 (October 1, 2019).
- [4] M. Zammit, C.L. DiMaggio, C.H. Kim, C. Lambert, G.G. Muntean, C.H. Peden, J.E. Parks, K. Howden, Future automotive aftertreatment solutions: The 150 C challenge workshop report (US Drive Workshop, 2012) https://www.pnnl.gov/main/publications/external/technical_reports/PNNL-22815.pdf.
- [5] Y. Shin, Y. Jung, C.P. Cho, Y.D. Pyo, J. Jang, G. Kim, T.M. Kim, NO_x abatement and N₂O formation over urea-SCR systems with zeolite supported Fe and Cu catalysts in a nonroad diesel engine, *Chem. Eng. J.* 381 (2020) 122751. <https://doi.org/10.1016/j.cej.2019.122751>.
- [6] B. Apicella, E. Mancaruso, C. Russo, A. Tregrossi, M.M. Oliano, A. Cijolo, B.M. Vaglieco, Effect Of After-Treatment Systems On Particulate Matter Emissions In Diesel Engine Exhaust, *Exp. Therm. Fluid Sci.* (2020) 110107. <https://doi.org/10.1016/j.expthermflusci.2020.110107>.

- [7] A. Ko, Y. Woo, J. Jang, Y. Jung, Y. Pyo, H. Jo, O. Lim, Y.J. Lee, Complementary effects between NO oxidation of DPF and NO₂ decomposition of SCR in light-duty diesel engine, *J. Ind. Eng. Chem.* 80 (2019) 160-170. <https://doi.org/10.1016/j.jiec.2019.07.045>.
- [8] K.G. Rappé, C. DiMaggio, J.A. Pihl, J.R. Theis, S.H. Oh, G.B. Fisher, J. Parks, V.G. Easterling, M. Yang, M.L. Stewart, Aftertreatment Protocols for Catalyst Characterization and Performance Evaluation: Low-Temperature Oxidation, Storage, Three-Way, and NH₃-SCR Catalyst Test Protocols, *Emiss. Control Sci. Technol.* 5(2) (2019) 183-214. <https://doi.org/10.1007/s40825-019-00120-7>.
- [9] S. Du, W. Tang, Y. Guo, A. Binder, E.A. Kyriakidou, T.J. Toops, S. Wang, Z. Ren, S. Hoang, P.-X. Gao, Understanding low temperature oxidation activity of nanoarray-based monolithic catalysts: from performance observation to structural and chemical insights, *Emiss. Control Sci. Technol.* 3(1) (2017) 18-36. <https://doi.org/10.1007/s40825-016-0054-y>.
- [10] S. Hoang, Y. Guo, A.J. Binder, W. Tang, S. Wang, J.J. Liu, T.D. Huan, X. Lu, Y. Wang, Y. Ding, Activating low-temperature diesel oxidation by single-atom Pt on TiO₂ nanowire array, *Nat. Commun.* 11(1) (2020) 1-10. <https://doi.org/10.1038/s41467-020-14816-w>.
- [11] Y. Xie, E. Rodrigues, N. Furtado, A. Matynia, T. Arlt, P. Rodatz, P. Da Costa, Aging of commercial diesel oxidation catalysts: a preliminary structure/reactivity study, *Top. Catal.* 59(10-12) (2016) 1039-1043. <https://doi.org/10.1007/s11244-016-0586-y>.
- [12] D. Kunwar, C. Carrillo, H. Xiong, E. Peterson, A. DeLaRiva, A. Ghosh, G. Qi, M. Yang, M. Wiebenga, S. Oh, Investigating Anomalous Growth of Platinum Particles during Accelerated Aging of Diesel Oxidation Catalysts, *Appl. Catal. B* 266 (2020) 118598. <https://doi.org/10.1016/j.apcatb.2020.118598>.

- [13] C. Carrillo, A. DeLaRiva, H. Xiong, E.J. Peterson, M.N. Spilde, D. Kunwar, R.S. Goeke, M. Wiebenga, S.H. Oh, G. Qi, S.R. Challa, A.K. Datye, Regenerative trapping: How Pd improves the durability of Pt diesel oxidation catalysts, *Appl. Catal. B* 218 (2017) 581-590. <https://doi.org/10.1016/j.apcatb.2017.06.085>.
- [14] J. Liu, B. Qiao, Y. Song, Y. Huang, J.J. Liu, Hetero-epitaxially anchoring Au nanoparticles onto ZnO nanowires for CO oxidation, *Chem. Comm.* 51(83) (2015) 15332-15335. <https://doi.org/10.1039/C5CC03353E>.
- [15] Y. Sun, W. Liu, M. Tian, L. Wang, Z. Wang, A Rational Design of the Sintering-Resistant Au-CeO₂ Nanoparticles Catalysts for CO Oxidation: The Influence of H₂ Pretreatments, *Materials* 11(10) (2018) 1952. <https://doi.org/10.3390/ma11101952>.
- [16] G.J. Kim, D.W. Kwon, S.C. Hong, Effect of Pt particle size and valence state on the performance of Pt/TiO₂ catalysts for CO oxidation at room temperature, *J. Phys. Chem. C* 120(32) (2016) 17996-18004. <https://doi.org/10.1021/acs.jpcc.6b02945>.
- [17] Q. Guo, R. Joyner, An X-ray photoelectron spectroscopy study of the stability of ZrO₂ films on Pd (110), *Appl. Surf. Sci.* 144 (1999) 375-379. [https://doi.org/10.1016/S0169-4332\(98\)00827-7](https://doi.org/10.1016/S0169-4332(98)00827-7).
- [18] J. Bitter, K. Seshan, J. Lercher, On the contribution of X-ray absorption spectroscopy to explore structure and activity relations of Pt/ZrO₂ catalysts for CO₂/CH₄ reforming, *Top. Catal.* 10(3-4) (2000) 295-305. <https://doi.org/10.1023/A:1019149025242>.
- [19] C. Dall'Agnol, A. Gervasini, F. Morazzoni, F. Pinna, G. Strukul, L. Zanderighi, Hydrogenation of carbon monoxide: Evidence of a strong metal-support interaction in RhZrO₂ catalysts, *J. Catal.* 96(1) (1985) 106-114. [https://doi.org/10.1016/0021-9517\(85\)90364-1](https://doi.org/10.1016/0021-9517(85)90364-1).

- [20] M.-Y. Kim, E.A. Kyriakidou, J.-S. Choi, T.J. Toops, A.J. Binder, C. Thomas, J.E. Parks II, V. Schwartz, J. Chen, D.K. Hensley, Enhancing low-temperature activity and durability of Pd-based diesel oxidation catalysts using ZrO₂ supports, Appl. Catal. B 187 (2016) 181-194. <https://doi.org/10.1016/j.apcatb.2016.01.023>.
- [21] D. Aguilar, L. Torres-Gonzalez, L. Torres-Martinez, T. Lopez, P. Quintana, A study of the crystallization of ZrO₂ in the sol-gel system: ZrO₂-SiO₂, J. Solid State Chem. 158(2) (2001) 349-357. <https://doi.org/10.1006/jssc.2001.9126>.
- [22] G. Dingemans, A. Clark, J. Van Delft, M. Van De Sanden, W. Kessels, Er³⁺ and Si luminescence of atomic layer deposited Er-doped Al₂O₃ thin films on Si (100), J. Appl. Phys. 109(11) (2011) 113107. <https://doi.org/10.1063/1.3595691>.
- [23] V. Nagarajan, K. Rao, Crystallization studies of ZrO₂-SiO₂ composite gels, J. Mater. Sci. 24(6) (1989) 2140-2146. <https://doi.org/10.1007/BF02385434>.
- [24] T. Ono, M. Kagawa, Y. Syono, Ultrafine particles of the ZrO₂-SiO₂ system prepared by the spray-ICP technique, J. Mater. Sci. 20(7) (1985) 2483-2487. <https://doi.org/10.1007/BF00556078>.
- [25] C. Zhao, O. Richard, H. Bender, M. Caymax, S. De Gendt, M. Heyns, E. Young, G. Roebben, O. Van der Biest, S. Haukka, Miscibility of amorphous ZrO₂-Al₂O₃ binary alloy, Appl. Phys. Lett. 80(13) (2002) 2374-2376. <https://doi.org/10.1063/1.1459765>.
- [26] G. Balakrishnan, A. Wasy, H.S. Ho, P. Sudhakara, S. Bae, J. Song, Study of Al₂O₃/ZrO₂ (5 nm/20nm) Nanolaminate Composite, Compos. Res. 26(1) (2013) 60-65. <https://doi.org/10.7234/kscm.2013.26.1.60>.
- [27] M.-Y. Kim, J.-S. Choi, T.J. Toops, E.-S. Jeong, S.-W. Han, V. Schwartz, J. Chen, Coating SiO₂ support with TiO₂ or ZrO₂ and effects on structure and CO oxidation performance of Pt catalysts, Catalysts 3(1) (2013) 88-103. <https://doi.org/10.3390/catal3010088>.

- [28] D.P. Nolan, Fire Pump Arrangements at Industrial Facilities, third ed., Gulf Professional Publishing, Oxford, 2017.
- [29] W. Stöber, A. Fink, E. Bohn, Controlled growth of monodisperse silica spheres in the micron size range, J. Colloid Interface Sci. 26(1) (1968) 62-69. [https://doi.org/10.1016/0021-9797\(68\)90272-5](https://doi.org/10.1016/0021-9797(68)90272-5).
- [30] C.-H. Liu, K. Giewont, T.J. Toops, E.A. Walker, C. Horvatits, E.A. Kyriakidou, Non-catalytic gas phase NO oxidation in the presence of decane, Fuel 286 (2021) 119388. <https://doi.org/10.1016/j.fuel.2020.119388>.
- [31] S. Musić, N. Filipović-Vinceković, L. Sekovanić, Precipitation of amorphous SiO₂ particles and their properties, Braz. J. Chem. Eng. 28(1) (2011) 89-94. <https://doi.org/10.1590/S0104-66322011000100011>.
- [32] S. Tada, S. Kayamori, T. Honma, H. Kamei, A. Nariyuki, K. Kon, T. Toyao, K.-i. Shimizu, S. Satokawa, Design of interfacial sites between Cu and amorphous ZrO₂ dedicated to CO₂-to-methanol hydrogenation, ACS Catalysis 8(9) (2018) 7809-7819. <https://pubs.acs.org/doi/abs/10.1021/acscatal.8b01396>.
- [33] F. Lu, J. Zhang, M. Huang, F. Namavar, R.C. Ewing, J. Lian, Phase transformation of nanosized ZrO₂ upon thermal annealing and intense radiation, J. Phys. Chem. C 115(15) (2011) 7193-7201. <https://doi.org/10.1021/jp109558s>.
- [34] K.S. Sing, Reporting physisorption data for gas/solid systems with special reference to the determination of surface area and porosity (Recommendations 1984), Pure Appl. Chem. 57(4) (1985) 603-619.
- [35] R.G. Bergman, C-H activation, Nature 446(7134) (2007) 391-393. <https://doi.org/10.1038/446391a>.

- [36] S.S. Kum, B.Y. Jo, S.H. Moon, Performance of Pd-promoted Mo–V–Te–Nb–O catalysts in the partial oxidation of propane to acrylic acid, *Appl. Catal., A* 365(1) (2009) 79-87. <https://doi.org/10.1016/j.apcata.2009.05.056>.
- [37] P. Piqueras, A. García, J. Monsalve-Serrano, M.J. Ruiz, Performance of a diesel oxidation catalyst under diesel-gasoline reactivity controlled compression ignition combustion conditions, *Energy Convers. Manag.* 196 (2019) 18-31. <https://doi.org/10.1016/j.enconman.2019.05.111>.
- [38] R. Burch, J. Breen, F. Meunier, A review of the selective reduction of NO_x with hydrocarbons under lean-burn conditions with non-zeolitic oxide and platinum group metal catalysts, *Appl. Catal. B* 39(4) (2002) 283-303. [https://doi.org/10.1016/S0926-3373\(02\)00118-2](https://doi.org/10.1016/S0926-3373(02)00118-2).
- [39] X. Auvray, L. Olsson, Stability and activity of Pd-, Pt-and Pd–Pt catalysts supported on alumina for NO oxidation, *Appl. Catal. B* 168 (2015) 342-352. <https://doi.org/10.1016/j.apcatb.2014.12.035>.
- [40] T. Zhang, J. Ge, Y. Hu, Q. Zhang, S. Aloni, Y. Yin, Formation of hollow silica colloids through a spontaneous dissolution–regrowth process, *Angew. Chem.* 120(31) (2008) 5890-5895. <https://doi.org/10.1002/ange.200800927>.
- [41] N. Hassan, A. Jalil, N. Khusnun, M. Ali, S. Haron, Role of reduced graphene oxide in improving interfacial charge transfer of hybridized rGO/silica/zirconia for enhanced Bisphenol A photodegradation, *J. Alloys Compd.* 789 (2019) 221-230. <https://doi.org/10.1016/j.jallcom.2019.03.105>.
- [42] P.M. Arnal, C. Weidenthaler, F. Schüth, Highly monodisperse zirconia-coated silica spheres and zirconia/silica hollow spheres with remarkable textural properties, *Chem. Mater.* 18(11) (2006) 2733-2739. <https://doi.org/10.1021/cm052580a>.

- [43] S. Kongwudthiti, P. Praserttham, W. Tanakulrungsank, M. Inoue, The influence of Si–O–Zr bonds on the crystal-growth inhibition of zirconia prepared by the glycothermal method, *J. Mater. Process. Technol.* 136(1-3) (2003) 186-189. [https://doi.org/10.1016/S0924-0136\(03\)00157-2](https://doi.org/10.1016/S0924-0136(03)00157-2).
- [44] H.Y. Law, J. Blanchard, X. Carrier, C. Thomas, NO_x-TPD as a Tool to Estimate the Accessible Zirconia Surface of ZrO₂-Containing Materials, *J. Phys. Chem. C* 114(21) (2010) 9731-9738. <https://doi.org/10.1021/jp9089535>.
- [45] C. Thomas, Should W Surface Density of WO_x–ZrO₂ Catalysts Be Calculated With Respect To the Specific Surface Area of the Sample or That of ZrO₂ Only?, *J. Phys. Chem. C* 115(5) (2011) 2253-2256. <https://doi.org/10.1021/jp110497e>.
- [46] M. Ogura, R. Guillet-Nicolas, D. Brouri, S. Casale, J. Blanchard, K.A. Cychosz, M. Thommes, C. Thomas, Insights into the accessibility of Zr in Zr/SBA-15 mesoporous silica supports with increasing Zr loadings, *Micropor. Mesopor. Mat.* 225 (2016) 440-449. <https://doi.org/10.1016/j.micromeso.2016.01.026>.

Table 1. BET surface areas and BJH pore volumes of SiO₂ core, SiO₂@Zr, and (fresh, HTA) 1 wt.% Pd/SiO₂@Zr.

	BET surface area (m ² /g)	BJH pore volume (cm ³ /g)
Fresh SiO ₂	2.3	0.009
Fresh SiO ₂ @Zr	226.7	0.170
Fresh 1 wt.% Pd/SiO ₂ @Zr	207.2	0.152
HTA 1 wt.% Pd/SiO ₂ @Zr	103.9	0.089

Fig. 1. Synthesis of $\text{SiO}_2@\text{Zr}$ core@shell support using a hard template method.

Fig. 2. HAADF-STEM images and EDS elemental maps of fresh (a.1-5) 1 wt.% Pd/SiO₂@Zr, (b.1-5) 2 wt.% Pd/SiO₂@Zr, and (c.1-5) 4 wt.% Pd/SiO₂@Zr catalysts.

Fig. 3. (a) CO, THC, NO_x, (b) C₂H₄, C₃H₆, C₃H₈ conversions and (c) NO, NO₂, N₂O concentrations and their total concentration ($= [\text{NO}] + [\text{NO}_2] + 2[\text{N}_2\text{O}]$) as a function of temperature of degreened 1 wt.% Pd/SiO₂@Zr.

Fig. 4. (a) CO, THC, NO_x, (b) C₂H₄, C₃H₆, C₃H₈ conversions and (c) NO, NO₂, N₂O concentrations and their total concentration ($= [\text{NO}] + [\text{NO}_2] + 2[\text{N}_2\text{O}]$) as a function of temperature of hydrothermally aged 1 wt.% Pd/SiO₂@Zr.

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55

Fig. 5. Comparison of $T_{50,90}$'s of CO, THCs, C_2H_4 , C_3H_6 , C_3H_8 over (a) degreened and (b) hydrothermally aged 1, 2, 4 wt.% Pd/SiO₂@Zr catalysts. The horizontal dashed line denotes the 150 °C target temperature for achieving 90% conversion.

Fig. 6. NO_x-TPD profiles over fresh SiO₂@Zr.

Supplementary material

Hydrothermally Stable Pd/SiO₂@Zr Core@Shell Catalysts for Diesel

Oxidation Applications

ChihHan Liu^{a,+}, Junjie Chen^{a,+}, Todd J. Toops^b, Jae-Soon Choi^{b,1}, Cyril Thomas^c, Michael J. Lance^b, and Eleni A. Kyriakidou^{a,*}

^a *Department of Chemical and Biological Engineering, University at Buffalo, The State University of New York, Buffalo, NY 14260, USA*

^b *Oak Ridge National Laboratory, Oak Ridge, TN 37831, USA*

^c *Sorbonne Université, CNRS, Laboratoire de Réactivité de Surface (LRS), 4 Place Jussieu, F-75252 Paris, France*

⁺These authors contributed equally to this work

¹Present address: Catalyst Development Center, Basic Materials and Chemicals R&D, LG Chem, Daejeon, Korea.

*Corresponding author at: elenikyr@buffalo.edu (E.A. Kyriakidou)

This manuscript has been authored by UT-Battelle, LLC under Contract No. DE-AC05-00OR22725 with the U.S. Department of Energy. The United States Government retains and the publisher, by accepting the article for publication, acknowledges that the United States Government retains a non-exclusive, paid-up, irrevocable, world-wide license to publish or reproduce the published form of this manuscript, or allow others to do so, for United States Government purposes. The Department of Energy will provide public access to these results of federally sponsored research in accordance with the DOE Public Access Plan (<http://energy.gov/downloads/doe-public-access-plan>).

Table of Contents

Content	Page
1. Table of contents	1
2. Reagents and materials	2
3. Characterizations	3
4. Table S1	4
5. Figure S1	5
6. Figure S2	6
7. Figure S3	7
8. Figure S4	8
9. Figure S5	9
10. Video S1	10
11. References	11

Reagents and materials

Zirconium(IV) butoxide solution ($\text{Zr}(\text{BuO})_4$) (80 wt.% in 1-butanol, Sigma-Aldrich), tetraethyl orthosilicate (TEOS) (98% purity, Strem), anhydrous ethyl alcohol (200 proof, Decon), ammonium hydroxide (NH_4OH , 28-30 wt.% solution of NH_3 in water, Sigma-Aldrich), nitric acid (65 wt.%, Fisher) and tetraamminepalladium nitrate ($\text{Pd}(\text{NH}_3)_4(\text{NO}_3)_2$) (10% in H_2O , Sigma-Aldrich), zirconium silicate (98%, ACROS) were used as received. Brij30 (ACROS) was diluted with DI water to a 3.76 wt.% Brij30 solution prior to usage. Nitric acid was diluted with DI water to 0.1 M prior to usage. DI water purified to $18.2 \text{ M}\Omega\cdot\text{cm}$ (Milli-Q grade) was used for all reported synthesis.

Characterizations

HAADF-STEM images and EDS elemental maps of $\text{Pd}/\text{SiO}_2@\text{Zr}$ catalysts were obtained with a FEI Talos F200X STEM. The catalysts were first dispersed in isopropyl alcohol under ultrasonication for 15 minutes. One drop of the solution was added onto carbon-coated copper TEM grids followed by drying in air at ambient temperature.

The BET surface areas and BJH pore volumes of the studied samples were determined by N_2 physisorption with a Micromeritics Tri-Star II surface area and porosity analyzer. Before the measurement, all the samples were degassed at 150°C for 2 h.

XRD was conducted in a Rigaku Ultima IV using a $\text{Cu-K}\alpha$ X-ray source (wavelength: 0.15406 nm) operating at 40 kV, 44 mA. XRD patterns were collected in a 2θ range of $5-85^\circ$, with a scan rate of $2^\circ/\text{min}$.

Fourier transform infrared (FT-IR) spectra of SiO_2 spheres and $\text{SiO}_2@\text{Zr}$ were collected between $400-4000 \text{ cm}^{-1}$ with a Bruker Vertex 70 FTIR spectrophotometer.

NO_x-TPD experiments were conducted following the procedure reported previously [1]. The catalysts (~500 mg) were first loaded in a U-shaped quartz reactor (I.D. = 15 mm) and pretreated at 500 °C /2 h with 100 sccm (100 mL/min, STP) 20% O₂/He. After cooling down to room temperature, the samples were exposed to the adsorption mixture (400 ppm NO_x and 8% O₂/He) for ~ 200 min. The samples were then purged with 8% O₂/He (230 sccm) to remove gas phase NO_x until negligible NO and NO₂ were detected at the reactor outlet, followed by heating up to 560 °C (3 °C /min) to perform the NO_x-TPD experiments. The NO and NO₂ concentrations were recorded by a chemiluminescence NO_x analyzer (42C-HT, Thermo Environmental Instruments). A correction for the weight loss due to dehydration of the samples was conducted for the NO_x-TPD profiles.

Table S1. Simulated exhaust for low temperature combustion of diesel (LTC-D) based on the low temperature oxidation protocol by U.S. Drive [2], balance Ar.

Components	Concentration
O ₂	12%
H ₂ O	6%
CO ₂	6%
H ₂	400 ppm
CO	2000 ppm
NO	100 ppm
Hydrocarbon - on C ₁ basis	
Total HCs	3000 ppm
C ₂ H ₄	1667 ppm
C ₃ H ₆	1000 ppm
C ₃ H ₈	333 ppm

Fig. S1. XRD patterns of fresh SiO₂@Zr, fresh and HTA 1 wt.% Pd/SiO₂@Zr.

Fig. S2. N₂ adsorption (solid) – desorption (open) isotherms of fresh and HTA 1 wt.% Pd/SiO₂@Zr.

Fig. S3. C_2H_4 conversion (left y-axis) and CO, formaldehyde concentrations (right y-axis) over hydrothermally aged 1 wt.% Pd/SiO₂@Zr under reactor feed containing (a) 6% CO_2 , 12% O_2 , 6% H_2O , 400 ppm H_2 , 2000 ppm CO, 100 ppm NO, 1667 ppm C_2H_4 , 1000 ppm C_3H_6 , 333 ppm C_3H_8 and (b) 6% CO_2 , 12% O_2 , 6% H_2O , 400 ppm H_2 , 1667 ppm C_2H_4 ; HCs in C_1 basis. The slow light-off profile of C_2H_4 in Fig. S3b compared to Fig. S3a can be attributed to the decreased exothermic effect when C_3H_6 , C_3H_8 , and CO were removed from the reactor feed (data not shown).

Fig. S4. FT-IR spectra of SiO₂ spheres and SiO₂@Zr support.

Fig. S5. NO_x-TPD profiles over fresh ZrSiO₄.

Video. S1. 3D tomography video of 1 wt.% Pd/SiO₂@Zr.

References:

- [1] H.Y. Law, J. Blanchard, X. Carrier, C. Thomas, NO_x-TPD as a Tool to Estimate the Accessible Zirconia Surface of ZrO₂-Containing Materials, *J. Phys. Chem. C* 114(21) (2010) 9731-9738.
<https://doi.org/https://doi.org/10.1021/jp9089535>.
- [2] K.G. Rappé, C. DiMaggio, J.A. Pihl, J.R. Theis, S.H. Oh, G.B. Fisher, J. Parks, V.G. Easterling, M. Yang, M.L. Stewart, Aftertreatment Protocols for Catalyst Characterization and Performance Evaluation: Low-Temperature Oxidation, Storage, Three-Way, and NH₃-SCR Catalyst Test Protocols, *Emiss. Control Sci. Technol.* 5(2) (2019) 183-214.
<https://doi.org/https://doi.org/10.1007/s40825-019-00120-7>.