Biocompatibility, drug release, and anti-tumor effect of pH -sensitive micelles prepared from poly(2-ethyl-2-oxazoline)-poly(DL -lactide) block copolymers

Yuandou Wang, Baogang Zhang, Xin Shen, Qian Li, Feng Su, S.M. Li

► To cite this version:

Yuandou Wang, Baogang Zhang, Xin Shen, Qian Li, Feng Su, et al.. Biocompatibility, drug release, and anti-tumor effect of pH -sensitive micelles prepared from poly(2-ethyl-2-oxazoline)-poly(DL -lactide) block copolymers. *Polymers for Advanced Technologies*, 2021, 32 (10), pp.4142-4152. 10.1002/pat.5423 . hal-03369643

HAL Id: hal-03369643

<https://hal.science/hal-03369643>

Submitted on 7 Oct 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Biocompatibility, drug release and anti-tumor effect of pH-sensitive micelles prepared from poly(2-ethyl-2-oxazoline)-poly(DL-lactide) block copolymers

Journal:	<i>Polymers for Advanced Technologies</i>
Manuscript ID	PAT-21-397.R1
Wiley - Manuscript type:	Research Article
Date Submitted by the Author:	n/a
Complete List of Authors:	Wang, Yuandou Zhang, Baogang Shen, Xin; CP Pharmaceutical (Qingdao) Co Li, Qian; Qingdao University su, feng; Qingdao University of Science and Technology, College of Chemical Engineering Li, Suming; Universite de Montpellier,
Keywords:	poly(2-ethyl-2-oxazoline), poly(DL-lactide), self-assembly, micelle, curcumin

SCHOLARONE™
Manuscripts

Biocompatibility, drug release and anti-tumor effect of pH-sensitive micelles prepared from poly(2-ethyl-2-oxazoline)-poly(DL-lactide) block copolymers

Yuandou Wang,^{a†} Baogang Zhang,^{b†} Xin Shen,^{c,d} Qian Li,^d Feng Su,^{a,b*} Suming Li^{e*}

^a State Key Laboratory Base of Eco-chemical Engineering, College of Chemical Engineering, Qingdao University of Science and Technology, Qingdao 266042, China

^b Institute of High Performance Polymers, Qingdao University of Science and Technology, Qingdao 266042, China

^c CP Pharmaceutical (Qingdao) Co., Ltd., Qingdao, 266426, China

^d Cancer Institute, The Affiliated Hospital of Qingdao University, Qingdao, 266071, China

^e Institut Européen des Membranes, IEM UMR 5635, Univ Montpellier, CNRS, ENSCM, Montpellier, France

Correspondence to: F. Su (E-mail: sufeng@qust.edu.cn), S. Li (E-mail: suming.li@umontpellier.fr)

[†]Authors equally contributed to this work and are both co-first authors.

ABSTRACT

Various ratios PEOz-PDLLA diblock copolymers were synthesized through ring-opening polymerization of DL-lactide initiated by monohydroxyl terminated poly(2-ethyl-2-oxazoline) (PEOz-OH). The chemical composition and molar mass of the resulting copolymers were determined by using NMR and GPC. Spherical micelles with a diameter from 104 to 136 nm were obtained via self-assembly of PEOz-PDLLA

in water, as evidenced by TEM and DLS. The CMC of copolymers was well below 0.01 mg/mL, and showed a decreasing trend with increase of PDLLA block length. A two-step procedure was applied to encapsulate curcumin taken as a hydrophobic model drug. Copolymers with longer PDLLA block exhibit enhanced drug loading capacity. In vitro drug release was carried out in phosphate buffered saline at physiological and slightly acidic pH values. A pH-sensitive biphasic drug release behavior was detected with an initial burst release followed by slower prolonged release. Lower pH or shorter PDLLA block length leads to higher drug release rate because of faster degradation of micelles. Hemo- and cytocompatibility studies illustrated the excellent biocompatibility of PEOz-PDLLA micelles. MTT assay showed a significant cytotoxicity of curcumin-loaded micelles against A549 lung cancer cells. Therefore, it can be inferred that PEOz-PDLLA block copolymers with outstanding biocompatibility, controllable drug loading performance, and prolonged drug release present a good potential as nano-carrier of hydrophobic drugs.

Keywords: poly(2-ethyl-2-oxazoline); poly(DL-lactide); self-assembly; micelles; curcumin; nano carrier

1 Introduction

Nowadays, cancer is one of the most common causes of death globally. Nearly 10 million of people died of cancer in 2020 according to the World Health Organization.¹⁻³. For patients with different types of solid tumors, the most commonly used first-line clinical treatment is combination of surgery and chemotherapy. However, one of the main problems of chemotherapy is the extremely low bioavailability of anti-tumor drugs and adverse side effects.⁴⁻⁶ Many nano-platforms such as micelles, liposomes, vesicles and nanoparticles have been designed to prevent drug deterioration while increasing effective drug concentration at lesion site.⁷⁻¹⁰ Among them, micelles have attracted much interest due to their advantageous characteristics, including good

1
2
3
4 stability in vivo, long circulation in the bloodstream, sustained and adjustable drug
5 release performance. A number of micelles prepared from amphiphilic block
6 copolymers, have been brought to the stage of clinical trials.¹¹⁻¹³ Drugs encapsulated in
7 micelles can be delivered at the target site through drug diffusion and copolymer
8 degradation^{14,15}. Additionally, the chemical structure of micelle material can be
9 designed to tailor the degradation rate and, thus allowing spatiotemporally controlled
10 drug release.
11
12

13
14
15
16
17
18 Curcumin is a natural polyphenol extracted from the rhizome of turmeric
19 (*Curcuma longa*) which exhibits various pharmacological activities because of its
20 versatile molecular targets.¹⁶ Curcumin has been widely explored in preventing or
21 treating different types of diseases, such as cancer, gastrointestinal diseases, as well as
22 gastrointestinal and arthritis-related disorders.¹⁷⁻²⁰ However, the very low solubility (11
23 ng mL⁻¹), fast metabolism and clearance of curcumin lead to low bioavailability, which
24 considerably limits its clinical applications. It is thus of major importance to develop a
25 nano carrier to encapsulate curcumin so as to improve its bioavailability.
26
27
28
29
30
31
32

33
34 Poly(2-ethyl-2-oxazoline) (PEOz) is a hydrophilic polymer with aliphatic side
35 chains and a skeleton structure similar to natural polypeptides. It has been approved by
36 the food and drug administration (FDA) as a food additive.²¹ Due to its biosafety and
37 hydrophilicity, PEOz is considered as an excellent substitute to poly(ethylene glycol)
38 (PEG) in the field of biomedical research. Micelles prepared from PEOz-based block
39 copolymers present attractive properties, including long circulation time, sustained
40 drug release and no accumulation in normal organs.^{22,23} Meanwhile, ionization of
41 tertiary amide groups leads to electrostatic repulsion between PEOz chains that
42 provides PEOz-based micelles with pH sensitivity. Zhao et al. synthesized a PEOz-
43 poly(DL-lactide) (PEOz-PDLLA) copolymer composed of a PEOz block with Mn of
44 6514 and a PDLLA block with Mn of 8200.²⁴ Doxorubicin loaded micelles were
45 prepared using dialysis method. Drug release studies were performed at pH 7.4, 6.5 and
46 5.0 to simulate the blood environment, the tumoral extracellular environment, and the
47 endo/lysosome mimetic circumstance, respectively. All the designed micelles exhibited
48
49
50
51
52
53
54
55
56
57
58
59
60

an accelerated drug release in acidic pH media as doxorubicin was almost totally released beyond 12 h at pH 5.0.²⁴ In our previous work, a number of PEOz-poly(L-lactide) (PEOz-PLLA) copolymers were synthesized as pH-sensitive carrier of paclitaxel.²⁵ It was observed that the hydrophilic/hydrophobic balance and hydrophobic block length of copolymers significantly affect the micelle formation and paclitaxel release behavior. Spherical micelles were exclusively observed for PEOz-PLLA copolymers with short PLA blocks, whereas both worm-like and spherical micelles were obtained for copolymers with long PLA blocks. But drug release was rather slow with less than 40% of drug released after 30 days.

In the present work, PEOz-PDLLA diblock copolymers with various compositions were prepared using monohydroxyl terminated PEOz as macro-initiator. Nano-sized micelles were obtained by self-assembly of the resulted copolymers in water using chloroform as a co-solvent, and characterized from dynamic light scattering (DLS), transmission electron microscopy (TEM), and critical micelle concentration (CMC) measurements. The cytocompatibility, hemocompatibility and Zebrafish embryo compatibility of the copolymers were studied in detail. Using curcumin as a drug model, the drug encapsulation properties and drug release behaviors of micelles were evaluated under in vitro conditions. Finally, the anti-tumor activity of curcumin loaded PEOz-PDLLA micelles on lung cancer cells was assessed for their potential applications in cancer therapy.

2 EXPERIMENTAL

2.1 Materials

DL-lactide was synthesized by polycondensation of DL-lactic acid, followed by thermal composition and cyclization according to literature method.²⁶ Monohydroxyl terminated poly(2-ethyl-2-oxazoline) was prepared by ring-opening polymerization of 2-ethyl-2-oxazoline.²⁷ Tin(II) 2-ethylhexanoate ($\text{Sn}(\text{Oct})_2$), curcumin, acetonitrile and chlorobenzene were supplied by Sigma-Aldrich (Shanghai, China). Chlorobenzene and

acetonitrile were treated with calcium hydride for water removal. All other organic reagents were employed without further treatment.

2.2 Synthesis of PEOz-PDLLA copolymers

Monohydroxyl terminated PEOz-OH was first synthesized according to our previously reported work.²⁵ The M_n of obtained PEOz-OH was 2800 g/mol. PEOz-PDLLA block copolymers were synthesized in chlorobenzene according to the following procedure. Typically, PEOz-OH (1.0 g), DL-lactide (0.58 g), and stannous octoate (5 mg) were introduced in a flask, followed by addition of chlorobenzene (15 mL). Ring opening polymerization then occurred at 120 °C with inert gas protection. After 30 h reaction, the PEOz-PDLLA copolymer was obtained by filtration through silica gel, precipitation in cold diethyl ether, and vacuum drying in oven at 40°C up to constant weight.

2.3 Self-assembly of PEOz-PDLLA copolymers

Co-solvent method was employed to prepare self-assembled PEOz-PDLLA micelles. Typically, PEOz-PDLLA copolymer (20 mg) was introduced in chloroform (1 mL), and solubilized. The resulted copolymer solution was then dropped in ultrapure water (20 mL). Vigorous stirring was applied for 4 h so as to allow self-assembly of copolymer micelles and evaporation of the solvent. A micelles solution at 1.0 mg/mL was finally obtained by filtration via a 0.22 μm filter membrane.

2.4 Characterization

Proton nuclear magnetic resonance (^1H NMR) was performed using a Bruker Avance III instrument. 5 mg of sample were dissolved in 0.6 mL deuterated chloroform (CDCl_3). And the spectra were recorded at 500 MHz with tetramethylsilane as an internal reference.

Gel permeation chromatography (GPC) was carried out on a Shimadzu apparatus equipped with a Waters 410 refractometer. 10 mg of sample were dissolved in 1 mL tetrahydrofuran taken as mobile phase. Measurements were made at 25°C, and calculations were realized based on a calibration curve previously obtained using

polystyrene standards.

Transmission electron microscopy (TEM) was performed on JEM 1200EX microscope (JEOL, Japan). A micelle solution (5 μL) at 1.0 mg/mL was dropped onto a carbon coated copper grid, followed by negative staining with a phosphotungstic acid solution at 1.0 wt.%. The sample was air dried, and then examined by TEM at an acceleration voltage of 80 kV.

Dynamic light scattering (DLS) was carried out by using a Nano-ZS90 nanosizer (Malvern, UK). Micelle solutions at 1.0 mg/mL were filtered via a 0.45 μm PTFE microfilter before measurements made at room temperature. The scattering angle was fixed at 90°.

The critical micelle concentration (CMC) of PEOz-PDLLA copolymers was determined using fluorescence spectrophotometer (F-4600). Pyrene was taken as a fluorescent probe. First, 1 mL pyrene solution in benzene (2×10^{-5} M) was poured into a 10 mL flask, followed by solvent evaporation. Various volumes of micelle solution and ultrapure water were added to the flask to a total volume of 10 mL. The final concentration of micelles was in the range from 1.0×10^{-3} to 0.5 mg/mL, and that of pyrene was 2.0×10^{-6} M. After 24 h equilibrium at 25°C, the excitation spectra of the solutions were registered in the range from 350 to 450 nm at a wavelength of 334 nm. The intensity ratio at 375 and 395 nm was plotted vs copolymer concentration, and the CMC value was derived from the cross-over point of the two regression lines.

2.5 Biocompatibility studies

2.5.1 Hemolysis test

A micelle solution (10 mL) at 1.0 mg/mL was poured in a beaker which was previously silanized. The solution was heated at 37 °C for a period of 30 min. 0.2 mL rabbit blood diluted with acid-citrate-dextrose (ACD) at a dilution ratio of 9/1 was then added. The mixture was incubated at 37 °C for 30 min, and then centrifuged. The optical density (OD) of the supernatant was measured at 540 nm. Physiological saline was taken as negative control, and ultrapure water as positive control. The hemolysis

ratio (HR) was obtained using the following equation:

$$HR(\%) = \frac{OD_{test\ sample} - OD_{negative\ control}}{OD_{positive\ control} - OD_{negative\ control}} \times 100\% \quad (1)$$

2.5.2 Dynamic clotting time

The dynamic clotting time was determined according to the method previously reported in literature.²⁸ A micelle solution (25 µL) in 0.025 M calcium chloride (CaCl₂) was poured into a siliconized tube. After 5 min incubation at 37°C, ACD solution (200 µL) was introduced into the tube and mixed. At preset time points up to 140 min, distilled water (20 mL) was gently poured into the tube to rinse the watch-glass. Subsequently, the absorbance of the rinsing liquid was measured at 490 nm wavelength. Similar analyses were made on siliconized glass as negative control and ordinary glass as positive control. The clotting time of micelle samples was obtained from the OD value vs time plots. Experiments were repeated three times in each case.

2.5.3 MTT assay

MTT assay was employed to examine the cytotoxicity of copolymers, using L929 fibroblast cell line. Various micelle solutions at a concentration from 0.05 to 1.0 mg/mL with 10% calf serum were exposed to L929 cells in 96-well plates. At preset time intervals (24, 48 and 72 h), MTT (20 µL) at 5 mg/mL was added in the well, and incubated for 6 h. The medium was then taken out, followed by addition of 150 µL dimethyl sulfoxide (DMSO). The plates were shaken during 10 min. And the OD value was measured at 570 nm in a microplate reader. A phenol solution (100 µL) was taken as positive control, and a fresh medium (100 µL) as negative control. The relative growth rate (RGR) of cells was obtained according to the following equation:

$$RGR(\%) = \frac{OD_{test\ sample}}{OD_{negative\ control}} \times 100\% \quad (2)$$

2.6 Drug release studies

Curcumin was loaded in the core of micelles using a two-step procedure. Drug free micelles were first prepared as described in Section 2.3. 1 mg curcumin was dissolved in 1 mL methanol, and the solution was then introduced into 10 mL micelle

solution. Vigorous stirring was applied during 4 h to ensure efficient drug loading, followed by gentle stirring for 24 h to completely eliminate the solvent. The resulting curcumin-loaded micelle solution was centrifuged to remove unloaded drug, and filtered through 0.22 μm filter.

Curcumin release from PEOz-PDLLA micelles was studied under in vitro conditions according to literature method.^{29,30} A dialysis system was employed, which includes Float-A-Lyzer G2 dialysis devices (MWCO of 3500 Da), an oscillator and a thermostat. 1 mL curcumin loaded micellar solution was introduced in a dialysis device which was immersed in a centrifugation tube filled with 40 mL phosphate buffered saline (PBS). The tubes were fixed in an oscillator thermostated at 37°C. Drug release then proceeded under constant shaking. Sink conditions were ensured by regular renewal of the release medium. At each time point, a volume of 25 μL was taken out and equal volume of PBS was added. The collected samples were lyophilized, and dissolved in ethanol. The UV absorbance was measured to determine the drug concentration based on a previously established calibration curve. The drug loading content (LC) and loading efficiency (LE) were calculated from the following equations:

$$LC(\%) = \frac{\text{weight of loaded drug}}{\text{weight of drug loaded micelles}} \times 100\% \quad (3)$$

$$LE(\%) = \frac{\text{weight of loaded drug}}{\text{theoretical drug loading}} \times 100\% \quad (4)$$

2.7 In vitro antitumor activity

The anti-tumor activity of free curcumin and curcumin loaded micelles was determined by MTT assay using A549 lung cancer cell line. A549 cells were suspended in Dulbecco's Modified Eagle Medium (DMEM) which contains 10% fetal bovine serum (FBS), 100 U/mL penicillin and 100 $\mu\text{g/mL}$ streptomycin, and incubated at 37 °C during 24 h in a humidified environment with 5% carbon dioxide. MTT assay was then realized according to the experimental protocol described above.

3 Results

3.1 Characterization of PEOz-PDLLA copolymers

PEOz-PDLLA copolymers were prepared by ring-opening polymerization of DL-lactide using monohydroxy terminated PEOz-OH with M_n of 2800 as macro-initiator and $\text{Sn}(\text{Oct})_2$ as catalyst. The chemical composition of PEOz-PDLLA copolymers was determined by ^1H NMR, as shown in Fig. 1. Three main signals are detected for the PEOz block. Peak **a** at 1.12 ppm belongs to the methyl protons of ethyl side chain, peak **b** at 2.40 and 2.31 ppm to the methylene protons of ethyl side chain, and peak **c** at 3.46 ppm to the methylene protons of PEOz main chain, respectively. In the case of the PDLLA hydrophobic block, two signals are detected. Peak **d** at 5.17 ppm is attributed to the methine proton, and peak **e** at 1.59 ppm to the methyl protons of lactyl repeat units. The signals **d** and **a** are integrated using MestReNova software, and the integrations are used to calculate the LA/EOz molar ratio of PEOz-PDLLA copolymers. The degree of polymerization (DP) of both blocks and M_n of PEOz-PDLLA are then obtained according to the following equations :

$$\text{DP}_{\text{PEOz}} = M_{n\text{PEOz}}/99 \quad (5)$$

$$\text{DP}_{\text{PDLLA}} = \text{DP}_{\text{PEOz}} \times (\text{LA}/\text{EOz}) \quad (6)$$

$$M_n = M_{n\text{PEOz}} + \text{DP}_{\text{PDLLA}} \times 72 \quad (7)$$

where 99 designates the molar mass of 2-ethyl-2-oxazoline moieties, and 72 that of lactyl moieties.

Figure 1. ^1H NMR spectrum of PEOz-PDLLA copolymer in CDCl_3

Table 1 presents the characterization results of the three copolymers. The copolymers are abbreviated as EOZ_xDL_y for the sake of simplicity, with the subscripts x and y representing the DP of PEOz and PDLLA blocks, respectively. The DP_{PEOz} is 28 for the three copolymers, and DP_{PDLLA} is 13, 29 and 38 for $\text{EOZ}_{28}\text{DL}_{13}$, $\text{EOZ}_{28}\text{DL}_{29}$ and $\text{EOZ}_{28}\text{DL}_{38}$, respectively. The M_{nNMR} derived from NMR spectra varies from 3700 to 5500 g/mol. GPC was also used to characterize the copolymers as it allows to determine not only the molar mass, but also the molar mass distribution. As shown in Fig. 2, the GPC chromatograms shift to shorter retention time with increasing PDLLA block length, in agreement with higher molar mass. M_{nGPC} values are slightly different from M_{nNMR} ones because the former are derived from the hydrodynamic volume of polymers in solution compared to standards (Table 1). The dispersity (D) is in the range from 1.15 to 1.39, indicating that the copolymers have a narrow distribution of molar masses.

Figure 2. The curves of GPC of PEOz-PDLLA copolymers

The Griffin's method is widely used to determine the hydrophilic-lipophilic balance (HLB) of amphiphilic polymers. High HLB values imply strong hydrophilicity, and *vice versa*. In Table 1 are shown HLB values of the three copolymers which are in the range from 10.2 to 15.1. Copolymers with longer PDLLA block length have lower HLB, in agreement with lower hydrophilicity.

Table 1 Structural characterization of PEOz-PDLLA diblock copolymers

Copolymer	M _n PEOz	LA/EOz	DP _{PEOz}	DP _{PDLLA}	M _n NMR	M _n GPC	Đ	HLB
EOz ₂₈ DL ₁₃	2800	0.45 (0.6) ^{a)}	28	13	3700	3500	1.15	15.1
EOz ₂₈ DL ₂₉	2800	1.05 (1.2)	28	29	4900	5300	1.34	11.4
EOz ₂₈ DL ₃₈	2800	1.35 (1.6)	28	38	5500	5800	1.39	10.2

^{a)} Values in parentheses designate the LA/EOz molar ratios in the feed.

3.2 Self-assembly of PEOz-PDLLA diblock copolymers

Amphiphilic PEOz-PDLLA diblock copolymers can spontaneously self-assemble in aqueous medium, leading to formation of nano-sized micelles with a hydrophilic PEOz corona and a hydrophobic PDLLA core. TEM was used to observe the morphology of self-assembled aggregates as shown in Fig. 3A-C. All copolymer micelles exhibit a spherical shape and are uniformly distributed. The diameter of micelles is in the range from 20 to 30 nm as estimated from TEM images. No worm-like micelles were observed, in contrast to PEOz-PLLA copolymers.²⁵ In fact, polymer chain structure regularity strongly affects the self-assembled morphology of micelles. PDLLA blocks have a disordered chain structure with randomly distributed L- and D-lactidyl units, and PEOz-PDLLA copolymers seem to be more inclined to form spherical micelles as compared to PEOz-PLLA copolymers with rigid stereoregular PLLA blocks.

Figure 3. TEM images and DLS graphs of EOZ₂₈DL₁₃ (A, D), EOZ₂₈DL₂₉ (B, E), and EOZ₂₈DL₃₈ (C, F) copolymer micelles.

The average micelle diameter and polydispersity index (PDI) were determined DLS measurements (Fig. 3). A symmetric size distribution is detected for all copolymer micelles, as shown in Fig. 3D-F. Table 2 summarizes the micelle diameter and PDI data of the three copolymers. The diameter of micelles slightly increases with the increase of the PDLLA block length, from 104 nm for EOZ₂₈DL₁₃ to 131 and 136 nm for EOZ₂₈DL₂₉ and EOZ₂₈DL₃₈, respectively. This finding could be attributed to the increasing hydrophobic block length which could attract more copolymer chains in micelles, as reported in literature.²⁵ A slight increase of micelle size is observed after encapsulation of curcumin. The micelle diameter slightly increases to 131, 135 and 145 nm for EOZ₂₈DL₁₃, EOZ₂₈DL₂₉ and EOZ₂₈DL₃₈, respectively. The PDI values of micelle sizes are below 0.30 in all cases, in agreement with narrow size distribution. It is noteworthy that the diameter values derived from DLS are much larger than those from TEM due to the dehydration or shrinkage of micelles during air drying before TEM observation. Zhao et al. obtained a smaller micelle diameter of 41-43 nm for PEOZ-PDLLA copolymer with Mn of 6514 for PEOZ and 8200 for PDLLA,²⁴ which could be assigned to the more compact micelle core due to longer PDLLA block length.

The CMC is one of the key parameters of micelles as it allows to assess their stability *in vivo* after dilution caused by intravenous injection. As shown in Table 2, the CMC value obtained from fluorescence spectroscopy is highly dependent on the PDLLA block length or the HLB of copolymers. The longer the PDLLA block, the lower the HLB, and the smaller the CMC value. This finding is attributed to the fact

that copolymers with longer hydrophobic segments self-assemble more easily in aqueous medium, leading to more stable micelle structures.

Table 2. Self-assembly and drug loading properties of PEOz-PDLLA micelles

Sample	Diameter (nm)	PDI	CMC (mg/mL)	LC (%)	LE (%)
EOz ₂₈ DL ₁₃	104	0.29	0.0065	-	-
EOz ₂₈ DL ₂₉	131	0.26	0.0043	-	-
EOz ₂₈ DL ₃₈	136	0.22	0.0039	-	-
EOz ₂₈ DL ₁₃ -Cur	131	0.22	-	7.0	75.0
EOz ₂₈ DL ₂₉ -Cur	135	0.18	-	7.3	79.3
EOz ₂₈ DL ₃₈ -Cur	145	0.13	-	7.6	82.5

3.4 Biocompatibility studies

3.4.1 Hemolysis test

As potential drug carrier for intravenous application, hemolysis test is of major importance as it indicates the interaction of biomaterials and red blood cells (RBC). The hemolytic ratio (HR) reflects the dissociation level of hemoglobin after in vitro co-culture of materials with RBC. In Table 3 are summarized the OD and HR values of PEOz-PDLLA micelles, together with the OD values of both positive and negative controls. The HR value of EOz₂₈DL₁₃, EOz₂₈DL₂₉ and EOz₂₈DL₃₈ micelles is 3.4%, 3.8% and 3.5%, respectively. Therefore, the hemolytic properties of PEOz-PDLLA copolymers are acceptable for medical and pharmaceutical uses as the HR value is lower than 5%, the threshold defined by ISO 10993.

Table 3 Hemolytic properties of PEOz-PDLLA micelles

Copolymer	OD value	Hemolytic ratio (%)
Negative control	0.028±0.006	-
Positive control	0.795±0.032	-
EOZ ₂₈ DL ₁₃	0.054±0.006	3.4±0.8
EOZ ₂₈ DL ₂₉	0.057±0.004	3.8±0.5
EOZ ₂₈ DL ₃₈	0.055±0.006	3.5±0.8

3.4.2 Dynamic clotting time

Fresh blood in vitro will initiate endogenous coagulation due to foreign bodies activating endogenous coagulation factors. The dynamic coagulation behavior of PEOz-PDLLA micelles and controls was evaluated from time dependent changes of absorbance, as shown in Fig. 4. 0.1 and 0.01 was defined as the initial clotting time (ICT) and the complete clotting time (CCT), respectively. The blood in contact with positive control was the first to undergo endogenous coagulation. The ICT and CCT of positive control were 23 min and 60 min, respectively. EOZ₂₈DL₁₃, EOZ₂₈DL₂₉ and EOZ₂₈DL₃₈ micelles showed the same trend as the negative control. The OD values gradually decreased over time. The ICT of all PEOz-PDLLA micelles was about 80 min and that of the negative control was 90 min. Furthermore, the CCT of PEOz-PDLLA micelles and the negative control were almost the same (above 140 min), thus suggesting that PEOz-PDLLA micelles present outstanding anticoagulant properties.

Figure 4. OD value changes of PEOz-PDLLA micelles as a function of time in comparison with the positive and negative controls.

3.4.3 MTT assay

Within a certain cell concentration range, the amount of formazan crystals formed by MTT is directly proportional to cell viability. Fig. 5 presents L929 cell viability data after 24, 48 and 72 h co-culture with PEOz-PDLLA micelles at various concentrations from 0.5 to 5.0 mg/mL. The positive control showed very low RGR values which decreased from 24% at 24 h to 12.4% at 72 h. However, the RGR values are over 95% for all micelles at different concentrations throughout the 72 h period, thus showing a cytocompatibility very close to the negative control (100%). Therefore, both hemocompatibility and cytocompatibility data showed that PEOz-PDLLA micelles are biocompatible for potential applications in drug delivery according to the ISO 10993.

Figure 5. RGR of L929 cells after 24 (A), 48 (B) and 72 h (C) co-culture with PEOz-PDLLA micelles.

3.3 In vitro drug release

Due to its excellent anti-tumor activity and unique physico-chemical properties, curcumin was selected as a model of hydrophobic anti-tumor drugs. The nano-drug delivery system containing curcumin was prepared in two steps.³¹ Blank micelles were first obtained by using co-solvent evaporation method, and a curcumin solution in methanol was then added into the micelle solution. Drug loaded nano-micelles were obtained under vigorous stirring to remove the solvent.

The LC and LE data of curcumin loaded micelles are summarized in Table 2. EOz₂₈DL₁₃ presents an LE of 75.0% and an LC of 7.0%. Higher LE and LC values are obtained for EOz₂₈DL₂₉ and EOz₂₈DL₃₈. EOz₂₈DL₃₈ presents the highest LE and LC values of 82.5% and 7.6%, respectively. The increase of LE and LC with increasing PDLLA block length could be attributed to the larger core volume of micelles with longer PDLLA blocks.

Dialysis method was used to determine the drug release behavior of curcumin-loaded micelles at different pH values. Three representative pH values were selected to simulate the environments of micelles entering the body: pH 7.4 when the micelles were intravenously injected into the blood environment, pH 6.5 when the micelles were endocytosed by tumor cells, and pH 5.0 when the micelles were transferred into the

endo/lysosome mimetic environment. As shown in Fig. 6, two distinct release phases were observed in the release curves of drug loaded PEOz-PDLLA micelles. An initial fast release of curcumin was detected in the first 12 h, which could be attributed to the fact that drug molecules are partly located at the interface of the core-corona structure.³² Subsequently, a stable and sustained release behavior was detected up to 144 h. At pH 7.4, the drug release in first 12 h was about 36%, 31%, and 31% for EOz₂₈DL₁₃, EOz₂₈DL₂₉ and EOz₂₈DL₃₈, respectively. At pH 5.0, the initial drug release at 12 h increased to 56%, 53% and 45% for EOz₂₈DL₁₃, EOz₂₈DL₂₉ and EOz₂₈DL₃₈, respectively. Intermediate rates were obtained at pH 6.5. Beyond 12 h, the three drug loaded micelle systems showed slower release rates. At 144 h, the final cumulative release of curcumin at pH 7.4, 6.5 and 5.0 was 59%, 81% and 93% for EOz₂₈DL₁₃, 52%, 72% and 85% for EOz₂₈DL₂₉, and 48%, 61% and 73% for EOz₂₈DL₃₈, respectively.

The drug release behaviors of three micelle systems at the same pH (pH 5) are comparatively shown in Fig. 6D. In the first 12 h, the cumulative release curves of EOz₂₈DL₁₃ and EOz₂₈DL₂₉ almost overlap, while EOz₂₈DL₃₈ shows lower release rate. In the later stage, drug release continues to increase in all three systems, but at a slower rate. At pH 5.0, the cumulative drug release was 93%, 85% and 73% for EOz₂₈DL₁₃, EOz₂₈DL₂₉ and EOz₂₈DL₃₈, respectively. Therefore, curcumin release from PEOz-PDLLA micelles is strongly affected by the environmental conditions and the composition or PDLLA block length of copolymers.

The release data of curcumin from PEOz-PDLLA micelles clearly illustrate the responsiveness of micelles to pH stimulation. Drug diffusion and carrier degradation are the two main mechanisms that affect drug release behaviors. Jelonek et al. studied paclitaxel release from PLLA-PEG and PDLLA-PEG micelles at different pH values, and found that the degradation of micelles strongly affects drug release rate.³³ In our previous study on PLGA-PEG copolymer micelles, faster degradation was observed for micelles with shorter PLGA blocks as compared to micelles with longer PLGA blocks.³⁴ Thus, the various drug release rates obtained for EOz₂₈DL₁₃, EOz₂₈DL₂₉ and

EOZ₂₈DL₃₈ micelles can be directly related to the degradation rate of copolymers. The lower the pH, the shorter the PDLLA block length, the faster the degradation of micelles and the faster the release of curcumin.

Figure 6. *In vitro* release profiles of curcumin from EOZ₂₈DL₁₃ (A), EOZ₂₈DL₂₉ (B), EOZ₂₈DL₃₈ (C) copolymer micelles in PBS at pH = 7.4, 6.5 and 5.0 at 37 °C; and comparison of the release curves of the three copolymers at pH 5.0 (D). All data are represented as the mean ± SD (n = 3).

Zhao et al. studied the release of doxorubicin from PEOZ-PDLLA micelles at different pH values.²⁴ The acidic environment promoted the release of doxorubicin because of higher water-solubility of doxorubicin and accelerated degradation of the hydrophobic PDLLA block. Almost total drug release was achieved within 24 h. In our previous work, a series of PEOZ-PLLA micelles were evaluated for controlled release of paclitaxel which is one of the most widely studied and most efficacious anti-tumor drugs. Within a 30-day period, copolymers with shorter PLLA blocks exhibit faster drug release than those with longer PLLA blocks. Faster drug release is also obtained at

acidic pH than at pH 7.4. Nevertheless, the highest release ratio was only 37.6% which was obtained for EOZ₁₈L₅ micelles after 30 days release in PBS at pH 5.0. Therefore, PEOZ-PDLLA micelles present much faster drug release than PEOZ-PLLA ones, which is consistent with the faster degradation rate of PDLLA compared to PLLA.²⁵

3.5 In vitro antitumor studies

Lung cancer is one of the most deadly malignant tumors for both women and men, making up nearly 25% of all cancer deaths. The inhibitory effect of curcumin loaded micelles on the proliferation of A549 lung cancer cells is studied to evaluate their potential for lung tumor treatment. As shown in Fig. 7A, no cytotoxicity was detected for PEOZ-PDLLA micelles (0.25-250 µg) after 72 h co-culture with A549 cells. The relative proliferation rate of A549 cells in micelle solutions was similar to that in fresh medium. This result is consistent with the good cytocompatibility of PEOZ-PDLLA micelles described above.

Fig. 7B presents the inhibitory effect of free curcumin and curcumin loaded micelles on the proliferation of A549 cells. The concentration of free drug is the same as that in the micellar system, taking into account the drug loading content of micelles. For low concentrations of curcumin from 0.025 to 2.5 µg/mL, cell proliferation was significantly inhibited and showed a dose-dependent decrease with increasing concentration. In contrast, little RGR changes were detected in the drug concentration range of 2.5-25 µg/mL. In the whole drug concentration range, the anti-tumor effect of curcumin loaded micelles was comparable to that of free curcumin.

Figure 7. RGR data of A549 cells after 72 h culture with blank micelles (A), free curcumin and curcumin loaded micelles (B) in comparison with the control (DMEM).

Conclusion

Amphiphilic PEOz-PDLLA diblock copolymers with different hydrophobic block lengths were prepared by ring opening polymerization of DL-lactide in the presence of hydroxyl terminated PEOz-OH, and characterized by using NMR and GPC analyses. PEOz-PDLLA copolymers are susceptible to self-assemble in water, yielding uniformly distributed spherical micelles. The size of micelles is well below 200 nm, which should allow applications as drug carrier by intravenous injection. The increase in the hydrophobic block length leads to a decrease in the CMC of copolymers, but to a increases of the LE and LC of micelles. Curcumin loaded PEOz-PDLLA micelles exhibit biphasic drug release profile characterized by an initial burst and subsequent slower release. The release behavior is greatly affected by pH of the medium and the PDLLA block length. Lower pH or shorter block length leads to faster drug release. Both blood and cell compatibility experiments demonstrated the excellent biocompatibility of PEOz-PDLLA block copolymers. Finally the inhibitory effect of curcumin loaded micelles on the proliferation of A549 cells was evidenced, thus showing that PEOz-PDLLA copolymer micelles could be a promising nano-carrier of lipophilic antitumor drugs.

Acknowledgments

The work was financially supported by the Talent Fund of Shandong Collaborative Innovation Center of Eco-Chemical Engineering (XTCXQN20), the Shandong Provincial Natural Science Foundation (ZR2020QH271, ZR2020MH324), and the Postdoctoral Applied Research Project of Qingdao Municipality (04030431060088).

References

- [1] Siegel R, Miller K, Jemal A. Cancer statistics, 2020. *CA-Cancer J Clin.* 2020; 70(1): 7-30.
<https://doi.org/10.3322/caac.21590>
- [2] Sung H, Ferlay J, Siegel RL, Laversanne M, Soerjomataram I, Jemal A, Bray F. Global cancer statistics 2020: GLOBOCAN estimates of incidence and mortality worldwide for 36 cancers in 185 countries. *CA-Cancer J Clin.* 2021;0:1-41.
<https://doi.org/10.3322/caac.21660>
- [3] Zheng R, Sun XK, Zhang SW, Zeng HM, Zou XN, Chen R, Gu XY, Wei WW, He J. Report of cancer epidemiology in China, 2015. *China Cancer.* 2019; 41(1): 19-28.
<https://pubmed.ncbi.nlm.nih.gov/30678413/>
- [4] Aquib M, Juthi AZ, Farooq MA, Ali MG, Janabi A, Bavi S, Banerjee P, Bhosale R, Bavi R, Wang B. Advances in local and systemic drug delivery systems for post-surgical cancer treatment. *J Mater Chem B.* 2020; 8: 8507-8518.
<https://doi.org/10.1039/d0tb00987c>
- [5] Christiana CD, Martino D, Donato M, Pier B, Robertac E, Cirot S, Mariac L, Maurizioc G, Giuseppea M. Chemotherapy-induced cardiotoxicity: New insights into mechanisms, monitoring, and prevention. *J Cardiovasc Med.* 2018; 19(7): 315-323.
<https://doi.org/10.2459/jcm.0000000000000667>
- [6] Hanovich E, Aamis T, Ong M, Stewart D. Rechallenge strategy in cancer therapy. *Oncology.* 2020; 98: 669-679.
<https://doi.org/10.1159/000507816>
- [7] Wan D, Li C, Pan J. Polymeric micelles with reduction-responsive function for targeted cancer chemotherapy. *ACS Appl Bio Mater.* 2020; 3(2): 1139-1146.
<https://pubs.acs.org/doi/10.1021/acsabm.9b01070>

- [8] Jin YS, Liang XL, An YK, Dai ZF. Microwave-triggered smart drug release from liposomes co-encapsulating doxorubicin and salt for local combined hyperthermia and chemotherapy of cancer. *Bioconjugate Chem.* 2016; 27(12): 2931-2942.
<https://doi.org/10.1021/acs.bioconjchem.6b00603>
- [9] Wang Q, Zhang P, Xu JZ, Xia B, Tian L, Chen JQ, Li J, Fu F, Shen QM, Lu XM, Huang W, Fan Q. NIR-absorbing dye functionalized supramolecular vesicles for chemo-photothermal synergistic therapy. *ACS Appl Bio Mater.* 2018; 1(1): 70-78.
<https://doi.org/10.1021/acsabm.8b00014>
- [10] Lu N, Tian Y, Tian W, Huang P, Liu Y, Tang YX, Wang CY, Wang SJ, Su YY, Zhang YS, Pan J, Teng ZG, Lu GM. Smart cancer cell targeting imaging and drug delivery system by systematically engineering periodic mesoporous organosilica nanoparticles. *ACS Appl Mater Inter.* 2016; 8(5): 2985-2993.
<https://doi.org/10.1021/acsami.5b09585>
- [11] Hasenstein JR, Shin HC, Kasmerchak K, Buehler D, Kwon GS, Kozak KR. Antitumor activity of Triolimus: a novel multidrug-loaded micelle containing Paclitaxel, Rapamycin, and 17-AAG. *Mol Cancer Ther.* 2012; 11(10): 2233-2242.
<https://doi.org/10.1158/1535-7163.mct-11-0987>
- [12] Fletcher NL, Kempe K, Thurecht KJ. Next generation polymeric nanomedicines for oncology: Perspectives and future directions. *Macromol Rapid Comm.* 2020; 41(18): e2000319.
<https://doi.org/10.1002/marc.202000319>
- [13] Khanna C, Rosenberg M, Vail D. A review of paclitaxel and novel formulations including those suitable for use in dogs. *J Vet Intern Med.* 2015; 29(4): 1006-1012.
<https://doi.org/10.1111/jvim.12596>
- [14] Fan W, Zhang LY, Li YW, Wu HX. Recent progress of crosslinking strategies for polymeric micelles with enhanced drug delivery in cancer therapy. *Curr Med Chem.*

2019; 26(13): 2356-2376.

<https://doi.org/10.2174/0929867324666171121102255>

- [15] Varela-Moreira A, Shi Y, Fens M, Lammers T, Hennink W, Schiffelers RM. Clinical application of polymeric micelles for the treatment of cancer. *Materials Chemistry Frontiers*. 2017; 1: 1485-1501.

<https://doi.org/10.1039/C6QM00289G>

- [16] Bandyopadhyay D. Farmer to pharmacist: Curcumin as an anti-invasive and antimetastatic agent for the treatment of cancer. *Front Chem*. 2014; 2: 113.

<https://doi.org/10.3389/fchem.2014.00113>

- [17] Mehta HJ, Patel V, Sadikot RT. Curcumin and lung cancer-a review target. *Target Oncol*. 2014; 9: 295-310.

<https://doi.org/10.1007/s11523-014-0321-1>

- [18] Mirzaie Z, Barati M, Tokmedash MA. Anticancer drug delivery systems based on curcumin nanostructures: A review. *Pharm Chem J*. 2020; 54: 353-360

<https://doi.org/10.1007/s11094-020-02203-0>

- [19] Najafi M, Mortezaee K, Rahimifard M, Frahood B, Haghi-Aminjan H. The role of curcumin/curcuminoids during gastric cancer chemotherapy: A systematic review of non-clinical study. *Life Sci*. 2020; 257(15): 118051.

<https://doi.org/10.1016/j.lfs.2020.118051>

- [20] Ashrafizadeh M, Zarrabi A, Hashemi F, Moghadam ER, Hashemi F, Entezari M, Hushmandi K, Mohammadinejad R, Najafi M. Curcumin in cancer therapy: A novel adjunct for combination chemotherapy with paclitaxel and alleviation of its adverse effects. *Life Sci*. 2020; 256(1): 117984.

<https://doi.org/10.1016/j.lfs.2020.117984>

- [21] Viegas T, Bentley MD, Harris JM, Fang ZH, Yoon KS, Dizman B, Weimer R, Mero A, Pasut G, Veronese FM. Polyoxazoline: Chemistry, properties, and

applications in drug delivery. *Bioconjug Chem.* 2011; 22(5): 976-986.

<https://doi.org/10.1021/bc200049d>

- [22] Bauer M, Lautenschlaeger C, Kempe K, Tauhardt L, Schubert US, Fischer D. Poly(2-ethyl-2-oxazoline) as alternative for the stealth polymer poly(ethylene glycol): Comparison of in vitro cytotoxicity and hemocompatibility. *Macromol Biosci.* 2012; 12(7): 986–998.

<https://doi.org/10.1002/mabi.201200017>

- [23] Mero A, Pasut G, Via LD, Fijten M, Schubert US, Hoogenboom R, Veronese FM. Synthesis and characterization of poly(2-ethyl-2-oxazoline)-conjugates with proteins and drugs: Suitable alternatives to PEG-conjugates. *J Control Release* 2005; 125(2): 87–95.

<https://doi.org/10.1016/j.jconrel.2007.10.010>

- [24] Zao Y, Zhou Y, Wang DS, Gao YJ, Li JW, Ma SJ, Zhao L, Zhang C, Liu Y, Li XR. pH-responsive polymeric micelles based on poly(2-ethyl-2-oxazoline) - poly(D,L-lactide) for tumor-targeting and controlled delivery of doxorubicin and P-glycoprotein inhibitor. *Acta Biomater.* 2015; 17: 182-192.

<https://doi.org/10.1016/j.actbio.2015.01.010>

- [25] Su F, Yun P, Li CL, Li RY, Xi LS, Wang YD, Chen YS, Li SM. Novel self-assembled micelles of amphiphilic poly (2-ethyl-2-oxazoline)-poly (L-lactide) diblock copolymers for sustained drug delivery. *Colloid Surface A.* 2019; 566: 120-127.

<https://doi.org/10.1016/j.colsurfa.2019.01.015>

- [26] Zhang HP, Ruan JM, Zhou ZC, Li YJ. Preparation of monomer of degradable biomaterial poly(L-lactide). *J Cent South Univ Technol.* 2005;12: 246-250.

<https://doi.org/10.1007/s11771-005-0136-4>

- [27] Lee SC, Chang Y, Yoon JS, Kim C, Kwon IC, Kim Y, Jeong SY. Phase-transition

characteristics of amphiphilic poly(2-ethyl-2-oxazoline)/poly(ϵ -caprolactone) block copolymers in aqueous solutions. *Macromolecules*. 1999;32: 1847-1852.

<https://doi.org/10.1021/ma981664k>

- [28] Wang YD, Xi LS, Zhang BG, Zhu QZ, Su F, Jelonek K, Orchel A, Kasperczk J, Li SM. Bioresorbable hydrogels prepared by photo-initiated crosslinking of diacrylated PTMC-PEG-PTMC triblock copolymers as potential carrier of antitumor drugs. *Saudi Pharm J*. 2020; 28(3): 290-299.

<https://doi.org/10.1016/j.jsps.2020.01.008>

- [29] Lu AJ, Petit E, Jelonek K, Orchel A, Kasperczyk J, Wang YD, Su F, Li SM. Self-assembled micelles prepared from bio-based hydroxypropyl methyl cellulose and polylactide amphiphilic block copolymers for anti-tumor drug release. *Int J Biol Macromol*. 2020; 154: 39-47.

<https://doi.org/10.1016/j.ijbiomac.2020.03.094>

- [30] Lu AJ, Petit E, Wang YD, Su F, Li SM. Synthesis and self-assembly of hydroxypropyl methyl cellulose-block-poly(ϵ -caprolactone) copolymers as nanocarriers of lipophilic drugs. *ACS Appl Nano Mater*. 2020; 3(5): 4367-4375.

<https://doi.org/10.1021/acsanm.0c00498>

- [31] Mansouri K, Rasoulpoor S, Daneshkhah A, Abolfathi S, Salari N, Mohammadi M, Rasoulpoor S, Shabani S. Clinical effects of curcumin in enhancing cancer therapy: A systematic review. *BMC Cancer*. 2020; 20: 791.

<https://doi.org/10.1186/s12885-020-07256-8>

- [32] Tyrrell Z, Shen Y, Radosz M. Fabrication of micellar nanoparticles for drug delivery through the self-assembly of block copolymers. *Prog Polym Sci*. 2010; 35(9): 1128-1143.

<https://doi.org/10.1016/j.progpolymsci.2010.06.003>

- [33] Jelonek K, Li SM, Kasperczyk J, Wu XH, Orchel A. Effect of polymer degradation

on prolonged release of paclitaxel from filomicelles of polylactide/poly(ethylene glycol) block copolymers. Mater Sci Eng C. 2017; 75: 918-925.

<https://doi.org/10.1016/j.msec.2017.03.006>

[34] Su F, Li CL, Li RY, Yun P, Wang YD, Xi LS, Chen YS, Li SM. Effects of chemical composition on the in vitro degradation of micelles prepared from poly(D,L-lactide-co-glycolide)-poly(ethylene glycol) block copolymers. Polym Degrad Stab. 2018; 158: 202-211.

<https://doi.org/10.1016/j.polymdegradstab.2018.11.007>