Postmodulation of the Metal–Organic Framework Precursor toward the Vacancy-Rich Cu_xO Transducer for Sensitivity Boost: Synthesis, Catalysis, and H₂O₂ Sensing

Serge Cosnier, Junji Li, Wen-Li Xin, Yu-Xuan Dai, Guofang Shu, Xue-Ji Zhang, Robert Marks, Dan Shan

► To cite this version:

Serge Cosnier, Junji Li, Wen-Li Xin, Yu-Xuan Dai, Guofang Shu, et al.. Postmodulation of the Metal–Organic Framework Precursor toward the Vacancy-Rich Cu_xO Transducer for Sensitivity Boost: Synthesis, Catalysis, and H₂O₂ Sensing. *Analytical Chemistry*, 2021, 93 (32), pp.11066-11071. 10.1021/acs.analchem.1c02183 . hal-03376495

HAL Id: hal-03376495

<https://hal.science/hal-03376495>

Submitted on 13 Oct 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

This document is confidential and is proprietary to the American Chemical Society and its authors. Do not copy or disclose without written permission. If you have received this item in error, notify the sender and delete all copies.

**Modulation of Crystalline Metal-organic Framework
Precursor towards Carbon-based CuxO Electro-catalyst for
Boosting Sensitive Hydrogen Peroxide Detection: Synthesis,
Catalysis and Sensing Application**

Journal:	<i>Analytical Chemistry</i>
Manuscript ID	ac-2021-021836
Manuscript Type:	Technical Note
Date Submitted by the Author:	24-May-2021
Complete List of Authors:	Li, Junji; Nanjing University of Science and Technology, School of Environmental & Biological Engineering Xin, Wen-Li; Nanjing University of Science and Technology Dai, Yu-Xuan; Nanjing University of Science and Technology, School of Environmental & Biological Engineering Shu, Guofang; Southeast University Zhongda Hospital Zhang, Xueji; Nanjing University of Science and Technology, School of Environmental & Biological Engineering Marks, Robert; Ben-Gurion University of the Negev, Department of Biotechnology Engineering Cosnier, Serge; Universite Grenoble Alpes, Département de Chimie Moléculaire UMR CNRS 5250 Shan, Dan; Nanjing University of Science and Technology, School of Environmental and Biological Engineering

SCHOLARONE™
Manuscripts

**Modulation of Crystalline Metal-organic Framework
Precursor towards Carbon-based Cu_xO Electro-catalyst for
Boosting Sensitive Hydrogen Peroxide Detection: Synthesis,
Catalysis and Sensing Application**

Junji Li^a, Wen-Li Xin^a, Yu-Xuan Dai^a, Guofang Shu^b, Xue-Ji Zhang^a, Robert S. Marks^c,
Serge Cosnier^d, Dan Shan^{a*}

^a School of Environmental and Biological Engineering, Nanjing University of Science and
Technology, Nanjing 210094, China

^b Department of Clinical Laboratory, Zhongda Hospital, Southeast University School of
Medicine, Nanjing, 210009, Jiangsu, China

^c Department of Biotechnology Engineering, Ben-Gurion University of the Negev, Beer-Sheva,
Israel

^d University of Grenoble Alpes-CNRS, DCM UMR 5250, F-38000 Grenoble, France

*** Corresponding to:**

Prof. Dan Shan

School of Environmental and Biological Engineering,

Nanjing University of Science and Technology,

Nanjing, Jiangsu, 210094, China.

Tel. +86(25) 84303107;

E-mail: danshan@njust.edu.cn

Abstract:

Metal-organic frameworks (MOFs) act as versatile coordinators for the subsequent synthesis of high-performance electrochemical catalysts by providing dispersed metal-ion distribution, initial coordination condition, and modular dopant atom ratios, etc. In this work, a copper-based crystalline MOF *trans*-[Cu(NO₃)₂(Him)₄] was synthesized as a novel precursor of a carbon-based electrochemical valence-alternating NC@Cu_xO catalyst. Through simple temperature modulation of the pyrolysis procedure, the gradual transformation towards highly-active catalytic nanocomposite was characterized and investigated to ascertain the signal enhancing mechanism during H₂O₂ detection. Owing to its proprietary structure and ensuing electrochemical reduction activity, a proof-of-principle sensor using NC@Cu_xO as transducer was able to provide an amplified sensitivity of 2330 μA mM⁻¹ cm⁻². In addition, its facile one-vessel preparation and the intrinsic non-enzymatic nature suggests a wide range of potential applications in medical settings.

Keywords:

Metal-organic framework derivate, Non-enzyme catalyst, Electrochemical biosensor, Fenton-like signal amplification, One-pot synthesis

1
2
3
4 47 The electrochemically active material, or rather the transducer, plays an
5
6 48 imperative role in the construction of an electrochemical biosensor ¹. Its
7
8
9 49 intrinsic properties, such as active center density, electron transfer ability, as
10
11
12 50 well as, internal structure and external morphology, set the fundamental
13
14
15 51 performance of the derived sensing systems or devices ²⁻⁴. Use of
16
17 52 metal-organic frameworks (MOFs) as self-sacrificed precursors ^{5, 6} provides
18
19
20 53 invaluable properties, such as: 1) tunable initial coordination environment and
21
22
23 54 heteroatom doping, that can be easily achieved through the selection of
24
25
26 55 multitudinous ligand molecules; 2) atomic migration process can be accessed
27
28
29 56 and manually paused to obtain a series of products with diverse composite
30
31
32 57 configurations, including metal centers at different valence states or more
33
34
35 58 precisely the nuanced electronic regulation states, or carbon substrates with
36
37
38 59 various interconnecting degrees or doping ratios, and active catalysis clusters
39
40
41 60 with distinguished diameters; 3) porous characteristics can be inherited, thus
42
43
44 61 allowing high-throughput mass diffusion and interfacial contact ^{7, 8}. Already,
45
46
47 62 some state-of-the-art single atom catalysts (SACs) with satisfactory
48
49
50 63 performance have been synthesized using MOFs as starting templates ^{9, 10}.

51
52
53 64 Copper-based MOFs or derived nanomaterials have drawn conspicuous
54
55
56 65 attention due to their specific enzyme-like activities, reasonable cost efficiency
57
58
59 66 and robust stability ¹¹⁻¹³. According to the aforementioned advantages, these
60
61
62 67 copper-based enzyme mimics have been well accepted as signal transducers
63
64
65 68 to construct sensitive biosensor systems ¹⁴. Copper species, no matter in
66

forms of elementary clusters ^{15, 16}, compound nanoparticles ¹⁷ or even secondary coordination units ¹⁸, show prominent redox activity, with or without, extra potential energy from the external circuit. In some latest articles, more complex copper-based transducer materials with excellent and versatile capabilities were synthesized from MOFs-contained composite precursors, e.g. with several 2D materials like graphene, C₃N₄ or MXene ¹⁹. All these treasures figure out an efficient clue of massively converting homogeneous structural units inside the MOF crystal into highly disperse nano-catalysts decorated upon a simultaneously generated substrate, and meanwhile investigate the transiting procedure of some certain catalysis activity to the other ²⁰.

In the present communication, we designed the synthesis of a crystalline MOF-derived Cu_xO composite catalyst, serving as an electrochemical peroxidase mimic. Inspired by the coordination structure of copper catalysts, both the ligand atoms and the central metal valence state of the catalysis unit were modulated simply using a short period of differential thermal treatment. Thanks to the uniform texture of the crystalline precursor, the generation process of a well-tuned transducer material was monitored and sought. An electrochemical Fenton-like signal enhancing mechanism was herein discussed, in view of the derived prototype biosensor and its corresponding interfacial reactions (Fig. 1A). We expect that this novel and concise transducer material will provide proprietary engineering insights in providing

improved biosensor devices suitable for commercialization^{21, 22}.

Fig. 1. Stepwise modulation from crystalline MOF precursor to active electrochemical transducer. (A) Schematic overview of the preparation and signal amplification mechanism of the composite transducer material NC@Cu_xO. (B) Crystal structure diagram of the MOF precursor *trans*-[Cu(NO₃)₂(Him)₄]. (C) Three comparative routes to prepare MOF precursors with distinguished preferential crystallographic orientation and lattice shrinkage or bulge. (D) FT-IR spectra of the obtained crystalline precursors with arrows and blue dashed lines or region indicating critical changes of the transmittance peak. (E) SEM image of the board-like precursor crystals. (F and G) TEM images of the layered transducer material NC@Cu_xO after a short period of pyrolysis under air atmosphere.

To ascertain that copper atoms were highly dispersed at the initial precursor stage, powder X-ray diffraction (PXRD) was performed immediately after lyophilization (Supplementary methods). All of the main peaks have been indexed as a well-defined orthorhombic phase of *trans*-[Cu(NO₃)₂(Him)₄]

crystal (PDF 27-1527)²³, indicating that the copper ions were strictly hexa-coordinated by four nitrogen atoms (from imidazole) and two oxygen atoms (belonging to the nitrate ions) (Fig. 1B). The specific crystal herein was obtained according to the following procedures: N,N'-carbonyldiimidazole (CDI) underwent decomposition in some polar solvents like ethanol, thus, releasing free imidazole (Him) molecules as well as di-esters of carbonic acid or imidazole-N-carboxylic esters, as shown in *eq. 1*. Whereas, in the presence of lattice water, CDI was possible to be hydrolyzed into carbonate ions (*eq. 2*) which would further react with copper ions and generate stable basic modalities²⁴.

In order to know the priority of the aforementioned possible reaction routes, two contrast synthesis strategies were introduced. In detail, anhydrous copper nitrate with CDI and $\text{CuNO}_3 \cdot 3\text{H}_2\text{O}$ with imidazole were each examined under the same ethanol-solvent condition and compared in terms of their respective diffraction peaks which almost kept the same with a slight peak shift of about 10^{-2} degrees, implying lattice shrinkage and bulge of these copper-imidazole frameworks due to the differences in accessory products (Fig. 1C and Fig. S1)²⁵. Interestingly, the preferential crystallographic orientations echoed by the diffraction peak intensities, however, were significantly different between the

two groups. From the Fourier transform infrared spectrometer (FT-IR) spectra, it is clear that these Cu-MOFs acquired through different formulas maintained perfectly identical chemical bonds. The transmittance peak variations from the ligand monomers suggested probable reaction routes and the inner connections of MOFs, detailed as follows: 1) the vanishing of carbonyl stretching vibration at $\sim 1735\text{ cm}^{-1}$, as well as the strong broad band from 2200 to 3100 cm^{-1} , respectively indicated the decomposition of CDI, and the following coordination reaction of derived imidazole with copper ion which accompanied the collapse of $\text{N-H}\cdots\text{N}$ hydrogen bonds; and 2) the strong vibration peak at 1394 cm^{-1} that can be assigned to the amide C–N of CDI red-shifted to 1340 cm^{-1} as a result of the formation of ester C–O bonds in all MOF samples (Fig. 1D and Fig. S2)²⁶. These results imply that regardless of the presence of lattice water, CDI reacts with ethanol thereby generating ester species.

The bluish violet Cu-MOF powder exhibited tabular hexagon-like morphology with a thickness of hundreds of nanometers in scanning electron microscope (SEM) images (Fig. 1E). After the pyrolysis process under air atmosphere, the resulting $\text{NC@Cu}_x\text{O}$ catalyst, showed an obviously decreased plane size down to 10-nm scale, according to the transmission electron microscope (TEM) results (Fig. 1F and 1G). Furthermore, the absence of aggregated nanoparticles suggested highly dispersed catalytic sites. To further understand the transformation from a Cu-MOF precursor to a

1
2
3
4 148 copper-based catalyst and its accompanying H_2O_2 reduction properties,
5
6
7 149 thermogravimetric-differential scanning calorimetry (TG-DSC) analysis was
8
9
10 150 conducted at a $5\text{ }^\circ\text{C min}^{-1}$ heating rate (Fig. 2B). A sharp weight loss was
11
12 151 noticed from 200 to $240\text{ }^\circ\text{C}$, accompanied with a clear exothermic peak at
13
14 152 $226\text{ }^\circ\text{C}$. Thereafter, three representative temperature points (200, 300 and
15
16 153 $400\text{ }^\circ\text{C}$) were set with their corresponding products named $\text{NC@Cu}_x\text{O-L}$,
17
18
19 154 $\text{NC@Cu}_x\text{O}$ and $\text{NC@Cu}_x\text{O-H}$ respectively.
20
21

22 155 When the Cu-MOF precursor was heated at $200\text{ }^\circ\text{C}$ for 2 hours, the
23
24 156 obtained $\text{NC@Cu}_x\text{O-L}$ still preserved the typical lattice characteristics of
25
26
27 157 *trans*- $[\text{Cu}(\text{NO}_3)_2(\text{Him})_4]$, and its weight loss can be attributed to the desorption
28
29 158 of solvent molecules and the decomposition of thermolabile esters. With a
30
31
32 159 further rise in temperature, broad peaks of graphite and copper oxide
33
34 160 appeared in the $\text{NC@Cu}_x\text{O}$ PXRD spectrum (Fig. 2A). By substituting the
35
36
37 161 measured value of full width at half maximum (FWHM) into the Scherrer
38
39 162 equation, the crystallite size of the newly formed copper oxide was calculated
40
41
42 163 to be several nanometers, which was in accordance with the lack of gathered
43
44 164 clusters in the TEM image ²⁷. *Via* calcination at $400\text{ }^\circ\text{C}$, the derived
45
46
47 165 $\text{NC@Cu}_x\text{O-H}$ showed striking peaks identical to that of CuO , owing to the
48
49 166 deep substitution of oxygen for the initial coordinated nitrogen through atomic
50
51
52
53 167 transfer.
54
55
56
57
58
59
60

Fig. 2. Temperature modulation of the valence state of the central metal as well as the neighboring ligand atoms and vacancies. (A) XRD spectra of the pyrolyzed samples under different heat-treatment temperature. (B) TG-DSC curves of the self-sacrifice MOF precursor in air atmosphere with the heating rate of 5 °C min⁻¹. High-resolution XPS spectra of Cu 2p (C) and O 1s (D) orbitals of the under-heated NC@Cu_xO-L, experimental NC@Cu_xO and over-heated NC@Cu_xO-H samples.

A mutually corroborating result was obtained by investigating the chemical state alternations of atoms. In both NC@Cu_xO-L and NC@Cu_xO samples, the high-resolution X-ray photoelectron spectroscopy (XPS) spectra of Cu 2p orbitals displayed relatively weaker satellite peaks and slightly lower binding

energies of both the $2p_{1/2}$ and $2p_{3/2}$ orbitals than that of NC@Cu_xO-H (Fig. 2C). Due to the existence of CuO nanocrystalline in NC@Cu_xO, we surmised that these features ought to be attributed to the abundant intermediate low-valent Cu(I) rather than Cu(II) of coordinated state or compound state²⁸. Taking O 1s spectra into consideration, on the other dimension, the gradual shift of the predominant sub-peaks from 532.2 to 529.7 eV can help determine the exact components of the aforementioned NC@Cu_xO catalysts. In detail, NC@Cu_xO-L displayed Cu-MOF-like characteristics with respect to crystal structure, and the chemical state of organic oxygen assigned as incompletely decomposed esters. NC@Cu_xO-H, at the other extreme, exhibited canonical CuO properties with a standard XRD pattern and typical XPS spectrum features, such as the intensive satellite peaks of Cu 2p and the nearly complete conversion to lattice oxygen which belongs to the metal-oxide compounds (Fig. 2D).

The aforementioned under- or over- heating treatments exhibit variance in the resulting functional ingredient of the composite catalyst NC@Cu_xO. On one hand, the crystalline framework collapsed and recombined as a N-doped carbon substrate. The copper atoms, on the other hand, were gradually aggregated and oxidized into nanoscale CuO nanoparticles, while preserving an overall amorphous state with abundant oxygen vacancies (Fig. 2D)²⁹. Therefore, the uniformly dispersed catalytic centers of reductive copper oxide in NC@Cu_xO determined their high reaction activity towards oxidizing

substances. Simultaneously, the internal structural porosity is substantially retained which guarantees sufficient mass transfer during the catalyzing procedures (Fig. S3 and S4). The Cu-MOF precursor's periodic atom distributions and definite melting point enable the investigation of some critical catalyst-evolving processes, such as metal migration and oxygen transfer, by simply modulating temperature.

Fig. 3. Electrochemical catalysis behavior investigation of the transducer material to support sensitive sensing of H₂O₂ concentration. **(A)** Electrochemical redox characteristics of the MOF-residual dominant (NC@Cu_xO-L, top), O-vacancy abundant (NC@Cu_xO, middle) and deeply oxidized (NC@Cu_xO-H, bottom) samples as transducers in the absence and presence of 0.05 mM H₂O₂. **(B)** Cyclic voltammograms of NC@Cu_xO electrode at different scan rates from 10 to 250 mV s⁻¹ in condition of saturated nitrogen without H₂O₂. **(C)** Cyclic voltammogram of NC@Cu_xO electrode in response to H₂O₂ concentrations of 0 to 0.5 mM with an insert exhibiting the linear fitting of the reductive peak-current density values. **(D)** Chronoamperometric responses of NC@Cu_xO to stepwise addition of H₂O₂ at -0.5 V (vs. SCE). **(E)** Selectivity test of the biosensor against some common interferences in body fluid, including 1 mM Na⁺, K⁺, ascorbic acid, uric acid and glucose.

Based on the characteristics of the NC@Cu_xO catalyst species, their respective electrochemical behaviors were further examined using cyclic

1
2
3
4 221 voltammetry (CV) (Fig. 3A). In the absence of H_2O_2 , the lower-heated sample
5
6 222 showed inconspicuous redox peaks, implying an inert electron transfer ability
7
8
9 223 of the Cu-N coordinate-bond dominated MOF material. In contrast, the 400 °C
10
11 224 pyrolyzed product exhibited both obvious redox peaks ($\text{Cu}^{\text{I}}/\text{Cu}^{\text{II}}$, $E_p = -0.34$ and
12
13
14 225 -0.15 V) due to the formation of conductive carbon substrates. In regard to the
15
16
17 226 NC@Cu_xO, its undiscovered reduction peak at this particular potential window
18
19 227 indicated that copper existed in a low valence state in Cu_xO and the
20
21
22 228 electrochemically oxidized copper ions would then be released into the liquid
23
24
25 229 phase, resulting in an irreversible procedure. When the solution contained
26
27 230 0.05 mM H_2O_2 , a strong reduction peak appeared around -0.45 V, significantly
28
29
30 231 deviating from the CV curve without adding H_2O_2 . It is worth noting that the
31
32
33 232 oxidization peak, in the meanwhile, became quite indistinct especially when
34
35 233 the H_2O_2 concentration increased. This result implied that reductive copper in
36
37
38 234 NC@Cu_xO preferred to react with the oxidizing substances derived from H_2O_2
39
40 235 decomposition, prior to being electrochemically oxidized at the anode (*eq. 3*).

41
42
43 236 The emphasis in sensitive H_2O_2 detection lays on enhanced signal
44
45
46 237 transduction or an amplified feedback. Therefore, the catalysis mechanism
47
48 238 and its signal conversion process was studied first. The NC@Cu_xO modified
49
50
51 239 glassy carbon electrode (GCE) was tested by cyclic voltammetry at different
52
53
54 240 scan rates in 0.1 M PBS and 0.3 M KCl solution (Fig. 3B). With increasing
55
56 241 scan rate from 10 to 250 mV s^{-1} , both of the anodic and cathodic peak
57
58
59 242 currents were measured as linear with the square root of the scan rate (Fig.

S5), indicating characteristic diffusion-controlled electrochemical redox behaviors³⁰ from which we inferred a Fenton-induced enhancing mechanism:

The highly dispersed Cu(I) catalysis centers of Cu_xO efficiently accelerated the decomposition of H₂O₂, while releasing an equivalent amount of ·OH radicals. Thereafter, increased reductive copper sites would be oxidized through rapid radical reactions. At the reduction potential, the newly generated Cu(II) would then get reduced by capturing the electrons from the outer circuit. More importantly, the electrochemical procedures at the electrodes were shown to be rapid, which meant this redox cycle (*eq.3-5*) would continuously proceed until the diffusion limit and simultaneously provide amplified current response³¹. In addition, this catalytic process relied on not only the valence state of copper centers, but also the structural configuration of ligand atoms and defects, which can be supposed from the poor activity of both the NC@Cu_xO-L and NC@Cu_xO-H samples.

By adding H₂O₂ solutions of differing concentrations (Fig. 3C), the current intensity of the reduction peak at -0.45 V was identified as a linear coefficient of the concentration, with a corresponding linear equation: $j \text{ (mA cm}^{-2}\text{)} =$

265 $-2.33C$ (mM) - 0.05 ($R^2=0.9998$), ranging from 10 μ M to 0.5 mM. The limit of
266 detection for the NC@Cu_xO sensor, (LOD= $3\sigma/S_d$, where σ represents the
267 standard deviation of the current density value measured in blank solution, and S_d
268 stands for the slope of linear regression calibration line), reached 6.67 nM. Fig. 3D
269 shows the amperometric response towards concentrated H₂O₂ solutions. The
270 cathodic current rapidly achieved steady states and increased in pace with the
271 addition of H₂O₂. The selectivity and stability of this proof-of-principle
272 biosensor were also evaluated as these two important parameters could
273 reflect whether an artificial catalyst could mimic or even surpass natural
274 enzymes in practical use. From Fig. 3E, we can conclude that NC@Cu_xO has
275 good selectivity towards H₂O₂. The i-t curve in Fig. S6 exhibited the stability of
276 this electrochemical sensor for long-term continuous detection. After dropping
277 in 1 mM H₂O₂ solution, the output current could keep steady for more than 1 h,
278 indicating that the NC@Cu_xO nanocomposite did not leach out from the
279 electrode during multiple cycles of electrochemical redox process, while
280 maintaining high catalytic activity. By simply modulating the thermal redox
281 condition of a well-characterized crystalline MOF precursor, both the chemical
282 valence and coordination environment of the central metal were adjusted to
283 render a transducer enhanced signal feedback. In comparison with previous
284 studies which introduced other functional materials or not, this NC@Cu_xO
285 electrode offers a highly competitive sensitivity, as well as other decent
286 performances (Table 1).

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

Table 1. Comparison of copper-based electrochemical H₂O₂ transducer materials on catalysis mechanism and sensitivity performance.

Transducer material	Active-center type	Redox potential (V)	Additional materials	Sensitivity (μA mM ⁻¹ cm ⁻²)	LOD (μM)	References
CuO nanoflowers	monoclinic CuO	-0.4 (vs. Ag/AgCl)	n.a.	956.69	0.85	32
Cu ₂ O nanoparticles	~100 nm size with (111) facets	-0.42 (vs. Ag/AgCl)	n.a.	28.0	0.2	33
3DIO Au/NiO@CuO	Ni ³⁺ species	0.5 (vs. Ag/AgCl)	CuO skeleton & AuNPs	650.2	0.0037	34
CuNPs@Y-1,4-NDC-MOF/ERGO	CuNPs supported by ERGO	-0.2 (vs. SCE)	Y-1,4-NDC-MOF & ERGO	8.8	0.43	35
Cu ₂ O-rGO-P	cubic Cu ₂ O	-0.4 (vs. Ag/AgCl)	rGO paper	77*	3.78	36
NCNT MOF CoCu	Co(0) & Cu(0)	0.5 (vs. Ag/AgCl)	Co(0)	639.5	0.206	37
Cu-Mo ₂ C/C	Synergic Mo ₂ C with Cu(0)	-0.4 (vs. SCE)	hexagonal β-Mo ₂ C	392.7	0.04	38
NC@Cu _x O	Amorphous Cu _x O with oxygen vacancies	-0.45 (vs. SCE)	n.a.	2330	0.00667	This work

* estimated from the offered linear regression curve.

We presented, herein, a sensitive H₂O₂ sensor constructed with a tailored amorphous Cu_xO composite catalyst. The corresponding mechanism of enhanced signal transduction were stepwise investigated from the precursor conformation, to its catalytic evolution, up to a final amplified electron cascades. With the initial copper-nitrogen square domains converting into low-valent amorphous copper oxide catalytic centers, the resulting current remarkably increased due to its synergistic enhancement, contributed by both rapid radical and electrochemical reactions. Moreover, the structural property of specific neighboring ligand-atom configuration was proven to be a factor as predominant as the valence state of central metals. From the perspective of material, catalysis and the final sensing application, the way to design and

modulate a proper copper-based transducer was comprehensively explored. We envision that our work would hold the prospect for accurate bio-analyte quantitation and promote the mainstreaming of precision diagnosis and medicine.

Acknowledgements

The authors greatly acknowledge the financial support from National Natural Science Foundation of China (Grant No. 62001224), Natural Science Foundation of Jiangsu Province (Grant No. BK20190457), “Overseas Academic Partnership Program” of Nanjing University of Technology (2019), and Sino-French international research network “New nanostructured materials and biomaterials for renewable electrical energy sources”

1. Zhao, S.; Zang, G.; Zhang, Y.; Liu, H.; Wang, N.; Cai, S.; Durkan, C.; Xie, G.; Wang, G., Recent advances of electrochemical sensors for detecting and monitoring ROS/RNS. *Biosens. Bioelectron.* **2021**, *179*, 113052.
2. Sehit, E.; Altintas, Z., Significance of nanomaterials in electrochemical glucose sensors: An updated review (2016-2020). *Biosens. Bioelectron.* **2020**, *159*, 112165.
3. Lu, S.-M.; Peng, Y.-Y.; Ying, Y.-L.; Long, Y.-T., Electrochemical Sensing at a Confined Space. *Anal. Chem.* **2020**, *92* (8), 5621-5644.
4. Lawal, A. T., Graphene-based nano composites and their applications. A review. *Biosens. Bioelectron.* **2019**, *141*, 111384.
5. Ji, D.; Zhou, H.; Tong, Y.; Wang, J.; Zhu, M.; Chen, T.; Yuan, A., Facile

- 323 fabrication of MOF-derived octahedral CuO wrapped 3D graphene network as binder-free
324 anode for high performance lithium-ion batteries. *Chem. Eng. J.* **2017**, *313*, 1623-1632.
- 325 6. Wang, H.-F.; Chen, L.; Pang, H.; Kaskel, S.; Xu, Q., MOF-derived electrocatalysts
326 for oxygen reduction, oxygen evolution and hydrogen evolution reactions. *Chem. Soc. Rev.*
327 **2020**, *49*(5), 1414-1448.
- 328 7. Bavykina, A.; Kolobov, N.; Khan, I. S.; Bau, J. A.; Ramirez, A.; Gascon, J.,
329 Metal-Organic Frameworks in Heterogeneous Catalysis: Recent Progress, New Trends, and
330 Future Perspectives. *Chem. Rev.* **2020**, *120*(16), 8468-8535.
- 331 8. Yang, Q.; Xu, Q.; Jiang, H.-L., Metal-organic frameworks meet metal nanoparticles:
332 synergistic effect for enhanced catalysis. *Chem. Soc. Rev.* **2017**, *46*(15), 4774-4808.
- 333 9. Sun, T.; Xu, L.; Wang, D.; Li, Y., Metal organic frameworks derived single atom
334 catalysts for electrocatalytic energy conversion. *Nano Res.* **2019**, *12*(9), 2067-2080.
- 335 10. Ji, S.; Chen, Y.; Wang, X.; Zhang, Z.; Wang, D.; Li, Y., Chemical Synthesis of
336 Single Atomic Site Catalysts. *Chem. Rev.* **2020**, *120*(21), 11900-11955.
- 337 11. Bao, J.; Yang, G.; Yoneyama, Y.; Tsubaki, N., Significant Advances in C1 Catalysis:
338 Highly Efficient Catalysts and Catalytic Reactions. *ACS Catalysis* **2019**, *9*(4), 3026-3053.
- 339 12. Wang, R.; Dong, X. Y.; Du, J.; Zhao, J. Y.; Zang, S. Q., MOF-Derived Bifunctional
340 Cu₃P Nanoparticles Coated by a N,P-Codoped Carbon Shell for Hydrogen Evolution and
341 Oxygen Reduction. *Adv. Mater.* **2018**, *30*(6), 29266417.
- 342 13. Abdel-Mageed, A. M.; Rungtaweeworant, B.; Parlinska-Wojtan, M.; Pei, X.; Yaghi,
343 O. M.; Behm, R. J., Highly Active and Stable Single-Atom Cu Catalysts Supported by a
344 Metal-Organic Framework. *J. Am. Chem. Soc.* **2019**, *141*(13), 5201-5210.

- 1
2
3
4 345 14. Xiangyu, L.; Shanshan, G.; Han, L.; Luodan, Y.; Yunhu, H.; Piao, Z.; Weichao,
5
6 346 B.; Heliang, Y.; Yu, C.; Jianlin, S., Bioinspired Copper Single-Atom Catalysts for Tumor
7
8 347 Parallel Catalytic Therapy. *Adv. Mater.* **2020**, *32* (36), 2002246.
9
10
11 348 15. Subarna, M.; Dipankar, B.; Sikta, C.; Sarita, K.; Amitava, P., Copper Nanocluster
12
13 349 (Cu₂₃ NC)-Based Biomimetic System with Peroxidase Activity. *ACS Sustainable Chem. Eng.*
14
15 350 **2020**, *8* (49), 18335-18344.
16
17
18 351 16. Mei-Chen, P.; Yan-Mei, L.; Ya-Qin, C.; Ruo, Y.; Ying, Z., In Situ Controllable
19
20 352 Generation of Copper Nanoclusters Confined in a Poly-L-Cysteine Porous Film with Enhanced
21
22 353 Electrochemiluminescence for Alkaline Phosphatase Detection. *Anal. Chem.* **2020**, *92* (19),
23
24 354 13581-13587.
25
26
27 355 17. Wang, W.; Zhang, Y.; Zhang, J.; Li, G.; Leng, D.; Gao, Y.; Gao, J.; Lu, H.; Li,
28
29 356 X., Metal-organic framework-derived Cu₂O-CuO octahedrons for sensitive and selective
30
31 357 detection of ppb-level NO₂ at room temperature. *Sens. Actuators, B* **2021**, *328*, 129045.
32
33
34 358 18. Wang, B.; Luo, Y.; Gao, L.; Liu, B.; Duan, G., High-performance field-effect
35
36 359 transistor glucose biosensors based on bimetallic Ni/Cu metal-organic frameworks. *Biosens.*
37
38 360 *Bioelectron.* **2021**, *171*, 112736.
39
40
41 361 19. Wang, D.; Zhang, D.; Yang, Y.; Mi, Q.; Zhang, J.; Yu, L., Multifunctional
42
43 362 Latex/Polytetrafluoroethylene-Based Triboelectric Nanogenerator for Self-Powered Organ-like
44
45 363 MXene/Metal-Organic Framework-Derived CuO Nanohybrid Ammonia Sensor. *ACS Nano*
46
47 364 **2021**, *15* (2), 2911-2919.
48
49
50
51 365 20. Chen, Y.-Z.; Zhang, R.; Jiao, L.; Jiang, H.-L., Metal-organic framework-derived porous
52
53 366 materials for catalysis. *Coord. Chem. Rev.* **2018**, *362*, 1-23.
54
55
56
57
58
59
60

- 1
2
3
4 367 21. Goud, K. Y.; Reddy, K. K.; Khorshed, A.; Kumar, V. S.; Mishra, R. K.; Oraby, M.;
5
6 368 Ibrahim, A. H.; Kim, H.; Gobi, K. V., Electrochemical diagnostics of infectious viral diseases:
7
8
9 369 Trends and challenges. *Biosens. Bioelectron.* **2021**, *180*, 113112.
10
11 370 22. Cesewski, E.; Johnson, B. N., Electrochemical biosensors for pathogen detection.
12
13 371 *Biosens. Bioelectron.* **2020**, *159*, 112214.
14
15
16 372 23. Stamatatos, T. C.; Perlepes, S. P.; Raptopoulou, C. P.; Terzis, A.; Patrickios, C. S.;
17
18 373 Tasiopoulos, A. J.; Boudalis, A. K., Alcoholysis/hydrolysis of 1,1'-carbonyldiimidazole as a
19
20 374 means of preparing unprecedented, imidazole-containing one-dimensional coordination
21
22 375 polymers of copper(II). *Dalton Trans.* **2009**, (17), 3354-3362.
23
24
25 376 24. Staab, H. A., New Methods of Preparative Organic Chemistry IV. Syntheses Using
26
27 377 Heterocyclic Amides (Azolides). *Angew. Chem., Int. Ed.* **1962**, *1*(7), 351-367.
28
29
30 378 25. Yao, M.-S.; Zheng, J.-J.; Wu, A.-Q.; Xu, G.; Nagarkar, S. S.; Zhang, G.;
31
32 379 Tsujimoto, M.; Sakaki, S.; Horike, S.; Otake, K.; Kitagawa, S., A Dual-Ligand Porous
33
34 380 Coordination Polymer Chemiresistor with Modulated Conductivity and Porosity. *Angew.*
35
36 381 *Chem., Int. Ed.* **2020**, *59*(1), 172-176.
37
38
39 382 26. Hadrich, A.; Dulong, V.; Rihouey, C.; Labat, B.; Picton, L.; Cerf, D. L., Biomimetic
40
41 383 hydrogel by enzymatic crosslinking of pullulan grafted with ferulic acid. *Carbohydr. Polym.*
42
43 384 **2020**, *250*, 116967.
44
45
46 385 27. Abdullah, F. H.; Abu Bakar, N. H. H.; Abu Bakar, M., Comparative study of chemically
47
48 386 synthesized and low temperature bio-inspired Musa acuminata peel extract mediated zinc
49
50 387 oxide nanoparticles for enhanced visible-photocatalytic degradation of organic contaminants
51
52 388 in wastewater treatment. *J. Hazard. Mater.* **2021**, *406*, 124779.
53
54
55
56
57
58
59
60

- 389 28. Yang, P.-P.; Zhang, X.-L.; Gao, F.-Y.; Zheng, Y.-R.; Niu, Z.-Z.; Yu, X.; Liu, R.;
390 Wu, Z.-Z.; Qin, S.; Chi, L.-P.; Duan, Y.; Ma, T.; Zheng, X.-S.; Zhu, J.-F.; Wang,
391 H.-J.; Gao, M.-R.; Yu, S.-H., Protecting Copper Oxidation State via Intermediate
392 Confinement for Selective CO₂ Electroreduction to C₂+ Fuels. *J. Am. Chem. Soc.* **2020**, *142*
393 (13), 6400-6408.
- 394 29. Xiao, Z.; Huang, Y.-C.; Dong, C.-L.; Xie, C.; Liu, Z.; Du, S.; Chen, W.; Yan, D.;
395 Tao, L.; Shu, Z.; Zhang, G.; Duan, H.; Wang, Y.; Zou, Y.; Chen, R.; Wang, S.,
396 Operando Identification of the Dynamic Behavior of Oxygen Vacancy-Rich Co₃O₄ for Oxygen
397 Evolution Reaction. *J. Am. Chem. Soc.* **2020**, *142* (28), 12087-12095.
- 398 30. Fang, Y.; Luan, D.; Chen, Y.; Gao, S.; Lou, X. W., Rationally Designed
399 Three-Layered Cu₂S@Carbon@MoS₂ Hierarchical Nanoboxes for Efficient Sodium Storage.
400 *Angew. Chem., Int. Ed.* **2020**, *59* (18), 7178-7183.
- 401 31. Savéant, J.-M., Molecular Catalysis of Electrochemical Reactions. Cyclic Voltammetry of
402 Systems Approaching Reversibility. *ACS Catalysis* **2018**, *8* (8), 7608-7611.
- 403 32. Ni, Y.; Sun, Z.; Zeng, Z.; Liu, F.; Qin, J., Hydrothermal fabrication of hierarchical
404 CuO nanoflowers for dual-function amperometric sensing of hydrogen peroxide and glucose.
405 *New J. Chem.* **2019**, *43* (47), 18629-18636.
- 406 33. Juang, F.-R.; Chern, W.-C., Controlled Synthesis of Cuprous Oxide Nanoparticles with
407 Different Morphologies for Nonenzymatic Hydrogen Peroxide Sensing Applications. *J.*
408 *Electrochem. Soc.* **2019**, *166* (4), B200-B204.
- 409 34. Zhou, X.; Xu, L.; Lv, J.; Yang, S.; Zhu, S.; Chen, X.; Sun, X.; Dong, B.; Bai,
410 X.; Lu, G.; Song, H., Au anchored three-dimensional macroporous NiO@CuO inverse opals

411 for in-situ sensing of hydrogen peroxide secretion from living cells. *Sens. Actuators, B* **2019**,
412 297, 126729.

413 35. Li, C.; Wu, R.; Zou, J.; Zhang, T.; Zhang, S.; Zhang, Z.; Hu, X.; Yan, Y.; Ling,
414 X., MNPs@anionic MOFs/ERGO with the size selectivity for the electrochemical
415 determination of H₂O₂ released from living cells. *Biosens. Bioelectron.* **2018**, 116, 81-88.

416 36. Cheng, C.; Zhang, C.; Gao, X.; Zhuang, Z.; Du, C.; Chen, W., 3D Network and 2D
417 Paper of Reduced Graphene Oxide/Cu₂O Composite for Electrochemical Sensing of
418 Hydrogen Peroxide. *Anal. Chem.* **2018**, 90 (3), 1983-1991.

419 37. Kim, S. E.; Muthurasu, A., Highly Oriented Nitrogen-doped Carbon Nanotube Integrated
420 Bimetallic Cobalt Copper Organic Framework for Non-enzymatic Electrochemical Glucose
421 and Hydrogen Peroxide Sensor. *Electroanalysis* **2021**, 33, 1-14.

422 38. Li, B.; Liu, L.-H.; Zhang, X.-F.; Gao, Y.; Deng, Z.-P.; Huo, L.-H.; Gao, S.,
423 Echinus-like Cu-Mo₂C/C yolk-shell composites for ultrasensitive detection of hydrogen
424 peroxide. *Electrochim. Acta* **2021**, 373, 137908.

425